

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization

International Bureau

(43) International Publication Date
07 May 2020 (07.05.2020)



(10) International Publication Number
WO 2020/092920 A1

(51) International Patent Classification:

C09K 8/80 (2006.01) C09K 8/84 (2006.01)

(21) International Application Number:

PCT/US2019/059417

(22) International Filing Date:

01 November 2019 (01.11.2019)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

62/755,357 02 November 2018 (02.11.2018) US

(71) Applicant: **NISSAN CHEMICAL AMERICA CORPORATION** [US/US]; 10333 Richmond Avenue, Suite 1100, Houston, TX 77042 (US).

(72) Inventors: **SOUTHWELL, John, Edmond**; 735 Pleasant Avenue, Glen Ellyn, IL 60137 (US). **AHMAD, Yusra, Khan**; 1606 Falcon Ridge Boulevard, Friendswood, TX 77546 (US). **HOLCOMB, David**; 6760 West Stony Quail Way, Florence, AZ 85132 (US).

(74) Agent: **HOOVER, Kenley, K.**; Nixon & Vanderhye P.C., 901 North Glebe Road, 11th Floor, Arlington, VA 22203-1808 (US).

(81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JO, JP, KE, KG, KH, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

— of inventorship (Rule 4.17(iv))

Published:

— with international search report (Art. 21(3))

(54) Title: ENHANCED OIL RECOVERY USING TREATMENT FLUIDS COMPRISING COLLOIDAL SILICA WITH A PROP-PANT

(57) Abstract: A method of increasing production from a hydrocarbon containing formation by adding a proppant to the formation, wherein a treatment fluid comprising a colloidal silica nanoparticle is added to the formation before, during or after the time the proppant is added to the formation is described and claimed.



WO 2020/092920 A1

ENHANCED OIL RECOVERY USING TREATMENT FLUIDS COMPRISING COLLOIDAL SILICA WITH A PROPPANT

5

Field of the Invention

The present invention relates to improved oil recovery methods using known proppants in combination with treatment fluids comprising colloidal silica.

Background of the Invention

10

A **proppant** is a solid material, typically sand, treated sand or man-made ceramic materials, designed to keep an induced hydraulic fracture open, during or following a fracturing treatment. It is added to a *fracking fluid* which may vary in composition depending on the type of fracturing used, and can be gel, foam or slickwater-based. In addition, there may be unconventional fracking fluids. Fluids make tradeoffs in such material properties as viscosity, where more viscous fluids can carry more concentrated proppant; the energy or pressure demands to maintain a certain flux pump rate (flow velocity) that will conduct the proppant appropriately; pH, various rheological factors, among others. In addition, fluids may be used in low-volume well stimulation of high-permeability sandstone wells (20k to 80k gallons per well) to the high-volume operations such as shale gas and tight gas that use millions of gallons of water per well.

15

Although hydraulic fracturing was first performed in 1947 (in Kansas, using sand from the Arkansas river), wide-spread experimentation didn't occur until the Barnett Shale play in the 80s, and usage has exploded in the first decade of this century.

20

Initially, proppant was simply sand, but over time other materials have been incorporated. There are resin-coated sands, ceramic-coated sands, and now we have proppant composed of sintered (powdered) bauxite – and ceramic materials made from it.

25

Although sand is a common proppant, untreated sand is prone to significant fines generation; fines generation is often measured in wt% of initial feed. A commercial newsletter from Momentive cites untreated sand fines production to be 23.9% compared with 8.2% for lightweight ceramic and 0.5% for their product. One way to maintain an ideal mesh size (i.e. permeability) while having sufficient strength is to choose proppants of sufficient strength; sand

might be coated with resin, to form CRCS (Curable Resin Coated Sand) or PRCS (Pre-Cured Resin Coated Sands).

U.S. Patent No. 10,113,406B1, “Pulsed Hydraulic Fracturing with NanoSilica Carrier Fluid”, **issued Oct. 30, 2018**, to Saudi Arabian Oil Company of Dhahran, Saudia Arabia. The invention described and claimed herein relates to fracturing a reservoir includes providing a pad
5 fluid to the reservoir via a wellbore in a well to create fractures in the reservoir, providing a fracturing fluid to the fractures via the wellbore, providing a nanosilica carrier fluid to the fractures via the wellbore, activating the nanosilica particles with an activator to yield a nanosilica gel, and shutting in the wellbore at a wellbore pressure, thereby allowing the
10 nanosilica gel to form proppant pillars in the fractures. The nanosilica carrier fluid includes nanosilica particles. The nanosilica carrier fluid is provided to the fractures and it comprises pulsing quantities of the nanosilica carrier fluid into a continuous flow of the fracturing fluid or alternately pulsing quantities of the nanosilica carrier fluid and the fracturing fluid. An elapsed time between pulsing the quantities of the nanosilica carrier fluid is between 2 seconds and 10
15 minutes.

U.S. Patent No. 9,512,352 B2, “Well Treatment Fluids and Methods Utilizing Nano-Particles”, issued **Dec. 6, 2016** and is assigned to Halliburton Energy Services, Inc. of Houston, Texas. Well treatment fluids and methods that utilize nano-particles are described and claimed. Exemplary nano-particles are selected from the group consisting of particulate nano-silica, nano-
20 alumina, nano-zinc oxide, nano-boron, nano-iron oxide, and combinations thereof. Embodiments also relate to methods of cementing that include the use of nano-particles. An exemplary method of cementing comprises introducing a cement composition into a subterranean formation, wherein the cement composition comprises cement, water and a particulate nano-silica. Embodiments also relate to use of nano-particles in drilling fluids, completion fluids, simulation
25 fluids, and well clean-up fluids.

U.S. Patent No. 9,951,267, “Infused and Coated Proppant Containing Chemical Treatment Agents and Methods of Using Same”, **issued April 24, 2018**, to Carbo Ceramics Inc. of Houston, Texas, This patent claims a proppant composition for use in hydraulic fracturing, the composition comprising: a plurality of particulates; a non-degradable coating; and at least
30 one particulate of the plurality of particulates comprising a degradable shell encapsulating at least a portion of the non-degradable coating, and a chemical treatment agent, the at least one

particulate having a long term permeability measured in accordance with ISO 13503-5 at 7,500 psi of at least about 10 D; wherein the particulate is a porous particulate; and wherein the at least one chemical treatment agent separates from the at least one particulate when located inside a fracture of a subterranean formation after a period of time.

5 **US Patent No. 9,234,127**, “Angular Abrasive Proppant, Process for the Preparation Thereof and Process for Hydraulic Fracturing of Oil and Gas Wells, issued on January 12, 2016 to Mineracao Curbimba Ltda of Brazil. This invention is an angular abrasive proppant comprising angular sintered particles of a material selected from bauxite, clay-minerals and mixtures thereof, with particle sizes varying from 30 mesh to 150 mesh. A process for the
10 production of an angular abrasive proppant comprising sintered particles of a material selected from bauxite, clay-minerals, and mixtures thereof comprises the steps of drying, grinding, pelletizing and sintering a bauxite starting material, grinding the sintered pellets, and sizing said particles to a particle size varying from 35 to 150 mesh is also described. A hydraulic fracturing process uses as proppant the angular abrasive proppant as described above.

15 **US Patent No. 7,954,548**, “Proppant for Hydraulic Fracturing of Oil and Gas Wells”. issued on June 7, 2011 to Mineracao Curimbaba Ltda. of Brazil. This patent describes and claims a proppant for the hydraulic fracturing oil or gas wells, which consists of a mixture of from 10 to 95% by weight of a spherical proppant and from 5 to 90% by weight of an angular material, the percentages being based on the total weight of the mixture. The proppant obtained
20 according to the present invention is useful for eliminating or decreasing the “flow-back” phenomenon in operations in oil or gas wells.

US 7,482,310 B1, “Method of Fracturing Subterranean Formations Utilizing Emulsions Comprising Acrylamide Copolymers, issued on **Jan. 27, 2009** to Kroof Chemical Company, Inc. and Superior Well Services, Inc., both of Pennsylvania. A method of treating a subterranean
25 formation penetrated by a well bore is described and claimed. This method includes the steps of(a) preparing a fracturing fluid containing a mixture resulting from:(I) providing a water-in-oil emulsion composition that includes:(i) 5% to 99% by weight of a water-in-oil emulsion polymer comprising a polymer or copolymer containing repeat units from an acrylamide monomer;(ii) 0.5% to 90% by weight of a carrier solvent; and (iii) 0 to 90% by weight of a fluidizing agent;
30 and adding 0.1% to 10% by weight of one or more inorganic microparticles, where the total of

all components is 100% by weight; and (II) adding the water-in-oil emulsion composition to water; and (b) contacting the subterranean formation with the fracturing fluid.

WO 2018/187550 A1, “Brine Resistant Silica Sol”, Published on **Oct 11, 2018** and is
5 assigned to Nissan Chemical America Corporation (the same assignee of the instant patent
application.) A brine resistant silica sol is described and claimed. This brine resistant silica sol
comprises an aqueous colloidal silica mixture that has been surface functionalized with at least
one moiety selected from the group consisting of a monomeric hydrophilic organosilane, a
mixture of monomeric hydrophilic organosilane(s) and monomeric hydrophobic organosilane(s),
10 or a polysiloxane oligomer, wherein the surface functionalized brine resistant aqueous colloidal
silica sol passes at least two of three of these brine resistant tests: API Brine Visual, 24 Hour
Seawater Visual and API Turbidity Meter.

US 2015/0292308 A1, “Stimulation of Wells in Nano-Darcy Shale Formations”,
Published on **Oct. 15, 2018**, and is assigned to Flex-Chem Holding Company, LLC of
15 Weatherford, Oklahoma. This patent application issued on **April 17, 2018** as **US Patent No.**
9,944,843 B2. This patent describes and claims formulations and methods for stimulating the
production from wells in nano-darcy shale formations. In one embodiment, the method includes
injecting a treatment mixture containing a metal complexing agent into a nano-darcy shale
formation adjacent to a well at a pressure below the fracture pressure of the formation. A
20 sufficient contact time is allowed and then the treatment mixture is pumped from the subsurface.
This has been shown to stimulate well production in shale formations. Without being held to a
particular theory it appears that the metal complexing agent is binding with naturally occurring
metals in the shale formation, and particularly divalent metal ions, which are then extracted with
the spent fluid. This removal of naturally occurring metals may be increasing the permeability of
25 the formation in the contact region adjacent to the well, thereby causing the observed increased
production.

US 2014/0374095 A1, “Nanoparticle Slurries and Methods”, Published on **Dec. 25, 2014**
and is assigned to Schlumberger Technology Corporation of Sugar Land, Texas, and is now
abandoned. This patent application describes and claims fluids comprising elongated
30 nanoparticles and methods of using the fluids in treating a subterranean formation penetrated by
a wellbore.

US 2014/0338906 A1, entitled “Proppant With Enhanced Interparticle Bonding”,
Published on **Nov. 20, 2014** and is assigned to Preferred Technology, LLC of Radnor,
Pennsylvania. This patent application issued on **Oct. 16, 2018 as US Patent No. 10,100,247 B2**.
In this patent application, polymer-coated proppants for hydraulic fracturing of oil and gas wells
5 have an outer layer portion that comprises an organofunctional coupling agent, preferably an
organofunctional silane coupling agent are described and claimed. The use of an
organofunctional silane coupling agent in the outer layer portion of the proppant coating is
preferably chosen to expose functionalities that will be reactive towards similar functionalities of
adjacent and similarly coated proppants so that, when introduced downhole, these proppants
10 form interparticle bonds at the temperatures and crack closure pressures found downhole in
fractured strata. Such enhanced interparticle bonding helps keep the proppant in the fracture and
maintains conductivity with reduced flowback. The invention also helps proppants designed for
low temperature well to bond more firmly and allows proppants designed for high temperature
wells to bond well even at lower downhole temperatures, thereby extending their useful range.

15 **WO 2014/176188 A1**, “Process for Treating and Recycling Hydraulic Fracturing Fluid”,
Published on **Oct. 30, 2014** and is assigned to E.I. DuPont de Nemours and Company of
Wilmington, Delaware. A method for treating hydraulic fracturing fluid is disclosed. The
hydraulic fracturing fluid is treated with an anionic silica-based colloid in an amount and for a
sufficient time to coagulate certain contaminants contained in the hydraulic fracturing fluid. The
20 contaminants can thereafter be removed from the hydraulic fracturing fluid.

WO 2013/192634 A2, “Self-Suspending Proppants for Hydraulic Fracturing”, Published
on **Dec. 27, 2013**, assigned to Self-Suspending Proppant LLC. This patent application describes
and claims modified proppants, comprising a proppant particle and a hydrogel coating, wherein
the hydrogel coating localizes on the surface of the proppant particle to produce the modified
25 proppant. Methods of manufacturing such proppants and methods of use are also included.

US 2010/0147515 A1, “Surface Modification for Cross-Linking or Breaking Interactions
with Injected Fluid”, Published on **Jun. 17, 2010**, issued as US Patent No. **US 8,360,149 B2** on
January 29, 2013, and is assigned to Schlumberger Technology Corporation. A method and
apparatus for treating a subterranean formation with a fluid, including forming a fluid including a
30 organosilane and a particulate and introducing the fluid into a subterranean formation with
exposed surfaces, wherein the organosilane modifies the particulate or surfaces or both is

described and claimed. Also, a method and apparatus for treating a subterranean formation with a fluid, including forming a fluid including an organosilane and introducing the fluid into a subterranean formation with exposed surfaces, wherein the organosilane modifies the surfaces with a first functional group.

5 “Oilfield Applications of Colloidal Silica Gel”, published in November of 1991 by the Society of Petroleum Engineers, authors: J.J. Jurinak (Conoco Inc.) and L.E. Summers (Conoco Inc.), Document ID: SPE-18505-PA, describes the development of a practical reservoir fluid flow control system based on colloidal silica gel.

10 Commercially available ceramic proppants are available from Carbo, <http://www.carboceramics.com/products-and-services/fracture-technologies/ceramic-proppant>. CARBO is an industry-leading technology and service company that provides engineered oilfield production enhancement, industrial performance enhancement, and environmental protection solutions. Carbo’s corporate headquarters are located at Energy Center II, 575 N. Dairy Ashford
15 Rd., Suite 300, Houston, Texas, USA 77079.

 These are considerations when selecting proppants (as shown in <https://info.drillinginfo.com/proppant-the-greatest-oilfield-innovation/>)

Size – the physical size of the proppant needs to be adjustable per the condition of the rock. Typically measured between 8 and 140 mesh (106 μm – 2.36 mm).

20 **Geometry** – in some cases the shape of the proppant needs to be adjusted.

Weight – largely depending on the depth of the frac the density of the proppant will need to be adjusted.

Some important measured qualities of proppant are:

Conductivity – basically the amount of flow that the proppant will allow.

25 **Crush Resistance** – deeper wells and varied lithologies require different stress properties.

Acid Solubility – tests of solubility in acid can indicate contaminants, and let you know how the proppant is likely to perform underground.

 Nissan Chemical America Corporation offers colloidal silica products for sale as well as fluids incorporating colloidal silica products. <https://www.nissanchem-usa.com/> Nissan

30 Chemical America Corporation, is a New York corporation having a place of business at 10333 Richmond Avenue, Suite 1100, Houston, Texas 77042 acting in its own name and in the name of

its parent company, Nissan Chemical Corporation, having offices at 5-1, Nihonbashi 2-Chome, Chuo-ku, Tokyo 103-6119, Japan.

Improved oil recovery treatment methods are well established in the oil industry. What would be desirable are modifications to existing EOR methods to increase the recovery of oil
5 from an underperforming oil well using engineered nanoparticles or colloidal particle-based treatment fluids.

Summary of the Invention

The first aspect of the instant claimed invention is a method of increasing production from a hydrocarbon containing formation by adding a proppant to the formation, characterized in that a treatment fluid comprising a colloidal silica nanoparticle is added to the formation before, during or after the time the proppant is added to the formation.

The second aspect of the invention is the method of the first aspect, characterized in that the treatment fluid comprising the colloidal silica nanoparticles is added to the formation before the time the proppant is added to the formation.

The third aspect of the invention is the method of the first aspect of the invention, characterized in that the treatment fluid comprising the colloidal silica nanoparticles is added to the formation during the time the proppant is added to the formation.

The fourth aspect of the invention is the method of the first aspect of the invention, characterized in that the treatment fluid comprising the colloidal silica nanoparticles is added to the formation after the time the proppant is added to the formation.

The fifth aspect of the invention is the method of the first aspect of the invention characterized in that the treatment fluid comprising the colloidal silica nanoparticles is added to the formation before and during the time the proppant is added to the formation.

The sixth aspect of the invention is the method of first aspect of the invention characterized in that the treatment fluid comprising the colloidal silica nanoparticles is added to the formation during and after the time the proppant is added to the formation.

The seventh aspect of the invention is the method of the first aspect of the invention characterized in that the treatment fluid comprising the colloidal silica nanoparticles is added to the formation before and after the time the proppant is added to the formation.

The eighth aspect of the invention is the method of any one of the first through seventh aspects of the invention, wherein the treatment fluid comprising a colloidal silica nanoparticle is a crude oil recovery chemical solution comprising a silane compound, an aqueous silica sol having an average particle size of from about 3 nm to about 200 nm.

The ninth aspect of the invention is the method of the eighth aspect of the invention, wherein the aqueous silica sol comprises silica particles in which at least a part of the silane compound is bonded on the surface of at least a part of the silica particles in the sol.

The tenth aspect of the invention is the method of eighth or ninth aspect of the invention, wherein the silane compound is at least one compound selected from the group consisting of a silane coupling agent having at least one organic functional group selected from the group consisting of a vinyl group, an ether group, an epoxy group, a styryl group, a methacryl group, an acryl group, an amino group, an isocyanurate group, an alkoxy silane group, a silazane group and a siloxane group.

The eleventh aspect of the invention is the method of any one of the eighth, ninth or tenth aspects of the invention, wherein the aqueous silica sol is present in an amount of from about 0.1 % by mass to about 20 % by mass, based on the total mass of the crude oil recovery chemical solution, in terms of silica solid content.

The twelfth aspect of the invention is the method of any one of the 1st through 11th aspects of the invention, wherein the proppant is sand.

The thirteenth aspect of the invention is the method of the 12th aspect of the invention, wherein the sand is 20 mesh, 40 mesh, 70 mesh, or 100 mesh.

The fourteenth aspect of the instant claimed invention is the method of the twelfth aspect of the invention, wherein the sand is a combination of 100 mesh and 40 mesh, a combination of 70 mesh and 40 mesh, or a combination of 40 mesh and 20 mesh.

The fifteenth aspect of the invention is the method of the first aspect of the invention, wherein the proppant is coated with the treatment fluid comprising colloidal silica nanoparticles.

Brief Description of the Drawings

Figure 1 Shows Modern Proppant Choices

Detailed Description of the Invention

The first aspect of the instant claimed invention is a method of increasing production from a hydrocarbon containing formation by adding a proppant to the formation, wherein a treatment fluid comprising a colloidal silica nanoparticle is added to the formation before, during or after the time the proppant is added to the formation.

The proppant materials that are intended to stay within the hydrocarbon-bearing formation are referred to as the proppant pack.

Proppants are commercially available and come in many different shapes and sizes and compositions. See Figure 1 for an illustration of commercially available Proppants.

Nanoparticle-based fluids are used in hydraulic fracturing procedures to improve the recovery of oil and gas hydrocarbons. In a current process, a nanoparticle-based hydrocarbon
5 recovery fluid is pumped down an oil well in one portion, referred to as a “pill”, directly prior to pumping a pad stage, i.e. nanoparticle-based Hydrocarbon Recovery fluid is pumped as a pre-pad pill. The pad stage during a fracture stimulation job consists of pumping a fracturing fluid which initiates and propagates the fracture in a formation. The pad stage is followed by a
10 slurry/proppant stage where both fluid and proppant are pumped to keep the created fractures open and provide conductivity to the wellbore. The slurry/proppant stage is usually followed by a flush stage. In this way the nanoparticle-based fluid is forced into the induced and secondary fracture network of a hydraulically-fractured or re-fractured well to affect intimate contact of nanoparticle-based fluid with hydrocarbons existing in the fracture network. This occurs before induced fractures are created and further “propped” open by the proppant materials pumped into
15 the oil well during the Proppant stage.

When the proppant stage is finished, fluids may be pumped from the surface through the proppant materials to affect different desired outcomes. A nanoparticle-based fluid may be pumped after the proppant stage as a post-proppant/pre-flush pill to affect deposition of the engineered nanoparticles onto the surfaces of the proppant materials after this fluid stage is
20 allowed to flow back over the proppant pack. A nanoparticle-based fluid may also be pumped as a pre-pad pill, during the pad stage or with the proppant in the slurry/proppant stage concurrently.

During the flowback/production phase, and as fluids flow out of the freshly fractured/re-fractured oil well to the surface, the fluids experience a drop in temperature and pressure. The
25 change in temperature and pressure conditions may cause several types of precipitation of dissolved species which may negatively affect the performance of the well.

From the hydrocarbon phase, relatively high molecular weight paraffins may be caused to precipitate out of the hydrocarbon solution. This precipitation may occur within the proppant pack, near well bore or in tubulars (aka piping). This may cause paraffins to be deposited onto
30 the surface of the proppant materials, effectively reducing the permeability and/or fluid conductivity of the proppant pack. From the aqueous phase, dissolved salts and/or minerals may

also experience precipitation onto available surfaces as the fluid experiences reduced temperature and pressure on the way out of the well. These precipitated salts and minerals are typically referred to as “scale”.

5 It has been found that an appropriately formulated nanoparticle-based fluid can be formulated to deposit the designed nanoparticles deliberately onto the surface of proppant particles before or during the flowback/production phase. This deposition process may be designed to occur after a nanoparticle-based fluid is pumped as a pre-pad pill, during the pad stage, in the slurry/proppant stage, as a post-proppant/pre-flush pill and as the frac fluids flow back after the well is completed.

10 The deposition of the proper type of nanoparticles onto the surfaces of proppant materials is expected to reduce the tendency of paraffins and scale to nucleate and form deposits onto the surfaces of proppant materials. This, in turn, will mitigate the reduction in permeability/fluid conductivity through the proppant pack and allow desirable hydrocarbons to be produced more efficiently and for a longer period of time from the well.

15 In addition to providing paraffin and scale control an appropriately formulated nanoparticle-based fluid can aid in the flowback of desirable oil and gas. An appropriately formulated nanoparticle-based fluid can also effectively act as a friction reducing agent, which can be observed by a pressure drop during pumping when the particles are first pumped downhole as well as the reduced pressure required to produce oil from the treated well. This
20 friction-reduction property can also be observed as a reduced need for artificial lift in a typical well where artificial lift is usually required.

This deliberate deposition of nanoparticles can also be applied to the induced fracture network within the formation, the secondary/existing fracture network within the formation, and the “tubulars” or piping that is used to conduct fluids up out of the formation to the surface.

25 Engineered nanoparticles are expected to reduce the tendency of high molecular weight hydrocarbons such as paraffin and scale to nucleate onto available surfaces and cause a reduction in recovery of desirable hydrocarbons.

Example

In the following potential examples, each ingredient that is used to create a surface treated colloidal silica, is listed as Parts of Ingredient, per 100 parts of surface treated colloidal silica.

5 ST-O25 and ST-32C are commercially available colloidal silicas from Nissan Chemical America Corporation, located at 10333 Richmond Avenue, Suite 1100 Houston, TX 77042 or from Nissan Chemical Corporation, located at 5-1, Nihonbashi 2-Chome, Chuo-ku, Tokyo 103-6119, Japan.

10 The first set of Examples focuses on the synthesis of brine resistant colloidal silicas.

Examples □	1	2	3	4	5	6
Ingredients □						
ST-O25	76	76	76	76	76	76
Deionized water	11.1	11.1	11.1	11.1	11.1	11.1
Propylene Glycol	10	10	10	10	10	10
3-(Triethoxysilyl)propyl Succinic Anhydride	2.9				1.9	1.9
N-(Triethoxysilylpropyl)-O-Polyethyleneoxide Urethane		2.9				
Silane, trimethoxy[3-(oxiranyl methoxy)propyl]			2.9			
3-Ureidopropyl Triethoxysilane				2.9		
2-(3,4 epoxy cyclohexyl)-ethyltrimethoxysilane					1	
3-(Trimethoxysilyl)propyl Methacrylate						1
Total	100.00	100.00	100.00	100.00	100.00	100.00

Examples □	7	8	9	10	11	12	13
Ingredients □							
ST-O25	76	76	76	76	76	76	76
Deionized water	11.1	11.1	11.1	11.1	11.1	11.1	11.1
Propylene Glycol	10	10	10	10	10	10	10
3-(Triethoxysilyl)propyl Succinic Anhydride	1.9	1.9	1.9	1.9	1.9	1.9	1.9
Hexamethyl Disiloxane	1						
Hexamethyl Disilazane		1					
Trimethoxy Methyl Silane			1				
Trimethoxy Phenyl Silane				1			
Vinyl Trimethoxysilane					1		
3-(N,N-Dimethylaminopropyl)-Trimethoxysilane						1	
3-(Diethylamino)propyl trimethoxysilane							1
Total	100	100	100	100	100	100	100

Examples □	14	15	16	17	18	19	20	21
Ingredients □								
ST-O25	76	76	76	76	76	76	76	76
Deionized water	11.1	11.1	11.1	11.1	11.1	11.1	11.1	11.1
Propylene Glycol	10	10	10	10	10	10	10	10
3-(Triethoxysilyl)propyl Succinic Anhydride	1.9	1.9	1.9	1.9	1.9	1.9	1.9	1.9
Trimethoxy(octadecyl)silane	1							
Isobutyl Trimethoxysilane		1						
Hexyltrimethoxysilane			1					
Decyltrimethoxysilane				1				
Isooctyltrimethoxysilane					1			
Hexadecyltrimethoxysilane						1		
Propyltrimethoxysilane							1	
Octyltriethoxysilane								1
Total	100	100	100	100	100	100	100	100

Examples □	22	23	24	25	26	27	28	29	30
Ingredients □									
ST-O25	70	80	75	72	76	76	76	76	76
Deionized water	14.1	19.1	11.1	13.1	11.1	11.1	11.1	11.1	11
Propylene Glycol	13	8	10	12	10	10	10	10	10
3-(Triethoxysilyl)propyl Succinic Anhydride	2.9								
N-(Triethoxysilylpropyl)-O-Polyethyleneoxide Urethane		2.9			1.9	1.9	1.9	1.9	1.9
Silane, trimethoxy[3-(oxiranyl methoxy)propyl]			3.9						
3-Ureidopropyl Triethoxysilane				2.9					
2-(3,4 epoxy-cyclohexyl)-ethyltrimethoxysilane					1				
3-(Trimethoxysilyl)propyl Methacrylate						1			
Hexamethyl Disiloxane							1		
Hexamethyl Disilazane								1	
Trimethoxy Methyl Silane									1
Total	100	100	100	100	100	100	100	100	100

Examples □	31	32	33	34	35	36	37
Ingredients □							
ST-O25	76	76	76	76	76	76	76
Deionized water	11.1	11.1	11.1	11.1	11.1	11.1	11.1
Propylene Glycol	10	10	10	10	10	10	10
N-(Triethoxysilylpropyl)-O-Polyethyleneoxide Urethane	1.9	1.9	1.9	1.9	1.9	1.9	1.9
Trimethoxy Phenyl Silane	1						
Vinyl Trimethoxysilane		1					
3-(N,N-Dimethylaminopropyl)-Trimethoxysilane			1				
3-(Diethylamino)propyl trimethoxysilane				1			
Trimethoxy-(octadecyl)silane					1		
Isobutyl Trimethoxysilane						1	
Hexyl-trimethoxysilane							1
Total	100	100	100	100	100	100	100

Examples □	38	39	40	41	42
Ingredients □					
ST-O25	76	76	76	76	76
Deionized water	11.1	11.1	11.1	11.1	11.1
Propylene Glycol	10	10	10	10	10
N-(Triethoxysilylpropyl)-O-Polyethyleneoxide Urethane	1.9	1.9	1.9	1.9	1.9
Decyl-trimethoxysilane	1				
Isooctyl-trimethoxysilane		1			
Hexadecyl-trimethoxysilane			1		
Propyl-trimethoxysilane				1	
Octyl-triethoxysilane					1
Total	100.00	100.00	100.00	100.00	100.00

Examples □	43	44	45	46	47	48	49	50	51
Ingredients □									
ST-O25	76	76	70	80	76	76	76	76	76
Deionized water	10	9	16.1	11.1	11.1	11.1	11.1	11.1	11
Propylene Glycol	11.1	12.1	11	6	10	10	10	10	10
3-(Triethoxysilyl)propyl Succinic Anhydride	2.9								
N-(Triethoxysilylpropyl)-O-Polyethyleneoxide Urethane		2.9							
Silane, trimethoxy[3-(oxiranyl methoxy)propyl]			2.9		1.9	1.9	1.9	1.9	1.9
3-Ureidopropyl Triethoxysilane				2.9					
2-(3,4 epoxy cyclohexyl)-ethyltrimethoxysilane					1				
3-(Trimethoxysilyl)propyl Methacrylate						1			
Hexamethyl Disiloxane							1		
Hexamethyl Disilazane								1	
Trimethoxy Methyl Silane									1
Total	100								

Examples □	52	53	54	55	56	57	58
Ingredients □							
ST-O25	76	76	76	76	76	76	76
Deionized water	11.1	11.1	11.1	11.1	11.1	11.1	11.1
Propylene Glycol	10	10	10	10	10	10	10
Silane, trimethoxy[3-(oxiranyl methoxy)propyl]	1.9	1.9	1.9	1.9	1.9	1.9	1.9
Trimethoxy Phenyl Silane	1						
Vinyl Trimethoxysilane		1					
3-(N,N-Dimethylaminopropyl)-Trimethoxysilane			1				
3-(Diethylamino)propyl trimethoxysilane				1			
Trimethoxy(octadecyl)silane					1		
Isobutyl Trimethoxysilane						1	
Hexyltrimethoxysilane							1
Total	100.00	100.00	100.00	100.00	100.00	100.00	100.00

Examples □	59	60	61	62	63
Ingredients □					
ST-O25	76	76	76	76	76
Deionized water	11.1	11.1	11.1	11.1	11.1
Propylene Glycol	10	10	10	10	10
Silane, trimethoxy[3-(oxiranyl methoxy)propyl]	1.9	1.9	1.9	1.9	1.9
Decyltrimethoxysilane	1				
Isooctyltrimethoxysilane		1			
Hexadecyltrimethoxysilane			1		
Propyltrimethoxysilane				1	
Octyltriethoxysilane					1
Total	100.00	100.00	100.00	100.00	100.00

Examples □	64	65	66	67	68	69	70	71	72	73
Ingredients □										
ST-O25	76	76	76	76	76	76	76	76	76	76
Deionized water	11.1	11.1	11.1	11.1	11.1	11.1	11.1	11.1	11	11.1
Propylene Glycol	10	10	10	10	10	10	10	10	10	10
3-(Triethoxysilyl)propyl Succinic Anhydride	1.45									
N-(Triethoxysilylpropyl)-O-Polyethyleneoxide Urethane	1.45	2.9								
Silane, trimethoxy[3-(oxiranyl methoxy)propyl]			2.9							
3-Ureidopropyl Triethoxysilane				2.9	1.9	1.9	1.9	1.9	1.9	1.9
2-(3,4 epoxy cyclohexyl)-ethyltrimethoxysilane					1					
3-(Trimethoxysilyl)propyl Methacrylate						1				
Hexamethyl Disiloxane							1			
Hexamethyl Disilazane								1		
Trimethoxy Methyl Silane									1	
Trimethoxy Phenyl Silane										1
Total	100	100	100	100	100	100	100	100	100	100

Examples □	74	75	76	77	78	79	80	81
Ingredients □								
ST-O25	76	76	76	76	76	76	76	76
Deionized water	11.1	11.1	11.1	11.1	11.1	11.1	11.1	11.1
Propylene Glycol	10	10	10	10	10	10	10	10
3-Ureidopropyl Triethoxysilane	1.9	1.9	1.9	1.9	1.9	1.9	1.9	1.9
Vinyl Trimethoxysilane	1							
3-(N,N- Dimethylaminopropyl)- Trimethoxysilane		1						
3-(Diethylamino)propyl trimethoxysilane			1					
Trimethoxy(octadecyl)silane				1				
Isobutyl Trimethoxysilane					1			
Hexyltrimethoxysilane						1		
Decyltrimethoxysilane							1	
Isooctyltrimethoxysilane								1
Hexadecyltrimethoxysilane								
Propyltrimethoxysilane								
Octyltriethoxysilane								
Total	100.00	100.00	100.00	100.00	100.00	100.00	100.00	100.00

Examples □	82	83	84
Ingredients □			
ST-O25	76	76	76
Deionized water	11.1	11.1	11.1
Propylene Glycol	10	10	10
3-Ureidopropyl Triethoxysilane	1.9	1.9	1.9
Hexadecyltrimethoxysilane	1		
Propyltrimethoxysilane		1	
Octyltriethoxysilane			1
Total	100.00	100.00	100.00

Examples □	85	86	87	88	89
Ingredients □					
ST-O25	76	76	76	76	76
Deionized water	11.1	11.1	11.1	11.1	11.1
Ethylene Glycol	10	10	10	10	10
3-(Triethoxysilyl)propyl Succinic Anhydride	2.9				1.9
N-(Triethoxysilylpropyl)-O-Polyethyleneoxide Urethane		2.9			
Silane, trimethoxy[3-(oxiranyl methoxy)propyl]			2.9		
3-Ureidopropyl Triethoxysilane				2.9	
2-(3,4-epoxycyclohexyl)-ethyltrimethoxysilane					1
3-(Trimethoxysilyl)propyl Methacrylate					
Hexamethyl Disiloxane					
Hexamethyl Disilazane					
Total	100.00	100.00	100.00	100.00	100.00

Examples □	90	91	92
Ingredients □			
ST-O25	76	76	76
Deionized water	11.1	11.1	11.1
Ethylene Glycol	10	10	10
3-(Triethoxysilyl)propyl Succinic Anhydride	1.9	1.9	1.9
3-(Trimethoxysilyl)propyl Methacrylate	1		
Hexamethyl Disiloxane		1	
Hexamethyl Disilazane			1
Total	100.00	100.00	100.00

Examples □	93	94	95	96	97	98	99
Ingredients □							
ST-O25	76	76	76	76	76	76	76
Deionized water	11.1	11.1	11.1	11.1	11.1	11.1	11.1
Ethylene Glycol	10	10	10	10	10	10	10
3-(Triethoxysilyl)propyl Succinic Anhydride	1.9	1.9	1.9	1.9	1.9	1.9	1.9
Trimethoxy Methyl Silane	1						
Trimethoxy Phenyl Silane		1					
Vinyl Trimethoxysilane			1				
Total	100.00	100.00	100.00	100.00	100.00	100.00	100.00

Examples □	100	101	102	103	104	105
Ingredients □						
ST-O25	76	76	76	76	76	76
Deionized water	11.1	11.1	11.1	11.1	11.1	11.1
Ethylene Glycol	10	10	10	10	10	10
3-(Triethoxysilyl)propyl Succinic Anhydride	1.9	1.9	1.9	1.9	1.9	1.9
Hexyltrimethoxysilane	1					
Decyltrimethoxysilane		1				
Isooctyltrimethoxysilane			1			
Hexadecyltrimethoxysilane				1		
Propyltrimethoxysilane					1	
Octyltriethoxysilane						1
Total	100.00	100.00	100.00	100.00	100.00	100.00

Examples □	106	107	108	109	110	111	112
Ingredients □							
ST-O25	78	74	76	76	76	76	76
Deionized water	11.1	11.1	11.1	11.1	11.1	11.1	11.1
Ethylene Glycol	8	12	10	10	10	10	10
3-(Triethoxysilyl)propyl Succinic Anhydride	1.45						
N-(Triethoxysilylpropyl)-O-Polyethyleneoxide Urethane	1.45	1.45			1.9	1.9	1.9
Silane, trimethoxy[3-(oxiranyl methoxy)propyl]		1.45	1.45				
3-Ureidopropyl Triethoxysilane			1.45	1.45			
2-(3,4 epoxy cyclohexyl)-ethyltrimethoxysilane				1.45	1		
3-(Trimethoxysilyl)propyl Methacrylate						1	
Hexamethyl Disiloxane							1
Total	100.00	100.00	100.00	100.00	100.00	100.00	100.00

Examples □	113	114	115	116	117	118
Ingredients □						
ST-O25	76	76	76	76	76	76
Deionized water	11.1	11.1	11.1	11.1	11.1	11.1
Ethylene Glycol	10	10	10	10	10	10
N-(Triethoxysilylpropyl)-O-Polyethyleneoxide Urethane	1.9	1.9	1.9	1.9	1.9	1.9
Hexamethyl Disilazane	1					
Trimethoxy Methyl Silane		1				
Trimethoxy Phenyl Silane			1			
Vinyl Trimethoxysilane				1		
3-(N,N-Dimethylaminopropyl)-Trimethoxysilane					1	
3-(Diethylamino)propyl trimethoxysilane						1
Total	100.00	100.00	100.00	100.00	100.00	100.00

Examples □	119	120	121	122	123	124	125	126
Ingredients □								
ST-O25	76	76	76	76	76	76	76	76
Deionized water	11.1	11.1	11.1	11.1	11.1	11.1	11.1	11.1
Ethylene Glycol	10	10	10	10	10	10	10	10
N-(Triethoxysilylpropyl)-O-Polyethyleneoxide Urethane	1.9	1.9	1.9	1.9	1.9	1.9	1.9	1.9
Trimethoxy(octadecyl)silane	1							
Isobutyl Trimethoxysilane		1						
Hexyltrimethoxysilane			1					
Decyltrimethoxysilane				1				
Isooctyltrimethoxysilane					1			
Hexadecyltrimethoxysilane						1		
Propyltrimethoxysilane							1	
Octyltriethoxysilane								1
Total	100.00	100.00	100.00	100.00	100.00	100.00	100.00	100.00

Examples □	127	128	129	130	131	132	133	134
Ingredients □								
ST-O25	76	76	78	74	76	76	76	76
Deionized water	11.1	9.1	9.1	12.1	11.1	11.1	11.1	11.1
Ethylene Glycol	10	12	10	10	10	10	10	10
3-(Triethoxysilyl)propyl Succinic Anhydride	1.45							
N-(Triethoxysilylpropyl)-O-Polyethyleneoxide Urethane		1.45						
Silane, trimethoxy[3-(oxiranyl methoxy)propyl]	1.45		1.45		1.9	1.9	1.9	1.9
3-Ureidopropyl Triethoxysilane		1.45		1.45				
2-(3,4-Epoxy)cyclohexyl-ethyltrimethoxysilane			1.45		1			
3-(Trimethoxysilyl)propyl Methacrylate				1.45		1		
Hexamethyl Disiloxane							1	
Hexamethyl Disilazane								1
Total	100.00	100.00	100.00	100.00	100.00	100.00	100.00	100.00

Examples □	135	136	137	138	139	140	141
Ingredients □							
ST-O25	76	76	76	76	76	76	76
Deionized water	11.1	11.1	11.1	11.1	11.1	11.1	11.1
Ethylene Glycol	10	10	10	10	10	10	10
Silane, trimethoxy[3-(oxiranyl methoxy)propyl]	1.9	1.9	1.9	1.9	1.9	1.9	1.9
Trimethoxy Methyl Silane	1						
Trimethoxy Phenyl Silane		1					
Vinyl Trimethoxysilane			1				
3-(N,N-Dimethylaminopropyl)-Trimethoxysilane				1			
3-(Diethylamino)propyl trimethoxysilane					1		
Trimethoxy(octadecyl)silane						1	
Isobutyl Trimethoxysilane							1
Total	100.00	100.00	100.00	100.00	100.00	100.00	100.00

Examples □	142	143	144	145	146	147
Ingredients □						
ST-O25	76	76	76	76	76	76
Deionized water	11.1	11.1	11.1	11.1	11.1	11.1
Ethylene Glycol	10	10	10	10	10	10
Silane, trimethoxy[3-(oxiranyl methoxy)propyl]	1.9	1.9	1.9	1.9	1.9	1.9
Hexyltrimethoxysilane	1					
Decyltrimethoxysilane		1				
Isooctyltrimethoxysilane			1			
Hexadecyltrimethoxysilane				1		
Propyltrimethoxysilane					1	
Octyltriethoxysilane						1
Total	100.00	100.00	100.00	100.00	100.00	100.00

Examples □	148	149	150	151	152	153	154
Ingredients □							
ST-O25	76	76	76	76	76	76	76
Deionized water	6.1	7.1	8.1	9.1	11.1	11.1	11.1
Ethylene Glycol	15	14	13	12	10	10	10
3-(Triethoxysilyl)propyl Succinic Anhydride	2.9						
N-(Triethoxysilylpropyl)-O-Polyethyleneoxide Urethane		2.9					
Silane, trimethoxy[3-(oxiranyl methoxy)propyl]			2.9				
3-Ureidopropyl Triethoxysilane				2.9	1.9	1.9	1.9
2-(3,4 epoxy cyclohexyl)-ethyltrimethoxysilane					1		
3-(Trimethoxysilyl)propyl Methacrylate						1	
Hexamethyl Disiloxane							1
Total	100.00	100.00	100.00	100.00	100.00	100.00	100.00

Examples □	155	156	157	158	159	160	161
Ingredients □							
ST-O25	76	76	76	76	76	76	76
Deionized water	11.1	11.1	11.1	11.1	11.1	11.1	11.1
Ethylene Glycol	10	10	10	10	10	10	10
3-Ureidopropyl Triethoxysilane	1.9	1.9	1.9	1.9	1.9	1.9	1.9
Hexamethyl Disilazane	1						
Trimethoxy Methyl Silane		1					
Trimethoxy Phenyl Silane			1				
Vinyl Trimethoxysilane				1			
3-(N,N- Dimethylaminopropyl)- Trimethoxysilane					1		
3-(Diethylamino)propyl trimethoxysilane						1	
Trimethoxy(octadecyl)silane							1
Total	100.00	100.00	100.00	100.00	100.00	100.00	100.00

Examples □	162	163	164	165	166	167	168
Ingredients □							
ST-O25	76	76	76	76	76	76	76
Deionized water	11.1	11.1	11.1	11.1	11.1	11.1	11.1
Ethylene Glycol	10	10	10	10	10	10	10
3-Ureidopropyl Triethoxysilane	1.9	1.9	1.9	1.9	1.9	1.9	1.9
Isobutyl Trimethoxysilane	1						
Hexyltrimethoxysilane		1					
Decyltrimethoxysilane			1				
Isooctyltrimethoxysilane				1			
Hexadecyltrimethoxysilane					1		
Propyltrimethoxysilane						1	
Octyltriethoxysilane							1
Total	100.00	100.00	100.00	100.00	100.00	100.00	100.00

	Examples□	169	170	171	172	173	174	175
Description	Ingredients□							
Colloidal silica 25 wt% silica solids available from Nissan Chemical America	ST-O-25	52.68		50		51		25
Alkaline Colloidal Silica from Nissan Chemical Company, Japan	ST-32C		59.28		48		45	25
	Deionized water	36.05	27.97	40	41.5	38.5	43	35
	Propylene Glycol				8	7.5	8.5	
	Ethylene Glycol	8.06	9.85	7.5				10
	Silane, trimethoxy[3- (oxiranyl → methoxy)propyl]	3.21	2.9	2.5	2.5	3	3.5	5
	Total (g)	100	100	100	100	100	100	100

In examples 7-168 it is expedient to make a Polysiloxane Oligomer Premix Preparation
5 before surface functionalization of colloidal silica mixtures.

Polysiloxane Oligomer Premix Preparation:

10 Make pH 3 water from 100g deionized water and 3-4 drops of 10% HCl while mixing
and monitoring the pH using a calibrated pH meter. Continue until the pH of the mixture is
measured to be 3.0 Add the organosilanes in the required proportions to form a mixture of
organosilanes, then add pH 3 water to the organosilane combination and mix with magnetic
stirrer/stir bar in a 100mL polypropylene beaker.

The mixture will appear hazy at first, then it should change appearance and clarify to a
visually clear, transparent solution. After the clear, transparent mixture is achieved, wait at least
30 minutes to allow for the oligomerization reaction to proceed to completion.

Wait 30 minutes with each mixture to allow for oligomerization reaction before using it to surface treat aqueous silica sols. After 30 min the organosilane oligomer mixture can be used to surface treat aqueous silicasols.

Polysiloxane oligomer preparations are observed for clarity, gelation/polymerization, or formation of agglomerations/white precipitate. Preparations resulting in clear liquids or clear slight viscous liquids are listed as “OK” and deemed usable. Those preparations showing gelation/polymerization agglomeration, or white precipitate formation are concluded to be unusable. It is believed that oligomer preparation without sufficient monomeric hydrophilic content are prone to failure in an aqueous or semi aqueous environment.

Surface Functionalization Method of Aqueous Silicasols

Standard Formula, use for all Silica Sols utilizing Polysiloxane Oligomer surface treatment

15	Aqueous Silica Sol (ST-O25 or ST-32C)	59.28
	Deionized water	27.98
	Ethylene Glycol or Propylene Glycol	9.85
	<u>Silane Oligomer Premix</u>	<u>2.9</u>
20	Total Parts	100.01

Add aqueous silica sol ST-32 C or ST-O25, DI water, Ethylene Glycol or Propylene Glycol and a stir bar to a glass reactor and bring the silica sol to 50°C. A 10mL addition funnel is fitted to the reactor and used to add the polysiloxane oligomer preparations dropwise while the reaction mixes until finished. Surface treatment is allowed to react with silica surfaces for a period of 2 hours at 50C and allowed to cool.

Surface Functionalization Method of Aqueous Silicasols

Standard Formula use for all Silica Sols utilizing monomeric organosilanes surface treatment, such as examples 1-6 and examples 169-175.

30

	ST-32C or ST-O25	59.28
	Deionized water	27.98
	Ethylene Glycol or Propylene Glycol	9.85
	<u>Monomeric Organosilane or mixture</u>	<u>2.9</u>
5	Total Parts	100.01

Add aqueous silica sol ST-32 C or ST-O25, DI water, Ethylene Glycol and a stir bar to a glass reactor and bring the silica sol to 50°C. If a mixture of organosilanes is used, these are prepared and mixed by hand before adding to an addition funnel. A 10mL addition funnel is fitted to the reactor and used to add the monomeric organosilanes or mixture of monomeric organosilanes dropwise while the reaction mixes until finished. Surface treatment is allowed to react with silica surfaces for a period of 2 hours at 50C and allowed to cool.

Brine resistant silica sols and hydrocarbon recovery fluids comprising surface functionalized nanoparticles, where the surface functionalized nanoparticles are brine resistant silica sols, can be found in U.S. Patent Application. No. 15/946,252; filed April 5, 2018, entitled “Brine Resistant Silica Sols”; U.S. Patent Application No. 15/946,338, filed April 5, 2018, entitled “Hydrocarbon Formation Treatment Micellar Solutions”; U.S. Patent Application No. 16/129,688; filed: September 12, 2018, entitled “Crude Oil Recovery Chemical Fluids”, which application claims priority to Japanese Patent Application No. JP 2017-175511; and U.S. Patent Application No. 16/129,705; filed: September 12, 2018, entitled “Crude Oil Recovery Chemical Fluid”, which application claims priority to Japanese Patent Application No. JP 2017-175511; wherein all US Patent Applications are herein incorporated by reference, in their entirety.

When selecting/using a fluid to be used in combination with a proppant in the treatment of an oil and/or gas well, it is important for the fluid to have the right combination of additives and components to achieve the necessary characteristics of the specific end-use application. A primary goal amongst many aspects of hydrocarbon formation treatment is to optimize recovery of oil and/or gas from the formation. However, in part because the fluids utilized during the operation of an oil and/or gas well are often utilized to perform a number of tasks

simultaneously, achieving necessary to optimal characteristics of the Hydrocarbon Recovery Fluid comprising surface functionalized nanoparticles is always challenging.

Additional commercially available compositions suitable for the Hydrocarbon Recovery Fluid include the nanoActiv[®] HRT product line available from Nissan Chemical America Corporation, located at 10333 Richmond Avenue, Suite 1100 Houston, TX 77042. These products, including developmental products that are currently being trialed, use nanosized particles in a colloidal dispersion, which allows the fluid to work by causing a Brownian-motion, diffusion-driven mechanism known as disjoining pressure to produce long efficacy in the recovery of hydrocarbons in conventional and unconventional reservoirs.

Current commercially available nanoActiv[®]HRT products, include, but are not limited to:

- a. HRT BIO/G – an environmentally friendly version
- b. OFS CORR PRO – a version containing a sour gas scavenger for reducing corrosion of iron piping due to H₂S
- c. HRT-78 – a version formulated for high temperatures
- d. CPD-60 – a version containing a hydroxysultaine surfactant
- e. CPD-37 – the original version that was first sold
- f. HRT-53-economical, high performing commercial product
- g. HRT-53 C-another version of HRT-53C with a more dilute composition

Additional Hydrocarbon Recovery Fluids comprising functionalized colloidal silica mixtures suitable for this invention include a crude oil recovery chemical solution which is excellent in resistance to high temperature and salt, characterized by containing a silane compound, an aqueous silica sol having an average particle size of from about 3nm to about 200 nm.

In an embodiment of the Hydrocarbon Recovery Fluid comprising surface functionalized nanoparticles, the aqueous silica sol contains silica particles in which at least a part of the silane compound is bonded on the surface of at least a part of the silica particles in the sol.

In another embodiment of the Hydrocarbon Recovery Fluid comprising surface functionalized nanoparticles, the silane compound is at least one compound selected from the group consisting of a silane coupling agent having at least one organic functional group selected

from the group consisting of a vinyl group, an ether group, an epoxy group, a styryl group, a methacryl group, an acryl group, an amino group and an isocyanurate group, an alkoxy silane group, a silazane group and a siloxane group.

In another embodiment of the Hydrocarbon Recovery Fluid comprising surface
5 functionalized nanoparticles, aqueous silica sol is present in an amount of from about 0.1% by mass to about 20% by mass, based on the total mass of the crude oil recovery chemical solution, in terms of silica solid content.

Preparation of Treatment Fluid to be used with Proppant

10 First Step: Preparation of Aqueous Sol

Synthesis Example 1

In a 500-ml glass eggplant flask, 200 g of an aqueous silica sol (SNOWTEX (registered
trademark) ST-O manufactured by Nissan Chemical Corporation, silica concentration = 20.5%
by mass, the average particle diameter of 11.0 nm according to the BET method, DLS average
15 particle diameter of 17.2 nm) and a magnetic stir bar were put. After that, with stirring with a
magnetic stirrer, 4.0 g of 3-glycidoxypropyltrimethoxysilane (Dynasylan GLYMO manufactured
by Evonik Industries AG) was charged such that the mass ratio of the silane compound to silica
in the aqueous silica sol was 0.09. Subsequently, a cooling tube through which tap water flowed
was installed above the eggplant flask. Under reflux, the temperature of the aqueous sol was
20 increased to 60°C and held at 60°C for 3 hours, and thereafter cooled. After cooling to room
temperature, the aqueous sol was taken out.

We obtained 204 g of an aqueous sol including an aqueous silica sol surface-treated with
a silane compound in which the mass ratio of the silane compound was 0.09 with respect to silica
in the aqueous silica sol, the silica solid content = 20.2% by mass, pH = 3.1, electrical
25 conductivity = 452 μ S/cm, and DLS average particle diameter = 24.3 nm.

Synthesis Example 2

An aqueous sol was obtained through the same operation as in Synthesis Example 1
except that 7.9 g of 3-glycidoxypropyltrimethoxysilane (Dynasylan GLYMO manufactured by
30 Evonik Industries AG) was charged such that the mass ratio of the silane compound was 0.20
with respect to silica in the aqueous silica sol (SNOWTEX ® ST-O manufactured by Nissan

Chemical Corporation, silica concentration = 20.5% by mass, average particle diameter of 11.0 nm according to the BET method, DLS average particle diameter of 17.2 nm).

5 We obtained 208 g of an aqueous sol including an aqueous silica sol surface-treated with a silane compound in which the mass ratio of the silane compound was 0.2 with respect to silica in the aqueous silica sol, silica solid content = 20.6% by mass, pH = 2.9, electrical conductivity = 544 μ S/cm, and DLS average particle diameter = 19.5 nm.

Synthesis Example 3

10 An aqueous sol was obtained through the same operation as in Synthesis Example 1 except that 15.8 g of 3-glycidoxypropyltrimethoxysilane (Dynasylan GLYMO manufactured by Evonik Industries AG) was charged such that the mass ratio of the silane compound was 0.40 with respect to silica in the aqueous silica sol (SNOWTEX $\text{\textcircled{R}}$ ST-O manufactured by Nissan Chemical Corporation, silica concentration = 20.5% by mass, average particle diameter of 11.0
15 nm according to the BET method, DLS average particle diameter of 17.2 nm).

We obtained 216 g of an aqueous sol including an aqueous silica sol surface-treated with a silane compound in which the mass ratio of the silane compound was 0.4 with respect to silica in the aqueous silica sol, silica solid content = 20.5% by mass, pH = 2.9, electrical conductivity =
20 474 μ S/cm, and DLS average particle diameter = 19.7 nm.

Synthesis Example 4

An aqueous sol was obtained through the same operation as in Synthesis Example 1 except that 31.6 g of 3-glycidoxypropyltrimethoxysilane (Dynasylan GLYMO manufactured by
25 Evonik Industries AG) was charged such that the mass ratio of the silane compound was 0.80 with respect to silica in the aqueous silica sol (SNOWTEX $\text{\textcircled{R}}$ ST-O manufactured by Nissan Chemical Corporation, silica concentration = 20.5% by mass, average particle diameter of 11.0 nm according to the BET method, DLS average particle diameter of 17.2 nm).

30 We obtained 231 g of an aqueous silica sol surface-treated with a silane compound in which the mass ratio of the silane compound was 0.8 with respect to silica in the aqueous silica

sol, silica solid content = 20.6% by mass, pH = 2.8, electrical conductivity = 413 $\mu\text{S}/\text{cm}$, and DLS average particle diameter = 20.8 nm.

Synthesis Example 5

5 In a 500-ml glass eggplant flask, 250 g of an aqueous silica sol (SNOWTEX[®] ST-OXS manufactured by Nissan Chemical Corporation, silica concentration = 10.4% by mass, the average particle diameter of 5.0 nm according to Sears method, DLS average particle diameter of 8.1 nm) and a magnetic stir bar were put. After that, with stirring with a magnetic stirrer, 88.9 g of 3-glycidoxypropyltrimethoxysilane (Dynasylan GLYMO manufactured by Evonik Industries
10 AG) was charged such that the mass ratio of the silane compound to silica in the aqueous silica sol was 3.4. Subsequently, a cooling tube through which tap water flowed was installed above the eggplant flask. Under reflux, the temperature of the aqueous sol was increased to 60°C and held at 60°C for 3 hours, and thereafter cooled. After cooling to room temperature, the aqueous sol was taken out.

15

We obtained 338 g of an aqueous sol including an aqueous silica sol surface-treated with a silane compound in which the mass ratio of the silane compound was 3.4 with respect to silica in the aqueous silica sol, the silica solid content = 14.3% by mass, pH = 2.9, electrical conductivity = 163 $\mu\text{S}/\text{cm}$, and DLS average particle diameter = 8.1 nm.

20

Synthesis Example 6

An aqueous sol was obtained through the same operation as in Synthesis Example 1 except that in a 500-ml glass eggplant flask, 200 g of an aqueous silica sol (SNOWTEX[®] ST-OL manufactured by Nissan Chemical Corporation, silica concentration = 20.0% by mass, the
25 average particle diameter of 46 nm according to the BET method, DLS average particle diameter of 75.8 nm) and a magnetic stir bar were put, and then, with stirring with a magnetic stirrer, 31.9 g of 3-glycidoxypropyltrimethoxysilane (Dynasylan GLYMO manufactured by Evonik Industries AG) was charged such that the mass ratio of the silane compound was 1.6 with respect to silica in the aqueous silica sol.

30

We obtained 231 g of an aqueous silica sol surface-treated with a silane compound in which the mass ratio of the silane compound was 0.8 with respect to silica in the aqueous silica sol, silica solid content = 21.2% by mass, pH = 3.1, electrical conductivity = 160 μ S/cm, and DLS average particle diameter = 76.4 nm.

5

Synthesis Example 7

An aqueous sol was obtained through the same operation as in Synthesis Example 1 except that in a 500-ml glass eggplant flask, 115 g of an aqueous silica sol (SNOWTEX $\text{\textcircled{R}}$ ST-OZL-35 manufactured by Nissan Chemical Corporation, silica concentration = 35.7% by mass, the average particle diameter of 83 nm according to the BET method, DLS average particle diameter of 126 nm), 85 g of pure water and a magnetic stir bar were put, and then, with stirring with a magnetic stirrer, 32.8 g of 3-glycidoxypropyltrimethoxysilane (Dynasylan GLYMO manufactured by Evonik Industries AG) was charged such that the mass ratio of the silane compound was 0.8 with respect to silica in the aqueous silica sol.

15

We obtained 232 g of an aqueous silica sol surface-treated with a silane compound in which the mass ratio of the silane compound was 1.6 with respect to silica in the aqueous silica sol, silica solid content = 20.7% by mass, pH = 2.6, electrical conductivity = 579 μ S/cm, and DLS average particle diameter = 119 nm.

20

Preparation of Treatment Fluid for use with Proppant

Example 1

In a 300-ml styrene container, a stir bar was put, and 91.0 g of pure water was charged. With stirring with a magnetic stirrer, 2.3 g of an anionic surfactant sodium α -olefin sulfonate (NEOGEN $\text{\textcircled{R}}$ AO-90 manufactured by DKS Co. Ltd.) was charged and stirred until it was completely melted. Subsequently, 4.7 g of an anionic surfactant sodium dodecyl sulfate (Shinorine $\text{\textcircled{R}}$ 90TK-T manufactured by New Japan Chemical CO., Ltd.) was charged and stirred until it was completely melted.

30

Subsequently, 22.0 g of the aqueous silica sol produced in Synthesis Example 2 was charged. Subsequently, 30.0 g of polyoxyethylene nonylphenyl ether (reagent Tergitol ® NP-9 manufactured by Sigma-Aldrich Corporation) with HLB = 13.0 was charged as a nonionic surfactant and then stirred for 1 hour to produce a chemical fluid of Example 1.

5

A brine test sample (a) was prepared according to the high temperature and salt resistance evaluation-1 and held at 100°C for 30 hours. After that, the sample was taken out to evaluate the resistance to high temperature and salt.

10 Example 2

A chemical fluid of Example 2 was produced through the same operation as in Example 1 except that the amount of pure water charged was 106.0 g and the amount of polyoxyethylene nonylphenyl ether (reagent Tergitol ® NP-9 manufactured by Sigma-Aldrich Corporation) with HLB = 13.0 charged as a nonionic surfactant was 15.0 g.

15

A brine test sample (a) was prepared according to the high temperature and salt resistance evaluation-1 and held at 100°C for 30 hours. After that, the sample was taken out to evaluate the resistance to high temperature and salt.

20 Example 3

A chemical fluid of Example 3 was produced through the same operation as in Example 1 except that the amount of pure water charged was 113.5 g and the amount of polyoxyethylene nonylphenyl ether with HLB = 13.0 (reagent Tergitol ® NP-9 manufactured by Sigma-Aldrich Corporation) charged as a nonionic surfactant was 7.5 g.

25

A brine test sample (a) was prepared according to the high temperature and salt resistance evaluation-1 and held at 100°C for 30 hours. After that, the sample was taken out to evaluate the resistance to high temperature and salt.

30

Example 4

A chemical fluid of Example 4 was produced through the same operation as in Example 2 except that polyoxyethylene styrenated phenyl ether (NOIGEN ® EA-137 manufactured by DKS Co. Ltd.) with HLB = 13.0 was employed as a nonionic surfactant and charged in an amount of 15.0 g.

A brine test sample (a) was prepared according to the high temperature and salt resistance evaluation-1 and held at 100°C for 30 hours. After that, the sample was taken out to evaluate the resistance to high temperature and salt.

Example 5

A chemical fluid of Example 5 was produced through the same operation as in Example 2 except that the amount of pure water charged was 99.6 g, and 21.4 g of a product of polyoxyethylene styrenated phenyl ether (NOIGEN ® EA-157 manufactured by DKS Co. Ltd.) with HLB = 14.3 diluted with pure water to contain 70% of active ingredients was charged as a nonionic surfactant.

A brine test sample (a) was prepared according to the high temperature and salt resistance evaluation-1 and held at 100°C for 30 hours. After that, the sample was taken out to evaluate the resistance to high temperature and salt.

Example 6

In a 300-ml styrene container, a stir bar was put, and 99.5 g of pure water was charged. With stirring with a magnetic stirrer, 1.8 g of an anionic surfactant sodium α -olefin sulfonate (NEOGEN ® AO-90 manufactured by DKS Co. Ltd.) was charged and stirred until it was completely melted. Subsequently, 5.3 g of an anionic surfactant sodium dodecyl sulfate (Shinorine ® 90TK-T manufactured by New Japan Chemical CO., Ltd.) was charged and stirred until it was completely melted.

Subsequently, 22.0 g of the aqueous silica sol produced in Synthesis Example 2 was charged. Subsequently, 21.4 g of a product of polyoxyethylene styrenated phenyl ether

(NOIGEN ® EA-157 manufactured by DKS Co. Ltd.) with HLB = 14.3 diluted with pure water to contain 70% of active ingredients was charged as a nonionic surfactant and then stirred for 1 hour to produce a chemical fluid of Example 6.

5 A brine test sample (a) was prepared according to the high temperature and salt resistance evaluation-1 and held at 100°C for 60 hours. After that, the sample was taken out to evaluate the resistance to high temperature and salt.

Example 7

10 In a 300-ml styrene container, a stir bar was put, and 99.6 g of pure water was charged. With stirring with a magnetic stirrer, 3.5 g of an anionic surfactant sodium α -olefin sulfonate (NEOGEN ® AO-90 manufactured by DKS Co. Ltd.) was charged and stirred until it was completely melted. Subsequently, 3.5 g of an anionic surfactant sodium dodecyl sulfate (Shinorine ® 90TK-T manufactured by New Japan Chemical CO., Ltd.) was charged and stirred
15 until it was completely melted.

Subsequently, 22.0 g of the aqueous silica sol produced in Synthesis Example 3 was charged. Subsequently, 21.4 g of a product of polyoxyethylene styrenated phenyl ether (NOIGEN ® EA-157 manufactured by DKS Co. Ltd.) with HLB = 14.3 diluted with pure water
20 to contain 70% of active ingredients was charged as a nonionic surfactant and then stirred for 1 hour to produce a chemical fluid of Example 7.

A brine test sample (a) was prepared according to the high temperature and salt resistance evaluation-1 and held at 100°C for 60 hours. After that, the sample was taken out to evaluate the
25 resistance to high temperature and salt.

Example 8

In a 300-ml styrene container, a stir bar was put, and 99.6 g of pure water was charged. With stirring with a magnetic stirrer, 3.5 g of an anionic surfactant sodium α -olefin sulfonate (NEOGEN ® AO-90 manufactured by DKS Co. Ltd.) was charged and stirred until it was
30 completely melted. Subsequently, 3.5 g of an anionic surfactant sodium dodecyl sulfate

(Shinorine ® 90TK-T manufactured by New Japan Chemical CO., Ltd.) was charged and stirred until it was completely melted.

Subsequently, 22.0 g of the aqueous silica sol produced in Synthesis Example 3 was
5 charged. Subsequently, 21.4 g of a product of polyoxyethylene styrenated phenyl ether
(NOIGEN ® EA-157 manufactured by DKS Co. Ltd.) with HLB = 14.3 diluted with pure water
to contain 70% of active ingredients was charged as a nonionic surfactant and then stirred for 1
hour to produce a chemical fluid of Example 8.

10 A brine test sample (b) was prepared according to the high temperature and salt resistance
evaluation-2 and held at 100°C for 60 hours. After that, the sample was taken out to evaluate the
resistance to high temperature and salt.

Example 9

15 In a 300-ml styrene container, a stir bar was put, and 99.6 g of pure water was charged.
With stirring with a magnetic stirrer, 3.5 g of an anionic surfactant sodium α -olefin sulfonate
(NEOGEN ® AO-90 manufactured by DKS Co. Ltd.) was charged and stirred until it was
completely melted. Subsequently, 3.5 g of an anionic surfactant sodium dodecyl sulfate
(Shinorine ® 90TK-T manufactured by New Japan Chemical CO., Ltd.) was charged and stirred
20 until it was completely melted.

Subsequently, 22.0 g of the aqueous silica sol surface-treated with the silane compound
produced in Synthesis Example 4 was charged. Subsequently, 21.4 g of a product of
polyoxyethylene styrenated phenyl ether (manufactured by DKS Co. Ltd. NOIGEN ® EA-157)
25 with HLB = 14.3 diluted with pure water to contain 70% of active ingredients was charged as a
nonionic surfactant and then stirred for 1 hour to produce a chemical fluid of Example 9.

A seawater test sample was prepared according to the high temperature and salt
resistance evaluation-3 and held at 100°C for 60 hours. After that, the sample was taken out to
30 evaluate the resistance to high temperature and salt.

Example 10

In a 300-ml styrene container, a stir bar was put, and 99.6 g of pure water was charged. With stirring with a magnetic stirrer, 3.5 g of an anionic surfactant sodium α -olefin sulfonate (NEOGEN[®] AO-90 manufactured by DKS Co. Ltd.) was charged and stirred until it was completely melted. Subsequently, 3.5 g of an anionic surfactant sodium dodecyl sulfate (Shinorine[®] 90TK-T manufactured by New Japan Chemical CO., Ltd.) was charged and stirred until it was completely melted.

Subsequently, 22.0 g of the aqueous silica sol surface-treated with the silane compound produced in Synthesis Example 3 was charged. Subsequently, 15.2 g of polyoxyethylene tridecyl ether (NOIGEN[®] TDS-90 manufactured by DKS Co. Ltd.) with HLB = 13.6 was charged as a nonionic surfactant and then stirred for 1 hour to produce a chemical fluid of Example 10.

A brine test sample (a) was prepared according to the high temperature and salt resistance evaluation-1 and held at 100°C for 30 hours. After that, the sample was taken out to evaluate the resistance to high temperature and salt.

Example 11

In a 300-ml styrene container, a stir bar was put, and 99.6 g of pure water was charged. With stirring with a magnetic stirrer, 3.5 g of an anionic surfactant sodium α -olefin sulfonate (NEOGEN[®] AO-90 manufactured by DKS Co. Ltd.) was charged and stirred until it was completely melted. Subsequently, 3.5 g of an anionic surfactant sodium dodecyl sulfate (Shinorine[®] 90TK-T manufactured by New Japan Chemical CO., Ltd.) was charged and stirred until it was completely melted.

Subsequently, 22.0 g of the aqueous silica sol surface-treated with the silane compound produced in Synthesis Example 4 was charged. Subsequently, 21.4 g of a product of polyoxyethylene styrenated phenyl ether (manufactured by DKS Co. Ltd. NOIGEN[®] EA-157) with HLB = 14.3 diluted with pure water to contain 70% of active ingredients was charged as a nonionic surfactant and then stirred for 1 hour to produce a chemical fluid of

Example 11.

A brine test sample (b) was prepared according to the high temperature and salt resistance evaluation-2 and held at 100°C for 60 hours. After that, the sample was taken out to evaluate the
5 resistance to high temperature and salt.

Example 12

In a 300-ml styrene container, a stir bar was put, and 48.8 g of pure water was charged. With stirring with a magnetic stirrer, 3.5 g of an anionic surfactant sodium α -olefin sulfonate
10 (NEOGEN® AO-90 manufactured by DKS Co. Ltd.) was charged and stirred until it was completely melted. Subsequently, 3.5 g of an anionic surfactant sodium dodecyl sulfate (Shinorine® 90TK-T manufactured by New Japan Chemical CO., Ltd.) was charged and stirred until it was completely melted.

15 Subsequently, 72.8 g of the aqueous silica sol surface-treated with the silane compound produced in Synthesis Example 4 was charged. Subsequently, 21.4 g of a product of polyoxyethylene styrenated phenyl ether (manufactured by DKS Co. Ltd. NOIGEN® EA-157) with HLB = 14.3 diluted with pure water to contain 70% of active ingredients was charged as a nonionic surfactant and then stirred for 1 hour to produce a chemical fluid of Example 12.

20

A seawater test sample was prepared according to the high temperature and salt resistance evaluation-3 and held at 100°C for 60 hours. After that, the sample was taken out to evaluate the resistance to high temperature and salt.

25 Example 13

In a 300-ml styrene container, a stir bar was put and 6.4 g of pure water and 131.1 g of the aqueous silica sol surface-treated with the silane compound produced in Synthesis Example 4 were charged and stirred with a magnetic stirrer. With stirring with a magnetic stirrer, 3.5 g of
30 an anionic surfactant sodium α -olefin sulfonate (LIPOLAN® LB-440 manufactured by Lion Specialty Chemicals Co. Ltd., active ingredients: 36.3%) was charged and stirred. Subsequently, 1.3 g of an anionic surfactant sodium dodecyl sulfate (Shinorine® 90TK-T manufactured by

New Japan Chemical CO., Ltd.) was charged and stirred until it was completely melted. Then, 7.7 g of a product of polyoxyethylene styrenated phenyl ether (manufactured by DKS Co. Ltd. NOIGEN ® EA-157) with HLB = 14.3 diluted with pure water to contain 70% of active ingredients was charged as a nonionic surfactant and then stirred for 1 hour to produce a
5 chemical fluid of Example 13.

A seawater test sample was prepared according to the high temperature and salt resistance evaluation-3 and held at 100°C for 60 hours. After that, the sample was taken out to evaluate the resistance to high temperature and salt.

10

Example 14

In a 300-ml styrene container, a stir bar was put and 14.7 g of pure water and 131.1 g of the aqueous silica sol surface-treated with the silane compound produced in Synthesis Example 4 were charged and stirred with a magnetic stirrer. With stirring with a magnetic stirrer, 1.2 g of
15 an anionic surfactant sodium α -olefin sulfonate (LIPOLAN ® LB-440 manufactured by Lion Specialty Chemicals Co. Ltd., active ingredients: 36.3%) was charged and stirred. Subsequently, 0.45 g of an anionic surfactant sodium dodecyl sulfate (Shinorine ® 90TK-T manufactured by New Japan Chemical CO., Ltd.) was charged and stirred until it was completely melted. Then, 2.6 g of a product of polyoxyethylene styrenated phenyl ether (manufactured by DKS Co. Ltd.
20 NOIGEN ® EA-157) with HLB = 14.3 diluted with pure water to contain 70% of active ingredients was charged as a nonionic surfactant and then stirred for 1 hour to produce a chemical fluid of Example 14.

A seawater test sample was prepared according to the high temperature and salt
25 resistance evaluation-3 and held at 100°C for 60 hours. After that, the sample was taken out to evaluate the resistance to high temperature and salt.

Example 15

In a 300-ml styrene container, a stir bar was put and 15.5 g of pure water and 131.1 g of
30 the aqueous silica sol surface-treated with the silane compound produced in Synthesis Example 4 were charged and stirred with a magnetic stirrer. With stirring with a magnetic stirrer, 1.2 g of

an anionic surfactant sodium α -olefin sulfonate (LIPOLAN® LB-440 manufactured by Lion Specialty Chemicals Co. Ltd., active ingredients: 36.3%) was charged and stirred. Subsequently, 0.45 g of an anionic surfactant sodium dodecyl sulfate (Shinorine® 90TK-T manufactured by New Japan Chemical CO., Ltd.) was charged and stirred until it was completely melted. Then,
5 1.8 g of polyoxyethylene styrenated phenyl ether (manufactured by DKS Co. Ltd. NOIGEN® EA-127) with HLB = 11.7 was charged as a nonionic surfactant and then stirred for 1 hour to produce a chemical fluid of Example 15.

A seawater test sample was prepared according to the high temperature and salt
10 resistance evaluation-3 and held at 100°C for 60 hours. After that, the sample was taken out to evaluate the resistance to high temperature and salt.

Example 16

In a 300-ml styrene container, a stir bar was put and 14.0 g of pure water and 131.1 g of
15 the aqueous silica sol surface-treated with the silane compound produced in Synthesis Example 4 were charged and stirred with a magnetic stirrer. With stirring with a magnetic stirrer, 1.2 g of an anionic surfactant sodium α -olefin sulfonate (LIPOLAN® LB-440 manufactured by Lion Specialty Chemicals Co. Ltd., active ingredients: 36.3%) was charged and stirred. Subsequently, 0.45 g of an anionic surfactant sodium dodecyl sulfate (Shinorine® 90TK-T manufactured by
20 New Japan Chemical CO., Ltd.) was charged and stirred until it was completely melted. Then, 3.3 g of polyoxyethylene styrenated phenyl ether (manufactured by DKS Co. Ltd. NOIGEN® EA-207D, active ingredients: 55%) with HLB = 18.7 was charged as a nonionic surfactant and then stirred for 1 hour to produce a chemical fluid of Example 16.

25 A seawater test sample was prepared according to the high temperature and salt resistance evaluation-3 and held at 100°C for 60 hours. After that, the sample was taken out to evaluate the resistance to high temperature and salt.

Example 17

30 In a 300-ml styrene container, a stir bar was put, and 90.1 g of pure water was charged. With stirring with a magnetic stirrer, 3.5 g of an anionic surfactant sodium α -olefin sulfonate

(NEOGEN ® AO-90 manufactured by DKS Co. Ltd.) was charged and stirred until it was completely melted. Subsequently, 3.5 g of an anionic surfactant sodium dodecyl sulfate (Shinorine ® 90TK-T manufactured by New Japan Chemical CO., Ltd.) was charged and stirred until it was completely melted.

5

Subsequently, 31.5 g of the aqueous silica sol produced in Synthesis Example 5 was charged. Subsequently, 21.4 g of polyoxyethylene styrenated phenyl ether (manufactured by DKS Co. Ltd. NOIGEN ® EA-157) with HLB = 14.3 was charged as a nonionic surfactant and then stirred for 1 hour to produce a chemical fluid of Example 17.

10

A brine test sample (a) was prepared according to the high temperature and salt resistance evaluation-1 and held at 100°C for 60 hours. After that, the sample was taken out to evaluate the resistance to high temperature and salt.

15

Example 18

In a 300-ml styrene container, a stir bar was put and 18.4 g of pure water and 127.4 g of the aqueous silica sol surface-treated with the silane compound produced in Synthesis Example 6 were charged and stirred with a magnetic stirrer. With stirring with a magnetic stirrer, 1.2 g of an anionic surfactant sodium α -olefin sulfonate (LIPOLAN ® LB-440 manufactured by Lion Specialty Chemicals Co. Ltd., active ingredients: 36.3%) was charged and stirred. Subsequently, 0.45 g of an anionic surfactant sodium dodecyl sulfate (Shinorine ® 90TK-T manufactured by New Japan Chemical CO., Ltd.) was charged and stirred until it was completely melted. Then, 2.6 g of a product of polyoxyethylene styrenated phenyl ether (manufactured by DKS Co. Ltd. NOIGEN ® EA-157) with HLB = 14.3 diluted with pure water to contain 70% of active ingredients was charged as a nonionic surfactant and then stirred for 1 hour to produce a chemical fluid of Example 18.

25

A seawater test sample was prepared according to the high temperature and salt resistance evaluation-3 and held at 100°C for 30 hours. After that, the sample was taken out to evaluate the resistance to high temperature and salt.

30

Example 19

In a 300-ml styrene container, a stir bar was put and 15.3 g of pure water and 130.5 g of the aqueous silica sol surface-treated with the silane compound produced in Synthesis Example 7 were charged and stirred with a magnetic stirrer. With stirring with a magnetic stirrer, 1.2 g of
5 an anionic surfactant sodium α -olefin sulfonate (LIPOLAN® LB-440 manufactured by Lion Specialty Chemicals Co. Ltd., active ingredients: 36.3%) was charged and stirred. Subsequently, 0.4 g of an anionic surfactant sodium dodecyl sulfate (Shinorine® 90TK-T manufactured by New Japan Chemical CO., Ltd.) was charged and stirred until it was completely melted. Then, 2.6 g of a product of polyoxyethylene styrenated phenyl ether (manufactured by DKS Co. Ltd.
10 NOIGEN® EA-157) with HLB = 14.3 diluted with pure water to contain 70% of active ingredients was charged as a nonionic surfactant and then stirred for 1 hour to produce a chemical fluid of Example 19.

A seawater test sample was prepared according to the high temperature and salt
15 resistance evaluation-3 and held at 100°C for 30 hours. After that, the sample was taken out to evaluate the resistance to high temperature and salt.

Example 20

A chemical fluid of Example 20 was produced through the similar operation as in
20 Example 13.

A seawater test sample was prepared according to the high temperature and salt
resistance evaluation-4 and held at 100°C for 75 days (1800 hours). After that, the sample was
taken out to evaluate the resistance to high temperature and salt.
25

Example 21

A chemical fluid of Example 21 was produced through the similar operation as in
Example 14.

A seawater test sample was prepared according to the high temperature and salt resistance evaluation-4 and held at 100°C for 75 days (1800 hours). After that, the sample was taken out to evaluate the resistance to high temperature and salt.

5 Reference Example 1

A chemical fluid of Reference Example 1 (comprising no silane compound) was produced through the same operation as in Example 1 except that 22.0 g of an aqueous silica sol (SNOWTEX ® ST-O manufactured by Nissan Chemical Corporation) was charged instead of the aqueous silica sol produced in Synthesis Example 2.

10 A brine test sample (a) was prepared according to the high temperature and salt resistance evaluation-1 and held at room temperature for 7 days. After that, the sample was taken out to evaluate the salt resistance.

 Reference Example 2

15 A chemical fluid of Reference Example 2 (mass ratio of silane compound to silica: 0.09) was produced through the same operation as in Example 1 except that 22.0 g of the aqueous silica sol produced in Synthesis Example 1 was charged instead of the aqueous silica sol produced in Synthesis Example 2.

20 A brine test sample (a) was prepared according to the high temperature and salt resistance evaluation-1 and held at room temperature for 7 days. After that, the sample was taken out to evaluate the salt resistance.

 Reference Example 3

25 A chemical fluid of Reference Example 3 (comprising no nonionic surfactant) was produced through the same operation as in Example 1 except that the amount of polyoxyethylene nonylphenyl ether (reagent Tergitol ® NP-9 manufactured by Sigma-Aldrich Corporation) with HLB = 13.0 charged as a nonionic surfactant was 0 g.

30 A brine test sample (a) was prepared according to the high temperature and salt resistance evaluation-1, but it became cloudy immediately after preparation, and white gel was precipitated.

Reference Example 4

A chemical fluid of Reference Example 4 (comprising nonionic surfactant having a low HLB value) was produced through the same operation as in Example 4 except that the amount of polyoxyethylene styrenated phenyl ether (manufactured by DKS Co. Ltd. NOIGEN ® EA-017) with HLB = 2.7 charged as a nonionic surfactant was 15.0 g.

The chemical fluid prepared as above caused complete two-phase separation of an aqueous phase composed of the aqueous silica sol and the water-soluble anionic surfactant and an oil phase composed of the nonionic surfactant. Therefore, the evaluation of resistance to high temperature and salt could not be carried out.

Comparative Example 1

In a 300-ml styrene container, a stir bar was put, and 99.6 g of pure water was charged. With stirring with a magnetic stirrer, 6.8 g of an anionic surfactant sodium α -olefin sulfonate (NEOGEN ® AO-90 manufactured by DKS Co. Ltd.) was charged and stirred until it was completely melted.

Subsequently, 22.0 g of the aqueous silica sol produced in Synthesis Example 3 was charged. Subsequently, 21.4 g of a product of polyoxyethylene styrenated phenyl ether (NOIGEN ® EA-157 manufactured by DKS Co. Ltd.) with HLB = 14.3 diluted with pure water to contain 70% of active ingredients was charged as a nonionic surfactant and then stirred for 1 hour to produce a chemical fluid of Comparative Example 1 (comprising only one anionic surfactant).

A brine test sample (b) was prepared according to the high temperature and salt resistance evaluation-2 and held at 100°C for 60 hours. After that, the sample was taken out to evaluate the resistance to high temperature and salt.

Comparative Example 2

In a 300-ml styrene container, a stir bar was put, and 99.6 g of pure water was charged. With stirring with a magnetic stirrer, 6.8 g of an anionic surfactant sodium dodecyl sulfate (Shinorine ® 90TK-T manufactured by New Japan Chemical CO., Ltd.) was charged and stirred
5 until it was completely melted.

Subsequently, 22.0 g of the aqueous silica sol produced in Synthesis Example 3 was charged. Subsequently, 21.4 g of a product of polyoxyethylene styrenated phenyl ether (NOIGEN ® EA-157 manufactured by DKS Co. Ltd.) with HLB = 14.3 diluted with pure water
10 to contain 70% of active ingredients was charged as a nonionic surfactant and then stirred for 1 hour to produce a chemical fluid of Comparative Example 2 (comprising only one anionic surfactant).

A brine test sample (b) was prepared according to the high temperature and salt resistance
15 evaluation-2 and held at 100°C for 60 hours. After that, the sample was taken out to evaluate the resistance to high temperature and salt.

Comparative Example 3

In a 300-ml styrene container, a stir bar was put, and 128.0 g of pure water was charged.
20 With stirring with a magnetic stirrer, 22.0 g of the aqueous silica sol produced in Synthesis Example 4 was charged and stirred until it to produce a chemical fluid of Comparative Example 3 (comprising only silane/silica and comprising no surfactant).

A brine test sample (b) was prepared according to the high temperature and salt resistance
25 evaluation-2 and held at 100°C for 60 hours. After that, the sample was taken out to evaluate the resistance to high temperature and salt.

Comparative Example 4

In a 300-ml styrene container, a stir bar was put, and 121.6 g of pure water was charged.
30 With stirring with a magnetic stirrer, 3.5 g of an anionic surfactant sodium α -olefin sulfonate (NEOGEN ® AO-90 manufactured by DKS Co. Ltd.) was charged and stirred until it was

completely melted. Subsequently, 3.5 g of an anionic surfactant sodium dodecyl sulfate (Shinorine ® 90TK-T manufactured by New Japan Chemical CO., Ltd.) was charged and stirred until it was completely melted. Then, 21.4 g of a product of polyoxyethylene styrenated phenyl ether (NOIGEN ® EA-157 manufactured by DKS Co. Ltd.) with HLB = 14.3 diluted with pure water to contain 70% of active ingredients was charged as a nonionic surfactant and then stirred for 1 hour to produce a chemical fluid of Comparative Example 4 (comprising only surfactant and comprising no silica/silane).

Choice of Proppant

In an embodiment, the proppant is sand. This is the cheapest, most abundant, and most used. The common forms of proppant sand are 20 mesh, 40mesh, 70mesh, 100mesh, and combinations of these such as the common combinations 100/40mesh, 70/40mesh, and 40/20 mesh. There are many commercially available sources of sand suitable for use as a proppant.

Coating method of Proppant

4kg of commercially available proppant sand of 70/40 mesh size was placed into a 4L Nalgene container and covered with treatment fluid comprising colloidal silica particles. The container was then sealed, and the sand/fluid mixture was mixed by shaking allowed to stand at room temperature for 12 hours to effect nanoparticle deposition onto proppant sand surfaces. The mixture was then poured into a 12" x 24" glass baking dish and placed in a 100C oven for a period of 24 hours until the mixture was dried. Samples of coated proppant sand and uncoated proppant sand were submitted to a 3rd party laboratory for conductivity testing.

What is Claimed:

1. A method of increasing production from a hydrocarbon containing formation by adding a proppant to the formation, characterized in that a treatment fluid comprising a colloidal silica nanoparticle is added to the formation before, during or after the time the proppant is added
5 to the formation.
2. The method of Claim 1 characterized in that the treatment fluid comprising the colloidal silica nanoparticles is added to the formation before the time the proppant is added to the formation.
3. The method of Claim 1 characterized in that the treatment fluid comprising the
10 colloidal silica nanoparticles is added to the formation during the time the proppant is added to the formation.
4. The method of Claim 1 characterized in that the treatment fluid comprising the colloidal silica nanoparticles is added to the formation after the time the proppant is added to the formation.
- 15 5. The method of Claim 1 characterized in that the treatment fluid comprising the colloidal silica nanoparticles is added to the formation before and during the time the proppant is added to the formation.
6. The method of Claim 1 characterized in that the treatment fluid comprising the colloidal silica nanoparticles is added to the formation during and after the time the proppant is
20 added to the formation.
7. The method of Claim 1 characterized in that the treatment fluid comprising the colloidal silica nanoparticles is added to the formation before and after the time the proppant is added to the formation.
8. The method of any one of Claims 1-7, wherein the treatment fluid comprising a
25 colloidal silica nanoparticle is a crude oil recovery chemical solution comprising a silane

compound, an aqueous silica sol having an average particle size of from about 3 nm to about 200 nm.

9. The method of Claim 8, wherein the aqueous silica sol comprises silica particles in which at least a part of the silane compound is bonded on the surface of at least a part of the silica particles in the sol.

10. The method of Claim 8 of 9, wherein the silane compound is at least one compound selected from the group consisting of a silane coupling agent having at least one organic functional group selected from the group consisting of a vinyl group, an ether group, an epoxy group, a styryl group, a methacryl group, an acryl group, an amino group, an isocyanurate group, an alkoxy silane group, a silazane group and a siloxane group.

11. The method of any one of Claims 8-10, wherein the aqueous silica sol is present in an amount of from about 0.1 % by mass to about 20 % by mass, based on the total mass of the crude oil recovery chemical solution, in terms of silica solid content.

12. The method of any one of Claims 1-11, wherein the proppant is sand.

13. The method of Claim 12, wherein the sand is 20 mesh, 40 mesh, 70 mesh, or 100 mesh.

14. The method of Claim 12, wherein the sand is a combination of 100 mesh and 40 mesh, a combination of 70 mesh and 40 mesh, or a combination of 40 mesh and 20 mesh.

15. The method of Claim 1, wherein the proppant is coated with the treatment fluid comprising colloidal silica nanoparticles.

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2019/059417

A. CLASSIFICATION OF SUBJECT MATTER
INV. C09K8/80 C09K8/84
ADD.
According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED
Minimum documentation searched (classification system followed by classification symbols)
C09K
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)
EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 2018/004560 A1 (HALLIBURTON ENERGY SERVICES INC [US]) 4 January 2018 (2018-01-04) claims paragraph [0030]	1-15
X	US 2010/147515 A1 (HUGHES TREVOR LLOYD [GB] ET AL) 17 June 2010 (2010-06-17) cited in the application claims	1-15
X	WO 2014/204709 A2 (PRAXAIR TECHNOLOGY INC [US]) 24 December 2014 (2014-12-24) claims paragraph [0013] - paragraph [0014]	1-7, 12-15
	-/--	

Further documents are listed in the continuation of Box C. See patent family annex.

* Special categories of cited documents :

<p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier application or patent but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p>	<p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</p> <p>"&" document member of the same patent family</p>
---	---

Date of the actual completion of the international search 27 January 2020	Date of mailing of the international search report 06/02/2020
---	---

Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer Zimpfer, Emmanuel
--	--

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2019/059417

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2014/008067 A1 (RODDY CRAIG WAYNE [US] ET AL) 9 January 2014 (2014-01-09) claims	1,3

A	WO 2018/187563 A1 (NISSAN CHEMICAL AMERICA CORP [US]) 11 October 2018 (2018-10-11) claims	1-15

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No PCT/US2019/059417

Patent document cited in search report	A1	Publication date	Patent family member(s)	Publication date
WO 2018004560	A1	04-01-2018	CA 3014599 A1 US 2019345375 A1 WO 2018004560 A1	04-01-2018 14-11-2019 04-01-2018

US 2010147515	A1	17-06-2010	CA 2746684 A1 US 2010147515 A1 WO 2010070600 A1	24-06-2010 17-06-2010 24-06-2010

WO 2014204709	A2	24-12-2014	NONE	

US 2014008067	A1	09-01-2014	US 2014008067 A1 US 2014221257 A1	09-01-2014 07-08-2014

WO 2018187563	A1	11-10-2018	AU 2018250252 A1 AU 2018250262 A1 CA 3058469 A1 CA 3058470 A1 CN 110678531 A CN 110691835 A EP 3607023 A1 EP 3607024 A1 US 2018291261 A1 US 2019225871 A1 US 2019382645 A1 WO 2018187550 A1 WO 2018187563 A1	17-10-2019 10-10-2019 11-10-2018 11-10-2018 10-01-2020 14-01-2020 12-02-2020 12-02-2020 11-10-2018 25-07-2019 19-12-2019 11-10-2018 11-10-2018
