

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
14 February 2008 (14.02.2008)

PCT

(10) International Publication Number  
**WO 2008/017864 A1**

(51) International Patent Classification:  
*B42D 15/10* (2006.01) *B42D 15/00* (2006.01)

(74) Agent: GILL JENNINGS & EVERY LLP; Broadgate House, 7 Eldon Street, London EC2M 7LH (GB).

(21) International Application Number:  
PCT/GB2007/003057

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(22) International Filing Date: 10 August 2007 (10.08.2007)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
0615921.4 10 August 2006 (10.08.2006) GB

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).


(71) Applicant (for all designated States except US): DE LA RUE INTERNATIONAL LIMITED [GB/GB]; De La Rue House, Jays Close, Viables, Basingstoke, Hampshire RG22 4BS (GB).

(72) Inventor; and

(75) Inventor/Applicant (for US only): WHITEMAN, Robert [GB/GB]; 144 Hemdean Road, Caversham, Reading, Berkshire RG4 7ST (GB).

Published:  
— with international search report

(54) Title: PHOTONIC CRYSTAL SECURITY DEVICE



(57) Abstract: An optically variable security device comprises a photonic crystal which, upon receipt of incident light, generates a first optical effect, and which, when the device is subjected to an external stimulus, generates a second optical effect that is different from the first optical effect. At least one of the first and second optical effects is an optically variable effect observable over a set of directions. The optically variable effect is caused by the light being selectively reflected or transmitted by the crystal.



WO 2008/017864 A1

## Photonic Crystal Security Device

The present invention relates to improvements in security devices that can be used in varying shapes and sizes for various authenticating or security applications.

5 Security documents such as banknotes now frequently carry optically variable devices that exhibit an angularly dependent coloured reflection. This has been motivated by the progress in the fields of computer-based desktop publishing and scanning, which renders conventional security print technologies such as intaglio and offset printing more prone to attempts to  
10 replicate or mimic. It is well known in the prior art to use liquid crystal materials or thin film interference structures to generate such angularly dependent coloured reflection. Examples of liquid crystal based security devices are described in EP0435029, WO03061980, and EP1156934 and examples of security devices utilising thin film interference structures are  
15 described in US4186943 and US20050029800.

The planar nature of liquid crystal films and thin film interference structures results in the observed angularly dependent coloured reflection exhibiting limited spatial variation for example a simple red to green colour change on tilting the security device away from normal incidence.

20 Photonic crystals are structured optical materials in which the refractive index varies periodically in two or preferably three dimensions. These materials exhibit a range of interesting optical effects when subject to electromagnetic radiation of a wavelength comparable to the spatial modulation of the refractive index. Bragg reflection may occur over a range of  
25 wavelengths that depends on the direction of incidence/propagation and the periodicity of refractive index variation. This gives rise to photonic 'energy gaps' that are analogous to the electronic band gaps in semiconductors. Typically, electromagnetic waves within a certain frequency range cannot propagate in particular directions within the crystal, and incident  
30 electromagnetic radiation at these wavelengths is consequently reflected. It is

the presence of such partial photonic band gaps that gives rise to the shimmering colours observed in opal gemstones.

In general there is a complex dependence on the wavelength, direction of propagation and polarisation that dictates which electromagnetic waves  
5 may propagate within the photonic crystal and those that are otherwise reflected. However, if the modulation in refractive index is sufficiently strong, propagation of certain frequencies can be forbidden for any crystalline direction, and a complete photonic band gap arises. In this case light is prevented from propagating within the crystal in any direction, and the  
10 material acts as an ideal reflector such that all light of a wavelength within the band gap range is perfectly reflected irrespective of the incident direction.

There exists two well-documented methods of fabricating structures with the necessary highly ordered variation in refractive index - microfabrication and self-assembly. Due to the complexity of microfabrication  
15 considerable effort has been devoted to investigating self-assembling systems comprised of submicron three-dimensional arrays of dielectric spheres. Such photonic crystals are formed by allowing a colloidal suspension of identically sized spheres to settle slowly under the influence of gravity or by the application of an external force such that spheres naturally order. One well-  
20 known example is the fabrication of synthetic opal structures where uniformly sized sub-micron silica spheres are organised through a sedimentation process into a face-centred cubic crystal structure.

Further enhancements to this technique have been developed such that the synthetic opal acts as a precursor or template to further customise the  
25 structure. It has been shown that it is possible to use such systems as templates to realise materials known as inverted opals. Here, the voids between the silica spheres are first filled with materials of a high refractive index, and the silica is then dissolved by chemical means to give a material that consists of air spheres separated by a uniform matrix of the high  
30 refractive index material.

The use of photonic crystals to generate angular dependent coloured reflection is described in WO03062900 and US20050228072. The optical properties of photonic crystals can be engineered and varied to a greater extent than the optical properties of planar liquid crystal and thin film interference devices. Firstly the angular and wavelength dependence of the reflected light can be more easily controlled by varying the crystal lattice structure by either simply adjusting the sphere size, or the sphere separation. Similarly, selected allowed and disallowed reflections/transmissions may be engineered or enhanced by introducing structural defects into the lattice or by introducing nanoparticles into the structure. This in principle gives freedom to modify and engineer the band structure and hence the wavelength and spatial dependence of the reflectivity.

The use of photonic crystals in security devices has been limited and in the prior art their use is limited to a simple angular dependent coloured reflection the authenticator observes by tilting the device. There is also no teaching in the prior art on how to incorporate such devices into security documents such that the additional optical effects possible from photonic crystals, compared to other well known dichroic materials, can be used to validate the document. The object of the current invention is to improve the security of the devices described in the prior art.

In accordance with a first aspect of the invention we provide an optically variable security device comprising a photonic crystal which, upon receipt of incident light, generates a first optical effect, and which, when the device is subjected to an external stimulus, generates a second optical effect that is different from the first optical effect, wherein at least one of the first and second optical effects is an optically variable effect observable over a set of directions and caused by the light being selectively reflected or transmitted by the crystal.

We have realised that photonic crystals which have modifiable properties as a result of an external stimulus provide great advantage in the field of optically variable security devices.

One optical effect in each respective case may produce a non-optically variable effect, such as reflection of the incident light at all wavelengths. Typically however, the said optical effect generated is a second optically variable effect that is different from the first.

5           The second optical effect is preferably observable over the first set of directions, a subset of such directions or a larger set of directions comprising the first set.

          The term "observable" is intended to include observation by the naked eye and/or using appropriate instrumentation. Thus the effects may be partly  
10 or wholly in the non-visible spectrum (such as UV or IR), although they may be observed nevertheless using appropriate detectors.

          Typically the or each optically variable effect is dependent upon the crystal orientation with respect to the incident light and the or each optically variable effect may also be a function of the viewing angle with respect to the  
15 crystal.

          The light may comprise a visible and/or non-visible light, therefore including for example ultraviolet and infra-red light. Broad or narrow wavelength bands may be used. When the light is produced by a white light (broad wavelength band) source, preferably the effect observed is a colour  
20 effect.

          Preferably, the optically variable security device therefore comprises a photonic crystal that exhibits at least one angular dependent coloured reflection at ambient conditions and a second different angular dependent coloured reflection when a specified external stimulus is applied.

25           The change of the optical effect by the application of an external stimulus, preferably provided directly by the authenticator, provides an overt interactive characteristic to the device thereby increasing the memorability of the security feature to the general public. The device is therefore straightforward for the member of the public to authenticate but very difficult to

counterfeit due to the requirement to replicate the change in the optical effect when the external stimulus is applied.

The external stimulus may take a number of forms either alone or in combination, these including mechanical, thermal, chemical, electrical,  
5 magnetic, electromagnetic or ultrasonic stimuli.

The difference between the optical response of the crystal in the presence and absence of the external stimulus is preferably of sufficient magnitude to be detectable visually by a human observer and/or is machine-readable. Preferably therefore the first optically variable effect is a first  
10 angularly dependent colour effect and the second optically variable effect is a second angularly dependent colour effect, that is different from the first. In this way, the colour observed is a different function of the viewing angle when viewing in the presence and absence of the external stimulus.

The abovementioned effects may be typically reflective effects,  
15 although transmissive effects are also contemplated. Reflected light in the context of the present invention includes both specularly reflected light and scattered light.

Preferably the stimulus causes a modification in the periodic spacing of one or more refractive entities within the crystal structure. In one embodiment  
20 the modification is the direct result of deformation due to an applied stress, but in alternative embodiments there is no direct mechanical deformation and the modification is induced indirectly for example in the case of a thermal, chemical, electrical, magnetic, electromagnetic or ultrasonic stimulus.

In some cases, the stimulus causes a modification in the refractive  
25 index of one or more refractive entities within the crystal structure. For example, one or more of the entities within the crystal structure may exhibit electro-optical, magneto-optical or chemical effects wherein the change in the crystal structure is primarily one relating to a refractive index rather than spacing of the various entities from which the crystal structure is comprised. In  
30 chemical terms, this might for example result from the uptake of water.

However a combination of this with mechanical modification of the periodic spacing within the crystal is also envisaged.

The photonic crystal may be selected such that the effect of the stimulus upon the crystal is reversible upon removal of the stimulus or upon  
5 application of an opposite stimulus. The crystal lattice spacing can therefore be reversibly modified, for example contracted or expanded, in some cases elastically, by applying an external stimulus.

One preferred example is reversibly modifying the photonic crystal lattice spacing by mechanically stretching, bending, poking or pressing the  
10 material. As a result the characteristics of the full or partial photonic band gap that derive from the periodicity of the photonic crystal lattice are altered, and hence the reflective and transmissive properties can be engineered to respond to a mechanical stimulus. Suitable photonic crystals for use with a stimulus of mechanical deformation are those which have a flexible,  
15 elastomeric matrix and are known as elastic photonic crystals.

Elastic photonic crystals typically comprise polymeric materials for both the matrix and the spheres. Typical examples of elastic photonic crystals suitable for the current invention are described in US20040131799, US20050228072, US20040253443 and US6337131. The crystal may be  
20 formed from spheres of the first material and a matrix of a second material wherein each material has a different respective refractive index. The matrix therefore may be readily deformable by taking the form of an elastomeric material.

Materials suitable for forming the spheres are preferably single  
25 polymer or copolymer materials. Typical examples include both polymers and copolymers of polymerisable unsaturated monomers and polycondensates and copolycondensates of monomers containing at least two reactive groups, such as, for example, high-molecular-weight aliphatic, aliphatic/aromatic or fully aromatic polyesters, polyamides, polycarbonates, polyureas and  
30 polyurethanes, but also amino and phenolic resins, such as, for example,

melamine-formaldehyde, urea-formaldehyde and phenol-formaldehyde condensates, are suitable.

Materials suitable for forming an elastomeric matrix are addition polymers having a low glass transition temperature. Examples include  
5 addition polymers and copolymers of polymerizable unsaturated monomers and also of the polycondensates and copolycondensates of monomers having two or more reactive groups, e.g., high molecular weight aliphatic, aliphatic-aromatic or wholly aromatic polyesters and polyamides, but also of the amino and phenolic resins, such as melamine-formaldehyde, urea-formaldehyde and  
10 phenol-formaldehyde condensates.

Non-polymeric materials are also envisaged for the spheres and the matrix and they may be inorganic or metallic or a hybrid composite.

Various types of crystals may be used to achieve the present invention, and it should be noted that the term "photonic crystal" is intended to include  
15 quasi-crystals that exhibit this effect, as well as more conventional ordered "non-quasi" photonic crystals.

It is also envisaged that the structural parameters of the photonic crystal may be arranged to be different in different regions of the crystal, so as to effectively generate multiple crystals with different optical properties.  
20 Furthermore, the "crystal" may comprise a plurality of individual crystals.

The photonic crystal may be provided in a number of forms, for example as a self-supporting layer. Alternatively, it may be supported by a substrate or carrier layer to which it is mounted directly or indirectly (through one or more further layers). The substrate or the carrier layer may take the  
25 form of a polymeric layer.

The security device may also comprise one or more further adhesive layers, for example, for bonding the device to a further device and/or security document. Typically one or more of such adhesive layers are provided upon an outer surface of the device.



A scattering layer may also be provided so as to cause scattering of the reflected light from the photonic crystal.

The optically variable security device may further comprise an optically absorbent material provided as one or more layers applied to the device. Such a layer may be provided upon the photonic crystal or indeed the material may be formed within the crystal structure itself. A combination of these is also contemplated. The inclusion of such an absorbent material can be used to enhance the optical effect to an observer, or used to modify the optical effect by the use of for example absorbent materials that are selectively absorbent at the wavelengths of light used. In some examples dyes or inks are used for this purpose.

The optical properties may also be additionally or alternatively further modified or enhanced by the use of nanoparticles positioned within the crystal structure, preferably at interstitial sites. The nanoparticles may be distributed substantially uniformly through the crystal such that each part of the crystal exhibits substantially the same optical effect. Alternatively the nanoparticles may be distributed inhomogeneously through the crystal such that different parts of the crystal exhibit a substantially different optical effect. Thus the nanoparticles may be distributed according to a concentration gradient. The nanoparticles may also be distributed in a number of regions having different concentrations.

The optically variable security device may further comprise a metallised layer. Preferably such a layer is selectively demetallised at a number of locations. In addition the device may further comprise a layer of resist upon the metallised layer. The metallised layer and/or the layer of resist is preferably arranged as indicia. Such layers with or without indicia may be visible from the same side of the photonic crystal that receives the light, or from the reverse side. Transmissive viewing of the layers is also contemplated.

It is also preferred that the device is arranged to be machine-readable. This may be achieved in a number of ways. For example at least one layer of

the device (optionally as a separate layer) or the photonic crystal itself may further comprise machine-readable material. Preferably the machine-readable material is a magnetic material, such as magnetite. The machine-readable material may be responsive to an external stimulus. Furthermore,  
5 when the machine-readable material is formed into a layer, this layer may be transparent.

The optically variable security device may be used in many different applications, for example by attachment to objects of value. Preferably, the security devices are adhered to or substantially contained within a security  
10 document. Such security documents include banknotes, cheques, passports, identity cards, certificates of authenticity, fiscal stamps and other documents for securing value or personal identity.

The security device may therefore be attached to a surface of such a document or it may be embedded within the document so as to provide crystal  
15 surfaces for receiving incident light on one or each of opposing faces of the document. The security device may take various different forms for use with security documents, these including a security thread, a security fibre, a security patch, a security strip, a security stripe or a security foil as non-limiting examples.

20 Preferably the photonic crystal material for use in the current invention is in the form of a film. Production methods for forming films of photonic crystal materials are known in the art. For example films can be made using standard polymer continuous processing techniques such as rolling, calendaring, film blowing or flat-film extrusion as detailed in  
25 US200050228072. In this process the alignment of the spheres occurs under the mechanical force applied by the film forming process. Once the film is formed the matrix is cross-linked to fix the orientation of the spheres. Alternatively a film of photonic crystal material can be made by applying a coating composition comprising the spheres and matrix to a carrier film as  
30 described in US6337131. Once the coating composition has been applied any dispersing or diluting material is removed and the spheres orientate via a

settling process following which the matrix is cross-linked to fix the orientation of the spheres.

Alternatively the photonic crystal material can be used in a powder or pigmented form. The pigments are obtained by forming a film on a carrier layer, detaching the film and grinding it up into a pigment or powder.

The security device may include other additional security features or the device may be overlaid over an additional security feature, one example of which is the selectively demetallised layer discussed above, in order to provide enhanced security. The security device may also be supported upon a transparent layer, for example to allow the surface contacted by the transparent layer to receive or transmit light.

Security threads are now present in many of the world's currencies as well as vouchers, passports, travellers' cheques and other documents. In many cases the thread is provided in a partially embedded or windowed fashion where the thread appears to weave in and out of the paper. One method for producing paper with so-called windowed threads can be found in EP0059056. EP0860298 and WO03095188 describe different approaches for the embedding of wider partially exposed threads into a paper substrate. Wide threads, typically with a width of 2-6mm, are particularly useful as the additional exposed area allows for better use of optically variable devices such as the current invention.

The device could be incorporated into a document such that regions of the device are viewable from both sides of the document. Techniques are known in the art for forming transparent regions in both paper and polymer substrates. For example, WO8300659 describes a polymer banknote formed from a transparent substrate comprising an opacifying coating on both sides of the substrate. The opacifying coating is omitted in localised regions on both sides of the substrate to form a transparent region.

Methods for incorporating a security device such that it is viewable from both sides of a paper document are described in EP1141480 and WO03054297. In the method described in EP1141480 one side of the device

is wholly exposed at one surface of the document in which it is partially embedded, and partially exposed in windows at the other surface of the substrate.

In the case of a stripe or patch the photonic crystal film is preferably  
5 prefabricated on a carrier substrate and transferred to the substrate in a subsequent working step. The photonic crystal film can be applied to the document using an adhesive layer. The adhesive layer is applied either to the photonic crystal film or the surface of the secure document to which the device is to be applied. After transfer the carrier strip can be removed leaving  
10 the photonic crystal film device as the exposed layer or alternatively the carrier layer can remain as part of the structure acting as an outer protective layer.

Following the application of the photonic crystal device the document, such as a banknote, undergoes further standard security printing processes  
15 including one or more of the following; wet or dry lithographic printing, intaglio printing, letterpress printing, flexographic printing, screen-printing, and/or gravure printing. In a preferred example and to increase the effectiveness of the security device against counterfeiting the design of the security device should be linked to the document it is protecting by content and registration to  
20 the designs and identifying information provided on the document.

Furthermore the photonic crystal device may be customised by overprinting or embossing either before or after it is incorporated into the security document. The embossing may comprise a coarse non-diffractive embossing or a diffractive embossing. The device may be arranged to  
25 produce a latent image which is selectively visible according to the viewing angle and/or the application of an external stimulus. The surface of the photonic crystal may be directly embossed to produce raised structures which can be used to form a latent image. Furthermore the device may be arranged to comprise a hologram, optionally using an embossed structure on the  
30 photonic crystal surface, or by providing a diffractive structure in a further metallic layer which may partially overlay the crystal for example.

In examples particularly directed at mechanical deformation so as to produce the optical effect, the security device may be provided as a projection so that it or a part attached to the device may be grasped by a user and deformed (plastically or elastically) so as to apply the external stimulus.

5           Some examples of the invention will now be described with reference to the accompanying drawings, in which:-

Figure 1 shows a security device of a first example incorporated into a security document;

10           Figure 2 shows a second example of a security device for use in a windowed security thread;

Figure 3 shows a security device according to a third example having a polymeric carrier layer;

Figure 4a shows a security device according to a fourth example having demetallised characters;

15           Figure 4b shows a machine-readable fifth example including magnetic material;

Figure 5 shows the incorporation of a security device according to the examples within a transparent region;

20           Figure 6a shows a security device in accordance with an sixth example;

Figure 6b shows a machine-readable seventh example as an alternative of the sixth example;

Figure 7 shows an eighth example with a projecting security device.

25           Figures 8a,8b show front and rear views respectively of an ninth example security device having an elastic photonic crystal;

Figure 8c is a schematic view of the ninth example being deformed in the hand of a user.

Figure 9 shows a cross-section of a tenth example security device comprising two photonic crystals

Figures 10a,b,c show an eleventh example security device when viewed at three different deformation levels (10a, 10b, 10c respectively);

5 Figure 11 shows a twelfth example security device which is further embossed;

Figure 12 shows a thirteenth example security device having red and black absorbing layers;

10 Figure 13 shows the thirteenth example security device applied to a document;

Figure 14 shows a fourteenth example security device having gaps in the photonic crystal and having an absorbing layer;

Figure 15 shows a fifteenth example security device containing nanoparticles;

15 Figure 16 shows a sixteenth example security device for use as a label;

Figure 17 shows the sixteenth example device attached to a substrate;

Figure 18 shows a seventeenth example, analogous to the sixteenth;

20 Figures 19a,b,c show the seventeenth example security device when viewed at three different levels of deformation (19a, 19b, 19c respectively); and,

Figures 20a,b,c show a security device according to an eighteenth example when viewed at three different levels of deformation (20a,20b,20c respectively).

25 Figure 1 shows the security device of the current invention incorporated into a security document as a windowed thread with windows of exposed thread and areas of embedded thread. Figure 2 shows a cross-sectional view of one example of the current invention suitable for application as a windowed

security thread. The device comprises a self-supporting elastic photonic crystal film, onto which is applied a dark absorbing layer. An adhesive layer may be applied to the outer surfaces of the device to improve adherence to the secure document.

5           When the device in Figure 1 is viewed down on the elastic photonic crystal film in reflection under ambient conditions, i.e. prior to the application of an external stimulus, a highly contrasting colour shift effect is observed in the window regions from the photonic crystal layer as the device is tilted. For example the colourshift can be from red, when viewed at a normal angle of  
10 incidence to the plane of substrate, to green when viewed at a specified angle of incidence to the plane of the substrate. On pressing the security device in the exposed window regions, a contraction occurs in the crystal lattice spacing of the elastic photonic crystal perpendicular to the plane of the security device. This contraction modifies the photonic band structure of the crystal and hence  
15 the wavelength and spatial dependence of the reflectivity observed by the authenticator. In this example the contraction of the lattice results in the observed colour moving to a shorter wavelength for example on initial application of the pressure red goes to green and then as the pressure is increased further green goes to blue. An angular dependent colourshift will  
20 also be observed when the device is in its deformed state for example this could be from green to blue as the substrate is tilted in its initial pressed state. On removal of the deformation the photonic crystal layer will revert to its original colour and therefore the authentication process is reversible.

25           The materials used in the elastic photonic crystal film can be selected such that when the pressure is removed the ambient optical properties of the device do not instantly return but instead there is a delay such that the new colour can be easily verified.

30           In an alternative structure to that shown in Figure 2, and illustrated in Figure 3, the security device comprises a polymeric carrier substrate, for example Polyethylene Terephthalate (PET) or Bi-axially Oriented Polypropylene (BOPP), onto which is applied a dark absorbing layer. A layer of elastic photonic crystal material is then applied to the opposite surface of

the carrier film, or alternatively on to the dark absorbing layer. The elastic photonic crystal layer may be formed directly onto the carrier substrate as a coated film or formed as a separate film and then laminated to the carrier substrate. The separate film can be formed as a self-supporting layer, using  
5 for example extrusion, or by coating onto a temporary carrier layer which is then discarded during the lamination process. This is particularly beneficial when the carrier substrate for the security thread comprises additional security features, such as magnetic layers and metallised layers comprising demetallised characters, which may not be suitable to be applied directly to  
10 the photonic crystal layer or which reduce the suitability of the carrier substrate to be used as a layer onto which the elastic photonic crystal can be directly formed. An adhesive layer may be applied to the outer surfaces of the device to improve adherence to the secure document.

The fact that the security device in Figures 1, 2 and 3 is in the form of a  
15 windowing security thread is for illustration only and the elastic photonic crystal could just as easily be employed as part of a surface applied security feature such as a stripe or a patch.

The example of the current invention described in Figures 1 and 2 is viewed primarily in reflection and as such the optical effects of the photonic  
20 crystal material are best visualised against a dark non-selectively absorbing background. This can be achieved by placing an absorbing layer under the photonic crystal layer or by the introduction of absorbing particles into the photonic crystal materials. The absorbing particles should be significantly greater than the size of the spheres of the photonic lattice such that they do  
25 not cause a change in the lattice and consequently an undesirable change in the optical properties.

Whilst the use of a black, or very dark, substantially totally absorbing layer may give rise to the most strong colourshifts, other effects may be generated by the use of a partially absorbing layer of other colours or a  
30 combination of colours, giving rise to differing apparent colourshift colours. The absorbing layer of the current invention may comprise a pigmented ink or coating or alternatively a non-pigmented absorbing dye can be used.



The optical properties of the photonic crystal layer can be customised by modifying the characteristics of the photonic crystal lattice. The presence of a full or partial photonic band gap, resulting in the exclusion of certain wavelengths for specific directions of incidence/propagation, arises from the difference in refractive index between the matrix and the spheres forming the photonic crystal. Increasing the difference in refractive index between the spheres and the matrix increases the intensity of the observed colours and colourshifts and increases the number of directions of incidence propagation over which a specific wavelength is excluded.

Photonic crystals that can be more easily formed into films typically comprise polymeric materials for both the matrix and the spheres. Suitable examples can be found in US6337131 and US20050228072. In this case the polymers for both the matrix and the spheres are selected to maximise the refractive index difference. The refractive index difference should be at least 0.001, but more preferably greater than 0.01 and even more preferably greater than 0.1.

A specific example of polymeric materials that can be used to produce an elastic photonic crystal material suitable for use in the current invention consists of spheres of crosslinked polystyrene in a polyethylacrylate matrix. A polymethylmethacrylate interlayer is present between the spheres and the matrix to ensure compatibility. The elastic photonic crystal material produced exhibits a face-centred-cubic crystalline structure with the (111) plane parallel to the surface of the film.

The optical properties of the photonic crystal layer can also be modified by changing the crystal structure, the crystal spacing or the size of the spheres. For the specific example discussed above Ruhl et al, in Polymer 44 (2003) 7625-7634, have shown that the polystyrene sphere diameter can be varied between 150 and 300nm to produce films of different colours when viewed at normal incidence without the application of an external stimulus. For example when viewing at normal incidence and without application of an external stimulus the colour varies with the sphere size as follows:

Sphere Size (nm)	Colour observed at normal incidence
207	Blue
249	Green
259	Yellow
282	Red

As a general guide, irrespective of the polymer type, the particle size of the spheres is preferably in the range 50-500nm, and even more preferably in the range 100-500nm, in order for the crystal to reflect light in the visible region of the electromagnetic spectrum.

It has been reported in the scientific literature (see Optics Express, Vol 15, No. 15, Page 9553-9561, 23<sup>rd</sup> July 2007) that nanoparticles can be introduced into the matrix of a photonic crystal in order to change or enhance the observed colours, colourshifts and tolerance on illumination angle. Preferably the size of the nanoparticles are selected such that they sit within the interstitial sites of the crystal lattice. The nanoparticles enhance resonant scattering events that occur within the photonic crystal giving rise to strong structural colours. For example the incorporation of carbon nanoparticles less than 50nm in diameter into the polystyrene/polyethylacrylate system cited above with a sphere size of 200nm, enhances the resonant scattering of the photonic crystal and dramatically alters the appearance of the photonic crystal film from one with a weakly coloured opalescence appearance to an intensely coloured green film. The use of the nanoparticles therefore provides a key advantage in that strongly intense colours are observed without the requirement for a separate absorbing layer or the incorporation of coarse absorbing particles. Furthermore there is an increased tolerance on illumination angle such that the observed colour is no longer as dependent on the position of the light source. In a second example magnetite nanoparticles can be incorporated to generate a magnetic machine-readable colourshifting film.

The concentration of the nanoparticles may be varied across the device. For example the nanoparticles could be introduced into localised regions or there could be a gradient in the number of nanoparticles across the device. This will result in a variation in the intensity of the colour and the associated colourshift across the device.

In one preferred embodiment the elastic photonic crystal film is produced by an extrusion process and the nanoparticles are added to the polymer reservoir prior to extrusion. In this case laterally spaced bands of nanoparticles can be achieved by providing a set of dividers in the polymer reservoir so that the additives are supplied through the extruder at corresponding lateral positions.

The particles may be made from material which is orientable in an electric, magnetic or electromagnetic field. In this way, alignment of the particles may be affected by selective application of that specified field to the elastic photonic crystal film prior to the final cross-linking step in the film production.

Nano-photoluminescent particles such as quantum dots may be added to create a novel photoluminescence security feature. For example PbS nanoparticles can be added to produce luminescent films. It has been shown in the scientific literature (Nature Materials Volume 5 March 2006 Page 179) that embedding quantum dots in a photonic crystal results in suppression of luminescence if the emission frequency falls within the band gap of the photonic crystal. If the position of the photonic band gap can be changed in response to external stimulus, such that it overlaps or crosses through the photoluminescence peak of the embedded emitter suppression/enhancement of emission and dynamic modification of the luminescence lifetimes may occur. If the external stimulus is a mechanical deformation an interactive security device is created where the fluorescence or phosphorescence is switched on or off by simply pressing the device.

Security devices comprising photonic crystal materials are inherently machine-readable due to the wavelength selectivity of the photonic crystal

materials. In further examples the machine readable-aspect of the current invention can be extended further by the introduction of detectable materials in the photonic crystal or by the introduction of separate machine-readable layers. Detectable materials that react to an external stimulus include but are not limited to fluorescent, phosphorescent, infrared absorbing, thermochromic, photochromic, magnetic, electrochromic, conductive and piezochromic materials.

In one preferred embodiment, the pigment in the separate absorbing layers is machine readable, for example carbon black, to produce a machine-readable, conducting, or IR absorbing layer. Alternatively it may be a magnetic material, such as magnetite, to produce a machine-readable magnetic layer.

It will be further understood by those skilled in the art that the security device of the current invention could be used in combination with existing approaches for the manufacture of security threads. Examples of suitable methods and constructions that can be used include, but are not limited to, those cited within WO03061980, EP0516790, WO9825236, and WO9928852.

Figure 4a illustrates how the current invention can be combined with demetallised characters for application as a windowed security thread. The method requires a metallised film comprising a substantially clear polymeric film of PET or the like, which has an opaque layer of metal on a first side thereof. A suitable pre-metallised film is metallised MELINEX S film from DuPont of preferably 19 $\mu$ m thickness. The metal layer is printed with a resist which contains a black or dark dye or pigment. Suitable resists include the dye BASE Neozapon X51 or the pigment (well dispersed) "Carbon Black 7" mixed into a material with both good adhesion to metal and caustic resistance. The printed metallised film is then partially demetallised, according to a known demetallisation process using a caustic wash which removes the metal in the regions not printed with the resist. The remaining regions coated with resist provide a black layer which is visible when the demetallised film is viewed from its first side (along arrow Y) interspersed with clear regions. The shiny metal of the remaining parts of the metallic layer are only visible from an opposite side of the demetallised film (along arrow X). The resist may be

printed in the form of the indicia such as words, numerals, patterns and the like; in which case the resulting indicia will be positively metallised, with the metal still covered by the dark or black resist. Alternatively the resist may be printed so as to form indicia negatively, in which case the resulting indicia will be provided by the demetallised regions. The indicia however formed, are clearly visible from both sides, especially in transmitted light, due to the contrast between the regions of the metal which have been removed and the remaining opaque regions. The photonic crystal layer is then applied, preferably using a transfer process, as with reference to Figure 3.

10 The security device illustrated in Figure 4a exhibits two visually contrasting security characteristics. The device comprises the interactive optical effects of the elastic photonic crystal layer, as described for the previous examples, when the finished substrate is viewed in reflection from the first side (along arrow Y); and a metallic shiny partial coating when viewed from the other side (along arrow X). Additionally clear positive or negative 15 indicia, defined by the black resist, can be seen in transmission from either side. This example is particularly advantageous when used in a device that is viewable from both sides of the document in which it is incorporated. For example the device could be incorporated into a secure document using the methods described in EP1141480 or WO03054297.

Figure 4b illustrates a machine-readable version of the device illustrated in Figure 4a. The device comprises a metallised PET base layer demetallised with a suitable design including tramlines of metal along each edge of the device. As described with reference to Figure 4a a black resist is used during the demetallisation process. A protective layer may be applied 25 onto the metal tramlines (not shown in the figure) to prevent the metal from being corroded by the magnetic layer, which is applied next. A suitable protective layer is VHL31534 supplied by Sun Chemical applied with coat weight of 2gsm. The protective layer may optionally be pigmented. The magnetic material is only applied over the metal tramlines so as not to obscure the demetallised indicia. The photonic crystal layer is then applied, preferably using a transfer process, as with reference to Figure 3. An 30

adhesive layer may be applied to the outer surfaces of the device to improve adherence to the security document.

When a magnetic material is incorporated into the device either within the absorbing layer or as a separate layer the magnetic material can be applied in any design but common examples include the use of magnetic tramlines or the use of magnetic blocks to form a coded structure. Suitable magnetic materials include iron oxide pigments ( $\text{Fe}_2\text{O}_3$  or  $\text{Fe}_3\text{O}_4$ ), barium or strontium ferrites, iron, nickel, cobalt and alloys of these. In this context the term "alloy" includes materials such as Nickel:Cobalt, Iron:Aluminium:Nickel:Cobalt and the like. Flake Nickel materials can be used; in addition Iron flake materials are suitable. Typical nickel flakes have lateral dimensions in the range 5-50 microns and a thickness less than 2 microns. Typical iron flakes have lateral dimensions in the range 10-30 microns and a thickness less than 2 microns.

In an alternative machine-readable embodiment a transparent magnetic layer can be incorporated at any position within the device structure. Suitable transparent magnetic layers containing a distribution of particles of a magnetic material of a size and distributed in a concentration at which the magnetic layer remains transparent are described in WO03091953 and WO03091952.

In a further example the security device of the current invention may be incorporated in a security document such that the device is incorporated in a transparent region of the document. The security document may have a substrate formed from any conventional material including paper and polymer. Techniques are known in the art for forming transparent regions in each of these types of substrate. For example, WO8300659 describes a polymer banknote formed from a transparent substrate comprising an opacifying coating on both sides of the substrate. The opacifying coating is omitted in localised regions on both sides of the substrate to form a transparent region.

EP1141480 describes a method of making a transparent region in a paper substrate. Other methods for forming transparent regions in paper substrates are described in EP0723501, EP0724519 and WO03054297.

5 Figure 5 shows the security device of the current invention incorporated into a transparent region of a security document. Figure 6a shows a cross-sectional view of the security device within the transparent region. The security device comprises a transparent carrier layer, which preferably forms the transparent region of the substrate. An absorbing material is applied to the transparent layer in localised regions to form a recognisable pattern or  
10 identifying image. A layer comprising an elastic photonic crystal material, exhibiting the same optical characteristics as the elastic photonic crystal material in Figures 1 and 2, is located above the absorbing layer.

When the device in Figure 6a is viewed in reflection from side A, prior to the application of an external stimulus, a highly contrasting colour shift  
15 effect is observed, from the regions of the elastic photonic crystal layer located above the absorbing layer, as the device is tilted. For example the colourshift can be from red, when viewed at a normal angle of incidence to the plane of substrate, to green when viewed at a specified angle of incidence to the plane of the substrate. When viewed in transmitted light from side A the  
20 regions above the absorbing layer still exhibit the red-green colourshift but in the regions not above the absorbing layer the transmitted colour saturates the reflective colour. The transmitted and reflected colours are complementary, for example, a red to green colourshift in reflection is seen as a cyan to magenta colourshift in transmission. On pressing the security device, a contraction  
25 occurs in the crystal lattice spacing perpendicular to the plane of the security device. This contraction modifies the photonic band structure of the crystal and hence the wavelength and spatial dependence of the reflectivity observed by the authenticator. In this example the contraction of the lattice results in the observed reflected colour moving to a shorter wavelength for example red  
30 goes to green and green goes to blue, resulting in a colour shift from green to blue as the substrate is tilted in its pressed state. In contrast the observed

complementary transmitted colour moves to a longer wavelength resulting in a magenta to yellow colourshift as the substrate is tilted in its pressed state.

When the device in Figure 6a is viewed in reflection or transmission from side B the dark absorbing layer will be visible in the form of an identifying image. If a dark image is not aesthetically acceptable then a more aesthetically pleasing material/colour could be used to conceal the dark resist such that it is not viewable from side B. For example the dark absorbing areas could be overprinted on side B of the transparent region with differently coloured opaque inks or metallic inks. Alternatively the transparent carrier substrate could be replaced with a metallised polymeric substrate, as illustrated in Figure 6b. The metallised substrate is printed with a dark resist, as discussed in reference to Figure 4, in the form of the identifying image. The printed metallised film is then partially demetallised removing the metal in the regions not printed with the resist. When viewing from side A the elastic photonic crystal film is viewed against the absorbing dark resist and appears as described with reference to Figure 6a, but when viewing from side B a metallic image is observed of the identifying image printed with the dark resist. The image could be positive, i.e. defined by the metallic regions, or negative, i.e. defined by the transparent regions between the metallic regions.

In an alternative machine-readable construction the dark resist in Figure 6b can be formed using a magnetic pigment, for example magnetite to provide a machine-readable code. In a further embodiment, only part of the dark resist is provided with a magnetic pigment and the remainder is provided with a non-magnetic pigment. If both the magnetic and non-magnetic regions are substantially totally absorbing there will be no visual difference in the elastic photonic crystal film over the two regions and therefore the format of the code will not be readily apparent.

The materials used in the elastic photonic crystal can be selected such that when the pressure is removed the ambient optical properties of the device do not instantly return but instead there is a delay such that the new colour can be easily verified. The presence of such a device in a transparent regions means that the device can be poked from one side and viewed from



the other side. For example with reference to Figure 6 the device can be authenticated by poking side B and viewing the reflective colourshift against the dark absorbing background from side A. In this context poking is differentiated from pressing due to the fact that the transparent regions is not back supported during the deformation.

In an alternative method of authentication the security device comprising an elastic photonic crystal could be stretched to carry out the authentication process. WO2004001130 describes a method for incorporating an elongate element such as a security thread into a secure document such that the elongate element is exposed within an aperture. In one example of WO2004001130 the aperture is used to form a notch on the edge of the document in which the end of a security thread is exposed as illustrated in Figure 7. In one example of the current invention the exposed thread comprises an elastic photonic crystal layer which exhibits one angular dependent colourshift at ambient conditions and a second angular dependent colourshift when stretched. The fact that the thread is exposed enables it to be stretched easily without having to flex the document.

Figure 8 illustrates an example where the security device of the current invention is incorporated into an aperture of a paper substrate. A self-supporting elastic photonic crystal film is incorporated into a paper substrate as described in EP1141480. One side of the photonic crystal film is wholly exposed on the front surface of a paper substrate in which it is partially embedded (Figure 8a), and partially exposed in one aperture on the rear surface of the substrate (Figure 8b). In this example the photonic crystal material comprises spheres of crosslinked polystyrene in a polyethylacrylate matrix. Carbon nanoparticles have been incorporated into the photonic crystal structure such that the film has an intense red colour when viewed at normal incidence without the application of an external stimulus.

On viewing the device from the front of the document in reflection, illustrated in Figure 8a, prior to the application of an external stimulus a highly contrasting colour shift effect is observed along the whole of the exposed elongate security device. In this example the colourshift is from red, when

viewed at a normal angle of incidence to the plane of substrate, to green when viewed at a specified angle of incidence to the plane of the substrate. The incorporation of the nanoparticles produces a single layer, i.e. non-laminate, strongly coloured substantially opaque film. This is an advantage over liquid crystal colourshifting films where the use of a separate black or dark absorbing layer is required to generate a strongly coloured substantially opaque film. If a liquid crystal based device is used in the example shown in Figure 8 then in order for the reflective colourshifting effect to be visible from both sides of the document two liquid crystal films would be required with an absorbing layer between them. In contrast for the current invention the use of the self-supporting elastic photonic crystal film doped with carbon nanoparticles enables the reflective colourshifting effect to be visible from both sides of the document while using just a single layer of colourshifting material. On viewing the device from the rear of the document in reflection, illustrated in Figure 8b, prior to the application of an external stimulus the same highly contrasting colour shift effect, as is observed from the front of the document, is present where the elastic photonic crystal film is exposed in the aperture.

In this example a mechanical external stimulus is applied by bending the document around its central longitudinal axis, as illustrated in Figure 8c. This deformation modifies the photonic band structure of the crystal and hence the wavelength and spatial dependence of the reflectivity observed by the authenticator. In this example the deformation causes a contraction of the lattice perpendicular to the plane of the substrate that results in the observed colour moving to a shorter wavelength for example red goes to green and green goes to blue. In the current example the aperture is positioned such that it falls within the central axis of the document such that when the authenticator bends the document around the central axis the maximum deformation and hence colour change occurs in the aperture region of the document. An advantage of the current invention is that on deforming the elastic photonic crystal a dynamic colour change is observed. In the example in Figure 8 as the device is bent around the central aperture the initial colour change from red to green is in the central region of the aperture where the deformation is the highest, as the document is bent further the deformation increases

outwards towards the edges of the aperture and a green band is observed to move towards the edge of the aperture. If the document is bent to a sufficiently high radius of curvature the central region of the aperture will switch from green to blue. An angular dependent colourshift will also be  
5 observed when the device is in its deformed state for example this could be from green to blue as the substrate is tilted in its initial deformed state. On removal of the deformation the photonic crystal layer will revert to its original colour and therefore the authentication process is reversible. The change in colour with deformation provides an interactive component to the security  
10 device which is both memorable to the public and difficult to counterfeit.

In an alternative embodiment to that referenced in Figure 8 the elastic photonic crystal film can be supported by a carrier layer to facilitate its incorporation into the paper document. The elastic photonic crystal layer may be formed directly onto the carrier substrate as a coated film or formed as a  
15 separate film and then laminated to the carrier substrate. The carrier substrate may comprise additional security features including de-metallised designs, holographic designs in combination with a highly reflective layer such as a metallic layer or a thin transparent layer of a high refractive index material (for example ZnS), printed indicia, luminescent or magnetic materials, and coarse  
20 embossing with a security design that may be either blind embossed to produce a tactile/visible feature or could include printing inks to further enhance visibility. In this manner a different security feature can be observed on either side of the security device.

In a further embodiment the security device of current invention can be  
25 constructed such that different colourshifting effects are observed on either surface of the security device. This can be achieved by laminating together two photonic crystal films with different optical characteristics or by varying the optical characteristics of the photonic crystal film over the thickness of the film.

For example two elastic photonic crystal films can be made from the  
30 same materials for the spheres and matrix but differ in their optical properties due to a difference in sphere size. Figure 9 shows a cross-section of a security device comprising two elastic photonic crystal films adhered together

with a laminating adhesive. The laminating adhesive comprises a dark dye or pigment such that it also acts as an absorbing layer. The device can be made machine-readable by incorporating a magnetic pigment into the laminating adhesive or applying an additional magnetic layer to the inner surface of one or both of the elastic photonic crystal films. An adhesive layer may be applied to the outer surfaces of the device to improve adherence to the secure document. The security device is incorporated into a document such that in at least localised regions it is exposed on both surfaces of the secure document. In this example both the first and second elastic photonic crystal films consist of spheres of crosslinked polystyrene in a polyethylacrylate matrix. A polymethylmethacrylate interlayer is present between the spheres and the matrix to ensure compatibility. The elastic photonic crystal material produced exhibits a face-centred-cubic crystalline structure with the (111) plane parallel to the surface of the film. The first elastic photonic crystal film has a sphere size of 282 nm and appears red when viewed in reflected light at normal incidence and appears green when viewed at an oblique angle of incidence to the plane of the substrate. On deforming the security device, and viewing at normal incidence, the colour of the device changes from red to green and shifts to blue as the device is tilted in its deformed state. The second elastic photonic crystal film has a sphere size of 259 nm and appears yellow when viewed in reflected light at normal incidence and appears blue when viewed at an oblique angle of incidence to the plane of the substrate. On deforming the security device, and viewing at normal incidence, the colour of the device changes from yellow to blue and shifts to violet as the device is tilted in its deformed state.

The security device in Figure 9 is incorporated into a document such that it coincides with an aperture in the document. The authenticator will not only observe different angular dependent colourshifts when viewing from the opposite sides of the aperture but also a different optical response when it is deformed for example by bending, poking or pressing.

Different colourshifting effects on either surface of the security device can also be generated using a single layer of elastic photonic crystal film by

locally varying the optical characteristics of the elastic photonic crystal film over the thickness of the film. For example the sphere size can be varied through the thickness of the film. This variation can be introduced by controlling the assembly of the spheres during the formation of the elastic photonic crystal film. Alternatively if the film is manufactured by polymer extrusion then two polymer mixes, comprising the spheres and the matrix, can be generated with different sphere sizes. The two polymer mixes can then be co-extruded into a single polymer film forming a crystal structure where there is a step change in sphere size at an interface in the centre of the film.

10 The security device of the current invention may be further customised in order to increase the difficulty in counterfeiting and/or provide identifying information. The customisation process can take place before or after the device is incorporated into the document. In one example the customisation of the security device occurs by applying printed information to the elastic photonic crystal film. The elastic photonic crystal film may be printed with images using any of the conventional printing processes such as intaglio, gravure, ink jet, offset lithography, screen, dye diffusion and flexography. The print may be applied as a single print working in a single colour or as multiple print workings in multiple colours.

20 In a preferred embodiment the images are printed partly on the elastic photonic crystal film and partly on the substrate the device is incorporated into such that the design continues uninterrupted between the two surfaces. In a further embodiment, one of the colours of the printed images matches one of the switching colours of the elastic photonic crystal film. For example if the elastic photonic crystal film switches from red to green on pressing the device then any red printed information will be substantially invisible at normal incidence but becomes visible as the sample is pressed as the static red of the printed information contrasts with the green of the optically variable photonic crystal film. In this manner a latent image security feature can be created.

30 Figure 10 illustrates another example of the present invention where a security device has been incorporated into the document as a surface applied

patch. A red identifying image is printed such that a part is on the substrate and another part is on the security device. On viewing the substrate at normal incidence (Figure 10a) the security device appears red and saturates the printed information on the security device such that only the printed information on the substrate is visible. The printed information is revealed by either pressing the security device or tilting the substrate. On tilting the substrate, the elastic photonic crystal switches from red to green and on pressing the device the elastic photonic crystal also switches from red to green and as the pressure is increased further from green to blue. In both cases the red printed information will be revealed on the security device and a complete image will be formed with the printed information on the substrate (Figure 10b). A second green identifying image may also be printed on the security device, the green image will be visible at normal incidence but will disappear on tilting the sample as it becomes saturated by the green colour of the elastic photonic crystal. On pressing the device the green image will disappear initially as the device switches from red to green (Figure 10b) but as the pressure is increased the green image will reappear as the device switches from green to blue (Figure 10c).

The security device in the sample in figure 10 has a number of secure aspects; firstly a colourshift on tilting, secondly a colourshift on the application of an external stimulus, and thirdly the presence of two latent images which are switched on and off alternately by tilting but can be both switched on simultaneously by pressing the device.

As an alternative to the printing of ordinary coloured inks, it is also possible to print functional inks. By functional inks we mean inks that react to an external stimulus. Inks of this type include but are not limited to fluorescent, phosphorescent, infrared absorbing, thermochromic, photochromic, magnetic, electrochromic, conductive and piezochromic.

As well as functional inks, it is also possible to print onto the elastic photonic crystal film with other optical effect inks. Optical effect inks include OVI® and Oasis® marketed by Sicpa. Other optical inks include inks

containing iridescent, iriodine, pearlescent, liquid crystal and metal-based pigments.

In a further embodiment, the customisation of the security device occurs by embossing the elastic photonic crystal film with raised line structures. The embossing of raised line structures into elastic photonic crystal films is particularly advantageous because the facets generated by the embossing result in a change in the angle of incidence of the incoming light, generating facets of differing colours due to the fact that the colour of the elastic photonic crystal film is dependent on the angle of view. The use of a raised line structure with an elastic photonic crystal film has two secure aspects; firstly the optically variable feature generated by the line structure and secondly the creation of localised regions exhibiting different colourshifts from the background film.

For example if the elastic photonic crystal device exhibits a green to blue colourshift on tilting the device away from normal incidence then when viewed at normal incidence the embossed and non-embossed regions will appear green. On tilting the device the non-embossed and embossed regions will change from green to blue at different angles of view as the device is tilted. Furthermore if the device comprises regions of different orientations of the embossed line structures then each region will change from green to blue at different angles of view as the device is tilted. Likewise by rotating the device in the plane of the photonic crystal film the embossed regions will switch from green to blue or vice-versa at different points in the rotation as the orientation of the embossed structures varies relative to the observer.

A further advantage of using embossed raised line structures is that the structures have a raised surface that can be identified by touch. The smooth surface of the photonic crystal film further enhances the tactility of these raised structures.

The embossed line structures can take any convenient form including straight (rectilinear) or curved such as full or partial arcs of a circle or sections of a sinusoidal wave. The lines may be continuous or discontinuous and, for

example, formed of dashes, dots or other shapes. By other shapes we mean the dots or dashes could have a graphical form. The line widths are typically in the range 10-500 microns, preferably 50-300 microns. Preferably, the individual lines are barely visible to the naked eye, the main visual impression being given by an array of multiple lines. The lines can define any shape or form, for example square, triangle, hexagon, star, flower or indicia such as a letter or number.

The embossed line structures are preferably formed by applying an embossing plate to the elastic photonic crystal film under heat and pressure. Preferably the embossing process takes place during the intaglio printing process and is carried out using an intaglio plate having recesses defining the line structures. Preferably the elastic photonic crystal film is blind embossed, i.e. the recesses are not filled with ink. However it is also possible that some of the recesses defining the embossed structure may be filled with ink and others left unfilled. Further intaglio printing or blind embossing may be carried out on regions of the substrate adjacent to the security device using the same intaglio plate so as to achieve precise registration between the different regions.

Figure 11 shows an example of a security substrate comprising a security device of the current invention where the elastic photonic crystal films has been customised by embossing the film after it has been applied to the base substrate. In this example the elastic photonic crystal film has been incorporated into a paper substrate in the same manner as referenced in Figure 8 and described in EP1141480. Figure 11 shows the front surface of the paper substrate on which the device is wholly exposed. The device is also exposed on the back surface in the aperture region. In this example the elastic photonic crystal film exhibits a red-green colourshift on tilting away from normal incidence and a red to green to blue colourshift on poking the device. The embossed line structures, formed by a respective set of substantially parallel raised lines, define the numeral "5". The embossed regions provide an additional optically variable aspect to the device in addition to the angular dependent and pressure dependent colourshifts exhibited by the non-



embossed structures. When viewed at normal incidence, both the embossed and non-embossed regions appear red.

On tilting the substrate away from normal incidence, and viewing along viewing direction Y such that the lines extend at  $90^\circ$  to the incident light direction, the numeral "5" switches almost instantaneously from red to a predominantly green colour due to the dominant reflected light arising from the edges of the raised lines. In contrast, the non-embossed region switches from red to green at a greater angle of incidence relative to the flat substrate. The difference in the viewing angle at which the colour switch occurs arises because when viewed normally to the substrate the effective angle of incidence for light incident on the edge regions is greater than the angle of incidence for light incident on flat non-embossed regions. If the device is rotated by  $90^\circ$ , such that it is viewed along viewing direction X parallel to the direction of the embossed lines, then on tilting the substrate both the embossed and no-embossed regions switch from red to green at substantially the same viewing angle because very little light is reflected by the edge of the lines.

If the embossed lines are such that a significant portion of the edge region extends at an angle of approximately  $45^\circ$  to the base substrate, then on tilting the substrate away from normal incidence, and viewing perpendicularly to the direction of the lines, an almost instantaneous switch from red to a predominantly green colour will occur as described previously. However on tilting the substrate further, the angle of incidence for the light incident on the edge regions will move closer to normal incidence resulting in a switch back to red, effectively exhibiting a reverse colourshift.

In a further embodiment the customisation of the security device occurs by embossing the elastic photonic crystal film with a non-diffractive line structure. A non-diffractive line structure is an example of a raised line structure which produces an optically variable effect when the angle of incidence light varies, but in which this effect is not caused by interference or diffraction. Security devices based on non-diffractive line structures are known in the prior art for example WO9002658 describes a security device in which

one or more transitory images are embossed into a reflective surface. WO9820382 discloses a further security device in which a group of elemental areas in which lines extend at different angles from each other form respective image pixels. US1996539 discloses a decorative device in which a relief structure is formed in a surface and has an optically variable effect. 5 WO2005080089 discloses a security device which has segments defined by line structures in a reflective portion of a substrate, which cause incident light to be reflected non-diffractively as the angle of incidence changes.

In an alternative embodiment the security device further comprises an 10 optically variable device such as a hologram or diffraction grating. These devices are commonly formed as relief structures in a substrate, which is then provided with a reflective coating to enhance the replay of the device. In the current invention the elastic photonic crystal can act as the reflective coating and the relief structure can be embossed directly into the elastic photonic 15 crystal film or into an embossing lacquer applied onto the elastic photonic crystal film. Alternatively localised regions of the device can be provided with a metallised layer and the relief structure subsequently embossed into an embossing lacquer on top of the metallised layer. In this manner the device comprises two laterally spaced regions one exhibiting the colourshifting 20 properties of the elastic photonic crystal film and one exhibiting the optically variable properties of a holographic device. Alternatively the metallic reflective coating can be replaced with a transparent reflection enhancing materials for example a thin layer of a high refractive index material such as ZnS. In this case both the colourshifting properties of the elastic photonic crystal material and the optically variable properties of the holographic device are visible in all 25 areas of the device although the optically variable properties of the holographic device will only be visible at certain angles of view.

In a further embodiment of the invention the security device can be customised by the application of a scattering layer to the elastic photonic 30 crystal film. In a preferred embodiment the scattering layer takes the form of a matt varnish or lacquer. In this context a matt varnish or lacquer is one that reduces the gloss of the elastic photonic crystal film by scattering the light

reflected from it. One example of a suitable matt varnish is a suspension of fine particles in an organic resin. The surface particles scatter the light as it passes through the varnish resulting in a matt appearance. A suitable varnish for the present invention is "Hi-Seal O 340" supplied by Hi-Tech Coatings Ltd.

5 In an alternative solution the fine particles can be replaced by organic waxes. As a further alternative, the scattering layer can be generated by embossing a matt structure into the surface of a photonic crystal layer. Suitable embossed matt structures are described in W09719821. The scattering layer modifies the colourshifting properties of the elastic photonic crystal layer.

10 The scattering layer modifies the surface of the elastic photonic crystal film such that the reflection is now more diffuse reducing the glare of the elastic photonic crystal film and changing the angular range over which the respective colours of the security device are easily viewable to the authenticator. For example, if the elastic photonic crystal material exhibits a  
15 red to green colourshift on tilting the switch from red to green occurs closer to normal incidence for the region with the scattering layer compared to one without a scattering layer.

A further way of customising the security device is to use two or more different coloured absorbing layers. An example of this embodiment is  
20 illustrated in Figures 12 and 13. Figure 12 shows a cross-sectional view of a construction of the security device suitable for application as a surface stripe or patch. The device comprises a carrier substrate, which may be coated with a release layer, onto which is applied an elastic photonic crystal film. A red partial absorbing layer is applied over the elastic photonic crystal film in the  
25 form of a design and a second black absorbing layer is applied over all of the partial absorbing layer. An adhesive layer is applied to the black absorbing layer. The device is then transferred to a security document, such as a banknote (Figure 13). After transfer the carrier strip can be removed, leaving the elastic photonic crystal film exposed or alternatively the carrier layer can  
30 be left in place to form an outer protective layer. By selection of appropriate colours for the partial absorbing layer the designs defined by this layer can be visible at certain angles of view or states of deformation and invisible at others. In this example the elastic photonic crystal film transmits all

wavelengths except red at normal incidence. Then, at normal incidence, the design formed by the red partial absorbing layer is invisible with the device appearing a uniform red colour, but on tilting or deforming (for e.g. by pressing or bending) the device a different colourshift is observed for the elastic photonic crystal regions with and without the partial absorbing layer and therefore the designs are revealed. The revealing of the image is in addition to the two different optically variable effects observed with and without the presence of an external stimulus.

In yet a further embodiment of the present invention, the elastic photonic crystal film can be customised by providing gaps in the film such that in localised regions the underlying layer is visible. The gaps can be provided by transferring or coating the elastic photonic crystal film onto a carrier substrate in a partial manner. Alternatively the gaps can be created at later stage in the process for example by laser ablating a fully formed elastic photonic crystal film. Figure 14 illustrates a device comprising a carrier substrate over which has been applied a red partial absorbing layer onto which has been transferred an elastic photonic crystal film. A laser is used to form gaps in the elastic photonic crystal film in the form of an identifying image. In this example the elastic photonic crystal film transmits all wavelengths except red at normal incidence. Then, at normal incidence, both the gaps and the elastic photonic crystal film appear red and therefore the identifying information defined by the gaps is not distinguishable from the background. On deforming the device the photonic crystal film switches from red to green but the gaps which expose the underlying absorbing layer still appear red, In this manner the identifying image is made to appear by tilting or deforming the device. The revealing of the image is in addition to the two different optically variable effects observed with and without the presence of an external stimulus.

Figure 15 illustrates a further example where there are gaps present in the elastic photonic crystal film. The device in figure 15 comprises an elastic photonic crystal film which has been transferred onto a substantially transparent carrier substrate. Alternatively a self-supporting elastic photonic

crystal film can be used without the need for a carrier substrate. The elastic photonic crystal film is the same as that described in relation to figure 9 and carbon nanoparticles have been incorporated into the photonic crystal structure to produce a substantially opaque film with an intense red colour when viewed at normal incidence without the application of an external stimulus. A laser is used to form gaps in the elastic photonic crystal film in the form of an identifying image. The identifying image is clearly visible from both sides, especially in transmitted light due to the contrast between the regions of the substantially opaque elastic photonic crystal film which have been removed and the remaining opaque regions. The security device illustrated in Figure 15 exhibits two visually contrasting security characteristics; firstly the optical effects of the photonic crystal layer and secondly the identifying image clearly visible in transmission from either side of the device.

In yet a further embodiment of the present invention, photonic crystal materials can be selected such that once the external stimulus is applied the reflected light is in the non-visible wavelengths of the electromagnetic spectrum. The use of elastic photonic crystals where only one component of the colourshift is in the visible region of the electromagnetic spectrum enables an image to be incorporated into the device that only becomes apparent when the external stimulus is applied or removed.

Figure 16 shows a cross-sectional view of a further embodiment of the security device of the current invention. The device is intended for use as a security label and comprises an elastic photonic crystal film onto which is printed identifying indicia using inks or dyes. An adhesive layer is applied to one side of the device and over this is applied a glassine carrier layer. The glassine layer allows the label to be easily removed for reapplication to a document, or other item requiring protection.

Figure 17 shows the label device applied to a substrate. The glassine layer is first removed to expose the adhesive layer. The label device is then applied to the substrate; the adhesive used may be a pressure sensitive or hot melt adhesive and may be permanent or temporary. The use of temporary adhesives can be of use where a label needs to be removed and reapplied to

another article. However, it is more likely that the label must be applied in a permanent manner. To prevent removal and reapplication of a permanently applied label the label may also be provided with other tamper evident features e.g. frangible substrate layers, kiss cuts, and the like.

5           The elastic photonic crystal film consists of spheres of crosslinked polystyrene in a polyethylacrylate matrix. A polymethylmethacrylate interlayer is present between the spheres and the matrix to ensure compatibility. The elastic photonic crystal material produced exhibits a face-centred-cubic crystalline structure with the (111) plane parallel to the surface of the film.

10 Carbon nanoparticles have been incorporated into the photonic crystal structure such that the film has an intense blue colour when viewed at normal incidence without the application of an external stimulus. The identifying indicia is printed in a blue colour such that when the device is viewed at normal incidence the indicia is not readily apparent against the background

15 colour of the elastic photonic crystal film. On tilting the device, without applying an external stimulus, light reflected by the photonic crystal film changes from blue to invisible ultra violet light and the film will appear black due to the presence of the carbon nanoparticles. As the device is tilted the blue printed identifying indicia are revealed as the background changes from

20 blue to black. On deforming the security device, either by bending, pressing or stretching and viewing at normal incidence, the colour of the device changes from blue to black due to the reflected light changing from blue to invisible ultraviolet light with the black appearance again due to the presence of the carbon nanoparticles. In this manner the blue identifying indicia is

25 revealed on applying the external stimulus. If the device in this example is tilted in its deformed state its appearance in visible light will not change but there will be a change in the wavelength of the light reflected outside the visible range. This change in the wavelength of reflected UV light with viewing angle can provide the device with a machine-readable aspect that is not

30 apparent with the naked eye.

In a further embodiment a photonic crystal film, which in its deformed state reflects light in the non-visible wavelengths of the electromagnetic spectrum, is overprinted or embossed with a first array of fine lines. A second

array of fine lines is located underneath the security device, as part of the absorbing layer or an additional printed layer. When the device is deformed the elastic photonic crystal film transmits all visible light and is sufficiently transparent that the first and second array of lines combine to produce a visible moiré pattern, preferably in the form of an identifying image.

In a modification to the example of Figures 16 and 17, illustrated in Figures 18 and 19, the elastic photonic crystal film comprises a photonic crystal that solely reflects infrared light when viewed at normal incidence, and reflects visible light when an external stimulus is applied. Prior to the application of an external stimulus the device switches from reflecting infrared light to visible red light as the device is tilted. Figure 18 is a cross-section of a security device and comprises a polymeric carrier substrate onto which is printed a dark absorbing layer. An elastic photonic crystal film is then transferred onto the absorbing layer and is overprinted with a green identifying image. In this example the photonic crystal is not doped with carbon nanoparticles but the presence of the absorbing layer means that only the reflected wavelengths of light are seen as a colour. An adhesive layer is applied to one side of the device and over this is applied a glassine carrier layer.

Figure 19 illustrates a plan view of the device. On viewing the device illustrated in Figures 18 and 19 at normal incidence, without the application of an external stimulus, the elastic photonic crystal film will appear colourless and therefore the device will take on the black appearance of the underlying absorbing layer. The green identifying image will be visible against a black background (Figure 19a). On tilting the device, without applying an external stimulus, light reflected by the photonic crystal film changes from invisible infra-red light to visible red light and the security device will switch from black to red with the green identifying image still being observed. On deforming the security device, either by bending, pressing or stretching and viewing at normal incidence, the colour of the device changes initially from black to red, and a green identifying image is observed on a red background (Figure 19b). As the level of deformation increases there is further contraction of the photonic crystal lattice perpendicular to the plane of the substrate, and the

observed colour moves to a shorter wavelength and the device appears green. Throughout the deformation process the colour of the identifying image remains constant, i.e. green, and therefore as the authenticator deforms the sample he/she observes a green image firstly on a black background (Figure 5 19a) and then a red background (Figure 19b) and then the green image is seen to disappear into a uniform green background (Figure 19c). In this manner a highly interactive security feature is created which is both striking and memorable to the authenticator.

In a further embodiment of the current invention the mechanical 10 properties of the elastic photonic crystal film can be varied in localised regions such that the degree of contraction in the crystal lattice spacing perpendicular to the plane of the security device is varied across the device. This results in laterally spaced regions which exhibit different colourshift effects when the device is deformed. The variation in mechanical properties can take the form 15 of a local variation in the stiffness of a polymeric elastic photonic crystal film, which can be achieved, for example, by varying the cross-link density across the elastic photonic crystal film. Areas with a high cross-link density will require higher deformation to achieve the same colourshift compared to those areas with a low cross-link density. In the example in Figure 20 the polymeric 20 elastic photonic crystal film comprises regions A and B. Region A has a higher cross-link density than region B. On viewing the device illustrated in Figure 20 at normal incidence and without the application of an external stimulus, both regions A and B of the elastic photonic crystal film will appear a uniform red colour (Figure 20a). On initially deforming the elastic photonic crystal film 25 region A, with a high stiffness due to a high cross-link density, will remain red due to a negligible contraction in the crystal lattice spacing. Region B which is less stiff, due to a lower cross-link density, will switch from red to green due to a significant contraction in the crystal lattice spacing and will reveal the image of a green star (Figure 20b). If the level of deformation is increased region A 30 will eventually switch from red to green and region B will switch from green to blue (Figure 20c). At all points in its deformed state both regions A and B will also exhibit an angular dependent colourshift.



In an alternative embodiment to that discussed in relation to Figure 20 the variation in the mechanical properties can be achieved by locally varying the thickness of the elastic photonic crystal film. Thinner regions of the elastic photonic crystal film will be easier to deform than thicker regions and therefore will switch colour at lower levels of deformation. Local variations in thickness can be easily provided if the elastic photonic crystal film is formed by a coating process. Alternatively regions of reduced thickness can be provided by embossing.

In all of the examples the designs or identifying images created by any of the layers, for example the photonic crystal film, the absorbing layers or customising layers, can take any form. Preferably the designs are in the form of images such as patterns, symbols and alphanumeric characters and combinations thereof. The designs can be defined by patterns comprising solid or discontinuous regions which may include for example line patterns, fine filigree line patterns, dot structures and geometric patterns. Possible characters include those from non-Roman scripts of which examples include but are not limited to, Chinese, Japanese, Sanskrit and Arabic.

## CLAIMS

1. An optically variable security device comprising a photonic crystal which, upon receipt of incident light, generates a first optical effect, and which, when  
5 the device is subjected to an external stimulus, generates a second optical effect that is different from the first optical effect, wherein at least one of the first and second optical effects is an optically variable effect observable over a set of directions and caused by the light being selectively reflected or transmitted by the crystal.
- 10 2. An optically variable security device according to claim 1, wherein the said first and second optical effects comprise first and second optically variable effects respectively.
3. An optically variable security device according to claim 1 or claim 2, wherein the second optically variable effect is observable over the said set of  
15 directions.
4. An optically variable security device according to claim 2 or claim 3, wherein, when the device is illuminated with a white light source, the first and second optically variable effects are colour effects.
5. An optically variable security device according to any of claims 2 to 4,  
20 wherein the first optically variable effect is a first angularly dependent colour effect and the second optically variable effect is a second angularly dependent colour effect, that is different from the first.
6. An optically variable security device according to any of the preceding claims, wherein the first and second effects are reflective effects.
- 25 7. An optically variable security device according to any of the preceding claims, wherein the device is arranged such that effects are visible to the naked eye of a human observer.

8. An optically variable security device according to any of the preceding claims, wherein the or each optically variable effect is dependent upon the crystal orientation with respect to the incident light.
9. An optically variable security device according to any of the preceding  
5 claims, wherein the or each optically variable effect is a function of the viewing angle with respect to the crystal.
10. An optically variable security device according to any of the preceding claims, wherein part of one or more of the optically variable effects is in the infra-red or ultra-violet part of the electromagnetic spectrum.
- 10 11. An optically variable security device according to any of the preceding claims, wherein the photonic crystal comprises a quasi-crystal.
12. An optically variable security device according to any of the preceding claims, wherein the external stimulus is one or more of a mechanical, thermal, chemical, electrical, magnetic, electromagnetic or ultrasonic stimulus.
- 15 13. An optically variable security device according to any of the preceding claims, wherein the application of the stimulus causes a modification in the periodic spacing of one or more refractive entities within the crystal structure.
14. An optically variable security device according to any of the preceding  
20 claims, wherein the application of the stimulus causes a modification in the refractive index of one or more refractive entities within the crystal structure.
15. An optically variable security device according to any of the preceding claims, wherein the photonic crystal is arranged such that the effect of the stimulus upon the crystal is reversible upon removal of the stimulus or upon application of an opposite stimulus.
- 25 16. An optically variable security device according to any of the preceding claims, wherein the photonic crystal comprises an elastomeric component such that the stimulus can be applied by the application of a force to the security device.

17. An optically variable security device according to any of the preceding claims, wherein the light is one or more of, ultra violet, visible or infra red light.
18. An optically variable security device according to any of the preceding claims, wherein the photonic crystal is formed from spheres of a first material  
5 and a matrix of a second material, each material having a different respective refractive index.
19. An optically variable security device according to any of the preceding claims, wherein the photonic crystal structural parameters are different at different positions within the crystal so as to produce different corresponding  
10 optical properties.
20. An optically variable security device according to any of the preceding claims, wherein the photonic crystal is formed from two or more crystal structures having different optically variable properties.
21. An optically variable security device according to any of the preceding  
15 claims, wherein the photonic crystal is provided as a self-supporting film.
22. An optically variable security device according to any of claims 1 to 20, wherein the photonic crystal is supported by a substrate or carrier layer.
23. An optically variable security device according to claim 22, wherein the substrate or carrier layer is a polymeric layer.
- 20 24. An optically variable security device according to any of the preceding claims, wherein the security device is provided with an adhesive layer upon one or each outer surface thereof.
25. An optically variable security device according to any of the preceding claims, further comprising a scattering layer.
- 25 26. An optically variable security device according to any of the preceding claims, further comprising an optically absorbent material provided as one or more layers applied to the device.

27. An optically variable security device according to claim 26, wherein the absorbent material is selectively absorbent at light wavelengths.
28. An optically variable security device according to claim 26 or claim 27, wherein the absorbent material is an ink or dye.
- 5 29. An optically variable security device according to any of the preceding claims, wherein the device further comprises a metallised layer.
30. An optically variable security device according to claim 29, wherein the metallised layer is selectively demetallised at a number of locations.
31. An optically variable security device according to claim 29 or claim 30,  
10 wherein the device further comprises a layer of resist upon the metallised layer.
32. An optically variable security device according to any of claims 29 to 31, wherein the said metallised layer or the layer of resist is arranged as indicia.
33. An optically variable security device according to any of the preceding  
15 claims, wherein the device is arranged to be machine-readable.
34. An optically variable security device according to claim 33, wherein at least one layer of the device or the photonic crystal further comprises machine-readable material.
35. An optically variable security device according to claim 33, wherein the  
20 device further comprises a separate layer containing machine-readable material.
36. An optically variable security device according to claim 34 or claim 35, wherein the machine-readable material is a magnetic material.
37. An optically variable security device according to any of claims 34 to 36,  
25 wherein the machine-readable material comprises a material which is responsive to an external stimulus.

38. An optically variable security device according to any of claims 34 to 36, wherein the machine-readable layer is substantially transparent.
39. An optically variable security device according to any of the preceding claims, further comprising an optically absorbent material formed within the  
5 crystal structure.
40. An optically variable security device according to any of claims 1 to 38 further comprising nanoparticles within the crystal structure.
41. An optically variable security device according to claim 40, wherein the photonic crystal further comprises nanoparticles distributed substantially  
10 uniformly through the crystal such that each part of the crystal exhibits substantially the same optical effect.
42. An optically variable security device according to claim 40, wherein the photonic crystal further comprises nanoparticles distributed inhomogeneously through the crystal such that different parts of the crystal exhibit a  
15 substantially different optical effect.
43. An optically variable security device according to claim 40, wherein the nanoparticles are distributed according to a concentration gradient.
44. An optically variable security device according to claim 42, wherein the nanoparticles are distributed in a number of regions having different  
20 concentrations.
45. An optically variable security device according to any of claims 40 to 44, wherein the nanoparticles are carbon nanoparticles.
46. An optically variable security device according to any of the preceding claims, wherein the device is arranged to produce a latent image which is  
25 selectively visible according to the viewing angle.
47. An optically variable security device according to any of the preceding claims, wherein the surface of the photonic crystal is embossed with raised structures.

48. An optically variable security device according to any of the preceding claims, wherein the surface of the photonic crystal device is overprinted.
49. An optically variable security device according to any of the preceding claims, wherein the security device further comprises a hologram.
- 5 50. An optically variable security device according to any of the preceding claims, wherein the crystal is an elastic photonic crystal.
51. An optically variable security device according to any of the preceding claims, wherein the photonic crystal is provided as a polymeric film.
52. An optically variable security device according to claim 50, wherein the  
10 mechanical properties of the elastic photonic crystal are arranged to be different in respective localised regions.
53. An optically variable security device according to any of the preceding claims, wherein, following the removal of the stimulus, the effect of the stimulus upon the crystal remains for a delay period.
- 15 54. An optically variable security device according to any of the preceding claims comprising photoluminescent particles whose lifetime is affected by the external stimulus.
55. A security document comprising a security device according to any of the preceding claims wherein the security device is adhered to or substantially  
20 contained within the security document.
56. A security document according to claim 55, wherein the device is embedded within a document window so as to provide crystal surfaces for receiving incident light on each of opposing faces of the document.
57. A security document according to claim 55 or claim 56, wherein the  
25 device is overlaid upon, applied to or forms part of an additional security feature.
58. A security document according to any of claims 55 to 57, wherein the security device is supported upon a transparent layer.

59. A security document according to any of claims 55 to 58, wherein the security device is provided as a projection such that it or a part attached to the device may be grasped by a user and elastically deformed so as to apply the stimulus.
- 5 60. A security document according to any of claims 55 to 59, wherein the security device is provided in a form selected from the group of a security thread, a security fibre, a security patch, a security strip, a security stripe or a security foil.
61. A security document according to any of claims 55 to 60, wherein the  
10 security document is a bank note.






Figure 1




Figure 2




Figure 3




Figure 4a




Figure 4b




Figure 5




Figure 6a




Figure 6b




Figure 7

Photonic crystal device




Figure 8a

Aperture




Figure 8b

Paper substrate

8/16




Figure 8c






Figure 9




Figure 10a Secure document




Figure 10b




Figure 10c

11/16




Figure 11




Figure 12




Figure 13




Figure 14




Figure 15




Figure 16




Figure 17




Figure 18




Figure 19




Figure 20



# INTERNATIONAL SEARCH REPORT

International application No

PCT/GB2007/003057

**A. CLASSIFICATION OF SUBJECT MATTER**  
 INV. B42D15/10 B42D15/00

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)  
 B42D G02B C09C B41M G06K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, CHEM ABS Data

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 2003/179364 A1 (R.A.STEENBLIK ET AL.) 25 September 2003 (2003-09-25) paragraphs [0003], [0008], [0058], [0079], [0172], [0173] -----	1-61
A	WO 2006/018094 A (MERCK PATENT GMBH) 23 February 2006 (2006-02-23) page 1, line 1 - line 17 page 15, line 25 - page 16, line 13 page 18, line 22 - line 31 page 21, line 1 - line 8 claims 1,21,22,33,35 ----- -/--	1-61

Further documents are listed in the continuation of Box C.

See patent family annex.

\* Special categories of cited documents :

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*B\* document member of the same patent family

Date of the actual completion of the international search

25 September 2007

Date of mailing of the international search report

05/10/2007

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2  
 NL - 2280 HV Rijswijk  
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
 Fax: (+31-70) 340-3016

Authorized officer

Bacon, Alan

## INTERNATIONAL SEARCH REPORT

International application No

PCT/GB2007/003057

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 03/062900 A (NANOVENTIONS, INC.) 31 July 2003 (2003-07-31) cited in the application page 5, line 27 - line 29 page 7, line 17 - line 21 page 26, line 13 - line 22 page 28, line 12 - line 29 figures 20,21 -----	1-61

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/GB2007/003057

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2003179364 A1	25-09-2003	NONE	
WO 2006018094 A	23-02-2006	DE 102004039754 A1	23-02-2006
WO 03062900 A	31-07-2003	EP 1476782 A1	17-11-2004
		EP 1476317 A1	17-11-2004
		WO 03061983 A1	31-07-2003