



(86) Date de dépôt PCT/PCT Filing Date: 2015/04/23
 (87) Date publication PCT/PCT Publication Date: 2015/11/05
 (45) Date de délivrance/Issue Date: 2022/06/21
 (85) Entrée phase nationale/National Entry: 2016/10/07
 (86) N° demande PCT/PCT Application No.: US 2015/027224
 (87) N° publication PCT/PCT Publication No.: 2015/167916
 (30) Priorité/Priority: 2014/04/30 (US61/986,249)

(51) Cl.Int./Int.Cl. *C22C 21/10* (2006.01)
 (72) Inventeurs/Inventors:
 YAN, XINYAN, US;
 SIMIELLI, EIDER, US;
 LIN, JEN C., US;
 ZHANG, WENPING, US;
 BRYANT, JAMES DANIEL, US
 (73) Propriétaire/Owner:
 ALCOA USA CORP., US
 (74) Agent: BERESKIN & PARR LLP/S.E.N.C.R.L.,S.R.L.

(54) Titre : ALLIAGES DE MOULAGE D'ALUMINIUM 7XX, ET LEURS PROCÉDES DE FABRICATION
 (54) Title: IMPROVED 7XX ALUMINUM CASTING ALLOYS, AND METHODS FOR MAKING THE SAME

(57) **Abrégé/Abstract:**

New 7xx aluminum casting alloys are disclosed. The aluminum casting alloys generally include from 3.0 to 8.0 wt. % Zn, from 1.0 to 3.0 wt. % Mg, where the wt. % Zn exceeds the wt. % Mg, from 0.35 to 1.0 wt. % Cu, where the wt. % Mg exceeds the wt. % Cu, from 0.05 to 0.30 wt. % V, from 0.01 to 1.0 wt. % of at least one secondary element (Mn, Cr, Zr, Ti, B, and combinations thereof), up to 0.50 wt. % Fe, and up to 0.25 wt. % Si, the balance being aluminum and other elements, wherein the aluminum casting alloy include not greater than 0.05 wt. % each of the other elements, and wherein the aluminum casting alloy includes not greater than 0.15 wt. % in total of the other elements.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau(10) International Publication Number
WO 2015/167916 A1(43) International Publication Date
5 November 2015 (05.11.2015)(51) International Patent Classification:
C22C 21/10 (2006.01)(21) International Application Number:
PCT/US2015/027224(22) International Filing Date:
23 April 2015 (23.04.2015)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
61/986,249 30 April 2014 (30.04.2014) US(71) Applicant: **ALCOA INC.** [US/US]; 201 Isabella Street,
Alcoa Corporate Center, Pittsburgh, Pennsylvania 15212-
5858 (US).(72) Inventors: **YAN, Xinyan**; 3801 Buckingham Court,
Murrysville, Pennsylvania 15668 (US). **SIMIELLI, Eider**;
170 Glenwood Drive, Monroeville, Pennsylvania 15146
(US). **LIN, Jen C.**; 1001 Alton Court, Export,
Pennsylvania 15632 (US). **ZHANG, Wenping**; 4048 Iris
Court, Murrysville, Pennsylvania 15668 (US). **BRYANT,
James Daniel**; 5089 Cypress Drive, Murrysville,
Pennsylvania 15668 (US).(74) Agents: **BRIGGS, Heath J.** et al.; Greenberg Traurig,
LLP, c/o Alcoa Inc., 100 Technical Drive, Alcoa Center,
Pennsylvania 15069 (US).(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY,
BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM,
DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT,
HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR,
KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG,
MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM,
PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC,
SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN,
TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ,
TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU,
TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE,
DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU,
LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK,
SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,
GW, KM, ML, MR, NE, SN, TD, TG).**Declarations under Rule 4.17:**


- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii))

Published:

- with international search report (Art. 21(3))

(54) Title: IMPROVED 7XX ALUMINUM CASTING ALLOYS, AND METHODS FOR MAKING THE SAME

(57) Abstract: New 7xx aluminum casting alloys are disclosed. The aluminum casting alloys generally include from 3.0 to 8.0 wt. % Zn, from 1.0 to 3.0 wt. % Mg, where the wt. % Zn exceeds the wt. % Mg, from 0.35 to 1.0 wt. % Cu, where the wt. % Mg exceeds the wt. % Cu, from 0.05 to 0.30 wt. % V, from 0.01 to 1.0 wt. % of at least one secondary element (Mn, Cr, Zr, Ti, B, and combinations thereof), up to 0.50 wt. % Fe, and up to 0.25 wt. % Si, the balance being aluminum and other elements, wherein the aluminum casting alloy include not greater than 0.05 wt. % each of the other elements, and wherein the aluminum casting alloy includes not greater than 0.15 wt. % in total of the other elements.



WO 2015/167916 A1

IMPROVED 7XX ALUMINUM CASTING ALLOYS, AND METHODS FOR MAKING THE SAME

CROSS-REFERENCE TO RELATED APPLICATIONS

[001] This patent application claims benefit of priority of U.S. Provisional Patent Application No. 61/986,249, filed April 30, 2014, entitled "IMPROVED 7XX ALUMINUM CASTING ALLOYS, AND METHODS FOR MAKING THE SAME".

BACKGROUND

[002] Aluminum alloys are useful in a variety of applications. However, improving one property of an aluminum alloy without degrading another property is elusive. For example, it is difficult to increase the strength of an aluminum casting alloy without affecting other properties such as castability, elongation or stress corrosion cracking. See, for example, U. S. Patent Application Publication No. 2008/0066833.

SUMMARY OF THE DISCLOSURE

[003] Broadly, the present patent application relates to improved 7xx aluminum casting alloys, and methods for producing the same. The new 7xx aluminum casting alloys may realize, for instance, an improved combination of at least two of strength, corrosion resistance, castability, and fatigue failure resistance, among other properties.

[004] The new 7xx aluminum casting alloys generally comprise (and in some instance consist essentially of, or consist of), zinc (Zn), magnesium (Mg), copper (Cu), and vanadium (V) as primary alloying elements, and at least one secondary element selected from the group consisting of manganese (Mn), chromium (Cr), zirconium (Zr), titanium (Ti), and boron (B), the balance being aluminum (Al), iron (Fe), silicon (Si), and other elements, as defined below.

[005] Regarding zinc, the new 7xx aluminum casting alloys generally include from 3.0 to 8.0 wt. % Zn. In one embodiment, a new 7xx aluminum casting alloy includes not greater than 7.5 wt. % Zn. In another embodiment, a new 7xx aluminum casting alloy includes not greater than 7.0 wt. % Zn. In yet another embodiment, a new 7xx aluminum casting alloy includes not greater than 6.5 wt. % Zn. In another embodiment, a new 7xx aluminum casting alloy includes not greater than 6.0 wt. % Zn. In yet another embodiment, a new 7xx aluminum casting alloy includes not greater than 5.5 wt. % Zn. In another embodiment, a new 7xx aluminum casting alloy includes not greater than 5.0 wt. % Zn. In one embodiment,

a new 7xx aluminum casting alloy includes at least 3.25 wt. % Zn. In another embodiment, a new 7xx aluminum casting alloy includes at least 3.5 wt. % Zn. In yet another embodiment, a new 7xx aluminum casting alloy includes at least 3.75 wt. % Zn. In another embodiment, a new 7xx aluminum casting alloy includes at least 4.0 wt. % Zn.

[006] The new 7xx aluminum casting alloys generally include magnesium in the range of from 1.0 to 3.0 wt. % Mg. The amount of zinc exceeds the amount of magnesium. In one embodiment, a new 7xx aluminum casting alloy includes not greater than 2.75 wt. % Mg. In another embodiment, a new 7xx aluminum casting alloy includes not greater than 2.5 wt. % Mg. In yet another embodiment, a new 7xx aluminum casting alloy includes not greater than 2.25 wt. % Mg. In another embodiment, a new 7xx aluminum casting alloy includes not greater than 2.0 wt. % Mg. In yet another embodiment, a new 7xx aluminum casting alloy includes not greater than 1.8 wt. % Mg. In one embodiment, a new 7xx aluminum casting alloy includes at least 1.1 wt. % Mg. In another embodiment, a new 7xx aluminum casting alloy includes at least 1.2 wt. % Mg. In yet another embodiment, a new 7xx aluminum casting alloy includes at least 1.3 wt. % Mg. In another embodiment, a new 7xx aluminum casting alloy includes at least 1.4 wt. % Mg.

[007] The new 7xx aluminum casting alloys generally include copper and in the range of from 0.35 to 1.0 wt. % Cu. The amount of magnesium exceeds the amount of copper. As shown below, copper may facilitate, for example, improved corrosion resistance and/or strength. In one embodiment, a new 7xx aluminum casting alloy includes not greater than 0.95 wt. % Cu. In another embodiment, a new 7xx aluminum casting alloy includes not greater than 0.90 wt. % Cu. In yet another embodiment, a new 7xx aluminum casting alloy includes not greater than 0.85 wt. % Cu. In another embodiment, a new 7xx aluminum casting alloy includes not greater than 0.80 wt. % Cu. In one embodiment, a new 7xx aluminum casting alloy includes at least 0.40 wt. % Cu. In another embodiment, a new 7xx aluminum casting alloy includes at least 0.45 wt. % Cu. In yet another embodiment, a new 7xx aluminum casting alloy includes at least 0.50 wt. % Cu. In another embodiment, a new 7xx aluminum casting alloy includes at least 0.55 wt. % Cu. In yet another embodiment, a new 7xx aluminum casting alloy includes at least 0.60 wt. % Cu.

[008] The new 7xx aluminum casting alloys generally include from 0.05 to 0.30 wt. % V. As shown below, vanadium may facilitate, for example, improved corrosion resistance. In one embodiment, a new 7xx aluminum casting alloy includes not greater than 0.25 wt. % V. In another embodiment, a new 7xx aluminum casting alloy includes not greater than 0.20 wt. % V. In yet another embodiment, a new 7xx aluminum casting alloy includes not greater

than 0.18 wt. % V. In another embodiment, a new 7xx aluminum casting alloy includes not greater than 0.16 wt. % V. In yet another embodiment, a new 7xx aluminum casting alloy includes not greater than 0.15 wt. % V. In another embodiment, a new 7xx aluminum casting alloy includes not greater than 0.14 wt. % V. In yet another embodiment, a new 7xx aluminum casting alloy includes not greater than 0.13 wt. % V. In another embodiment, a new 7xx aluminum casting alloy includes not greater than 0.12 wt. % V. In yet another embodiment, a new 7xx aluminum casting alloy includes not greater than 0.11 wt. % V. In one embodiment, a new 7xx aluminum casting alloy includes at least 0.06 wt. % V. In another embodiment, a new 7xx aluminum casting alloy includes at least 0.07 wt. % V. In yet another embodiment, a new 7xx aluminum casting alloy includes at least 0.08 wt. % V. In another embodiment, a new 7xx aluminum casting alloy includes at least 0.09 wt. % V. Not greater than 0.15 wt. % V should be used when fatigue properties are important.

[009] The new 7xx aluminum casting alloys generally include from 0.01 to 1.0 wt. % (in total) of one or more secondary elements, wherein the secondary elements are selected from the group consisting of manganese, zirconium, chromium, titanium, boron and combinations thereof. Such secondary elements may at least partially assist, for example, with achieving the appropriate grain structure and size. In one embodiment, the new 7xx aluminum casting alloys include 0.10 to 0.80 wt. % (in total) of the secondary elements. In another embodiment, the new 7xx aluminum casting alloys include 0.15 to 0.60 wt. % (in total) of the secondary elements. In another embodiment, the new 7xx aluminum casting alloys include 0.15 to 0.45 wt. % (in total) of the secondary elements. The one or more secondary elements may be included in the 7xx aluminum casting alloy, and in any combination that facilitates the appropriate grain size and structure, so long as the total amount of the secondary elements falls within the scope of the ranges provided above. In one embodiment, the secondary elements at least include zirconium. In another embodiment, the secondary elements at least include zirconium and titanium. In yet another embodiment, the secondary elements at least include zirconium, titanium, and boron. In yet another embodiment, the secondary elements at least include zirconium, manganese, titanium, and boron. In some of these embodiments, the 7xx aluminum casting alloy is substantially free of chromium, as defined below. In another embodiment, the secondary elements include all of zirconium, manganese, titanium, chromium and boron. In other embodiments, the 7xx aluminum casting alloy at least includes chromium, but is substantially free of one or more of manganese, zirconium, titanium, and boron, as defined below.

[0010] In embodiments where manganese is present, the new 7xx aluminum casting alloys generally include from 0.01 to 0.50 wt. % Mn. In one embodiment, a new 7xx aluminum casting alloy includes from 0.01 to 0.25 wt. % Mn. In another embodiment, a new 7xx aluminum casting alloy includes from 0.01 to 0.15 wt. % Mn. In yet another embodiment, a new 7xx aluminum casting alloy includes from 0.01 to 0.10 wt. % Mn. In another embodiment, a new 7xx aluminum casting alloy includes from 0.01 to 0.09 wt. % Mn. In yet another embodiment, a new 7xx aluminum casting alloy includes from 0.01 to 0.08 wt. % Mn. In yet another embodiment, a new 7xx aluminum casting alloy includes from 0.01 to 0.07 wt. % Mn. In some embodiments, the new 7xx aluminum casting alloys are substantially free of manganese, and, in these embodiments, contain less than 0.01 wt. % Mn.

[0011] In embodiments where zirconium is present, the new 7xx aluminum casting alloys generally include from 0.05 to 0.25 wt. % Zr. In one embodiment, a new 7xx aluminum casting alloy includes from 0.05 to 0.20 wt. % Zr. In another embodiment, a new 7xx aluminum casting alloy includes from 0.07 to 0.18 wt. % Zr. In some embodiments, the new 7xx aluminum casting alloys are substantially free of zirconium, and, in these embodiments, contain less than 0.05 wt. % Zr, such as less than 0.03 wt. % Zr, or less than 0.01 wt. % Zr.

[0012] In embodiments where chromium is present, the new 7xx aluminum casting alloys generally include from 0.05 to 0.40 wt. % Cr. In one embodiment, a new 7xx aluminum casting alloy includes from 0.10 to 0.35 wt. % Cr. In another embodiment, a new 7xx aluminum casting alloy includes from 0.15 to 0.25 wt. % Cr. In some embodiments, the new 7xx aluminum casting alloys are substantially free of chromium, and, in these embodiments, contain less than 0.05 wt. % Cr, such as less than 0.03 wt. % Cr, or less than 0.01 wt. % Cr.

[0013] In embodiments where titanium is present, the new 7xx aluminum casting alloys generally include from 0.01 to 0.25 wt. % Ti. In one embodiment, a new 7xx aluminum casting alloy includes from 0.01 to 0.15 wt. % Ti. In another embodiment, a new 7xx aluminum casting alloy includes from 0.01 to 0.10 wt. % Ti. In yet another embodiment, a new 7xx aluminum casting alloy includes from 0.01 to 0.08 wt. % Ti. In another embodiment, a new 7xx aluminum casting alloy includes from 0.02 to 0.07 wt. % Ti. In some embodiments, the new 7xx aluminum casting alloys are substantially free of titanium, and, in these embodiments, contain less than 0.01 wt. % Ti, such as less than 0.005 wt. % Ti, or less than 0.001 wt. % Ti.

[0014] In embodiments where boron is present, the new 7xx aluminum casting alloys generally include from 0.001 to 0.050 wt. % B. In one embodiment, a new 7xx aluminum

casting alloy includes from 0.005 to 0.040 wt. % B. In another embodiment, a new 7xx aluminum casting alloy includes from 0.010 to 0.030 wt. % B. In some embodiments, the new 7xx aluminum casting alloys are substantially free of boron, and, in these embodiments, contain less than 0.001 wt. % Ti, such as less than 0.0005 wt. % B, or less than 0.0001 wt. % B.

[0015] The new 7xx casting alloys may include iron, up to 0.50 wt. % Fe, sometimes as an impurity. In one embodiment, a new 7xx aluminum casting alloy includes not greater than 0.35 wt. % Fe. In another embodiment, a new 7xx aluminum casting alloy includes not greater than 0.25 wt. % Fe. In yet another embodiment, a new 7xx aluminum casting alloy includes not greater than 0.15 wt. % Fe. In another embodiment, a new 7xx aluminum casting alloy includes not greater than 0.10 wt. % Fe. In one embodiment, a new 7xx aluminum casting alloy includes at least 0.01 wt. % Fe.

[0016] The new 7xx casting alloys may include silicon, up to 0.25 wt. % Si, sometimes as an impurity. In one embodiment, a new 7xx casting alloy includes not greater than 0.20 wt. % Si. In another embodiment, a new 7xx casting alloy includes not greater than 0.15 wt. % Si. In yet another embodiment, a new 7xx casting alloy includes not greater than 0.10 wt. % Si. In another embodiment, a new 7xx casting alloy includes not greater than 0.05 wt. % Si. In one embodiment, a new 7xx aluminum casting alloy includes at least 0.01 wt. % Si.

[0017] The new 7xx aluminum casting alloy may be substantially free of other elements. As used herein, "other elements" means any other elements of the periodic table other than the above-listed zinc, magnesium, copper, vanadium, manganese, zirconium, chromium, titanium, boron, iron, and silicon, as described above. In the context of this paragraph, the phrase "substantially free" means that the new 7xx aluminum casting alloys contain not more than 0.10 wt. % each of any element of the other elements, with the total combined amount of these other elements not exceeding 0.35 wt. % in the new 7xx aluminum casting alloys. In another embodiment, each one of these other elements, individually, does not exceed 0.05 wt. % in the new 7xx aluminum casting alloys, and the total combined amount of these other elements does not exceed 0.15 wt. % in the new 7xx aluminum casting alloys. In another embodiment, each one of these other elements, individually, does not exceed 0.03 wt. % in the new 7xx aluminum casting alloys, and the total combined amount of these other elements does not exceed 0.10 wt. % in the new 7xx aluminum casting alloys.

[0018] In one embodiment, the new 7xx aluminum casting alloy is cast into a 7xx shape-cast part. In this regard, the casting step may be low pressure die casting, gravity permanent mold, semi-permanent mold, squeeze, casting, sand mold casting and spin / centrifugal

casting. After the casting, the 7xx casting alloy may be tempered, such as by solution heat treating, and then quenching, and then natural or artificially aging. Suitable tempers include the T4, T5, T6, and T7 tempers, for instance.

[0019] The 7xx shape-cast part may be used in any suitable application, such as in any of an automotive, aerospace, industrial or commercial transportation application, among others. In one embodiment, the 7xx shape-cast part is an automotive part (e.g., a body-in-white (BIW) part; a suspension part). In one embodiment, the 7xx shape-cast part is included in an automobile. In one embodiment, the 7xx shape-cast part is an aerospace part. In one embodiment, the 7xx shape-cast part is included in an aerospace vehicle. In one embodiment, the 7xx shape-cast part is an industrial part. In one embodiment, the 7xx shape-cast part is a commercial transportation part. In one embodiment, the 7xx shape-cast part is included in a commercial transportation vehicle.

[0020] Although the new 7xx alloys have been described as shape-casting alloys, it is anticipated that the alloy compositions described herein may also be useful in producing wrought products. For instance, the alloys described herein may be cast (e.g., as ingot or billet), then homogenized, and then hot worked to an intermediate or final form (e.g., cold working after the hot working when the hot working produces an intermediate form). In one embodiment, the hot working is forging. In one embodiment, the forging produces a shaped product, such as a wheel product. In another embodiment, the hot working is rolling or extruding. After the hot working (and any optional cold working), the new alloy may be tempered, such as by solution heat treating, and then quenching, and then natural or artificially aging. Suitable tempers include the T4, T5, T6, and T7 tempers, for instance. In one embodiment, the new alloy compositions described herein are processed into a forged wheel product per the processes described in commonly-owned U.S. Patent Application Publication No. 2006/0000094, which is incorporated herein by reference in its entirety.

DETAILED DESCRIPTION

Example 1

[0021] Several 7xx aluminum casting alloys having the compositions shown in Table 1, below, were cast via directional solidification. The dimensions of the directionally solidified alloys were approximately 25.4 mm (1 inch) thick, 102 mm (4 inches) wide, and 254 mm (10 inches) long.

Table 1 - Composition of Example 1 Alloys (in wt. %)

Alloy	Actual Composition, wt. %									
	Zn	Mg	Cu	Fe	Si	Mn	Ti	V	Zr	B
A1	4.21	1.55	0.65	0.08	0.05	0.05	0.07	0.009	0.09	0.02
A2	4.20	1.56	0.65	0.08	0.05	0.05	0.07	0.057	0.09	0.02
A3	4.35	1.62	0.63	0.08	0.05	0.05	0.06	0.103	0.09	0.02
A4	4.33	1.63	0.63	0.08	0.05	0.05	0.07	0.151	0.09	0.02

Alloys A2-A4 are invention alloys.

[0022] After casting, the alloys were solution heated by heating from room temperature to about 515.6°C (960°F), in about 2 hours, holding at about 515.6°C (960°F) for 6 hours, and then quenching in boiling water. The alloys were then naturally aged for about 12-24 hours, and then artificially aged by heating to about 204°C (400°F) in about 50 minutes, holding at about 204°C (400°F) for about 10 minutes, cooling to 182°C (360°F) in about 15 minutes, holding at 182°C (360°F) for about 4 hours, and then air cooling to room temperature.

[0023] The Stress corrosion cracking (SCC) resistance of the alloys was then in accordance with ASTM G103-97(2011), the "Standard Practice for Evaluating Stress-Corrosion Cracking Resistance of Low Copper 7XXX Series Al-Zn-Mg-Cu Alloys in Boiling 6% Sodium Chloride Solution". A stress level of 240 MPa was used for all specimens evaluated. Five replicated SCC specimens were used for each alloy. The SCC results are shown in Table 2, below.

Table 2 - SCC boiling salt test results of Example 1 Alloys

Alloy	Days to Failure				
A1	10	OK 14	2.91	OK 14	5.9
A2	7.23	OK 14	OK 14	12.02	OK 14
A3	OK 14	OK 14	OK 14	OK 14	OK 14
A4	OK 14	OK 14	OK 14	OK 14	OK 14

"OK 14" = passed 14 days of testing without failure.

[0024] The addition of vanadium improves the SCC performance of the Al-Zn-Mg-Cu alloys. Two specimens of alloy A1 failed within one week in boiling salt tests, whereas the specimens of vanadium-containing alloys passed 1-week boiling salt tests without failure. Larger vanadium content leads to improved SCC performance. Two SCC specimens of alloy A2 (0.057 wt. % V) failed in between one to two weeks, while specimens of A3 (0.103 wt. % V) and A4 (0.151 wt. % V) passed two weeks without any failures.

[0025] The mechanical properties of the alloys were also tested in accordance with ASMT B557 and E8, the results of which are shown in Table 3, below. Adding vanadium did not materially impact tensile or yield strength, but did decrease elongation slightly.

Table 3 - Mechanical Properties of Example 1 Alloys

Alloy	Yield Strength, MPa	Tensile Strength, MPa	Elongation, %
A1	320.8	376.0	11.0
A2	305.9	365.4	10.3
A3	323.4	376.9	9.0
A4	321.3	375.0	9.0

Example 2

[0026] Several 7xx aluminum casting alloys having the compositions shown in Table 4, below, were prepared as per Example 1. SCC and mechanical properties were again measured using the same ASTM tests and conditions used in Example 1, the results of which are shown in Tables 5-6, below.

Table 4 - Composition of Example 2 Alloys (in wt. %)

Alloy	Actual composition, wt. %									
	Zn	Mg	Cu	Fe	Si	Mn	Ti	V	Zr	B
B1	4.39	1.61	--	0.10	0.05	0.05	0.07	0.11	0.093	0.02
B2	4.38	1.61	0.25	0.10	0.05	0.05	0.07	0.11	0.093	0.02
B3	4.38	1.62	0.48	0.10	0.05	0.05	0.07	0.10	0.091	0.02
B4	4.39	1.61	0.78	0.10	0.05	0.05	0.07	0.11	0.091	0.02

Alloys B3 and B4 are invention alloys.

Table 5 - SCC boiling salt test results for Example 2 Alloys

Alloy	Days to Failure				
B1	0.08	0.08	0.08	0.08	0.08
B2	0.08	0.75	3.74	0.75	0.92
B3	OK7	OK7	OK7	OK7	OK7
B4	OK7	OK7	OK7	5.77	OK7

"OK 7" = passed 7 days of testing without failure.

Table 6 - Mechanical Properties of Example 2 Alloys

Alloy	Yield Strength, MPA	Tensile Strength, MPA	Elongation, %
B1	268.5	323.0	12.0
B2	284.5	338.8	10.3
B3	301.5	353.8	8.7
B4	323.0	367.2	6.7

[0027] As shown in Table 5, copper had a significant impact on SCC performance. All specimens of the alloy without copper (B1) failed in less than 2 hours (0.08 days). All specimens of the alloy with 0.48 wt. % Cu (B3) passed 7 days of testing at a stress level of 240MPa. As shown in Table 6, increasing copper generally increases strength, but decreases elongation.

[0028] While various embodiments of the present disclosure have been described in detail, it is apparent that modifications and adaptations of those embodiments will occur to those skilled in the art. However, it is to be expressly understood that such modifications and adaptations are within the spirit and scope of the present disclosure.

CLAIMS

What is claimed is:

1. An aluminum casting alloy consisting of:

(a) from 3.0 to 8.0 wt. % Zn;

(b) from 1.0 to 3.0 wt. % Mg;

wherein the wt. % Zn exceeds the wt. % Mg;

(c) from 0.35 to 1.0 wt. % Cu;

wherein the wt. % Mg exceeds the wt. % Cu;

(d) from 0.05 to 0.30 wt. % V;

(e) from 0.01 to 1.0 wt. % of at least one secondary element, wherein the at least one secondary element is selected from the group consisting of Mn, Cr, Zr, Ti, B, and combinations thereof;

wherein, when present, the aluminum casting alloy includes not greater than 0.50 wt. % Mn as a secondary element;

wherein, when present, the aluminum casting alloy includes not greater than 0.40 wt. % Cr as a secondary element;

wherein, when present, the aluminum casting alloy includes not greater than 0.25 wt. % Zr as a secondary element;

wherein, when present, the aluminum casting alloy includes not greater than 0.25 wt. % Ti as a secondary element;

wherein, when present, the aluminum casting alloy includes not greater than 0.05 wt. % B as a secondary element;

(f) up to 0.50 wt. % Fe

(g) up to 0.25 wt. % Si; and

(h) the balance being aluminum and other elements, wherein the aluminum casting alloy includes not greater than 0.05 wt. % each of the other elements, and wherein the aluminum casting alloy includes not greater than 0.15 wt. % in total of the other elements.

2. The aluminum casting alloy of claim 1, wherein the alloy includes not greater than 7.5 wt. % Zn.

3. The aluminum casting alloy of claim 1, wherein the alloy includes not greater than 7.0 wt. % Zn.

4. The aluminum casting alloy of claim 1, wherein the alloy includes not greater than 6.5 wt. % Zn.

5. The aluminum casting alloy of claim 1, wherein the alloy includes not greater than 6.0 wt. % Zn.

6. The aluminum casting alloy of claim 1, wherein the alloy includes not greater than 5.5 wt. % Zn.

7. The aluminum casting alloy of claim 1, wherein the alloy includes not greater than 5.0 wt. % Zn.

8. The aluminum casting alloy of any one of claims 1-7, wherein the alloy includes at least 3.25 wt. % Zn.

9. The aluminum casting alloy of any one of claims 1-7, wherein the alloy includes at least 3.5 wt. % Zn.

10. The aluminum casting alloy of any one of claims 1-7, wherein the alloy includes at least 3.75 wt. % Zn.
11. The aluminum casting alloy of any one of claims 1-7, wherein the alloy includes at least 4.0 wt. % Zn.
12. The aluminum casting alloy of any one of claims 1-11, wherein the alloy includes not greater than 2.75 wt. % Mg.
13. The aluminum casting alloy of any one of claims 1-11, wherein the alloy includes not greater than 2.5 wt. % Mg.
14. The aluminum casting alloy of any one of claims 1-11, wherein the alloy includes not greater than 2.25 wt. % Mg.
15. The aluminum casting alloy of any one of claims 1-11, wherein the alloy includes not greater than 2.0 wt. % Mg.
16. The aluminum casting alloy of any one of claims 1-11, wherein the alloy includes not greater than 1.8 wt. % Mg.
17. The aluminum casting alloy of any one of claims 1-11, wherein the alloy includes from 1.1 to 3.0 wt. % Mg.
18. The aluminum casting alloy of any one of claims 1-11, wherein the alloy includes from 1.2 to 3.0 wt. % Mg.
19. The aluminum casting alloy of any one of claims 1-11, wherein the alloy includes from 1.3 to 3.0 wt. % Mg.
20. The aluminum casting alloy of any one of claims 1-11, wherein the alloy includes from 1.4 to 3.0 wt. % Mg.
21. The aluminum casting alloy of any one of claims 1-20, wherein the alloy includes from 0.40 to 1.0 wt. % Cu.
22. The aluminum casting alloy of any one of claims 1-20, wherein the alloy includes from 0.45 to 1.0 wt. % Cu.
23. The aluminum casting alloy of any one of claims 1-20, wherein the alloy includes 0.50 to 1.0 wt. % Cu.
24. The aluminum casting alloy of any one of claims 1-20, wherein the alloy includes 0.55 to 1.0 wt. % Cu.
25. The aluminum casting alloy of any one of claims 1-20, wherein the alloy includes from 0.60 to 1.0 wt. % Cu.
26. The aluminum casting alloy of any one of claims 1-20, wherein the alloy includes not greater than 0.95 wt. % Cu.
27. The aluminum casting alloy of any one of claims 1-20, wherein the alloy includes not greater than 0.90 wt. % Cu.

28. The aluminum casting alloy of any one of claims 1-20, wherein the alloy includes not greater than 0.85 wt. % Cu.
29. The aluminum casting alloy of any one of claims 1-20, wherein the alloy includes not greater than 0.80 wt. % Cu.
30. The aluminum casting alloy of any one of claims 1-29, wherein the alloy includes not greater than 0.35 wt. % Fe.
31. The aluminum casting alloy of any one of claims 1-29, wherein the alloy includes not greater than 0.25 wt. % Fe.
32. The aluminum casting alloy of any one of claims 1-29, wherein the alloy includes not greater than 0.15 wt. % Fe.
33. The aluminum casting alloy of any one of claims 1-29, wherein the alloy includes not greater than 0.10 wt. % Fe.
34. The aluminum casting alloy of any one of claims 1-33, wherein the alloy includes not greater than 0.20 wt. % Si.
35. The aluminum casting alloy of any one of claims 1-33, wherein the alloy includes not greater than 0.15 wt. % Si.
36. The aluminum casting alloy of any one of claims 1-33, wherein the alloy includes not greater than 0.10 wt. % Si.
37. The aluminum casting alloy of any one of claims 1-33, wherein the alloy includes not greater than 0.05 wt. % Si.
38. The aluminum casting alloy of any one of claims 1-29, wherein the alloy includes from 0.01 to 0.25 wt. % Si and from 0.01 to 0.50 wt. % Fe.
39. The aluminum casting alloy of any one of claims 1-38, wherein the at least one secondary element at least includes Zr, and wherein the aluminum casting alloy includes from 0.05 to 0.25 wt. % Zr.
40. The aluminum casting alloy of claim 39, wherein the aluminum casting alloy includes from 0.05 to 0.20 wt. % Zr.
41. The aluminum casting alloy of claim 39, wherein the aluminum casting alloy includes from 0.07 to 0.18 wt. % Zr.
42. The aluminum casting alloy of any one of claims 1-41, wherein the at least one secondary element at least includes Mn, and wherein the aluminum casting alloy includes from 0.01 to 0.50 wt. % Mn.
43. The aluminum casting alloy of claim 42, wherein the aluminum casting alloy includes from 0.01 to 0.25 wt. % Mn.
44. The aluminum casting alloy of claim 42, wherein the aluminum casting alloy includes from 0.01 to 0.15 wt. % Mn.
45. The aluminum casting alloy of claim 42, wherein the aluminum casting alloy includes from 0.01 to 0.10 wt. % Mn.

46. The aluminum casting alloy of claim 42, wherein the aluminum casting alloy includes from 0.01 to 0.09 wt. % Mn.
47. The aluminum casting alloy of claim 42, wherein the aluminum casting alloy includes from 0.01 to 0.08 wt. % Mn.
48. The aluminum casting alloy of claim 42, wherein the aluminum casting alloy includes from 0.01 to 0.07 wt. % Mn.
49. The aluminum casting alloy of any one of claims 1-48, wherein the at least one secondary element at least includes Cr, and wherein the aluminum casting alloy includes from 0.05 to 0.40 wt. % Cr.
50. The aluminum casting alloy of claim 49, wherein the aluminum casting alloy includes from 0.10 to 0.35 wt. % Cr.
51. The aluminum casting alloy of claim 49, wherein the aluminum casting alloy includes from 0.15 to 0.25 wt. % Cr.
52. The aluminum casting alloy of any one of claims 1-48, wherein the alloy includes not greater than 0.04 wt. % Cr.
53. The aluminum casting alloy of any one of claims 1-52, wherein the at least one secondary element at least includes Ti, and wherein the aluminum casting alloy includes from 0.01 to 0.25 wt. % Ti.
54. The aluminum casting alloy of claim 53, wherein the aluminum casting alloy includes from 0.01 to 0.15 wt. % Ti.
55. The aluminum casting alloy of claim 53, wherein the aluminum casting alloy includes from 0.01 to 0.10 wt. % Ti.
56. The aluminum casting alloy of claim 53, wherein the aluminum casting alloy includes from 0.01 to 0.08 wt. % Ti.
57. The aluminum casting alloy of claim 53, wherein the aluminum casting alloy includes from 0.02 to 0.07 wt. % Ti.
58. The aluminum casting alloy of any one of claims 53-57, wherein the at least one secondary element at least includes Ti and B, and wherein the aluminum casting alloy includes from 0.001 to 0.050 wt. % B.
59. The aluminum casting alloy of claim 58, wherein the aluminum casting alloy includes from 0.005 to 0.040 wt. % B.
60. The aluminum casting alloy of claim 58, wherein the aluminum casting alloy includes from 0.010 to 0.030 wt. % B.
61. The aluminum casting alloy of any one of claims 1-60, wherein the at least one secondary element at least includes Zr and Ti.
62. The aluminum casting alloy of any one of claims 1-61, wherein the at least one secondary element at least includes Zr, Ti, and B.
63. The aluminum casting alloy of any one of claims 1-62, wherein the at least one secondary element at least includes Zr, Mn, Ti, and B.

64. The aluminum casting alloy of any one of claims 1-63, wherein the at least one secondary element includes Zr, Mn, Ti, Cr, and B.
65. The aluminum casting alloy of claim 64, wherein the alloy includes not greater than 0.04 wt. % Cr.
66. The aluminum casting alloy of any one of claims 1-65, wherein the aluminum casting alloy includes not greater than 0.25 wt. % V.
67. The aluminum casting alloy of any one of claims 1-65, wherein the aluminum casting alloy includes not greater than 0.20 wt. % V.
68. The aluminum casting alloy of any one of claims 1-65, wherein the aluminum casting alloy includes not greater than 0.18 wt. % V.
69. The aluminum casting alloy of any one of claims 1-65, wherein the aluminum casting alloy includes not greater than 0.16 wt. % V.
70. The aluminum casting alloy of any one of claims 1-65, wherein the aluminum casting alloy includes not greater than 0.15 wt. % V.
71. The aluminum casting alloy of any one of claims 1-65, wherein the aluminum casting alloy includes not greater than 0.14 wt. % V.
72. The aluminum casting alloy of any one of claims 1-65, wherein the aluminum casting alloy includes not greater than 0.13 wt. % V.
73. The aluminum casting alloy of any one of claims 1-65, wherein the aluminum casting alloy includes not greater than 0.12 wt. % V.
74. The aluminum casting alloy of any one of claims 1-65, wherein the aluminum casting alloy includes not greater than 0.11 wt. % V.
75. The aluminum casting alloy of any one of claims 1-65, wherein the aluminum casting alloy includes from 0.06 to 0.30 wt. % V.
76. The aluminum casting alloy of any one of claims 1-65, wherein the aluminum casting alloy includes from 0.07 to 0.30 wt. % V.
77. The aluminum casting alloy of any one of claims 1-65, wherein the aluminum casting alloy includes from 0.08 to 0.30 wt. % V.
78. The aluminum casting alloy of any one of claims 1-65, wherein the aluminum casting alloy includes from 0.09 to 0.30 wt. % V.
79. A shape-cast part made from the aluminum casting alloy of any one of claims 1-78.
80. The shape cast-part of claim 79, wherein the shape-cast part is an automobile part.
81. A wrought aluminum alloy product made from the aluminum casting alloy of any one of claims 1-78.
82. The wrought aluminum alloy product of claim 81, wherein the wrought aluminum alloy product is a forged wheel product.