

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
8 February 2007 (08.02.2007)

PCT

(10) International Publication Number
WO 2007/015676 A1

(51) International Patent Classification:
C09D 5/16 (2006.01) *A01P 13/00* (2006.01)
A01N 43/48 (2006.01)

(21) International Application Number:
PCT/SE2006/050275

(22) International Filing Date: 2 August 2006 (02.08.2006)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/705,321 4 August 2005 (04.08.2005) US
11/497,454 1 August 2006 (01.08.2006) US

(71) Applicant (for all designated States except US): **I-TECH AB** [SE/SE]; Erik Dahlbergsgatan 11A, S-411 26 Göteborg (SE).

(72) Inventor: **MÅRTENSSON, Lena**; Grindslanten 5, S-442 39 Kungälv (SE).

(74) Agent: **FAGERLIN, Heléne**; Albihs International IP & Law Offices, Linnégatan 2, Box 5581, S-114 85 Stockholm (SE).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:
— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 2007/015676 A1

(54) Title: USE OF A COMBINATION OF SUBSTANCES TO PREVENT BIOFOULING ORGANISMS

(57) Abstract: A combination of selected substances in paint to prevent the settlement and growth of different bio-fouling organisms with a reduced negative effect on the ecosystems compared to present methods. Useful substances include medetomidine with various copper and zinc formulations, tolylfluanide, diclofluanide, Diuron and Irgarol. or more general biocides such as SeaNine (4,5-dichloro-2-n-octyl-3(2H)-isothiazolone) or EcoNea C2-(p-chlorophenyl)-3-Cyano-4-bromo-5-trifluoromethyl).

USE OF A COMBINATION OF SUBSTANCES TO PREVENT BIOFOULING ORGANISMS

CROSS-REFERENCE TO RELATED APPLICATIONS

This application claims priority from U.S. provisional patent application SN
60/705,321 filed August 4, 2005, the disclosure of which is incorporated herein by
reference.

BACKGROUND OF THE INVENTION

Field of the Invention

This invention relates to the use of a combination of selected
substances in paint to simultaneously prevent the settlement and growth of different
bio-fouling organisms, such as barnacles and algae.

Description of the Related Art

Biological growth (or bio-fouling) on marine installations and ships
constitutes a significant problem for the shipping industry and for owners of marine
installations and boats and ships at large. An untreated ship hull will rapidly
accumulate fouling of marine plants and animals, which considerably increases hull-
to-water friction and consequently, fuel consumption. Also other marine industries
and installations, e.g., aqua culture equipment and oil/gas off-shore installations and
plants have significant problems with marine bio-fouling.

One way of preventing marine bio-fouling is to apply paint with toxic
contents, e.g. tributyltin oxide (TBT) or copper. The use of marine paints with such
contents has, however, proven to cause significant harm to the marine ecosystem
including plants, animal species and humans. (1, 2). Many countries and
international organizations have therefore introduced restrictions and prohibitions
over their use, and further restrictions are expected. Sale and application of TBT
antifouling is to cease, under the International Maritime Organization (IMO)

Antifouling System Convention agreed in October 2001. The treaty calls for the ban on application from the first of January 2003, and total prohibition on hulls by the first of January 2008.

It is therefore of interest to find new solutions to prevent marine bio-fouling, to be able to reduce levels of metal and metal-oxides in paints and eventually replace them completely (3-5).

Mechanical cleaning of marine surfaces has been introduced as an alternative to toxics and biocides. Notably, water jet cleaning and mechanical cleaning using brushes are in use. Most of these methods are work-intensive, however, and are therefore expensive.

The tributyltin-ban (TBT) is a reality since the international paint companies have excluded TBT-containing paints from their product portfolio. Instead, the basic biocides are copper, copper oxide or other copper based formulations. When the copper compounds are used in reduced concentrations for ecological reasons, however, these paints need booster biocides against barnacles and algae to achieve a performance acceptable for ship owners and other types of marine industries. Also, paints with specific new compounds active mostly against barnacles, such as medetomidine ("Catemine I") as described below, will need a complementary booster compound against algae.

Along the Swedish west coast as well as along the coasts of the North Atlantic Ocean, barnacles and different kinds of algae are particularly apparent problems. The fully grown barnacle is a stationary crustacean, characterized by a centimeter-sized cone shape and enclosing layers of calcinous plates. The mechanical strength of the animal's attachment to solid surfaces is very high, and it is therefore difficult to mechanically remove barnacles from solid surfaces. The animal undergoes different development stages as free-swimming larvae, where the last larva stage is referred to as the cyprid stage. The cyprid screens solid surfaces suitable for settling with the help of a nervous protuberance. A "settling-glue" referred to as balanus cement is secreted from specialized glands localized near the protuberance and the animal thereby settles to the solid surface. After settlement the animal undergoes a metamorphosis into an adult and stationary animal. When using

an old copper leaking paint with high concentrations of copper, barnacles are one of the first organisms to foul.

Algae are also relatively insensitive to copper and the amount of leaking copper needed to inhibit fouling of algae is high. Therefore, copper-containing marine antifouling paints are “boosted” by some manufacturers with more specific algicides. The algicides inhibit the zoospores from attaching or inhibit photosynthesis. Both methods give the result of reduced algae fouling.

Previously various compounds have been described and used that interfere with nerve signalling or other specific action against the fauna of marine bio-fouling organisms, such as barnacles or tube worms. For example, U.S. Patent No. 6,762,227 describes the use of medetomidine (Catemine 1) and other substances. Also, Swedish patent application No. 0300863-8 describes the use of spiroimidazoline (Catemine 3) for the same purpose. However, the use of such products has no or very little effect on algae. For example, Catemine 1 (6) has a specific action on barnacle cyprids but no effect of algal growth due to the target protein being lacking within algae. This is true also for other pharmacological acting substances (7-11).

There are several methods to prevent algal growth, among them the use of copper and other metals in fairly high concentrations. Algicides are often invented as herbicides and are photosynthesis-inhibitors such as Diuron (3-(3,4-dichlorophenyl)-1,1-dimethylurea) by DuPont Agricultural Products Wilmington, DE, USA and Irgarol 1051 (2-methylthio-4-tert-butylamino-6-cyclopropylamino-s-triazine) by Ciba Inc, Tarrytown, NY, USA. A more common strategy is to use fungicides such as zincpyrithione (Zinc, bis(1-hydroxy-2(1H)-pyridinethionato-O,S)-, (T-4)-) by Arc Chemicals Inc and copperpyrithione (Copper, bis(1-hydroxy-2(1H)-pyridinethionato-O,S)-, (T-4)-) by Arc Chemicals Inc, tolylfluanide (N-(Dichlorofluoromethylthio)-N',N'-dimethyl-N-p-tolylsulfamide) by Bayer Chemicals, Pittsburgh, PA, USA, diclofluanide (N'-dimethyl-N-phenylsulphamide) by Bayer Chemicals, zineb (zinc ethylene bisdithiocarbamate) by FMC corp., zinram (Zinc bis (dimethylthiocarbamates)) (3-5) by Taminco, or quaternary ammonium compounds. A third strategy is to use toxic compounds but with short half life such as SeaNine (4,5-dichloro-2-n-octyl-3(2H)-isothiazolone) by Rohm and Haas Company,

Philadelphia, PA, USA and related compounds (12-13).

A strategy that has received a lot of attention for several years is to find natural substances that may work as antifoulants in paint. These substances are endogenously produced by different marine invertebrates and algae to protect their own surface from fouling. Several compounds have been isolated and identified and their antifouling activity been measured (4).

There is a need however to find compounds, or a combination of compounds, to be applied in antifouling paint so that such paint is more effective against both types of organisms such as barnacles and algae without having as many negative ecological effects as paint with high levels of metal-compounds.

SUMMARY OF THE INVENTION

The invention at hand refers to a method which is an ecologically acceptable way to prevent both cyprid larvae and algae from establishing at solid surfaces. The old kind of bio-fouling paints with high concentrations of metals are active against both barnacles and algae, but have several negative environmental effects. A reduced concentration of the active metal-compound in such paints will make it non-effective particular against algae and barnacles. Newer more ecological compounds, used, or proposed to be used, in antifouling are more effective against one or the other group of fouling organisms.

The present invention solves this problem by providing new and effective combinations of antifouling agents, such as medetomidine (Catemine 1) ((+/-)-4-[1-(2,3-dimethylphenyl)ethyl]-1H-imidazole) with Igarol (2-methylthio-4-tert-butylamino-6-cyclopropylamino-s-triazine), or medetomedine with Dichlofluanid and other combinations.

Other objects and features of the inventions will be more fully apparent from the following disclosure.

DETAILED DESCRIPTION OF THE INVENTION AND PREFERRED EMBODIMENTS THEREOF

The principle of the method of the invention is to use substances which disturb or block the nerve signalling to the target cells in the cyprid larvae in

combination with anti-algae compounds, for example, fungicides like zinc- and copper pyrithione, tolylfluanide and diclofluanide, herbicides such as Diuron and Irgarol, or more general biocides such as SeaNine or EcoNea (2-(p-chlorophenyl)-3-cyano-4-bromo-5-trifluoromethyl) by Janssen Pharmaceutical, Titusville, NJ, USA.

5 By using low toxic biodegradable compounds as booster biocides, it will be possible to reduce the non-biodegradable copper in a paint. One such example can be to use the environmentally friendly compounds to disturb important nerve signalling in barnacles and the like, while at the same time maintain low levels of metal-compounds in combination of a biodegradable algicide, with substantially less
10 negative effect on the environment. One important practical and industrial application of this invention is to mix these substances into a polymer base (paint). The polymer (paint) is consequently applied to ship hulls and in the seawater environment the substances will slowly release from the polymer. Settling cyprid larvae will consequently be disturbed in such a way that settling cannot take place.
15 By the addition of a booster algicide it is also possible to prevent algal growth. The invention includes the use of relatively low toxic pharmacological substances, e.g. medetomidines, which disturb, imitate or block nerve signal processing to the cells of some organisms, for example barnacles, in settling on solid surfaces and the combination with other substances for the prevention of settlement and growth of
20 algae which inhibit algal adhesion or growth. The immediate application of the invention is to add the substances in a base polymer paint which is later applied on e.g. ship hulls.

Example 1

25 The efficacy of algicides is usually tested by a spore germination test. Algae are collected from the field and grown in the laboratory. After induced sporulation the spores are added to test vials, with the test compound dissolved in pasteurized deep sea water, where they are allowed to settle in darkness for a couple of hours (2-3 h) to give an even distribution of settled spores in the vials. The water with test
30 compound is then removed and culture medium is added. The spores are left to germinate under fluorescent lamps (50 $\mu\text{Mm}^{-2}\text{s}^{-1}$ (PAR)), 16 h light, 8 h darkness, for 7 days in a culture medium, which is changed once a day.

Catemine 1 is to be combined with an effective anti-algae compound according to the invention, such as dichlofluanid (table 1), SeaNine (table 2), Irgarol (table 3) and Diuron (table 4). All the different brands are tested in combination with Catemine 1 for efficacy against both barnacles and algae with the two compounds together or separate. The assays that are to be used are the cyprid settling rate assay and the algae germination test.

By using this kind of a combination, it is possible to prevent fouling from both barnacles and macroalgae and increase the total efficacy of the antifouling paint.

10 Table 1

Catemine 1 (nM)	Dichlofluanid (µg/ml)	Barnacle biofouling (% settlement)	Ulva biofouling (% survival)
0	0	100	100
0.1	0	100	100
1	0	10	100
10	0	0	100
100	0	0	100
0	0	100	100
0	0.1	100	100
0	1	50	90
0	10	25	10
0	100	0	0
0	0	100	100
0.1	0.1	100	100
1	1	10	90
10	10	0	10
100	100	0	0

Table 2

Catemine 1 (nM)	SeaNine (nM)	Barnacle biofouling (% settlement)	Ulva biofouling (% survival)
0	0	100	100
0.1	0	100	100
1	0	10	100
10	0	0	100
100	0	0	100
0	0	100	100
0	0.1	100	100
0	1	50	50
0	10	10	10
0	100	0	0
0	0	100	100
0.1	0.1	100	100
1	1	10	50
10	10	0	10
100	100	0	0

Table 3

5

Catemine 1 (nM)	Irgarol (nM)	Barnacle biofouling (% settlement)	Enteromorpha biofouling (% survival)
0	0	100	100
0.1	0	100	100
1	0	10	100
10	0	0	100
100	0	0	100
0	0	100	100
0	0.1	100	100
0	1	100	100
0	10	100	50
0	100	100	0
0	0	100	100
0.1	0.1	100	100
1	1	10	100

10	10	0	50
100	100	0	0

Table 4

Catamine 1 (nM)	Diuron (μ M)	Barnacle biofouling (% settlement)	Ulva biofouling (% survival)
0	0	100	100
0.1	0	100	100
1	0	10	100
10	0	0	100
100	0	0	100
0	0	100	100
0	0.1	100	100
0	1	100	90
0	10	100	50
0	100	100	0
0	0	100	100
0.1	0.1	100	100
1	1	10	90
10	10	0	50
100	100	0	0

5

While the invention has been described with reference to specific embodiments, it will be appreciated that numerous variations, modifications, and embodiments are possible, and accordingly, all such variations, modifications, and embodiments are to be regarded as being within the spirit and scope of the invention.

References:

1. Ruiz, J.M., Bachelet, G., Caumette, P. and Donard, O.F.X. Three decades of tributyltin in the coastal environment with emphasis on Arachon Bay, France. *Environmental Pollution* 93(2) 195-203, 1996.
- 5 2. Mizuhashi, S., Ikegaya, Y. and Matsuki, N. Pharmacological property of tributyltin in vivo and in vitro. *Environmental Toxicology and Pharmacology* 8, 205-212, 2000.
3. Omae, I. Organotin antifouling paints and their alternatives. *Appl. Organometal. Chem.* 17, 81-105, 2003.
- 10 4. Omae, I. General aspects of tin-free antifouling paints. *Chem. Rev.* 103, 3431-3448, 2003.
5. Yebra, D.M., Kiil, S. And Dam-Johansen, K. Antifouling technology -- past, present and future steps towards efficient and environmentally friendly antifouling coatings. *Progress in Organic Coatings.* 50, 75-15 104,2004.
6. Dahlström M, Mårtensson LGE, Jonsson PR, Arnebrant T, Elwing H. Surface-active adrenoceptor compounds prevent the settlement of cyprid larvae of *Balanus improvisus*. *Biofouling* 16, 191– 203, 2000
7. Yamamoto H, Tachibana A, Saikawa W, Nagano M, Matsumura K, 20 Fusetani N. Effects of calmodulin inhibitors on cyprid larvae of the barnacle, *Balanus amphitrite*. *J. Exp. Zool.* 80:8–17, 1998.
8. Yamamoto H, Satuito CG, Yamazaki M, Natoyama K, Tachibana A, Fusetani N. Neurotransmitter blockers for antifoulants against planktonic larvae of the barnacle *Balanus amphitrite* and the mussel *Mytilus galloprovincialis*. *Biofouling* 13:69–82,1998.
- 25 9. Yamamoto, H., Shimizu, K., Tachibana, A. and Fusetani, N. Roles of dopamine and serotonin in larval attachment of the barnacle, *Balanus amphitrite*. *J. Exp. Zool.* 284, 746-758, 1999.
10. Faimali, M., Falugi, C., Gallus, L., Piazza, V. and Tagliaferro, C. 30 Involvement of acetylcholine in settlement of *Balanus amphitrite*. *Biofouling* 19 Suppl. 213-20, 2003.
11. Rittschof, D., Lai, C.H., Kok, L.M. and Teo, S.L. Pharmaceuticals as

antifoulants: concept and principles. Biofouling 19 Suppl. 207-12, 2003.

12. [http://www.janssenpharmaceutica.be/pmp/Pages/database/\\$Econea/\\$Leaflets/Econea%20028upd_PIS.pdf](http://www.janssenpharmaceutica.be/pmp/Pages/database/$Econea/$Leaflets/Econea%20028upd_PIS.pdf)
13. Jacobson, A.H. and Willingham, G.L. Sea-nine antifoulant: an environmentally acceptable alternative to organotin antifoulants. The Science of the Total Environment 258, 103-110, 2000.

THE CLAIMSWhat is Claimed is:

- 5 1. A method of preventing marine biofouling of a substrate by a marine biofouling organism, comprising applying a protective coating to the substrate, said coating containing a) a substance that affects nerve signaling in cyprid barnacles, and b) an algal inhibitory substance.
- 10 2. The method of preventing marine biofouling according to claim 1, wherein the substance that affects nerve signaling in cyprid barnacles is selected from the group consisting of medetomidine and spiroimidazoline.
- 15 3. The method of preventing marine biofouling according to claim 2, wherein the substance that affects nerve signaling in cyprid barnacles is medetomidine.
4. The method of preventing marine biofouling according to claim 2, wherein the algal inhibitory substance is selected from the group consisting of (3-(3,4-dichlorophenyl)-1,1-dimethylurea); (2-methylthio-4-tert-butylamino-6-cyclopropylamino-s-triziane); Zinc, bis(1-hydroxy-2(1H)-pyridinethionato-O,S)-, (T-4)-; Copper, bis(1-hydroxy-2(1H)-pyridinethionato-O,S)-, (T-4)-; tolylfluanide(N-(Dichlorofluoromethylthio)-N',N'-dimethyl-N-p-tolylsulfamide); diclofluanide (N' -dimethyl-N-phenylsulfamide); zinc ethylene bisdithiocarbamate) Zinc bis(dimethylthiocarbamates)) (3-5); quaternary ammonium compounds; 4,5-dichloro-2-n-octyl-3(2H)-isothiazolone).
- 20 5. The method of preventing marine biofouling according to claim 3, wherein the algal inhibitory substance is 2-methylthio-4-tert-butylamino-6-cyclopropylamino-s-triziane.
- 25 6. The method of preventing marine biofouling according to claim 4, wherein the algal inhibitory substance is 2-methylthio-4-tert-butylamino-6-
- 30

cyclopropylamino-s-triziane.

7. The method of preventing marine biofouling according to claim 3, wherein the algal inhibitory substance is N'-dimethyl-N-phenylsulphamide.
- 5
8. The method of preventing marine biofouling according to claim 4, wherein the algal inhibitory substance is N'-dimethyl-N-phenylsulphamide.
9. The method of preventing marine biofouling according to claim 1, wherein the protective coating further comprises o-xylene.
- 10
10. The method of preventing marine biofouling according to claim 1, wherein the protective coating further comprises a marine paint.
11. A product for preventing marine biofouling of a substrate by a marine biofouling organism, comprising a protective coating containing a) a substance that affects nerve signaling in cyprid barnacles, and b) an algal inhibitory substance.
- 15
12. The product for preventing marine biofouling according to claim 11, wherein the substance that affects nerve signaling in cyprid barnacles is selected from the group consisting of medetomidine and spiroimidazoline.
- 20
13. The product for preventing marine biofouling according to claim 12, wherein the substance that affects nerve signaling in cyprid barnacles is medetomidine.
- 25
14. The product for preventing marine biofouling according to claim 12, wherein the algal inhibitory substance is selected from the group consisting of (3-(3,4-dichlorophenyl)-1,1-dimethylurea); (2-methylthio-4-tert-butylamino-6-cyclopropylamino-s-triziane); Zinc, bis(1-hydroxy-2(1H)-pyridinethionato-O,S)-, (T-4)-; Copper, bis(1-hydroxy-2(1H)-pyridinethionato-O,S)-, (T-4)-; tolylfluanid (N-(Dichlorofluoromethylthio)-N',N'-dimethyl-N-p-
- 30
- tolylsulfamide); diclofluanide (N'-dimethyl-N-phenylsulphamide); zinc

ethylene bisdithiocarbamate) Zinc bis(dimethylthiocarbamates)) (3-5); quaternary ammonium compounds; 4,5-dichloro-2-n-octyl-3(2H)-isothiazolone).

- 5 15. The product for preventing marine biofouling according to claim 13, wherein the algal inhibitory substance is 2-methylthio-4-tert-butylamino-6-cyclopropylamino-s-triazine.
- 10 16. The product for preventing marine biofouling according to claim 14, wherein the algal inhibitory substance is 2-methylthio-4-tert-butylamino-6-cyclopropylamino-s-triazine.
- 15 17. The product for preventing marine biofouling according to claim 13, wherein the algal inhibitory substance is N'-dimethyl-N-phenylsulphamide.
18. The product for preventing marine biofouling according to claim 14, wherein the algal inhibitory substance is N'-dimethyl-N-phenylsulphamide.
- 20 19. The product for preventing marine biofouling according to claim 11, wherein the protective coating further comprises o-xylene.
20. The product for preventing marine biofouling according to claim 11, wherein the protective coating further comprises a marine paint.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE2006/050275

A. CLASSIFICATION OF SUBJECT MATTER

IPC: see extra sheet

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC: C09D, A01N, A01P

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-INTERNAL, WPI DATA, CA

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
E	WO 2006080890 A1 (I-TECH AB), 3 August 2006 (03.08.2006), whole document --	1-20
Y	US 5334389 A (DONALD J. GERHART), 2 August 1994 (02.08.1994), column 4, line 3 - line 19, claims 6,14,20,28	1-8,10-18,20
A	--	9,19
Y	GB 2278361 A (WATERLINE PAINTS LIMITED), 30 November 1994 (30.11.1994), page 2; page 3; page 6, line 16 - line 17, claims 1,9-11,14, abstract	1-4,7-14, 17-20
A	--	5-6,15-16

 Further documents are listed in the continuation of Box C. See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

16 November 2006

Date of mailing of the international search report

17-11-2006

Name and mailing address of the ISA/
Swedish Patent Office
Box 5055, S-102 42 STOCKHOLM
Facsimile No. +46 8 666 02 86

Authorized officer

Johanna Brolund/MP
Telephone No. +46 8 782 25 00

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 5252630 A (DONALD J. GERHART ET AL), 12 October 1993 (12.10.1993), column 5, line 21 - line 38, claims 9,19	1-8,10-18,20
A	--	9,19
Y	EP 0831134 A1 (SIGMA COATINGS B.V.), 25 March 1998 (25.03.1998), page 3, line 1 - line 6; page 5, line 6 - line 9, table 1	1-8,10-18,20
A	--	9,19
Y	WO 0042851 A1 (ELWING, HANS), 27 July 2000 (27.07.2000), page 4, line 26; page 5, line 3 - line 11, claims 8,18, abstract	1-20
Y	SE 03008638 A (I-TECH AB), 29 Sept 2004 (29.09.2004), page 2	1-20
A	EP 1042955 A1 (BAYER AG), 11 October 2000 (11.10.2000), paragraph (0007)	1-20
A	Diego Meseguer Yebra et al: "Antifouling technology-past, present and future steps towards efficient and environmentally friendly antifouling coatings" Progress in Organic Coatings, Vol 50, 2004, page 75-104; page 93 - page 98; page 100 - page 101	1-20
A	WO 03081199 A2 (INNOVENTUS PROJECT AB), 2 October 2003 (02.10.2003), page 13, line 27 - line 41; page 16	1-20

International patent classification (IPC)

C09D 5/16 (2006.01)

A01N 43/48 (2006.01)

A01P 13/00 (2006.01)

Download your patent documents at www.prv.se

The cited patent documents can be downloaded at www.prv.se by following the links:

- In English/Searches and advisory services/Cited documents (service in English) or
- e-tjänster/anförda dokument (service in Swedish).

Use the application number as username.

The password is **VKPPJUMGOJ**.

Paper copies can be ordered at a cost of 50 SEK per copy from PRV InterPat (telephone number 08-782 28 85).

Cited literature, if any, will be enclosed in paper form.

INTERNATIONAL SEARCH REPORT
Information on patent family members

01/11/2006

International application No.
PCT/SE2006/050275

WO	2006080890	A1	03/08/2006	US	20060189686 A	24/08/2006
US	5334389	A	02/08/1994	AU	5404394 A	09/05/1994
				CA	2146130 A,C	28/04/1994
				SG	49287 A	18/05/1998
				US	5470586 A	28/11/1995
				WO	9408904 A	28/04/1994
GB	2278361	A	30/11/1994	GB	9310873 D	00/00/0000
				GB	9410116 D	00/00/0000
US	5252630	A	12/10/1993	US	5314932 A	24/05/1994
EP	0831134	A1	25/03/1998	AU	744284 B	21/02/2002
				AU	4555597 A	14/04/1998
				CA	2265789 A,C	26/03/1998
				DE	69705228 D,T	11/10/2001
				DK	927230 T	03/09/2001
				EP	0927230 A,B	07/07/1999
				SE	0927230 T3	
				ES	2158590 T	01/09/2001
				GR	3036595 T	31/12/2001
				JP	2001503789 T	21/03/2001
				KR	2000036194 A	26/06/2000
				NO	320045 B	17/10/2005
				NO	991094 A	05/03/1999
				NZ	334505 A	28/07/2000
				PL	187300 B	30/06/2004
				PL	332276 A	30/08/1999
				PT	927230 T	28/12/2001
				TR	9900571 T	00/00/0000
				US	6069189 A	30/05/2000
				WO	9812269 A	26/03/1998
				ZA	9708449 A	24/03/1998

INTERNATIONAL SEARCH REPORT
Information on patent family members

01/11/2006

International application No.
PCT/SE2006/050275

WO	0042851	A1	27/07/2000	AT	244507	T	15/07/2003
				AU	748258	B	30/05/2002
				AU	2340700	A	07/08/2000
				DE	60003789	D,T	03/06/2004
				DK	1154688	T	13/10/2003
				EP	1154688	A,B	21/11/2001
				SE	1154688	T3	
				ES	2202046	T	01/04/2004
				JP	2002535255	T	22/10/2002
				NO	20013642	A	24/09/2001
				PT	1154688	T	28/11/2003
				SE	513474	C	18/09/2000
				SE	9900264	A	26/07/2000
				US	6762227	B	13/07/2004

SE	03008638	A	29/09/2004	NONE			
----	----------	---	------------	------	--	--	--

EP	1042955	A1	11/10/2000	AU	2639800	A	26/10/2000
				DE	19915476	A	12/10/2000
				JP	2000313855	A	14/11/2000
				NO	20001783	A	09/10/2000
				NZ	503798	A	31/08/2001
				US	6245784	B	12/06/2001
				DE	19922401	A	16/11/2000

WO	03081199	A2	02/10/2003	AU	2003232189	A	08/10/2003
				EP	1389264	A	18/02/2004
				JP	2004522022	T	22/07/2004
				SE	0200915	D	00/00/0000
