



(86) Date de dépôt PCT/PCT Filing Date: 2009/12/31  
(87) Date publication PCT/PCT Publication Date: 2010/07/08  
(45) Date de délivrance/Issue Date: 2016/02/23  
(85) Entrée phase nationale/National Entry: 2011/06/29  
(86) N° demande PCT/PCT Application No.: US 2009/069909  
(87) N° publication PCT/PCT Publication No.: 2010/078491  
(30) Priorité/Priority: 2008/12/31 (US61/141,694)

(51) Cl.Int./Int.Cl. *C11C 3/00* (2006.01),  
*C11C 3/04* (2006.01), *C11C 3/06* (2006.01),  
*C11C 3/10* (2006.01)

(72) Inventeurs/Inventors:  
BENECKE, HERMAN PAUL, US;  
GARBARK, DANIEL B., US;  
VIJAYENDRAN, BHIMA RAO, MY

(73) Propriétaire/Owner:  
BATTELLE MEMORIAL INSTITUTE, US

(74) Agent: GOWLING LAFLEUR HENDERSON LLP

(54) Titre : PRE-ESTERIFICATION DE POLYOLS PRIMAIRES POUR AMELIORER LA SOLUBILITE DANS DES SOLVANTS UTILISES DANS LE PROCEDE POLYOL  
(54) Title: PRE-ESTERIFICATION OF PRIMARY POLYOLS TO IMPROVE SOLUBILITY IN SOLVENTS USED IN POLYOL PROCESS

(57) **Abrégé/Abstract:**

Methods to pre-esterify primary polyols used in converting biobased oils, oil derivatives, and modified oils to highly functionalized esters, ester polyols, amides, and amide polyols.

## (12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau(43) International Publication Date  
8 July 2010 (08.07.2010)(10) International Publication Number  
**WO 2010/078491 A1**

## (51) International Patent Classification:

C11C 3/00 (2006.01) C11C 3/06 (2006.01)  
C11C 3/04 (2006.01) C11C 3/10 (2006.01)

## (21) International Application Number:

PCT/US2009/069909

## (22) International Filing Date:

31 December 2009 (31.12.2009)

## (25) Filing Language:

English

## (26) Publication Language:

English

## (30) Priority Data:

61/141,694 31 December 2008 (31.12.2008) US

(71) Applicant (for all designated States except US): **BATTELLE MEMORIAL INSTITUTE** [US/US]; 505 King Avenue, Columbus, OH 43201 (US).

## (72) Inventors; and

(75) Inventors/Applicants (for US only): **BENECKE, Herman, Paul** [US/US]; 920 Lansmere Lane, Columbus, OH 43220 (US). **GARBARK, Daniel, B.** [US/US]; 656 Cedar Run Drive, Blacklick, OH 43004 (US). **VIJAYENDRAN, Bhima, Rao** [US/MY]; A-26-2, Binjai Residency, No. 1 Binjai Lorong, Kuala Lumpur, 50450 (MY).(74) Agents: **PRIOR, Patricia, L.** et al.; Dinsmore & Shohl LLP, Fifth Third Center, Suite 1300, Dayton, OH 45402-2023 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO,

DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

## Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii))
- of inventorship (Rule 4.17(iv))

## Published:

- with international search report (Art. 21(3))
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments (Rule 48.2(h))

(54) Title: PRE-ESTERIFICATION OF PRIMARY POLYOLS TO IMPROVE SOLUBILITY IN SOLVENTS USED IN POLYOL PROCESS

(57) Abstract: Methods to pre-esterify primary polyols used in converting biobased oils, oil derivatives, and modified oils to highly functionalized esters, ester polyols, amides, and amide polyols.



WO 2010/078491 A1



-1-

**PRE-ESTERIFICATION  
OF PRIMARY POLYOLS TO IMPROVE SOLUBILITY IN  
SOLVENTS USED IN POLYOL PROCESS**

5           The invention provides for methods to convert vegetable and/or animal oils (e.g. soybean oil) to highly functionalized alcohols in essentially quantitative yields by an ozonolysis process. The functionalized alcohols are useful for further reaction to produce polyesters and polyurethanes. The invention provides a process that is able to utilize renewable resources such as oils and fats derived from plants and animals.

10           Polyols are very useful for the production of polyurethane-based coatings and foams as well as polyester applications. Soybean oil, which is composed primarily of unsaturated fatty acids, is a potential precursor for the production of polyols by adding hydroxyl functionality to its numerous double bonds. It is desirable that this hydroxyl functionality be primary rather than secondary to achieve enhanced polyol reactivity in the  
15 preparation of polyurethanes and polyesters from isocyanates and carboxylic acids, anhydrides, acid chlorides or esters, respectively. One disadvantage of soybean oil that needs a viable solution is the fact that about 16 percent of its fatty acids are saturated and thus not readily amenable to hydroxylation.

          One type of soybean oil modification described in the literature uses  
20 hydroformylation to add hydrogen and formyl groups across its double bonds, followed by reduction of these formyl groups to hydroxymethyl groups. Whereas this approach does produce primary hydroxyl groups, disadvantages include the fact that expensive transition metal catalysts are needed in both steps and only one hydroxyl group is introduced per original double bond. Monohydroxylation of soybean oil by epoxidation followed by  
25 hydrogenation or direct double bond hydration (typically accompanied with undesired triglyceride hydrolysis) results in generation of one secondary hydroxyl group per original double bond. The addition of two hydroxyl groups across soybean oil's double bonds (dihydroxylation) either requires transition metal catalysis or stoichiometric use of expensive reagents such as permanganate while generating secondary rather than primary  
30 hydroxyl groups.

          The literature discloses the low temperature ozonolysis of alkenes with simple alcohols and boron trifluoride catalyst followed by reflux to produce esters. See J. Neumeister, et al., *Angew. Chem. Int. Ed.*, Vol. 17, p. 939, (1978) and J.L. Sebedio, et al.,

-2-

Chemistry and Physics of Lipids, Vol. 35, p. 21 (1984). A probable mechanism for the low temperature ozonolysis discussed above is shown in Figure 1. They have shown that a molozonide is generated at relatively low temperatures in the presence of an alcohol and a Bronsted or Lewis acid and that the aldehyde can be captured by conversion to its acetal and the carbonyl oxide can be captured by conversion to an alkoxy hydroperoxide. In the presence of ozone the aldehyde acetal is converted to the corresponding hydrotrioxide at relatively low temperatures. If the reaction temperature is then raised to general reflux temperature, the hydrotrioxide fragments to form an ester by loss of oxygen and one equivalent of original alcohol. At elevated temperatures, and in the presence of an acid such as boron trifluoride, the alkoxy hydroperoxide will eliminate water to also form an ester in essentially quantitative yields. This overall process converts each olefinic carbon to the carbonyl carbon of an ester group so that two ester groups are produced from each double bond.

Figure 1 is a schematic depicting the reactions involved in the two stage ozonolysis of a generalized double bond in the presence of an alcohol and the catalyst boron trifluoride.

Figure 2 is a schematic depicting the reactions involved in the two stage ozonolysis of a generalized double bond in the presence of a polyol and the catalyst boron trifluoride.

Figure 3 is a schematic depicting the steps and specific products involved in converting an idealized soybean oil molecule by ozonolysis and triglyceride transesterification in the presence of glycerin and boron trifluoride to an ester alcohol with the relative proportions of the individual fatty acids indicated. The primary processes and products from each fatty acid are shown.

Figure 4 is a schematic depicting the steps involved in converting an idealized soybean molecule by ozonolysis and triglyceride transesterification in the presence of methanol and boron trifluoride to cleaved methyl esters as intermediates. The primary processes and intermediates from each fatty acid are indicated.

Figure 5 is a schematic depicting the amidification processes and products starting with the intermediate cleaved methyl esters (after initial ozonolysis and triglyceride transesterification) and then reacting with diethanolamine to produce the final amide alcohol product.



-3-

Figure 6 is a schematic flow diagram showing a method to prepare vegetable oil ester alcohols by initial preparation of alkyl esters followed by transesterification with glycerin or any polyol.

Figure 7 is a schematic depicting the amidification of triglyceride fatty acids at the triglyceride backbone to generate fatty acid amide alcohols.

Figure 8 is a schematic depicting the transesterification of the fatty acids at the triglyceride backbone to generate fatty acid ester alcohols.

Figure 9 shows the major azelaic (C<sub>9</sub>) components in soybean oil ester polyols and mixed polyols.

Figure 10 shows examples of various azelaic amide polyols and hybrid amide polyols which can be made using the methods of the present invention.

Figure 11 shows examples of various hybrid soybean ester and amide polyols which can be made using the methods of the present invention.

Fig. 12 shows glycerides obtained by the partial pre-transesterification of triglycerides or fatty acid esters with glycerin or by pre-esterification of glycerin with fatty acids and other fatty acid derivatives.

Fig. 13 shows general esterified primary polyols resulting from the partial pre-transesterification of triglycerides or fatty acid esters with primary polyols or by pre-esterification of primary polyols in general with fatty acids and other fatty acid derivatives.

Fig. 14 shows sorbitol pre-esterified with two moles of fatty acid.

Broadly, methods for the ozonolysis and transesterification of biobased oils, oil derivatives, or modified oils to generate highly functionalized esters, ester alcohols, amides, and amide alcohols are described. By biobased oils, we mean vegetable oils or animal fats having at least one triglyceride backbone, wherein at least one fatty acid has at least one double bond. By biobased oil derivatives, we mean derivatives of biobased oils, such as hydroformylated soybean oil, hydrogenated epoxidized soybean oil, and the like wherein fatty acid derivatization occurs along the fatty acid backbone. By biobased modified oils, we mean biobased oils which have been modified by transesterification or amidification of the fatty acids at the triglyceride backbone.

One broad method for producing an ester includes reacting a biobased oil, oil derivative, or modified oil with ozone and alcohol at a temperature between about -80°C

-4-

to about 80°C to produce intermediate products; and refluxing the intermediate products or further reacting at lower than reflux temperature; wherein esters are produced from the intermediate products at double bond sites, and substantially all of the fatty acids are transesterified to esters at the glyceride sites. The esters can be optionally amidified, if  
5 desired.

Another broad method for producing amides includes amidifying a biobased oil, or oil derivative so that substantially all of the fatty acids are amidified at the glyceride sites; reacting the amidified biobased oil, or oil derivative with ozone and alcohol at a temperature between about -80°C to about 80°C to produce intermediate products;  
10 refluxing the intermediate products or further reacting at lower than reflux temperature, wherein esters are produced from the intermediate products at double bond sites to produce a hybrid ester/amide.

Ozonolysis of olefins is typically performed at moderate to elevated temperatures whereby the initially formed molozonide rearranges to the ozonide which is then  
15 converted to a variety of products. Although not wishing to be bound by theory, it is presently believed that the mechanism of this rearrangement involves dissociation into an aldehyde and an unstable carbonyl oxide which recombine to form the ozonide. The disclosure herein provides for low temperature ozonolysis of fatty acids that produces an ester alcohol product without any ozonide, or substantially no ozonide as shown in Figure  
20 2. It has been discovered that if a primary polyol such as glycerin is used in this process that mainly one hydroxyl group will be used to generate ester functionality and the remaining alcohol groups will remain pendant in generating ester glycerides. By "primary polyol" we mean a polyol used as a reactant in the ozonolysis process that uses at least one of its hydroxyl groups in forming ester linkages to fatty acid components in generating the  
25 product polyol.

One basic method involves the combined ozonolysis and transesterification of a biobased oil, oil derivative, or modified oil to produce esters. As shown in Figure 1, if a monoalcohol is used, the process produces an ester. As shown in Figure 2, if a polyol is used, an ester alcohol is made.

30 The process typically includes the use of an ozonolysis catalyst. The ozonolysis catalyst is generally a Lewis acid or a Bronsted acid. Suitable catalysts include, but are not limited to, boron trifluoride, boron trichloride, boron tribromide, tin halides (such as



tin chlorides), aluminum halides (such as aluminum chlorides), zeolites (solid acid), molecular sieves (solid acid), sulfuric acid, phosphoric acid, boric acid, acetic acid, and hydrohalic acids (such as hydrochloric acid). The ozonolysis catalyst can be a resin-bound acid catalyst, such as SiliaBond<sup>\*</sup> propylsulfonic acid, or Amberlite<sup>®</sup> IR-120 (macroreticular or gellular resins or silica covalently bonded to sulfonic acid or carboxylic acid groups).  
5 One advantage of a solid acid or resin-bound acid catalyst is that it can be removed from the reaction mixture by simple filtration.

The process generally takes place at a temperature in a range of about -80°C to about 80°C, typically about 0°C to about 40°C, or about 10°C to about 20°C.

10 The process can take place in the presence of a solvent, if desired. Suitable solvents include, but are not limited to, ester solvents, ketone solvents, chlorinated solvents, amide solvents, or combinations thereof. Examples of suitable solvents include, but are not limited to, ethyl acetate, acetone, methyl ethyl ketone, chloroform, methylene chloride, and N-methylpyrrolidinone.

15 When the alcohol is a primary polyol, an ester alcohol is produced. Suitable polyols include, but are not limited to, glycerin, trimethylolpropane, pentaerythritol, or propylene glycol, alditols such as sorbitol, aldoses such as glucose, ketoses such as fructose, reduced ketoses, and disaccharides such as sucrose.

20 When the alcohol is a monoalcohol, the process may proceed too slowly to be practical in a commercial process and the extended reaction time can lead to undesired oxidation of the monoalcohol by ozone. Therefore, it may be desirable to include an oxidant. Suitable oxidants include, but are not limited to, hydrogen peroxide, Oxone<sup>®</sup> (potassium peroxymonosulfate), Caro's acid, or combinations thereof.

25 A significant issue in this ozonolysis process is the choice of solvent for the process. An ideal solvent will have relatively high solubilities for vegetable oils, such as soybean oil, as well as for primary polyols, such as glycerin, propylene glycol, and monosaccharides or monosaccharide derivatives such as sorbitol. The solvent also desirably has an appreciable solubility for ozone and is not degraded by ozone.

30 Suitable solvents include, but are not limited to, ester solvents, including, but not limited to, ethyl acetate, methyl acetate, and isobutyl isobutyrate. However, ester solvents have an important deficiency: although they have high solubility for vegetable oils and ozone, they have low solubility for primary polyols, such as glycerin or sorbitol. Low

\* trade-mark

-6-

primary polyol solubility in ester solvents results in the primary polyol initially generating a separate primary polyol phase and also an initial low concentration of primary polyol in the reactive phase. As discussed below, a low concentration of primary polyol in the reactive phase results in reduced primary/secondary hydroxyl group ratios. It should be noted that the solubility of primary polyols in the ester solvent will increase as relatively polar glyceride components are being generated during the ozonolysis reaction stage.

Another significant problem caused by the primary polyol generating a second phase is that it results in significant batch-to-batch compositional variations. Different batch compositions are caused by differences in diffusion rates of the relatively insoluble primary polyol into the reactive solvent phase caused by slight variations in reaction temperature, reaction mixture stirring equipment and stirring rates, as well as by variations in ozone gas flow, which also contributes to the general reaction turbulence which influences interphase contact.

It is desirable to reduce or eliminate this batch composition variability. In the case of vegetable oil-derived polyols or animal fat-derived polyols, one method for reducing the composition variability involves pre-esterification of the primary polyols. By pre-esterification we mean transesterification of the polyol with vegetable oil (or animal fat) or fatty acid esters such as methyl soyate, or direct esterification of the polyol with fatty acids or fatty acid derivatives, such as soy acid or soy acid derivatives, so that the hydroxyl groups of the primary polyol become partially esterified with fatty acids. The resulting primary polyol derivatives have significantly increased solubilities in esters and other organic solvents because of the reduction in polarity of the starting primary polyol due to attachment of low-polarity fatty acid groups. One or more primary polyols can be pre-esterified. The pre-esterified primary polyols can be used alone or in combination with one or more additional primary polyols which have not been pre-esterified. The additional primary polyols can be the same primary polyol as the one which is pre-esterified, or they can be different. Combinations of pre-esterified and non-modified primary polyols can be used to obtain desired hydroxylic acid/fatty acid ratios.

This approach will not work with a mono-ol(e.g., methanol, ethanol, etc.) alone because there would not be any available hydroxyl groups to react with the reactive intermediates generated at the double bond sites. Mono-ols can be used if they are



combined with either pre-esterified primary polyol or primary polyol itself which would provide the required ratio of fatty acid to available hydroxyl group.

The pre-esterified primary polyol can also be used in combination with fatty acids, as described in U.S. Provisional Application Serial No.61/141,882 filed on even date  
5 herewith, entitled Use Of Fatty Acids As Feed Material In Polyol Process (Attorney Docket No. BAT 0143 MA),

In some cases (where the pre-esterified polyol has sufficient hydroxyl groups), the pre-esterified polyol can be used without a biobased oil, oil derivative, or modified oil.

Fig. 12 shows glycerides obtained by the partial pre-transesterification of  
10 triglycerides or fatty acid esters with glycerin or by pre-esterification of glycerin with fatty acids and other fatty acid derivatives.

Fig. 13 shows general esterified primary polyols resulting from the partial pre-transesterification of triglycerides or fatty acid esters with primary polyols or by pre-esterification of primary polyols in general with fatty acids and other fatty acid  
15 derivatives.

Fig. 14 shows sorbitol pre-esterified with two moles of fatty acid (linoleic acid).

The resulting primary polyol derivatives produced by either pre-transesterification or pre-esterification have significantly increased solubilities in esters and other solvents while producing the same polyol components produced when non-modified polyols are  
20 used. In addition, the use of these modified primary polyols results in significantly increased batch-to-batch reproducibility. Furthermore, their use results in increased monoglyceride/diglyceride ratios and corresponding primary/secondary hydroxyl ratios. Also, the presence of these modified primary polyols in ozonolysis reaction mixtures allows the co-use of non-modified primary polyols and still obtain the above advantages  
25 since the solubilities of non-modified primary polyols are significantly increased in organic solvents when used in the presence of solvent-soluble modified primary polyols.

The use of a modified oil, which has been transesterified to esters or amidified at the fatty acid glyceride sites before reacting with the ozone and alcohol, allows the production of hybrid C<sub>9</sub> or azelate esters (the major component in the reaction mixture) in  
30 which the ester on one end of the azelate diester is different from the ester on the other end or hybrid amide esters in which there is an amide at one end of the azelate and an ester on the other end. In order to produce a hybrid ester composition, the alcohol used in

-8-

ozonolysis is different from the alcohol used to transesterify the esters at the fatty acid glyceride sites.

The esters produced by the process can optionally be amidified to form amides. One method of amidifying the esters to form amides is by reacting an amine alcohol with the esters to form the amides. The amidifying process can include heating the ester/amine alcohol mixture, distilling the ester/amine alcohol mixture, and/or refluxing the ester/amine alcohol mixture, in order too drive the reaction to completion. An amidifying catalyst can be used, although this is not necessary if the amine alcohol is ethanolamine, due to its relatively short reaction times, or if the reaction is allowed to proceed for suitable periods of time. Suitable catalysts include, but are not limited to, boron trifluoride, sodium methoxide, sodium iodide, sodium cyanide, or combinations thereof.

Another broad method for producing amides includes amidifying a biobased oil, or oil derivative so that substantially all of the fatty acids are amidified at the triglyceride sites, as shown in Figure 7. The amidified biobased oil, or oil derivative is then reacted with ozone and alcohol to produce esters at the double bond sites. This process allows the production of hybrid ester/amides.

The ester in the hybrid ester/amide can optionally be amidified. If a different amine alcohol is used for the initial amidification process from that used in the second amidification process, then C<sub>9</sub> or azelaic acid hybrid diamides (the major component in the reaction mixture) will be produced in which the amide functionality on one end of the molecule is different from the amide functionality on the other end.

#### ESTER POLYOLS

The following section discusses the production of highly functionalized glyceride alcohols (or glyceride polyols) from soybean oil by ozonolysis in the presence of glycerin and boron trifluoride as shown in Figure 3. Glycerin is a candidate primary polyol for ester polyol production since it is projected to be produced in high volume as a byproduct in the production of methyl soyate (biodiesel). Other candidate primary polyols include, but are not limited to, propylene glycol (a diol), trimethylolpropane (a triol) and pentaerythritol (a tetraol), alditols such as sorbitol, other aldoses and ketoses such as glucose and fructose, reduced ketoses, and disaccharides such as sucrose.



-9-

Broadly, ozonolysis of soybean oil is typically performed in the presence of a catalyst, such as catalytic quantities of boron trifluoride or sulfuric acid (e.g., 0.01-0.25 equivalents), and glycerin (e.g., 0.4-4 equivalents of glycerin) (compared to the number of reactive double bond plus triglyceride sites) at about -80°C to about 80°C (preferably  
5 about 0°C to about 40°C) in a solvent such as those disclosed herein.

It is expected that dehydrating agents such as molecular sieves and magnesium sulfate will stabilize the ester product by reducing product ester hydrolysis during the reflux stage based on chemical precedents.

Completion of ozonolysis was indicated by an external potassium iodide/starch test  
10 solution, and the reaction mixture was refluxed typically one hour or more in the same reaction vessel. Boron trifluoride or sulfuric acid was removed by treatment with sodium or potassium carbonate or bicarbonate, and the resulting ethyl acetate solution was washed with water to remove glycerin.


One benefit of using boron trifluoride or sulfuric acid as the catalyst is that it also  
15 functions as an effective transesterification catalyst so that the glycerin also undergoes transesterification reactions at the site of original fatty acid triglyceride backbone while partially or completely displacing the original glycerin from the fatty acid. Although not wishing to be bound by theory, it is believed that this transesterification process occurs during the reflux stage following the lower temperature ozonolysis. Other Lewis and  
20 Bronsted acids can also function as transesterification catalysts (see the list elsewhere herein).

Combined proton NMR and IR spectroscopy confirmed that the primary processes and products starting with an idealized soybean oil molecule showing the relative proportions of individual fatty acids are mainly 1-monoglycerides when an excess of  
25 primary polyol is used as indicated in Figure 3. However, some 2-monoglycerides are also produced. If diglyceride functionality is desired in the product polyol, lower quantities of primary polyol are used. Figure 3 illustrates typical reactions for an idealized soybean oil molecule. Figure 3 also shows that monoglyceride groups become attached to each original olefinic carbon atom and the original fatty acid carboxylic groups are also  
30 transesterified primarily to monoglyceride groups to generate a mixture of primarily 1-monoglycerides, 2-monoglycerides and diglycerides. Thus, not only are the unsaturated fatty acid groups multiply derivatized by glycerin, but the 16% saturated fatty acids are

-10-

also converted primarily to monoglycerides by transesterification at their carboxylic acid sites.

Glycerin (e.g., four equivalents) was used in order to produce primarily monoglycerides at the double bond sites and minimize formation of diglycerides and triglycerides by further reaction of pendant product alcohol groups with the ozonolysis intermediates. However, diglycerides will become more prevalent at lower primary polyol concentrations and diglyceride still function as polyols since they have available hydroxyl groups. One typical structure for diglycerides is shown below as Formula I.



This follows since the higher the concentration of glycerin, the greater the probability that, once a hydroxyl group of a glycerin molecule (preferentially primary hydroxyl groups) reacts with either the aldehyde or carbonyl oxide intermediates, the remaining hydroxyl groups in that molecule will not also be involved in these type reactions.

1-Monoglycerides have a 1:1 combination of primary and secondary hydroxyl groups for preparation of polyurethanes and polyesters. The combination of more reactive primary hydroxyl groups and less reactive secondary hydroxyl groups may lead to rapid initial cures and fast initial viscosity building followed by a slower final cure. However, when using starting polyols comprised substantially exclusively of primary hydroxyl groups such as trimethylolpropane or pentaerythritol, substantially all pendant hydroxyl groups will necessarily be primary in nature and have about equal initial reactivity.

25 Although it is not shown in Fig. 2, five-membered acetals (1,3-dioxolanes) are also formed, and these will initially produce only 2-monoglycerides, which have only primary hydroxyl groups. Also formed are six-membered acetals (1,3-dioxanes) which have secondary hydroxyl groups.

30 Although not shown in Fig. 2, diglycerides are also formed in both the upper and lower routes when glycerin concentrations in the reactive phase are relatively low. Considering the upper route (which proceeds to completion significantly faster than the lower route when sufficient ozone is present), it can be seen that initially formed 1-



-11-

monoglycerides can also form acetals with aldehyde intermediates that will ultimately be converted into diglycerides. Considering the lower route, it can be seen that pendent hydroxyl groups of initially formed alkoxy hydroperoxide intermediates or 1-monoglycerides can react with highly reactive carbonyl oxides to form glycerin bis(alkoxy hydroperoxides) that will undergo elimination reactions to form diglycerides. It is evident that monoglyceride/diglyceride ratios should increase with increased concentrations of primary polyols in the reactive phase due to the resulting increased probability of collisions of intermediate aldehydes or carbonyl oxide intermediates with glycerin, rather than with initially formed monoglycerides or alkoxy hydroperoxides.

10 It should be noted that increased monoglyceride/diglyceride ratios result in increased primary/secondary hydroxyl ratios which is desired due to the higher reactivity of primary hydroxyl groups in forming polyurethanes and polyesters in reaction with isocyanates and carboxylic acids or their equivalents, respectively. Thus, the methods described for increasing the concentration of primary polyols in ester solvents will  
15 advantageously increase primary/secondary hydroxyl group ratios.

The theoretical weight for the preparation of soybean oil monoglycerides shown above is about two times the starting weight of soybean oil, and the observed yields were close to this factor. Thus, the materials cost for this transformation is close to the average of the per pound cost of soybean oil and glycerin.

20 Glyceride alcohols obtained were clear and colorless and had low to moderately low viscosities. When ethyl acetate is used as the solvent, hydroxyl values range from about 90 to approximately 400 depending on the ratio of glycerin to soybean oil or pre-esterified glycerin starting material, acid values ranged from about 2 to about 12, and glycerin contents were reduced to <1% with two water or potassium carbonate washes.

25 When ester solvents such as ethyl acetate are used, there is a potential for a side reaction in the production of vegetable oil (or animal fat) glyceride alcohols (example for soybean oil shown in Figure 3), or ester alcohols in general, that involves the transesterification of the free hydroxyl groups in these products with the solvent ester to form ester-capped hydroxyl groups. When ethyl acetate is used, acetate esters are formed  
30 at the hydroxyl sites, resulting in capping of some hydroxyl groups so that they are no longer available for further reaction to produce foams and coatings. If the amount of ester capping is increased, the hydroxyl value will be decreased, thus providing a means to

-12-

reduce and adjust hydroxyl values. Ester capping may also be desirable since during purification of polyol products by water washing, the water solubility of the product ester alcohol is correspondingly decreased leading to lower polyol product loss in the aqueous layer.

5 Several methods are available to control ester capping reactions, and thus the hydroxyl value of the ester alcohol.

One method is shown in Figure 6, which illustrates an alternate approach to prepare vegetable oil glyceride alcohols, or ester alcohols in general, by reacting (transesterifying) the vegetable oil methyl ester mixture (shown in Figure 4), or any  
10 vegetable oil alkyl ester mixture, with glycerin, or any other polyol such as trimethylolpropane or pentaerythritol, to form the same product composition shown in Figure 3, or related ester alcohols if esters are not used as solvents in the transesterification step. Also, if esters are used as solvents in transesterifying the mixture of Figure 4 (alkyl esters) with a polyol, a shorter reaction time would be expected compared to  
15 transesterification of the fatty acids at the triglyceride backbone (as shown in Figure 3), thus leading to decreased ester capping of the hydroxyl groups. This method has merit in its own right, but involves one extra step than the sequence shown in Figure 3.

Another method of controlling the ester capping in general is to use solvents that are not esters (such as amides such as NMP (1-methyl-2-pyrrolidinone) and DMF (N,N-  
20 dimethyl formamide); ketones, or chlorinated solvents) and can not enter into transesterification reactions with the product or reactant hydroxyl groups. Alternatively, "hindered esters" such as alkyl (methyl, ethyl, etc.) pivalates (alkyl 2,2-  
dimethylpropionates) and alkyl 2-methylpropionates (isobutyrate) can be used. This type of hindered ester should serve well as an alternate recyclable solvent for vegetable oils and  
25 glycerin, while its tendency to enter into transesterification reactions (as ethyl acetate does) should be significantly impeded due to steric hindrance. The use of isobutyrate and pivalates provides the good solubilization properties of esters without ester capping to provide maximum hydroxyl value as desired.

Another way to control the ester capping is to vary the reflux time. Increasing the  
30 reflux time increases the amount of ester capping if esters are used as ozonolysis solvents.

Ester capping of polyol functionality can also be controlled by first transesterifying the triglyceride backbone, as shown in Figure 8 and described in Example 2, and then



-13-

performing ozonolysis, as described in Example 3, resulting in a shorter reaction time when esters are used as solvents.

Water or potassium carbonate washing of the product in ethyl acetate solutions has been used to remove the glycerin. Because of the high hydroxyl content of many of these products, water partitioning leads to extreme loss of ester polyol yield. It is expected that using water containing the appropriate amount of dissolved salt (sodium chloride, potassium carbonate, or others) will lead to reduced product loss currently observed with water washing. Even though not demonstrated, the glycerin used presumably can be separated from water washes by simple distillation.

In order to remove the non-resin bound acid catalyst boron trifluoride effectively without water partitioning, basic resins, such as Amberlyst® A-21 and Amberlyst® A-26 (macroreticular or gellular resins of silica covalently bonded to amine groups or quaternary ammonium hydroxide), have been used. The use of these resins may also be beneficial because of potential catalyst recycling by thermal treatment to release boron trifluoride from either resin or by chemical treatment with hydroxide ion. Sodium carbonate has been used to scavenge and also decompose the boron trifluoride catalyst.

The present invention allows the preparation of a unique mixture of components that are all end functionalized with alcohol or polyol groups. Evidence indicates when these mixtures are reacted with polyisocyanates to form polyurethanes, that the resulting mixtures of polyurethanes components plasticize each other so that a very low glass transition temperature for the mixed polyurethane has been measured. This glass transition is about 100°C lower than expected based solely on hydroxyl values of other biobased polyols, none of which have been transesterified or amidified at the glyceride backbone. Also, the polyols derived from these cleaved fatty acids have lower viscosities and higher molecular mobilities compared to these non-cleaved biobased polyols, leading to more efficient reactions with polyisocyanates and molecular incorporation into the polymer matrix. This effect is manifested in polyurethanes derived from the polyols of the present invention giving significantly lower extractables in comparison to other biobased polyols when extracted with a polar solvent such as N,N-dimethylacetamide.

30

-14-

## AMIDE ALCOHOLS

The following section discusses the production of highly functionalized amide alcohols from soybean oil by ozonolysis in the presence of methanol and boron trifluoride followed by amidification with amine alcohols. Refer now to Figures 4 and 5.

5 Ozonolysis of soybean oil was performed in the presence of catalytic quantities of boron trifluoride (e.g., 0.25 equivalent with respect to all reactive sites) at 20-40°C in methanol as the reactive solvent. It is anticipated that significantly lower concentrations of boron trifluoride or other Lewis or Bronsted acids could be used in this ozonolysis step (see the list of catalysts specified elsewhere). Completion of ozonolysis was indicated by  
10 an external potassium iodide/starch test solution. This reaction mixture was then typically refluxed typically one hour in the same reaction vessel. As stated previously, in addition to serving as a catalyst in the dehydration of intermediate methoxy hydroperoxides and the conversion of aldehydes to acetals, boron trifluoride also serves as an effective transesterification catalyst to generate a mixture of methyl esters at the original fatty acid  
15 ester sites at the triglyceride backbone while displacing glycerin from the triglyceride. It is anticipated that other Lewis and Bronsted acids can be used for this purpose. Thus, not only are all double bond carbon atoms of unsaturated fatty acid groups converted to methyl esters by methanol, but the 16% saturated fatty acids are also converted to methyl esters by transesterification at their carboxylic acid sites. Combined proton NMR and IR  
20 spectroscopy and GC analyses indicate that the primary processes and products starting with an idealized soybean oil molecule showing the relative proportions of individual fatty acids are mainly as indicated in Figure 4.

Amidification of the methyl ester mixture was performed with the amine alcohols diethanolamine, diisopropanolamine, N-methylethanolamine, N-ethylethanolamine, and  
25 ethanolamine. These reactions typically used 1.2-1.5 equivalents of amine and were driven to near completion by ambient pressure distillation of the methanol solvent and the methanol released during amidification, or just heat under reflux, or at lower temperatures. These amidification reactions were catalyzed by boron trifluoride or sodium methoxide which were removed after this reaction was complete by treatment with the strong base  
30 resins Amberlyst A-26<sup>®</sup> or the strong acid resin Amberlite<sup>®</sup> IR-120, respectively. Removal of boron trifluoride was monitored by flame tests on copper wire wherein boron trifluoride gives a green flame. After amidification reactions with amine alcohols, amine



-15-

alcohols were removed by short path distillation using a Kugelrohr short path distillation apparatus at temperatures typically ranging from 70°C to 125°C and pressures ranging from 0.02-0.5 Torr.

Combined proton NMR and IR spectroscopy indicate that the primary  
5 amidification processes and products starting with the cleaved methyl esters after initial ozonolysis and then reacting with an amine alcohol such as diethanolamine are mainly as indicated below in Figure 5. Thus, not only are the unsaturated fatty acid groups of soybean oil multiply converted to amide alcohols or amide polyols at their olefinic sites as well as the fatty acid triglyceride sites, but the 16% saturated fatty acids are also converted  
10 to amide alcohols or amide polyols at their fatty acid sites.

The boron trifluoride catalyst may be recycled by co-distillation during distillation of diethanolamine, due to strong complexation of boron trifluoride with amines.

One problem that has been identified is the oxidation of monoalcohols such as methanol, that is used both as a solvent and reactant, by ozone to oxidized products (such  
15 as formic acid, which is further oxidized to formate esters, when methanol is used). Methods that have been evaluated to minimize this problem are listed below:

- (1). Perform ozonolysis at decreased temperatures, ranging from about -78°C (dry ice temperature) to about 20°C;
- (2). Perform ozonolysis reaction with alcohols less prone to oxidation than methanol such  
20 as primary alcohols (ethanol, 1-propanol, 1-butanol, etc.), secondary alcohols (2-propanol, 2-hydroxybutane, etc.), or tertiary alcohols, such as tertiary-butanol;
- (3). Perform ozonolysis reaction using alternate ozone non-reactive cosolvents (esters, ketones, tertiary amides, ketones, chlorinated solvents) where any monoalcohol used as a reagent is present in much lower concentrations and thus would compete much less  
25 effectively for oxidation with ozone.

The boron trifluoride catalyst may be recycled by co-distillation during distillation of diethanolamine, due to strong complexation of boron trifluoride with amines.

All examples herein are merely illustrative of typical aspects of the invention and are not meant to limit the invention in any way.

30

-16-

### Example 1

This example shows a procedure for making glyceride alcohols or primarily soybean oil monoglycerides as shown in Figure 3 (also including products such as those in Figure 9 A, B, C).

5 All steps for making glyceride alcohols were performed under a blanket of Argon. The ozonolysis of soybean oil was carried out by first weighing 20.29 grams of soybean oil (0.02306 mole;  $0.02036 \times 12 = 0.2767$  mole double bond plus triglyceride reactive sites) and 101.34 grams of glycerol (1.10 mole; 4 fold molar excess) into a 500 mL 3-neck round bottom flask. A magnetic stirrer, ethyl acetate (300 mL) and boron trifluoride  
10 diethyl etherate (8.65 mL) were added to the round bottom flask. A thermocouple, sparge tube, and condenser (with a gas inlet attached to a bubbler containing potassium iodide (1 wt %) in starch solution (1%) were attached to the round bottom flask. The round bottom flask was placed into a water-ice bath on a magnetic stir plate to maintain the internal temperature at 10-20°C, and ozone was bubbled through the sparge tube into the mixture  
15 for 2 hours until the reaction was indicated to be complete by appearance of a blue color in the iodine-starch solution. The sparge tube and ice-water bath were removed, and a heating mantle was used to reflux this mixture for 1 hour.

After cooling to room temperature, sodium carbonate (33 g) was added to neutralize the boron trifluoride. This mixture was stirred overnight, after which distilled  
20 water (150 mL) was added and the mixture was again stirred well. The ethyl acetate layer was removed in a separatory funnel and remixed with distilled water (100mL) for 3 minutes. The ethyl acetate layer was placed into a 500 mL Erlenmeyer flask and dried with sodium sulfate. Once dry, the solution was filtered using a coarse fritted Buchner funnel, and the solvent was removed in a rotary evaporator (60°C at approximately 2  
25 Torr). The final weight of this product was 41.20 grams which corresponded to a yield of 84.2% when the theoretical yield was based on the exclusive formation of monoglycerides. The acid and hydroxyl values were 3.8 and 293.1 respectively. Proton NMR Spectroscopy yielded a complex spectrum, but the major portion matched the spectrum of bis(2,3-dihydroxy-1-propyl)azelate based on comparisons to authentic 1-  
30 monoglyceride esters.



-17-

### Example 2

This example shows the production of soybean oil transesterified with propylene glycol or glycerin as shown in Figure 8.

Soybean oil was added to a flask containing propylene glycol (1 mole soybean  
5 oil/6 mole propylene glycol) and lithium carbonate (1.5 wt% of soybean oil), and the flask  
was heated at 185°C for 14 hrs. The product was rinsed with hot distilled water and dried.  
Proton NMR spectroscopy indicated the presence of 1-propylene glycol monoester and no  
mono-, di- or triglycerides.

When reacting with glycerin, a working ratio of 1 mole soybean oil/20 mole  
10 glycerin was used when the reaction was performed at 220°C for 100 hrs to maximize the  
amount of monoglycerides that gave a composition containing 70% monoglycerides, 29%  
diglycerides and a trace of triglyceride (glyceryl soyate).

### Example 3

15 This example shows production of a mixed ester alcohol, as in Fig. 9D.

Soybean oil was initially transesterified with glycerin as specified in Example 2 to  
produce glyceryl soyate. 50.0 g glyceryl soyate was reacted with ozone in the presence of  
130 g propylene glycol, boron trifluoride etherate (13.4 mL) in chloroform (500 mL). The  
ozonolysis was performed at ambient temperature until indicated to be complete by  
20 passing the effluent gases from the reaction into a 1% potassium iodide/starch ozone-  
indicating solution and refluxing the ozonolysis solution for one hour. The mixture was  
stirred with 60 g sodium carbonate for 20 hours and filtered. The resulting solution was  
initially evaporated on a rotary evaporator and a short path distillation apparatus (a  
Kugelrohr apparatus) was used to vacuum distill the excess propylene glycol at 80°C and  
25 0.25 Torr. The final product is a hybrid ester alcohol with pendent glycerin and propylene  
glycol hydroxyl groups with respect to the azelate moiety in the product mixture.

### Example 4

This example shows the use of a resin-bound acid to catalyze soybean ozonolysis.  
30 20 g of soybean oil that was pretransesterified with glycerin were reacted with  
ozone in the presence of 64 g of glycerin, 34 g of SiliaBond propylsulfonic acid (silica  
bound acid prepared by Silicycle, Inc.), and 300 mL of acetone. Ozone treatment was

-18-

performed at 15-20°C, followed by a 1 hr reflux. The resin bound acid was filtered and product purified by vacuum distillation. The resulting product composition included about 83% monoglycerides with the balance being diglycerides. The yield was about 88% when the theoretical yield was based on exclusive formation of monoglycerides.

5

#### Example 5

This example shows a procedure for making amide alcohols (amide polyols such as those in Figure 10 A, B, C, D) starting with methanol-transesterified (modified) soybean oil (a commercial product called Soyclear<sup>®</sup> or more generally termed methyl

10

soyate).  
A problem in making the monoalcohol-derived ester intermediates during ozonolysis of soybean oil with mono-alcohols, such as methanol, in the presence of catalysts such as boron trifluoride is that oxidation of these intermediate acyclic acetals to hydrotrioxides to desired esters is very slow. This has been shown by determining the

15

composition of soybean oil reaction products using various instrumental methods, including gas chromatography. This slow step is also observed when model aldehydes were subjected to ozonolysis conditions in the presence of mono-alcohols and boron trifluoride.

Performing ozonolysis at high temperatures can be used to drive this reaction to

20

completion, but significant problems arise from oxidation of the alcohol and ozone loss due to the long reaction times required. When reactions were performed at low temperatures, the oxidation reaction proceeded slowly and did not progress to completion.

An alternate method for oxidation was developed that effectively used hydrogen peroxide to convert the aldehyde/acetal mixture to the desired carboxylic acid ester.

25

Without wishing to be bound by theory, it is possible that (1) the hydrogen peroxide oxidizes the acetal to an intermediate that rearranges to the ester, or (2) the aldehyde is oxidized to the carboxylic acid by hydrogen peroxide and the carboxylic acid is then esterified to the desired ester.

All steps for making amide alcohols were done under a blanket of Argon.

30

The first step in preparing amide alcohols was to prepare the methyl esters of methanol transesterified soybean oil. Soyclear<sup>®</sup> (151.50 grams; 0.1714 mole;  $0.1714 \times 9 = 1.54$  mole double bond reactive sites,) was weighed into a 1000 mL 3-neck round bottom



-19-

flask. A magnetic stirrer, methanol (500 mL; 12.34 mole), and 6.52 mL 99% sulfuric acid (0.122 moles) were added to the flask. A thermocouple, sparge tube, and condenser (with a gas inlet attached to a bubbler containing 1 wt % potassium iodide in 1 wt % starch solution) were attached to the round bottom flask. The flask was placed in a water bath on a magnetic stir plate to maintain temperature at 20°C, and ozone was added through the sparge tube into the mixture for 20 hours (at which time close to the theoretical amount of ozone required to cleave all double bonds had been added), after which the iodine-starch solution turned blue. The sparge tube and water bath were removed, a heating mantle was placed under the flask, and the mixture was refluxed for 1 hour. After reflux, 50 percent hydrogen peroxide (95 mL) was added to the mixture and then refluxed for 3 hrs (mixture was refluxed 1 hour longer but to no change was noted). The mixture was then partitioned with methylene chloride and water. The methylene chloride layer was also washed with 10% sodium bicarbonate and 10% sodium sulfite (to reduce unreacted hydrogen peroxide) until the mixture was both neutral and gave no response with peroxide indicating strips. The solution was then dried with magnesium sulfate and filtered. The product was purified by short path distillation to obtain 140.3 g of clear and colorless liquid. This yield could have been improved by initial distillation of the excess methanol or by continued extraction of all aqueous layers with methylene chloride.

The second step involved in preparing amide alcohols involved the reaction of the methyl esters of methanol transesterified soybean oil prepared above with 2-(ethylamino) ethanol (N-ethylethanolamine). 2-(Ethylamino) ethanol (137.01 g; 1.54 mole) was added to a round bottom containing the methyl esters of methanol transesterified soybean oil (135.20 g; 0.116 mole or 1.395 mole total reaction sites), sodium methoxide (15.38 g; 0.285 mole), and methyl alcohol (50 ml). A short path distillation apparatus was attached and the mixture was heated to 100°C for removal of methanol. The reaction was monitored by the decrease of the IR ester peak at approximately 1735 cm<sup>-1</sup> and was complete after 3 hours.

After cooling to room temperature, the oil was dissolved in methanol and stirred with 500 mL of Amberlite<sup>®</sup> IR-120 for 1 hour to neutralize the sodium methoxide. The solutions was filtered and then stirred with 100 mL Amberlyst A-26<sup>®</sup> resin (hydroxide form). The mixture was filtered, and the resin was washed thoroughly with methanol. The bulk solvent was then removed in vacuo on a rotary evaporator, and the resulting oil

-20-

was placed on a Kugelrohr system to remove residual excess 2-(ethylamino) ethanol and solvent at a temperature of 30°C and pressure of 0.04 to 0.2 Torr.

The final weight of the product was 181.85 grams, giving a yield of about 85%. The hydroxyl value was 351.5. The IR peak at 1620  $\text{cm}^{-1}$  is indicative of an amide structure. Proton NMR Spectroscopy shows no evidence of triglyceride. NMR peaks at 5 3.3-3.6 ppm region are indicative of beta-hydroxymethyl amide functionality and are characteristic of amide hindered rotation consistent with these amide structures.

Amide alcohol or amide polyol products obtained from this general process were clear and orange colored and had moderate viscosities. Analogous reactions were 10 performed with the amine alcohol used was diethanolamine, diisopropanolamine, N-methylethanolamine, and ethanolamine.

#### Example 6

This example shows a low temperature procedure for making the methyl esters of 15 methanol transesterified soybean oil.

Soyclear<sup>®</sup> (10.0 g; 0.01 mole; 0.10 mole double bond reactive sites) was weighed into a 500 mL 3 neck round bottom flask. A magnetic stirrer, methanol (150 mL), methylene chloride (150 mL), and boron trifluoride diethyl etherate (3.25 mL; 0.03 mole) were added to the flask. A thermometer, sparge tube, and condenser (with a gas inlet 20 attached to a bubbler containing 1 wt % potassium iodide in 1 wt % starch solution) were attached to the round bottom flask. The flask was placed into a dry ice acetone bath on a magnetic stir plate to maintain temperature at -68°C. Ozone was added through a sparge tube into the mixture for 1 hour in which the solution had turned blue in color. The sparge tube and bath was then removed, and the solution allowed to warm to room temperature. 25 Once at room temperature, a sample was taken showing that all double bonds had been consumed. At this point, 50 percent hydrogen peroxide (10 mL) was added to solution, a heating mantle was placed under the flask, and the mixture was refluxed for 2 hours. Sampling revealed the desired products. The mixture was then treated by methylene chloride-water partitioning in which the methylene chloride was washed with 10% sodium 30 bicarbonate and 10% sodium sulfite (to reduce unreacted hydrogen peroxide) until the mixture was both neutral and gave no response with peroxide indicating strips. The



-21-

solution was then dried with magnesium sulfate and filtered. The product was purified by short path distillation giving moderate yields.

#### Example 7

5 This example shows a procedure for making the methyl esters of methanol transesterified soybean oil (shown in Figure 4).

Soybean oil (128.0 g; 0.15 mole; 1.74 mole double bond reactive sites plus triglyceride reactive sites) was weighed into a 500 mL 3 neck round bottom flask. A magnetic stirrer, methanol (266 mL), and 99 percent sulfuric acid (3.0 mL; 0.06 mole) were added to the flask. A thermocouple and condenser were attached to the round bottom flask. A heating mantle and stir plate was placed under the flask and the mixture was refluxed for 3 hours (in which the heterogeneous mixture becomes homogeneous. The heating mantle was then replaced with a water bath to maintain temperature around 20°C. A sparge tube was attached to the flask and a gas inlet with a bubbler containing 1 wt % potassium iodide in 1 wt % starch solution was attached to the condenser. Ozone was added through a sparge tube into the mixture for 14 hours. The water bath was then replaced with a heating mantle, and the temperature was raised to 45°C. Ozone was stopped after 7 hours, and the solution was refluxed for 5 hours. Ozone was then restarted and sparged into the mixture for 13 hours longer at 45°C. The mixture was then refluxed 20 hours longer. Sampling showed 99.3% complete reaction. The mixture was then treated by methylene chloride-water partitioning in which the methylene chloride was washed with 10% sodium bicarbonate and 5% sodium sulfite (to reduce unreacted hydrogen peroxide) until the mixture was both neutral and gave no response with peroxide indicating strips. The solution was then dried with magnesium sulfate and filtered. The product was purified by short path distillation to obtain 146.3 g of clear and light yellow liquid. Initial distillation of the methanol or continued extraction of all aqueous layers with methylene chloride could have improved this yield.

#### Example 8

30 This example illustrates amidification fatty acid-cleaved methyl esters without the use of catalyst.

-22-

The methyl esters of methanol transesterified soybean oil (20.0g; the product of ozonolysis of methyl soyate in methanol described in the first step of Example 5) were added to 25.64 g (2 equivalents) of ethanolamine and 5 mL methanol. The mixture was heated to 120°C in a flask attached to a short path distillation apparatus overnight at ambient pressure. Thus, the reaction time was somewhat less than 16 hrs. The reaction was shown to be complete by loss of the ester peak at 1730 cm<sup>-1</sup> in its infrared spectra. Excess ethanolamine was removed by vacuum distillation.

#### Example 9

This example shows the amidification of fatty acids at the triglyceride backbone sites as shown in Figure 7.

Backbone amidification of esters can be performed not only using Lewis acids and Bronsted acids, but also using bases such as sodium methoxide.

100.0 g of soybean oil was reacted with 286.0 g of diethanolamine (2 equivalents) dissolved in 200 ml methanol, using 10.50 g of sodium methoxide as a catalyst. The reaction was complete after heating the reaction mixture at 100°C for three hours during which methanol was collected by short path distillation. The reaction mixture was purified by ethyl acetate/water partitioning to produce the desired product in about 98% yield. Proton NMR spectroscopy indicated a purity of about 98% purity with the balance being methyl esters.

This reaction can also be performed neat, but the use of methanol enhances solubility and reduces reaction times.

The reaction can be performed catalyst free, but slower, with a wide range of amines. See Example 8.

#### Example 10

This example shows the use of fatty acids amidified at the triglyceride backbone (soy amides) to produce hybrid soy amide/ester materials such as those shown in Figure 11.

Soy amides (fatty acids amidified at the triglyceride backbone as described in Example 9) can be converted to an array of amide/ester hybrids with respect in the azelate component. Soybean oil diethanolamide (200.0 g; from Example 9) was ozonized for 26



-23-

hours at 15-25°C in the presence of 500 g of propylene glycol using 1 liter of chloroform as solvent and 51.65 mL of boron trifluoride diethyl etherate. After ozone treatment, the solution was refluxed for 1.5 hours. The reaction mixture was neutralized by stirring the mixture for 3 hours with 166.5 g of sodium carbonate in 300 mL water. These solutions  
5 were placed into a 6 liter separatory funnel containing 1350 mL water. The chloroform layer was removed and the water layer was re-extracted with 1325 mL of ethyl acetate. The ethyl acetate and chloroform layers were combined, dried with magnesium sulfate, and then filtered. Solvent was removed on a rotary evaporator and the placed on a Kugelrohr short path distillation apparatus for 2.5 hours at 30°C at 0.17 Torr. This process  
10 yielded 289.25 g of material which constitutes a 81% yield. The hydroxyl value obtained on the material was 343.6.

To illustrate the chemical structure of this mixture, only the resulting azelate component (the major component) would have diethanolamide functionality on one end and the ester of propylene glycol on the other end. (This product could then be further  
15 amidified with a different amide to create a hybrid amide system such as the one in Figure 10 E).

#### Example 11

This example shows the amidification of soybean oil derivatives to increase hydroxyl value.

20 Amidification can be applied to oil derivatives, such as hydroformylated soybean oil and hydrogenated epoxidized soybean oil, to increase the hydroxyl value and reactivity.

Hydrogenated epoxidized soybean oil (257.0 g) was amidified with 131 g of diethanolamine with 6.55 g of sodium methoxide and 280 mL methanol using the  
25 amidification and purification process described for the amidification of esters in Example 9. The product was purified by ethyl acetate/water partitioning. When diethanolamine was used, the yield was 91% and the product had a theoretical hydroxyl value of 498.

This product has both primary hydroxyl groups (from the diethanolamide structure) and secondary hydroxyl groups along the fatty acid chain.

30

-24-

### Example 12

This example shows the transesterification of soybean oil mono-alcohol esters (ethyl and methyl esters) with glycerin to form primarily soybean oil monoglycerides (illustrated in Figure 6).

5           8 g of soy ethyl esters (product of ozonolysis and reflux of soybean oil in ethanol with individual structures analogous to those shown in Figure 4) were added to 30.0 g of glycerin, ethanol (30 mL), and 99% sulfuric acid (0.34 mL). The mixture was heated to 120°C in a short path distillation apparatus for 6.5 hours. The reaction was analyzed using NMR spectroscopy which showed about 54% glyceride product and balance being ethyl  
10 ester starting material. Boron trifluoride diethyl etherate (0.1 mL) was added, and the solution was heated to 120°C for 5 hours. The reaction was analyzed by NMR spectroscopy which indicated the presence of about 72% total glyceride product with the balance being the ethyl ester starting material.

In another experiment, 30.0 g soy methyl esters (product of ozonolysis and reflux  
15 soybean oil in methanol using sulfuric acid as catalyst as illustrated in Figure 4) were added to 96.8 g. glycerin, methanol (50 mL), and 7.15 g of sodium methoxide (shown in Figure 6). The mixture was heated to 100°C for 15.5 hours in a short path distillation apparatus, and the temperature was raised to 130°C for 2 hr. with vacuum being applied for the final 2 minutes of heating. The reaction was analyzed by NMR spectroscopy  
20 which showed 55% total glyceride product with the balance being methyl ester starting materials.


### Coatings

Polyurethane and polyester coatings can be made using the ester alcohols, ester polyols, amide alcohols, and amide polyols of the present invention and reacting them  
25 with polyisocyanates, polyacids, or polyesters.


A number of coatings with various polyols using specific di- and triisocyanates, and mixtures thereof were prepared. These coatings have been tested with respect to flexibility (conical mandrel bend), chemical resistance (double MEK rubs), adhesion (cross-hatch adhesion), impact resistance (direct and indirect impact with 80 lb weight), hardness (measured  
30 by the pencil hardness scale) and gloss (measured with a specular gloss meter set at 60°). The following structures are just the azealate component of select ester, amide, and ester/amide hybrid alcohols, with their corresponding hydroxyl functionality, that were prepared and tested.




-25-




Acetate-Capped Soybean Oil "Monoglycerides"  
Hydroxyl Functionality approximately 3




Soybean Oil Propylene Glycol Esters  
Hydroxyl Functionality approximately 2




Soybean Oil Mixed Diethanolamide Propylene Glycol Esters  
Hydroxyl Functionality approximately 3



Soybean Oil Mixed N-Methylethanolamine Propylene Glycol Ester  
Hydroxyl Functionality approximately 2



Soybean Oil N-Methylethanolamide  
Hydroxyl Functionality 2



Soybean Oil N-Ethylethanolamide  
Hydroxyl Functionality 2

- 5 The following commercial isocyanates (with commercial names, abbreviations and isocyanate functionality) were used in the coatings work: diphenylmethane 4,4'-diisocyanate (MDI, difunctional); Isonate<sup>\*</sup> 143L (MDI modified with a carbodiimide, trifunctional at < 90°C and difunctional at > 90°C); Isobond<sup>\*</sup> 1088 (a polymeric MDI derivative); Bayhydur<sup>\*</sup> 302 (Bayh. 302, a trimer of hexamethylene 1,6-diisocyanate, trifunctional); and 2,4-toluenediisocyanate  
10 (TDI, difunctional).

Coatings were initially cured at 120°C for 20 minutes using 0.5% dibutyltin dilaurate, but it became evident that curing at 163°C for 20 minutes gave higher performance coatings so curing at the higher temperature was adopted. A minimum pencil hardness needed for general-use coatings is HB and a hardness of 2H is sufficiently hard to be used in many applications  
15 where high hardness is required. High gloss is valued in coatings and 60° gloss readings of 90-100° are considered to be "very good" and 60° gloss readings approaching 100° match those required for "Class A" finishes.

#### Example 13

- 20 Coatings from Partially Acetate-Capped (And Non-Capped) Soybean Oil Monoglycerides

\* trade-mark

-26-

Polyurethane coatings were prepared from three different partially acetate-capped samples having different hydroxyl values as specified in Table 1 and numerous combinations of isocyanates were examined.

When using polyol batch 51056-66-28, most coatings were prepared from mixtures of Bayhydur 302 and MDI and it was determined that quite good coatings were obtained when underindexing with these isocyanate mixtures compositions (0.68-0.75 indexing). Two of the best coatings were obtained at a 90:10 ratio of Bayhydur 302:MDI where pencil hardness values of F and H were obtained (formulas 12-2105-4 and 12-2105-3). A very good coating was also obtained when 51056-66-28 was reacted with a 50:50 ratio of Bayhydur 302:MDI. The fact that these good coatings could be obtained when isocyanate was under indexed by about 25% could result from the fact that when the approximately trifunctional polyol reacts with isocyanates with >2 functionality, a sufficiently crosslinked structure is established to provide good coating properties while leaving some of the polyol functionality unreacted.

Polyol batch 51056-6-26, which has a somewhat lower hydroxyl value than 51056-66-28, was mainly reacted with mixtures of Bayhydur 302, Isobond 1088, and Isonate 143L with isocyanate indexing of 0.9-1.0. As can be seen, some very good coatings were obtained, with formulas 2-0206-3 and 2-2606-1 (10:90 ratio of Bayhydur 302:Isobond 1088) being two of the best coatings obtained.

A sample of polyol 51056-6-26 was formulated with a 2:1 mixture of TDI and Bayhydur 302 with no solvent and the viscosity was such that this mixture was applied well to surfaces with an ordinary siphon air gun without requiring any organic solvent. This coating cured well while passing all performance tests and had a 60° gloss of 97°. Such polyol/isocyanate formulations not containing any VOCs could be important because formulation of such mixtures for spray coatings without using organic solvents is of high value but difficult to achieve.

Polyol batch 51056-51-19 had an appreciably lower hydroxyl value than those of polyol batches 51056-66-28 or 51056-6-26 due to a different work-up procedure. This polyol was reacted mainly with mixtures of Bayhydur 302 and MDI. Formulas 2-2606-7 (90:10 Bayhydur 302:MDI and indexed at 1.0) gave an inferior coating in terms of hardness compared to that of polyol 51056-66-28 when reacted with the same, but underindexed, isocyanate composition (formula 12-2105-4).



-27-

One coating was obtained using non-capped soybean oil monoglycerides (51290-11-32) that had a hydroxyl value of approximately 585. This coating was prepared by reaction with a 50:50 ratio of Bayhydur 302:MDI (formula 3-0106-1) using approximately 1.0 indexing and had a 2H pencil hardness and a 60° gloss of 99°. This coating was rated  
5 as one of the best overall coatings prepared.

#### Example 14

##### Coatings from Soybean Oil Propylene Glycol Esters

Preparation and performance data of soybean oil propylene glycol esters are shown  
10 in Table 2. Significantly fewer isocyanate compositions were evaluated compared to the soybean oil monoglycerides described in Table 1. The isocyanate compositions that were evaluated with these propylene glycol esters did not correspond to the best compositions evaluated with the glycerides since the favorable data in Table 1 was obtained after the tests with soybean oil propylene glycol esters were initiated.

15 Coating formula 1-2306-5 was one of the best performing propylene glycol ester/isocyanate compositions that employed a 90:10 ratio of Isobond 1088:Bayhydur 302, with an isocyanate indexing of 1.39. The one test area requiring improvement was that its pencil hardness was only HB. This isocyanate composition is the same as the two high-performing glyceride coatings, formulas 2-2606-1 and 2-2606-3 but these had isocyanate  
20 indexing values of 1.0 and 0.90, respectively. The fact that these glyceride-containing coatings had better performance properties is probably due to this indexing difference. Coating formula 1-2306-4 was another relatively high performing coating derived from propylene glycol that was also derived from Isobond 1088 and Bayhydur 302 (with an isocyanate indexing of 1.39) but its pencil hardness was also HB.

25

#### Example 15

##### Soybean Oil-Derived Coatings Containing Hydroxyethylamide Components

Preparation and performance data of this class of polyurethane derivatives is shown in Table 3.

##### 30 Soybean Oil Diethanolamide (Backbone)-Propylene Glycol Esters

100% Bayhydur 302 gave a better coating in terms of hardness with polyol 51056-95-28 when the isocyanate indexing was 1.00 compared to 0.44 (formulas 2-2606-3

-28-

compared to 1-2606-1). Using 100% Isonate 143L and Isobond 1088 with isocyanate indexing of 1.00 gave inferior coatings compared to use of Bayhydur 302.

A polyurethane composition was also prepared with polyol 51056-95-28 using a 2:1 composition of 2,4-TDI:Bayhydur 302 and 10% of a highly branched polyester was added  
5 as a "hardening" agent. This coating passed all performance tests and had a pencil hardness of 5H and a 60° gloss of 115°. These results strongly indicate that use of very small quantities of such hardening agents will significantly enhance the performance of polyurethane coatings not only prepared from these hydroxyethylamide-containing coatings but also the glyceride-based and propylene glycol-based coatings as well.

10

Soybean Oil N-Methylethanolamide (Backbone)-Propylene Glycol Esters

The use of 50:50 Bayhydur 302:MDI with isocyanate indexing of only 0.57 gave good coating results with an exceptional 60° gloss of 101° but the coating pencil hardness was only HB.



**Table 1. Test Results of Polyurethane Coatings<sup>1</sup> Prepared from Acetate-Capped Soybean Oil "Monoglyceride"**

Sample LRB <sup>1/</sup> Formula Code	NCO/OH Ratio/ Cure Temp. (°C)	Isocyanate Percentage				Coatings Test Results						Pencil Hardness <sup>2</sup>	Aber-lack, Thumbprint	60 Degree Glos s
		MDI	Isonate 143L	Isobond 1088	Bayh. 302	Conical Mandrel Bend	MEK Rubs (100)	Cross-hatch Adhesion	Direct Impact (80 lb)	Reverse Impact (80 lb)	Hardness <sup>3</sup>			
51056-66-28/	.75/ 120				100	P	P	P	P	P	P	5B	-	-
12-2105-10	.75/ 120				100	P	P	P	P	P	P	4B	-	-
51056-66-28/	.75/ 163				100	P	P	P	P	P	P	4B	-	-
12-2105-2	.75/ 163	10			90	P	P	P	P	P	P	HB	-	94.1
51056-66-28/	.75/ 120				90	P	P	P	P	P	P	F	-	101.0
12-2105-12	.68/ 163	10			90	P	P	P	P	P	P	H	-	89.0
51056-66-28/	.75/ 163				90	P	P	P	P	P	P	H	-	-
12-2105-3	.75/ 163	10			90	P	P	P	P	P	P	H	-	-
51056-66-28/	.75/ 163				70	P	P	P	P	P	P	5B	-	-
12-2105-4**	.75/ 163	30			70	P	P	P	P	P	P	5B	-	-
51056-66-28/	.75/ 120				70	P	P	P	P	P	P	HB	-	-
12-2105-14	.75/ 163	30			50	P	P	P	P	P	P	5B	-	-
51056-66-28/	.75/ 120				50	P	P	P	P	P	P	HB	-	-
12-2105-6	.68/ 163	50			50	P	P	P	P	P	P	F	-	90.2
51056-66-28/	.75/ 120				50	P	P	P	P	P	P	HB	-	-
12-2105-16	.68/ 163	50			50	P	P	P	P	P	P	HB	-	-
51056-66-28/	.75/ 163				50	P	P	P	P	P	P	HB	-	-
12-2105-7	.75/ 163	50			50	P	P	P	P	P	P	2H	None	98.9
51056-66-28/	.75/ 163				50	P	P	P	P	P	P	2H	None	98.9
12-2105-8	.75/ 163	50			50	P	P	P	P	P	P	2H	None	98.9
51056-66-28/	.75/ 163				50	P	P	P	P	P	P	2H	None	98.9
12-2105-9	.75/ 163	50			50	P	P	P	P	P	P	2H	None	98.9
51290-11-32 <sup>4</sup>	1.00/ 163	50			50	P	P	P	P	P	P	2H	None	98.9
3-0106-1**	1.00/ 163	50			50	P	P	P	P	P	P	2H	None	98.9
51056-51-19/	1.22/ 163				100	P	P	P	P	P	P	HB	Very slight	-
1-1906-2	1.0/ 163				100	P	P	P	P	P	P	4B	Very slight	82.6
51056-51-19/	1.0/ 163				100	P	P	P	P	P	P	4B	Very slight	82.6
2-2606-2	1.0/ 163	10			90	P	P	P	P	P	P	4B	None	76
51056-51-19/	1.0/ 163	10			90	P	P	P	P	P	P	4B	None	76
2-2606-7	0.90/ 163	10			90	P	P	P	P	P	P	HB	Very slight	79.9
51056-51-19/	0.90/ 163	10			90	P	P	P	P	P	P	HB	Very slight	79.9
2-2706-3	1.0/ 163				90	P	P	P	P	P	P	HB	None	97.7
51056-51-19/	1.0/ 163				90	P	P	P	P	P	P	HB	None	97.7
2-2806-8	1.0/ 163				90	P	P	P	P	P	P	4B	None	98.7
51056-51-19/	1.0/ 163	100			90	P	P	P	P	P	P	4B	None	98.7
2-2606-9	1.0/ 163	100			90	P	P	P	P	P	P	4B	None	98.7
51290-6-26/	.90/ 163				100	P	P	P	P	P	P	4B	Slight	-
2-0206-1	.90/ 163				100	P	P	P	P	P	P	4B	Slight	-
51290-6-26/	.90/ 163				50	P	P	P	P	P	P	HB	None	94.0
2-0206-2	.90/ 163				50	P	P	P	P	P	P	HB	None	94.0
51290-6-26/	.90/ 163				90	P	P	P	P	P	P	H	None	96.2
2-0206-3**	.90/ 163				90	P	P	P	P	P	P	H	None	96.2
51290-6-26/	1.0/ 163				10	P	P	P	P	P	P	2H	None	96.6
2-2606-1**	1.0/ 163				10	P	P	P	P	P	P	2H	None	96.6
51290-6-26/	.90/ 163				50	P	P	P	P	P	P	HB	None	97.0
2-2606-4	.90/ 163				50	P	P	P	P	P	P	HB	None	97.0
51290-6-26/	.90/ 163				10	P	P	P	P	P	P	HB	None	-
2-0206-5	.90/ 163				10	P	P	P	P	P	P	HB	None	-

(a) Coating are 1.5-2.0 mils mm thick (dry) and cured with 0.5% (of total composition) dibutyltin dilaurate for 20 minutes. (b) Hydroxy Values: 51056-66-28 (288), 51056-51-19 (215), 51290-6-26 (250). (c) Pencil Hardness scale: (softest) 5B, 4B, 3B, 2B, B, HB, F, H, 2H through 9H (hardest). (d) 51290-11-32: Uncoated monoglyceride having Hydroxy Value of approximately 585. (\*\*\*) Four of the best overall coatings prepared in Phase 2 work.

Sample LRB/ Formula Code	NCO/OH Ratio// Cure Temp. (°C)	Isocyanate Percentage				Conical Mandrel Bend	MEK Rubs (100)	Cross- hatch Adhesion	Coatings Test Results				Pencil Hard- ness	After-tack, Thumbprint	60 Degree Gloss
		MDI	Isonate 143L	Isobond 1088	Bayh. 302I				Direct Impact (80 lb)	Reverse Impact (80 lb)	Pencil Hard- ness	After-tack, Thumbprint			
51920-9-25/ 2-2706-7	1.00// 163			100		P	F @ 5	P	P	P	P	B	None	86.0	
52190-9-25/ 1-2306-4	1.39// 163			50	50	P	P (SI dull)	P	P	P	P	HB	None	95.6	
52190-9-25/ 1-2306-5	1.39// 163			90	10	P	P (SI dull)	P	P	P	P	HB	None	--	
52190-9-25/ 1-2506-1	1.39// 163		100			P	F @ 7	F 40%	F	F	F	5B	None	--	
51920-9-25/ 2-2606-6	1.00// 163		100			P	F @ 5	P	P	P	P	5B	Very slight	98.4	
52190-9-25/ 1-2506-2	1.39// 163		50	50		F	F @ 7	F 60%	F	F	F	5B	None	--	
51920-9-25/ 2-2606-11	1.00// 163				100	Film was too sticky to run tests									
51920-9-25/ 2-2606-12	1.00// 163	100				P	F @ 5	P	P	P	P	5B	Very slight	96.2	

a) Coating are 1.5-2.0 mils mm thick (dry) and cured with 0.5% (of total composition) dibutyltin dilaurate for 20 minutes. (b) Hydroxyl Value of 52190-9-25 : 201  
(c) Pencil Hardness scale: (softest) 5B, 4B, 3B, 2B, B, HB, F, H, 2H through 9H (hardest).



Test Results of Polyurethane Coatings <sup>a</sup> Prepared from Soybean Oil Hydroxyethylamide Derivatives														
Sample LRB/ Formula Code	NCO/OH Ratio/ Cure Temp. (°C)	MDI	Isocyanate Percentage				Coatings Test Results						After-tack, Thumbprint	60 Degree Gloss
			Isonate 143L	Isobond 1088	Bayh. 302	Conical Mandrel Bend	MEK Rubs (100)	Cross- hatch Adhesion	Direct Impact (80 lb)	Reverse Impact (80 lb)	Pencil Hard- ness			
<b>Soybean Oil Diethanolamide (Backbone)-Propylene Glycol Esters</b>														
51056-95-28/ 2-2706-5	1.00// 163	100				P	F @ 15	F (40%)	F	P	P	HB	None	98
51056-95-28/ 1-2606-1	.44// 163	Compare To 12- 2105-171			100	P	P	P	P	P	P	HB	Very slight	
51056-95-28/ 2-2606-3	1.00// 163				100	P	P	P	P	P	P	F	None	86.3
51056-95-28/ 2-2606-10	1.00// 163	100				F	P	F (60%)	P	P	P	HB	None	102.7
51056-95-28/ 2-2706-6	1.00// 163				100	F	F @ 80	F (65%)	P	P	P	HB	None	71.6
51056-95-28/ 1-2706-2	.44// 163		50		50	P	F @ 10	P (90%)	P	P	P	HB	None	
51056-95-28/ 1-2706-4	.44// 163		25		25	P	F @ 7	P	P	P	P	5B	None	
51056-95-28/ 1-2706-5	.44// 163		37.5		37.5	P	F @ 10	P	P	P	P	4B	None	
<b>Soybean Oil N-Methylethanolamide (backbone)-Propylene Glycol Esters</b>														
51056-73-31/ 12-1505-5	.57// 163	50			50	P	P	P	P	P	P	HB	None	101.0
51056-73-31/ 1-0506-2	.63// 163		100			P	F @ 5	P	P	P	P	5B	None	
51056-73-31/ 1-0506-4	.63// 163	10	90			P	F @ 5	P	P	P	P	5B	None	
<b>SBO Methyl Esters Fully Amidified with N-Methylethanolamine</b>														
51056-79-33/ 1-1006-1	.73// 163		100			P	F @ 5	P	P	P	P	HB	None	
51056-79-33/ 1-1006-2	.73// 163	10	90			P	F @ 5	P	P	P	P	HB	None	

a) Coating are 1.5-2.0 mils mm thick (dry) and cured with 0.5% (of total composition) dibutyltin dilaurate for 20 minutes. (b) Hydroxyl Values: 51056-95-28 (343), 51056-73-31 (313), 51056-79-33 (291). (c) Pencil Hardness scale: (softest) 5B, 4B, 3B, 2B, B, HB, F, H, 2H through 9H (hardest).

Soybean Oil Fully Amidified with N-Methylethanolamine

The use of 100% Isonate I43L with an isocyanate indexing of 0.73 gave a coating  
5 that tested well except it had poor chemical resistance (based on MEK rubs) and only had  
a pencil hardness of HB.

Polyurethane foams can be made using the ester alcohols, ester polyols, amide  
alcohols, and amide polyols of the present invention and reacting them with  
polyisocyanates. The preparation methods of the present invention allow a range of  
10 hydroxyl functionalities that will allow the products to fit various applications. For  
example, higher functionality gives more rigid foams (more crosslinking), and lower  
functionality gives more flexible foams (less crosslinking).

While the forms of the invention herein disclosed constitute presently preferred  
embodiments, many others are possible. It is not intended herein to mention all of the  
15 possible equivalent forms or ramifications of the invention. The scope of the claims  
should not be limited by the preferred embodiments set forth in the examples, but  
should be given the broadest interpretation consistent with the description as a  
whole.



**CLAIMS:**

1. A method for producing an ester comprising:
  - a. pre-esterifying a primary polyol with a fatty acid, a fatty acid ester, a fatty acid anhydride, or a fatty acid chloride to form a partially acylated polyol, wherein the fatty acid, the fatty acid ester, the fatty acid anhydride, or the fatty acid chloride have double bond sites;
  - b. reacting the pre-esterified primary polyol with ozone, in the presence of a solvent at a temperature between about  $-80^{\circ}$  C. to about  $80^{\circ}$  C. to produce intermediate products; and
  - c. refluxing the intermediate products or further reacting at lower than reflux temperature, wherein esters are produced from the intermediate products at the double bond sites.
  
2. A method for producing an ester comprising:
  - a. pre-esterifying a primary polyol with a fatty acid, a fatty acid ester, a fatty acid anhydride, or a fatty acid chloride to form a partially acylated polyol wherein the fatty acid, the fatty acid ester, the fatty acid anhydride, or the fatty acid chloride have double bond sites;
  - b. reacting the pre-esterified primary polyol with ozone, and a biobased oil, oil derivative, or modified oil, in the presence of a solvent at a temperature between about  $-80^{\circ}$  C. to about  $80^{\circ}$  C. to produce intermediate products; and
  - c. refluxing the intermediate products or further reacting at lower than reflux temperature, wherein esters are produced from the intermediate products at the double bond sites.
  
3. The method of claim 1 or 2 wherein the solvent is selected from ester solvents, ketone solvents, chlorinated solvents, amide solvents, or

combinations thereof.

4. The method of claim 1 or 2 wherein the solvent is selected from chloroform, acetone, ethyl acetate, methyl acetate, ethyl propionate, methyl propionate, ethyl butyrate, methyl butyrate, isobutyl acetate, and isobutyl isobutyrate.
5. The method of claim 1 or 2 wherein the ester is an ester alcohol and the method further comprises reacting a hydroxyl group on the ester alcohol with an ester solvent to reduce a hydroxyl value of the ester alcohol.
6. The method of claim 1 or 2 wherein the primary polyol is selected from glycerin, trimethylolpropane, pentaerythritol, 1,2-propylene glycol, 1,3-propylene glycol, ethylene glycols, glucoses, sorbitol, fructoses, reduced fructoses, sucroses, aldoses, alditols, ketoses, reduced ketoses, disaccharides, or combinations thereof.
7. The method of claim 2 wherein the biobased oil, oil derivative, or modified oil is reacted in the presence of an ozonolysis catalyst.
8. The method of claim 7 wherein the ozonolysis catalyst is selected from Lewis acids and Bronsted acids.
9. The method of claim 1 or 2 further comprising amidifying the esters to form amides.
10. The method of claim 9 wherein amidifying the esters to form amides takes place in the presence of an amidifying catalyst.
11. The method of claim 1 further comprising reacting a second primary polyol or a monoalcohol with the pre-esterified primary polyol, the ozone, in the presence of the solvent.
12. The method of claim 2 further comprising reacting a second primary polyol or a monoalcohol with the pre-esterified primary polyol, the ozone,



and the biobased oil, oil derivative, or modified oil, in the presence of the solvent.

13. A method for producing amides comprising:

- a. pre-esterifying a primary polyol with a fatty acid, a fatty acid ester, a fatty acid anhydride, or a fatty acid chloride to form a partially acylated polyol, wherein the fatty acid, the fatty acid ester, the fatty acid anhydride, or the fatty acid chloride have double bond sites;
- b. amidifying a biobased oil, or oil derivatives so that substantially all of the fatty acids are amidified at the fatty acid sites;
- c. reacting the amidified biobased oil, or oil derivative with ozone and the pre-esterified primary polyol in the presence of a solvent at a temperature between about  $-80^{\circ}$  C. to about  $80^{\circ}$  C. to produce intermediate products;
- d. refluxing the intermediate products or further reacting at lower than reflux temperature, wherein ester are produced from the intermediate products at the double bond sites to produce a hybrid ester/amide.

14. The method of claim 13 wherein the solvent is selected from ester solvents, ketone solvents, chlorinated solvents, amide solvents, or combinations thereof.

15. The method of claim 13 wherein the solvent is selected from ethyl acetate, methyl acetate, ethyl propionate, methyl propionate, ethyl butyrate, methyl butyrate, isobutyl acetate and isobutyl isobutyrate.

16. The method of claim 13 wherein the ester is an ester alcohol and further comprising reacting a hydroxyl group on the ester alcohol with an ester solvent to reduce a hydroxyl value of the ester alcohol.

17. The method of claim 13 wherein the primary polyol is selected from glycerin, trimethylolpropane, pentaerythritol, 1,2-propylene glycol, 1,3-propylene glycol, ethylene glycols, glucoses, sorbitol, fructoses, reduced fructoses, sucroses, aldoses, alditols, ketoses, reduced ketoses, disaccharides, or combinations thereof.
18. The method of claim 13 wherein amidifying the biobased oil, or oil derivative takes place in the presence of an amidifying catalyst.
19. The method of claim 13 wherein the biobased oil, or oil derivative is reacted in the presence of an ozonolysis catalyst.
20. The method of claim 13 further comprising amidifying the esters to form amides.
21. The method of claim 20 wherein amidifying the esters to form amides comprises reacting an amine alcohol with the esters to form the amide alcohols.
22. The method of claim 20 wherein amidifying the esters to form amides takes place in the presence of an amidifying catalyst.
23. The method of claim 20 wherein the amide formed at the fatty acid site is different from the amide formed from the ester so that a hybrid diamide alcohol is produced.
24. The method of claim 13 further comprising reacting a second primary polyol or a monoalcohol with the amidified biobased oil, or oil derivative, ozone, and the pre-esterified primary polyol in the presence of the solvent.
25. The method of claim 1 or 2 wherein the ester is an ester alcohol.
26. The method of claim 13 wherein amidifying the biobased oil or oil derivative comprises amidifying the biobased oil or oil derivative with



diethanolamine, diisopropanolamine, N-methylethanolamine, N-ethylethanolamine, or ethanolamine.





FIGURE 1





Notes: BF<sub>3</sub> is typically used as catalyst in the reaction of the Aldehyde with R'OH(OH)<sub>n</sub> in the upper pathway.

The final product is typically an ester polyol, RCO<sub>2</sub>R'(OH)<sub>n</sub>.

FIGURE 2




FIGURE 3






FIGURE 4








FIGURE 6

### Direct Amidification of Soybean Oil




FIGURE 7



8/14

### Transesterification of Soybean Oil





FIGURE 8

### Major Azelaic (C<sub>9</sub>) Components in Soybean Oil Ester Polyols and Mixed Polyols




Azelaic bis(1-Monoglyceride)  
Functionality = 4

A


Acetate-Capped Azelaic bis(1-Monoglyceride)  
Functionality = 3

B



Azelaic bis(1-Propylene Glycol Ester)  
Functionality = 2

C




Hybrid Azelaic 1-Monoglyceride 1-Propylene Glycol Ester  
Functionality = 3

D




**Azelaic Amide Polyols and Hybrid Amide Polyols**




**Azelaic Bis(Diethanolamide)**  
Functionality = 4

A




**Azelaic Bis(N-Ethylethanamide)**  
Functionality = 2

B




**Azelaic Bis(N-Methylethanamide)**  
Functionality = 2

C



**Azelaic Bis(Ethanamide)**  
Functionality = 2

D




**Hybrid Azelaic Diethanolamide XXX**

E


### Hybrid Soybean Ester and Amide polyols

11/14




Hybrid Azelaic 1-Monoglyceride Diethanolamide  
Functionality = 4

A



Hybrid Azelaic 1-Propylene Glycol Ester Diethanolamide  
Functionality = 3

B



Hybrid Azelaic 1-Propylene Glycol N-Methylethanolamide  
Functionality = 2

C

FIGURE 11

**Pre-Transesterification or Pre-Esterification of Glycerin with Vegetable Oil or Fatty Acids and Derivatives**




FIGURE 12



## Pre-Transesterification or Pre-Esterification of Polyols with Vegetable Oil or Fatty Acids and Derivatives





FIGURE 13

14/14



Sorbitol Pre-Esterified with Two Moles Fatty Acid (Linoleic A.)

FIGURE 14