



(11) EP 1 398 317 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention of the grant of the patent:
12.01.2011 Bulletin 2011/02

(51) Int Cl.:
C07D 495/14 (2006.01) **G02B 1/04 (2006.01)**

(21) Application number: **02733473.9**

(86) International application number:
PCT/JP2002/005800

(22) Date of filing: **11.06.2002**

(87) International publication number:
WO 2002/102806 (27.12.2002 Gazette 2002/52)

(54) ALICYCLIC COMPOUND FOR OPTICAL MATERIAL

ALICYCLISCHE VERBINDUNG FÜR OPTISCHES MATERIAL

COMPOSE ALICYCLIQUE POUR MATERIAU OPTIQUE

(84) Designated Contracting States:
DE FR GB IT

(56) References cited:
EP-A2- 0 950 905 WO-A2-01/70853
DE-A1- 19 637 335 GB-A- 1 121 306
US-A- 3 378 522

(30) Priority: **19.06.2001 JP 2001185491**

- **PAGE JONATHAN E. ET AL.: 'Visible-light photochemistry and phototoxicity of thiarubrines' PHOTOCHEMISTRY AND PHOTOBIOLOGY vol. 70, no. 2, 1999, pages 159 - 165, XP002955629**
- **STELIOU KOSTA ET AL.: 'Does diatomic sulfur (S2) react as a free species?' J. AM. CHEMICAL SOCIETY vol. 114, no. 4, 1992, pages 1456 - 1462, XP000877279**
- **HULL DEREK M.C. ET AL.: 'Thio-sugars. Part 8. Methyl 2, 3-anhydro-5-thio-<SYM97>-D-ribopyranoside and methyl 3, 4-anhydro-5-thio-<SYM97>-D-ribopyranoside' J. CHEMICAL SOCIETY, PERKIN TRANS. 1 no. 10, 1977, pages 1234 - 1239, XP002955630**

(43) Date of publication of application:
17.03.2004 Bulletin 2004/12

(73) Proprietor: **MITSUBISHI GAS CHEMICAL COMPANY, INC.**
Tokyo 100-0005 (JP)

(72) Inventors:

- **YOSHIMURA, Yuichi**
Tokyo 125-0051 (JP)
- **TAKEUCHI, Motoharu**
Tokyo 125-0051 (JP)
- **KAMURA, Teruo**
Tokyo 125-0051 (JP)

(74) Representative: **Gille Hrabal Struck Neidlein Prop Roos**
Patentanwälte
Brucknerstrasse 20
40593 Düsseldorf (DE)

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

DescriptionTechnical Field

5 [0001] The present invention relates to optical materials suitable for producing plastic lenses, prisms, optical fibers, information recording media, and filters, particularly, suitable for producing plastic spectacle lenses.

Background Art

10 [0002] Plastic materials have been widely used in various optical applications, particularly in manufacturing spectacle lenses, because of their lightweight, toughness and easiness of dyeing. Optical materials, particularly spectacle lenses are required to have, in addition to a low specific gravity, a high clearness, a low yellowness, and optical properties such as a high refractive index and a large Abbe's number. Since a large refractive index reduces the thickness of a lens, many studies have been made thereon to date and many novel compounds have been proposed. Recently, many organic
15 compounds having sulfur atom and/or selenium atom have been proposed to achieve a high refractive index and a high Abbe's number. Of such compounds, some polyepisulfide compounds have been found to be well balanced in refractive index and Abbe's number. For example, Japanese Patent Application Laid-Open No. 9-110979 proposes a straight-chain polyepisulfide compound, Japanese Patent Application Laid-Open No. 9-71580 proposes a branched polyepisulfide compound, Japanese Patent Application Laid-Open No. 9-255781 proposes a polyepisulfide compound having a cyclic
20 structure, and Japanese Patent Application Laid-Open No. 11-140046 proposes a polyepisulfide compound having a selenium atom. However, the refractive index of materials obtained from these polyepisulfide are limited to 1.73 at most.

Disclosure of Invention

25 [0003] An object of the present invention is to provide an optical material which enables to attain a refractive index higher than attained by known materials.

[0004] As a result of extensive study for achieving the above object, the inventors have found that a five- or more membered alicyclic compound having two or more epithioethylene linkages and/or an epidithioethylene linkages its ring structure and two or more sulfur atoms in its molecule, or a composition containing the alicyclic compound provides an
30 optical material having a high refractive index upon curing by polymerization.

Best Mode for Carrying Out the Invention

[0005] The alicyclic compound for use in the present invention has a five- or more membered ring structure which has
35 two or more epithioethylene linkages and/or an epidithioethylene linkages (hereinafter referred to collectively as "epi(di) thioethylene linkage"). The alicyclic compound has two or more sulfur atoms including the sulfur atom in the epi(di) thioethylene linkage.

[0006] The optical material obtained by curing the alicyclic compound or a composition containing the alicyclic compound by polymerization exhibits a high refractive index. The composition may contain only one type or two or more of the alicyclic compounds. To achieve a high refractive index efficiently, the composition for optical materials contains the alicyclic compound in an amount of preferably 5 to 100% by weight, more preferably 10 to 100% by weight based on the total amount thereof.

[0007] The composition for optical materials referred to herein may include a mixture comprising at least one type of the alicyclic compound as only one essential component and a mixture comprising at least one type of the alicyclic compound and a compound capable of reacting with the alicyclic compound (hereinafter referred to as "reactive compound") as the essential components. The reactive compound is not specifically limited as long as it provides a transparent resin usable as optical materials upon curing by polymerization with the alicyclic compound.

[0008] The alicyclic compounds having two or more epi(di)thioethylene linkages are selected from the group consisting of 1,2:4,5-diepitio-3-thiacyclohexane, 1,2:4,5-diepitio-3,6-dithiacyclohexane, 1,2:4,5-diepidithio-3,6-dithiacyclohexane, 1,2:4,5-diepitio-3,6,7-trithiacycloheptane, 1,2:5,6-diepitio-3,4,7,8-tetrathiacyclooctane, 1,2:5,6-diepidithio-3,4,7,8-tetrathiacyclooctane, 1,2:1,4:4,5-triepitio-3,6-dithiacyclohexane, 1,2:1,4:2,5:4,5-tetraepitio-3,6-dithiacyclohexane, and 1,2:1,4:2,5:4,5-tetraepidithio-3,6-dithiacyclohexane.

[0009] The alicyclic compounds may be synthesized mainly from corresponding olefins, epoxy compounds, dihalogenated compounds and dithiols by the following method:

- 55 (1) a method in which a cyclic olefin is reacted with a thiosulfenyl halide or disulfur dichloride, followed by ring closure with alkali treatment to produce a compound having an epithioethylene linkage,
(2) a method in which a cyclic olefin is reacted with chlorosulfenylsuccinimide or chlorosulfenylphthalimide, followed

by treatment with alkali metal halide to produce a compound having an epithioethylene linkage,

(3) a method in which a cyclic olefin is reacted with a chlorothioacetic acid, followed by ring closure with hydrolysis to produce a compound having an epithioethylene linkage,

(4) a method in which a cyclic epoxy compound is reacted with a thia-introducing agent such as alkali thiocyanate and thiourea to produce a compound having an epithioethylene linkage,


(5) a method in which a cyclic gem-halogen compound is reacted with sodium sulfide to produce a compound having an epithioethylene linkage,

(6) a method in which a cyclic gem-halogen compound is reacted with sodium disulfide to produce a compound having an epidithioethylene linkage, and

(7) a method in which a cyclic gem-dithiol is subjected to hydrogenating ring closure in the presence of an oxidizing agent such as halogen and iron(III) chloride to produce a compound having an epidithioethylene linkage.

[0010] The above methods are only representative, and the alicyclic compound of the present invention may be synthesized by a combination of other known methods.

[0011] As described above, the composition for optical materials of the present invention may contain the reactive compound in addition to the alicyclic compound. The reactive compound is preferably an episulfide compound having a functional group that is easily reacted with the alicyclic compound, for example, an epithioethyl group and/or an epidithioethyl group represented by the following formula 2:



25 wherein S is sulfur atom and v is 1 or 2.

[0012] Examples of the episulfide compounds are shown below.

(1) Episulfide compounds having aliphatic chain skeleton

30 **[0013]** 1,1-Bis(epithioethyl)methane, 1-(epithioethyl)-1-(β -epithiopropyl)methane, 1,1-bis(β -epithiopropyl)methane, 1-(epithioethyl)-1-(β -epithiopropyl)ethane, 1,2-bis(β -epithiopropyl)ethane, 1-(epithioethyl)-3-(β -epithiopropyl)butane, 1,3-bis(β -epithiopropyl)propane, 1-(epithioethyl)-4-(β -epithiopropyl)pentane, 1,4-bis(β -epithiopropyl)butane, 1-(epithioethyl)-5-(β -epithiopropyl)hexane, 1-(epithioethyl)-2-(β -epithiobutylthio)ethane, 1-(epithioethyl)-2-[2-(β -epithiobutylthio)ethylthio]ethane, tetrakis(β -epithiopropyl)methane, 1,1,1-tris(β -epithiopropyl)propane, 1,3-bis(β -epithiopropyl)-1-(β -epithiopropyl)-2-thiapropane, 1,5-bis(β -epithiopropyl)-2,4-bis(β -epithiopropyl)-3-thiapentane, 1,3- or 1,4-bis(epithioethyl)cyclohexane, 1,3- or 1,4-bis(β -epithiopropyl)cyclohexane, bis[4-(epithioethyl)cyclohexyl]methane, bis[4-(β -epithiopropyl)cyclohexyl]methane, 2,2-bis[4-(epithioethyl)cyclohexyl]propane, 2,2-bis[4-(β -epithiopropyl)cyclohexyl]propane, bis[4-(β -epithiopropyl)cyclohexyl] sulfide, bis[4-(epithioethyl)cyclohexyl] sulfide, 2,5-bis(epithioethyl)-1,4-dithiane, 2,5-bis(β -epithiopropyl)-1,4-dithiane, 4-epithioethyl-1,2-cyclohexene sulfide, 4-epoxy-1,2-cyclohexene sulfide, 2,3-, 2,5- or 2,6-bis(1,2-epithioethyl)-1,4-diselenane, 2,3-, 2,5- or 2,6-bis(2,3-epithiopropyl)-1,4-diselenane, 2,4-, 2,5- or 2,6-bis(1,2-epithioethyl)-1,3-diselenane, 2,4-, 2,5- or 2,6-bis(2,4-epithiopropyl)-1,3-diselenane, 2,3-, 2,5-, 2,6- or 3,5-bis(1,2-epithioethyl)-1-thia-4-selenane, 2,3-, 2,5-, 2,6- or 3,5-bis(2,3-epithiopropyl)-1-thia-4-selenane, 2,4- or 4,5-bis(1,2-epithioethyl)-1,3-diselenolane, 2,4- or 4,5-bis(2,4-epithiopropyl)-1,3-diselenolane, 2,4-, 2,5- or 4,5-bis(1,2-epithioethyl)-1-thia-3-selenolane; 2,4-, 2,5- or 4,5-bis(2,4-epithiopropyl)-1-thia-3-selenolane, 2,3-, 2,4-, 2,5- or 3,4-bis(1,2-epithioethyl)selenophane, 2,3-, 2,4-, 2,5- or 3,4-bis(2,3-epithiopropyl)selenophane, 2,3-, 2,5- or 2,6-bis(1,2-epithioethyl)-1,4-ditellurane, 2,3-, 2,5- or 2,6-bis(2,3-epithiopropyl)-1,4-ditellurane, 2,4-, 2,5- or 2,6-bis(1,2-epithioethyl)-1,3-ditellurane, 2,4-, 2,5- or 2,6-bis(2,4-epithiopropyl)-1,3-ditellurane, 2,3-, 2,5-, 2,6- or 3,5-bis(1,2-epithioethyl)-1-thia-4-tellurane, 2,3-, 2,5-, 2,6- or 3,5-bis(2,3-epithiopropyl)-1-thia-4-tellurane, 2,4- or 4,5-bis(1,2-epithioethyl)-1,3-ditellurolane, 2,4- or 4,5-bis(2,4-epithiopropyl)-1,3-ditellurolane, 2,4-, 2,5- or 4,5-bis(1,2-epithioethyl)-1-thia-3-tellurolane, 2,3-, 2,4-, 2,5- or 3,4-bis(1,2-epithiopropyl)tellurophane, 1,3- or 1,4-bis(epithioethyl)benzene, bis[4-(epithioethyl)phenyl]methane, bis[4-(β -epithiopropyl)phenyl]methane, 2,2-bis[4-(epithioethyl)phenyl]propane, 2,2-bis[4-(β -epithiopropyl)phenyl]propane, bis[4-(epithioethyl)phenyl] sulfide, bis[4-(β -epithiopropyl)phenyl] sulfide, bis[4-(epithioethyl)phenyl] sulfoxide, bis[4-(β -epithiopropyl)phenyl] sulfone, 4,4'-bis(epithioethyl)biphenyl, and 4,4'-bis(β -epithiopropyl)biphenyl.

(2) Thioglycidyl ethers

[0014] Methyl thioglycidyl ether, ethyl thioglycidyl ether, propyl thioglycidyl ether, and butyl thioglycidyl ether.

5 (3) Episulfide compounds having at least one epithioalkyloxy group

[0015] Bis(β-epithiopropyl) ether, bis(β-epithiopropyloxy)methane, 1,2-bis(β-epithiopropyloxy)ethane, 1,3-bis(β-epithiopropyloxy)propane, 1,2-bis(β-epithiopropyloxy)propane, 1-(β-epithiopropyloxy)-2-(β-epithiopropyloxymethyl)propane, 1,4-bis(β-epithiopropyloxy)butane, 1,3-bis(β-epithiopropyloxy)butane, 1-(β-epithiopropyloxy)-3-(β-epithiopropyloxymethyl)butane, 1,5-bis(β-epithiopropyloxy)pentane, 1-(β-epithiopropyloxy)-4-(β-epithiopropyloxymethyl)pentane, 1,6-bis(β-epithiopropyloxy)hexane, 1-(β-epithiopropyloxy)-5-(β-epithiopropyloxymethyl)hexane, 1-(β-epithiopropyloxy)-2-[(2-β-epithiopropyloxyethyl)oxy]ethane, 1-(β-epithiopropyloxy)-2-[[2-(2-β-epithiopropyloxyethyl)oxyethyl]oxy]ethane, bis(5,6-epithio-3-oxahexyl) selenide, bis(5,6-epithio-3-oxahexyl) telluride, tetrakis(β-epithiopropyloxymethyl)methane, 1,1,1-tris(β-epithiopropyloxymethyl)propane, 1,5-bis(β-epithiopropyloxy)-2-(β-epithiopropyloxymethyl)-3-thiapentane, 1,5-bis(β-epithiopropyloxy)-2,4-bis(β-epithiopropyloxymethyl)-3-thiapentane, 1-(β-epithiopropyloxy)-2,2-bis(β-epithiopropyloxymethyl)-4-thiahexane, 1,5,6-tris(β-epithiopropyloxy)-4-(β-epithiopropyloxymethyl)-3-thiahexane, 1,8-bis(β-epithiopropyloxy)-4-(β-epithiopropyloxymethyl)-3,6-dithiaoctane, 1,8-bis(β-epithiopropyloxy)-4,5bis(β-epithiopropyloxymethyl)-3,6-dithiaoctane, 1,8-bis(β-epithiopropyloxy)-4,4-bis(β-epithiopropyloxymethyl)-3,6-dithiaoctane, 1,8-bis(β-epithiopropyloxy)-2,4,5-tris(β-epithiopropyloxymethyl)-3,6-dithiaoctane, 1,8-bis(β-epithiopropyloxy)-2,5-bis(β-epithiopropyloxymethyl)-3,6-dithiaoctane, 1,9-bis(β-epithiopropyloxy)-5-(β-epithiopropyloxymethyl)-5-[(2-β-epithiopropyloxyethyl)oxymethyl]-3,7-dithianonane, 1,10-bis(β-epithiopropyloxy)-5,6-bis[(2-β-epithiopropyloxyethyl)oxy]-3,6,9-trithiadecane, 1,11-bis(β-epithiopropyloxy)-4,8-bis(β-epithiopropyloxymethyl)-3,6,9-trithiaundecane, 1,11-bis(β-epithiopropyloxy)-5,7-bis(β-epithiopropyloxymethyl)-3,6,9-trithiaundecane, 1,11-bis(β-epithiopropyloxy)-5,7-[(2-β-epithiopropyloxyethyl)oxymethyl]-3,6,9-trithiaundecane, 1,11-bis(β-epithiopropyloxy)-4,7-bis(β-epithiopropyloxymethyl)-3,6,9-trithiaundecane, 1,3-or 1,4-bis(β-epithiopropyloxy)cyclohexane, 1,3- or 1,4-bis(β-epithiopropyloxymethyl)cyclohexane, bis[4-(β-epithiopropyloxy)cyclohexyl]methane, 2,2-bis[4-(β-epithiopropyloxy)cyclohexyl]propane, bis[4-(β-epithiopropyloxy)cyclohexyl] sulfide, 2,5-bis(β-epithiopropyloxymethyl)-1,4-dithiane, 2,5-bis(β-epithiopropyloxyethyloxymethyl)-1,4-dithiane, 2,4- or 4,5-bis(3,4-epithio-1-oxabutyl)-1,3-diselenolane, 2,4- or 4,5-bis(4,5-epithio-2-oxapentyl)-1,3-diselenolane, 2,4-, 2,5- or 4,5-bis(3,4-epithio-1-oxabutyl)-1-thia-3-selenolane, 2,4-, 2,5- or 4,5-bis(4,5-epithio-2-oxapentyl)-1-thia-3-selenolane, bis(3,4-epithio-1-oxabutyl)tricycloselenaoctane, bis(3,4-epithio-1-oxabutyl)dicycloselenanonane, 2,3-, 2,4-, 2,5- or 3,4-bis(3,4-epithio-1-oxabutyl)selenophane, 2,3-, 2,4-, 2,5- or 3,4-bis(4,5-epithio-2-oxapentyl)selenophane, 2,3-, 2,5- or 2,6-bis(3,4-epithio-1-oxabutyl)-1,4-diselenane, 2,3-, 2,5- or 2,6-bis(4,5-epithio-2-oxapentyl)-1,4-diselenane, 2,4-, 2,5- or 2,6-bis(3,4-epithio-1-oxabutyl)-1,3-diselenane, 2,4-, 2,5- or 2,6-bis(4,5-epithio-2-oxapentyl)-1,3-diselenane, 2,3-, 2,5-, 2,6- or 3,5-bis(3,4-epithio-1-oxabutyl)-1-thia-4-selenane, 2,3-, 2,5-, 2,6- or 3,5-bis(4,5-epithio-2-oxapentyl)-1-thia-4-selenane, 2,4- or 4,5-bis(3,4-epithio-1-oxabutyl)-1,3-ditellurolane, 2,4- or 4,5-bis(4,5-epithio-2-oxapentyl)-1,3-ditellurolane, 2,4-, 2,5- or 4,5-bis(3,4-epithio-1-oxabutyl)-1-thia-3-tellurolane, 2,4-, 2,5- or 4,5-bis(4,5-epithio-2-oxapentyl)-1-thia-3-tellurolane, bis(3,4-epithio-1-oxabutyl)tricyclotelluraoctane, bis(3,4-epithio-1-oxabutyl)dicyclotelluranonane, 2,3-, 2,4-, 2,5- or 3,4-bis(3,4-epithio-1-oxabutyl)tellurophane, 2,3-, 2,4-, 2,5- or 3,4-bis(4,5-epithio-2-oxapentyl)tellurophane, 2,3-, 2,5- or 2,6-bis(3,4-epithio-1-oxabutyl)-1,4-ditellurane, 2,3-, 2,5- or 2,6-bis(4,5-epithio-2-oxapentyl)-1,4-ditellurane, 2,4-, 2,5- or 2,6-bis(3,4-epithio-1-oxabutyl)-1,3-ditellurane, 2,4-, 2,5- or 2,6-bis(4,5-epithio-2-oxapentyl)-1,3-ditellurane, 2,3-, 2,5-, 2,6- or 3,5-bis(3,4-epithio-1-oxabutyl)-1-thia-4-tellurane, 2,3-, 2,5-, 2,6- or 3,5-bis(4,5-epithio-2-oxapentyl)-1-thia-4-tellurane, 1,3- or 1,4-bis(β-epithiopropyloxy)benzene, 1,3- or 1,4-bis(β-epithiopropyloxymethyl)benzene, bis[4-(β-epithiopropyl)phenyl]methane, 2,2-bis[4-(β-epithiopropylthio)phenyl]propane, bis[4-(β-epithiopropylthio)phenyl] sulfide, bis[4-(β-epithiopropylthio)phenyl] sulfone, and 4,4'-bis(β-epithiopropylthio) biphenyl.

(4) Episulfide compounds having at least one epithioalkylthio group

pylthio)-4,5bis(β-epithiopropylthiomethyl)-3,6-dithiaoctane, 1,8-bis(β-epithiopropylthio)-4,4-bis(β-epithiopropylthiomethyl)-3,6-dithiaoctane, 1,8-bis(β-epithiopropylthio)-2,4,5-tris(β-epithiopropylthiomethyl)-3,6-dithiaoctane, 1,8-bis(β-epithiopropylthio)-2,5-bis(β-epithiopropylthiomethyl)-3,6-dithiaoctane, 1,9-bis(β-epithiopropylthio)-5-(β-epithiopropylthiomethyl)-5-[(2-β-epithiopropylthioethyl)thiomethyl]-3,7-dithianonane, 1,10-bis(β-epithiopropylthio)-5,6-bis[2-(2-β-epithiopropylthioethyl)thio]-3,6,9-trithiadecane, 1,11-bis(β-epithiopropylthio)-4,8-bis(β-epithiopropylthiomethyl)-3,6,9-trithiaundecane, 1,11-bis(β-epithiopropylthio)-5,7-bis(β-epithiopropylthiomethyl)-3,6,9-trithiaundecane, 1,11-bis(β-epithiopropylthio)-4,7-bis(β-epithiopropylthiomethyl)-3,6,9-trithiaundecane, tetra[2-(β-epithiopropylthio)acetyl]methane, 1,1,1-tri[2-(β-epithiopropylthio)acetyl]propane, tetra[2-(β-epithiopropylthiomethyl)acetyl]methane, 1,1,1-tri[2-(β-epithiopropylthiomethyl)acetyl]propane, bis(5,6-epithio-3-thiahexyl) selenide, 2,3-bis(6,7-thioepoxy-1-selena-4-thiaheptyl)-1-(3,4-thioepoxy-1-thiabutyl)propane, 1,1,3,3-tetrakis(4,5-thioepoxy-2-thiapentyl)-2-selenapropane, bis(4,5-thioepoxy-2-thiapentyl)-3,6,9-triselenaundecane-1,11-bis(3,4-thioepoxy-1-thiabutyl), 1,4-bis(3,4-thioepoxy-1-thiabutyl)-2,3-bis(6,7-thioepoxy-1-selena-4-thiaheptyl)butane, tris(4,5-thioepoxy-2-thiapentyl)-3-selena-6-thiaoctane-1,8-bis(3,4-thioepoxy-1-thiabutyl), bis(5,6-epithio-3-thiahexyl) telluride, 2,3-bis(6,7-thioepoxy-1-tellura-4-thiaheptyl)-1-(3,4-thioepoxy-1-thiabutyl)propane, 1,1,3,3-tetrakis(4,5-thioepoxy-2-thiapentyl)-2-tellurapropane, bis(4,5-thioepoxy-2-thiapentyl)-3,6,9-tritelluraundecane-1,11-bis(3,4-thioepoxy-1-thiabutyl), 1,4-bis(3,4-thioepoxy-1-thiabutyl)-2,3-bis(6,7-thioepoxy-1-tellura-4-thiaheptyl)butane, tris(4,5-thioepoxy-2-thiapentyl)-3-tellura-6-thiaoctane-1,8-bis(3,4-thioepoxy-1-thiabutyl), 1,3- or 1,4-bis(β-epithiopropylthio)cyclohexane, 1,3- or 1,4-bis(β-epithiopropylthiomethyl)cyclohexane, bis[4-(β-epithiopropylthio)cyclohexyl]methane, 2,2-bis[4-(β-epithiopropylthio)cyclohexyl]propane, bis[4-(β-epithiopropylthio)cyclohexyl] sulfide, 2,5-bis(β-epithiopropylthiomethyl)-1,4-dithiane, 2,5-bis(β-epithiopropylthioethylthiomethyl)-1,4-dithiane, 2,3-, 2,5- or 2,6-bis(3,4-epithio-1-thiabutyl)-1,4-diselenane, 2,3-, 2,5- or 2,6-bis(4,5-epithio-2-thiapentyl)-1,4-diselenane, 2,4-, 2,5- or 5,6-bis(3,4-epithio-1-thiabutyl)-1,3-diselenane, 2,4-, 2,5- or 5,6-bis(4,5-epithio-2-thiapentyl)-1,3-diselenane, 2,3-, 2,5-, 2,6- or 3,5-bis(3,4-epithio-1-thiabutyl)-1-thia-4-selenane, 2,3-, 2,5-, 2,6- or 3,5-bis(4,5-epithio-2-thiapentyl)-1-thia-4-selenane, 2,4- or 4,5-bis(3,4-epithio-1-thiabutyl)-1,3-diselenolane, 2,4- or 4,5-bis(4,5-epithio-2-thiapentyl)-1,3-diselenolane, 2,4-, 2,5- or 4,5-bis(4,5-epithio-2-thiapentyl)-1-thia-3-selenolane, 2,6-bis(4,5-epithio-2-thiapentyl)-1,3,5-triselenane, bis(3,4-epithio-1-thiabutyl)tricycloselenaoctane, bis(3,4-epithio-1-thiabutyl)dicycloselenanonane, 2,3-, 2,4-, 2,5- or 3,4-bis(3,4-epithio-1-thiabutyl)selenophane, 2,3-, 2,4-, 2,5- or 3,4-bis(4,5-epithio-2-thiapentyl)-5-(3,4-thioepoxy-1-thiabutyl)-1-selenacyclohexane, 2,3-, 2,4-, 2,5- or 4,5-bis(3,4-epithio-1-thiabutyl)-1-selenacyclohexane, 2,3-, 2,4-, 2,5- or 4,5-bis(3,4-epithio-1-thiabutyl)-1,4-ditellurane, 2,3-, 2,5- or 2,6-bis(4,5-epithio-2-thiapentyl)-1,4-ditellurane, 2,4-, 2,5- or 5,6-bis(3,4-epithio-1-thiabutyl)-1,3-ditellurane, 2,4-, 2,5- or 5,6-bis(4,5-epithio-2-thiapentyl)-1,3-ditellurane, 2,3-, 2,5-, 2,6- or 3,5-bis(3,4-epithio-1-thiabutyl)-1-thia-4-tellurane, 2,3-, 2,5-, 2,6- or 3,5-bis(4,5-epithio-2-thiapentyl)-1-thia-4-tellurane, 2,4- or 4,5-bis(3,4-epithio-1-thiabutyl)-1,3-ditellurolane, 2,4- or 4,5-bis(4,5-epithio-2-thiapentyl)-1,3-ditellurolane, 2,4-, 2,5- or 4,5-bis(3,4-epithio-1-thiabutyl)-1-thia-3-tellurolane, 2,4-, 2,5- or 4,5-bis(4,5-epithio-2-thiapentyl)-1-thia-3-tellurolane, 2,6-bis(4,5-epithio-2-thiapentyl)-1,3,5-tritellurane, bis(3,4-epithio-1-thiabutyl)tricyclotelluraoctane, bis(3,4-epithio-1-thiabutyl)dicyclotelluranonane, 2,3-, 2,4-, 2,5- or 3,4-bis(3,4-epithio-1-thiabutyl)tellurophane, 2,3-, 2,4-, 2,5- or 3,4-bis(4,5-epithio-2-thiapentyl)tellurophane, 2-(4,5-thioepoxy-2-thiapentyl)-5-(3,4-thioepoxy-1-thiabutyl)-1-telluracyclohexane, 2,3-, 2,4-, 2,5- or 3,4-bis(4,5-epithio-2-thiapentyl)telluracyclohexane, 1,3- or 1,4-bis(β-epithiopropylthio)benzene, 1,3- or 1,4-bis(β-epithiopropylthiomethyl)benzene, bis[4-(β-epithiopropylthio)phenyl]methane, 2,2-bis[4-(β-epithiopropylthio)phenyl]propane, bis[4-(β-epithiopropylthio)phenyl] sulfide, bis[4-(β-epithiopropylthio)phenyl] sulfone, and 4,4'-bis(β-epithiopropylthio) biphenyl.

45 (5) Episulfide compounds having at least one epithioalkylseleno group

[0017] Bis(β-epithiopropyl) selenide, bis(β-epithiopropyl) diselenide, bis(β-epithiopropyl)triselenide, bis(β-epithiopropylseleno)methane, 1,2-bis(β-epithiopropylseleno)ethane, 1,3-bis(β-epithiopropylseleno)propane, 1,2-bis(β-epithiopropylseleno)propane, 1-(β-epithiopropylseleno)-2-(β-epithiopropylselenomethyl)propane, 1,4-bis(β-epithiopropylseleno)butane, 1,3-bis(β-epithiopropylseleno)butane, 1-(β-epithiopropylseleno)-3-(β-epithiopropylselenomethyl)butane, 1,5-bis(β-epithiopropylseleno)pentane, 1-(β-epithiopropylseleno)-4-(β-epithiopropylselenomethyl)pentane, 1,6-bis(β-epithiopropylseleno)hexane, 1-(β-epithiopropylseleno)-5-(β-epithiopropylselenomethyl)hexane, 1-(β-epithiopropylseleno)-2-[(2-β-epithiopropylselenoethyl)thio]ethane, 1-(β-epithiopropylseleno)-2-[[2-(2-β-epithiopropylselenoethyl)selenoethyl]thio]ethane, tetrakis(β-epithiopropylselenomethyl)methane, 1,1,1-tris(β-epithiopropylselenomethyl)propane, 1,5-bis(β-epithiopropylseleno)-2-(β-epithiopropylselenomethyl)-3-thiapentane, 1,5-bis(β-epithiopropylseleno)-2,4-bis(β-epithiopropylselenomethyl)-3-thiapentane, 1-(β-epithiopropylseleno)-2,2-bis(β-epithiopropylselenomethyl)-4-thiahexane, 1,5,6-tris(β-epithiopropylseleno)-4-(β-epithiopropylselenomethyl)-3-thiahexane, 1,8-bis(β-epithiopropylseleno)-4-(β-epithiopropylselenomethyl)-3,6-dithiaoctane, 1,8-bis(β-epithiopropylseleno)-4,5-bis(β-epithiopropylselenomethyl)-3,6-

dithiaoctane, 1,8-bis(β-epithiopropylseleno)-4,4-bis(β-epithiopropylselenomethyl)-3,6-dithiaoctane, 1,8-bis(β-epithiopropylseleno)-2,4,5-tris(β-epithiopropylselenomethyl)-3,6-dithiaoctane, 1,8-bis(β-epithiopropylseleno)-2,5-bis(β-epithiopropylselenomethyl)-3,6-dithiaoctane, 1,9-bis(β-epithiopropylseleno)-5-(β-epithiopropylselenomethyl)-5-[(2-β-epithiopropylselenoethyl)selenomethyl]-3,7-dithianonane, 1,10-bis(β-epithiopropylseleno)-5,6-bis[(2-β-epithiopropylselenoethyl)thio]-3,6,9-trithiadecane, 1,11-bis(β-epithiopropylseleno)-4,8-bis(β-epithiopropylselenomethyl)-3,6,9-trithiaundecane, 1,11-bis(β-epithiopropylseleno)-5,7-bis(β-epithiopropylselenomethyl)-3,6,9-trithiaundecane, 1,11-bis(β-epithiopropylseleno)-4,7-bis(β-epithiopropylselenomethyl)-3,6,9-trithiaundecane, tetra[2-(β-epithiopropylseleno)acetyl methyl]methane, 1,1,1-tri[2-(β-epithiopropylseleno)acetyl methyl]propane, tetra[2-(β-epithiopropylselenomethyl)acetyl methyl]methane, 1,1,1-tri[2-(β-epithiopropylselenomethyl)acetyl methyl]propane, bis(5,6-epithio-3-selenohexyl) selenide, 2,3-bis(6,7-thioepoxy-1-selena-4-selenoheptyl)-1-(3,4-thioepoxy-1-selenobutyl)propane, 1,1,3,3-tetrakis(4,5-thioepoxy-2-selenopentyl)-2-selenapropane, bis(4,5-thioepoxy-2-selenopentyl)-3,6,9-triselenaunderdecane-1,11-bis(3,4-thioepoxy-1-selenobutyl), 1,4-bis(3,4-thioepoxy-1-selenobutyl)-2,3-bis(6,7-thioepoxy-1-selena-4-selenoheptyl)butane, tris(4,5-thioepoxy-2-selenopentyl)-3-selena-6-thiaoctane-1,8-bis(3,4-thioepoxy-1-selenobutyl), bis(5,6-epithio-3-selenohexyl) telluride, 2,3-bis(6,7-thioepoxy-1-tellura-4-selenoheptyl)-1-(3,4-thioepoxy-1-selenobutyl)propane, 1,1,3,3-tetrakis(4,5-thioepoxy-2-selenopentyl)-2-tellurapropane, bis(4,5-thioepoxy-2-selenopentyl)-3,6,9-tritelluraundecane-1,11-bis(3,4-thioepoxy-1-selenobutyl), 1,4-bis(3,4-thioepoxy-1-selenobutyl)-2,3-bis(6,7-thioepoxy-1-tellura-4-selenoheptyl)butane, tris(4,5-thioepoxy-2-selenopentyl)-3-tellura-6-thiaoctane-1,8-bis(3,4-thioepoxy-1-selenobutyl), 1,3- or 1,4-bis(β-epithiopropylseleno)cyclohexane, 1,3- or 1,4-bis(β-epithiopropylselenomethyl)cyclohexane, bis[4-(β-epithiopropylseleno)cyclohexyl]methane, 2,2-bis[4-(β-epithiopropylseleno)cyclohexyl]propane, bis[4-(β-epithiopropylseleno)cyclohexyl] sulfide, 2,5-bis(β-epithiopropylselenomethyl)-1,4-dithiane, 2,5-bis(β-epithiopropylselenoethylthiomethyl)-1,4-dithiane, 2,3-, 2,5- or 2,6-bis(3,4-epithio-1-selenobutyl)-1,4-diselenane, 2,3-, 2,5- or 2,6-bis(4,5-epithio-2-selenopentyl)-1,4-diselenane, 2,4-, 2,5- or 5,6-bis(4,5-epithio-2-selenopentyl)-1,3-diselenane, 2,4-, 2,5- or 5,6-bis(4,5-epithio-2-selenopentyl)-1,3-diselenane, 2,3-, 2,5-, 2,6- or 3,5-bis(4,5-epithio-2-selenopentyl)-1-thia-4-selenane, 2,3-, 2,5-, 2,6- or 3,5-bis(4,5-epithio-2-selenopentyl)-1-thia-4-selenane, 2,4- or 4,5-bis(3,4-epithio-1-selenobutyl)-1,3-diselenolane, 2,4- or 4,5-bis(4,5-epithio-2-selenopentyl)-1,3-diselenolane, 2,4-, 2,5- or 4,5-bis(3,4-epithio-1-selenobutyl)tricycloselenaoctane, bis(3,4-epithio-1-selenobutyl)dicycloselenanonane, 2,3-, 2,4-, 2,5- or 3,4-bis(4,5-epithio-2-selenopentyl)selenophane, 2,3-, 2,4-, 2,5- or 3,4-bis(4,5-epithio-2-selenopentyl)-1-selenacyclohexane, 2,3-, 2,4-, 2,5-, 2,6-, 3,4-, 3,5- or 4,5-bis(4,5-thioepoxy-2-selenopentyl)-1-selenacyclohexane, 2,3-, 2,4-, 2,5-, 2,6-, 3,4-, 3,5- or 4,5-bis(3,4-thioepoxy-1-selenobutyl)-1-selenacyclohexane, 2,3-, 2,5- or 2,6-bis(3,4-epithio-1-selenobutyl)-1,4-ditellurane, 2,3-, 2,5- or 2,6-bis(4,5-epithio-2-selenopentyl)-1,4-ditellurane, 2,4-, 2,5- or 5,6-bis(3,4-epithio-1-selenobutyl)-1,3-ditellurane, 2,4-, 2,5- or 5,6-bis(4,5-epithio-2-selenopentyl)-1,3-ditellurane, 2,3-, 2,5-, 2,6- or 3,5-bis(3,4-epithio-1-selenobutyl)-1-thia-4-tellurane, 2,3-, 2,5-, 2,6- or 3,5-bis(4,5-epithio-2-selenopentyl)-1-thia-4-tellurane, 2,4- or 4,5-bis(3,4-epithio-1-selenobutyl)-1,3-ditellurolane, 2,4- or 4,5-bis(4,5-epithio-2-selenopentyl)-1,3-ditellurolane, 2,4-, 2,5- or 4,5-bis(3,4-epithio-1-selenobutyl)-1-thia-3-tellurolane, 2,4-, 2,5- or 4,5-bis(4,5-epithio-2-selenopentyl)-1-thia-3-tellurolane, 2,6-bis(4,5-epithio-2-selenopentyl-1,3,5-tritellurane, bis(3,4-epithio-1-selenobutyl)tricyclotelluraoctane, bis(3,4-epithio-1-selenobutyl)dicyclotelluranonane, 2,3-, 2,4-, 2,5- or 3,4-bis(3,4-epithio-1-selenobutyl)tellurophane, 2,3-, 2,4-, 2,5- or 3,4-bis(4,5-epithio-2-selenopentyl)tellurophane, 2-(4,5-thioepoxy-2-selenopentyl)-5-(3,4-thioepoxy-1-selenobutyl)-1-telluracyclohexane, 2,3-, 2,4-, 2,5-, 2,6-, 3,4-, 3,5- or 4,5-bis(4,5-thioepoxy-2-selenopentyl)-1-telluracyclohexane, 1,3- or 1,4-bis(β-epithiopropylselenomethyl)benzene, bis[4-(β-epithiopropylseleno)phenyl]methane, 2,2-bis[4-(β-epithiopropylseleno)phenyl]propane, bis[4-(β-epithiopropylseleno)phenyl] sulfide, bis[4-(β-epithiopropylseleno)phenyl]sulfone, and 4,4'-bis(β-epithiopropylseleno) biphenyl.

(6) Episulfide compounds having at least one epithioalkyltelluro group

[0018] Bis(β-epithiopropyl) telluride, bis(β-epithiopropyl) ditelluride, bis(β-epithiopropyl)tritelluride, bis(β-epithiopropyltelluro)methane, 1,2-bis(β-epithiopropyltelluro)ethane, 1,3-bis(β-epithiopropyltelluro)propane, 1,2-bis(β-epithiopropyltelluro)propane, 1-(β-epithiopropyltelluro)-2-(β-epithiopropyltelluromethyl)propane, 1,4-bis(β-epithiopropyltelluro)butane, 1,3-bis(β-epithiopropyltelluro)butane, 1-(β-epithiopropyltelluro)-3-(β-epithiopropyltelluromethyl)butane, 1,5-bis(β-epithiopropyltelluro)pentane, 1-(β-epithiopropyltelluro)-4-(β-epithiopropyltelluromethyl)pentane, 1,6-bis(β-epithiopropyltelluro)hexane, 1-(β-epithiopropyltelluro)-5-(β-epithiopropyltelluromethyl)hexane, 1-(β-epithiopropyltelluro)-2-[(2-β-epithiopropyltelluroethyl)thio]ethane, 1-(β-epithiopropyltelluro)-2-[2-(2-β-epithiopropyltelluroethyl)telluroethyl]thio]ethane, tetrakis(β-epithiopropyltelluromethyl)methane, 1,1,1-tris(β-epithiopropyltelluromethyl)propane, 1,5-bis(β-epithiopropyltelluro)-2-(β-epithiopropyltelluromethyl)-3-thiapentane, 1,5-bis(β-epithiopropyltelluro)-2,4-bis(β-epithiopropyltelluromethyl)-3-thiapentane, 1-(β-epithiopropyltelluro)-2,2-bis(β-epithiopropyltelluromethyl)-4-thiahexane, 1,5,6-tris

(β -epithiopropyltelluro)-4-(β -epithiopropyltefluromethyl)-3-thiahexane, 1,8-bis(β -epithiopropyltelluro)-4-(β -epithiopropyltelluromethyl)-3,6-dithiaoctane, 1,8-bis(β -epithiopropyltelluro)-4,5bis(β -epithiopropyltelluromethyl)-3,6-dithiaoctane, 1,8-bis(β -epithiopropyltelluro)-2,4,5-tris(β -epithiopropyltelluromethyl)-3,6-dithiaoctane, 1,8-bis(β -epithiopropyltelluro)-2,5-bis(β -epithiopropyltel-
5 luromethyl)-3,6-dithiaoctane, 1,9-bis(β -epithiopropyltelluro)-5-(β -epithiopropyltelluromethyl)-5-[2-(β -epithiopropyltel-
luroethyl)selenomethyl]-3,7-dithianonane, 1,10-bis(β -epithiopropyltelluro)-5,6-bis[(2- β -epithiopropyltelluroethyl)thio]-
10 3,6,9-trithiadecane, 1,11-bis(β -epithiopropyltelluro)-4,8-bis(β -epithiopropyltelluromethyl)-3,6,9-trithiaundecane, 1,11-
bis(β -epithiopropyltelluro)-5,7-bis(β -epithiopropyltelluromethyl)-3,6,9-trithiaundecane, 1,11-bis(β -epithiopropyltelluro)-
15 5,7-[2-(β -epithiopropyltelluroethyl)selenomethyl]-3,6,9-trithiaundecane, 1,11-bis(β -epithiopropyltelluro)-4,7-bis(β -epithi-
o-propyltelluromethyl)-3,6,9-trithiaundecane, tetra[2-(β -epithiopropyltelluro)acetyl methyl]methane, 1,1,1-tri[2-(β -epithi-
o-propyltelluro)acetyl methyl]propane, tetra[2-(β -epithiopropyltelluromethyl)acetyl methyl]methane, 1,1,1-tri[2-(β -epithi-
o-propyltelluromethyl)acetyl methyl]propane, bis(5,6-epithio-3-tellurohexyl) selenide, 2,3-bis(6,7-thioepoxy-1-selena-4-tel-
20 luroheptyl)-1-(3,4-thioepoxy-1-tellurobutyl)propane, 1,1,3,3,-tetrakis(4,5-thioepoxy-2-telluropentyl)-2-selenapropane,
bis(4,5-thioepoxy-2-telluropentyl)-3,6,9-triselenaunderdecane-1,11-bis(3,4-thioepoxy-1-tellurobutyl), 1,4-bis(3,4-thioe-
25 poxy-1-tellurobutyl)-2,3-bis(6,7-thioepoxy-1-selena-4-telluroheptyl)butane, tris(4,5-thioepoxy-2-telluropentyl)-3-selena-
6-thiaoctane-1,8-bis(3,4-thioepoxy-1-tellurobutyl), bis(5,6-epithio-3-tellurohexyl) telluride, 2,3-bis(6,7-thioepoxy-1-tellu-
ra-4-telluroheptyl)-1-(3,4-thioepoxy-1-tellurobutyl)propane, 1,1,3,3,-tetrakis(4,5-thioepoxy-2-telluropentyl)-2-tellurapro-
pane, bis(4,5-thioepoxy-2-telluropentyl)-3,6,9-tritelluraundecane-1,11-bis(3,4-thioepoxy-1-tellurobutyl), 1,4-bis(3,4-
30 thioepoxy-1-tellurobutyl)-2,3-bis(6,7-thioepoxy-1-tellura-4-telluroheptyl)butane, tris(4,5-thioepoxy-2-telluropentyl)-3-tel-
lura-6-thiaoctane-1,8-bis(3,4-thioepoxy-1-tellurobutyl), 1,3- or 1,4-bis(β -epithiopropyltelluro)cyclohexane, 1,3- or 1,4-bis
(β -epithiopropyltelluromethyl)cyclohexane, bis[4-(β -epithiopropyltelluro)cyclohexyl]methane, 2,2-bis[4-(β -epithiopropyl-
35 telluro)cyclohexyl]propane, bis[4-(β -epithiopropyltelluro)cyclohexyl] sulfide, 2,5-bis(β -epithiopropyltelluromethyl)-1,4-
dithiane, 2,5-bis(β -epithiopropyltelluroethylthiomethyl)-1,4-dithiane, 2,3-, 2,5- or 2,6-bis(3,4-epithio-1-tellurobutyl)-1,4-
diselenane, 2,3-, 2,5- or 2,6-bis(4,5-epithio-2-telluropentyl)-1,4-diselenane, 2,4-, 2,5- or 5,6-bis(3,4-epithio-1-tel-
40 lurobutyl)-1,3-diselenane, 2,4-, 2,5- or 5,6-bis(4,5-epithio-2-telluropentyl)-1,3-diselenane, 2,3-, 2,5-, 2,6- or 3,5-bis(3,4-
epithio-1-tellurobutyl)-1-thia-4-selenane, 2,3-, 2,5-, 2,6- or 3,5-bis(4,5-epithio-2-telluropentyl)-1-thia-4-selenane, 2,4- or
4,5-bis(3,4-epithio-1-tellurobutyl)-1,3-diselenolane, 2,4- or 4,5-bis(4,5-epithio-2-telluropentyl)-1,3-diselenolane, 2,4-,
2,5- or 4,5-bis(3,4-epithio-1-tellurobutyl)-1-thia-3-selenolane, 2,4-, 2,5- or 4,5-bis(4,5-epithio-2-telluropentyl)-1-thia-3-
45 selenolane, 2,6-bis(4,5-epithio-2-telluropentyl)-1,3,5-triselenane, bis(3,4-epithio-1-tellurobutyl)tricycloselenaoctane, bis
(3,4-epithio-1-tellurobutyl)dicycloselenaanonane, 2,3-, 2,4-, 2,5- or 3,4-bis(3,4-epithio-1-tellurobutyl)selenophane, 2,3-,
2,4-, 2,5- or 3,4-bis(4,5-epithio-2-telluropentyl)selenophane, 2-(4,5-thioepoxy-2-telluropentyl)-5-(3,4-thioepoxy-1-tel-
lurobutyl)-1-selenacyclohexane, 2,3-, 2,4-, 2,5-, 2,6-, 3,4-, 3,5- or 4,5-bis(3,4-thioepoxy-1-tellurobutyl)-1-selenacyclohex-
ane, 2,3-, 2,4-, 2,5-, 2,6-, 3,4-, 3,5- or 4,5-bis(4,5-thioepoxy-2-telluropentyl)-1-selenacyclohexane, 2,3-, 2,5- or 2,6-bis
(3,4-epithio-1-tellurobutyl)-1,4-ditellurane, 2,3-, 2,5- or 2,6-bis(4,5-epithio-2-telluropentyl)-1,4-ditellurane, 2,4-, 2,5- or
5,6-bis(3,4-epithio-1-tellurobutyl)-1,3-ditellurane, 2,4-, 2,5- or 5,6-bis(4,5-epithio-2-telluropentyl)-1,3-ditellurane, 2,3-,
2,5-, 2,6- or 3,5-bis(3,4-epithio-1-tellurobutyl)-1-thia-4-tellurane, 2,3-, 2,5-, 2,6- or 3,5-bis(4,5-epithio-2-telluropentyl)-1-
thia-4-tellurane, 2,4- or 4,5-bis(3,4-epithio-1-tellurobutyl)-1,3-ditellurolane, 2,4- or 4,5-bis(4,5-epithio-2-telluropentyl)-
1,3-ditellurolane, 2,4-, 2,5- or 4,5-bis(3,4-epithio-1-tellurobutyl)-1-thia-3-tellurolane, 2,4-, 2,5- or 4,5-bis(4,5-epithio-2-
telluropentyl)-1-thia-3-tellurolane, 2,6-bis(4,5-epithio-2-telluropentyl)-1,3,5-tritellurane, bis(3,4-epithio-1-tellurobutyl)tri-
cyclotelluraoctane, bis(3,4-epithio-1-tellurobutyl)dicyclotelluranonane, 2,3-, 2,4-, 2,5- or 3,4-bis(3,4-epithio-1-tel-
lurobutyl)tellurophane, 2,3-, 2,4-, 2,5- or 3,4-bis(4,5-epithio-2-telluropentyl)tellurophane, 2-(4,5-thioepoxy-2-tellu-
40 ropentyl)-5-(3,4-thioepoxy-1-tellurobutyl)-1-telluracyclohexane, 2,3-, 2,4-, 2,5-, 2,6-, 3,4-, 3,5- or 4,5-bis(3,4-thioepoxy-1-
tellurobutyl)-1-telluracyclohexane, 2,3-, 2,4-, 2,5-, 2,6-, 3,4-, 3,5- or 4,5-bis(4,5-thioepoxy-2-telluropentyl)-1-telluracy-
clohexane, 1,3- or 1,4-bis(β -epithiopropyltelluro)benzene, 1,3- or 1,4-bis(β -epithiopropyltelluromethyl)benzene, bis[4-(β -
45 epithiopropyltelluro)phenyl]methane, 2,2-bis[4-(β -epithiopropyltelluro)phenyl]propane, bis[4-(β -epithiopropyltelluro)
phenyl] sulfide, bis[4-(β -epithiopropyltelluro)phenyl] sulfone, and 4,4'-bis(β -epithiopropyltelluro) biphenyl.

(7) Episulfide compounds having unsaturated group

50 [0019] Vinylphenyl thioglycidyl ether, vinylbenzyl thioglycidyl ether, thioglycidyl methacrylate, thioglycidyl acrylate, and allyl thioglycidyl ether.

(8) Other episulfide compounds

55 [0020] Ethylene sulfide, propylene sulfide, thioglycidol, thioglycidyl acetate, thioglycidyl propionate, and thioglycidyl benzoate.

[0021] The episulfide compounds referred to herein may further include the compounds derived from the above episulfide compounds by replacing at least one hydrogen of its epithio group with methyl group.

[0022] The episulfide compounds having an epi(di)thioethyl group represented by the formula 2 may be used alone or in combination of two or more, and preferably used in an amount of 1 to 95 parts by weight based on 100 parts by weight of the alicyclic compound.

[0023] To improve the properties such as oxidation resistance, weathering resistance, dyeability, strength and refractive index, the composition for optical materials of the present invention may further contain an compound capable of reacting with the alicyclic compound and/or the additive compound (episulfide compound) in an amount of 1 to 50 parts by weight based on 100 parts by weight of the alicyclic compound. Such a compound is hereinafter referred to as "additive compound." A composition containing the additive compound is cured by polymerization, if necessary, in the presence of a known catalyst for curing by polymerization.

[0024] The additive compound may include epoxy compounds, iso(thio)cyanates, carboxylic acids, carboxylic anhydrides, phenol compounds, amines, vinyl compounds, allyl compounds, acryl compounds, methacryl compounds, mercaptans, inorganic compounds having sulfur atom, and inorganic compounds having selenium atom. Examples thereof are shown below.

15 (1) Epoxy compounds

[0025]

- (i) Monoepoxy compounds such as ethylene oxide and propylene oxide;
- (ii) Phenolic epoxy compounds produced by condensing epihalohydrins with polyhydric phenol compounds such as hydroquinone, catechol, resorcinol, bisphenol A, bisphenol F, bisphenol ether, halogenated bisphenol A and novolak resins;
- (iii) Alcoholic epoxy compounds produced by condensing epihalohydrins with alcohol compounds such as methanol, ethanol, propanol, butanol, ethylene glycol, diethylene glycol, triethylene glycol, polyethylene glycol, propylene glycol, dipropylene glycol, polypropylene glycol, 1,3-propanediol, 1,4-butanediol, 1,6-hexanediol, neopentyl glycol, glycerol, trimethylolpropane, pentaerythritol, 1,3- or 1,4-cyclohexanediol, 1,3- or 1,4-cyclohexanedimethanol, hydrogenated bisphenol A, bisphenol A-ethylene oxide adducts, and bisphenol A-propylene oxide adducts;
- (iv) Urethane epoxy compounds produced by the reaction of diisocyanate compounds with the above alcohol compounds or phenol compounds;
- (v) Glycidyl ester epoxy compounds produced by condensing epihalohydrins with carboxylic acids such as acetic acid, propionic acid, benzoic acid, adipic acid, sebacic acid, dodecandicarboxylic acid, dimer acid, phthalic acid, isophthalic acid, terephthalic acid, tetrahydrophthalic acid, methyltetrahydrophthalic acid, hexahydrophthalic acid, HET acid, nadic acid, maleic acid, succinic acid, fumaric acid, trimellitic acid, benzenetetracarboxylic acid, benzophonetetracarboxylic acid, naphthalenedicarboxylic acid and diphenyldicarboxylic acid, acrylic acid, methacrylic acid, and fumaric acid;
- (vi) Amine epoxy compounds produced by condensing epihalohydrins with amine compounds such as ethylenediamine, 1,2-diaminopropane, 1,3-diaminopropane, 1,2-diaminobutane, 1,3-diaminobutane, 1,4-diaminobutane, 1,5-diaminopentane, 1,6-diaminohexane, 1,7-diaminoheptane, 1,8-diaminoctane, bis(3-aminopropyl) ether, 1,2-bis(3-aminopropoxy)ethane, 1,3-bis(3-aminopropoxy)-2,2'-dimethylpropane, 1,2-, 1,3- or 1,4-bisaminocyclohexane, 1,3- or 1,4-bisaminomethylcyclohexane, 1,3- or 1,4-bisaminoethylcyclohexane, 1,3- or 1,4-bisaminopropylcyclohexane, hydrogenated 4,4'-diaminodiphenylmethane, isophoronediamine, 1,4-bisaminopropylpiperadine, m- or p-phenylenediamine, 2,4- or 2,6-tolylendiamine, m- or p-xylylenediamine, 1,5- or 2,6-naphthalenediamine, 4,4'-diaminodiphenylmethane, 4,4'-diaminodiphenyl ether, 2,2-(4,4'-diaminodiphenyl)propane, N,N'-dimethylethylenediamine, N,N-dimethyl-1,2-diaminopropane, N,N'-dimethyl-1,3-diaminopropane, N,N'-dimethyl-1,2-diaminobutane, N,N'-dimethyl-1,3-diaminobutane, N,N'-dimethyl-1,4-diaminobutane, N,N'-dimethyl-1,5-diaminopentane, N,N'-dimethyl-1,6-diaminohexane, N,N'-dimethyl-1,7-diaminoheptane, N,N'-diethylethylenediamine, N,N'-diethyl-1,2-diaminopropane, N,N'-diethyl-1,3-diaminopropane, N,N'-diethyl-1,2-diaminobutane, N,N'-diethyl-1,3-diaminobutane, N,N'-diethyl-1,4-diaminobutane, N,N'-diethyl-1,6-diaminohexane, piperadine, 2-methylpiperadine, 2,5- or 2,6-dimethylpiperadine, homopiperadine, 1,1-di(4-piperidyl)methane, 1,2-di(4-piperidyl)ethane, 1,3-di(4-piperidyl)propane, and 1,4-di(4-piperidyl)butane;
- (vii) Sulfur-containing epoxy compounds such as bis(β -epoxypropyl) sulfide, bis(β -epoxypropylthio)methane, 1,2-bis(β -epoxypropylthio)ethane, 1,3-bis(β -epoxypropylthio)propane, 1,2-bis(β -epoxypropylthio)propane, 1-(β -epoxypropylthio)-2-(β -epoxypropylthiomethyl)propane, 1,4-bis(β -epoxypropylthio)butane, 1,3-bis(β -epoxypropylthio)butane, 1-(β -epoxypropylthio)-3-(β -epoxypropylthiomethyl)butane, 1,5-bis(β -epoxypropylthio)pentane, 1-(β -epoxypropylthio)-4-(β -epoxypropylthiomethyl)pentane, 1,6-bis(β -epoxypropylthio)hexane, 1-(β -epoxypropylthio)-5-(β -epoxypropylthiomethyl)hexane, 1-(β -epoxypropylthio)-2-[2-(β -epoxypropylthioethyl)thio]ethane, 1-(β -epoxypropylthio)-2-[[2-(β -epoxypropylthioethyl)thioethyl]thio]ethane, tetrakis(β -epoxypropyl-thiomethyl)methane, 1,1,1-tris(β -epoxypropylthiomethyl)propane, 1,5-bis(β -epoxypropylthio)-2-(β -epoxypropylthiomethyl)-3-thiapentane, 1,5-bis(β -

epoxypropylthio)-2,4-bis(β-epoxypropylthiomethyl)-3-thiapentane, 1-(β-epoxypropylthio)-2,2-bis(β-epoxypropylthiomethyl)-4-thiahexane, 1,5,6-trips(β-epoxypropylthio)-4-(β-epoxypropylthiomethyl)-3-thiahexane, 1,8-bis(β-epoxypropylthio)-4-(β-epoxypropylthiomethyl)-3,6-dithiaoctane, 1,8-bis(β-epoxypropylthio)-4,5-bis(β-epoxypropylthiomethyl)-3,6-dithiaoctane, 1,8-bis(β-epoxypropylthio)-4,4-bis(β-epoxypropylthiomethyl)-3,6-dithiaoctane, 1,8-bis(β-epoxypropylthio)-2,4,5-tris(β-epoxypropylthiomethyl)-3,6-dithiaoctane, 1,8-bis(β-epoxypropylthio)-2,5-bis(β-epoxypropylthiomethyl)-3,6-dithiaoctane, 1,9-bis(β-epoxypropylthio)-5-(β-epoxypropylthiomethyl)-5-[(2-β-epoxypropylthioethyl)thiomethyl]-3,7-dithianonane, 1,10-bis(β-epoxypropylthio)-5,6-bis[(2-β-epoxypropylthioethyl)thio]-3,6,9-trithiadecane, 1,11-bis(β-epoxypropylthio)-4,8-bis(β-epoxypropylthiomethyl)-3,6,9-trithiaundecane, 1,11-bis(β-epoxypropylthio)-5,7-bis(β-epoxypropylthiomethyl)-3,6,9-trithiaundecane, 1,11-bis(β-epoxypropylthio)-4,7-bis(β-epoxypropylthiomethyl)-3,6,9-trithiaundecane, 1,3-or 1,4-bis(β-epoxypropylthio)cyclohexane, 1,3- or 1,4-bis(β-epoxypropylthiomethyl)cyclohexane, bis[4-(β-epoxypropylthio)cyclohexyl]methane, 2,2-bis[4-(β-epoxypropylthio)cyclohexyl]propane, bis[4-(β-epoxypropylthio)cyclohexyl] sulfide, 2,5-bis(β-epoxypropylthiomethyl)-1,4-dithiane, 1,3- or 1,4-bis(β-epoxypropylthio)benzene, 1,3- or 1,4-bis(β-epoxypropylthiomethyl)benzene, bis[4-(β-epoxypropylthio)phenyl]methane, 2,2-bis[4-(β-epoxypropylthio)phenyl]propane, bis[4-(β-epoxypropylthio)phenyl] sulfide, bis[4-(β-epoxypropylthio)phenyl] sulfone, and 4,4'-bis(β-epoxypropylthio)biphenyl;

(viii) Alicyclic epoxy compounds such as 3,4-epoxycyclohexyl-3,4-epoxycyclohexanecarboxylate, vinylcyclohexane dioxide, 2-(3,4-epoxycyclohexyl)-5,5-spiro-3,4-epoxycyclohexane-meta-dioxane, and bis(3,4-epoxycyclohexyl) adipate;

(ix) Epoxidized compounds of unsaturated compounds, such as cyclopentadiene epoxide, epoxidized soy bean oil, epoxidized polybutadiene, and vinylcyclohexene epoxide; and

(x) Epoxy compounds having unsaturated group such as vinylphenyl glycidyl ether, vinylbenzyl glycidyl ether, glycidyl methacrylate, glycidyl acrylate, and allyl glycidyl ether.

25 (2) Iso(thio)cyanates

[0026]

(i) Monoisocyanates such as methyl isocyanate, ethyl isocyanate, propyl isocyanate, isopropyl isocyanate, n-butyl isocyanate, sec-butyl isocyanate, tert-butyl isocyanate, pentyl isocyanate, hexyl isocyanate, octyl isocyanate, decyl isocyanate, cyclohexyl isocyanate, phenyl isocyanate, and tolyl isocyanate;

(ii) Polyisocyanates such as diethylene diisocyanate, tetramethylene diisocyanate, hexamethylene diisocyanate, trimethylhexamethylene diisocyanate, cyclohexane diisocyanate, 1,3-bis(isocyanatomethyl)cyclohexane, 1,4-bis(isocyanatomethyl)cyclohexane, isophorone diisocyanate, 2,6-bis(isocyanatomethyl)decahydronaphthalene, lysine triisocyanate, 2,4-tolenediisocyanate, 2,6-tolylene diisocyanate, o-tolydyne diisocyanate, 4,4'-diphenylmethane diisocyanate, diphenyl ether diisocyanate, 3-(2'-isocyanatocyclohexyl)propyl isocyanate, tris(phenylisocyanate) thiophosphate, isopropylidene bis(cyclohexylisocyanate), 2,2'-bis(4-isocyanatophenyl)propane, triphenylmethane triisocyanate, bis(diisocyanatotolyl)phenylmethane, 4,4',4"-triisocyanato-2,5-dimethoxyphenylamine, 3,3'-dimethoxybenzidine-4,4'-diisocyanate, 1,3-phenylene diisocyanate, 1,4-phenylene diisocyanate, 4,4'-diisocyanatobiphenyl, 4,4'-diisocyanato-3,3'-dimethylbiphenyl, dicyclohexylmethan-4,4'-diisocyanate, 1,1'-methylenebis(4-isocyanatobenzene), 1,1'-methylenebis(3-methyl-4-isocyanatobenzene), m-xylylene diisocyanate, p-xylylene diisocyanate, 1,3-bis(1-isocyanato-1-methylethyl)benzene, 1,4-bis(1-isocyanato-1-methylethyl)benzene, 1,3-bis(2-isocyanato-2-propyl)benzene, 2,6-bis(isocyanatomethyl)naphthalene, 1,5-naphthalene diisocyanate, bis(isocyanatomethyl)tetrahydrodicyclopentadiene, bis(isocyanatomethyl)dicyclopentadiene, bis(isocyanatomethyl)tetrahydrothiophene, 2,5-bis(isocyanatomethyl)norbornene, bis(isocyanatomethyl)adamantane, thiodiethyl diisocyanate, thiodipropyl diisocyanate, thiodihexyl diisocyanate, bis[(4-isocyanatomethyl)phenyl] sulfide, 2,5-diisocyanato-1,4-dithiane, 2,5-diisocyanatomethyl-1,4-dithiane, 2,5-diisocyanatomethyl thiophene, dithiodiethyl diisocyanate, dithiodipropyl diisocyanate, dimeric acid diisocyanate, and 1,3,5-tri(1-isocyanatohexyl)isocyanuric acid;

(iii) Isocyanates such as dimers produced by biuret reaction of the preceding polyisocyanates, cyclic trimers of the preceding polyisocyanates, and adducts of the preceding polyisocyanates with alcohols or thiols; and

(iv) Isothiocyanates corresponding to the preceding isocyanates having its isocyanate group or groups replaced by isothiocyanate group or groups partly or completely.

55 (3) Carboxylic acids

[0027] Acetic acid, propionic acid, benzoic acid, adipic acid, sebacic acid, dodecanedicarboxylic acid, dimer acid, phthalic acid, isophthalic acid, terephthalic acid, tetrahydrophthalic acid, methyltetrahydrophthalic acid, hexahydrophthalic acid, HET acid, nadic acid, maleic acid, succinic acid, fumaric acid, trimellitic acid, benzenetetracarboxylic acid,

benzophenonetetracarboxylic acid, naphthalenedicarboxylic acid and diphenyldicarboxylic acid, acrylic acid, methacrylic acid, and fumaric acid.

5 (4) Carboxylic anhydrides

[0028] Anhydrides of carboxylic acids described above.

10 (5) Phenol compounds

[0029] Polyhydric phenol compounds such as hydroquinone, catechol, resorcinol, bisphenol A, bisphenol F, bisphenol ether, halogenated bisphenol A and novolak resins.

15 (6) Amines

[0030] Amines described in "(1) Epoxy compounds."

20 (7) Vinyl compounds

[0031] Vinyl ether, ethyl vinyl ether, isobutyl vinyl ether, 2-ethylhexyl vinyl ether, phenyl vinyl ether, benzyl vinyl ether, 2-chloroethyl vinyl ether, cyclohexyl vinyl ether, vinyl glycidyl ether, vinylalcohol, methylvinylcarbinol, ethylene glycol monovinyl ether, ethylene glycol divinyl ether, diethylene glycol monovinyl ether, diethylene glycol divinyl ether, tetramethylene glycol monovinyl ether, divinyl sulfide, vinyl ethyl sulfide, vinyl phenyl sulfide, methyl vinyl ketone, divinyl dicarbonate, vinyl diglycol carbonate, vinylene carbonate, vinyl acetate, vinyl chloroacetate, vinyl propionate, vinyl butylate, vinyl hexanoate, vinyl 2-ethylhexanoate, divinyl adipate, vinyl benzoate, vinyl salicylate, vinyl acrylate, vinyl methacrylate, vinyl bromide, vinyl iodide, vinylphosphoric acid, vinylurea, styrene, 2-methylstyrene, 3-methylstyrene, 4-methylstyrene, α -methylstyrene, 2,4,6-trimethylstyrene, 4-t-butylstyrene, stilbene, vinylphenol, 3-vinylbenzyl alcohol, 4-vinylbenzyl alcohol, 2-(4-vinylphenylthio)ethanol, 2-(3-vinylphenylthio)ethanol, 2-(4-vinylbenzylthio)ethanol, 2-(3-vinylbenzylthio)ethanol, 1,3-bis(4-vinylbenzylthio)-2-propanol, 1,3-bis(3-vinylbenzylthio)-2-propanol, 2,3-bis(4-vinylbenzylthio)-1-propanol, 2,3-bis(3-vinylbenzylthio)-1-propanol, cinnamyl alcohol, cinnamaldehyde, 1,3-divinylbenzene, 1,4-divinylbenzene, trivinylbenzene, divinyl phthalate, 2-chlorostyrene, 3-chlorostyrene, 4-chlorostyrene, 3-chloromethylstyrene, 4-chloromethylstyrene, 4-aminostyrene, 3-cyanomethylstyrene, 4-cyanomethylstyrene, 4-vinylbiphenyl, 2,2'-divinylbiphenyl, 4,4'-divinylbiphenyl, 2,2'-distyryl ether, 4,4'-distyryl ether, 2,2'-distyryl sulfide, 4,4'-distyryl sulfide, 2,2-bis(4-vinylphenyl)propane, bis(4-vinylphenyl) ether, and 2,2-bis(4-vinyloxyphenyl)propane.

35 (8) Allyl compounds

[0032] Compounds described in "(7) Vinyl compounds" having its vinyl group replaced by an allyl group partially or completely.

40 (9) Acryl compounds

[0033] Methyl acrylate, ethyl acrylate, propyl acrylate, butyl acrylate, cyclohexyl acrylate, 2-hydroxyethyl acrylate, 3-hydroxypropyl acrylate, 2-hydroxypropyl acrylate, 3-phenoxy-2-hydroxypropyl acrylate, trimethylolpropane monoacrylate, 2-hydroxyethyl isocyanurate monoacrylate, 2-hydroxyethyl isocyanurate diacrylate, 2-hydroxyethyl cyanurate monoacrylate, 2-hydroxyethyl cyanurate diacrylate, ethylene glycol diacrylate, diethylene glycol diacrylate, 1,3-butylene glycol diacrylate, triethylene glycol diacrylate, polyethylene glycol diacrylate, propylene glycol diacrylate, 1,3-propanediol diacrylate, 1,3-butanediol diacrylate, 1,4-butanediol diacrylate, 1,6-hexanediol diacrylate, neopentyl glycol diacrylate, polypropylene glycol diacrylate, 2-hydroxy-1,3-diacyloxypropane, 2,2-bis[4-(acryloxyethoxy)phenyl]propane, 2,2-bis[4-(acryloxyethoxy)cyclohexyl]propane, 2,2-bis[4-(2-hydoroxy-3-acryloxypropoxy)phenyl]propane, 2,2-bis[4-(acryloxydiethoxy)phenyl]propane, 2,2-bis[4-(acryloxypolyethoxy)phenyl]propane, trimethylolpropane triacrylate, pentarythritol monoacrylate, pentarythritol diacrylate, pentarythritol triacrylate, pentarythritol tetraacrylate, bis(2,2,2-trimethylethyl) ether pentaacrylate, bis(2,2,2-trimethylethyl) ether hexaacrylate, and bis(4-acryloylthiophenyl) sulfide.

55 (10) Methacryl compounds

[0034] Compounds described in "(9) Acryl compounds" having its acryl group replaced by methacryl group partially or completely.

(11) Mercaptans

35 (12) Inorganic compounds having sulfur atom

[0036] Sulfur, hydrogen sulfide, carbon disulfide, carbon selenosulfide, ammonium sulfide, oxides of sulfur such as sulfur dioxide and sulfur trioxide, salts of thiocarbonic acid, sulfuric acid, salts of sulfuric acid, salts of hydrogensulfuric acid, salts of sulfurous acid, salts of hyposulfurous acid, salts of persulfuric acid, salts of thiocyanic acid, salts of thiosulfuric acid, halides such as sulfur dichloride, thionyl chloride and thiophosgen, boron sulfide, nitrogen sulfide, silicon sulfide, phosphorus sulfide, arsenic sulfide, metal sulfides, and metal hydrogensulfides.

(13) Inorganic compounds having selenium atom

[0037] Selenium, hydrogen selenide, selenium dioxide, carbon diselenide, ammonium selenide, oxides of selenium such as selenium dioxide, selenic acid, salts of selenic acid, selenous acid, salts of selenous acid, salts of hydrogenselenic acid, selenosulfuric acid, salts of selenosulfuric acid, selenopyrosulfuric acid, salts of selenopyrosulfuric acid, halides such as selenium tetrabromide and selenium oxychloride, salts of selenocyanic acid, boron selenide, phosphorus selenide, arsenic selenide, and metal selenides.

[0038] The composition for optical materials may be cured by polymerization, if necessary, in the presence of a curing catalyst such as amines, phosphines, quaternary ammonium salts, quaternary phosphonium salts, tertiary sulfonium salts, secondary iodonium salts, mineral acids, Lewis acids, organic acids, silicic acid compounds, tetrafluoroboric acid compounds, peroxides, azo compounds, condensates of aldehyde and ammonia compound, guanidine compounds, thiourea compounds, thiazole compounds, sulfenamide compounds, thiuram compounds, salts of dithiocarbamic acid, salts of xanthogenic acid, and esters of acid phosphoric acid. Examples of the curing catalysts are mentioned below.

(1) Amines

[0039] Primary amines such as ethylamine, n-propylamine, sec-propylamine, n-butylamine, sec-butylamine, iso-butylamine, tert-butylamine, pentylamine, hexylamine, heptylamine, octylamine, decylamine, laurylamine, myristylamine,

5 1,2-dimethylhexylamine, 3-pentylamine, 2-ethylhexylamine, allylamine, aminoethanol, 1-aminopropanol, 2-aminopropanol, aminobutanol, aminopentanol, aminohexanol, 3-ethoxypropylamine, 3-propoxypropylamine, 3-isopropoxypropylamine, 3-butoxypropylamine, 3-isobutoxypropylamine, 3-(2-ethylhexyloxy)propylamine, aminocyclopentane, amino-cyclohexane, aminonorbornene, aminomethylcyclohexane, aminobenzene, benzylamine, phenetylamine, α -phe-

10 nylethylamine, naphthylamine and furfurylamine;

primary polyamines such as ethylenediamine, 1,2-diaminopropane, 1,3-diaminopropane, 1,2-diaminobutane, 1,3-diamino-

butane, 1,4-diaminobutane, 1,5-diaminopentane, 1,6-diaminohexane, 1,7-diaminoheptane, 1,8-diaminoctane, dimethylaminopropylamine, diethylaminopropylamine, bis-(3-aminopropyl) ether, 1,2-bis-(3-aminopropoxy)ethane, 1,3-

15 bis-(3-aminopropoxy)-2,2'-dimethylpropane, aminoethylethanamine, 1,2-, 1,3- or 1,4-bisaminocyclohexane, 1,3- or 1,4-bisaminomethylcyclohexane, 1,3- or 1,4-bisaminoethylcyclohexane, 1,3- or 1,4-bisaminopropylcyclohexane, hydro-

20 genated 4,4'-diaminodiphenylmethane, 2- or 4-aminopiperidine, 2- or 4-aminomethylpiperidine, 2- or 4-aminoethylpiperidine, N-aminoethylpiperidine, N-aminopropylpiperidine, N-aminoethylmorpholine, N-aminopropylmorpholine, isophor-

25 onediamine, menthanediamine, 1,4-bisaminopropylpiperidine, o-, m- or p-phenylenediamine, 2,4- or 2,6-tolylenedi-

amine, 2,4-toluenediamine, m-aminobenzylamine, 4-chloro-o-phenylenediamine, tetrachloro-p-xylylenediamine, 4-

25 methoxy-6-methyl-m-phenylenediamine, m- or p-xylylenediamine, 1,5- or 2,6-naphthalenediamine, benzidine, 4,4'-bis

(o-toluidine), dianisidine, 4,4'-diaminodiphenylmethane, 2,2-(4,4'-diaminodiphenyl)propane, 4,4'-diaminodiphenyl ether, 4,4'-thiodianiline, 4,4'-diaminodiphenyl sulfone, 4,4'-diaminoditoly sulfone, methylenebis(o-chloroaniline), 3,9-bis(3-ami-

30 nopropyl)-2,4,8,10-tetraoxaspiro[5.5]undecane, diethylenetriamine, iminobispropylamine, methyliminobispropylamine, bis(hexamethylene)triamine, triethylenetetramine, tetraethylenepentamine, pentaethylenehexamine, N-aminoethyl-

35 piperidine, N-aminopropylpiperadine, 1,4-bis(aminoethylpiperadine), 1,4-bis(aminopropylpiperadine), 2,6-diaminopyri-

dine, and bis(3,4-diaminophenyl) sulfone;

secondary amines such as diethylamine, dipropylamine, di-n-butylamine, di-sec-butylamine, diisobutylamine, di-n-

30 pentylamine, di-3-pentylamine, dihexylamine, dioctylamine, di(2-ethylhexyl)amine, methylhexylamine, diallylamine, pyr-

35 rolidine, piperidine, 2-, 3- or 4-picoline, 2,4-, 2,6- or 3,5-lupetidine, diphenylamine, N-methylaniline, N-ethylaniline, diben-

40 zylamine, methylbenzylamine, dinaphthylamine, pyrrol, indoline, indole, and morpholine;

secondary polyamines such as N,N'-dimethylethylenediamine, N,N'-dimethyl-1,2-diaminopropane, N,N'-dimethyl-1,3-

45 diaminopropane, N,N'-dimethyl-1,2-diaminobutane, N,N'-dimethyl-1,3-diaminobutane, N,N'-dimethyl-1,4-diaminobu-

(2) Complexes of amines (1) and borane or boron trifluoride

(3) Phosphines

5 [0040] Trimethylphosphine, triethylphosphine, triisopropylphosphine, tri-n-butylphosphine, tri-n-hexylphosphine, tri-n-octylphosphine, tricyclohexylphosphine, triphenylphosphine, tribenzylphosphine, tris(2-methylphenyl)phosphine, tris(3-methylphenyl)phosphine, tris(4-methylphenyl)phosphine, tris(diethylamino)phosphine, tris(4-methylphenyl)phosphine, dimethylphenylphosphine, diethylphenylphosphine, dicyclohexylphenylphosphine, ethyldiphenylphosphine, diphenylcyclohexylphosphine, and chlorodiphenylphosphine.

10 (4) Quaternary ammonium salts

[0041] Tetramethylammonium chloride, tetramethylammonium bromide, tetramethylammonium acetate, tetraethylammonium chloride, tetraethylammonium bromide, tetraethylammonium acetate, tetra-n-butylammonium fluoride, tetra-n-butylammonium chloride, tetra-n-butylammonium bromide, tetra-n-butylammonium iodide, tetra-n-butylammonium acetate, tetra-n-butylammonium borohydride, tetra-n-butylammonium hexafluorophosphate, tetra-n-butylammonium hydrogensulfite, tetra-n-butylammonium tetrafluoroborate, tetra-n-butylammonium tetraphenylborate, tetra-n-butylammonium p-toluenesulfonate, tetra-n-hexylammonium chloride, tetra-n-hexylammonium bromide, tetra-n-hexylammonium acetate, tetra-n-octylammonium chloride, tetra-n-octylammonium bromide, tetra-n-octylammonium acetate, trimethyl-n-octylammonium chloride, trimethyldecylammonium chloride, trimethyldodecylammonium chloride, trimethylcetylammonium chloride, trimethyllaurylammonium chloride, trimethylbenzylammonium chloride, trimethylbenzylammonium bromide, triethyl-n-octylammonium chloride, triethylbenzylammonium chloride, triethylbenzylammonium bromide, tri-n-butyl-n-octylammonium chloride, tri-n-butylbenzylammonium fluoride, tri-n-butylbenzylammonium chloride, tri-n-butylbenzylammonium bromide, tri-n-butylbenzylammonium iodide, n-butyldimethylbenzylammonium chloride, n-octyldimethylbenzylammonium chloride, decyldimethylbenzylammonium chloride, dodecyldimethylbenzylammonium chloride, cetyltrimethylbenzylammonium chloride, lauryldimethylbenzylammonium chloride, methyltriphenylammonium chloride, methyltribenzyllammonium chloride, methyltribenzyllammonium bromide, ethyltribenzyllammonium chloride, ethyltribenzyllammonium bromide, n-butyltribenzyllammonium chloride, n-butyltribenzyllammonium bromide, n-butyltribenzyllammonium chloride, n-butyltribenzyllammonium bromide, 1-methylpyridinium chloride, 1-methylpyridinium bromide, 1-ethylpyridinium chloride, 1-ethylpyridinium bromide, 1-n-butylpyridinium chloride, 1-n-butylpyridinium bromide, 1-n-hexylpyridinium chloride, 1-n-hexylpyridinium bromide, 1-n-octylpyridinium chloride, 1-n-dodecylpyridinium chloride, 1-n-dodecylpyridinium bromide, 1-n-cetylpyridinium chloride, 1-n-cetylpyridinium bromide, 1-phenylpyridinium chloride, 1-phenylpyridinium bromide, 1-benzylpyridinium chloride, 1-benzylpyridinium bromide, 1-methylpicolinium chloride, 1-methylpicolinium bromide, 1-ethylpicolinium chloride, 1-ethylpicolinium bromide, 1-n-butylpicolinium chloride, 1-n-butylpicolinium bromide, 1-n-hexylpicolinium chloride, 1-n-hexylpicolinium bromide, 1-n-octylpicolinium chloride, 1-n-octylpicolinium bromide, 1-n-dodecylpicolinium chloride, 1-n-dodecylpicolinium bromide, 1-n-cetylpicolinium chloride, 1-n-cetylpicolinium bromide, 1-phenylpicolinium chloride, 1-phenylpicolinium bromide, 1-benzylpicolinium chloride, and 1-benzylpicolinium bromide.

40 (5) Quaternary phosphonium salts

[0042] Tetramethylphosphonium chloride, tetramethylphosphonium bromide, tetraethylphosphonium chloride, tetraethylphosphonium bromide, tetra-n-butylphosphonium chloride, tetra-n-butylphosphonium bromide, tetra-n-butylphosphonium iodide, tetra-n-hexylphosphonium bromide, tetra-n-octylphosphonium bromide, methyltriphenylphosphonium bromide, methyltriphenylphosphonium iodide, ethyltriphenylphosphonium bromide, ethyltriphenylphosphonium iodide, n-butyltriphenylphosphonium bromide, n-butyltriphenylphosphonium iodide, n-hexyltriphenylphosphonium bromide, n-octyltriphenylphosphonium bromide, tetraphenylphosphonium bromide, tetrakishydroxymethylphosphonium chloride, tetrakishydroxymethylphosphonium bromide, tetrakishydroxyethylphosphonium chloride, and tetrakishydroxybutylphosphonium chloride.

50 (6) Tertiary sulfonium salts

[0043] Trimethylsulfonium bromide, triethylsulfonium bromide, tri-n-butylsulfonium chloride, tri-n-butylsulfonium bromide, tri-n-butylsulfonium iodide, tri-n-butylsulfonium tetrafluoroborate, tri-n-hexylsulfonium bromide, tri-n-octylsulfonium bromide, triphenylsulfonium chloride, triphenylsulfonium bromide, and triphenylsulfonium iodide.

(7) Secondary iodonium salts

[0044] Diphenyliodonium chloride, diphenyliodonium bromide, and diphenyliodonium iodide.

5 (8) Mineral acids

[0045] Hydrochloric acid, sulfuric acid, nitric acid, phosphoric acid and carbonic acid, and half-esters of the mineral acids.

10 (9) Lewis acids

[0046] Boron trifluoride and boron trifluoride etherate.

15 (10) Organic acids

[0047] Organic acids and their semi esters.

(11) Silicic acid compounds and tetrafluoroboric acid compounds

20 **[0048]** Silicic acid and tetrafluoroboric acid.

(12) Peroxides

[0049] Cumyl peroxyneodecanoate, diisopropyl peroxydicarbonate, diallyl peroxydicarbonate, di-n-propyl peroxydicarbonate, dimyristyl peroxydicarbonate, cumyl peroxyneohexanoate, t-hexyl peroxyneodecanoate, t-butyl peroxyneodecanoate, t-hexyl peroxyneohexanoate, t-butyl peroxyneohexanoate, 2,4-dichlorobenzoyl peroxide, benzoyl peroxide, dicumyl peroxide, di-t-butyl peroxide, cumene hydroperoxide, and tert-butyl hydroperoxide.

30 (13) Azo compounds

[0050] 2,2'-Azobis(4-methoxy-2,4-dimethylvaleronitrile), 2,2'-azobis(2-cyclopropylpropionitrile), 2,2'-azobis(2,4-dimethylvaleronitrile), 2,2'-azobisisobutylonitrile, 2,2'-azobis(2-methylbutylonitrile), 1,1'-azobis(cyclohexane-1-carbonitrile), 1-[(1-cyano-1-methyl)azo]formamide, 2-pnaylazo-4-methoxy-2,4-dimethylvaleronitrile, 2,2'-azobis(2-methylpropane), and 2,2'-azobis(2,4,4-trimethylpentane). (14) Condensates of aldehyde and ammonia compound

35 **[0051]** Reaction product of acetaldehyde and ammonia, condensate of formaldehyde and p-toluidine, condensate of acetaldehyde and p-toluidine, reaction product of formaldehyde and aniline, reaction product of acetaldehyde and aniline, reaction product of butylaldehyde and aniline, reaction product of formaldehyde, acetaldehyde and aniline, reaction product of acetaldehyde, butylaldehyde and aniline, condensate of butylaldehyde and monobutylamine, reaction product of butylaldehyde and butyldeneaniline, reaction product of heptaldehyde and aniline, reaction product of trichlotonylidenetetramine, condensate of α -ethyl- β -propylacrolein and aniline, and condensate of formaldehyde and alkylimidazole.

40 (15) Guanidine compounds

[0052] Diphenylguanidine, phenyltolylguanidine, phenylxylylguanidine, tolylxylylguanidine, di-o-tolylguanidine, o-tolylguanide, diphenylguanidine phthalate, tetramethylguanidine, and di-o-tolylguanidine salt of dicatechol boric acid.

(16) Thiourea compounds

[0053] Thiocarbonilide, di-o-tolylthiourea, ethylenethiourea, diethylthiourea, dibutylthiourea, dilaurylthiourea, trimethylthiourea, dimethylethylthiourea, and tetramethylthiourea.

(17) Thiazole compounds

[0054] 2-Mercaptobenzothiazole, dibenzothiazyl disulfide, cyclohexylamine salt of 2-mercaptobenzothiazole, 2-(2,4-dinitrophenylthio)benzothiazole, 2-(morpholinodithio)benzothiazole, 2-(2,6-dimethyl-4-morpholinothio)benzothiazole, N,N-diethylthiocarbamoyl-2-benzothiazolyl disulfide, 1,3-bis(2-benzothiazolylmercaptomethyl)urea, benzothiadiazylthio benzoate, 2-mercaptopthiazoline, sodium salt of 2-mercaptobenzothiazole, zinc salt of 2-mercaptobenzothiazole, and complex of dibenzothiazyl disulfide and zinc chloride.

(18) Sulfenamide compounds

[0055] N-cyclohexyl-2-benzothiazyl sulfenamide, N-t-butyl-2-benzothiazyl sulfenamide, N-t-octyl-2-benzothiazyl sulfenamide, N-oxydiethylene-2-benzothiazyl sulfenamide, N,N-diethyl-2-benzothiazyl sulfenamide, N,N-diisopropyl-2-benzothiazyl sulfenamide, and N,N-dicyclohexyl-2-benzothiazyl sulfenamide.

(19) Thiuram compounds

[0056] Tetramethylthiuram monosulfide, tetraethylthiuram monosulfide, tetrabutylthiuram monosulfide, dipentamethylenethiuram monosulfide, tetramethylthiuram disulfide, tetraethylthiuram disulfide, tetrabutylthiuram disulfide, N,N'-dimethyl-N,N'-diphenylthiuram disulfide, N,N'-diethyl-N,N'-diphenylthiuram disulfide, dipentamethylenethiuram disulfide, dipentamethylenethiuram tetrasulfide, and cyclic thiuram.

(20) Salts of dithiocarbamic acid

[0057] Sodium dimethyldithiocarbamate, sodium diethyldithiocarbamate, sodium dibutyldithiocarbamate, sodium pentamethylenedithiocarbamate, sodium cyclohexylethyldithiocarbamate, potassium dimethyldithiocarbamate, lead dimethyldithiocarbamate, zinc dimethyldithiocarbamate, zinc diethyldithiocarbamate, zinc dibutyldithiocarbamate, zinc dibenzylidithiocarbamate, zinc pentamethylenedithiocarbamate, zinc dimethylpentamethylenedithiocarbamate, zinc ethylphenyldithiocarbamate, bismuth dimethyldithiocarbamate, cadmium diethyldithiocarbamate, cadmium pentamethylenedithiocarbamate, selenium dimethyldithiocarbamate, selenium diethyldithiocarbamate, tellurium dimethyldithiocarbamate, tellurium diethyldithiocarbamate, iron dimethyldithiocarbamate, copper dimethyldithiocarbamate, diethylammonium diethyldithiocarbamate, N,N-dicyclohexylammonium dibutyldithiocarbamate, piperidinium pentamethylenedithiocarbamate, cyclohexylethylammonium sodium cyclohexylethyldithiocarbamate, pipecolinium methylpentamethylenedithiocarbamate, and complex of zinc pentamethylenedithiocarbamate and piperidine.

(21) Salts of xanthogenic acid

[0058] Sodium isopropylxanthate, zinc isopropylxanthate, zinc butylxanthate, and disulfide dibutylxanthate.

(22) Esters of acid phosphoric acid

[0059] Mono- or dimethyl phosphate, mono- or diethyl phosphate, mono- or dipropyl phosphate, mono- or dibutyl phosphate, mono- or dihexyl phosphate, mono- or dioctyl phosphate, mono- or didecyl phosphate, mono- or didodecyl phosphate, mono- or diphenyl phosphate, mono- or dibenzyl phosphate, and mono- or didecanol phosphate.

[0060] The polymerization catalysts recited above are only illustrative and not limited thereto as long as a compound is effective for curing the composition by polymerization. These catalysts may be used alone or in combination of two or more. The addition amount of the catalyst is 0.0001 to 10.0 parts by weight, preferably 0.0005 to 5.0 parts by weight based on 100 parts by weight of the composition for optical materials (the alicyclic compound and the optional reactive compound and additive compound).

[0061] To improve the practical properties of the optical materials of the present invention, the composition may be cured by polymerization in the presence of a known additive such as antioxidants and ultraviolet light absorbers. It is effective to improve the adhesion or the releasability between the cured materials and a mold by adding a known external and/or internal adhesion improver if the cured material is easy to separate from the mold during polymerization, or by adding a known external or internal mold release improver if the cured material is difficult to release from the mold after polymerization.

[0062] After uniformly blended with the catalyst, the adhesion or mold release improver, the additive such as antioxidants, bluing agents, ultraviolet absorbers, and property improvers, the alicyclic compound alone or a composition comprising it is cast into a mold made of glass or metal, heated to allow the curing by polymerization to proceed, and then released from the mold to obtain the optical materials of the present invention.

[0063] Before casting into the mold, the alicyclic compound alone or a composition comprising it may be pre-polymerized partly or completely in the presence or absence of a catalyst with or without stirring at -100 to 160°C for 0.1 to 480 h. Then, the optical materials are produced by following the casting into a mold and the curing by polymerization. The pre-polymerization is effective, in particular, if the composition for optical materials includes a solid component and is not easy to handle. The pre-polymerization is performed preferably at -10 to 120°C for 0.1 to 240 h, more preferably at 0 to 100°C for 0.1 to 120 h.

[0064] As described above, a composition prepared by blending the main starting material and the secondary starting material is cast into a mold and cured therein by polymerization to provide the optical materials of the present invention.

The alicyclic compound, the reactive compound, the additive compound, the catalyst and the additive such as adhesion improvers, mold release improvers, antioxidants, bluing agents, ultraviolet absorbers and property improvers may be blended under stirring in a single container simultaneously or stepwise. Alternatively, a few of the starting materials are blended in separate containers and then blended together in the same container. The order of adding the starting materials and additives is not specifically limited. The mixing temperature and time are not critical as long as the materials are sufficiently mixed. An excessively high temperature and an excessively long mixing time unfavorably make the casting operation difficult because undesirable reaction between the materials and additives is induced to increase the viscosity. The mixing temperature is about -50 to 100°C, preferably -30 to 70°C, more preferably -5 to 50°C. The mixing time is 1 min to 12 h, preferably 5 min to 10 h, more preferably 5 min to 6 h. The degasification under reduced pressure prior to the mixing, during the mixing or after the mixing of the materials and additives is preferred to prevent the generation of bubbles during the subsequent casting step and curing step by polymerization. The degree of evacuation is about 0.1 to 700 mmHg, preferably 0.5 to 300 mmHg. To increase the quality of the optical materials of the invention, it is preferred to remove impurities by filtering the materials or additives, before or after mixing, through a filter having a pore size of about 0.05 to 3 µm. After casting the starting mixture into a glass or metal mold, the curing by polymerization is conducted using an electric furnace, a water bath or an oil bath. The curing time is 0.1 to 100 h, preferably 1 to 72 h. The curing temperature is -10 to 160°C, preferably 0 to 140°C. The polymerization is carried out by keeping the starting mixture at a given polymerization temperature for a given period of time while raising the temperature at 0.1 to 100°C/h, lowering the temperature at 0.1 to 100°C/h or using a combination thereof. After curing, it is preferred to anneal the optical material at 50 to 150°C for 10 min to 5 h because the strain of the optical material can be removed. The optical material may be further subjected to surface treatment for improving dyeability, providing hard coating and imparting non-reflection, non-fogging or impact resistance properties.

[0065] The present invention will be described in more detail by reference to the following examples which should not be construed to limit the scope of the invention thereto. The refractive index (Nd) and Abbe's number (vd) of the lenses were measured at 25°C using Abbe refractometer.


25

SYNTHESIS EXAMPLE 1

[0066] Into a reaction flask equipped with a thermometer and a calcium chloride drying tube, 381.4 g (2.0 mol) of toluenethiosulfenyl chloride and 1000 mL of chloroform were charged and cooled to -80°C. Stirring vigorously, a solution of 116.2 g (1.0 mol) of 1,4-dithiane-2,5-diene in 500 mL of chloroform was added dropwise. 1,4-Dithiane-2,5-diene was prepared by the method described in J. Am. Chem. Soc., 75, 2065 (1953). After the addition, the reaction was allowed to proceed at room temperature for 30 min. After adding a solution of 74.1 g (0.95 mol) of sodium sulfide in 500 mL of methanol, the reaction was allowed to further proceed at 50°C for one hour. The reaction product was added with 1000 mL of water and 1000 mL of chloroform to collect the lower chloroform layer, followed by drying and evaporation. The residue was purified by distillation and silica gel column chromatography to obtain 45.2 g of the product.

[0067] The product was identified as 1,2:4,5-diepitio-3,6-dithiacyclohexane represented by the following formula 3:

40



45

50 by elemental analysis, mass spectrometry and IR spectrometry.

Elemental Analysis

55

	Found	Calculated
C	26.44%	26.64%
H	2.41%	2.24%
S	71.01%	71.12%

Mass Spectrum (EI)

Found	Calculated
180	180

5


Infrared Absorption Spectrum
 620-630 cm⁻¹ (stretching vibration of epithioethylene linkage)

10 EXAMPLE 1

[0068] 1,2:4,5-Diepitio-3,6-dithiacyclohexane (100 parts by weight) prepared in Synthesis Example 1 and 0.02 part by weight of N-methylimidazole (catalyst) were mixed to a uniform liquid, which was then filtered through a PTFE filter (0.5 µm pore size), cast into a mold for flat lens of 2.5 mm thick, and cured by polymerization in an oven by raising the temperature from 10°C to 120°C over 22 h to produce a lens. The obtained lens was excellent in heat resistance and physical properties, and showed an excellent transparency and surface condition. The refractive index was 1.78 and the Abbe's number was 30.

20 COMPARATIVE EXAMPLE 1

[0069] The procedure of Example 1 was repeated except for using 100 parts by weight of 1,2:6,7-diepitio-4-thiaheptane represented by the following formula 4:



30 in place of 1,2:4,5-diepitio-3,6-dithiacyclohexane. The obtained lens had a refractive index of 1.71 and an Abbe's number of 36.

Industrial Applicability

35 [0070] The alicyclic compound of the present invention alone or a composition for optical materials containing it is cured by polymerization to provide optical materials having a higher refractive index.

40 Claims

1. An alicyclic compound of five- or more membered ring structure, having two or more epithioethylene linkages and/or epidithioethylene linkages in its ring structure and two or more sulfur atoms in its molecule, which alicyclic compound is selected from the group consisting of 1,2:4,5-diepitio-3-thiacyclohexane, 1,2:4,5-diepitio-3,6-dithiacyclohexane, 1,2:4,5-diepidithio-3,6-dithiacyclohexane, 1,2:4,5-diepitio-3,6,7-trithiacycloheptane, 1,2:5,6-diepitio-3,4,7,8-tetrathiacyclooctane, 1,2:5,6-diepidithio-3,4,7,8-tetrathiacyclooctane, 1,2:1,4:4,5-triepitio-3,6-dithiacyclohexane, 1,2:1,4:2,5:4,5-tetra-epithio-3,6-dithiacyclohexane, and 1,2:1,4:2,5:4,5-tetraepidithio-3,6-dithiacyclohexane.
2. A composition for optical materials comprising the alicyclic compound as defined in Claim 1.
3. The composition for optical materials according to Claim 2, wherein the content of the alicyclic compound is 5 to 100% by weight based on the total amount of the compound for optical materials.
4. The composition for optical materials according to Claim 2 or 3, further comprising a compound capable of reacting with the alicyclic compound.
5. The composition for optical materials according to Claim 4, wherein the compound capable of reacting with the

5 alicyclic compound is an episulfide compound having an epithioethyl group and/or an epidithioethyl group.

6. The composition for optical materials according to Claim 5, wherein the content of the episulfide compound is 1 to
95 parts by weight based on 100 parts by weight of the alicyclic compound.
7. A method for producing optical materials, comprising a step of curing the alicyclic compound as defined in Claim 1
by polymerization.
8. A method for producing optical materials, comprising a step of curing the composition for optical materials as defined
in any one of Claims 2 to 6 by polymerization.
9. An optical material produced by the method according to Claim 7 or 8.
10. A lens comprising the optical material according to Claim 9.

15 Patentansprüche

1. Eine alicyclische Verbindung mit 5- oder mehrgliedriger Ringstruktur, welche zwei oder mehr Epithioethylen-Bin-
dungen und/oder Epidithioethylen-Bindungen in der Ringstruktur und zwei oder mehr Schwefelatome im Molekül
aufweist,
wobei die alicyclische Verbindung ausgewählt wird aus der Gruppe, die besteht aus 1,2:4,5-Diepithio-3-thiacyclo-
hexan, 1,2:4,5-Diepithio-3,6-dithiacyclohexan, 1,2:4,5-Diepithio-3,6-dithiacyclohexan, 1,2:4,5-Diepithio-3,6,7-tri-
thiacycloheptan, 1,2:5,6-Diepithio-3,4,7,8-tetrathiacyclooctan, 1,2:5,6-Diepithio-3,4,7,8-tetrathiacyclooctan, 1,2:
1,4:4,5-Triepithio-3,b-dithiacyclohexan, 1,2:1,4:2,5:4,5-Tetra-epithio-3,6-dithiacyclohexan, und 1,2:1,4:2,5:4,5-Tet-
raepidithio-3,6-dithiacyclohexan.
2. Zusammensetzung für optische Materialien, umfassend die alicyclische Verbindung, wie in Anspruch 1 definiert.
3. Zusammensetzung für optische Materialien nach Anspruch 2, wobei der Gehalt der alicyclischen Verbindung 5 bis
100 Gew.-%, bezogen auf die Gesamtmenge der Verbindung für optische Materialien, beträgt.
4. Zusammensetzung für optische Materialien nach Anspruch 2 oder 3, darüber hinaus umfassend eine Verbindung,
die dazu fähig ist, mit der alicyclischen Verbindung zu reagieren.
5. Zusammensetzung für optische Materialien nach Anspruch 4, wobei die Verbindung, die zur Reaktion mit der ali-
cyclischen Verbindung fähig ist, eine Episulfidverbindung ist, welche eine Epithioethylgruppe und/oder eine Epi-
dithioethylgruppe aufweist.
6. Zusammensetzung für optische Materialien nach Anspruch 5, wobei der Gehalt der Episulfidverbindung 1 bis 95
Gew.-Teile, bezogen auf 100 Gew.-Teile der alicyclischen Verbindung, beträgt.
7. Verfahren zur Herstellung von optischen Materialien, umfassend einen Schritt des Härtens der alicyclischen Ver-
bindung, wie in Anspruch 1 definiert, durch Polymerisation.
8. Verfahren zur Herstellung von optischen Materialien, umfassend einen Schritt der Härtung der Zusammensetzung
für optische Materialien, wie in einem der Ansprüche 2 bis 6 definiert, durch Polymerisation.
9. Optisches Material, hergestellt durch das Verfahren nach Anspruch 7 oder 8.
10. Linse, umfassend das optische Material nach Anspruch 9.

55 Revendications

1. Composé alicyclique de structure cyclique à cinq chaînons ou plus, comportant deux liaisons épithioéthylène et/ou
liaisons epidithioéthylène ou plus dans sa structure de cycle et deux atomes de soufre ou plus dans sa molécule,
lequel composé alicyclique est choisi dans le groupe consistant en le 1,2:4,5-diépithio-3-thiacyclohexane, 1,2:4,5-

diépithio-3,6-dithiacyclohexane, le 1,2:4,5-diépidithio-3,6-dithiacyclohexane, le 1,2:4,5-diépithio-3,6,7-trithiacycloheptane, le 1,2:5,6-diépithio-3,4,7,8-tétrathiacyclooctane, le 1,2:5,6-diépidithio-3,4,7,8-tétrathiacyclooctane, le 1,2:1,4:4,5-triépithio-3,6-dithiacyclohexane, le 1,2:1,4:2,5:4,5-tétra-épithio-3,6-dithiacyclohexane, et le 1,2:1,4:2,5:4,5-tétraépidithio-3,6-dithiacyclohexane.

- 5 2. Composition pour matériaux optiques comprenant le composé alicyclique tel que défini dans la revendication 1.
- 10 3. Composition pour matériaux optiques selon la revendication 2, dans laquelle la teneur du composé alicyclique est de 5 à 100 % en poids par rapport à la quantité totale du composé pour matériaux optiques.
- 15 4. Composition pour matériaux optiques selon la revendication 2 ou 3, comprenant en outre un composé capable de réagir avec le composé alicyclique.
- 20 5. Composition pour matériaux optiques selon la revendication 4, dans laquelle le composé capable de réagir avec le composé alicyclique est un composé épisulfure comportant un groupe épithioéthyle et/ou un groupe épidithioéthyle.
- 25 6. Composition pour matériaux optiques selon la revendication 5, dans laquelle la teneur en composé épisulfure est de 1 à 95 parties en poids pour 100 parties en poids du composé alicyclique.
- 30 7. Procédé de production de matériaux optiques, comprenant une étape de cuisson du composé alicyclique tel que défini dans la revendication 1 par polymérisation.
- 35 8. Procédé de production de matériaux optiques, comprenant une étape de cuisson de la composition pour matériaux optiques telle que définie dans l'une quelconque des revendications 2 à 6 par polymérisation.
- 40 9. Matériau optique produit par le procédé selon les revendications 7 ou 8.
- 45 10. Lentille comprenant le matériau optique selon la revendication 9.

30

35

40

45

50

55

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- JP 9110979 A [0002]
- JP 9071580 A [0002]
- JP 9255781 A [0002]
- JP 11140046 A [0002]

Non-patent literature cited in the description

- *J. Am. Chem. Soc.*, 1953, vol. 75, 2065 [0066]