

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
15 March 2001 (15.03.2001)

PCT


(10) International Publication Number  
**WO 01/18147 A1**

- (51) International Patent Classification: **C09K 7/02**, E21B 43/25, 43/26 (74) Agent: **MA, Shirley, S.**; Crompton Corporation, 199 Benson Road, Middlebury, CT 06749 (US).
- (21) International Application Number: PCT/US00/24142 (81) Designated States (*national*): AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (22) International Filing Date: 1 September 2000 (01.09.2000) (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data: 60/152,662 7 September 1999 (07.09.1999) US
- (71) Applicant (*for all designated States except US*): **CROMPTON CORPORATION** [US/US]; 199 Benson Road, Middlebury, CT 06749 (US).

- (72) Inventors; and  
(75) Inventors/Applicants (*for US only*): **SUBRAMANIAN, Shankar** [IN/US]; 5725 Killiney Lane, Dublin, OH 43016 (US). **ISLAM, Mojahedul** [GB/US]; 65 Chenango Drive, Powell, OH 43065 (US). **BURGAZLI, Cent, R.** [US/US]; Country Road 24, Cardungton, OH 43315 (US).

**Published:**  
— *With international search report.*

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*



**WO 01/18147 A1**

(54) Title: QUATERNARY AMMONIUM SALTS AS THICKENING AGENTS FOR AQUEOUS SYSTEMS

(57) Abstract: This invention relates to the use of alkyl amido quaternary ammonium salts, and formulations thereof, as thickening agents in aqueous based fluids, especially those used in oil field applications. The quaternary ammonium salts of the present invention exhibit improved gelling characteristics.

## QUATERNARY AMMONIUM SALTS AS THICKENING AGENTS FOR AQUEOUS SYSTEMS

### FIELD OF THE INVENTION

5                   This invention relates to the use of alkyl amido quaternary ammonium salts, and formulations thereof, as thickening agents in aqueous based fluids, especially those used in oil field applications. In particular, the compositions of the present invention find use as gelants in fluids used in oil recovery operations such as fracturing fluids, completion fluids, and drilling fluids, that are used in the process of recovering  
10 hydrocarbons from subterranean formations. The quaternary ammonium salts of the present invention exhibit improved gelling characteristics.

### BACKGROUND OF THE INVENTION

                  Hydraulic fracturing is used to stimulate the production of hydrocarbons  
15 such as oil or natural gas from subterranean formations. In this process, a fracturing fluid is injected through a wellbore and propelled against the formation strata by high pressure sufficient to cause the strata to crack and fracture.

                  The fracturing fluid also carries what is referred to as a proppant to the fracture site. These proppant particles remain in the fracture thereby "propping" the  
20 fracture open when the well is in production. The proppant material is commonly sand, sintered bauxite, glass balls, polystyrene beads, and so forth.

                  Traditional fracturing fluids were polymer based fluids. Naturally occurring polysaccharides such as guar and derivatized guar, upon dissolution in water, form hydrated polymers which can be crosslinked with organometallic compounds such as  
25 borates, zirconates or titanates to form a crosslinked gel structure which increases the viscosity of the fluid. However, these crosslinked polymers can ultimately form a rubbery semi-solid material that is difficult to recover from the fracture causing reduction in the conductivity of the fracture. Peroxides and other gel breakers are therefore often utilized to break the gelled polymeric structure into smaller molecules and facilitate clean-up of  
30 the fracture site. Production of oil or gas is often dependent on the ability to clean the

fracture site of such materials.

It is a widely known concept to use certain chemical agents to increase the viscosity or induce gel formation in aqueous or hydrocarbon based fluids. These gelled or thickened fluids may be referred to as viscoelastic fluids. The term viscoelastic is commonly understood to refer to a fluid that has the capability to partially return to its original non-disturbed form upon release of applied stress. It is believed that under the right conditions, i.e. concentration, counter ion, pH and so forth, that certain surfactants from rod-like or cylindrical micelles which can entangle to form these gelatinous, viscoelastic fluids in aqueous solutions.

These thickened fluids are then capable of suspending the proppant particles and carrying them to the fracture site. These gelled fluids also diminish loss of fluid into the fracture face, thereby improving the efficiency in the fracturing process and reducing the overall cost.

Viscoelastic fluids can be formed with a combination of ionic and/or non-ionic surfactants and by the incorporation of additives such as organic and/or inorganic salts. U.S. Patent No. 5,551,516 issued Sept. 3, 1996 to Norman et al. describe surfactant based viscoelastic aqueous fluid systems useful in fracturing subterranean formations penetrated by a wellbore, and state that the fracturing fluids are useful in high temperature, high permeability formations. Norman et al. state that the preferred thickening agents are quaternary ammonium halide salts derived from certain waxes, fats and oils. The thickening agent is used in conjunction with an inorganic water soluble salt, an organic stabilizing additive selected from the group of organic salts such as sodium salicylate. The fluids are said to be stable to a temperature of 225° F.

Various problems have been encountered with these gelled fluids in oil field applications including the lack of thermal stability of the fracturing fluids caused by the degradation of the additives or the instability of the gel upon exposure to high temperatures and/or high shear conditions. This can result in changes in the rheological properties of the gel which can ultimately affect the ability of the fluid to suspend proppant material. If proppant material is prematurely lost from the fracturing fluid it can have a detrimental effect on the fracturing treatment. Furthermore, gel instability can


result in higher loss of fluid into the formation thereby diminishing the amount of fracturing that occurs. High temperatures in the formation can further impact gel stability.

For high brine solutions, i.e. those having salt concentrations of about 30 wt-% or more, polymeric materials have been used as thickeners but tend to precipitate from these high salt concentration solutions which can result in plugging and formation damage. Furthermore, the high salt concentration makes it difficult to dissolve these polymeric viscosifiers or thickeners in the solutions. Such high brine solutions are found in completion fluids used in drilling operations.

## 10 SUMMARY OF THE INVENTION

The present invention relates to improved gelling agents for use in oil field applications. In particular, the compositions find use in fracturing fluids, completion fluids and well drilling fluids.

The gelling agents of the present invention are cationic in nature and have the following general structure:



20

R<sup>1</sup> is alkyl amine alkylene, alkyl amido alkylene, alkyl ester alkylene where the alkyl group contains 1-26 carbon atoms and the alkylene group preferably contains 1 to 8 carbon atoms; R<sup>2</sup> and R<sup>3</sup> are each alkyl, hydroxy alkyl, polyalkoxy with the degree of polymerization ranging from 2-30, alkyl sulfonate, hydroxyalkyl sulfonate or alkylaryl sulfonate; R<sup>4</sup> is hydrocarbon such as alkyl, aryl, aralkyl, or alkaryl and can be saturated or unsaturated; or wherein any two or R<sup>2</sup>, R<sup>3</sup> and R<sup>4</sup> together with the nitrogen atom to which they are attached, form a heterocyclic ring; and X is selected from the group

consisting of halides; oxo ions of phosphorous, sulfur or chloride; and various organic anionic molecules.

The surfactants of the present invention, in combination with at least one additive which may be an inorganic salt, organic salt, organic acid, alcohol or a mixture  
5 thereof, form stable gels in aqueous environments.

The present invention further relates to a method of fracturing a subterranean formation comprising the steps of providing a thickened fracturing fluid as described above, and injecting the aqueous fracturing fluid through a wellbore and against a subterranean formation at a pressure sufficient to initiate and or extend a fracture into  
10 the formation.

The present invention further relates to a method of suspending particles in a thickened aqueous liquid by providing an aqueous medium and adding to the aqueous medium an effective amount of at least one surfactant and at least one counterion selected from the group consisting of organic salts, inorganic salts, organic acids, alcohols, and  
15 mixtures thereof, sufficient to increase the viscosity of said aqueous medium. The surfactant has the general structure as provided above. The thickened aqueous fluid is capable of suspending solid particulate matter. The thickened fluid may then be further used to transport the solid particulate matter to a remote location.

This type of method is useful in well-drilling operations, coil-tubing  
20 operations, construction operations, mining operations, and so forth, where it is desirable to remove solid matter from the site of operation.

The present invention further relates to a method of reducing the friction of an aqueous liquid as it passes through a conduit by adding to the aqueous liquid, at least one surfactant of the present invention, and at least one additive which is an  
25 inorganic salt, organic salt, organic acid, an alcohol, or a mixture thereof. The amount of surfactant and additive added to the aqueous liquid are sufficient to reduce the friction of the aqueous liquid as it passes through the conduit.

The present invention further relates to an oil field high brine oil completion fluid comprising about 30 wt-% to about 70 wt-% of at least one inorganic or  
30 organic salt and about 0.1 wt-% to about 4 wt-% of at least one cationic surfactant having

the following general structure:



10 wherein R<sup>1</sup> is alkyl amine alkylene or alkyl amido alkylene; R<sup>2</sup> and R<sup>3</sup> are each alkyl, hydroxy alkyl, polyalkoxy with the degree of polymerization ranging from 2 to 30, hydroxyl alkyl sulfonate, alkyl sulfonate or alkylarylsulfonate; R<sup>4</sup> is hydrocarbon, saturated or unsaturated; or wherein any two of R<sup>2</sup>, R<sup>3</sup> and R<sup>4</sup>, together with the nitrogen atom to which they are attached, form a heterocyclic ring; and X is selected from the group consisting of halides; oxo ions of  
15 phosphorous, sulfur or chloride; and organic anions.

A counterion, i.e. an inorganic salt, organic salt, inorganic acid, alcohol, or mixture thereof, is optional in the case of the high brine completion fluid.


20 These compositions have been found to provide a reversible thickening phenomenon whereby with increasing temperature, the viscosity increases. However, when the heat source is removed, and the temperature drops, the viscosity will again decrease.

#### DETAILED DESCRIPTIONS OF THE PREFERRED EMBODIMENTS

25 The monomeric surfactants of the present invention in the presence of organic or inorganic activators or gel promoters, can be used as thickening agents in aqueous based systems.

The surfactant ions of the present invention are preferably cationic and have the following general structure:

30



(I)

5

where R<sup>1</sup> is alkyl amine alkylene, alkyl amido alkylene, alkyl ether alkylene or alkyl ester alkylene where the alkyl group contains 1-26 carbon atoms and the alkylene group  
 10 preferably contains 1 to 8 carbon atoms; R<sup>2</sup> and R<sup>3</sup> are each alkyl, hydroxy alkyl, polyalkoxy with the degree of polymerization ranging from 2-30, alkyl sulfonate, hydroxyalkyl sulfonate or alkylaryl sulfonate; R<sup>4</sup> is hydrocarbon such as alkyl, aryl, aralkyl, alkaryl and can be saturated or unsaturated; or wherein any two of R<sup>2</sup>, R<sup>3</sup> and R<sup>4</sup>,  
 15 together with the nitrogen atom to which they are attached, form a heterocyclic ring containing 2 to 5 carbon atoms and 1 to 6 sulfur atoms such as sulfur (S), nitrogen (N), oxygen (O) or silicon (Si); and X is selected from the group consisting of halides; oxo ions of phosphorous, sulfur or chloride; and various organic molecules.

In some preferred embodiments of the present invention, R<sup>1</sup> is alkyl amine alkylene or alkyl amido alkylene, and/or R<sup>2</sup> and R<sup>3</sup> are each alkyl or hydroxy alkyl.

20 Examples of suitable alkyl groups, R<sup>2</sup>, R<sup>3</sup> or R<sup>4</sup> include methyl, ethyl, propyl, butyl, hexyl, allyl, benzyl, vinyl benzyl, and the like, including *iso*-propyl, *iso*-butyl, *sec*-butyl, *tert*-butyl, and so forth. Examples of suitable hydroxy alkyl groups include 2-hydroxyethyl-2-hydroxypropyl and 2,3-dihydroxypropyl. Examples of heterocyclic rings which may be formed by combination of two of R<sup>2</sup>, R<sup>3</sup> and R<sup>4</sup> include  
 25 morpholine, piperidine, piperazine, and so forth. Polyalkoxy groups are preferably ethyl, propyl or butyl.


Alkyl sulfonate may also be referred to as sulfobetaines and hydroxyalkyl sulfonates may also be referred to as sultaines. An example of a sulfobetaine is propyl sulfonate and an example of a sultaine is 2-hydroxypropyl sulfonate.

30 The thickening agent is employed in an amount which in combination with

the other ingredients is sufficient to increase the viscosity of the aqueous fluid enough to maintain proppant in suspension during fluid placement.

Preferably, the surfactants of the present invention are alkyl amidoalkyltrialkyl ammonium quaternary salts and have the following general structure:

5




10

$R^2$  and  $R^3$  are alkyl and preferably have from 1 to 8 carbon atoms; hydroxy alkyl preferably having from 1 to 8 carbon atoms; polyalkoxy including ethyl, propyl and butyl with the degree of polymerization ranging from 2 to 30; hydroxyalkyl sulfonate, i.e. sultaine; alkyl sulfonate, i.e. sulfobetaine; alkylarylsulfonate;  $R_4$  is hydrocarbon and can be alkyl, aryl, aralkyl, alkaryl, saturated or unsaturated; or wherein any of  $R^2$ ,  $R^3$  and  $R^4$ , together with the nitrogen atom to which they are attached, form a heterocyclic ring containing 2-5 carbon atoms and 1-6 hetero atoms such as sulfur (S), nitrogen (N), oxygen (O), and silicon (Si); R is a saturated or unsaturated alkyl having from 1 to 30 carbon atoms, preferably from about 6 to 26 carbon atoms and most preferably from about 12 to 22 carbon atoms; y is an integer from 0 to 12, and preferably from 1 to 12; and X is defined above. Suitable R groups include coco, palmityl, stearyl, oleyl, erucyl, as well as other saturated or unsaturated moieties. As a general rule, although other factors affect stability as well, the higher the number of carbon atoms in R, the better the stability of the resultant gel.

25

In a specific preferred embodiment y is 1 and X is chloride, and the surfactant is an alkylamidopropyltrialkyl ammonium quaternary chloride having the following general structure:






where R is erucyl (22 carbon unsaturated fatty acid chain); R<sup>2</sup>, R<sup>3</sup>, and R<sup>4</sup> are methyl; and X is preferably chloride.

10                    These types of compounds are obtained by quaternization of a corresponding alkylamidopropyltrimethylamide with methylene chloride, ethyl chloride, benzyl chloride, vinyl chloride, butyl chloride, methyl sulfate, chlorohydroxyalkylsulfonate, chloroalkylsulfonates and so forth, and mixtures thereof.

The long chain alkyl groups, R, are hydrophobic in nature and are  
 15 generally derived from a fatty acid. The fatty carboxylic acid is reacted with an amine to form the amide. These long chain alkyl groups are generally derived from the fatty acids and include cetyl, oleyl, stearyl, erucyl, and the derivatives of tallow, coco, soya and rapeseed oils.

In a preferred embodiment of the present invention, the quaternary  
 20 ammonium salt is erucyl amidopropyltrimethyl ammonium quaternary salt.

In another embodiment, the surfactant is an amidopropylmorpholine quaternary salt having the following general structure:




R and X are defined as above.

30                    One specific surfactant of this particular structure is


isosterylamidopropylmorpholine lactate.

Examples of other useful quaternary salts generally include the following structures:


5



10




15




20

R, R<sup>2</sup>, R<sup>3</sup>, R<sup>4</sup> and X are as defined above. Preferably, R has about 6 to about 26 carbons and most preferably R has about 12 to 24 carbon atoms. As stated above, it has been found to be a general rule that R groups having a higher number of carbon atoms, result in a gel having better thermal stability. A specific example of structure VII, above, is dimethylalkylglycerolammonium chloride.


5




10



15



20



25

Where R, R<sup>2</sup>, R<sup>3</sup> and R<sup>4</sup> are defined as above.

X may be halides; oxo ions of phosphorous, sulfur or chloride; and various organic anions, including chlorides, bromides, iodides, oxides of phosphorous, hypochlorides, phosphates, phosphites, oxides of sulfur, sulfates, sulfites, sulfonates, phosphates, acetates, carboxylates, chlorates, perchlorates, salicylates, phthalates,

lactates, maleates, glycinates, citrates, citric acid, lactic acid, salicylic acid, phthalic acid, benzoic acid, naphthoic acid, amino acids, and so forth.

The concentration of the surfactant is preferably from about 0.05% to about 10% by weight of the fluid, more preferably from about 0.05% to about 6%, even  
5 more preferably from about 0.1% to about 5%, even more preferably from about 0.2% to about 4% and most preferably from about 0.5% to about 4%.

The surfactants of the present invention are rheologically stable up to temperatures of about 300° F (about 149° C). In some specific embodiments, the surfactants are stable up to temperatures of about 110° C or 225° F, to about 275° F  
10 (about 135° C). It is important to note, however, that the gels can be used at low temperatures, i.e. 25° C, as well as in the operations where the temperature is high.

The gelation is assisted by the presence of an activator or gel promoter. These are often referred to in the art as counterions or additives. An organic acid, a salt, either organic or inorganic, an alcohol, or any combination thereof, may be added as an  
15 activator or gel promoter so as to increase the viscosity of the fluid or in the development of the gel. Such additives can also aid in maintaining the stability of the geologic formation to which the fluid is exposed. The use of such compounds to improve the thickening characteristics of the fluid, are known to one of skill in the art. The compounds are chosen such that the thickening agent is compatible with the electrolyte to  
20 avoid the formation of undesirable precipitates. While some gelants, such as the sultaines or sulfobetaines, have been found to thicken or gel the aqueous fluids without the presence of the counterions, the gel stability has been found to be poor.

The organic salts useful herein are typically water soluble compounds involving a metal or an amine salt of an organic anion. Organic anions include salicylates,  
25 phthalates, naphthalates, sulfates, sulfonates, lactates, glycinates, citrates, carboxylates, benzoates, chlorobenzoates, phenates, acetates, sulfobetaines, hydroxysultaines, and so forth. Preferably, sulfates and sulfonates are used in the present invention, and in particular, those having aromatic groups such as xylene or toluene are preferred. Specific examples include xylene sulfonate, *p*-toluene sulfonate, naphthalene sulfonate,  
30 hydroxynaphthalene sulfonate, ethoxylauryl sulfate, methyl sulfate, ethyl sulfate, and so

forth.

The organic acids useful herein include citric acids, lactic acids, salicylic acids, sulfonic acids, carboxylic acids, salicylic acids, benzoic acids, phthalic acids, naphthoic acids, and so forth. Specific examples include 3-hydroxy 2-naphthoic acid, 5-  
5 hydroxy-1-naphthoic acid, 7-hydroxy-2-naphthoic acid, 1,3-dihydroxy-2-naphthoic acid, 4-amino-5-hydroxy-1-naphthalene sulfonic acid, 2-amino-1-naphthalene sulfonic acid, and so forth.

The organic acids or salts may be modified with alkyl, ether, alpha-olefin, alkoxyates including ethoxyates, aromatic groups, hydroxyl, amino, thio and so forth. A  
10 preferably class of organic counter ion is the sulfonate ion. These organic acids or salts are useful in the aqueous medium from about 0.1% to about 5% by weight of the composition and preferably from about 0.2% to about 1% by weight of the composition.

The alcohols useful herein are preferably medium to long chain alcohols and may be alkanols or alcohol alkoxyates, i.e. alcohol ethoxyates. Alcohols are useful  
15 at a concentration in the aqueous medium of about 0.1% to about 4% by weight of the composition and preferably from about 0.2% to about 2% by weight of the composition.

Inorganic salts or small quaternary ammonium salts such as tetramethyl ammonium chloride, are also useful to the present invention. Preferably, the salts will be salts of sodium, potassium, ammonium, calcium, magnesium, zinc and so forth. These  
20 ions preferably will be in combination with a halide ion. More specifically, the inorganic salt may include potassium chloride, ammonium chloride, sodium chloride, magnesium chloride, calcium chloride, calcium bromide, and so forth. These inorganic salts both aid in the development of the gel, and assist in maintaining stability of the geologic formation to which the fluid is exposed. These inorganic salts are useful at a concentration in the  
25 aqueous medium from 0% to about 10% by weight, preferably from 1% to about 6%. The concentration of the counterion or additive appears to be somewhat dependent on the size of the molecule, and that larger molecules may be added in lower concentrations.

Specific examples of such counter ions include chloride, bromide, methyl sulfate, ethyl sulfate, xylene sulfonate, p-toluene sulfonate, naphthalene sulfonate,  
30 hydroxynaphthalene sulfonates and carboxylates, 4-amino-5-hydroxy-1-naphthalene

sulfonic acid, 2-amino-1-naphthalene sulfonic acid, 3-hydroxy-2-naphthenic acid, ethoxylated lauryl sulfate, sulfobetaines, 5-hydroxy-1-naphthoic acid, 6-hydroxy-1-naphthoic acid, 7-hydroxy-1-naphthoic acid, 3-hydroxy-2-naphthoic acid, 5-hydroxy-2-naphthoic acid, 7-hydroxy-2-naphthoic acid, 1,3-dihydroxy-2-naphthoic acid, 3,4-  
5 dichlorobenzoate, and so forth.

Preferably, at least one organic counterion will be present in the compositions of the present invention. Although, in some preferred embodiments of the present invention both an inorganic salt and an organic salt, or acid, are utilized together with the quaternary ammonium cationic surfactant of the present invention. Preferably,  
10 the organic salt utilized is from the sulfonate family.

The total amount of the additives present will preferably range anywhere from about 0.1% to about 10% by weight of the total composition.

It is envisioned that the cationic surfactants of the present invention may also be used in combination with other surfactants such as anionic, non-ionic, amphoteric  
15 (or zwitterionic) surfactants.

To prepare the aqueous fracturing fluid of the present invention, the viscoelastic surfactant is added to an aqueous solution in which has been dissolved at least one water soluble inorganic salt (i.e. NaCl, KCl, NH<sub>4</sub>Cl, NH<sub>4</sub>NO<sub>3</sub>, etc.), and/or at least one organic salt, organic acid, or alcohol, to provide formation stability, or to provide  
20 selective control of the loss of particle suspension properties. As stated above, the salts both aid in the development of the gel, and assist in maintaining stability of the geological formation to which the fluid is exposed.

Standard mixing procedures known to one of skill in the art may be employed in the present invention.

25 Other ingredients may also be added to the fluids of the present invention including defoamers, fluid loss additives, breakers, demulsifiers, and so forth, as well as other polymeric materials such as guar, guar derivatives, starch, cellulose, polyacrylates, and so forth. Additives such as these are known to one of skill in the art.

In some instances, it may be preferable to foam the fluids of the present  
30 invention by adding air, nitrogen, carbon dioxide, and a foaming agent.

These gelled or thickened fluids may be referred to as viscoelastic fluids. The term viscoelastic is commonly understood to refer to a fluid that has the capability to partially return to its original non-disturbed form upon release of applied stress. It is believed that under the right conditions, i.e. concentration, counter ion, pH and so forth, 5 that certain surfactants form rod-like or cylindrical micelles which can entangle to form these gelatinous, viscoelastic fluids in aqueous solutions.

The gelled or thickened fluids of the present invention may exhibit a reversible thickening phenomenon. The fluids of the present invention may exhibit an increase in viscosity as the temperature is increased as opposed to most fluids which 10 exhibit a decrease in viscosity as the temperature is increased. Furthermore, when the heat source is removed and the temperature decreases, the viscosity will also decrease. This phenomena, for instance, is illustrated in Table 11 of the Examples section where the viscosity of a high brine oil field completion fluid increases as the temperature is increased from about 170° F to about 250° F (about 76.7° C to about 121.1° C).

15 The thickened fluids of the present invention find particular utility as fracturing fluids, in compositions used in well drilling operations, for proppant and cutting transportation to and from the fracture site, and drilling fluids. These compositions have also found excellent utility in completion fluids. Completion fluids are often used in high brine situations where the salt concentration (divalent salts such as CaCl<sub>2</sub>, CaBr<sub>2</sub>, ZnBr<sub>2</sub>, 20 and so forth) may be as high as about 30 wt-% to about 70 wt-%. Polymeric thickeners are not as advantageously used in such high brine fluids because the polymers tend to be incompatible in these high salt environments. The polymers often precipitate from the solutions which can result in damage to the subterranean formation.

Fracturing of a subterranean formation involves pumping or injecting the 25 aqueous fluid through a wellbore and against a subterranean formation at a flow rate and pressure sufficient to initiate and or extend a fracture into the formation. The thickened fluid also acts as a transportation vehicle for the proppant particles. These particles are carried to the fracture where they will remain in order to "prop" the fracture site open after the pressure is removed and the well goes into production. Keeping the fracture 30 open allows for better flow of hydrocarbons from the site.

The gels of the present invention have excellent thermal stability of greater than about 65° C, preferably greater than about 80° C, more preferably greater than about 90° C, even more preferably greater than about 95° C, and most preferably greater than about 105° C. Many of the preferred surfactants have been found to have thermal  
5 stability in excess of about 225° F (about 107° C), although in some instances the surfactants exhibit thermal stability in the 275° F (about 135° C) to 300° F (about 149° C) range. It is preferred that the compositions exhibit stability of at least about 185° F (about 85° C) to about 230° F (about 110° C).

The gels of the present invention exhibit excellent viscosity stability to  
10 shear forces and high pressure and do not readily degrade upon exposure to high shear. This decreases the amount of fluid lost to the formation during the fracturing process when they are exposed to extreme pressures, and subsequently, leakoff rates for these fluids are low.

The excellent thermal and shear stability of the thickened fluids of the  
15 present invention make them particularly useful for fracturing operations where the temperature is high and/or the fracture site has high permeability. If the viscosity of the fluid is susceptible to decrease at high temperatures, more fluid can be lost to the formation resulting in less efficiency in the fracturing process, and more fluid lost in the formation.

20 The gel-like structure formed by the surfactants of the present invention may be disrupted on contact with hydrocarbon liquids, resulting in loss of viscosity. This can be advantageous for removal of the gel from the fracture once the fracturing process is complete and the well goes into production.

The gels of the present invention also find utility in other various other oil  
25 field and non-oil field applications including gravel-pack applications, in acidizing treatments, as diverting agents or lost-circulation agents, in pipeline drag reduction, in coil-tubing operations, in drilling operations as drilling fluids, as completion fluids, as foamed underbalance drilling fluids, and so forth.

The use of polymer-free viscoelastic gels in gravel-pack applications is  
30 discussed in Society of Petroleum Engineers (SPE) 17168, W.L. Nehmer, "Viscoelastic



Gravel-Pack Carrier Fluids," incorporated by reference herein. The gels of the present invention provide excellent rheological properties making the especially useful in gravel-pack treatments where the rheology of the fluid is essential to achieving a good "pack". As opposed to polymer gels, the surfactant based gels of the present invention  
5 are not as susceptible to high shear forces. Further, they are less likely to damage the formation than those gels which utilize polymeric materials.

The surfactants of the present invention find utility in gelled acid systems for use in acidizing carbonate and dolomite formations for prevention of loss of fluid in the formation due to the presence of natural fissures and cracks. The systems of the  
10 present invention provide a cleaner system than the polymeric based gels.

The gels of the present invention find utility as diverting agents or lost-circulation agents which aid in preventing loss of treating fluid into the natural fissures and cracks in the formation. Again, as opposed to polymeric gels, the gels of the present invention impart less damage to the formation and are easier to clean out of the formation  
15 upon completion of the treatment.

The gels of the present invention also find utility in reducing drag in pipelines. Pipeline drag reduction is discussed in U.S. Patent No. 4,615,825 to Teot et al. incorporated by reference herein. Surprisingly, the surfactants of the present invention provide more shear stability and greater reduction in frictional forces than polymeric  
20 additives. In a preferred embodiment of the present invention, a salicylate is utilized as the counterion in the composition, providing excellent drag reduction.

The amount of surfactant and additive added to the aqueous fluid to reduce the friction as it passes through a conduit will depend on a variety of factors including the particular aqueous liquid, the surfactant chosen, as well as the type of  
25 additive chosen. In general, the concentration of the surfactant is preferably from about 0.01% to about 10% by weight of the fluid, and more preferably from about 0.05% to about 5%. The additive is preferably from about 0.1% to about 10% by weight of the total composition.

The gels of the present invention find utility in both coil-tubing and drilling  
30 operations which involve the circulation of the thickened fluids through wells. The

primary function of the gels in this instance is to transport cuttings or other fine debris including the filtered proppant out of the well bore. The gels of the present invention provide excellent rheological properties for such applications, and contribute minimally to the friction pressure. The thickened fluids are reusable upon removal of the cuttings from  
5 the fluid. These applications are discussed in U.S. Patent No. 4,735,731 to Rose et al. incorporated by reference herein.

In drilling operations, in addition to the transportation of cuttings, the compositions of the present invention also find utility as drilling fluids to maintain the integrity of the wellbore and to lubricate the drill bit. Typically in these drilling  
10 operations, the fluids are referred to as drilling mud.

The compositions of the present invention also find utility as completion fluids for drilling operations and for work over rigs. Viscosifiers are necessary in completion fluids in order to prevent too much water from filtering out into the porous surface of the formation, a phenomenon referred to in the industry as fluid loss. These  
15 viscosifiers are necessary both during the actual drilling process, and for preventing settling of the solids later on.

The completion fluids are typically heavy brine solutions having a density in the range of about 11 pounds per gallon ( $\sim 1098 \text{ kg/m}^3$ ) to about 19 pounds per gallon ( $\sim 1896 \text{ kg/m}^3$ ) as compared to water which is about 8.32 lbs/gallon. The gelants of the  
20 present invention are excellent thickeners for these high salt concentration fluids. The resultant completion fluids exhibit excellent thermal stability of at least about 250° F (about 120° C) to about 350° F (about 177° C). For these completion fluids, a small amount of surfactant in an amount of about 0.5 wt-% to about 4 wt-% facilitates gel formation. Furthermore, the use of counterions, e.g. inorganic salts, organic salts, organic  
25 acids, alcohols, and so forth, is not necessary. However, a small amount of counterion may be desirable. If a counterion is used, the desirable range is about 0.10% to about 5%. The addition of the counterions can improve gel stability but the gelants of the present invention function without the presence of such counterions.

In a particular embodiment, sodium salicylate in an amount of less than  
30 about 0.2 wt-% was added in addition to the gelant.

Non-oil field applications include applications in the mining and metal cutting industries. The compositions of the present invention may also be used in the construction industry during excavation, digging, tunneling, drilling, and so forth. They may also be used for dust control. The compositions of the present invention may also be used in the masonry, cement and concrete industries.


The compositions of the present invention also find use as rheology modifiers, and may be used in household products including shampoos, detergents, cleaning products, and so forth.

The viscoelastic surfactants of the present invention also exhibit drag reducing properties.

#### EXAMPLES

KCl solution, 2% by weight, was stirred in a 500 ml stainless steel blender at an rpm of 200-300. To this solution, approximately 4 ml (~60% by weight concentration in ethylene glycol) of the quaternary ammonium salt (dimethylamidopropyltrimethyl ammonium chloride) was added to the KCl solution (forming a 3% by weight concentration of surfactant). Witconate® SXS, xylene sulfonate, was added (2 ml, ~40% concentration) and the resulting mixture was stirred for about 5 minutes at an rpm of 2000 to 3000 (Variact set at about 25). The resultant gel was defoamed using a sonicator and/or heating to 80°C. Rheological performance was evaluated using a model 50 rheometer (a Fann 50 Rheometer). The results may be found in the following tables.

The quaternary compound found in Table I has the following general structure:



R is erucyl, (22 carbon, unsaturated fatty acid chain), R<sup>2</sup>, R<sup>3</sup> and R<sup>4</sup> are each methyl, y is 1, and X is chloride. This compound will be referred to hereinafter as erucyl-DMAPA quat.

5                   Preblending of the quaternary salt and the xylene sulfonate before addition to the water appeared to delay gel formation more than adding each ingredient to the water separately.

#### Example 1

10

Table 1

Rheological Performance of a Gelled Fluid

Temperature ° F (° C)	Viscosity		
	40 sec <sup>-1</sup>	100 sec <sup>-1</sup>	170 sec <sup>-1</sup>
80 (26.7)	740	430	200
15    100 (37.8)	745	435	215
125 (51.7)	408	312	180
150 (65.6)	274	150	100
175 (79.4)	310	167	80
200 (93.3)	247	170	76
20    225 (107.2)	120	90	60
250 (121.1)	60	--	27

Gel Composition: 2% KCL; 4% erucyl-DMAPA quat, 60% active (gelling agent); 2% Witconate® SXS (40% solution) sodium xylene sulfonate available from  
25 Witco Corp.

Example 1 illustrates the rheological performance of a viscoelastic gel of the present invention. The gels exhibits high viscosity at low shear rates thereby providing excellent proppant transportation and control of fluid penetration into the formation when the fluid is forced at high pressure into the fracture face.

## Example 2

Table 2

Effect of Gellant Concentration on Viscosity

5 Temperature ° F (° C)	Viscosity (cPs) @ 100 sec <sup>-1</sup>		
	2.5% gelant	4% gelant (60% active)	6% gelant
80 (~27)	260	430	590
100 (~38)	215	435	600
125 (~52)	142	312	542
150 (~66)	70	150	283
10 175 (~79)	77	167	231
200 (~93)	80	170	182
225 (~107)	61	90	100

The gel composition contained 2% KCL, 2% Witconate® SXS (40%  
15 solution), and erucyl-DMAPA quat gelant.

Example 2 illustrates the effect of the concentration of the gelant on the  
rheological performance of the fluid. The amount of gelant may be tailored to the  
physical characteristics of the geological formation such as temperature and permeability.  
For instance, a fluid with a high concentration of surfactant thereby providing higher  
20 viscosity, would find utility in a high temperature formation.

Example 3

Table 3  
Effect of Chain Length of R on Stability

No. of carbon atoms	Group	Stability
22	erucyl (unsaturated)	~225° F (~107° C)
22	saturated C <sub>22</sub>	<150° F (65.5° C)
18	oleyl	<150° F(65.5° C)
16	palmityl	<150° F (65.5° C)
12	lauryl	weak gel

\*Each of the compositions contained 2% KCL; 4% gelant; and 2% Witconate® SXS.

Comparative Examples A and B

Comparative example A was composed of 2% KCL; 4% Kemamine® EX-300 erucyl-amine gelant; and 5 lbs sodium salicylate/1000 gallons. The heat stability was approximately 200° F (~93° C).

Comparative example B was composed of 2% KCL; 4% erucylamidopropylamine oxide (45% active) gelant; 2% Witconate® SXS; and 1% Adogen® 471. Comparative B had heat stability of <175° F (79.4° C).

Example 3 as compared to comparative examples A and B illustrates that surprisingly, comparable heat stabilities are being obtained with the gelants of the present invention as compared to commercially available gelants which are standards in the industry, even though the chemical structures are different.

## Example 4

Table 4

## Effect of Counter Ion Concentration on Gel Stability

Temp ° F (° C)	Viscosity (cPs) @ 1000 sec <sup>-1</sup>				
	1% SXS	2% SXS	3% SXS	4% SXS	6% SXS
80 (~27)	300	430	360	370	-
100 (~38)	220	435	340	400	285
125 (~52)	250	310	220	200	170
150 (~66)	230	150	150	166	105
175 (~79)	150	165	145	115	75
200 (~93)	110	170	90	90	-
225 (~107)	80	90	-	-	-

\*The gel composition was 2% KCl; 4% erucyl-DMAPA quat gelling agent (60% active); and Witconate® SXS (40% solution) varied as shown in Table 4.

## Example 5

Table 5

## Effect of Counter Ion Concentration on Gel Stability

Temp ° F (° C)	Viscosity (cPs) @ 1000 sec <sup>-1</sup>				
	1% salicylate	2% salicylate	3% salicylate	4% salicylate	6% salicylate
80 (~27)	110	300	310	330	250
100 (~38)	95	380	300	350	280
125 (~52)	75	260	320	325	245
150 (~66)	50	215	360	275	175
175 (~79)	-	160	155	165	130
200 (~93)	-	115	140	130	90

\*The gel composition was 2% KCl; 4% erucyl-DMAPA quat gelling agent (60% active); and the concentration of the sodium salicylate counter ion (25% solution) varied as shown in Table 5.

5

Example 6

Table 6  
Effect of Type of Counter Ion on Stability

	Counter Ion	Counter Ion Concentration	Stability
10	Witconate® SXS sodium xylene sulfonate (40% solution)	2%	~225° F (~107° C)
	sodium salicylate (25% solution.)	2%	~200° F (~93° C)
15	Witconate® 1247H ammonium alcohol ether sulfonate	0.6%	~225° F (~107° C)
	Witco® TX Acid (sodium salt, 20% soln)	5%	~210° F (~99° C)
20	sodium 3-hydroxy-2-naphthanoate	4%	<150° F (~65.5° C)
	sodium 2-amino-1-naphthalene sulfonate (10% soln.)	4%	<150° F (~65.5° C)

25

\*Each of the compositions in Table 6 contained 2% KCl and 4% erucyl-DMAPA quat gelling agent (60% active). The sodium xylene sulfonate counter ion and the ammonium alcohol ether sulfate counter ion produced the most stable gels, while those counter ions having naphthalene groups decreased the stability of the gel. The amount of  
30 counterion utilized to aid in gel formation appears to be somewhat dependent on the size



of the counterion, and the larger the counterion, the less required.

### Example 7

5

Table 7

Effect of Substitution on the Amine on the Stability of the Gel

$R^2$	Stability
methyl	~225° F (~ 107° C)
allyl	~200° F (~ 93° C)
10 benzyl	~150° F (~ 65.5° C)
vinyl benzyl	~150° F (~ 65.5° C)
propylsulfonate	~200° F (~ 93° C)
dihydroxypropyl	~210° F (~ 99° C)

15 \*Each composition contained 2% KCl; 4% erucyl-DMAPA quat gelant (60% active); and 2% Witconate® SXS sodium xylene sulfonate counterion.  $R^2$  was varied on the erucyl-DMAPA quat gelant. The smaller alkyl groups and the hydroxyalkyl groups appear to increase the stability of the gelled fluid.

### 20 Example 8

Example 8 illustrates the use of the gelant system of the present invention for use in a completion fluid. A completion fluid brine, 100 mL, was added to a blender fitted with a 200 mL stainless steel blender jar. Surfactant was added in amount of 4 wt-%. The resultant solution was stirred at low shear for (less than 1000 rpm) for 10  
25 minutes. A erucyl-DMAPA quat gelling agent was added and each solution was heated at 75° F (23.8° C) for 1 hour. A counterion, sodium salicylate, was added to one solution in order to determine its effect on gel formation.

Table 8  
Completion Fluids

	Brine Density (kg/m <sup>3</sup> )	Gel Formation/Comments	Gel Stability at 121° C
5	(1157) 11.6 lbs/gallon	*0.1875 wt-% sodium salicylate counterion	not measured
	(1507) 15.1 lbs/gallon	gel formed when heat was applied at 75° F for 1 hour	stable
	(1716) 17.2 lbs/gallon	gel formed rapidly at room temperature	stable
10	(1916) 19.2 lbs/gallon	gel formed at room temperature	stable

\*The gel composition was 4% gelant (~2% active).

It can be noted that the gel formation time can be reduced for fluids less  
15 than 16 ppg when a counterion such as sodium salicylates are added. However,  
counterions are not necessary for the compositions of the present invention. For the gels  
which formed at room temperature, gel thickness could be increased with the addition of  
heat. In many instances, this is reversible.

The rheological performance of the completion fluid brine prepared with  
20 the completion fluid having a density of 19.2 lbs/gallon was determined. The viscosity  
was measured using a Fann 50 modified rheometer with a R1B5 configuration. The  
results are shown in Table 9 below.

Table 9

Time (Min)	Temp °F (°C)	visc @ 1 sec <sup>-1</sup>	n'	K(ind)	K'slot	R <sup>2</sup>	Calculated Viscosity (cP) @		
							40 sec <sup>-1</sup>	100 sec <sup>-1</sup>	170 sec <sup>-1</sup>
2	76 (~24)	---	0.293	0.3868	0.4598	0.941	1622	848	583
5 40	95 (35)	20237	0.282	0.3838	0.4564	0.992	1549	803	548
74	121 (~49)	13274	0.364	0.2541	0.3003	0.990	1375	767	548
102	146 (~63)	9327	0.384	0.1787	0.2107	0.990	1041	592	427
127	170 (~77)	4495	0.480	0.0871	0.1010	0.974	710	441	335
150	195 (~90.5)	2450	0.508	0.0476	0.0548	0.956	427	272	210
10 179	221 (105)	2154	0.390	0.0414	0.0487	0.942	246	141	102
199	245 (~118)	2421	0.250	0.0458	0.0544	0.902	164	82	55

The rheological performance of the completion fluid brine prepared with the brine solution having a density of 17.2 lbs/gallon was determined. The results are shown in the following Table 10.

Table 10

Time (Min)	Temp °F (°C)	visc @ 1sec <sup>-1</sup>	n'	K(ind)	K'slot	R <sup>2</sup>	Calculated Viscosity (cP) @		
							40sec <sup>-1</sup>	100sec <sup>-1</sup>	170sec <sup>-1</sup>
20 2	76 (~24)	6900	0.466	0.1337	0.1554	0.996	1039	637	480
44	95 (35)	6597	0.474	0.1280	0.1485	0.955	1023	632	478
79	120 (~49)	13217	0.368	0.2533	0.2992	0.927	1394	782	559
108	146 (~63)	18889	0.312	0.3600	0.4276	0.907	1618	862	598
25 133	170 (~77)	8814	0.502	0.1715	0.1980	0.922	1512	958	736
156	195 (90.5)	8194	0.412	0.1581	0.1855	0.904	1016	593	434
183	221 (105)	13124	0.167	0.2474	0.2913	0.805	646	301	193
203	245 (~118)	7117	0.316	0.1355	0.1608	0.939	617	330	229

The rheological performance of the completion fluid brine prepared with the brine solution having a density of 15.1 was determined. The results are shown in the following Tables 11 and 12. The viscosity data found in Table 11 was determined using a Fann 50 rheometer.

Table 11  
(viscosity measured using a Fann 50 Rheometer)

Time (Min)	Temp °F (° C)	Visc @ 1 sec <sup>-1</sup>	n'	K(ind)	K'slot	R <sup>2</sup>	Calculated Viscosity (cP) @			
							40 sec <sup>-1</sup>	100sec <sup>-1</sup>	170sec <sup>-1</sup>	
5	2	82 (~28)	5069	0.339	0.0968	0.1147	0.976	479	261	184
	33	96 (35.5)	4989	0.319	0.0948	0.1126	0.957	438	235	163
	65	121 (~49)	5010	0.286	0.0950	0.1129	0.965	388	202	138
	93	145 (~62)	4991	0.272	0.0945	0.1124	0.966	367	188	128
	118	171 (~77)	2812	0.425	0.0542	0.0635	0.931	365	215	159
10	139	195 (90.5)	4244	0.412	0.0818	0.0961	0.965	525	306	224
	166	220 (~104)	9391	0.259	0.1783	0.2120	0.916	660	335	226
	186	245 (~118)	11322	0.289	0.2154	0.2561	0.917	890	464	318

15                    The viscosity data found in the following Table 12 was determined using a  
Constien & Associates Reciprocating Capillary Viscometer (RCV). The viscous  
properties are determined by displacing fluids at selected shear rates through a calibrated  
section of tubing. Flow direction is reversed at 1/3 of the tubing volume in order to  
maintain the fluid under shear for the entire test. Tubing and displacement accumulators  
20 are maintained at preselected temperatures in an oil bath. The entire system is pressurized  
at 200 psi. The shear rates are ramped at each temperature over about a 25 minute  
interval at rates of 3.4, 5.1, 6.8, 12.9, 25 and 50 sec<sup>-1</sup>. The temperature is then raised and  
the shear rate is maintained at 97 sec<sup>-1</sup> while the temperature is equilibrating between  
ramping intervals. The fluid parameters n' and K were determined using a Power Law  
25 Model.

Table 12  
(viscosity measured using an RCV)

Ramp Temp ° F (° C)	n'	K (ind)	K' slot	R <sup>2</sup>	Calculated Viscosity (cPs) @		
					1 sec <sup>-1</sup>	40 sec <sup>-1</sup>	100sec <sup>-1</sup>
5 ambient	0.458	0.061	0.071	0.910	3420	464	282
100 (~38)	0.420	0.055	0.065	0.995	3091	364	214
125 (~52)	0.375	0.059	0.070	0.992	3345	334	188
150 (65.5)	0.294	0.069	0.082	0.984	3909	289	151
175 (~79)	0.396	0.039	0.046	0.870	2193	236	136
10 200 (~93)	0.380	0.096	0.113	0.999	5422	551	312
225 (~107)	0.330	0.181	0.214	0.992	10258	865	468
250 (~121)	0.429	0.161	0.189	0.995	9046	1100	652
275 (135)	0.427	0.074	0.087	0.977	4175	504	298

15

The rheological performance of the 19.2 lb/gallon density completion fluid brine was measured with a Brook field viscometer (#2 Disc at 0.3 rpm). The results are found in the following Table 13.

As can be noted from the viscosity data, in particular the data collected  
20 from 118 minutes to 186 minutes, the viscosity increased with an increase in temperature. In contrast, most fluids exhibit a decrease in viscosity with increasing temperature.

Table 13

Temperature	High Viscosity (cps)	Low Viscosity (cps)
25 122°F (50° C)	100,000	100,000
140°F (60° C)	36,000	16,000
149°F (65° C)	29,000	19,000
158°F (70° C)	25,000	6,000
167°F (75° C)	23,000	8,300
30 176°F (80° C)	17,000	2,500

The completion fluid brine having a density of 15.1 lbs/gallon was tested for settling using the barite. The concentration of the erucyl-DMAPA quat was varied from 1% to 4%. The gelled fluid was mixed with the barite (37 grams per 150 mL of gel) in a covered graduated cylinder, and the amount of settling was observed at 100° C. The results are found in the following Table 14.

Table 14

Erucyl-DMAPA quat concentration	% Settling
4 wt-% (60% active)	none
2 wt-% (60% active)	<1%
1 wt-% (60% active)	<2%

10


The results found in Table 13 indicate that the amount of settling improves as the amount of the gelant of the present invention is increased from 1 wt-% to 4 wt-%.

15

## CLAIMS:

1. An aqueous based fluid useful in oil field applications comprising:  
 a) at least one cationic surfactant having the following general structure:

5



10

wherein R<sup>1</sup> is alkyl amine alkylene or alkyl amido alkylene; R<sup>2</sup> and R<sup>3</sup> are each alkyl, hydroxy alkyl, polyalkoxy with the degree of polymerization ranging from 2 to 30, hydroxyl alkyl sulfonate, alkyl sulfonate or alkylarylsulfonate; R<sup>4</sup> is hydrocarbon, saturated or unsaturated; or wherein any two of R<sup>2</sup>, R<sup>3</sup> and R<sup>4</sup>, together with the nitrogen atom to which they are attached, form a heterocyclic ring; and X is selected from the group consisting of halides; oxo ions of phosphorous, sulfur or chloride; and organic anions; and

15

- b) at least one additive selected from the group consisting of

20

inorganic salts, organic salts, organic acids, alcohols, and mixtures thereof.


2. The aqueous based fluid of Claim 1 wherein said fluid comprises at least one counterion selected from the group consisting of organic salts and organic acids.
3. The aqueous based fluid of Claim 1 wherein said fluid comprises at least one counterion selected from the group consisting of sulfates, sulfonates and salicylates.
4. The aqueous based fluid of Claim 2 wherein said counterion comprises at least one aromatic group.
5. The aqueous based fluid of Claim 1 wherein X is an aromatic sulfonate.
6. The aqueous based fluid of Claim 1 wherein said fluid comprises from about 0.1% to about 5% by weight of the counterion.

25

30

7. The aqueous based fluid of Claim 1 wherein said cationic surfactant has the following general structure:

5



10


wherein R is saturated or unsaturated alkyl and y is an integer from 1 to 12.

8. The aqueous based fluid of Claim 7 wherein R has from about 6 to about 26 carbon atoms.
9. The aqueous based fluid of Claim 7 wherein R has from about 12 to about 22 carbon atoms.
10. The aqueous based fluid of Claim 7 wherein R is erucyl.
11. The aqueous based fluid of Claim 7 wherein y is 1.
12. The aqueous based fluid of Claim 1 wherein said cationic surfactant is isostearylamidopropylmorpholine.
13. The aqueous based fluid of Claim 1 wherein said surfactant is present in said fluid at a concentration of about 0.05% to about 10% by weight of said fluid.
14. The aqueous based fluid of Claim 1 wherein said fluid has thermal stability of greater than about 85° C.
15. The aqueous based fluid of Claim 1 in combination with a high brine liquid comprising from about 30 wt-% to about 70 wt-% salt.
16. A method of fracturing a subterranean formation comprising the steps of:
- I) providing a thickened aqueous based hydraulic fracturing fluid, comprising:
    - a) an aqueous medium; and
    - b) an effective amount of at least one gelling agent having the following general structure:

30



5



10 wherein R<sup>1</sup> is alkylamine alkene or alkyl amidoalkene, R<sup>2</sup> and R<sup>3</sup> are each alkyl, hydroxy alkyl, alkyl, hydroxy alkyl, polyalkoxy with the degree of polymerization ranging from 2 to 30, hydroxyl alkyl sulfonate, alkyl sulfonate or  
 15 alkylarylsulfonate; R<sup>4</sup> is hydrocarbon, saturated or unsaturated; or wherein any two of R<sup>2</sup>, R<sup>3</sup> and R<sup>4</sup>, together with the nitrogen atom to which they are attached, form a heterocyclic ring; and X is selected from the group consisting of halides; oxo ions of phosphorous, sulfur or chloride; and organic anions; and

c) at least one counterion selected from the group consisting of organic salts, inorganic salts, organic acids, alcohols, and mixtures thereof; and

20 II. pumping the aqueous fracturing fluid through a wellbore and into a subterranean formation at a pressure sufficient to fracture the formation.

17. The method of Claim 16 wherein said fracturing fluid comprises at least one counterion selected from the group consisting of organic acids and organic salts.

18. The method of Claim 16 wherein said counter ion is selected from the group  
 25 consisting of sulfates, sulfonates and salicylates.

19. The method of Claim 17 wherein said counterion comprises at least one aromatic group.

20. The method of Claim 17 wherein said counterion is an aromatic sulfonate.

21. The method of Claim 16 wherein said gel has a thermal stability up to  
 30 temperatures of about 110° C.

22. The method of Claim 16 wherein said fracturing fluid has thermal stability of


greater than about 90° C.

23. The method of Claim 16 wherein said fracturing fluid comprises from about 0.05% to about 10% by weight of said cationic surfactant.

24. A method of suspending particies in a thickened aqueous liquid the method comprising the steps of:

I) providing an aqueous medium; and

II) adding to said aqueous medium, an effective amount of at least one surfactant and at least one counterion selected from the group consisting of organic salts, inorganic salts, organic acids, alcohols, and mixtures thereof, sufficient to increase the viscosity of said aqueous medium wherein said surfactant has the following having the following general structure:



wherein R<sup>1</sup> is alkylamine alkene or alkyl amidoalkene, R<sup>2</sup> and R<sup>3</sup> are each alkyl, hydroxy alkyl, alkyl, hydroxy alkyl, polyalkoxy with the degree of polymerization ranging from 2 to 30, hydroxyl alkyl sulfonate, alkyl sulfonate or alkylarylsulfonate; R<sup>4</sup> is hydrocarbon, saturated or unsaturated; or wherein any two of R<sup>2</sup>, R<sup>3</sup> and R<sup>4</sup>, together with the nitrogen atom to which they are attached, form a heterocyclic ring; and X is selected from the group consisting of halides; oxo ions of phosphorous, sulfur or chloride; and organic anions.


wherein said aqueous liquid is sufficiently thickened to suspend solid particulate matter.

25. The method of Claim 24 further comprising transporting the suspension of said solid particulate matter in said aqueous liquid to a remote location.


26. The method of Claim 24 wherein said solid particulate matter is selected from the group consisting of cuttings and proppants.

27. The method of Claim 24 wherein said method is implemented in a well drilling operation.
28. The method of Claim 24 wherein said method is implemented in a coil-tubing operation.
- 5 29. The method of Claim 24 wherein said method is implemented in a construction operation.
30. The method of Claim 24 wherein said method is implemented in a mining operations.
31. A method of reducing the friction exhibited by an aqueous liquid during flow  
10 through a conduit comprising the steps of:
- a) providing an aqueous medium;
  - b) contacting said aqueous medium with a friction reducing amount of a viscoelastic surfactant having the following general structure:

15



- 20 wherein R is saturated or unsaturated alkyl and y is an integer from 1 to 12, and an additive selected from the group consisting of inorganic salts, organic salts, organic acids, alcohols, and mixtures thereof; and
- c) passing said aqueous fluid through said conduit;
- 25 wherein said viscoelastic surfactant and said additive are present in an amount capable of reducing the friction exhibited by said aqueous liquid as said aqueous liquid passes through said conduit.
32. An oil field high brine completion fluid comprising:
- a) about 30 wt-% to about 70 wt-% of at least one inorganic or organic salt; and
  - 30 b) about 0.1 wt-% to about 4 wt-% of at least one cationic surfactant having the following general structure:



5

wherein R<sup>1</sup> is alkyl amine alkylene or alkyl amido alkylene; R<sup>2</sup> and R<sup>3</sup> are each alkyl, hydroxy alkyl, polyalkoxy with the degree of polymerization ranging from 2 to 30, hydroxyl alkyl sulfonate, alkyl sulfonate or alkylarylsulfonate; R<sup>4</sup> is hydrocarbon, saturated or unsaturated; or wherein any two of R<sup>2</sup>, R<sup>3</sup> and R<sup>4</sup>, together with the nitrogen atom to which they are attached, form a heterocyclic ring; and X is selected from the group consisting of halides; oxo ions of phosphorous, sulfur or chloride; and organic anions.

- 10
- 15 33. The fluid of Claim 32 further comprising at least one additive selected from the group consisting of inorganic salts, organic salts, organic acids, alcohols, and mixtures thereof.
- 20 34. The fluid of Claim 32 wherein the viscosity of said fluid increases when the temperature is increased and decreases when the temperature is decreased.

# INTERNATIONAL SEARCH REPORT

Internatic Application No

PCT/US 00/24142

**A. CLASSIFICATION OF SUBJECT MATTER**

IPC 7 C09K7/02 E21B43/25 E21B43/26

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C09K E21B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 99 32572 A (AKZO NOBEL NV) 1 July 1999 (1999-07-01) page 5, line 3 -page 6, line 15 ---	1,7
A	US 4 725 372 A (TEOT ARTHUR S ET AL) 16 February 1988 (1988-02-16)  column 1, line 8 - line 15 column 2, line 24 -column 3, line 17 column 4, line 12 - line 32; table 1 ---	1-5,13, 15-20, 23,32
A	US 5 551 516 A (NORMAN WILLIAM D ET AL) 3 September 1996 (1996-09-03)  column 6, line 26 -column 10, line 31 ---  -/--	1-5,13, 15-20, 23,32

Further documents are listed in the continuation of box C.

Patent family members are listed in annex.

° Special categories of cited documents :

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*Z\* document member of the same patent family

Date of the actual completion of the international search

21 November 2000

Date of mailing of the international search report

28/11/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Boulon, A

# INTERNATIONAL SEARCH REPORT

Internatic Application No  
PCT/US 00/24142

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 089 151 A (HALL BOBBY E ET AL) 18 February 1992 (1992-02-18)  column 2, line 30 -column 3, line 56 -----	1-5, 13, 15-20, 23, 32

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No  
PCT/US 00/24142

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9932572 A	01-07-1999	BR 9813785 A EP 1042425 A	03-10-2000 11-10-2000
US 4725372 A	16-02-1988	NONE	
US 5551516 A	03-09-1996	NONE	
US 5089151 A	18-02-1992	WO 9208039 A	14-05-1992