

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



WIPO | PCT



(10) International Publication Number
WO 2013/181237 A1

(43) International Publication Date
5 December 2013 (05.12.2013)

- (51) International Patent Classification:
C07C 41/09 (2006.01) B01J 23/10 (2006.01)
- (21) International Application Number:
PCT/US2013/043091
- (22) International Filing Date:
29 May 2013 (29.05.2013)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
61/653,493 31 May 2012 (31.05.2012) US
- (71) Applicant: **DOW GLOBAL TECHNOLOGIES LLC**
[US/US]; 2040 Dow Center, Midland, MI 48674 (US).
- (72) Inventors: **BARTON, David, G.**; 3408 Greenbrier Terrace, Midland, MI 48642 (US). **CHOJECKI, Adam**; Poelsnepstraat 7 Bus 202, B-9000 Gent (BE). **ELOWE, Paul, R.**; 5417 Oakridge Drive, Midland, MI 48640 (US). **KILOS, Beata, A.**; 1615 Wood Pointe Lane, Apartment 2, Midland, MI 48642 (US). **STANGLAND, Eric, E.**; 5912 North Heritage Court, Midland, MI 48640 (US).
- (74) Agent: **SHALTOUT, Raef, M.**; The Dow Chemical Company, P.O. Box 1967, Intellectual Property, Midland, MI 48641-1967 (US).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).
- Published:
— with international search report (Art. 21(3))



WO 2013/181237 A1

(54) Title: CATALYTIC DEHYDRATION OF ARYL ALCOHOLS TO DIARYL ETHERS

(57) Abstract: Provided is a process for preparing a diaryl ether compound through the dehydration of an aromatic alcohol compound in the presence of a dehydration catalyst. The dehydration catalyst is an oxide of a light rare earth element, wherein the light earth element is lanthanum, praseodymium, neodymium, or mixtures thereof.

CATALYSTS AND METHODS FOR ALCOHOL DEHYDRATION

Cross-Reference to Related Applications

This application claims priority from provisional application serial number 61/653,493, filed May 31, 2012, which is incorporated herein by reference in its entirety.

5 Background

This invention relates generally to catalysts and methods for the dehydration of aromatic alcohol compounds to ethers. More particularly, the invention uses a dehydration catalyst comprising an oxide of a light rare earth element for the dehydration of aromatic alcohol compounds to diaryl ethers.

10 Diaryl ethers are an important class of industrial materials. Diphenyl oxide (DPO), for instance, has many uses, most notably as the major component of the eutectic mixture of DPO and biphenyl, which is the standard heat transfer fluid for the concentrating solar power (CSP) industry. With the current boom in CSP has come a tightening of the supply of DPO globally and questions surrounding the sustainability of the technology have arisen.

15 Diaryl ethers are currently manufactured commercially via two major routes: reaction of a haloaryl compound with an aryl alcohol; or gas-phase dehydration of an aryl alcohol. The first route, for example where chlorobenzene reacts with phenol in the presence of caustic and a copper catalyst, typically leads to less pure product and requires high pressure (5000 psig), uses an expensive alloy reactor and produces stoichiometric
20 quantities of sodium chloride.

The second route, which is a more desirable approach, accounts for the largest volume of diaryl ethers produced but requires a very active and selective catalytic material. For instance, DPO can be manufactured by the gas-phase dehydration of phenol over a thorium oxide (thoria) catalyst (e.g., U.S. Patent 5,925,798). A major drawback of thoria
25 however is its radioactive nature, which makes its handling difficult and potentially costly. Furthermore, the supply of thoria globally has been largely unavailable in recent years putting at risk existing DPO manufacturers utilizing this technology. Additionally, other catalysts for the gas-phase dehydration of phenol, such as zeolite catalysts, titanium oxide, zirconium oxide and tungsten oxide, generally suffer from lower activity, significantly
30 higher impurity content and fast catalyst deactivation.

With a chronic shortage of diaryl ethers such as DPO in sight and a pressing need to increase capacity, it has become crucial to develop alternate methods to produce such materials in a cost-effective and sustainable manner.

The problem addressed by this invention, therefore, is the provision of new catalysts
5 and methods for manufacture of diaryl ethers from aryl alcohol compounds.

Statement of Invention

We have now found that a catalyst comprising an oxide of a light rare earth element is effective for the preparation of diaryl ethers from aromatic alcohol compounds.

Advantageously, the catalyst exhibits remarkable selectivity for the desired product.

10 Moreover, since various light rare earth element oxides are abundant globally, relatively inexpensive and non-radioactive, this invention represents a unique solution for diaryl ether supply issues globally.

In one aspect, there is provided a method for preparing a diaryl ether, the method comprising dehydrating an aromatic alcohol compound over a dehydration catalyst, wherein
15 the dehydration catalyst is an oxide of a light rare earth element.

In another aspect, there is provided a method for producing a heat transfer fluid, the method comprising: preparing a diaryl ether by contacting an aromatic alcohol compound with a dehydration catalyst, wherein the dehydration catalyst is an oxide of a light rare earth element; isolating the diaryl ether from the dehydration catalyst; and mixing the isolated
20 diaryl ether with biphenyl, wherein the mixture forms a eutectic mixture.

Detailed Description

Unless otherwise indicated, numeric ranges, for instance as in "from 2 to 10," are inclusive of the numbers defining the range (e.g., 2 and 10).

Unless otherwise indicated, ratios, percentages, parts, and the like are by weight.

25 As noted above, in one aspect the invention provides a method for producing a diaryl ether by dehydrating an aromatic alcohol compound over an oxide of a light rare earth element. It has been discovered that such catalysts exhibit high selectivity for the desired diaryl ether compounds with relatively low formation of undesirable byproducts. For instance, as demonstrated by the examples, in the synthesis of diphenyl oxide from
30 phenol, a selectivity for the DPO of 50% or greater may be achieved. In some embodiments, a selectivity of 80 % or greater may be achieved. In some embodiments, a selectivity of 90 % or greater, or alternatively 95 % or greater is possible.

In addition to being highly selective, the catalysts are further advantaged because they are inexpensive. Moreover, the catalysts are non-radioactive, thus eliminating the safety and environmental issues, as well as higher costs, associated with the handling of radioactive materials, such as the thoria catalysts of the prior art.

5 The dehydration catalyst of the invention comprises an oxide of a light rare earth element. By a "light rare earth element" is meant lanthanum, praseodymium, neodymium, or mixtures of two or more thereof. By "oxide of a light rare earth element" is meant a compound that contains at least one oxygen-light rare earth element chemical bond. Examples include lanthanum oxide (La_2O_3), praseodymium oxide (e.g., PrO_2 , Pr_2O_3 , Pr_6O_{11} ,
10 or mixtures), and neodymium oxide (Nd_2O_3).

In some embodiments, the catalyst is an oxide of lanthanum. In some embodiments, the catalyst is an oxide of praseodymium. In some embodiments, the catalyst is an oxide of neodymium. Mixtures of oxides, such as mixtures of oxides of one light rare earth element, or mixtures of oxides of two or more different light rare earth elements, are also
15 encompassed by the invention.

The catalyst may optionally contain other atoms, such as halogens, including chloride or fluoride ion. In some embodiments, a preferred catalyst for use in the invention contains lanthanum, oxygen and chlorine atoms. In some embodiments, the catalyst comprises, in addition to the lanthanum and oxygen, chlorine in an amount of less than 43.4
20 weight percent, alternatively 30 weight percent or less, alternatively 19 weight percent or less, alternatively 10 weight percent or less, or alternatively 2 weight percent or less. In some embodiments, the catalyst comprises the chlorine in an amount of at least 0.001 weight percent, alternatively at least 0.1 weight percent, alternatively at least 1 weight percent, or alternatively at least 2 weight percent. In some embodiments, the catalyst
25 contains between 1 and 19 weight percent chlorine. The chlorine is in the form of chloride ion (Cl^-). Non limiting examples of suitable compounds may include lanthanum oxychloride, or lanthanum oxide containing a chloride (e.g., from NH_4Cl , HCl , etc., or from chloride containing lanthanum precursors). By "oxychloride," as used in this specification, is meant a compound that contains metal-oxygen and metal-chlorine bonds. Examples
30 further include, again without limitation, lanthanum oxide catalysts based on chlorate oxyanions, such as hypochlorite (ClO^-); chlorite (ClO_2^-); chlorate (ClO_3^-), perchlorate (ClO_4^-) where Cl is oxidized (+2, +3, +4, +5), as well as amorphous materials.

In some embodiments, a preferred catalyst contains praseodymium, oxygen and chlorine atoms. In some embodiments, the catalyst comprises, in addition to the praseodymium and oxygen, chlorine in an amount of less than 43.0 weight percent, alternatively 30 weight percent or less, alternatively 19 weight percent or less, alternatively 5 10 weight percent or less, or alternatively 2 weight percent or less. In some embodiments, the catalyst comprises the chlorine in an amount of at least 0.001 weight percent, alternatively at least 0.1 weight percent, alternatively at least 1 weight percent, or alternatively at least 2 weight percent. In some embodiments, the catalyst contains between 1 and 26 weight percent chlorine. The chlorine is in the form of chloride ion (Cl^-). Non 10 limiting examples of suitable compounds may include praseodymium oxychloride or praseodymium oxide containing a chloride (e.g., from NH_4Cl , HCl , etc., or from chloride containing praseodymium precursors). Examples further include, again without limitation, praseodymium oxide catalysts based on chlorate oxyanions, such as hypochlorite (ClO^-); chlorite (ClO_2^-); chlorate (ClO_3^-), perchlorate (ClO_4^-) where Cl is oxidized (+2, +3, +4, +5), 15 as well as amorphous materials.

In some embodiments, a preferred catalyst contains neodymium, oxygen and chlorine atoms. In some embodiments, the catalyst comprises, in addition to the neodymium and oxygen, chlorine in an amount of less than 42.4 weight percent, alternatively 30 weight percent or less, alternatively 19 weight percent or less, alternatively 20 10 weight percent or less, or alternatively 2 weight percent or less. In some embodiments, the catalyst comprises the chlorine in an amount of at least 0.001 weight percent, alternatively at least 0.1 weight percent, alternatively at least 1 weight percent, or alternatively at least 2 weight percent. In some embodiments, the catalyst contains between 2 and 26 weight percent chlorine. The chlorine is in the form of chloride ion (Cl^-). Non 25 limiting examples of suitable compounds may include neodymium oxychloride, or neodymium oxide containing a chloride (e.g., NH_4Cl , HCl , or from chloride containing neodymium precursors). Examples further include, again without limitation, praseodymium oxide catalysts based on chlorate oxyanions, such as hypochlorite (ClO^-); chlorite (ClO_2^-); chlorate (ClO_3^-), perchlorate (ClO_4^-) where Cl is oxidized (+2, +3, +4, +5), as well as 30 amorphous materials.

Catalysts suitable for use in the invention may be prepared by those skilled in the art or they may be purchased from commercial vendors.

The catalyst may optionally contain a binder and/or matrix material that is different from the active oxide of the light rare earth element. Non-limiting examples of binders that are useful alone or in combination include various types of hydrated alumina, silicas and/or other inorganic oxide sols, and carbon. Upon heating, the inorganic oxide sol, preferably
5 having a low viscosity, is converted into an inorganic oxide binder component.

Where the catalyst composition contains a matrix material, this is preferably different from the active catalyst and any binder. Non-limiting examples of matrix materials include clays or clay-type compositions.

The catalyst, including any binder or matrix materials, may be unsupported or
10 supported. Non-limiting examples of suitable support materials include titania, alumina, zirconia, silica, carbons, zeolites, magnesium oxide, and mixtures thereof. Where the catalyst contains a binder, matrix or support material, the amount of oxide of light rare earth element (the active component of the catalyst) may be between 1 and 99 percent by weight based on the total weight of the catalyst (including the oxide, and any support, binder or
15 matrix materials).

The catalyst may be formed into various shapes and sizes for ease of handling. For instance, the catalyst (plus any binder, matrix, or support) may be in the form of pellets, spheres, or other shapes used in the industry.

Aromatic alcohol compounds suitable for use in the process of this invention include
20 aromatic compounds containing at least one alcohol group and one, two, three or more aromatic moieties. Suitable compounds include phenols and α - and β -hydroxy-substituted fused aromatic ring systems. Apart from the hydroxy substituent, the compounds may be unsubstituted, as in phenol or naphthol. Optionally, however, the compounds may be further substituted with at least one alkyl group containing from 1 to about 10 carbon atoms,
25 preferably, from 1 to 3 carbon atoms, or substituted with at least one alternative substituent which is inert to the dehydration coupling reaction. Suitable inert substituents include cyano, amino, nitro, carboxylic acid (e.g., C₀-C₆-COOH), ester, C₆-C₁₂ aryl, C₂-C₆ alkenyl, alkyloxy, aryloxy, and phenoxy moieties. It is also possible for the aromatic alcohol compound to be substituted with both an alkyl substituent and one of the alternative inert
30 substituents. Each of the aforementioned alkyl substituents and/or alternative inert substituents is attached preferably to an aromatic ring carbon atom which is located in an ortho, meta or para position relative to the hydroxy moiety. Optionally, the alkyl substituent may contain from 3 to 4 carbon atoms, and in combination with a phenol or fused aromatic

ring system may form a saturated ring fused to the aromatic ring. An acceptable feed may contain a mixture of aromatic alcohols, including mixtures of the foregoing.

Non-limiting examples of suitable phenols include unsubstituted phenol, *m*-cresol, *p*-cresol, 3,4-xylenol, 3,5-xylenol, and 3,4,5-trimethylphenol. Other suitable phenols include
5 compounds corresponding to the above-mentioned examples except that one or more of the methyl substituents are replaced by an ethyl, propyl or butyl substituent. Non-limiting examples of α - and β -hydroxy-substituted fused aromatic ring systems include α - and β -naphthol and 5-tetralinol. Other non-limiting examples of aromatic alcohols include
10 benzenediols (catechol, resorcinol or hydroquinone), *o*-cresol, *o*-phenylphenol, *m*-phenylphenol or *p*-phenylphenol. One skilled in the art may find other phenols and α - and β -hydroxy-substituted fused aromatic ring systems which are also suitable for the purposes of this invention. Preferably, the aromatic alcohol is unsubstituted phenol or a substituted phenol wherein the substituent is methyl, ethyl, or hydroxyl. More preferably, the aromatic alcohol is unsubstituted phenol, cresol, or a benzenediol. Most preferably, the aromatic
15 alcohol is unsubstituted phenol.

According to the method of the invention for preparing a diaryl ether, a dehydration catalyst as described herein is contacted with the aromatic alcohol compound. The contacting of the catalyst with the aromatic alcohol compound is carried out under reaction conditions such that the diaryl ether is formed.

20 The catalyst is contacted with the aromatic alcohol compound either in the gas phase or in the liquid phase. In addition, the aromatic alcohol may be diluted with a diluent or it may be neat. Suitable diluents include, without limitation, nitrogen, argon, water vapor, water, oxygen or hydrogen. When a diluent is used, the concentration of the aromatic alcohol compound may be, for instance, 1 volume percent or greater and less than 100
25 volume percent.

In a preferred embodiment, the aromatic alcohol is contacted with the catalyst in the gas phase. Typically, the aromatic alcohol is introduced into a reactor containing the catalyst at elevated temperature, for instance, between 200 and 800 °C, alternatively between 300 and 600 °C, alternatively between 400 and 600 °C, or alternatively between
30 450 and 550 °C. The reaction may be conducted at atmospheric pressure, under reduced pressure, or at elevated pressure such as up to 5000 psi. In some embodiments, atmospheric pressure or slightly above (e.g., up to about 50 psi) is preferred. In some embodiments, the gas flow rate of the aromatic alcohol over the catalyst (weighted hourly space velocity or

WHSV) is from 0.01 to 100 grams per hour per gram (g/g·h). In some embodiments, WHSV is from 0.1 to 20 g/g·h, alternatively 0.1 to 5 g/g·h, or alternatively 0.1 to 1 g/g·h.

In some embodiments, it may be useful to subject the reactor to startup conditions which may provide various benefits, such as prolonging catalyst life. Suitable startup
5 condition include, for example, exposing the catalyst to dilute amounts of the aromatic alcohol at lower temperature before changing to full operating conditions as described above and demonstrated by the examples.

Following the reaction, the diaryl ether product is recovered from the catalyst and optionally further purified. Unreacted alcohol and other reaction by-products may be
10 separated using methods known in the art. Such methods include but are not limited to distillation, crystal refining, simulated moving bed technique or a combination thereof.

In some embodiments, the diaryl ether prepared by the process of the invention is diphenyl oxide (DPO). Other diaryl ether compounds that may be prepared by the process of the invention include, without limitation, compounds containing at least one ether
15 functionality whereby two aryl moieties are connected by an oxygen atom (Ar-O-Ar'), including polyaryl compounds and compounds prepared from the aromatic alcohols described above. Specific examples include, but are not limited to, phenoxytoluene isomers, including 3-phenoxytoluene, ditolyl ether isomers, polyphenyl ethers (PPEs), biphenylphenyl ether isomers, naphthyl phenyl ethers, and dibenzofuran.

20 The diaryl ethers prepared by the invention are useful in a variety of applications, including as high temperature solvents, as intermediates in preparing flame retardants and surfactants, and as components in heat transfer fluids. Furthermore, certain diaryl ethers prepared by the invention are useful as high performance lubricants and as intermediates in preparing pyrethroid insecticides.

25 In some embodiments, a preferred use of the diaryl ether is in high temperature heat transfer fluids. High temperature heat transfer fluids may be prepared by making the diaryl ether according to the process described above and then mixing the diaryl ether with biphenyl. The amounts necessary to provide a suitable fluid can be readily determined by a person with ordinary skill in the art. For diphenyl oxide and biphenyl, the amount of DPO
30 may be, for instance, from 70 to 75 weight percent based on the total weight of the DPO and biphenyl. A preferred amount of DPO is that required to form a eutectic mixture with the biphenyl, which is about 73.5 weight percent based on the total weight of the DPO and biphenyl.

Some embodiments of the invention will now be described in detail in the following Examples.

EXAMPLES

Example 1

5 The synthesis of lanthanum oxychloride is carried out by thermal decomposition of $\text{LaCl}_3 \cdot 7 \text{H}_2\text{O}$. A sample of the powdered precursor (approximately 10 g) is calcined in air in a static calcination oven under the following temperature protocol: ramp $1.41^\circ\text{C}/\text{min}$ to 550°C , dwell 3 hrs at 550°C , cool down to room temperature. The elemental composition of the catalyst is assayed by X-ray fluorescence spectroscopy (XRF) to 17.23 wt.% chlorine,
10 69.63 wt.% lanthanum and 13.14 wt.% oxygen (balance). Thus, the elemental composition of the catalyst is $\text{La}_{1.00}\text{O}_{1.64}\text{Cl}_{0.97}$. The specific surface area (BET) of the catalyst sample is measured to $6.2 \text{ m}^2/\text{g}$ and its pore volume to $0.013 \text{ cm}^3/\text{g}$. The XRD data shows the presence of lanthanum oxychloride phases.

Example 2

15 The lanthanum oxychloride catalyst from Example 1 is used for the dehydration of phenol. The powder is pressed and sieved to obtain particles that are between 0.60 mm and 0.85 mm in diameter. The particles are loaded into an electrically heated stainless steel reactor tube and heated to the reaction temperature with nitrogen flowing through the tube. After the reaction temperature is reached, vapor-phase phenol is passed through the reactor
20 tube. The conversion of phenol is carried out at a weight hourly space velocity of 1 (WHSV=gram phenol/gram catalyst-hour) and at 500°C . Test conditions and results are shown in Table 1.

Table 1

Test Conditions	Conversion [mol. %]	Selectivity [mol. %]					
		Phenol	Diphenyl Oxide	OPP	DBF	O-BIPPE	M-BIPPE
T = 500 °C Feed: PhOH ToS = 1.5 hrs WHSV 1 hr ⁻¹	0.70%	95.86%	0.02%	4.12%	0.00%	0.00%	0.00%
T = 500 °C Feed: PhOH ToS = 2.75 hrs WHSV 1 hr ⁻¹	0.82%	95.83%	0.07%	4.09%	0.00%	0.00%	0.00%
T = 500 °C Feed: PhOH ToS = 3.75 hrs WHSV 1 hr ⁻¹	0.82%	95.90%	0.18%	3.93%	0.00%	0.00%	0.00%
T = 500 °C Feed: PhOH ToS = 7.5 hrs WHSV 1 hr ⁻¹	0.74%	95.70%	0.13%	4.17%	0.00%	0.00%	0.00%

OPP: orthophenylphenol

DBF: dibenzofuran

O-BIPPE: ortho-biphenylphenyl ether

M-BIPPE: meta-biphenylphenyl ether

P-BIPPE: para-biphenylphenyl ether

PhOH: phenol

N₂: nitrogen

ToS: time on stream (ToS=0 hours defined at start of phenol flow)

10 Example 3

A 1M LaCl₃ solution, prepared by dissolving 50.00 g LaCl₃ in 135 mL DI H₂O, is added dropwise over 15 min into a 2L flask equipped with an overhead stirrer and an initial 500 mL DI H₂O. The solution is stirred at 400 rpm with a 6 mm PTFE screw propeller blade. Approximately 182 mL of tetrapropylammonium hydroxide is added during the precipitation to keep the pH at a constant value of 9. The resulting white precipitate is allowed to age in solution for 1 h without stirring, after which time it is centrifuged at 7000 rpm for 5 min. The decanted precipitate is placed into an oven, dried at 120 °C for 4 h and calcined at 500 °C for 4 h with a ramp rate of 5 °C/min to give 23 g of product. Neutron activation analysis (NAA) reveals a total chlorine concentration of 5.8 wt%.

20 Example 4

Catalytic evaluation of the catalyst from Example 3 is carried out using a similar procedure as in Example 2. Test conditions and results are shown in Table 2.

Table 2

Test Conditions	Conversion [mol. %]	Selectivity [mol. %]					
		Phenol	Diphenyl Oxide	OPP	DBF	O-BIPPE	M-BIPPE
T = 500 °C Feed: PhOH ToS = 1 hr WHSV 1 hr ⁻¹	1.46%	82.41%	0.35%	16.74%	0.00%	0.22%	0.28%
T = 500 °C Feed: PhOH ToS = 2 hrs WHSV 1 hr ⁻¹	1.42%	84.03%	0.29%	15.69%	0.00%	0.00%	0.00%
T = 500 °C Feed: PhOH ToS = 3.5 hrs WHSV 1 hr ⁻¹	1.39%	84.69%	0.22%	14.93%	0.00%	0.00%	0.16%
T = 500 °C Feed: PhOH ToS = 5.75 hrs WHSV 1 hr ⁻¹	1.19%	86.49%	0.19%	13.32%	0.00%	0.00%	0.00%

Example 5

A 1M LaCl₃ solution, prepared by dissolving 55.70 g LaCl₃ in 150 mL DI H₂O, is added dropwise along with ammonium hydroxide (52.78 g) over 15 min into a 1L beaker containing an initial 100 mL DI H₂O. The solution is stirred at 500 rpm on magnetic stir plate with a 6 inch stir bar. The resulting white precipitate is allowed to age in solution for 1 h with stirring. The batch is split into two parts, one of which is centrifuged at 5000 rpm for 10 min. The decanted precipitate is placed into an oven, dried at 120 °C for 4 h and calcined at 500 °C for 4 h with a ramp rate of 5 °C/min. Neutron activation analysis reveals a total chlorine concentration of 16.3 wt%.

Example 6

Catalytic evaluation of the catalyst from Example 5 is carried out using a similar procedure as in Example 2. Test conditions and results are shown in Table 3.

Table 3

Test Conditions	Conversion [mol. %]	Selectivity [mol. %]					
		Phenol	Diphenyl Oxide	OPP	DBF	O-BIPPE	M-BIPPE
T = 500 °C Feed: PhOH ToS = 2 hrs WHSV 1 hr ⁻¹	0.74%	84.35%	0.04%	9.42%	0.00%	5.73%	0.47%
T = 500 °C Feed: PhOH ToS = 3.5 hrs WHSV 1 hr ⁻¹	0.71%	88.99%	0.46%	10.55%	0.00%	0.00%	0.00%
T = 500 °C Feed: PhOH ToS = 5 hrs WHSV 1 hr ⁻¹	0.67%	88.91%	0.94%	10.15%	0.00%	0.00%	0.00%
T = 500 °C Feed: PhOH ToS = 6.25 hrs WHSV 1 hr ⁻¹	0.64%	88.51%	0.22%	11.27%	0.00%	0.00%	0.00%

Example 7

A 1M PrCl₃ solution, prepared by dissolving 10 g PrCl₃ in 50 mL DI H₂O, is added dropwise along with tetrapropylammonium hydroxide (76.36 g) over 15 min into a 600 mL beaker containing an initial 100 mL DI H₂O. The solution is stirred at 500 rpm on magnetic stir plate with a 4.5 inch stir bar. The resulting green precipitate is allowed to age in solution for 1 h with stirring, after which it is centrifuged at 5000 rpm for 10 min. The decanted precipitate is placed into an oven, dried at 120 °C for 4 h and calcined at 500 °C for 4 h with a ramp rate of 5 °C/min to yield approximately 8 g of product. Neutron activation analysis reveals a total chlorine concentration of 1.17 wt%.

Example 8

Catalytic evaluation of the catalyst from Example 7 is carried out using a similar procedure as in Example 2. Test conditions and results are shown in Table 4.

Table 4.

Test Conditions	Conversion [mol. %]	Selectivity [mol. %]					
		Phenol	Diphenyl Oxide	OPP	DBF	O-BIPPE	M-BIPPE
T = 500 °C Feed: PhOH ToS = 1 hr WHSV 1 hr ⁻¹	2.63%	73.15%	1.94%	24.91%	0.00%	0.00%	0.00%
T = 500 °C Feed: PhOH ToS = 2 hrs WHSV 1 hr ⁻¹	2.75%	78.64%	2.16%	19.20%	0.00%	0.00%	0.00%
T = 500 °C Feed: PhOH ToS = 3.5 hrs WHSV 1 hr ⁻¹	3.70%	76.14%	1.92%	21.94%	0.00%	0.00%	0.00%
T = 500 °C Feed: PhOH ToS = 5.75 hrs WHSV 1 hr ⁻¹	2.28%	73.28%	3.58%	23.14%	0.00%	0.00%	0.00%

Example 9

A 1M NdCl₃ solution, prepared by dissolving 17.94 g NdCl₃ in 50 mL DI H₂O, is added dropwise along with tetrapropylammonium hydroxide (76.26 g, from a 40 wt% TPAOH solution) over 15 min into a 600 mL beaker containing an initial 100 mL DI H₂O. The solution is stirred at 500 rpm on magnetic stir plate with a 3 inch stir bar. The resulting precipitate is allowed to age in solution for 1 h with stirring, after which it is centrifuged at 5000 rpm for 10 min. The decanted precipitate is placed into an oven, dried at 120 °C for 4 h and calcined at 500 °C for 4 h with a ramp rate of 5 °C/min to yield approximately 8 g of product. Neutron activation analysis reveals a total chlorine concentration of 5.8 wt%.

Example 10

Catalytic evaluation of the catalyst from Example 9 is carried out using a similar procedure as in Example 2. Test conditions and results are shown in Table 5.

Table 5.

Test Conditions	Conversion [mol. %]	Selectivity [mol. %]					
		Phenol	Diphenyl Oxide	OPP	DBF	O-BIPPE	M-BIPPE
T = 500 °C Feed: PhOH ToS = 1.75 hrs WHSV 1 hr ⁻¹	1.32%	37.89%	3.84%	56.56%	0.00%	0.21%	1.50%
T = 500 °C Feed: PhOH ToS = 2.75 hrs WHSV 1 hr ⁻¹	0.71%	37.84%	5.95%	51.32%	0.00%	0.38%	4.51%
T = 500 °C Feed: PhOH ToS = 4 hrs WHSV 1 hr ⁻¹	0.71%	52.64%	6.67%	40.37%	0.00%	0.00%	0.32%

Example 11

The synthesis of supported lanthanum oxychloride is carried out via an incipient wetness impregnation of amorphous silica.

Precursors:

Support: amorphous silica (WR Grace-Davison 57, 30 – 60 mesh size, BET = 275.3 m²/g) that exhibits an incipient wetness condition of approximately 0.90 mL per 1 g.

Solution: lanthanum(III) chloride heptahydrate (LaCl₃·7 H₂O) and deionized water (DI water), prepared to c = 1.25 mol/L.

Synthesis:

4.5 mL of the solution is added dropwise to 5 g of the support at ambient conditions under vigorous shaking using a shaker plate. The impregnated material is then dried at 150 °C for 1 h, and the preparation is finished off by calcining the impregnated material in a static air calcination oven using the following protocol: ramp 1 °C/min; dwell at T = 550°C for 3 hrs, cool down to room temperature. The chlorine content of the catalyst is assayed by XRF to 3.43 wt.% chlorine.

Example 12

Catalytic evaluation of the catalyst from Example 11 is carried out using a similar procedure as in Example 2. Test conditions and results are shown in Table 6.

Table 6.

Test Conditions	Conversion [mol. %]	Selectivity [mol. %]					
		Phenol	Diphenyl Oxide	OPP	DBF	O-BIPPE	M-BIPPE
T = 500 °C Feed: PhOH ToS = 1 hr WHSV 1 hr ⁻¹	0.55%	84.35%	0.04%	15.13%	0.00%	0.00%	0.47%
T = 500 °C Feed: PhOH ToS = 3 hrs WHSV 1 hr ⁻¹	0.46%	85.72%	0.94%	13.34%	0.00%	0.00%	0.00%
T = 500 °C Feed: PhOH ToS = 5 hrs WHSV 1 hr ⁻¹	0.44%	86.58%	1.04%	12.38%	0.00%	0.00%	0.00%
T = 500 °C Feed: PhOH ToS = 7 hrs WHSV 1 hr ⁻¹	0.46%	86.11%	0.28%	13.61%	0.00%	0.00%	0.00%

Example 13

The synthesis of supported lanthanum oxychloride is carried out via an incipient wetness impregnation of amorphous silica coated with magnesia.

Precursors:

Support: the parent amorphous silica (WR Grace-Davison 57, 30 – 60 mesh size, BET = 275.3 m²/g) that exhibits an incipient wetness condition of approximately 0.90 mL per 1 g is treated with a solution of magnesium nitrate (c = 1 mol/L) and calcined in a static air calcination oven under temperature programmed conditions (ramp 5°C/min, dwell 3 hrs 600 °C, cool down) to produce magnesia coated amorphous silica characterized by BET = 212 m²/g and Mg-loading of 6.41 wt.%.

Solution: lanthanum(III) chloride heptahydrate (LaCl₃·7 H₂O) and deionized water (DI water), prepared to c = 1.25 mol/L.

15 *Synthesis:*

4.5 mL of the solution is added dropwise to 5 g of the support at ambient conditions under vigorous shaking using a shaker plate. The impregnated material is then dried at 150 °C for 1 h, and the preparation is finished off by calcining the impregnated material in a static air calcination oven using the following protocol: ramp 1 °C/min; dwell at T = 550 °C for 3 hrs, cool down to room temperature. The chlorine content of the catalyst is assayed by XRF to 6.47 wt.% chlorine.

Example 14

Catalytic evaluation of the catalyst from Example 13 is carried out using a similar procedure as in Example 2. Test conditions and results are shown in Table 7.

5 Table 7.

Test Conditions	Conversion [mol. %]	Selectivity [mol. %]					
		Phenol	Diphenyl Oxide	OPP	DBF	O-BIPPE	M-BIPPE
T = 500 °C Feed: PhOH ToS = 1 hr WHSV 1 hr ⁻¹	1.25%	77.40%	2.47%	19.87%	0.00%	0.00%	0.26%
T = 500 °C Feed: PhOH ToS = 3 hrs WHSV 1 hr ⁻¹	1.43%	76.56%	0.99%	22.15%	0.00%	0.00%	0.31%
T = 500 °C Feed: PhOH ToS = 5 hrs WHSV 1 hr ⁻¹	0.90%	78.01%	2.41%	19.01%	0.00%	0.00%	0.58%
T = 500 °C Feed: PhOH ToS = 7 hrs WHSV 1 hr ⁻¹	1.03%	78.24%	2.23%	19.19%	0.00%	0.00%	0.34%

Example 15

The synthesis of supported lanthanum oxychloride is carried out via an incipient wetness impregnation of gamma alumina.

Precursors:

Support: gamma alumina (Saint-Gobain NorPro, 30 – 60 mesh size, BET = 178.9 m²/g) that exhibits an incipient wetness condition of approximately 0.75 mL per 1 g.

Solution: lanthanum(III) chloride heptahydrate (LaCl₃·7 H₂O) and deionized water (DI water), prepared to c = 0.75 mol/L.

Synthesis:

3.75 mL of the solution is added dropwise to 5 g of the support at ambient conditions under vigorous shaking using a shaker plate. The impregnated material is then dried at 150 °C for 1 h, and the impregnation procedure repeated three more times (total of 4 x 3.75 mL used for 5 g of carrier) to achieve a high loading of lanthanum inside the pores of the carrier. The preparation is finished off by calcining the impregnated material in a static air calcination oven using the following protocol: ramp 1 °C/min; dwell at T = 550 °C

for 3 hrs, cool down to room temperature. The chlorine content of the catalyst is assayed by XRF to 5.85 wt.% chlorine.

Example 16

Catalytic evaluation of the catalyst from Example 15 is carried out using a similar procedure as in Example 2. Test conditions and results are shown in Table 8.

Table 8

Test Conditions	Conversion [mol. %]	Selectivity [mol. %]					
		Diphenyl Oxide	OPP	DBF	O-BIPPE	M-BIPPE	P-BIPPE
T = 500 °C Feed: PhOH ToS = 1 hr WHSV 1 hr ⁻¹	5.28%	88.71%	0.06%	11.23%	0.00%	0.00%	0.00%
T = 500 °C Feed: PhOH ToS = 2 hrs WHSV 1 hr ⁻¹	4.94%	88.01%	1.41%	10.57%	0.00%	0.00%	0.00%
T = 500 °C Feed: PhOH ToS = 3.25 hrs WHSV 1 hr ⁻¹	4.54%	91.87%	0.58%	7.55%	0.00%	0.00%	0.00%
T = 500 °C Feed: PhOH ToS = 4.5 hrs WHSV 1 hr ⁻¹	4.53%	92.76%	1.16%	6.09%	0.00%	0.00%	0.00%

Example 17

A preparation of a lanthanum oxychloride sample is accomplished by setting up a 2-
 10 L 3-necked flask with two air-tight addition funnels, pH meter, and argon bubbling into 750 ml of DI H₂O at a flow rate of 300 sccm. After purging with argon, an aqueous solution of LaCl₃, prepared by dissolving 61.3 g LaCl₃ in 165 mL DI H₂O, is added dropwise over 0.5 hours along with a controlled addition of aqueous ammonia to maintain the pH constant at 9. The resulting suspension is added to a nitrogen purged centrifuge container, capped, and
 15 centrifuged to separate the white precipitate from the solution. The liquid is poured off and the containers are placed in a vacuum oven at 80 °C for 16 hours. The dried sample is transferred into a purged quartz tube within a tube furnace where it is treated in flowing 1% oxygen in helium mixture for 5 minutes at room temperature, thermally treated at 500 °C for 3 h, and then cooled to room temperature in flowing nitrogen.

Example 18

Catalytic evaluation of the catalyst from Example 17 is carried out using a similar procedure as in Example 2. Test conditions and results are shown in Table 9.

Table 9

Test Conditions	Conversion [mol. %]	Selectivity [mol. %]					
		Diphenyl Oxide	OPP	DBF	O-BIPPE	M-BIPPE	P-BIPPE
T = 500 °C Feed: PhOH ToS = 1.75 hrs WHSV 1 hr ⁻¹	4.27%	94.18%	1.12%	4.70%	0.00%	0.00%	0.00%
T = 500 °C Feed: PhOH ToS = 3 hrs WHSV 1 hr ⁻¹	4.02%	93.96%	0.44%	5.51%	0.00%	0.00%	0.08%
T = 500 °C Feed: PhOH ToS = 4 hrs WHSV 1 hr ⁻¹	3.67%	94.21%	0.85%	4.94%	0.00%	0.00%	0.00%
T = 500 °C Feed: PhOH ToS = 5 hrs WHSV 1 hr ⁻¹	3.69%	94.40%	1.10%	4.51%	0.00%	0.00%	0.00%

5 Example 19

Preparation of 12 wt% La supported on ZrO₂ via incipient wetness impregnation.

Prior to the impregnation process, a hydrous ZrO₂ support with BET surface area of 323 m²/g is pre-dried at 120 °C for 4 hours in static air. 12 wt% La on ZrO₂ catalyst is prepared by two-step incipient wetness impregnation of the treated ZrO₂ at ambient
 10 temperature. A glass beaker is charged with 5 g of pre-dried ZrO₂. A 10-ml graduated cylinder is loaded with a 0.8049 g of LaCl₃·7 H₂O to yield 6 wt% of La and with 1.2 ml of H₂O. The support is impregnated with aqueous solution being added to the ZrO₂ in small fractions. After each addition, the support is agitated to break up clumps and uniformly
 15 disperse lanthanum throughout the carrier material. After the first step impregnation, the sample is dried at 110 °C for 4 hours. In the next step the whole process is repeated using 0.7994 g of LaCl₃·7H₂O to again yield 6 wt% of La with 1.2 ml of H₂O. The impregnated sample is then treated at 110 °C for 4 hours in flowing air and then at 600 °C for an additional 4 hours at 5 °C/min ramp.

Example 20

Catalytic evaluation of the catalyst from Example 19 is carried out using a similar procedure as in Example 2. Test conditions and results are shown in Table 10.

Table 10

Test Conditions	Conversion [mol. %]	Selectivity [mol. %]					
		Diphenyl Oxide	OPP	DBF	O-BIPPE	M-BIPPE	P-BIPPE
T = 500 °C Feed: PhOH ToS = 1.5 hrs WHSV 1 hr ⁻¹	3.15%	94.60%	0.49%	4.06%	0.00%	0.40%	0.46%
T = 500 °C Feed: PhOH ToS = 2.5 hrs WHSV 1 hr ⁻¹	2.71%	94.81%	0.62%	3.78%	0.00%	0.43%	0.37%
T = 500 °C Feed: PhOH ToS = 3.75 hrs WHSV 1 hr ⁻¹	2.56%	94.56%	1.03%	3.76%	0.00%	0.36%	0.30%
T = 500 °C Feed: PhOH ToS = 5.5 hrs WHSV 1 hr ⁻¹	2.54%	95.04%	0.30%	4.10%	0.00%	0.33%	0.23%

5

We claim:

1. A method for preparing a diaryl ether, the method comprising dehydrating an aromatic alcohol compound over a dehydration catalyst, wherein the dehydration catalyst is an oxide of a light rare earth element.
- 5 2. The method of claim 1 wherein the dehydration catalyst further comprises a halogen.
3. The method of claim 2 wherein the halogen is chloride or fluoride ion.
4. The method of any one of claims 1-3 wherein the dehydration catalyst further comprises a binder.
5. The method of any one of claims 1-4 wherein the dehydration catalyst is supported.
- 10 6. The method of any one of claims 1-4 wherein the dehydration catalyst is unsupported.
7. The method of any one of claims 1-6 wherein the dehydration of the alcohol is conducted at a temperature from 250 to 600 °C.
8. The method of any one of claims 1-7 wherein the alcohol feed is diluted with a
15 diluent.
9. The method of any one of claims 1-8 wherein the aromatic alcohol compound is phenol and the diaryl ether produced is diphenyl oxide.
10. A method for producing a heat transfer fluid, the method comprising:
preparing a diaryl ether by contacting an aromatic alcohol compound with a
20 dehydration catalyst, wherein the dehydration catalyst is an oxide of a light rare earth element;
isolating the diaryl ether from the dehydration catalyst; and
mixing the isolated diaryl ether with biphenyl, wherein the mixture forms a eutectic mixture.

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2013/043091

A. CLASSIFICATION OF SUBJECT MATTER
INV. C07C41/09 B01J23/10
ADD.
According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED
Minimum documentation searched (classification system followed by classification symbols)
C07C B01J
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)
EPO-Internal, WPI Data, CHEM ABS Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 584 415 A1 (UOP INC [US]) 2 March 1994 (1994-03-02) Examples; claim 1 -----	1,4-10
X	EP 0 317 208 A2 (AMOCO CORP [US]) 24 May 1989 (1989-05-24) claim 1; examples 11-23 -----	1,4-10
A	US 3 922 331 A (MACDONALD DAVID J ET AL) 25 November 1975 (1975-11-25) column 1, line 46 - line 50 -----	1-10
A	WO 02/060818 A1 (RHODIA ELECTRONIC & CATALYSIS INC) 8 August 2002 (2002-08-08) claim 20 -----	1-10
	-/--	

Further documents are listed in the continuation of Box C.

See patent family annex.

* Special categories of cited documents :

<p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier application or patent but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p>	<p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</p> <p>"&" document member of the same patent family</p>
---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------	-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

Date of the actual completion of the international search 2 September 2013	Date of mailing of the international search report 11/09/2013
--------------------------------------------------------------------------------------	-------------------------------------------------------------------------

Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer Fritz, Martin
----------------------------------------------------------------------------------------------------------------------------------------------------------------------	--------------------------------------------

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2013/043091

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 00/15730 A1 (DAMIANI ROBERT A [US]; DAMIANI MICHAEL R [US]) 23 March 2000 (2000-03-23) the whole document	10
A	----- US 4 156 698 A (DWYER FRANCIS G [US] ET AL) 29 May 1979 (1979-05-29) Paragraph "Summary of invention" -----	1-10

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No PCT/US2013/043091

Patent document cited in search report	Publication date	Patent family member(s)	Publication date	
EP 0584415	A1	02-03-1994	CA 2077207 A1 EP 0584415 A1	01-03-1994 02-03-1994
EP 0317208	A2	24-05-1989	EP 0317208 A2 JP H01165540 A US 4898982 A	24-05-1989 29-06-1989 06-02-1990
US 3922331	A	25-11-1975	NONE	
WO 02060818	A1	08-08-2002	FR 2820134 A1 WO 02060818 A1	02-08-2002 08-08-2002
WO 0015730	A1	23-03-2000	AU 5549599 A CA 2344276 A1 EP 1114114 A1 MX PA01002760 A TW 495546 B WO 0015730 A1	03-04-2000 23-03-2000 11-07-2001 24-04-2002 21-07-2002 23-03-2000
US 4156698	A	29-05-1979	DE 2818831 A1 DE 2857758 C2 US 4156698 A	16-11-1978 22-01-1987 29-05-1979