

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
26 June 2008 (26.06.2008)

PCT

(10) International Publication Number  
**WO 2008/076785 A1**

- (51) **International Patent Classification:**  
*B41M 3/00* (2006.01)      *B41M 7/00* (2006.01)  
*B41M 3/14* (2006.01)      *G03H 1/02* (2006.01)
- (21) **International Application Number:**  
PCT/US2007/087348
- (22) **International Filing Date:**  
13 December 2007 (13.12.2007)
- (25) **Filing Language:** English
- (26) **Publication Language:** English
- (30) **Priority Data:**  
60/869,983      14 December 2006 (14.12.2006)      US
- (71) **Applicant (for all designated States except US):** COLGATE-PALMOLIVE COMPANY [US/US]; 300 Park Avenue, New York, NY 10022 (US).
- (72) **Inventor; and**
- (75) **Inventor/Applicant (for US only):** SARNATARO, John, A. [US/US]; 3 Earl Gate, Melville, NY 11747 (US).
- (74) **Agent:** WALLACE, Michael; Colgate-palmolive Company, 909 River Road, Po Box 1343, Piscataway, NJ 08854 (US).
- (81) **Designated States (unless otherwise indicated, for every kind of national protection available):** AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.
- (84) **Designated States (unless otherwise indicated, for every kind of regional protection available):** ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:**  
— with international search report  
— before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments



WO 2008/076785 A1

(54) **Title:** A HOLOGRAM APPEARING PACKAGE IMAGE

(57) **Abstract:** A package that has at least one hologram on its exterior surface is formed from a paper, paperboard or thermoplastic substrate material that has an inner surface and an outer surface. The outer surface has a radiation curable particulate metal containing coating. This coating is cured and zero to one or more ink containing coatings are applied to the radiation curable particulate metal containing coating in areas that are not to have a hologram. Each of these ink containing coatings are cured, and a substantially transparent radiation curable coating is applied to the areas deficient in the zero to one or more ink coatings. This substantially transparent radiation curable coating is contacted with a substantially transparent holographic shim in an area not having thereon ink containing coatings while curing radiation is applied to the substantially transparent radiation curable coating and the substantially transparent shim.

## TITLE OF THE INVENTION

## A HOLOGRAM APPEARING PACKAGE IMAGE

[0001] This invention is directed to a package that has a type of hologram image on at least a part of its exterior surface, and the process to produce this hologram image that has on the exterior surface of a package. More particularly, this invention is directed to producing a hologram image on paper, paperboard, plastics and related substrates that can be used to package products.

## BACKGROUND OF THE INVENTION

[0002] Holograms have been used to enhance the appearance of packages for many years. They have been formed on labels and substrates that are applied to and are used as a layer on the surface of packages, such as cartons. However, the conventional hologram image on packages is expensive and usually requires the production of a hologram containing laminate film and the bonding of this film to a package surface. This requires several processing steps and costly materials. It would be more efficient and less costly to form the hologram on the packaging material in line with the printing of other image and information onto the packaging material.

[0003] In U.S. Patent 5,889,598 there is disclosed the printing of a hologram onto a surface followed by the printing of another image onto the same surface. The hologram design is embossed onto the surface followed by a metallizing of the hologram design surface, in turn followed by the cutting of the surface into sheets for subsequent printing of other image and information. This process requires the subsequent metallizing of the embossed hologram design. This metallizing is by a relatively slow vapor deposition process. U.S. Patent 5,003,915 discloses the forming of a hologram directly onto the desired end product paper or other sheet material. However, after the embossing of a hologram design there is a required step of metallizing the hologram surface. This could be by vapor deposition to produce a reflective film or refractive layer onto the hologram. A protective layer can be coated over this hologram. U.S. Patent 6,979,487 discloses the printing of textured pattern over a substrate. A reflective ink or foil can be deposited or laminated onto this textured pattern layer. This produces an effect of depth and

dimensionality. This is interesting but does not disclose the production of a hologram. This process would be inoperable to produce a holographic image. U.S. Patent 6,638,386 discloses the technique of forming a holographic image or a diffraction grating image onto a composite sheet and the subsequent attachment of this sheet to a substrate. This involves the operation of separately forming the hologram on a composite sheet and applying this composite sheet onto a substrate to produce the finished hologram on a package or other item. All of these processes have the differing drawbacks. However, all are less efficient than the holograms on a package surface produced by the present processes.

[0004] The present processes produce a hologram image directly on the package surface solely through printing steps. Further, no subsequent metallizing steps are required. Such steps which usually involve the vapor deposition of a metal, such as aluminum, onto a hologram surface are relatively slow as compared to printing techniques and require specialized equipment. In the present processes a hologram image is produced on a substrate solely through the use of printing techniques and equipment.

#### BRIEF SUMMARY OF THE INVENTION

[0005] The present invention comprises a hologram image directly on packaging material, and the process to produce this hologram image directly on the packaging material. The process comprises having a paper, paperboard or plastic surface, which in one embodiment can be a substantially white paperboard surface, coating onto at least a part of this surface a polymeric radiation curable coating that contains a particulate metal component, curing this polymeric radiation curable coating, coating the cured polymeric radiation curable coating containing the particulate metal with a radiation curable and substantially transparent polymer coating, contacting this radiation curable substantially transparent coating with the negative of a hologram on a shim, and at least partially curing the radiation curable coating while the shim carrying the negative of the hologram is in contact with this coating. The combination of these two coatings and the negative of the hologram produce a hologram image in the areas where there also is an underlying

particulate metal coating. An effective hologram image is formed by the technique of at least partially curing the substantially transparent radiation curable coating while the shim is in contact with this coating.

[0006] In a preferred embodiment a substantially white paperboard stock comprising blanks for the production of carton comprising a blank for the production of cartons is in a first step coated over at least a part of its surface with a coating that contains a particulate metal, this coating is cured, one or more image and/or information layers are then coated onto the cured particulate metal coated layer and each cured, coating these image and/or in formation layers with a substantially transparent radiation curable coating, and contacting this substantially transparent radiation curable coating with a shim that contains the negative of a hologram, and at least partially curing the radiation curable coating while the shim is in contact with the radiation curable coating. In this preferred embodiment the coatings are applied to the paperboard stock using printing techniques. A preferred technique is the use of flexographic printing. However, other commercially available printing techniques and equipment can be used.

[0007] After the paper or paperboard stock has been printed and contains the hologram it is finished by forming it into a package. The paper or paperboard stock usually will be in the form of a continuous sheet. The paper or paperboard stock can be use directly to make packages or it can be formed into cartons. To make cartons the continuous sheet will be formed into individual carton blanks. The carton blanks are shipped to the place where a product is to be packaged and placed in the magazine of a carton making and filling machine. The cartons containing a product are filled with a product, sealed and then usually placed in corrugated shipping cartons.

#### DETAILED DESCRIPTION OF THE INVENTION

[0008] The invention will be described now in more detail in its preferred embodiments. Modifications can be made to the hologram materials and the processes of their manufacture, however all such materials and processes will be within the concepts disclosed herein.

[0009] The substrate material on which the hologram is formed, is in the preferred

embodiments, a paper material which includes various grades of paper and paperboard. However, plastics and other substrate materials can be used. When a paper, the paper material in this preferred embodiment will have a thickness of about .001 inch (.00254 cm) to about .005 inch (.0127 cm), and when a paperboard will have a thickness of about .010 inch (.0254 cm) to about .050 inch (.127 cm). Plastics and other substrate materials will have a range of thicknesses. The substrate material can be of essentially any color or hue. However, it is preferred that the substrate material be from a brown paperboard color to white. If white the whiteness of the substrate material preferably will be about TAPPI Whiteness of about 70 or better and preferably about 75 to 95. The substrate material can be a CCNB (Clay Coated News Back) recycled paperboard or an SBS (Solid Bleach White Sulfate) virgin paperboard. White or lightly colored substrate materials are preferred. The preferred processes for forming the hologram on the substrate material are printing processes such as flexographic printing processes. Flexographic printing processes have been found to be very useful. In this process the substrate material is fed to a set of rolls, usually the first set of rolls, which will coat the substrate material with a radiation curable thermoplastic polymer composition containing a particulate metal having a particle size of about 5 to 40 microns, and preferably about 10 to 25 microns. The useful particulate metals include aluminum, silver and zinc. These are applied using a solvent/polymer carrier mixture. Useful coating compositions are ULTRASTAR UV FP-8209 flexo silver having a particulate metal content of 3.25% applied using a 200 to 300 analox flexo roller. Another useful coating composition is ULTRASTAR UV SP-8700 screen print silver having a pigment content of 2.5% applied using a Rotomesh 150 to 250 line mesh screen. The analox flexo roller will deposit a wet polymer film coating of about 2 to 12 microns while the Rotomesh screen will deposit a wet polymer film coating of about 12 to 20 microns. In general a wet film coating of about 1 to 40 microns will be useful. The viscosity of the polymer coating products will be about 150 to 350 cps. The ULTRASTAR products are available from Eckhart America LP of Painsville, Ohio. This coating can be over the entire surface of the substrate material, but for reasons of economy it only will be in the areas that are to contain a hologram. This usually will be less than 50% of the

substrate material surface.

[00010] Prior to the application of the radiation curable thermoplastic containing the particulate metal, a primer can be applied to the material substrate which usually will be a paper or a paperboard. This will seal the substrate material and provide a better base for the radiation curable thermoplastic polymer containing the particulate metal. This primer coating can be a water based acrylic lacquer. Also useful in place of a primer is a lamination of a polyethylene terephthalate (PET) film which can have a white surface of a TAPPI Whiteness of about 75 to 95.

[00011] After the application and radiation curing of the radiation curable thermoplastic polymer containing the particulate metal the substrate can be printed with image and information material. The radiation curing usually will be through the use of commonly used 300 watt ultraviolet lamps. They will be chosen emit a range of wavelengths depending on the polymers to be set. Electron beam radiation also can be used. However, ultraviolet radiation is preferred. The printing with image and information material, if to be used, usually will be in a number of printing steps since different printing rolls will be required for each image color. The inks used will preferably be ultraviolet curing inks which can be cured within seconds using 300 watt ultraviolet lamps. The substrate material is not printed with image and information material in the areas where there is to be a hologram. The cured metal coating will be exposed in these areas. This is needed for the application of an effective hologram in a subsequent step.

[00012] In a next step the substrate material with the above cured coatings is coated with a substantially transparent radiation curable coating. This preferably is a high gloss coating and is 100% radiation curable. The viscosity will be in the range of about 150 to 350 cps. The application weight is about .04 lbs (18.1gms.) to about .12 lbs (54.4 gms) per 1000 square feet (93 sq.m). A useful coating material is CORKCURE 1093RHG-10 from Cork Industries, Inc. in Foxcroft, Pennsylvania. This is an ultra high gloss, solvent-less coating for lithographic and flexographic coating equipment. It is a 100% ultraviolet radiation curable coating having a viscosity of 210(+/- 20) cps. It is applied to the

substrate material at a last set of flexographic rolls. It is applied at a weight of .06 lbs (27.2 gms.) to .09 lbs (41 gms) per 1000 square feet (93 sq.m). It is curable at 150 feet per minute using a 300 watt ultraviolet source. Just subsequent to the substrate material being coated, and prior to the coating being cured, the coating is contacted with the negative of a hologram. This negative of a hologram is a micro-grid which is on a shim that is a part of the flexographic roll, which usually is the final roll. There can be more than one shim. The shim is a substantially transparent plastic, such as a thermoplastic. A useful material for the shim is polypropylene. However, other substantially transparent polymeric materials such as polyethylene terephthalate can be used. The substantially transparent radiation curable coating is at least partially cured when the shim is in contact with this coating, with the curing bring completed just after contact with this coating. There can be a protective coating over the coating containing the hologram as long as the hologram is not affected.

[00013] Assuming that the coated and hologram containing substrate material is to be used to make packaging cartons the decorative substrate material from the printing operations is then fed to a carton blank forming machine. This machine forms carton blanks by cutting the substrate material to length and trimming the edges to form the foldable flaps. Weakened fold points to fold the panels and end foldable flaps into a carton also are formed. The foldable flaps form the ends of the carton. These carton blanks can be loaded into the magazine of a carton forming machine which is in-line with the equipment making the primary package that is to be packaged in the carton. The primary package can be a tube, bottle or any other container, or the product itself if the product is a solid. This has been found to be useful in the packaging of dentifrice products.

[00014] The primary system for UV curing is based on acrylate polymers and monomers and cured through free radical polymerization. The acrylate polymers and monomers are high boiling which reduces VOC contamination. These systems include pigments, oligomers, reactive acrylated resins, monomers that usually are multifunctional, photoinitiators and additives. The UV energy is absorbed by the

photoinitiators to produce free radicals which in turn initiate the polymerization of the acrylate polymers and monomers. Useful photoinitiators include benzoin derivatives, benzil ketals, acetophenone derivatives and benzophenone. The particular acrylate systems are chosen for a particular process depending on the compatibility with other components, the speed of the cure needed, cost, and end product appearance. Useful systems for UV curing utilizing acrylate chemistry are disclosed U.S. Patent 3,418,292, which is incorporated herein in its entirety by reference. Cationic curing systems also can be used. These are based on vinyl ethers and epoxy resins for the oligomers, reactive resins, and monomers. However systems based on acrylate chemistry are preferred.

**[00015]** Another system that can be used is electron beam curing. The compositions for electron beam curing are based on acrylate chemistry similar to the free radical induced polymerization compositions. The primary difference is that a photoinitiator is not used. The electron beam causes the acrylate double bonds to directly cleave forming free radicals which initiate the polymerization. Although fast curing and have a low odor there is the processing drawback in that the curing must be done in an oxygen free atmosphere. Oxygen inhibits free radical formation. This requires the use of an inert gas. Electron beam systems are disclosed in U.S. Patent 3,948,739, which is incorporated herein in its entirety by reference.



## CLAIMS

1. A carton blank having a hologram comprising a substrate material having an inner surface and an outer surface, the outer surface having a particulate metallic coating over up to about 100% of its surface; from zero to one or more ink coatings over a portion of the metallic surface, and a substantially transparent radiation curable coating over the zero to one or more ink coatings, a hologram formed in the radiation curable coating in an area with an exposed underlying metallic coating as the radiation curable coating is being cured.
2. A decorated carton blank as in claim 1 wherein the substrate material is selected from the group consisting of a paper, paperboard or thermoplastic.
3. A decorated carton blank as in claim 2 wherein the substrate material has a substantially white surface.
4. A decorated carton blank as in claim 2 wherein the metallic surface is a metallic coating and contains a metal selected from the group consisting of aluminum, silver and zinc.
5. A decorated carton blank as in claim 1 wherein the metallic coating is a radiation curable thermoplastic coating.
6. A decorated carton blank as in claim 5 wherein the metallic coating is ultraviolet energy curable.
7. A decorated carton blank as in claim 5 wherein the metallic coating is electron beam curable.

8. A decorated carton blank as in claim 1 wherein the substantially transparent radiation curable coating is ultraviolet energy curable.

9. A decorated carton blank as in claim 5 wherein the substantially transparent radiation coating is electron beam curable.

10. A method of making a decorated package comprising providing a material substrate having an inner and an outer surface, the outer surface to form the outer surface of a carton, coating up to about 100% of the outer surface with a radiation curable coating containing a particulate metal, curing the radiation curable coating containing the particulate metal coating by contacting the radiation curable coating containing the particulate metal coating with radiation, applying zero to one or more ink containing coatings to a substantial portion of the radiation curable coating containing the particulate metal, excluding an area that is to contain a hologram, curing the one or more ink containing coatings, applying a substantially transparent radiation curable coating to the surface of the one or more ink containing coatings, and contacting the substantially transparent radiation curable coating with at least one shim containing a negative of a hologram image in an area not having one or more ink containing coatings, and at least partially curing the substantially transparent coating while the at least one shim is in contact with the substantially transparent coating to form the hologram image in the material substrate.

11. A decorated package as in claim 10 wherein the at least one shim is substantially transparent.

12. A decorated package as in claim 10 wherein the material substrate is selected from the group consisting of paper and paperboard.

13. A decorated package as in claim 12 wherein the paper material has a

substantially white outer surface.

14. A decorated package as in claim 12 wherein the metallic surface is a metallic coating and contains a metal selected from the group consisting of aluminum, silver and zinc.

15. A decorated package as in claim 10 wherein the metallic coating is a radiation curable thermoplastic coating.

16. A decorated package as in claim 14 wherein the metallic coating is ultraviolet energy curable.

17. A decorated package as in claim 15 wherein the metallic coating is electron beam curable.

18. A decorated package as in claim 10 wherein the substantially transparent radiation curable coating is ultraviolet energy curable.

19. A decorated package as in claim 10 wherein the substantially transparent radiation coating is electron beam curable.

20. A decorated package as in claim 10 wherein the package is a carton and the material substrate is formed into carton blanks.

21. A decorated package as in claim 20 the carton is formed from the carton blanks by forming the carton blank into a top panel, a bottom panel and two connecting side panels, each of the top panel, bottom panel and side panels having attached end flaps, folding the top panel, the bottom panel and the connecting side panels to form a tubular structure, folding over the end flaps to form the carton.

# INTERNATIONAL SEARCH REPORT

International application No  
PCT/US2007/087348

**A. CLASSIFICATION OF SUBJECT MATTER**

INV. B41M3/00 B41M3/14 B41M7/00 G03H1/02

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)

B41M G03H B42D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 98/18635 A (DITTLER BROTHERS INC [US]) 7 May 1998 (1998-05-07)	1-4,8
A	page 2, line 27 - page 3, line 12 page 4, line 5 - page 7, line 10	5-7,9-21
X	EP 1 632 362 A (DAINIPPON PRINTING CO LTD [JP]) 8 March 2006 (2006-03-08)	1-4,8
A	paragraphs [0004], [0033] - [0041] figure 1	5-7,9-21
X	WO 98/41904 A (METALLIZED PRODUCTS INC [US]; DELANEY WILLIAM [US]; HOVASSE RICHARD [U]) 24 September 1998 (1998-09-24)	1-3,8
A	page 3, lines 22-27 page 6, line 15 - page 8, line 25 page 9, lines 24-27 page 10, line 8 - page 11, line 5	4-7,9-21
	-/--	

Further documents are listed in the continuation of Box C.

See patent family annex.

\* Special categories of cited documents :

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*Z\* document member of the same patent family

Date of the actual completion of the international search

16 April 2008

Date of mailing of the international search report

07/05/2008

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Patosuo, Susanna

## INTERNATIONAL SEARCH REPORT

International application No

PCT/US2007/087348

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 95/26872 A (NOVAVISION INC [US]) 12 October 1995 (1995-10-12)	1-3,8
A	page 1, lines 29-31 page 2, lines 10-21 page 3, line 22 - page 4, line 15 page 5, lines 11-30 page 6, line 20 - page 7, line 3 page 8, line 29 - page 9, line 31 page 11, line 25 - page 12, line 6 figure 3	4-7,9-21
X	US 6 979 487 B2 (SCARBOROUGH JOEL SCOTT [US] ET AL SCARBROUGH JOEL SCOTT [US] ET AL) 27 December 2005 (2005-12-27) cited in the application	1-3,8
A	column 2, lines 23-57 column 3, line 31 - column 4, line 42	4-7,9-21
X	JP 58 132271 A (DAINIPPON PRINTING CO LTD) 6 August 1983 (1983-08-06)	1
A	abstract	2-21
P,X	WO 2006/132919 A (HOLOINKS INC [US]; LIEBERMAN DANIEL [US]) 14 December 2006 (2006-12-14) page 8, lines 19-22 page 9, lines 3-7 page 12, lines 22-35 page 13, line 31 page 13, line 33 - page 15, line 4 figures 5,6	1-20
A	WO 2005/051675 A (PRINTETCH LTD [GB]; BOSWELL DAVID [GB]; DICKER MARK [GB]; WINTON STEVE) 9 June 2005 (2005-06-09) page 10 - page 14 examples 1,2	1-21
A	EP 0 677 400 A (DAINIPPON PRINTING CO LTD [JP]) 18 October 1995 (1995-10-18) page 3, lines 30-57 page 4, line 54 - page 5, line 10 page 5, line 50 - page 6, line 7 page 7, lines 1,14-56 figure 2	1-21
A	EP 1 527 902 A (GIESECKE & DEVRIENT GMBH [DE]) 4 May 2005 (2005-05-04) paragraphs [0011] - [0021], [0033], [0034]	1-21

## INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2007/087348

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9818635	A	07-05-1998	AU 4918297 A US 5981040 A	22-05-1998 09-11-1999
EP 1632362	A	08-03-2006	AU 2004245390 A1 JP 2004361622 A WO 2004108433 A1 US 2006127623 A1	16-12-2004 24-12-2004 16-12-2004 15-06-2006
WO 9841904	A	24-09-1998	AU 3705397 A CA 2283766 A1 EP 0983534 A1 JP 2001519919 T US 6358442 B1	12-10-1998 24-09-1998 08-03-2000 23-10-2001 19-03-2002
WO 9526872	A	12-10-1995	AU 688874 B2 AU 1926895 A CA 2185358 A1 EP 0754120 A1 JP 9508722 T KR 100221670 B1 NZ 282221 A US 5464690 A US 5674580 A US 5670003 A US 5759683 A US 5643678 A	19-03-1998 23-10-1995 12-10-1995 22-01-1997 02-09-1997 15-09-1999 27-04-1998 07-11-1995 07-10-1997 23-09-1997 02-06-1998 01-07-1997
US 6979487	B2	27-12-2005	US 2006019074 A1 US 2003211295 A1	26-01-2006 13-11-2003
JP 58132271	A	06-08-1983	NONE	
WO 2006132919	A	14-12-2006	EP 1893409 A2 US 2007098959 A1	05-03-2008 03-05-2007
WO 2005051675	A	09-06-2005	AU 2004293251 A1 BR PI0416587 A CA 2545263 A1 CN 1929998 A EP 1689586 A2 JP 2007515311 T KR 20060134001 A US 2007070503 A1	09-06-2005 30-01-2007 09-06-2005 14-03-2007 16-08-2006 14-06-2007 27-12-2006 29-03-2007
EP 0677400	A	18-10-1995	NONE	
EP 1527902	A	04-05-2005	DE 10350212 A1	25-05-2005