

(19) World Intellectual Property
Organization
International Bureau




(43) International Publication Date
29 April 2004 (29.04.2004)

PCT

(10) International Publication Number
WO 2004/035930 A1

- (51) International Patent Classification⁷: **D21H 23/48**, 19/82, B05D 1/30, 1/36
- (21) International Application Number: PCT/US2002/033113
- (22) International Filing Date: 15 October 2002 (15.10.2002)
- (25) Filing Language: English
- (26) Publication Language: English
- (71) Applicant (for all designated States except US): **DOW GLOBAL TECHNOLOGIES INC.** [US/US]; Washington Street, 1790 Building, Midland, MI 48674 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **URSCHELER, Robert** [CH/CH]; Hintere Rietswies 60, CH-8810 Horgen (CH). **ROPER, John, A., III** [US/US]; 2805 Georgetown Drive, Midland, MI 48642 (US). **SALMINEN, Pekka, J.** [FI/CH]; Jostenstrasse 12, CH-8854 Galgenin (CH). **DOBLER, Francis** [FR/CH]; Im Gassacker 7, CH-8122 Binz (CH).
- (74) Agent: **HAYHURST, Paul, D.**; The Dow Chemical Company, Intellectual Property Section, P.O. Box 1967, Midland, MI 48641-1967 (US).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, YU, ZA, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:**
— with international search report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: A METHOD OF PRODUCING A COATED SUBSTRATE



(57) Abstract: The present invention refers to a method of producing a coated substrate comprising the steps of: a) forming a free flowing curtain, the curtain having at least one component capable of reacting, and b) contacting the curtain with a continuous web substrate.

WO 2004/035930 A1

A METHOD OF PRODUCING A COATED SUBSTRATE

This invention relates to a method of producing coated substrates. In a further embodiment the present invention
5 relates to a method of producing coated paper or paperboard.

In the manufacturing of coated substrates usually coating compositions are applied to said substrate, for example, by blade type, bar type, or reverse roll type coating methods.
10 The line speed may exceed 1,000 m/min. Any or all of these methods are commonly employed to sequentially apply coatings to the moving substrates.

However, each of these application methods inherently has its
15 own set of problems that can result in an inferior coated surface quality. In the case of the blade type coating method, the lodgment of particles under the blade can result in streaks in the coating layer, which lowers the quality of the coated paper or paperboard. In addition, the high
20 pressure that must be applied to the blade to achieve the desired coating weight places a very high stress on the substrate and can result in breakage of the substrate web, resulting in lowered production efficiency. Moreover, since the pigmented coatings are highly abrasive, the blade must be
25 replaced regularly in order to maintain the evenness of the coated surface. Also, the distribution of the coating on the surface of the paper or paperboard substrate is affected by the surface irregularities of the substrate. An uneven distribution of coating across the paper or paperboard
30 surface can result in a dappled or mottled surface appearance that can lead to an inferior printing result.

The bar (rod) type coating method has a limitation of solids content and viscosity of the pigmented coating color that is
35 to be applied. Pigmented coatings applied by the bar type coating method are typically lower in solids content and viscosity than are pigmented coating colors applied by the

blade type method. Accordingly, for the bar type coating method it is not possible to freely change the amount of coating that can be applied to the surface of the paper or paperboard substrate. Undesirable reductions in the quality of the surface of the coated paper or paperboard can result when the parameters of coating solids content, viscosity and coat weight are imbalanced. Moreover, abrasion of the bar by the pigmented coatings requires that the bar be replaced at regular intervals in order to maintain the evenness of the coated surface.

The roll type (film) coating method is a particularly complex process of applying pigmented coatings to paper and paperboard in that there is a narrow range of operating conditions related to substrate surface characteristics, substrate porosity, coating solids content and coating viscosity that must be observed for each operating speed and each desired coat weight to be achieved. An imbalance between these variables can lead to an uneven film-split pattern on the surface of the coated paper, which can lead to an inferior printing result, or the expulsion of small droplets of coating as the sheet exits the coating nip. These droplets, if re-deposited on the sheet surface, can lead to an inferior printing result. Moreover, the maximum amount of coating that can be applied to a paper or paperboard surface in one pass using the roll type coating method is typically less than that which can be applied in one pass by the blade or bar type coating methods. This coating weight limitation is especially pronounced at high coating speeds.

Furthermore, a common feature of all these methods is that the amount of coating liquid applied to a paper web, which generally has an irregular surface with hills and valleys, is different depending on whether it is applied to a hill or a valley. Therefore, coating thickness, and thus ink reception properties, will vary across the surface of the coated paper resulting in irregularities in the printed image. Despite

their drawbacks, these coating methods are still the dominant processes in the paper industry due to their economics, especially since very high line speeds can be achieved.

5 All of the mentioned coating techniques have in common that an excess of coating liquid is applied to the substrate and then is metered off. In the case of a reactive coating, which is a coating comprising compounds capable of reacting with each other, the reaction occurring in the metered excess
10 coating renders it useless. Furthermore, each of these coating methods have, as already mentioned, rheological constraints for obtaining good runnability so that the addition of a reactive additive changes the coating rheology profile so that it falls outside of the window of
15 coatability. There are cases where reactive chemistries are used to impart functionality to the coated substrate; however, these coatings are applied through the use of a subsequent coating or converting step that adds complexity and expense.

20

Curtain coating is a relatively new coating technique. Japanese patent applications JP-94-89437, JP-93-311931, JP-93-177816, JP-93-131718, JP-92-298683, JP-92-51933, JP-91-298229, JP-90-217327, and JP-8-310110 and EP-A 517 223
25 disclose the use of curtain coating methods to apply one or more pigmented coating layers to a moving paper surface. More specifically, the prior art relates to:

(i) The curtain coating method being used to apply a
30 single layer of pigmented coating to a basepaper substrate to produce a single-layer-pigmented coating on paper.

(ii) The curtain coating method being used to apply a
35 single priming layer of pigmented coating to a basepaper substrate prior to the application of a single layer of pigmented topcoat applied by a blade type coating process. Thus a multilayer-pigmented

coating of paper was achieved by sequential applications of pigmented coating.

- 5 (iii) The curtain coating method being used to apply a single topcoating layer of pigmented coating to a basepaper substrate that has previously been primed with a single layer of pigmented precoat that was applied by a blade or a metering roll type coating process. Thus a multilayer-pigmented paper coating was achieved by sequential applications of pigmented
- 10 coating.
- (iv) The curtain coating method being used to apply two single layers of specialized pigmented coating to a basepaper substrate such that the single layers were applied in consecutive processes. Thus a multilayer-
- 15 pigmented coating of paper was achieved by sequential applications of pigmented coating.

The use of a curtain coating method to apply a single layer of pigmented coating to the surface of a moving web of paper, as disclosed in the prior art discussed above, is stated to offer the opportunity to produce a superior quality coated paper surface compared to that produced by conventional means. However, the sequential application of single layers of pigmented coating using curtain coating techniques is

25 constrained by the dynamics of the curtain coating process. Specifically, lightweight coating applications can only be made at coating speeds below those currently employed by conventional coating processes because at high coating speeds the curtain becomes unstable, and this results in an inferior

30 coated surface. Therefore, the conventional methods of producing multi-coated papers and paperboards employ the blade, rod or roll metering processes. Unfortunately, the application of consecutive single layers of pigmented coatings to paper or paperboard at successive coating

35 stations, whether by any of the above coating methods, remains a capital-intensive process due to the number of coating stations required, the amount of ancillary hardware

required, for example, drive units, dryers, etc., and the space that is required to house the machinery.

Coated papers and paperboards that have received a coating
5 that contains an additive designed to impart functional
properties, such as barrier properties, printability
properties, adhesive properties, release properties, and
optical properties such as color, brightness, opacity, gloss,
etc., are described as functional products and their coatings
10 may be referred to as functional coatings. The coating
components that impart these properties may also be referred
to as functional additives. Functional products include paper
types such as self adhesive papers, stamp papers, wallpapers,
silicone release papers, food packaging, grease-proof papers,
15 moisture resistant papers, and saturated tape backing papers.

The curtain coating method for the simultaneous coating of
multiple layers is well known and is described in U.S.
Patents 3,508,947 and 3,632,374 for applying photographic
20 compositions to paper and plastic web. However, photographic
solutions or emulsions have a low viscosity and a low solids
content, and are applied at low coating speeds.

In addition to photographic applications, the simultaneous
25 application of multiple coatings by curtain coating methods
is known from the art of making pressure sensitive copying
paper. For example, U.S. Patent 4,230,743 discloses in one
embodiment the simultaneous application of a base coating
comprising microcapsules as a main component and a second
30 layer comprising a color developer as a main component onto a
travelling web. However, it is reported that the resulting
paper has the same characteristics as the paper made by
sequential application of the layers. Moreover, the coating
composition containing the color developer is described as
35 having a viscosity between 10 and 20 cps at 22°C.

JP-A-10-328613 discloses the simultaneous application of two coating layers onto a paper web by curtain coating to make an inkjet paper. The coating compositions applied according to the teaching of that reference are aqueous solutions with an
5 extremely low solids content of about 8 percent by weight. Furthermore a thickener is added in order to obtain non-Newtonian behavior of the coating solutions. The examples in JP-A-10-328613 reveal that acceptable coating quality is only achieved at line speeds below 400m/min. The low operation
10 speed of the coating process is not suitable for an economic production of printing paper, especially commodity printing paper.

It is taught in the art that a critical requirement for
15 successful curtain coating at high speeds is that the kinetic energy of the falling curtain impacting the moving web be sufficiently high to displace the boundary layer air and wet the web to avoid air entrainment defects. This can be accomplished by raising the height of the curtain and/or by
20 increasing the density of the coating. Hence, high speed curtain coating of low-density coatings, such as a functional or glossing coating containing synthetic polymer pigment for improved gloss, is taught to be difficult due to the lower kinetic energy of low-density materials, and due to the fact
25 that increasing the height of the curtain is limited by the difficulty of maintaining a stable uniform curtain.

In view of the deficiencies of conventional commercial paper coating techniques, it would be desirable to have a process
30 capable of improving the properties of a coated substrate, such as printing quality of the resulting coated substrate.

The technical problem underlying the present invention is to overcome the disadvantages of the prior art and, thus, to
35 provide a coating method capable of applying coatings comprising one or more reactive compounds. A further aspect of the present invention is to provide a coating method

whereby the properties of the applied coating is not detrimentally affected by said compounds capable of reacting with each other. Moreover, a further aim of the present invention is to provide coated substrates having improved
5 properties and a method of producing the same.

The technical problem of the present invention is solved by a method of producing a coated substrate comprising the steps of:

- 10 a) forming a free flowing curtain, the curtain having at least a first component and a second component capable of reacting with each other, and
b) contacting the curtain with a continuous web substrate.

- 15 In one embodiment, the present invention is a method of producing a coated substrate comprising the steps of:
a) forming a composite, multilayer free flowing curtain, the curtain having at least two layers, whereby one layer comprises at least a first component which is capable of
20 reacting with at least a second component comprised in the other layer, and
b) contacting the curtain with a continuous web substrate.

In a preferred embodiment there is at least one internal
25 layer present between the layer comprising the first component and the layer comprising the second component.

- In a further embodiment, the problem of the invention is solved by a process for producing a coated substrate
30 comprising the steps of:
a) forming a free flowing curtain, the curtain having at least one component capable of reacting with itself or another compound, and
b) contacting the curtain with a continuous web substrate,
35 wherein at least one component of the curtain begins reacting during the coating process and is essentially completely reacted before the coating process is complete.

In another embodiment, the problem of the present invention is solved by a method of producing a coated substrate comprising the steps of:

- 5 a) forming a free flowing curtain, the curtain having at least one layer comprising a composition capable of reacting, and
- b) contacting the curtain with a continuous web substrate.

10 The composition forming the at least one layer of the free flowing curtain of step a) may comprise at least one first component and at least one second component capable of reacting with each other or may contain a reaction system wherein reaction of at least one reactive component can be
15 induced by means of catalyst, initiator or activator present in the composition or by exposure to energy such as heat or radiation. As used herein, the term "reactive component" means a material that is capable of reacting and/or a material that initiates, catalyzes or is otherwise involved
20 in a reaction. As used herein, the term "coating process" means a process comprising coating a substrate to a point such that the coating is immobilized and/or the coated substrate is finished and ready for sale.

25 Preferably, said free flowing curtain of step a) is a composite multilayer free flowing curtain.

Preferably, there are three main means by which the curtain coating can be used to apply reactive coatings:

30

- 1) Precoat reaction - the first and second component capable of reacting with each other are added to the coating liquid just before or when said coating liquid passes through the curtain coating head, possibly
35 through the use of inline mixing;

2) Coating reaction - where two or more reactive layers are prepared and brought together in the falling curtain so that the reaction can begin during the coating application process; and

5

3) Postcoat reaction - where at least one reactive layer is introduced into the coating and the reaction takes place after said coating is applied to the substrate but before the coated substrate is in its finished form.

10

Thus, preferably the reaction between the first component and the second component of step a) takes place within the coating die or head, in the free flowing curtain and/or when applied to the substrate. and/or when initiated by, for example, pressure, heat, pH change, radiation and/or exposure to a gas or vapor, such as oxygen or ammonia.

The reaction type of which the first component and the second component of step a) react with each other is not limited, and may be, for example: an anionic-cationic interaction; a crosslinking reaction; a free radical reaction; a step growth reaction; a addition reaction; a curing reaction such as a UV induced curing reaction, an oxygen induced curing reaction, a catalyzed reaction or an electron beam induced curing reaction; an acid base reaction; a grafting reaction; a ring opening reaction; a precipitation; a phase change; a flocculation/coagulation reaction or a combination thereof.

In a preferred embodiment it is excluded that a crosslinking reaction takes place between the at least first component and at least second component if said components are present in the same layer.

In a further preferred embodiment it is excluded that a flocculation can be induced by adding calcium chloride solution to a coating composition.

The term anionic-cationic interaction refers to the reaction of an anionic compound with a cationic compound in a coating liquid, whereby the properties of said coating liquid change due to said anionic-cationic interaction. The property change
5 may be a flocculation which would make it impossible to apply said coating to substrates using blade, rod, or airbrush (air knife) coating techniques.

In a preferred embodiment, the first component of step a) is
10 a polyvinyl alcohol, and the second component is borax.

Another embodiment of the present invention is that in step a) the first component is cationic starch and the second component is an anionic coating composition.
15

The substrate of the present invention preferably is a basepaper or paperboard so that a coated basepaper or paperboard is produced accordingly.

20 In a preferred embodiment, photographic papers and/or pressure sensitive copying papers are excluded from the scope of the present invention. The term "excluding photographic papers should be interpreted in the sense that none of the layers of the curtain used in the practice of the present
25 invention comprise silver compounds. The term "excluding pressure sensitive copying papers" should be interpreted in the sense that the layers of the curtain do not contain a combination of a microencapsulated color former and a color developer in a single layer or in different layers.

30 The curtain layers can be simultaneously applied according to the present invention by using a curtain coating unit with a slide nozzle arrangement for delivering multiple liquid layers to form a continuous, multilayer curtain.

35 Alternatively, an extrusion type supplying head, such as a slot die or nozzle, having several adjacent extrusion nozzles can be employed in the practice of the present invention. In

a preferred embodiment, the entire coating liquid, which passes through the curtain coating unit, is applied to the substrate. Preferably, on the edges of the formed curtain only a minor part of coating liquid is removed before said
5 curtain is applied to the substrate. Coating liquids which pass the curtain coating unit and which are not applied to the substrate may be discarded.

According to a preferred embodiment of the present invention
10 at least one curtain layer forming the free falling curtain comprises at least one pigment. Preferably, in making a paper for printing purposes at least two of the coating layers comprise at least one pigment. Preferably, a top layer ensuring printability is present. Said layer improves surface
15 properties like gloss or smoothness and optionally is not pigmented. For the manufacture of commodity printing paper, coating with two pigmented layers is sufficient for most purposes.

20 The present inventors have surprisingly discovered that coated substrates, such as paper and paperboard, with improved properties can be readily prepared using reactive coating color components via the process of the invention.

25 The curtain employed in the invention has a bottom, or interface, layer, and optionally a top layer, and/or optionally one or more internal layers. Each layer comprises a liquid, emulsion, suspension, dispersion or solution. The coating curtain of the present invention suitably includes at
30 least one layer, and also includes embodiments having at least 2, at least 3, at least 4, at least 5, or at least 6 or more layers. The layers of the curtain can include one or more printing layers, one or more functional layers, one or more spacing layers, one or more coating layers, and one or
35 more layers imparting reactive functionalities, and the like, or any combination thereof. A spacing layer is a layer that separates at least two other layers. For example, a spacing

layer can be employed between layers having reactive components in order to delay the initiation of a reaction between the components.

5 A coating layer of the invention preferably comprises at least one pigment and/or binder, and can be formulated to be the same or different than conventional paper coating formulations. The primary function of a coating layer is to cover the surface of the substrate as is well known in the
10 paper-coating art. Conventional coating formulations, referred to in the industry as coating colors, can be employed as the coating layer. Examples of pigments useful in the process of the present invention include clay, kaolin, talc, calcium carbonate, titanium dioxide, satin white,
15 synthetic polymer pigment, zinc oxide, barium sulphate, gypsum, silica, alumina trihydrate, mica, and diatomaceous earth. Kaolin, talc, calcium carbonate, titanium dioxide, satin white and synthetic polymer pigments, including hollow polymer pigments, are particularly preferred.

20 Binders useful in the practice of the present invention include, for example, styrene-butadiene latex, styrene-acrylate latex, styrene-acrylate-acrylonitrile latex, styrene-butadiene-acrylate-acrylonitrile latex, styrene-
25 butadiene-acrylonitrile latex, styrene-maleic anhydride latex, styrene-acrylate-maleic anhydride latex, polysaccharides, proteins, polyvinyl pyrrolidone, polyvinyl alcohol, polyvinyl acetate, epoxy resin, polyurethane, cellulose derivatives. Examples of preferred binders include
30 carboxylated styrene-butadiene latex, carboxylated styrene-acrylate latex, carboxylated styrene-butadiene-acrylonitrile latex, carboxylated styrene-maleic anhydride latex, carboxylated polysaccharides, proteins, polyvinyl alcohol, and carboxylated polyvinyl acetate latex. Examples of
35 polysaccharides include agar, sodium alginate, and starch, including modified starches such as thermally modified starch, carboxymethylated starch, hydroxyethylated starch,

and oxidized starch. Examples of proteins that can be employed in the process of the present invention include albumin, soy protein, and casein. A wide variety of suitable binders are commercially available.

5

When a multilayer curtain is employed, the coat weight of each layer of the curtain can be adjusted to obtain the desired coated substrate properties. At least one of the layers of the multilayer curtain desirably has a dry coat
10 weight of less than 30 g/cm^2 , preferably less than 20 g/cm^2 , more preferably less than 10 g/cm^2 , even more preferably less than 5 g/cm^2 , and most preferably less than 3 g/cm^2 .

In a further embodiment the coating prepared from the curtain
15 desirably has a dry coat weight of less than 60 g/cm^2 , preferably less than 30 g/cm^2 , more preferably less than 20 g/cm^2 , even more preferably less than 10 g/cm^2 and most preferably less than 5 g/cm^2 . In a preferred embodiment, the coat weight of the coating is from 5 to 25 g/cm^2 .

20

The curtain of the invention comprises an interface layer, which is the layer that comes in contact with the substrate to be coated. One important function of the interface layer may be to promote wetting of the substrate paper. The
25 interface layer can have more than one function. For example, in addition to wetting it may provide coverage of the substrate and improved functional performance such as adhesion, sizing, stiffness or a combination of functions. The interface layer can include a reactive component or can
30 be free of reactive compounds. This layer is preferably a relatively thin layer when employed in a multilayer curtain. The coat weight of the interface layer when employed in a multilayer curtain preferably is from 0.01 to 5 g/m^2 , and more preferably is from 1 to 3 g/m^2 .

35

In a preferred embodiment of the invention, the interface layer includes one or more of the following: a dispersion

such as a latex, including an alkali swellable latex, a blend of starch and poly(ethylene acrylic acid) copolymer, and the like; or a water soluble polymer, such as, for example, polyvinyl alcohol, a starch, an alkali soluble latex, a
5 polyethylene oxide, or a polyacrylamide. The interface layer can optionally be pigmented, and this is preferred for certain applications.

The curtain of the invention can include one or more
10 functional layers. The purpose of the functional layer is to impart a desired functionality to the coated paper. Functional layers can be selected to provide, for example, printability, barrier properties, such as moisture barrier, oil barrier, grease barrier and oxygen barrier properties,
15 sheet stiffness, fold crack resistance, paper sizing properties, release properties, adhesive properties, and optical properties, such as, color, brightness, opacity, gloss, etc. In one embodiment of the invention, the first and second reactive components can react to impart functionality
20 to a layer in the coating. Functional coatings that are very tacky in character would not normally be coated by conventional consecutive coating processes because of the tendency of the tacky coating material to adhere the substrate to guiding rolls or other coating equipment. The
25 simultaneous multilayer method, on the other hand, allows such functional coatings to be placed underneath a topcoat that shields the functional coating from contact with the coating machinery.

30 The solids content of a functional layer can vary widely depending on the desired function. A functional layer of the present invention preferably has a solids content of up to 75 percent by weight based on the total weight of the functional layer and a viscosity of up to 10,000 cps (Brookfield,
35 spindle 5, 100 rpm, 25°C), more preferably 50 to 3,000 cps. Preferably, the coat weight of a functional layer is from 0.1 to 30 g/m², more preferably 0.5 to 10 g/m², and most

preferably from 1 to 3 g/m². In certain situations, such as, for example, when a dye layer is employed or in the case of certain reactants such as borax, the coat weight of the functional layer can be less than 0.1 g/m².

5

The functional layer of the present invention can contain, for example, a polymer of ethylene acrylic acid, a polyethylene, other polyolefins, a polyurethane, an epoxy resin, a polyester, an adhesive such as a styrene butadiene latex, a styrene acrylate latex, a carboxylated latex, a starch, a protein, or the like, a sizing agent such as a starch, a styrene-acrylic copolymer, a styrene-maleic anhydride, a polyvinyl alcohol, a polyvinyl acetate, a carboxymethyl cellulose or the like, a barrier such as
10 silicone, a wax or the like.
15

Each functional layer can include, but is not limited to include, at least one pigment and/or binder as previously described for the coating layer, and/or one or more reactive
20 components.

If desired, at least one additive such as, for example, at least one dispersant, at least one lubricant, at least one water retention agent, at least one surfactant, at least one
25 optical brightening agent, at least one pigment dye or colorant, at least one thickening agent, at least one defoamer, at least one anti-foaming agent, at least one biocide, or at least one soluble dye or colorant or the like may be used in at least one layer of the curtain.

30

For the purposes of the present invention, in a multilayer curtain the layer most distant from the substrate paper is referred to as the top layer. This layer typically is the layer that will be printed upon, although it is possible that
35 the coated paper of the present invention could also be further coated using conventional means, such as rod, blade, roll, bar, or air knife (airbrush) coating techniques, and

the like. The top layer can be a coating layer or a functional layer, including a gloss layer, and can contain a reactive component. In a preferred embodiment of the invention, the top layer is very thin, having a coat weight
5 of, for example from 0.5 to 3 g/m². This advantageously allows the use of less expensive materials under the top layer, while still producing a paper having good printing properties. In one embodiment, the top layer is free of mineral pigment.

10

According to a particularly preferred embodiment the top layer comprises a glossing formulation. The novel combination of glossing formulation and simultaneous multilayer curtain coating combines the advantages of curtain coating with good
15 gloss.

The glossing formulations useful in the present invention comprise gloss additives, such as synthetic polymer pigments, including hollow polymer pigments, produced by polymerization
20 of, for example, styrene, acrylonitrile and/or acrylic monomers. The synthetic polymer pigments preferably have a glass transition temperature of 40 - 200°C, more preferably 50 - 130°C, and a particle size of 0.02 - 10 µm, more preferably 0.05 - 2 µm. The glossing formulations contain 5 -
25 100 weight percent, based on solids, of gloss additive, more preferably 60 - 100 weight percent. Another type of glossing formulation comprises gloss varnishes, such as those based on epoxyacrylates, polyester, polyesteracrylates, polyurethanes, polyetheracrylates, oleoresins, nitrocellulose, polyamide,
30 vinyl copolymers and various forms of polyacrylates.

According to a preferred embodiment of the present invention the viscosity of the top layer is above 20 cps (at 25°C). A preferred viscosity range is from 90 cps to 2,000 cps, more preferably from 200 cps to 1,000 cps.

35

When the curtain has at least 3 layers, then it has at least one internal layer. The viscosity and solids content of the

internal layer(s) is not critical, provided a stable curtain can be maintained. The internal layer preferably is a functional layer or a coating layer. When more than one internal layer is present, combinations of functional and coating layers can be employed. For example, the internal layers can comprise a combination of identical or different functional layers, a combination of identical or different coating layers, or a combination of coating and functional layers. An internal layer may contain a reactive component.

10

The process of the invention expands the limits of paper coating technology, gives the coated paper producer unprecedented flexibility, and he ability to prepare novel coated papers.

15

Preferably, the free flowing curtain desirably has a solids content of at least 10 weight percent, preferably at least 40 wt%, more preferably at least 45 wt%, and most preferably at least 50 wt%. At least one layer of a multilayer free flowing curtain of the invention preferably has a solids content of at least 40 wt%, preferably at least 50 wt%, and most preferably at least 65 wt%.

20

A particular advantage of one embodiment of the present invention is that, by the simultaneous application of at least two coating layers by curtain coating, very thin layers or in other words very low coat weights of the respective layers can be obtained even at very high application speeds. For example, the coat weight of each layer in the composite curtain can be from 0.01 to 10 g/m², more preferably 0.1 to 3 g/m². The coat weight of each layer can be the same as the others, or can vary widely from the other layers; thus, many combinations are possible.

30

The process of the invention can produce substrates having a wide range of coat weights. Preferably, the coat weight of the coating on the paper produced is from 3 to 60 g/m².

35

Preferably, the curtain of step a) has a dry coat-weight of less than 30 g/m². In one embodiment of the invention, the total coat weight of the coating is less than 20 g/m², preferably less than 15 g/m², and more preferably less than
5 12 g/m².

In one embodiment of the present invention the coat weight of the top layer is lower than the coat weight of the layer contacting the basepaper or baseboard. Preferably, the coat
10 weight of the top layer is less than 75 percent, more preferably less than 50 percent, of the coat weight of the layer contacting the basepaper or baseboard. Thus, a greater coating raw material efficiencies in the paper and paperboard
15 coating operations is achieved. In another embodiment, the coat weight of the top layer is higher than the coat weight of the layer(s) below it. Unlike conventional coating processes, the simultaneous multilayer coating method of the present invention allows the use of much larger quantities of relatively inexpensive raw materials such as, for example,
20 under an extremely thin top layer of more expensive raw materials or in combination with an expensive reactant, such as a curing agent, without compromising the quality of the finished coated product. In addition, the method of the invention allows the preparation of papers that have never
25 been produced before. For example, a tacky functional internal layer can be included in the curtain.

A pronounced advantage of the present invention irrespective of which embodiment is used is that the process of the
30 present invention can be run at very high coating speeds that hitherto in the production of printing paper could only be achieved using blade, bar or roll application methods.

Usual line speeds in the process of the invention are at
35 least 300 m/min, preferably at least 400 m/min, more preferably at least 500 m/min, such as in a range of 600 - 3200 m/min, and more preferably at least 800 m/min, such as

in a range of 800 to 2500 m/min. In one embodiment of the invention, the line speed, or speed of the moving substrate, is at least 1000 m/min, preferably at least 1500 m/min.

5 Preferably, the continuous web substrate of step b) is neither precoated nor precalendered. In another embodiment the continuous web substrate of step b) is not precoated, and in a further embodiment the continuous web substrate of step b) is not precalendered. The continuous web substrate of step
10 b) preferably has a grammage, or basis weight, of from 20-400 g/m².

Figure 1 is an explanatory cross-sectional view of a curtain coating unit 1 with a slide nozzle arrangement 2 for
15 delivering multiple streams 3 of curtain layer to form a continuous, multilayer curtain 4. When a dynamic equilibrium state is reached, the flow amount of the curtain layers flowing into the slide nozzle arrangement 2 is completely balanced with the flow amount flowing out of the slide nozzle
20 arrangement. The free falling multilayer curtain 4 comes into contact with web 5 which is running continuously and thus the web 5 is coated with multiple layers of the respective curtain layers. The running direction of the web 5 is changed immediately before the coating area by means of a roller 6 to
25 minimize the effect of air flow accompanying the fast moving web 5.

An advantage of the process of the present invention over the prior art is that a coated substrate having specific
30 properties can be obtained by applying a curtain comprising at least two reactive compounds to a substrate. Said method allows one to prepare a coated substrate having specific layers imparting, due to the reaction of said reactive compounds, specific properties. As the methods known in the
35 prior art apply an excess of coating color, they cannot effectively apply coatings comprising reactive compounds to substrates. Preferably, the coated substrates can be printed

with any printing method customary to a person skilled in the art.

The present invention is exemplified by the following
5 examples. All parts and percentages are by weight unless otherwise specified.

Examples:

10 The following materials were used to make the layers in the reactive coating structure:

- Carbonate: dispersion of calcium carbonate with particle size of 90% < 2 μm in water (Hydrocarb® 90 ME available
15 from Pluess-Stauffer), 77% solids.
- Clay: dispersion of No. 1 high brightness kaolin clay with particle size of 98% < 2 μm in water (Hydragloss® 90 available from J.M Huber Corp., Have de Grace, Maryland, USA), 71% solids.
- 20 • Latex (A): carboxylated styrene-butadiene latex (DL 966 available from The Dow Chemical Company, Midland, Michigan, USA), 50% solids in water.
- Latex (B): carboxylated styrene-butadiene latex (DL 980 available from The Dow Chemical Company, Midland, Michigan,
25 USA), 50% solids in water.
- Latex (C): alkali swellable carboxylated acrylate latex (XZ 92338 available from The Dow Chemical Company, Midland, Michigan, USA), 27% solids in water.
- PVOH: solution of 15% of low molecular weight synthetic
30 polyvinyl alcohol (Mowiol® 6/98 available from Clariant AG, Basel Switzerland)
- Surfactant (A): aqueous solution of sodium di-alkylsulphosuccinate (Aerosol® OT available from Cyanamid, Wayne, New Jersey, USA), 75% solids.

- Surfactant (B): Tergitol TMN 6 aqueous solution of Trimethylnonanol ethoxylate 6 EO (available from DOW, USA), 90% solids.
- 5 • Whitener: fluorescent whitening agent derived from diamino-stilbenedisulfonic acid (Tinopol® ABP/Z, available from Ciba Specialty Chemicals Inc. Basel, Switzerland).
- Borax: Sodium tetra borate purity >98%, available from FLUKA
- 10 • Starch (A) Cationic Starch (C Size SP 5855 available from Cerestar, Krefeld, Germany).
- Starch (B) Anionic Starch (C Film 07311 available from Cerestar, Krefeld, Germany).

Coating Method

15

The above ingredients were mixed in the amounts given in Tables 1 and 4 where all parts are based on dry weights unless otherwise indicated. The pH of the pigmented coating formulations was adjusted by adding NaOH solution (10%) as indicated in Table 1. Water was added as needed to adjust the solids content of the formulations. The formulations were coated onto paper according to the following procedure. A multilayer slide die type curtain coater manufactured by Troller Schweizer Engineering (TSE, Murgenthal, Switzerland) 25 was used. The curtain coating apparatus was equipped with edge guides lubricated with a trickle of water and with a vacuum suction device to remove this edge lubrication water at the bottom of the edge guide just above the coated paper edge. In addition, the curtain coater was equipped with a vacuum suction device to remove interface surface air from the paper substrate upstream from the curtain impingement zone. The height of the curtain was 300 mm unless otherwise noted. Coating formulations were deaerated prior to use to remove air bubbles.

35

Test MethodsBrookfield Viscosity

The viscosity is measured using a Brookfield RVT viscometer
5 (available from Brookfield Engineering Laboratories, Inc.,
Stoughton, Massachusetts, USA). For viscosity determination,
600 ml of a sample are poured into a 1000 ml beaker and the
viscosity is measured at 25°C at a spindle speed of 100 rpm.

10 Paper Gloss

Paper gloss is measured using a Zehntner ZLR-1050 instrument
at an incident angle of 75°.

Ink Gloss

15 The test is carried out on a Pruefbau Test Printing unit with
Lorrilleux Red Ink No. 8588. An amount of 0.8 g/m² (or 1.6
g/m² respectively) of ink is applied to coated paper test
strips mounted on a long rubber-backed platen with a steel
printing disk. The pressure of the ink application is 1,000 N
20 and the speed is 1 m/s. The printed strips are dried for 12
hours at 20°C at 55 % minimum room humidity. The gloss is
then measured on a Zehntner ZLR-1050 instrument at an
incident angle of 75°.

25 Ink Set Off

The test is carried out on a Pruefbau Test Printing unit. 250
mm³ of ink (Huber no 520068) is distributed for 1 minute on
the distributor. A metal printing disk is inked by being
placed on the distributor for 15 seconds. The disk is placed
30 on the first printing station. At the second printing station
an uninked metal printing disk is placed, with a pressure of
400N. The coated paper strip, mounted on a rubber-backed
platen, is printed with a printing pressure of 1000N at a
speed of 1.5m/s. Time 0 is taken when printing happens. After
35 the strip is printed at the first station, move the strip
towards second printing station, or Set off station, by
moving the hand lever. At the set off station, place a blank

paper strip between the printed paper and the disk. At 15, 30
60 and 120 seconds, the blank paper is pressed against the
printed sample in the set off station by moving the hand
lever. The amount of non-immobilized ink from the printed
5 paper transferred to the blank paper is measured by ink
densities as given by optical density measurements.

Brightness

Brightness is measured on a Zeiss Elrepho 2000. Brightness
10 is measured according to ISO standard 2469 on a pile of
sheets. The result is given as R457.

Opacity

Opacity is measured on a Zeiss Elrepho 2000. Opacity is
15 measured on a single sheet backed by black standard (R_0) and
on a pile of sheets (R_∞). The result is given as $R_0/R_\infty \times 100$
(percentage).

Burn out test:

20 The test is used to illustrate coating distributions and
uniformity on unprinted or printed papers (exc. full-tone
specimens).

Procedure:

- 25 1. Dip the 4 x 4 cm paper sample for 1 minute into a 10%
(weight/weight) aqueous NH_4Cl solution.
2. Dry the test paper for 3 minutes in an oven at 120 degrees
Celsius.
3. Char the paper by moving it 5-10 cm over a hot plate until
30 smoke has disappeared (the sample should not burn).
4. Measure Brightness. This procedure stains coating fibers
which appear dark so a higher brightness value is indicative
of improved coverage by the coating which appears bright
compared to the blackened fibers.

35

Dry Pick Resistance (IGT)

This test measures the ability of the paper surface to accept the transfer of ink without picking. The test is carried out on an A2 type printability tester, commercially available
5 from IGT Reptest BV. Coated paper strips (4 mm x 22 mm) are printed with inked aluminum disks at a printing pressure of 36 N with the pendulum drive system and the high viscosity test oil (red) from Reptest BV. After the printing is completed, the distance where the coating begins to show
10 picking is marked under a stereomicroscope. The marked distance is then transferred into the IGT velocity curve and the velocities in cm/s are read from the corresponding drive curve. High velocities mean high resistance to dry pick.

15 Paper Roughness

The roughness of the coated paper surface is measured with a Parker PrintSurf roughness tester. A sample sheet of coated paper is clamped between a cork-melinex platen and a measuring head at a clamping pressure of 1,000 kPa.
20 Compressed air is supplied to the instrument at 400 kPa and the leakage of air between the measuring head and the coated paper surface is measured. A higher number indicates a higher degree of roughness of the coated paper surface.

25 Paper Stiffness

Paper stiffness is measured using the Kodak Stiffness method, TAPPI 535-PM-79.

Coat weight

30 The coat weight achieved in each coating experiment is calculated from the known volumetric flow rate of the pump delivering the coating to the curtain coating head, the speed at which the continuous web of paper is moving under the curtain coating head, the density and percent solids of the
35 curtain, and the width of the curtain.

Comparative Experiment A and Examples 1 to 4.

These examples used the reaction between borax in one layer and PVOH in another layer. This reaction leads to a rapid increase in viscosity and the formation of a gel. The details
5 of the formulations are shown in Table 1.

Table 1

	Comparative A		Example 1		Example 2		Example 3		Example 4		
	Bottom Layer	Top Layer	Bottom Layer	Top Layer	Bottom Layer	Top Layer	Bottom Layer	Top Layer	Bottom Layer	Middle Layer	Top Layer
Carbonate	100	70	100	70	100	70		70	100		70
Clay		30		30		30		30			30
Latex (A)		11		11		11		11			11
Latex (B)	20		20		20				20		
PVOH		2.5		2.5		2.5		2.5			2.5
Latex (C)	0.5		0.5		0.5		66.4		0.5	66.4	
Borax			0.25		0.5		33.3			33.3	
Whitener		1	0	1	0	1		1			1
Surfactant (A)	0.4	0.2	0.4	0.2	0.4	0.2		0.2	0.4		0.2
pH	8.5	8.5	8.5	8.5	8.5	8.5	9	8.5	8.5	9	8.5
Density (9/cc)	1.32	1.53	1.32	1.53	1.34	1.53	1.0	1.53	1.32	1.0	1.53
Brookfield	100	520	90	520	100	520		520	100		520
Viscosity (mPa · s)											
solids %	45.0	62.0	45.0	62.0	45.0	62.0	1.0	62.0	45.0	1.0	62.0

The coatings were applied at 1000 m/min onto a wood-containing basepaper with a roughness of 4.3 microns. Two coating conditions were used for Examples 1, 2 and 3: Coating Condition 1 - where the bottom layer coat weight was 1 g/m² and top layer coat weight was 7 g/m² and Coating Condition 2 - where the bottom layer coat weight was 2 g/m² and top layer coat weight was 6 g/m². These two coating conditions tested the effect of increasing the amount of the reactive bottom layer. The comparative experiment used the same two coating conditions but the reactive ingredient (borax) was left out. Example 4 used a three-layer coating having a thin middle layer containing the borax. For Example 4, the bottom layer coat weight was fixed at 1 g/m² and the top layer coat weight was 7 g/m² while the coat weight of the middle layer was varied from 0.018 g/m² (Condition 1) to 0.036 g/m² (Condition 2). The coated paper properties for these examples are shown in Tables 2 and 3.

20

25

30

35

Table 2

	Comparative A	Example 1	Example 2	Example 3	Example 4
Coated Paper Property	Coating Condition 1	Coating Condition 1	Coating Condition 1	Coating Condition 1	Coating Condition 1
PAPER GLOSS 75° (%)	43	43	45	43	37
INK GLOSS 75°; 0.8 g/m ² INK (%)	58	62	62	58	51
INK GLOSS 75°; 1.6 g/m ² INK (%)	65	69	68	71	63
ROUGHNESS PPS (μ)	1.8	1.7	1.7	1.6	1.8
ISO BRIGHTNESS R 457 (%)	76.8	78.4	77.1	77.2	78.4
OPACITY (%)	92.8	92.8	93.5	93.6	93.8
INK SET OFF AFTER 15 SEC. (Density)	0.08	0.11	0.11	0.05	0.09
INK SET OFF AFTER 30 SEC. (Density)	0.00	0.00	0.01	0.00	0.00
INK SET OFF AFTER 60 SEC. (Density)	0.00	0.00	0.00	0.00	0.00
INK SET OFF AFTER 120 SEC. (Density)	0.00	0.00	0.00	0.00	0.00
Burn Out Test Brightness	28.4	30.8	28.9	31.3	30.5
Bending Stiffness Machine Direction (mNm)	0.050	0.049	0.055	0.056	0.060

5

10

Table 3

	Comparative A	Example 1	Example 2	Example 3	Example 4
Coated Paper Property	Coating Condition 2	Coating Condition 2	Coating Condition 2	Coating Condition 2	Coating Condition 2
PAPER GLOSS 75° (%)	37	39	41	41	32
INK GLOSS 75°; 0.8 g/m ² INK (%)	52	58	56	54	47
INK GLOSS 75°; 1.6 g/m ² INK (%)	63	69	70	62	60
ROUGHNESS PPS (μ)	2.0	1.8	1.7	1.4	1.9
ISO BRIGHTNESS R 457 (%)	77.0	77.8	76.6	77.3	78.3
OPACITY (%)	92.6	93.3	92.9	92.3	93.7
INK SET OFF AFTER 15 SEC. (Density)	0.06	0.12	0.19	0.24	0.22
INK SET OFF AFTER 30 SEC. (Density)	0.01	0.01	0.00	0.01	0.05
INK SET OFF AFTER 60 SEC. (Density)	0.00	0.00	0.00	0.00	0.01
INK SET OFF AFTER 120 SEC. (Density)	0.00	0.00	0.00	0.00	0.00
Burn Out Brightness	27.4	27.9	29.5	29.9	29.4
BENDING STIFFNESS MACHINE DIRECTION (mNm)	0.049	0.057	0.057	0.064	0.057

These results show that reaction between the borax and PVOH had a minor effect on paper gloss, a minor effect on paper roughness, a significant improvement in ink gloss, a slowing down of ink setting, a significant improvement in opacity, a significant improvement in stiffness, a significant improvement in coating coverage determined by the burn out test, and some effect on brightness depending on the thickness of the borax-containing layer. In comparing Coating Condition 1 with Coating Condition 2 it was found that doubling the amount of borax affects significantly the ink set off and stiffness properties.

Comparative Experiment B and Example 5

This example uses a cationic starch in the bottom layer to react with a conventional anionic paper coating top layer. The comparative experiment replaces the cationic starch with a conventional anionic coating starch. The details of the coating formulations are given in Table 4.

Table 4:

	Comparative B		Example 5	
	Bottom Layer	Top Layer	Bottom Layer	Top Layer
Carbonate		70		70
Clay		30		30
Latex (A)		11		11
PVOH		2.5		2.5
Starch (A)			100	
Starch (B)	100			
Whitener (A)		1	0	1
Surfactant (B)	2	0.4	2	0.4
pH	8.5	8.5	8.5	8.5
Density	1.08	1.53	1.10	1.53
Brookfield Viscosity	920	580	120	580
solids %	20.0	62.0	20.0	62.0

10

The coatings were applied at 1000 m/min to a wood-containing basepaper with a roughness of 6.2 microns. The bottom layer coat weight was 0.5 g/m² and top layer coat weight was 6.5 g/m². The coated paper properties are in Table 5.

15

20

Table 5:

Coated Paper Properties	Comparative B	Example 5
PAPER GLOSS 75° (%)	35	37
INK GLOSS 75°; 0.8 g/m ² INK (%)	47	52
INK GLOSS 75°; 1.6 g/m ² INK (%)	58	68
IGT DRY PICK (cm/s)	52	57
INK SET OFF AFTER 15 SEC. (Density)	0.48	0.57
INK SET OFF AFTER 30 SEC. (Density)	0.20	0.25
INK SET OFF AFTER 60 SEC. (Density)	0.07	0.09
INK SET OFF AFTER 120 SEC. (Density)	0.04	0.01
BENDING STIFFNESS MACHINE DIRECTION (mNm)	0.042	0.050

The use of the cationic starch gave a significant improvement in stiffness and coating strength as measured by IGT dry pick. In addition ink set off gets lower.

Claims

1. A method of producing a coated substrate comprising the steps of:
- 5 a) forming a free flowing curtain, the curtain having a first component and a second component capable of reacting with each other, and
- b) contacting the curtain with a continuous web substrate.
- 10
2. A method according to claim 1, characterized in that the method comprises the steps of:
- a) forming a composite, multilayer free flowing curtain, the curtain having at least two layers, whereby one layer
- 15 comprises a first component which is capable of reacting with a second component in a different layer, and
- b) contacting the curtain with a continuous web substrate.
- 20
3. A method according to claim 2, characterized in that in the multilayer free flowing curtain of step a) at least one internal layer is present between the layer comprising the first component and the layer comprising the second component.
- 25
4. A method according to any of claims 2 and 3, characterized in that the reaction type of which the first component and the second component of step a) react with each other is selected from the group consisting of
- 30 anionic-cationic-interaction, crosslinking reaction, free radical reaction, step growth reaction, addition reaction, UV induced curing reaction, electron beam induced curing reaction, acid-base reaction, flocculation/coagulation reaction and combinations
- 35 thereof.

5. A method according to claim 1 comprising the steps of:
a) forming a free flowing curtain, the curtain having at least one layer comprising a composition capable of reacting, and
5 b) contacting the curtain with a continuous web substrate.
6. A method according to claim 5 comprising the steps of:
a) forming a free flowing curtain, the curtain having at least one layer comprising a first component and a second component capable of reacting with each other, and
10 b) contacting the curtain with a continuous web substrate.
- 15 7. A method according to claim 5 or 6, characterized in that the reaction type of which the at least first component and the at least second component of step a) react with each other is selected from the group consisting of anionic-cationic-interaction, free radical reaction, step
20 growth reaction, addition reaction, UV induced curing reaction, electron beam induced curing reaction, acid-base reaction, flocculation/coagulation reaction and combinations thereof.
- 25 8. A method according to claim 5, 6 or 7 characterized in that the free flowing curtain of step a) is a composite, multilayer free flowing curtain.
9. A method according to any of the preceding claims,
30 characterized in that the reaction between the first component and the second component of step a) takes place in the free flowing curtain and/or when applied to the substrate and/or when initiated by heat, pressure, radiation, and/or oxygen.

35

10. A method according to any of the preceding claims,
characterized in that in step a) the first component is a
polyvinyl alcohol and the second component is borax.
- 5 11. A method according to any of the preceding claims,
characterized in that in step a) the first component is
cationic starch and the second component is an anionic
coating composition.
- 10 12. A method according to any of the preceding claims,
characterized in that the free flowing curtain of step a)
comprises a top layer ensuring printability.
13. A method according to any of the preceding claims,
15 characterized in that the continuous web substrate of step
b) has a grammage of from 20 to 400 g/m².
14. A method according to any of the preceding claims,
characterized in that at least one of the layers of the
20 multilayer curtain of step a) has a coat-weight when
dried of less than 30 g/m², preferably less than 20 g/m²,
most preferred less than 10 g/m².
15. A method according to any of the preceding claims,
25 characterized in that the multilayer curtain of step a)
has a coat-weight when dried of less than 60 g/m².
16. A method according to any of the preceding claims,
characterized in that the multilayer curtain of step a)
30 comprises at least 3 layers, preferably at least 4
layers, more preferred at least 5 layers and most
preferred at least 6 layers.
17. A method according to any of the preceding claims,
35 characterized in that the multilayer curtain of step a)
comprises at least one layer comprising at least one
pigment.

18. A method according to claim 17, characterized in that the pigment is selected from the group consisting of clay, kaolin, calcined clay, talc, calcium carbonate, titanium dioxide, satin white, synthetic polymer pigment, zinc oxide, barium sulfate, gypsum, silica, alumina trihydrate, mica, and diatomaceous earth.
19. A method according to any of the preceding claims, characterized in that at least one layer of the multilayer free flowing curtain of step a) comprises a binder.
20. A method according to claim 19, characterized in that the binder is selected from the group consisting of styrene-butadiene latex, styrene-acrylate latex, styrene-acrylate-acrylonitrile latex, styrene-acrylate-acrylonitrile latex, styrene-butadiene-acrylate-acrylonitrile latex, styrene-butadiene-acrylonitrile latex, styrene-butadiene-acrylate-acrylonitrile latex, styrene-maleic anhydride latex, styrene-acrylate-maleic latex, styrene-acrylate-maleic anhydride latex, polysaccharides, proteins, polyvinyl pyrrolidone, polyvinyl alcohol, polyvinyl acetate, cellulose derivatives and mixtures thereof.
21. A method according to any of the preceding claims, characterized in that at least one layer of the multilayer free flowing curtain of step a) comprises at least one optical brightening agent.
22. A method according to any of the preceding claims, characterized in that at least one layer of the multilayer free flowing curtain of step a) comprises at least one surfactant.

23. A method according to any of the preceding claims,
characterized in that at least one layer of the
multilayer free flowing curtain of step a) has a solids
content of at least 40 wt%, preferably of at least 50
5 wt%, most preferred of at least 65 wt%.
24. A method according to any of the preceding claims,
characterized in that the multilayer free flowing curtain
of step a) has a solids content of at least 10 wt%,
10 preferably of at least 40 wt%, most preferred of at least
45 wt%.
25. A method according to any of the preceding claims,
characterized in that the continuous web substrate of
15 step b) is a basepaper or a paperboard.
26. A method according to any of the preceding claims,
characterized in that the continuous web substrate of
step b) is neither precoated nor precalendered.
20
27. A method according to any of the preceding claims,
characterized in that the continuous web substrate of
step b) has a web velocity of at least 300 m/min,
preferably at least 400 m/min, most preferred at least
25 500 m/min.
28. A coated substrate obtainable by the method of any of the
preceding claims.
- 30 29. A coated substrate according to claim 28, characterized
in that the coated substrate is coated paper or
paperboard.
30. A process for producing a coated substrate comprising
35 the steps of:
a) forming a free flowing curtain, the curtain having at
least one component capable of reacting with itself or

- another compound, and
b) contacting the curtain with a continuous web substrate,
wherein at least one component of the curtain begins
5 reacting during the coating process and is essentially completely reacted before the coating process is complete.
31. A method according to claim 30 comprising the steps of:
10 a) forming a free flowing curtain, the curtain having at least one layer comprising a first component and a second component capable of reacting with each other, and
b) contacting the curtain with a continuous web substrate.
- 15 32. A method according to claim 30, characterized in that the free flowing curtain of step a) is a composite, multilayer free flowing curtain.
- 20 33. A method according to claim 31, characterized in that the reaction type of which the first component and the second component of step a) react with each other is selected from the group consisting of anionic-cationic-
interaction, free radical reaction, step growth reaction,
25 addition reaction, UV induced curing reaction, electron beam induced curing reaction, acid-base reaction, flocculation/coagulation reaction and combinations thereof.
- 30 34. A method according to claim 31, characterized in that the reaction between the first component and the second component of step a) takes place in the free flowing curtain and/or when applied to the substrate and/or when initiated by heat, radiation, and/or oxygen.

35

35. A method according to claim 30, characterized in that the free flowing curtain of step a) comprises a top layer ensuring printability.
- 5 36. A method according to claim 32, characterized in that at least one of the layers of the multilayer curtain of step a) has a coat-weight when dried of less than 30 g/m^2 , preferably less than 20 g/m^2 , most preferred less than 10 g/m^2 .
- 10 37. A method according to claims 32, characterized in that the multilayer curtain of step a) has a coat-weight when dried of less than 60 g/m^2 .
- 15 38. A method according to claim 32, characterized in that the multilayer curtain of step a) comprises at least 3 layers, preferably at least 4 layers, more preferred at least 5 layers and most preferred at least 6 layers.
- 20 39. A method according to claim 32, characterized in that the multilayer curtain of step a) comprises at least one layer comprising at least one pigment.
- 25 40. A method according to claim 32, characterized in that the pigment is selected from the group consisting of clay, kaolin, calcined clay, talc, calcium carbonate, titanium dioxide, satin white, synthetic polymer pigment, zinc oxide, barium sulfate, gypsum, silica, alumina trihydrate, mica, and diatomaceous earth.
- 30 41. A method according to claim 32, characterized in that at least one layer of the multilayer free flowing curtain of step a) comprises a binder.
- 35 42. A method according to claim 41, characterized in that the binder is selected from the group consisting of styrene-butadiene latex, styrene-acrylate latex, styrene-

acrylate-acrylonitrile latex, styrene-acrylate-acrylonitrile latex, styrene-butadiene-acrylate-acrylonitrile latex, styrene-butadiene-acrylonitrile latex, styrene-butadiene-acrylate-acrylonitrile latex, styrene-maleic anhydride latex, styrene-acrylate-maleic latex, styrene-acrylate-maleic anhydride latex, polysaccharides, proteins, polyvinyl pyrrolidone, polyvinyl alcohol, polyvinyl acetate, cellulose derivatives and mixtures thereof.

10

43. A method according to claim 32, characterized in that at least one layer of the multilayer free flowing curtain of step a) comprises at least one optical brightening agent.

15 44. A method according to claim 32, characterized in that at least one layer of the multilayer free flowing curtain of step a) comprises at least one surfactant.

20 45. A method according to claim 32, characterized in that at least one layer of the multilayer free flowing curtain of step a) has a solids content of at least 40 wt%, preferably of at least 50 wt%, most preferred of at least 65 wt%.

25 46. A method according to claim 32, characterized in that the multilayer free flowing curtain of step a) has a solids content of at least 10 wt%, preferably of at least 40 wt%, most preferred of at least 45 wt%.

30 47. A method according to claim 30, characterized in that the continuous web substrate of step b) is a basepaper or a paperboard.

35 48. A method according to claim 30, characterized in that the continuous web substrate of step b) is neither precoated nor precalendered.

49. A method according to claim 30, characterized in that the continuous web substrate of step b) has a web velocity of at least 300 m/min, preferably at least 400 m/min, most preferred at least 500 m/min.

5


50. A method according to claim 30, characterized in that the continuous web substrate of step b) has a grammage of from 20 to 400 g/m².

10 51. A coated substrate obtainable by the method of claim 30.

52. A coated substrate according to claim 30, characterized in that the coated substrate is coated paper or paperboard.

15

FIG. 1



INTERNATIONAL SEARCH REPORT

Internationa	Application No
PCT/US 02/33113	

A. CLASSIFICATION OF SUBJECT MATTER
 IPC 7 D21H23/48 D21H19/82 B05D1/30 B05D1/36

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
 IPC 7 D21H B05D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 3 436 022 A (ERNST ROLF K) 1 April 1969 (1969-04-01) -----	
A	BE 852 751 A (E.I. DU PONT DE NEMOURS AND COMPANY) 22 September 1977 (1977-09-22) -----	
A	GB 838 392 A (KASIKA CHEM FAB G M B H) 22 June 1960 (1960-06-22) -----	

Further documents are listed in the continuation of box C.

Patent family members are listed in annex.

° Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

25 July 2003

Date of mailing of the international search report

01/08/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
 Fax: (+31-70) 340-3016

Authorized officer

Sony, O.

INTERNATIONAL SEARCH REPORT

nation on patent family members

Intern: Application No

PCT/US 02/33113

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 3436022	A	01-04-1969	NONE	
BE 852751	A	22-09-1977	BE 852751 A1	22-09-1977
			DE 2712259 A1	29-09-1977
			FR 2345228 A1	21-10-1977
			GB 1574241 A	03-09-1980
			JP 52114636 A	26-09-1977
GB 838392	A	22-06-1960	DE 1093549 B	24-11-1960
			AT 201849 B	26-01-1959
			BE 553416 A	
			FR 1189893 A	07-10-1959