



US 20070064195A1

(19) **United States**

(12) **Patent Application Publication** (10) **Pub. No.: US 2007/0064195 A1**

Destro et al. (43) **Pub. Date: Mar. 22, 2007**

(54) **STABILIZATION OF PHOTOCROMIC SYSTEMS**

(76) Inventors: **Mara Destro**, Bologna (IT); **Dario Lazzari**, Bologna (IT); **Dirk Simon**, Lorrach-Brombach (DE); **Manuele Vitali**, Bologna (IT)

Correspondence Address:
CIBA SPECIALTY CHEMICALS CORPORATION
PATENT DEPARTMENT
540 WHITE PLAINS RD
P O BOX 2005
TARRYTOWN, NY 10591-9005 (US)

(21) Appl. No.: **10/572,154**

(22) PCT Filed: **Sep. 20, 2004**

(86) PCT No.: **PCT/EP04/52238**

§ 371(c)(1),
(2), (4) Date: **Mar. 16, 2006**

(30) **Foreign Application Priority Data**

Sep. 29, 2003 (EP)..... 03103587.6

Publication Classification

(51) **Int. Cl.**
G02C 7/10 (2006.01)
C08K 5/3412 (2006.01)
C08K 5/3477 (2006.01)
(52) **U.S. Cl.** **351/63; 524/91; 524/95; 524/100**

(57) **ABSTRACT**

Photochromic compositions are disclosed comprising a polymeric material, a photochromic dye, a hydroxyphenyl triazine UV absorber and, optionally, a further light stabilizer selected from the sterically hindered amines. These systems provide a reversible photochromic effect and show improved light stabilization and color fastness.

STABILIZATION OF PHOTOCROMIC SYSTEMS

[0001] The present invention relates to light stabilized polymer compositions comprising a photochromic dye, to a process of improving the stability and/or colour fastness of a photochromic dye, and to the use of a certain stabilizer for improving the light fastness of photochromic dyes or compositions containing them.

[0002] Photochromic systems comprise molecules able to change the color due to a reversible transformation of a chemical species induced by daylight.

[0003] Typical photochromic systems employ naphtho- or benzopyrans (chromenes), spiropyrans, spirooxazines. These molecules have found several fields of application especially in plastics (e.g. ophthalmic lenses). One of the most severe limitations to a large scale employment of such devices is due to the intrinsically poor long term stability, e.g. the photostability of both colorless and colored forms under conditions of more or less continuous irradiation with daylight. WO 96/37576 notes some stabilization of these systems using certain light stabilizers.

[0004] U.S. Pat. No. 5,770,115 pertains to compositions of a carrier photochromic naphthopyran material and a stabilizer system comprising a polyphenolic antioxidant, a ultraviolet light absorber and a hindered amine light stabilizer. The stabilizer system is used to improve the fatigue resistance of the photochromic naphthopyran compounds.


[0005] It has now been found that an improved light stabilization and color fastness of photochromic systems and the dyes used, e.g. of marks and colorations on polymeric materials such as plastics and elastomers, may be achieved using a specific UV absorber and optional further stabilizer.

[0006] The UV absorbers are selected from the family of hydroxyphenyltriazines; thus, present invention pertains to a composition comprising

[0007] a) a polymeric material containing


[0008] b) a photochromic dye and

[0009] c) a stabilizer comprising a hydroxyphenyl triazine UV absorber (i) conforming to formula I, II, III, IV or V




I


-continued



II




III



IV

V



wherein

[0010] Y is phenyl, naphthyl, or said phenyl or said naphthyl substituted by one to three alkyl of 1 to 6 carbon atoms, by halogen, by hydroxy or by alkoxy of 1 to 6 carbon atoms or by mixtures thereof; or Y is Z, or Z₂;

X is Z₁ or Z₂;


[0011] R₁ is hydrogen, straight or branched chain alkyl of 1 to 24 carbon atoms, cycloalkyl of 5 to 12 carbon atoms, phenylalkyl of 7 to 15 carbon atoms, halogen, —SR₃,

—SOR₃ or —SO₂R₃; or said alkyl, said cycloalkyl or said phenylalkyl substituted by one to three halogen, —R₄, —OR₅, —N(R₅)₂, —COR₅, —COOR₅, —OCOR₅, —CN, —NO₂, —SR₅, —SOR₅, —SO₂R₅ or —P(O)(OR₅)₂, morpholinyl, piperidinyl, 2,2,6,6-tetramethylpiperidinyl, piperazinyl or N-methylpiperidinyl groups or combinations thereof; or said alkyl or said cycloalkyl interrupted by one to four phenylene, —O—, —NR₅—, —CONR₅—, —COO—, —OCO— or —CO groups or combinations thereof; or said alkyl or said cycloalkyl both substituted and interrupted by combinations of the groups mentioned above;

[0012] R₃ is alkyl of 1 to 20 carbon atoms, alkenyl of 3 to 18 carbon atoms, cycloalkyl of 5 to 12 carbon atoms, phenylalkyl of 7 to 15 carbon atoms, aryl of 6 to 10 carbon atoms or said aryl substituted by one or two alkyl of 1 to 4 carbon atoms;

[0013] R₄ is aryl of 6 to 10 carbon atoms or said aryl substituted by one to three halogen, alkyl of 1 to 8 carbon atoms, alkoxy of 1 to 8 carbon atoms or combinations thereof; cycloalkyl of 5 to 12 carbon atoms; phenylalkyl of 7 to 15 carbon atoms or said phenylalkyl substituted on the phenyl ring by one to three halogen, alkyl of 1 to 8 carbon atoms, alkoxy of 1 to 8 carbon atoms or combinations thereof; or straight or branched chain alkenyl of 2 to 18 carbon atoms;


[0014] R₅ is defined as is R₄; or R₅ is also hydrogen or straight or branched chain alkyl of 1 to 24 carbon atoms, alkenyl of 2 to 24 carbon atoms; or R₅ a group for formula



[0015] T is hydrogen, oxyl, hydroxyl, —OT₁, alkyl of 1 to 24 carbon atoms, said alkyl substituted by one to three hydroxy; benzyl or alkanoyl of 2 to 18 carbon atoms;

[0016] T₁ is alkyl of 1 to 24 carbon atoms, cycloalkyl of 5 to 12 carbon atoms, alkenyl of 2 to 24 carbon atoms, cycloalkenyl of 5 to 12 carbon atoms, phenylalkyl of 7 to 15 carbon atoms, a radical of a saturated or unsaturated bicyclic or tricyclic hydrocarbon of 7 to 12 carbon atoms or aryl of 6 to 10 carbon atoms or said aryl substituted by one to three alkyl of 1 to 4 carbon atoms;

[0017] R₂ is hydrogen, straight or branched chain alkyl of 1 to 24 carbon atoms or cycloalkyl of 5 to 12 carbon atoms; or said alkyl or said cycloalkyl substituted by one to four halogen, epoxy, glycidyl, furyloxy, —R₄, —OR₅, —N(R₅)₂, —CON(R₅)₂, —COR₅, —COOR₅, —OCOR₅, —OCOC(R₅)=C(R₅)₂, —C(R₅)=CCOOR₅, —CN, —NCO, or




or combinations thereof; or said alkyl or said cycloalkyl interrupted by one to four epoxy, —O—, —NR₅—, —CONR₅—, —COO—, —OCO—, —CO—, —C(R₅)=C(R₅)COO—, —OCOC(R₅)=C(R₅)—, —C(R₅)=C(R₅)—, phenylene or phenylene-G-phenylene in which G is —O—, —S—, —SO₂—, —CH₂— or —C(CH₃)₂— or combinations thereof; or said alkyl or said cycloalkyl both substituted and interrupted by combinations of the groups mentioned above; or R₂ is —SO₂R₃ or —COR₆;

[0018] R₆ is straight or branched chain alkyl of 1 to 18 carbon atoms, straight or branched chain alkenyl of 2 to 12 carbon atoms, phenoxy, alkylamino of 1 to 12 carbon atoms, arylamino of 6 to 12 carbon atoms, —R₇COOH or —NH—R₈—NCO;

[0019] R₇ is alkylene of 2 to 14 carbon atoms or phenylene;

[0020] R₈ is alkylene of 2 to 24 carbon atoms, phenylene, tolylene, diphenylmethane or a group




[0021] R₁ and R₁' are the same or different and are as defined for R₁;

[0022] R₂ and R₂' are the same or different and are as defined for R₂;

[0023] X, X' are the same or different and are as defined for X; Y and Y' are the same or different and are as defined for Y;

t is 0 to 9;

[0024] L is straight or branched alkylene of 1 to 12 carbon atoms, cycloalkylene of 5 to 12 carbon atoms or alkylene substituted or interrupted by cyclohexylene or phenylene; or L is benzylidene; or L is —S—, —S—S—, —S—E—S—, —SO—, —SO₂—, —SO—E—SO—, —SO₂—E—SO₂—, —CH₂—NH—E—NH—CH₂— or




[0025] E is alkylene of 2 to 12 carbon atoms, cycloalkylene of 5 to 12 carbon atoms or alkylene interrupted or terminated by cycloalkylene of 5 to 12 carbon atoms;

n is 2, 3 or 4;

[0026] when n is 2; Q is straight or branched alkylene of 2 to 16 carbon atoms; or said alkylene substituted by one to three hydroxy groups; or said alkylene interrupted by one to three

—CH=CH— or —O—; or said alkylene both substituted and interrupted by combinations of the groups mentioned above; or Q is xylylene or a group —CONH—R₈—NHCO—, —CH₂CH(OH)CH₂O—R₉—OCH₂CH(OH)CH₂—, —CO—R₁₀—CO—, or —(CH₂)_m—COO—R₁₁—OOC—(CH₂)_m—, where m is 1 to 3; or Q is



[0027] R₉ is alkylene of 2 to 50 carbon atoms; or said alkylene interrupted by one to ten —O—, phenylene or a group -phenylene-G-phenylene in which G is —O—, —S—, —SO₂—, —CH₂— or —C(CH₃)₂—;


[0028] R₁₀ is alkylene of 2 to 10 carbon atoms, or said alkylene interrupted by one to four —O—, —S— or —CH=CH—; or R₁₀ is arylene of 6 to 12 carbon atoms;

[0029] R₁₁ is alkylene of 2 to 20 carbon atoms or said alkylene interrupted by one to eight —O—;


[0030] when n is 3, Q is a group —[(CH₂)_mCOO]₃—R₁₂ where m is 1 to 3, and R₁₂ is an alkanetriyl of 3 to 12 carbon atoms;

[0031] when n is 4, Q is a group —[(CH₂)_mCOO]₄—R₁₃ where m is 1 to 3, and R₁₄ is an alkanetetrayl of 4 to 12 carbon atoms;

[0032] Z₁ is a group of formula



[0033] Z₂ is a group of formula



where

[0034] r₁ and r₂ are 1;

[0035] R₁₄, R₁₅, R₁₆, R₁₇, R₁₈, R₁₉, R₂₀, R₂₁, R₂₂ and R₂₃ are independently of one another hydrogen, hydroxy, cyano, alkyl of 1 to 20 carbon atoms, alkoxy of 1 to 20 carbon atoms, phenylalkyl of 7 to 15 carbon atoms, cycloalkyl of 5 to 12 carbon atoms, cycloalkoxy of 5 to 12 carbon atoms, halogen, haloalkyl of 1 to 5 carbon atoms, sulfo, carboxy, acylamino of 2 to 12 carbon atoms, acyloxy of 2 to 12 carbon atoms, alkoxycarbonyl of 2 to 12 carbon atoms or aminocarbonyl; or R₁₇ and R₁₈ or R₂₂ and R₂₃ together with the phenyl radical to which they are attached are a cyclic radical interrupted by one to three —O— or —NR₅—.

[0036] In another embodiment of the instant invention, the s-triazine UV absorbers are those of formula I where

X and Y are Z₁ or Z₂;


[0037] R₁ is hydrogen, straight or branched chain alkyl of 1 to 24 carbon atoms, cycloalkyl of 5 to 12 carbon atoms, phenylalkyl of 7 to 15 carbon atoms or halogen;

[0038] R₂ is hydrogen, straight or branched chain alkyl of 1 to 24 carbon atoms or cycloalkyl of 5 to 12 carbon atoms; or said alkyl or said cycloalkyl substituted by one to three —R₄—, —OR₅—, —COOR₅—, —OCOR₅— or combinations thereof; or said alkyl or cycloalkyl interrupted by one to three epoxy, —O—, —COO—, —OCO— or —CO—;


[0039] R₄ is aryl of 6 to 10 carbon atoms or said aryl substituted by one to three halogen, alkyl of 1 to 8 carbon atoms, alkoxy of 1 to 8 carbon atoms or combinations thereof; cycloalkyl of 5 to 12 carbon atoms; phenylalkyl of 7 to 15 carbon atoms or said phenylalkyl substituted on the phenyl ring by one to three halogen, alkyl of 1 to 8 carbon atoms, alkoxy of 1 to 8 carbon atoms or combinations thereof;

[0040] R₅ is defined as is R₄; or R₅ is also hydrogen or straight or branched chain alkyl of 1 to 24 carbon atoms;

[0041] Z₁ is a group of formula




[0042] Z_2 is a group of formula



where r_1 and r_2 are each 1; and

[0043] R_{14} , R_{15} , R_{16} , R_{17} , R_{18} , R_{19} , R_{20} , R_{21} , R_{22} and R_{23} are independently of one another hydrogen, hydroxy, cyano, alkyl of 1 to 20 carbon atoms, alkoxy of 1 to 20 carbon atoms, phenylalkyl of 7 to 15 carbon atoms, cycloalkyl of 5 to 12 carbon atoms, cycloalkoxy of 5 to 12 carbon atoms, halogen, haloalkyl of 1 to 5 carbon atoms, sulfo, carboxy, acylamino of 2 to 12 carbon atoms, acyloxy of 2 to 12 carbon atoms, or alkoxycarbonyl of 2 to 12 carbon atoms or aminocarbonyl.

[0044] Preferred are, for example, those conforming to the general structure



wherein

[0045] R_{28} is $(CH_2-CH_2-O)_n-R_{29}$; $-CH_2-CH(OH)-CH_2-O-R_{29}$; or $-CH(R_{30})-CO-O-R_{40}$; n is 0 or 1; R_{29} is C_1-C_{13} alkyl or C_2-C_{20} alkenyl or C_6-C_{12} aryl or $CO-C_1-C_{18}$ alkyl; R_{30} is H or C_1-C_8 alkyl; R_{40} is C_1-C_{12} alkyl or C_2-C_{12} alkenyl or C_5-C_6 cycloalkyl.


[0046] A further example of hydroxyphenyltriazines (i) is the compound (a)

[0047] a) 2-(2-hydroxy-4-[2-ethylhexyl]oxyphenyl)-4,6-di(4-phenylphenyl)-1,3,5-triazine,

[0048] Compound UV1 as used in the examples below is identical with the above compound a (also disclosed as compound A8 of US-6060543).

[0049] Hydroxyphenyl triazine UV absorber are described e.g. in GB-A-975966, EP-A-434608, U.S. Pat. No. 4,619,956, U.S. Pat. No. 5,298,067, EP-A-530135, EP-A-520938, EP-A-531258, U.S. Pat. No. 5,556,973, U.S. Pat. No. 5,959,008, U.S. Pat. No. 6,184,375, U.S. Pat. No. 6,117,997; for example in U.S. Pat. No. 5,998,116, U.S. Pat. No. 6,255,483, U.S. Pat. No. 6060543.


[0050] Of interest are also such compositions wherein the hydroxyphenyl triazine UV absorber (i) is an oligo- or polyester of formula (100)



in which

[0051] x_2 is a number from 1 to 50;

[0052] A_1 is a group of the formula (101)



or has one of the meanings given for T_{10} ;

[0053] D_1 is C_4-C_{12} alkylene or said alkylene substituted by OH or interrupted by O or both substituted by OH and interrupted by O;

[0054] L_1 is C_1-C_{18} alkylene; C_5-C_{12} cycloalkylene; C_3-C_{18} alkenylene; or one of said residues substituted by phenyl, C_7-C_{11} alkylphenyl, C_5-C_{12} cycloalkyl, OH, halogen, C_1-C_{18} alkoxy, C_5-C_{12} cycloalkoxy, C_3-C_{18} alkenyloxy, COOH;

[0055] the R_{50} are independently of each other H, OR_{54} or OH, with the proviso that at least one of R_{50} or R_{53} is OH;

[0056] the R_5 are independently of each other hydrogen, C_1-C_{12} alkyl or a radical of formula $-L_1-CO-O-R_{55}$;

[0057] R_{55} is H, C_1-C_{18} alkyl, C_2-C_{12} hydroxyalkyl;

[0058] R_5 is hydrogen, C_1-C_4 alkyl, Cl, phenyl or a group $-OR_{54}$;

[0059] R_{52} is hydrogen or methyl;

[0060] R_5 is hydrogen, methyl, OH or OR_{54} ; and


[0061] T_{10} is the divalent acyl residue of an aliphatic or cycloaliphatic dicarboxylic acid of 13 to 60 carbon atoms;

and which contains at least one moiety of formula (101) and at least one moiety T_{10} .

[0062] In a preferred compound, L_1 is C_1-C_4 alkylene, especially C_2-C_4 alkylidene or methylene. D_1 is advantageously C_4-C_{12} alkylene or C_4-C_{10} alkylene interrupted by O.


[0063] T_{10} as the divalent acyl residue of an aliphatic or cycloaliphatic dicarboxylic acid of 13 to 60 carbon atoms includes, for example, aliphatic diaclys wherein the 2 car-

bonyl groups are interconnected by C_{11} - C_{58} alkylene or -alkenylylene or alkylene interrupted by cycloalkylene or cycloalkenylylene, each of which is unsubstituted or substituted by alkyl, and containing 11 to 58 carbon atoms in total, preferably 20 to 50 carbon atoms. Alkylene or alkenylylene may be branched or unbranched, or, preferably not adjacent to an ethylenic double bond, interrupted by oxygen. In preferred compounds, T_{10} is $-\text{CO}-T_{10}'-\text{CO}-$, wherein T_{10}' is C_{20} - C_{50} alkylene or C_{20} - C_{50} alkylene interrupted by one or more oxygen atoms; especially preferred is unbranched C_{20} - C_{50} alkylene. In further preferred compounds, T_{10} is $-\text{CO}-T_{10}'-\text{CO}-$, wherein T_{10}' is alkylene interrupted by C_5 - C_{12} cycloalkylene or C_5 - C_{12} cycloalkenylylene or said cycloalkylene or cycloalkenylylene substituted by alkyl and containing 11 to 58 carbon atoms, especially 20-50 carbon atoms, in total; especially preferred cycloalkylene is cyclohexylene; especially preferred cycloalkenylylene is cyclohexenylylene. Valuable spacer groups T_{10}' are, for example, of the formula 102



wherein R_{56} is $-(C_bH_{2b})-$ and R_{57} is $-(C_cH_{2c})-$ and

[0064] R_{58} , R_{59} and R_{60} are $-(C_dH_{2d})-H$, $-(C_eH_{2e})-H$, and $-(C_fH_{2f})-H$, respectively, where b, is from the range 0-7, and each of the indices b-f is from the range 0-20, with the condition that the sum $b_1+b+c+d+e+f$ is from the range 15-45, or of the formula 103



wherein

[0065] R_{61} and R_{62} each are C_1 - C_{18} alkylene and each of R_{63} , R_{64} , R_{65} and R_{66} , independently, are H or C_1 - C_{18} alkyl, and R_{65} and R_{66} together may also be a chemical bond, with the condition that the total number of carbon atoms in formula 103 ranges from 20 to 50.

[0066] Of special technical importance are spacer groups T_{10}' of the formula 103 wherein R_{61} , and R_{62} independently are alkylene of 4-12 carbon atoms, each of R_{63} and R_{64} , independently, are C_4 - C_{12} alkyl, while R_{65} and R_{66} are hydrogen.

[0067] In the compounds of present formula (100), most preferably, the R_{50} are OH;

[0068] the Ru are hydrogen or methyl;

[0069] R_{51} is hydrogen, methyl or a group $-\text{OR}_{54}$;

[0070] R_{52} is hydrogen;


[0071] R_{53} is hydrogen, OH or methyl.

[0072] Terminal groups of the oligomer or polymer of formula (100) usually are $-\text{O}-D_1-\text{OR}_{67}$, or $-\text{OR}_{67}$ if bonded to A_1 (left side of formula 100),

[0073] or $-\text{A}_1-\text{OR}_{67}$, such as $-\text{T}_{10}'-\text{COOR}_{67}$ or $-\text{[formula 101]}-\text{OR}_{67}$, or $-\text{R}_{67}$ if bonded to O (right side of formula 100),

[0074] where R_{67} is H or C_1 - C_8 alkyl.

[0075] For example, the ester of formula (100) may conform to the formula (104)



in which

[0076] x_2 is a number from 1 to 20;

[0077] the number y is at least 1 and ranges from (x_2+z-1) to (x_2+z+1) ;

[0078] z is a number from 1 to 20; and

[0079] R_{68} is hydrogen, C_1 - C_{12} alkyl; C_5 - C_{12} cycloalkyl; C_2 - C_{12} alkenyl; phenyl; C_7 - C_{11} alkylphenyl; C_1 - C_{12} alkyl substituted by phenyl, OH, halogen; C_1 - C_{18} alkoxy, C_5 - C_{12} cycloalkoxy, C_3 - C_{18} alkenyloxy or COOH; especially hydrogen or C_1 - C_4 alkyl;

[0080] R_{67} is hydrogen or C_1 - C_8 alkyl;

[0081] R_{69} is hydrogen or C_1 - C_4 alkyl;

[0082] D_1 is C_4 - C_8 alkylene or C_4 - C_{10} alkylene interrupted by O; and T_{10}' is C_{20} - C_{50} alkylene or C_{20} - C_{50} alkylene interrupted by one or more oxygen atoms;

and all other symbols are as defined for formula 100 above.

[0083] T_{10}' may also be alkylene interrupted by C_5 - C_{12} cycloalkylene or said cycloalkylene, especially cyclohexylene, substituted by alkyl and containing 20-50 carbon atoms in total.

[0084] In the oligo- or polyester of formula (104), each of the divalent structural units identified by the indices x_2 and z bond to the structural unit $-O-D_1-$ identified by the index y , and/or to an end group R_{67} or OR_{67} .

[0085] In compounds of the formula (100), x_2 is preferably from the range 2-50, more preferably from the range 2-20, especially 4-12; the number of triazine moieties of the formula 101 to diacid residues T_{10} preferably ranges from about 1:3 to about 10:1, more preferably from about 1:1 to about 5:1. In compounds of the formula (104), each of x_2 and z are preferably from the range 1-16; more preferably, x_2 is from the range 1-10 and z is ranging from 2-12.

[0086] Oligomeric or polymeric esters of the invention such as those of formula 100 or 104 usually have a molecular weight within the range 1000 to 50000 g/mol, more preferably 1500 to 20000 g/mol, most preferably 2000 to 10000 g/mol (number average Mn as determined by gel permeation chromatography GPC).

[0087] Alkylphenyl is alkyl-substituted phenyl; C_7 - C_{14} alkylphenyl embraces examples such as methylphenyl (tolyl), dimethylphenyl (xylyl), trimethylphenyl (mesityl), ethylphenyl, propylphenyl, butylphenyl, dibutylphenyl, pentylphenyl, hexylphenyl, heptylphenyl and octylphenyl.

[0088] Phenylalkyl is phenyl-substituted alkyl; C_7 - C_{11} phenylalkyl embraces examples such as benzyl,

α -methylbenzyl, α -ethylbenzyl, α,α -dimethylbenzyl, phenylethyl, phenylpropyl, phenylbutyl and phenylpentyl.

[0089] Alkyl interrupted by O can generally comprise one or more nonadjacent oxygen atom(s). Preferably, a carbon atom of an alkylene chain such as D_1 or T_{10}' bonds to not more than 1 heteroatom.

[0090] Within the scope of the stated definitions, the alkyl radicals are branched or unbranched alkyl such as methyl, ethyl, propyl, isopropyl, n-butyl, sec-butyl, isobutyl, t-butyl, 2-ethylbutyl, n-pentyl, isopentyl, 1-methylpentyl, 1,3-dimethylbutyl, n-hexyl, 1-methylhexyl, n-heptyl, isoheptyl, 1,1,3,3-tetramethylbutyl, 1-methylheptyl, 3-methylheptyl, n-octyl, 2-ethylhexyl, 1,1,3-trimethylhexyl, 1,1,3,3-tetramethylpentyl, nonyl, decyl, undecyl, 1-methylundecyl, dodecyl, 1,1,3,3,5,5-hexamethylhexyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl and octadecyl.

[0091] Alkylene such as of L_1 or D_1 derives from such alkyls by abstraction of an hydrogen atom.


[0092] Within the scope of the stated definitions, the alkenyl radicals include allyl, isopropenyl, 2-butenyl, 3-butenyl, isobutenyl, n-penta-2,4-dienyl, 3-methyl-but-2-enyl; n-oct-2-enyl, n-dodec-2-enyl, isododecenyl, n-octadec-2-enyl and n-octadec4-enyl.

[0093] The heavy chains of T_{10} , e.g. alkylene groups of T_{10}' , may have a certain molecular distribution around their main component. Ranges may be, for example, from 22-26, 28-32 or 34-38 C-atoms. It is however also possible that broader ranges are used such as for example from 20 to 40, from 30 to 50 or from 30 to 40 carbon atoms, each for T_{10}' in total.

[0094] Since the educts for preparing a compound of formula (100) or (104) are commercial products, they may vary within certain specifications. This is particularly the case for high molecular weight diacids from which the T_{10} groups are derived, when T_{10} is C_{20} - C_{60} alkylene (which may be interrupted as described above).

[0095] Commercially available diacids or diacid esters may also contain small amounts of chains below C_{20} . Therefore mixtures of compounds wherein T_{10} is a mixture containing up to 10% of diacyl chains below 20 carbon atoms and 90 to 100% of diacyl chains between 20 and 60, particularly between 20 and 40 carbon atoms are also subject of the invention. Percentage is weight percent, based on the total mixture.

[0096] Present invention also pertains to an oligoester or polyester which is obtained by reacting a tris-aryl-triazine of the formula (105)



and a compound of the formula $R_{67}-O-T_{10}-O-R_{67}$, where Y_1 is CO and all other all symbols are as defined above, with a diol $HO-D_1-OH$.

[0097] Hydroxyphenyl triazine UV absorber (i) of formula (100)-(105) may be prepared as described in the international patent application with application no. EP2004/050804.

[0098] Preference is given to hydroxyphenyl triazine UV absorber (i) of the formula I, II, III, IV or V.

[0099] Preferred further light stabilizers to be employed are sterically hindered amines (HALS), especially selected from oligomeric and monodispersed HALS, oligomeric HALS of the alkoxyamine class (NOR-HALS), and low basicity HALS like piperazinones (such as products described in WO 00/31069), morpholinones (see WO 99/14206), piperazinediones (see DE-A-19924984), and thioimidazolidinones (see WO 01/62739).

[0100] Thus, present invention specifically pertains to a composition comprising

[0101] a) a polymeric material containing

[0102] b) a photochromic dye and

[0103] c) a stabilizer combination of

[0104] i) a hydroxyphenyl triazine UV absorber and

[0105] ii) at least one further light stabilizer selected from the sterically hindered amines (HALS).

[0106] The compositions of the invention are useful for all applications wherein a photochromic effect is to be achieved. Some examples are described below:

[0107] Optical devices such as particular types of ophthalmic lenses, referred to as "photochromatic", where the beneficial neutralization of harmful UV solar radiation and the anti-glare effect are effective only when needed, allowing the use of the sunglasses with the photochromatic lenses also indoor. Such lenses are often made of polyacrylates, cellulose esters, polyvinylalcohol, polyurethanes, polycarbonates, polyesters such as polyethyleneterephthalates, polyvinylbutyrate, polystyrenes and related copolymers such as styrene-

methacrylate or styrene-acrylonitrile. The systems may further be applied in optical films as seen in WO 97/32225, and U.S. Pat. Nos. 4,871,784 and 5,217,794 which are incorporated herein by reference.

[0108] Additional applications can be in the field of glazing, where filtration of visible light triggered by the UV part of the solar radiation may enhance the comfort inside a building or vehicle and/or contribute to reduce costs for conditioning an indoor environment. The photochromic system can be present either in the plastic window or used in a film that is laminated onto or embedded in a glass or plastic window. Typical materials used in these contexts are polyethyleneterephthalate, glycole modified polyethyleneterephthalate, polycarbonate, polymethylmethacrylate, polyvinylbutyral, and/or as described in WO 92/01557, Japanese Nos. 75-33286; 93-143668; 95-3217 and 96-143831, and U.S. Pat. No. 5,643,676 which is incorporated herein by reference, for films and glazings; or as seen in Japanese Nos. 8040018; 90-192118; 90-335037; 90-335038; 92-110128 and 94-127591, and U.S. Pat. No. 5,618,863 which is incorporated herein by reference, for windscreens/vehicle glazings and intermediate layers.

[0109] Also greenhouse plastic covers can be additivated with photochromes, aiming at reducing light intensity inside the greenhouse, that eventually turns into heat, as excessive heat may be detrimental to some crops and/or inhibit growth. Low density polyethylene, linear low density polyethylene, ethylene-vinyl acetate copolymer (EVA) and ethylene-butyl acrylate copolymer and blends of the mentioned polymers are typical materials for plastic covers used in agriculture.

[0110] Photochromic coatings.

[0111] Construction elements or articles containing photochromic parts for the purpose of labelling, signalling, decoration etc.

[0112] In general, the polymeric material of component a) may be selected from polymers listed below:

[0113] 1. Polymers of monoolefins and diolefins, for example polypropylene, polyisobutylene, polybut-1-ene,

poly4-methylpent-1-ene, polyvinylcyclohexane, polyisoprene or polybutadiene, as well as polymers of cycloolefins, for instance of cyclopentene or norbornene, polyethylene (which optionally can be crosslinked), for example high density polyethylene (HDPE), high density and high molecular weight polyethylene (HDPE-HMW), high density and ultrahigh molecular weight polyethylene (HDPE-UHMW), medium density polyethylene (MDPE), low density polyethylene (LDPE), linear low density polyethylene (LLDPE), (VLDPE) and (ULDPE).

[0114] Polyolefins, i.e. the polymers of monoolefins exemplified in the preceding paragraph, preferably polyethylene and polypropylene, can be prepared by different, and especially by the following, methods:

[0115] a) radical polymerisation (normally under high pressure and at elevated temperature).

[0116] b) catalytic polymerisation using a catalyst that normally contains one or more than one metal of groups IVb, Vb, VIb or VIII of the Periodic Table. These metals usually have one or more than one ligand, typically oxides, halides, alcoholates, esters, ethers, amines, alkyls, alkenyls and/or aryls that may be either π - or σ -coordinated. These metal complexes may be in the free form or fixed on substrates, typically on activated magnesium chloride, titanium(III) chloride, alumina or silicon oxide. These catalysts may be soluble or insoluble in the polymerisation medium. The catalysts can be used by themselves in the polymerisation or further activators may be used, typically metal alkyls, metal hydrides, metal alkyl halides, metal alkyl oxides or metal alkyloxanes, said metals being elements of groups Ia, IIa and/or IIIa of the Periodic Table. The activators may be modified conveniently with further ester, ether, amine or silyl ether groups. These catalyst systems are usually termed Phillips, Standard Oil Indiana, Ziegler (-Natta), TNZ (DuPont), metallocene or single site catalysts (SSC).

[0117] 2. Mixtures of the polymers mentioned under 1), for example mixtures of polypropylene with polyisobutylene, polypropylene with polyethylene (for example PP/HDPE, PP/LDPE) and mixtures of different types of polyethylene (for example LDPE/HDPE).

[0118] 3. Copolymers of monoolefins and diolefins with each other or with other vinyl monomers, for example ethylene/propylene copolymers, linear low density polyethylene (LLDPE) and mixtures thereof with low density polyethylene (LDPE), propylene/but-1-ene copolymers, propylene/isobutylene copolymers, ethylene/but-1-ene copolymers, ethylene/hexene copolymers, ethylene/methylpentene copolymers, ethylene/heptene copolymers, ethylene/octene copolymers, ethylene/vinylcyclohexane copolymers, ethylene/cycloolefin copolymers (e.g. ethylene/norbornene like COC), ethylene/1-olefins copolymers, where the 1-olefin is generated in-situ; propylene/butadiene copolymers, isobutylene/isoprene copolymers, ethylene/vinylcyclohexane copolymers, ethylene/alkyl acrylate copolymers, ethylene/alkyl methacrylate copolymers, ethylene/vinyl acetate copolymers or ethylene/acrylic acid copolymers and their salts (ionomers) as well as terpolymers of ethylene with propylene and a diene such as hexadiene, dicyclopentadiene or ethylidene-norbornene; and mixtures of such copolymers with one another and with polymers mentioned in 1) above, for example polypropylene/ethylene-propylene copolymers,

LDPE/ethylene-vinyl acetate copolymers (EVA), LDPE/ethylene-acrylic acid copolymers (EM), LLDPE/EVA, LLDPE/EAA and alternating or random polyalkylene/carbon monoxide copolymers and mixtures thereof with other polymers, for example polyamides.

[0119] 4. Hydrocarbon resins (for example C_5 - C_9) including hydrogenated modifications thereof (e.g. tackifiers) and mixtures of polyalkylenes and starch.

[0120] Homopolymers and copolymers from 1.)-4.) may have any stereostructure including syndiotactic, isotactic, hemi-isotactic or atactic; where atactic polymers are preferred. Stereoblock polymers are also included.

[0121] 5. Polystyrene, poly(p-methylstyrene), poly(α -methylstyrene).

[0122] 6. Aromatic homopolymers and copolymers derived from vinyl aromatic monomers including styrene, α -methylstyrene, all isomers of vinyl toluene, especially p-vinyltoluene, all isomers of ethyl styrene, propyl styrene, vinyl biphenyl, vinyl naphthalene, and vinyl anthracene, and mixtures thereof. Homopolymers and copolymers may have any stereostructure including syndiotactic, isotactic, hemi-isotactic or atactic; where atactic polymers are preferred. Stereoblock polymers are also included.

[0123] 6a. Copolymers including aforementioned vinyl aromatic monomers and comonomers selected from ethylene, propylene, dienes, nitriles, acids, maleic anhydrides, maleimides, vinyl acetate and vinyl chloride or acrylic derivatives and mixtures thereof, for example styrene/butadiene, styrene/acrylonitrile, styrene/ethylene (interpolymers), styrene/alkyl methacrylate, styrene/butadiene/alkyl acrylate, styrene/butadiene/alkyl methacrylate, styrene/maleic anhydride, styrene/acrylonitrile/methyl acrylate; mixtures of high impact strength of styrene copolymers and another polymer, for example a polyacrylate, a diene polymer or an ethylene/propylene/diene terpolymer; and block copolymers of styrene such as styrene/butadiene/styrene, styrene/isoprene/styrene, styrene/ethylene/butylene/styrene or styrene/ethylene/propylene/styrene.

[0124] 6b. Hydrogenated aromatic polymers derived from hydrogenation of polymers mentioned under 6.), especially including polycyclohexylethylene (PCHE) prepared by hydrogenating atactic polystyrene, often referred to as polyvinylcyclohexane (PVCH).

[0125] 6c. Hydrogenated aromatic polymers derived from hydrogenation of polymers mentioned under 6a.).

[0126] Homopolymers and copolymers may have any stereostructure including syndiotactic, isotactic, hemi-isotactic or atactic; where atactic polymers are preferred. Stereoblock polymers are also included.

[0127] 7. Graft copolymers of vinyl aromatic monomers such as styrene or α -methylstyrene, for example styrene on polybutadiene, styrene on polybutadiene-styrene or polybutadiene-acrylonitrile copolymers; styrene and acrylonitrile (or methacrylonitrile) on polybutadiene; styrene, acrylonitrile and methyl methacrylate on polybutadiene; styrene and maleic anhydride on polybutadiene; styrene, acrylonitrile and maleic anhydride or maleimide on polybutadiene; styrene and maleimide on polybutadiene; styrene and alkyl acrylates or methacrylates on polybutadiene; styrene and acrylonitrile on ethylene/propylene/diene terpolymers; styrene and acrylonitrile on

- polyalkyl acrylates or polyalkyl methacrylates, styrene and acrylonitrile on acrylate/butadiene copolymers, as well as mixtures thereof with the copolymers listed under 6), for example the copolymer mixtures known as ABS, MBS, ASA or AES polymers.
- [0128] 8. Halogen-containing polymers such as polychloroprene, chlorinated rubbers, chlorinated and brominated copolymer of isobutylene-isoprene (halobutyl rubber), chlorinated or sulfo-chlorinated polyethylene, copolymers of ethylene and chlorinated ethylene, epichlorohydrin homo- and copolymers, especially polymers of halogen-containing vinyl compounds, for example polyvinyl chloride, polyvinylidene chloride, polyvinyl fluoride, polyvinylidene fluoride, as well as copolymers thereof such as vinyl chloride/vinylidene chloride, vinyl chloride/vinyl acetate or vinylidene chloride/vinyl acetate copolymers.
- [0129] 9. Polymers derived from α,β -unsaturated acids and derivatives thereof such as polyacrylates and polymethacrylates; polymethyl methacrylates, polyacrylamides and polyacrylonitriles, impact-modified with butyl acrylate.
- [0130] 10. Copolymers of the monomers mentioned under 9) with each other or with other unsaturated monomers, for example acrylonitrile/ butadiene copolymers, acrylonitrile/alkyl acrylate copolymers, acrylonitrile/alkoxyalkyl acrylate or acrylonitrile/vinyl halide copolymers or acrylonitrile/alkyl methacrylate/butadiene terpolymers.
- [0131] 11. Polymers derived from unsaturated alcohols and amines or the acyl derivatives or acetals thereof, for example polyvinyl alcohol, polyvinyl acetate, polyvinyl stearate, polyvinyl benzoate, polyvinyl maleate, polyvinyl butyral, polyallyl phthalate or polyallyl melamine; as well as their copolymers with olefins mentioned in 1) above.
- [0132] 12. Homopolymers and copolymers of cyclic ethers such as polyalkylene glycols, polyethylene oxide, polypropylene oxide or copolymers thereof with bisglycidyl ethers.
- [0133] 13. Polyacetals such as polyoxymethylene and those polyoxymethylenes which contain ethylene oxide as a comonomer; polyacetals modified with thermoplastic polyurethanes, acrylates or MBS.
- [0134] 14. Polyphenylene oxides and sulfides, and mixtures of polyphenylene oxides with styrene polymers or polyamides.
- [0135] 15. Polyurethanes derived from hydroxyl-terminated polyethers, polyesters or polybutadienes on the one hand and aliphatic or aromatic polyisocyanates on the other, as well as precursors thereof.
- [0136] 16. Polyamides and copolyamides derived from diamines and dicarboxylic acids and/or from aminocarboxylic acids or the corresponding lactams, for example polyamide 4, polyamide 6, polyamide 6/6, 6/10, 6/9, 6/12, 4/6, 12/12, polyamide 11, polyamide 12, aromatic polyamides starting from *m*-xylene diamine and adipic acid; polyamides prepared from hexamethylenediamine and isophthalic or/and terephthalic acid and with or without an elastomer as modifier, for example poly-2,4,4'-trimethylhexamethylene terephthalamide or poly-*m*-phenylene isophthalamide; and also block copolymers of the aforementioned polyamides with polyolefins, olefin copolymers, ionomers or chemically bonded or grafted elastomers; or with polyethers, e.g. with polyethylene glycol, polypropylene glycol or polytetramethylene glycol; as well as polyamides or copolyamides modified with EPDM or ABS; and polyamides condensed during processing (RIM polyamide systems).
- [0137] 17. Polyureas, polyimides, polyamide-imides, polyetherimids, polyesterimids, polyhydantoins and polybenzimidazoles.
- [0138] 18. Polyesters derived from dicarboxylic acids and diols and/or from hydroxycarboxylic acids or the corresponding lactones, for example polyethylene terephthalate (PET), polybutylene terephthalate, poly-1,4-dimethylcyclohexane terephthalate, polyalkylene naphthalate (PAN) and polyhydroxybenzoates, as well as block copolyether esters derived from hydroxyl-terminated polyethers; and also polyesters modified with polycarbonates or MBS. Specific examples are PET, polybutylene terephthalate (PBT), polyethyleneterephthalate (PEN), polytrimethylene terephthalate (PTT), and their copolyesters, for example with isophthalic acid, di-ethylene glycol, 1,4-bis(hydroxymethyl)cyclohexane.
- [0139] 19. Polycarbonates and polyester carbonates.
- [0140] 20. Polyketones.
- [0141] 21. Polysulfones, polyether sulfones and polyether ketones.
- [0142] 22. Crosslinked polymers derived from aldehydes on the one hand and phenols, ureas and melamines on the other hand, such as phenol/formaldehyde resins, urea/formaldehyde resins and melamine/formaldehyde resins.
- [0143] 23. Drying and non-drying alkyd resins.
- [0144] 24. Unsaturated polyester resins derived from copolyesters of saturated and unsaturated dicarboxylic acids with polyhydric alcohols and vinyl compounds as crosslinking agents, and also halogen-containing modifications thereof of low flammability.
- [0145] 25. Crosslinkable acrylic resins derived from substituted acrylates, for example epoxy acrylates, urethane acrylates or polyester acrylates.
- [0146] 26. Alkyd resins, polyester resins and acrylate resins crosslinked with melamine resins, urea resins, isocyanates, isocyanurates, polyisocyanates or epoxy resins.
- [0147] 27. Crosslinked epoxy resins derived from aliphatic, cycloaliphatic, heterocyclic or aromatic glycidyl compounds, e.g. products of diglycidyl ethers of bisphenol A and bisphenol F, which are crosslinked with customary hardeners such as anhydrides or amines, with or without accelerators.
- [0148] 28. Natural polymers such as cellulose, rubber, gelatin and chemically modified homologous derivatives thereof, for example cellulose acetates, cellulose propionates and cellulose butyrates, or the cellulose ethers such as methyl cellulose; as well as rosins and their derivatives.
- [0149] 29. Blends of the aforementioned polymers (polyblends), for example PP/EPDM, Polyamide/EPDM or ABS, PVC/EVA, PVC/ABS, PVC/MBS, PC/ABS, PBTP/ABS, PC/ASA, PC/PBT, PVC/CPE, PVC/acrylates, POM/thermoplastic PUR, PC/thermoplastic PUR, POM/acrylate, POM/MBS, PPO/HIPS, PPO/PA 6.6 and copolymers, PA/HDPE, PA/PP, PA/PPO, PBT/PC/ABS or PBT/PET/PC.


[0150] Polymeric material useable for the present invention is preferably synthetic organic polymeric material, for example, material commonly used for electronic applications.

[0151] In particular the following polymers are preferred:

[0152] Polyolefines such as polyethylene and polypropylene, polycarbonate, polyesters such as polyethylene terephthalate (PET) and its copolyesters; styrene polymers or copolymers such as polystyrene or high impact polystyrene (PS-HIPS); or the specific polymers mentioned above.

[0153] The photochromic dye is usually selected from naphtho- and benzopyranes (chromenes), or from spiropyranes or spirooxazines; these components are commercial available.

[0154] Photochromic spiro-indolino-oxazine compounds useful in the invention have the general structural formula (I):



where:





[0155] R_1 and R_2 , either the same or different, each represent independently a C_1 - C_5 alkyl group, linear or branched; a phenyl group; or R_1 and R_2 , together with the carbon atom to which they are connected, jointly represent a cycloalkyl(C_4 - C_7)group, bicycloalkyl(C_6 - C_{11})group, or tricycloalkyl(C_7 - C_{13})group;

[0156] R_3 represents a hydrogen atom; a C_1 - C_5 alkyl group, linear or branched; a similar C_1 - C_5 alkyl group substituted with from 1 to 5 halogen atoms chosen from fluorine, chlorine, bromine or iodine, hydroxy groups, C_1 - C_5 alkoxy groups, C_1 - C_5 carboxy alkyl groups, cyano groups; a C_2 - C_5 alkenyl group; a phenyl group; or benzyl group;

[0157] from R_4 to R_7 , either the same or different, each stand independently for a hydrogen atom; a C_1 - C_5 alkyl group, linear or branched; a similar C_1 - C_5 alkyl group substituted with from 1 to 5 halogen atoms chosen from fluorine, chlorine, bromine or iodine, hydroxy groups, C_1 - C_5 alkoxy groups, C_1 - C_5 carboxy alkyl groups, cyano groups; a C_2 - C_5 alkenyl group; a phenyl group; a benzyl group; a halogen atom chosen from either fluorine, chlorine, bromine or iodine; a hydroxy group; a C_1 - C_5 alkoxy group; an amino group; a monoalkyl(C_1 - C_5)amino group; a dialkyl(C_1 - C_5)amino group; a cyclo-alkyl(C_3 - C_{10})amino group; a piperidine, piperazine or morpholine group; a carboxyl group; a carboxy alkyl(C_1 - C_5)group; a carboxy alkenyl(C_2 - C_5)group; a carboxamide group; a substituted carboxamide N-alkyl(C_1 - C_5)group; a substituted carboxamide N,N-di-alkyl(C_1 - C_5)group; a cyano group; a nitro group; a sulfonic group; a (C_1 - C_5)alkyl sulfonic group; an aryl sulfonic group chosen from benzene sulfonic, p-toluene sulfonic, p-chlorotoluene sulfonic groups; an aryl group chosen from phenyl, biphenyl, naphthyl groups;

[0158] R_8 represents a hydrogen atom; a linear or branched alkyl(C_1 - C_5)group; a phenyl group; a halogen atom chosen from either fluorine, chlorine, bromine; an alkoxy(C_1 - C_5)group; or a phenoxy group;

[0159] A represents an arenic, monocyclic or polycyclic group, chosen from those that can be defined with formula (II'), (III'), (IV') or (V'):



two contiguous points from R_9 to R_{12} represent the condensation position between the oxazinic nucleus in the general formula (I') and the other two groups and R_{13} - R_{16} have the same meaning as R_4 - R_7 in the general formula (I'); or two contiguous groups together are alkylene of 3-6 carbon atoms, or a corresponding azaalkylene or oxaalkylene; or three contiguous groups jointly represent an alkane-triyl, i.e. 3-valent saturated hydrocarbon residue, of 4-8 carbon atoms, or a corresponding aza- or oxaalkane-triyl.

[0160] In the oxa- or aza-residues, one of the carbon atoms, along with bonding hydrogens, if present, are replaced by oxygen, nitrogen or NH.

[0161] Preferably in formula (I'):

[0162] R_1 and R_2 , either the same or different, each represent independently a methyl, ethyl, propyl or phenyl group, or together with the carbon atom to which they are connected, jointly represent a cyclohexyl group or a bi- or tricycloalkyl of 7-11 carbon atoms;

[0163] R_3 represents a methyl, ethyl, propyl, phenyl, benzyl, 2-allyl, 2-hydroxyethyl or 2-carboxy-methyl group;

[0164] from R_4 to R_7 , either the same or different, each stand independently for the hydrogen atom, a fluorine, chlorine or bromine atom, or a methyl, isopropyl, trifluoromethyl, hydroxymethyl, benzyl, hydroxy, methoxy, amino, piperidino, morpholino, carboxyl, carboxymethyl, N,N-di-methylcarboxamide, cyano, nitro or phenyl group;

[0165] R_8 represents the hydrogen atom, the chlorine atom, methyl, phenyl, or methoxy group; and/or

[0166] A is one of the groups with formula (II'), (III'), (IV') or (V') where:

[0167] two contiguous points from R_9 to R_{12} represent the condensation position between the oxazinic nucleus in the general formula (I') and the other two groups in addition to R_{13} - R_{16} each represent independently the hydrogen atom, a fluorine, chlorine or bromine atom, or a methyl, ethyl, propyl, isopropyl, trifluoromethyl, hydroxymethyl, benzyl, hydroxy, methoxy, amino, piperidino, morpholino, carboxyl, carboxymethyl, N,N-dimethylcarboxamide, cyano, nitro or phenyl group.


[0168] Specific examples of preferred spiro-indolino-oxazine photochromic compounds useful in the present invention are:

1',3'-dihydro-5,7-dimethoxy-1'n-propyl-3'ethyl-3',4',5'-(and 3',5',6')-trimethyl-spiro[2H-1,4-benzoxazine-2,2'-[2H]indole] (VI');


1,3-dihydro-1,3,3,4,5-(and 1,3,3,5,6)-pentamethyl-spiro[2H-indole-2,3'-[3H]pyrido[3,2-f][1,4]benzoxazine] (VII');

1,3-dihydro-1,3,3,4,5-(and 1,3,3,5,6)-pentamethyl-spiro[2H-indole-2,3'-[3H]naphth[2,1-b][1,4]oxazine] (VIII');


[0169]



-continued



[0170] Naphthopyran photochromic compounds usually have the general structural formula (IX'):




where:

[0171] R_1 to R_{11} , either the same or different, each stand independently for a hydrogen atom; a C_1 - C_5 alkyl group, linear or branched; a similar C_1 - C_5 alkyl group substituted with from 1 to 5 halogen atoms chosen from fluorine, chlorine, bromine or iodine, hydroxy groups, C_1 - C_5 alkoxy groups, C_1 - C_5 carboxy alkyl groups, cyano groups; a C_2 - C_5 alkenyl group; a phenyl group; a benzyl group; a halogen atom chosen from either fluorine, chlorine, bromine or iodine; a hydroxy group; a C_1 - C_5 alkoxy group; an amino group; a monoalkyl(C_1 - C_5)amino group; a dialkyl(C_1 - C_5)amino group; a cyclo-alkyl(C_3 - C_{10})amino group; a piperidine, piperazine or morpholine group; a carboxyl group; a carboxy alkyl(C_1 - C_5)group; a carboxy alkenyl(C_2 - C_5)group; a carboxamide group; a substituted carboxamide N-alkyl(C_1 - C_5)group; a substituted carboxamide N,N-di-alkyl(C_1 - C_5)group; a cyano group; a nitro group; a sulfonic group; a (C_1 - C_5)alkyl sulfonic group; an aryl sulfonic group chosen from ben-

zene sulfonic, p-toluene sulfonic, p-chlorotoluene sulfonic groups; an aryl group chosen from phenyl, biphenyl, naphthyl groups;

[0172] A represents an arenic polycyclic group, chosen from those that can be defined with formula (X'):



two contiguous points from R₁₂ to R₁₅ represent the condensation position between the pyran nucleus in the general formula (IX') and the other two groups in addition to R₁₆-R₁₉ have the same meaning as R₁-R₁₁ in the general formula (IX').

[0173] Preferably in formula (IX'):

[0174] R₁ to R₁₁, either the same or different, each stand independently for the hydrogen atom, a fluorine, chlorine or bromine atom, or a methyl, isopropyl, trifluoromethyl, hydroxymethyl, benzyl, hydroxy, methoxy, amino, piperidino, morpholino, carboxyl, carboxymethyl, N,N-dimethylcarboxamide, cyano, nitro or phenyl group;


[0175] A is one of the groups with formula (X') where:

[0176] two contiguous points from R₁₂ to R₁₅ represent the condensation position between the pyran nucleus in the general formula (IX') and the other two groups in addition to R₁₆-R₁₉ each represent independently the hydrogen atom, a fluorine, chlorine or bromine atom, or a methyl, ethyl, propyl, isopropyl, trifluoromethyl, hydroxymethyl, benzyl, hydroxy, methoxy, amino, piperidino, morpholino, carboxyl, carboxymethyl, N,N-dimethylcarboxamide, cyano, nitro or phenyl group.

[0177] Specific examples of preferred naphthopyran photochromic compounds useful in the present invention are:


[0178] 3,3-diphenyl-3H-naphtho[2,1-b]pyran (XI');

[0179] 3-(2-fluorophenyl)-3-(3-methyl-4-methoxyphenyl)-5-acetoxy-3H-naphtho[2,1-b]pyran (XII');



-continued

(XII')



[0180] 3-(2-fluorophenyl)-3-(4-methoxyphenyl)-3H-naphtho[2,1-b]pyran;

[0181] 3-(2-fluorophenyl)-3-(4'-methoxyphenyl)-8-methoxy-3H-naphtho[2,1-b]pyran;

[0182] 3-(2,4-dimethoxyphenyl)-3,4'-methoxyphenyl)-3H-naphtho[2,1-b]pyran;

[0183] 3-(2-fluorophenyl)-3-(3,4-dimethoxyphenyl)-3H-naphtho[2,1-b]pyran;


[0184] 3-(2-methyl-4-methoxyphenyl)-3-(4-methoxyphenyl)-3H-naphtho[2,1-b]pyran;

[0185] 3-(2-methylphenyl)-3-(4-methoxyphenyl)-3H-naphtho[2,1-b]pyran;

[0186] 3-phenyl-3-(2,4-dimethoxyphenyl)-3H-naphtho[2,1-b]pyran; and


[0187] 3-(2,6-difluorophenyl)-3-(4-methoxyphenyl)-3H-naphtho[2,1-b]pyran.

[0188] Preferred naphthopyranes also include those of the formulae




where each of R₃₁, R₃₂, R₃₃, R₃₄, R₃₅ independently may be hydrogen, a hydrocarbon of 1 to 18 carbon atoms such as phenyl, naphthyl, alkyl, optionally substituted by OH, C₁-C₆alkoxy; —NR'R"; —NO₂; where R' and R" independently are H or C₁-C₁₂alkyl, C₄-C₁₂cycloalkyl, C₇-C₁₃phenylalkyl, or together are tetramethylene or pentamethylene or O-interrupted tetramethylene.

[0189] Benzopyranes, another class of chromenes, include those of the formula



where each of R₄₁, R₄₂, R₄₃, R₄₄, R₄₅ independently may be hydrogen, a hydrocarbon of 1 to 18 carbon atoms such as phenyl, naphthyl, alkyl, optionally substituted by OH, C₁-C₆alkoxy; —NR'R"; —NO₂; where R' and R" independently are H or C₁-C₁₂alkyl, C₄-C₁₂cycloalkyl, C₇-C₁₃phenylalkyl, or together are tetramethylene or pentamethylene or O-interrupted tetramethylene.


[0190] For example, a chromene may be selected from naphthopyrans of the formula



wherein R is H; C₁-C₆alkyl; C₁-C₆alkoxy; —NR'R"; —NO₂; where R' and R" independently are H or C₁-C₁₂alkyl, C₄-C₁₂cycloalkyl, C₇-C₁₃phenylalkyl, or together are tetramethylene or pentamethylene or O-interrupted tetramethylene. Chromenel as used in the examples below is of the above formula where each R is H.


[0191] Preference is given to photochromic dyes (b) that do not contain mercury.

[0192] Preferred sterically hindered amines (HALS) of component (ii) are those comprising at least one radical of the formula IX, X and/or XI




(IX)

-continued



(X)



(XI)


in which

[0193] G is hydrogen or methyl, and

[0194] G₁ and G₂ are hydrogen, methyl or together are oxygen.

[0195] Of particular interest are systems comprising as component (ii) at least one compound from the group of the sterically hindered amines as described under the following classes (a') to (I') which comprise at least one radical of the formula II or III:

(a') A compound of the formula (1a)



(1a)

in which n₁ is a number from 1 to 4, G and G₁, independently of one another, are hydrogen or methyl,

[0196] G₁₁ is hydrogen, O, hydroxyl, NO, —CH₂CN, C₁-C₁₈alkyl, C₃-C₈alkenyl, C₃-C₈alkynyl, C₇-C₁₂aralkyl, C₁-C₁₈alkoxy, C₅-C₁₂cycloalkoxy, C₇-C₁₅phenylalkoxy, C₁-C₈alkanoyl, C₃-C₅alkenoyl, C₁-C₁₈alkanoyloxy, benzyloxy, glycidyl or a group —CH₂CH(OH)—Z, where Z is hydrogen, methyl or phenyl; or G₁₁ is C₁-C₁₈alkoxy, C₅-C₁₂cycloalkoxy or C₇-C₁₅phenylalkoxy each of which is substituted in the aliphatic part by 1-3 OH groups; G₁₁ preferably being C₁-C₁₂alkoxy or cyclohexyloxy or C₂-C₈hydroxyalkoxy or hydrogen or C₁-C₄alkyl or allyl or benzyl or acetyl or acryloyl; especially H, methyl, octyloxy, cyclohexyloxy or 2-hydroxy-2-methyl-propoxy,

[0197] of interest is also G₁₁ being C₁-C₁₈alkoxy, C₅-C₁₂cycloalkoxy, C₇-C₁₅phenylalkoxy, benzyloxy or G₁₁ being C₁-C₁₈alkoxy, C₅-C₁₂cycloalkoxy or C₇-C₁₅phenylalkoxy each of which is substituted in the aliphatic part by 1-3 OH groups;

[0198] and G₁₂, if n₁ is 1, is hydrogen, C₁-C₁₈alkyl which is uninterrupted or interrupted by one or more oxygen

atoms, COO and/or CONH groups, or is cyanoethyl, benzoyl, glycidyl, a monovalent radical of an aliphatic, cycloaliphatic, araliphatic, unsaturated or aromatic carboxylic acid, carbamic acid or phosphorus-containing acid or a monovalent silyl radical, preferably a radical of an aliphatic carboxylic acid having 2 to 18 carbon atoms, of a cycloaliphatic carboxylic acid having 7 to 15 carbon atoms, or an α,β -unsaturated carboxylic acid having 3 to 5 carbon atoms or of an aromatic carboxylic acid having 7 to 15 carbon atoms, where each carboxylic acid can be substituted in the aliphatic, cycloaliphatic or aromatic moiety by 1 to 3 $-\text{COOZ}_{12}$ groups, in which Z_{12} is H, C_1 - C_{20} alkyl, C_3 - C_{12} alkenyl, C_5 - C_7 cycloalkyl, phenyl or benzyl,

[0199] G_{12} , if n_1 is 2, is C_2 - C_{12} alkylene, C_4 - C_{12} alkenylene, xylylene, a divalent radical of an aliphatic, cycloaliphatic, araliphatic or aromatic dicarboxylic acid, dicarbamic acid or phosphorus-containing acid or a divalent silyl radical, preferably a radical of an aliphatic dicarboxylic acid having 2 to 36 carbon atoms, or a cycloaliphatic or aromatic dicarboxylic acid having 8-14 carbon atoms or of an aliphatic, cycloaliphatic or aromatic dicarbamic acid having 8-14 carbon atoms, where each dicarboxylic acid may be substituted in the aliphatic, cycloaliphatic or aromatic moiety by one or two $-\text{COOZ}_{12}$ groups,

[0200] G_{12} , if n_1 is 3, is a trivalent radical of an aliphatic, cycloaliphatic or aromatic tricarboxylic acid, which may be substituted in the aliphatic, cycloaliphatic or aromatic moiety by $-\text{COOZ}_{12}$, of an aromatic tricarbamic acid or of a phosphorus-containing acid, or is a trivalent silyl radical, preferred radicals including triacyl radicals of nitrilo triacetic acid of benzene tricarboxylic acid,

[0201] and G_{12} , if n_1 is 4, is a tetravalent radical of an aliphatic, cycloaliphatic or aromatic tetracarboxylic acid.

[0202] The carboxylic acid radicals mentioned above are in each case taken to mean radicals of the formula $(-\text{CO})_x\text{R}$, where x is as defined above for n_1 , and the meaning of R arises from the definition given above.

[0203] Alkyl with up to 20 carbon atoms is, for example, methyl, ethyl, n-propyl, n-butyl, sec-butyl, tert-butyl, n-hexyl, n-octyl, 2-ethylhexyl, n-nonyl, n-decyl, n-undecyl, n-dodecyl, n-tridecyl, n-tetradecyl, n-hexadecyl or n-octadecyl.

[0204] C_1 - C_{18} alkoxy G_{11} is, for example, methoxy, ethoxy, propoxy, isopropoxy, butoxy, isobutoxy, pentoxy, isopentoxy, hexoxy, heptoxy, octoxy, decyloxy, dodecyloxy, tetradecyloxy, hexadecyloxy and octadecyloxy. C_6 - C_{12} alkoxy, in particular heptoxy and octoxy, is preferred.

[0205] C_5 - C_{12} cycloalkoxy G_{11} is, for example, cyclopentoxy, cyclohexoxy, cycloheptoxy, cyclooctoxy, cyclodecyloxy and cyclododecyloxy. C_5 - C_8 cycloalkoxy, in particular cyclopentoxy and cyclohexoxy, is preferred.

[0206] C_7 - C_8 phenylalkoxy is, for example, benzyloxy.

[0207] G_{11} as C_1 - C_{18} alkoxy, C_5 - C_{12} cycloalkoxy or C_7 - C_{15} phenylalkoxy substituted in the aliphatic part by 1-3 OH groups is a radical formed by abstraction of a carbon-bonded hydrogen atom preferably from 2-methyl-2-propanol (tert.-butanol), 2-propanol, 2,2-dimethyl-1-propanol, 2-methyl-2-butanol, ethanol, 1-propanol, 1-butanol, 1-pentanol, 1-hexanol, 1-nonanol, 1-decanol, 1-dodecanol, 1-octadecanol, 2-butanol, 2-pentanol, 2-ethyl-1-hexanol, cyclohexanol, cyclooctanol, allyl alcohol, phenethyl alcohol or


1-phenyl-1-ethanol; 1,2-ethanediol, 1,2-propanediol, 1,3-propanediol, 1,2-butanediol, 1,3-butanediol, 1,4-butanediol, 2,2-dimethyl-1,3-propanediol, 1,2-cyclohexanediol, 1,3-cyclohexanediol or 1,4-cyclohexanediol; glycerol, 1,1,1-tris(hydroxymethyl)methane, 2-ethyl-2-(hydroxymethyl)-1,3-propanediol, 1,2,4-butanetriol or 1,2,6-hexanetriol. Most preferred hydroxy substituted G_{11} is 2-hydroxy-2-methylpropoxy.

[0208] Examples of several G_{12} radicals are given below.

[0209] If G_{12} is a monovalent radical of a carboxylic acid, it is, for example, an acetyl, caproyl, stearoyl, acryloyl, methacryloyl, benzoyl or β -(3,5-di-tert-butyl-4-hydroxyphenyl)propionyl radical.

[0210] If G_{12} is a monovalent silyl radical, it is, for example, a radical of the formula $-(C_jH_{2j})-Si(Z')_2Z''$, in which j is an integer in the range from 2 to 5, and Z' and Z'' , independently of one another, are C_1 - C_4 alkyl or C_1 - C_4 alkoxy.

[0211] If G_{12} is a divalent radical of a dicarboxylic acid, it is, for example, a malonyl, succinyl, glutaryl, adipoyl, suberoyl, sebacoyl, maleoyl, itaconyl, phthaloyl, dibutylmalonyl, dibenzylmalonyl, butyl(3,5-di-tert-butyl-4-hydroxybenzyl)malonyl or bicycloheptenedicarbonyl radical or a group of the formula




[0212] If G_{12} is a trivalent radical of a tricarboxylic acid, it is, for example, a trimellitoyl, citryl or nitrilotriacetyl radical.

[0213] If G_{12} is a tetravalent radical of a tetracarboxylic acid, it is, for example, the tetravalent radical of butane-1,2,3,4-tetracarboxylic acid or of pyromellitic acid.

[0214] If G_{12} is a divalent radical of a dicarbamic acid, it is, for example, hexamethylenedicarbamoyl or 2,4-toluylenedicarbamoyl radical.

[0215] Preference is given to compounds of the formula (1a) in which G and G_1 are hydrogen, G_{11} is hydrogen or methyl, n_1 is 2 and G_{12} is the diacyl radical of an aliphatic dicarboxylic acid having 4-12 carbon atoms.


(b') A compound of the formula (1b)



(1b)

in which n_2 is the number 1, 2 or 3, and G, G_1 and G_{11} are as defined under (a'),


[0216] G_{13} is hydrogen, C_1 - C_{12} alkyl, C_2 - C_3 hydroxyalkyl, C_5 - C_7 cycloalkyl, C_7 - C_8 aralkyl, C_1 - C_{18} alkanoyl, C_3 - C_5 alkenoyl, benzoyl or a group of the formula



and G_{14} , if n_2 is 1, is hydrogen, C_1 - C_{18} alkyl, C_3 - C_8 alkenyl, C_5 - C_7 cycloalkyl, C_1 - C_4 alkyl which is substituted by a hydroxyl, cyano, alkoxycarbonyl or carbamide group or group of the formula $-\text{CONH}-\text{Z}$, or G_{14} is glycidyl, a group of the formula $-\text{CH}_2-\text{CH}(\text{OH})-\text{Z}$ or of the formula $-\text{CONH}-\text{Z}$, in which Z is hydrogen, methyl or phenyl or $\text{CH}_2-\text{OZ}_{14}$ with Z_{14} being hydrogen or C_1 - C_{18} alkyl;

[0217] G_{14} , if n_2 is 2, is C_2 - C_{12} alkylene, C_6 - C_{12} arylene, xylylene, a $-\text{CH}_2-\text{CH}(\text{OH})-\text{CH}_2$ group or a $-\text{CH}_2-\text{CH}(\text{OH})-\text{CH}_2-\text{O}-\text{D}-\text{O}-$ group, in which D is C_2 - C_{10} alkylene, C_6 - C_{15} arylene, C_6 - C_{12} cycloalkylene, or, provided that G_{13} is not alkanoyl, alkenoyl or benzoyl, G_{14} can alternatively be 1-oxo- C_2 - C_{12} alkylene, a divalent radical of an aliphatic, cycloaliphatic or aromatic dicarboxylic acid or dicarbamic acid or alternatively the group $-\text{CO}-$,

[0218] G_{14} , if n_2 is 3, is a group



or, if n_2 is 1, G_{13} and G_{14} together can be the divalent radical of an aliphatic, cycloaliphatic or aromatic 1,2- or 1,3-dicarboxylic acid.

[0219] Some examples for the radicals G_{13} , G_{14} and D are given below.

[0220] Any alkyl substituents are as defined above for (a').

[0221] Any C_5 - C_7 cycloalkyl substituents are, in particular, cyclohexyl.

[0222] C_7 - C_8 aralkyl G_{13} is, in particular, phenylethyl or especially benzyl.

[0223] C_2 - C_3 hydroxyalkyl G_{13} is, in particular, 2-hydroxyethyl or 2-hydroxypropyl.

[0224] C_1 - C_{18} alkanoyl G_{13} is, for example, formyl, acetyl, propionyl, butyryl, octanoyl, dodecanoyl, hexadecanoyl, octadecanoyl, but preferably acetyl, and C_3 - C_5 alkenoyl G_{13} is, in particular, acryloyl.

[0225] C_2 - C_8 alkenyl G_{14} is, for example, allyl, methallyl, 2-butenyl, 2-pentenyl, 2-hexenyl or 2-octenyl.


[0226] G_{14} as a hydroxyl-, cyano-, alkoxycarbonyl- or carbamide-substituted C_1 - C_4 alkyl can be, for example, 2-hydroxyethyl, 2-hydroxypropyl, 2-cyanoethyl, methoxycarbonylmethyl, 2-ethoxycarbonyl ethyl, 2-aminocarbonylpropyl or 2-(dimethylaminocarbonyl)ethyl.

[0227] Any C_2 - C_{12} alkylene radicals are, for example, ethylene, propylene, 2,2-dimethylpropylene, tetramethylene, hexamethylene, octamethylene, decamethylene or dodecamethylene.


[0228] Any C_6 - C_{15} arylene substituents are, for example, o-, m- or p-phenylene, 1,4-naphthylene or 4,4'-diphenylene.

[0229] C_6 - C_{12} cycloalkylene is, in particular, cyclohexylene.

[0230] G_{14} as 1-oxo- C_2 - C_{12} alkylene is preferably a group



(c') A compound of the formula (1c)





in which n_3 is the number 1 or 2, G, G_1 and G_{11} are as defined under (a'), and G_{15} and G'_{15} if n_3 is 1, are independently C_1 - C_{12} alkyl, C_2 - C_{12} alkenyl, C_7 - C_{12} aralkyl, or G_{15} is also hydrogen, or G_{15} and G'_{15} together are C_2 - C_8 alkylene, C_5 - C_{15} alkenylene, C_2 - C_8 hydroxyalkylene or C_4 - C_{22} acyloxyalkylene, and if n_3 is 2, G_{15} and G'_{15} together are the $(-\text{CH}_2)_2\text{C}(\text{CH}_2)_2$ group.

[0231] C_2 - C_8 alkylene or C_2 - C_8 hydroxyalkylene G_{15} and G'_{15} is, for example, ethylene, 1-methylethylene, propylene, 2-ethylpropylene or 2-ethyl-2-hydroxymethylpropylene.

[0232] C_4 - C_{22} acyloxyalkylene G_{15} and G'_{15} is, for example, 2-ethyl-2-acetoxymethylpropylene.

(d') A compound of the formula (1d-1), (1d-2) or (1d-3),





in which n_4 is the number 1 or 2, G, G_1 and G_{11} are as defined under (a'),

[0233] G_{16} is hydrogen, C_1 - C_{12} alkyl, allyl, benzyl, glycidyl or C_2 - C_6 alkoxyalkyl, and

[0234] G_{17} , if n_4 is 1, is hydrogen, C_1 - C_{12} alkyl, C_3 - C_5 alkenyl, C_7 - C_9 aralkyl, C_5 - C_7 cycloalkyl, C_2 - C_4 hydroxyalkyl, C_2 - C_6 alkoxyalkyl, C_6 - C_{10} aryl, glycidyl or a group of the formula $-(CH_2)_p-COO-Q$ or $-(CH_2)_p-O-CO-Q$, in which p is 1 or 2, and Q is C_1 - C_4 alkyl or phenyl, and

[0235] G_{17} , if n_4 is 2, is C_2 - C_{12} alkylene, C_4 - C_{12} alkenylene, C_6 - C_{12} arylene, a group of the formula $-CH_2-CH(OH)-CH_2-O-D'-O-CH_2-CH(OH)-CH_2-$, in which D' is C_2 - C_{10} alkylene, C_6 - C_{15} arylene or C_6 - C_{12} cycloalkylene, or a group of the formula $-CH_2CH(OD'')CH_2-(OCH_2-CH(OD'')CH_2)_2-$, in which D'' is hydrogen, C_1 - C_{18} alkyl, allyl, benzyl, C_2 - C_{12} alkanoyl or benzoyl,

[0236] T_1 and T_2 , independently of one another, are hydrogen, C_1 - C_{18} alkyl or unsubstituted or halogen- or C_1 - C_4 alkyl-substituted C_6 - C_{10} aryl or C_7 - C_9 aralkyl, or

[0237] T_1 and T_2 together with the carbon atom bonding them form a C_5 - C_{14} cycloalkane ring.

[0238] Any C_1 - C_{12} alkyl substituents are, for example, methyl, ethyl, n-propyl, n-butyl, sec-butyl, tert-butyl, n-hexyl, n-octyl, 2-ethylhexyl, n-nonyl, n-decyl, n-undecyl or n-dodecyl.

[0239] Any C_1 - C_{18} alkyl substituents can be, for example, the abovementioned groups and in addition, for example, n-tridecyl, n-tetradecyl, n-hexadecyl or n-octadecyl.

[0240] Any C_2 - C_6 alkoxyalkyl substituents are, for example, methoxymethyl, ethoxymethyl, propoxymethyl, tert-butoxymethyl, ethoxyethyl, ethoxypropyl, n-butoxyethyl, tert-butoxyethyl, isopropoxyethyl or propoxypropyl.

[0241] C_3 - C_5 alkenyl G_{17} is, for example, 1-propenyl, allyl, methallyl, 2-butenyl or 2-pentenyl.

[0242] C_7 - C_9 aralkyl G_{17} , T_1 and T_2 are, in particular, phenethyl or especially benzyl. If T_1 and T_2 together with the

carbon atom form a cycloalkane ring, this can be, for example, a cyclopentane, cyclohexane, cyclooctane or cyclododecane ring.

[0243] C_2 - C_4 hydroxyalkyl G_{17} is, for example, 2-hydroxyethyl, 2-hydroxypropyl, 2-hydroxybutyl or 4-hydroxybutyl.

[0244] C_6 - C_{10} aryl G_{17} , T_1 and T_2 are, in particular, phenyl or α - or β -naphthyl, which are unsubstituted or substituted by halogen or C_1 - C_4 alkyl.

[0245] C_2 - C_{12} alkylene G_{17} is, for example, ethylene, propylene, 2,2-dimethylpropylene, tetramethylene, hexamethylene, octamethylene, decamethylene or dodecamethylene.


[0246] C_4 - C_{12} alkenylene G_{17} is, in particular, 2-butenylene, 2-pentenylene or 3-hexenylene.

[0247] C_6 - C_{12} arylene G_{17} is, for example, o-, m- or p-phenylene, 1,4-naphthylene or 4,4'-diphenylene.


[0248] C_2 - C_{12} alkanoyl D'' is, for example, propionyl, butyryl, octanoyl, dodecanoyl, but preferably acetyl.

[0249] C_2 - C_{10} alkylene, C_6 - C_5 arylene or C_6 - C_{12} cycloalkylene D' have, for example, one of the definitions given for D under (b').

(e') A compound of the formula (1e)



in which n_5 is the number 1 or 2, and G_{18} is a group of the formula



in which G and G_{11} are as defined under (a'), and G_1 and G_2 are hydrogen, methyl or, together, are a substituent =O,

[0250] E is $-O-$ or $-ND'''-$,

[0251] A is C_2 - C_6 alkylene or $-(CH_2)_3-O-$ and


[0252] x_1 is the number 0 or 1,

[0253] D^{III} is hydrogen, C₁-C₁₂alkyl, C₂-C₁₂alkylene-N(D^V)₂, C₂-C₅hydroxyalkyl or C₅-C₇cycloalkyl, where D^V, independently, is hydrogen or butyl,

[0254] G₁₉ is identical to G₁₈ or is one of the groups —N(G₂₁)(G₂₂), —OG₂₃, —N(H)(CH₂OG₂₃) or —N(CH₂OG₂₃)₂,

[0255] G₂₀, if n₅=1, is identical to G₁₈ or G₁₉ and, if n₅=2, is an —E—D^{IV}—E— group, in which D^{IV} is C₂-C₈alkylene or C₂-C₈alkylene which is interrupted by 1 or 2 —NG₂₁— groups,

[0256] G₂₁ is hydrogen, C₁-C₁₂alkyl, cyclohexyl, benzyl or C₁-C₄-hydroxyalkyl or a group of the formula



[0257] G₂₂ is C₁-C₁₂alkyl, cyclohexyl, benzyl or C₁-C₄hydroxyalkyl, and

[0258] G₂₃ is hydrogen, C₁-C₁₂alkyl or phenyl, or G₂₁, and G₂₂ together are C₄-C₅alkylene or C₄-C₅oxaalkylene, for example —CH₂CH₂—O—CH₂CH₂—, or a group of the formula —CH₂CH₂—N(G₁₁)—CH₂CH₂—.

[0259] Some examples of the several variables in the formula (1e) are given below.

[0260] Any C₁-C₁₂alkyl substituents are, for example, methyl, ethyl, n-propyl, n-butyl, sec-butyl, tert-butyl, n-hexyl, n-octyl, 2-ethylhexyl, n-nonyl, n-decyl, n-undecyl or n-dodecyl.


[0261] Any hydroxyalkyl substituents are, for example, 2-hydroxyethyl, 2-hydroxypropyl, 3-hydroxypropyl, 2-hydroxybutyl or 4-hydroxybutyl.

[0262] Any C₅-C₇cycloalkyl substituents are, for example, cyclopentyl, cyclohexyl or cycloheptyl. Cyclohexyl is preferred.

[0263] C₂-C₆alkylene A is, for example, ethylene, propylene, 2,2-dimethylpropylene, tetramethylene or hexamethylene.

[0264] If G₂₁ and G₂₂ together are C₄-C₅alkylene or oxaalkylene, they are, for example, tetramethylene, pentamethylene or 3-oxapentamethylene.

(f) A compound of the formula (1f)



wherein G₁₁ is as defined under (a').


[0265] (g') Oligomeric or polymeric compounds whose recurring structural unit contains a 2,2,6,6-tetraalkylpiperidiny radical, in particular polyesters, polyethers, polyamides, polyamines, polyurethanes, polyureas, polyaminotriazines, poly(meth)acrylates, poly(meth)acrylamides and copolymers thereof which contain such radicals.

[0266] Examples of 2,2,6,6-polyalkylpiperidine compounds from this class are the compounds of the following formulae. m₁ to m₁₄ is a number from 2 to about 200, preferably 2 to 100, for example 2 to 50, 2 to 40, 3 to 40 or 4 to 10.

[0267] The meanings of the end groups which saturate the free valences in the oligomeric or polymeric compounds listed below depend on the processes used for the preparation of said compounds. The end groups can also in addition be modified after the synthesis of the compounds.


[0268] Examples for polymeric compounds are:

[0269] 1) A compound of the formula (1g)




wherein G_{24} , G_{25} , G_{26} , G_{27} and G_{28} , independently of one another, are a direct bond or C_1 - C_{10} alkylene, G_{11} is as defined under (a') and m_{17} is a number from 1 to 50.


[0270] In the compound of the formula (1g), the end group bonded to the $>C=O$ group can be, for example,



and the end group bonded to the oxygen can be, for example



[0271] 2) Compound of the formula (2g)




in which the index m_{18} ranges from 1 to 15;

[0272] R_{12} is C_2 - C_{12} alkylene, C_4 - C_{12} alkenylene, C_5 - C_7 cycloalkylene, C_5 - C_7 cycloalkylene-di(C_1 - C_4 alkylene), C_1 - C_4 alkylenedi(C_5 - C_7 cycloalkylene), phenylenedi(C_1 - C_4 alkylene) or C_4 - C_{12} alkylene interrupted by 1,4-piperazinediyl, $-O-$ or $>N-X_1$ with X_1 being C_1 - C_{12} acyl or (C_1 - C_{12} alkoxy)carbonyl or having one of the definitions of R_{14} given below except hydrogen; or R_{12} is a group of the formula (2g') or (2g'');




(2g')



(2g'')


X_2 being C_1 - C_{18} alkyl, C_5 - C_{12} cycloalkyl which is unsubstituted or substituted by 1, 2 or 3 C_1 - C_4 alkyl; phenyl which is unsubstituted or substituted by 1, 2 or 3 C_1 - C_4 alkyl or C_1 - C_4 alkoxy; C_7 - C_9 phenylalkyl which is unsubstituted or substituted on the phenyl by 1, 2 or 3 C_1 - C_4 alkyl; and

[0273] the radicals X_3 being independently of one another C_2 - C_{12} alkylene; the radicals A are independently of one another $-OR_{13}$, $-N(R_{14})(R_{15})$ or a group of the formula (2g''');



(2g''')

R_{13} , R_{14} and R_{15} , which are identical or different, are hydrogen, C_1 - C_{18} alkyl, C_5 - C_{12} cycloalkyl which is unsubstituted or substituted by 1, 2 or 3 C_1 - C_4 alkyl; C_3 - C_{18} alkenyl, phenyl which is unsubstituted or substituted by 1, 2 or 3 C_1 - C_4 alkyl or C_1 - C_4 alkoxy; C_7 - C_9 phenylalkyl which is unsubstituted or substituted on the phenyl by 1, 2 or 3 C_1 - C_4 alkyl; tetrahydrofurfuryl or C_2 - C_4 alkyl which is substituted in the 2, 3 or 4 position by $-OH$, C_1 - C_8 alkoxy, di(C_1 - C_4 alkyl)amino or a group of the formula (2g^{IV});

(2g^{IV})


with Y being $-O-$, $-CH_2-$, $-CH_2CH_2-$ or $>N-CH_3$,

[0274] or $-N(R_{14})(R_{15})$ is additionally a group of the formula (2g^{IV});

[0275] X is $-O-$ or $>N-R_{16}$;

[0276] R_{16} is hydrogen, C_1 - C_{18} alkyl, C_3 - C_{18} alkenyl, C_5 - C_{12} cycloalkyl which is unsubstituted or substituted by 1, 2 or 3 C_1 - C_4 alkyl; C_7 - C_9 phenylalkyl which is unsub-

stituted or substituted on the phenyl by 1, 2 or 3 C₁-C₄alkyl; tetrahydrofurfuryl, a group of the formula (2g^v),




or C₂-C₄alkyl which is substituted in the 2, 3 or 4 position by —OH, C₁-C₈alkoxy, di(C₁-C₄alkyl)amino or a group of the formula (2g^{iv});


[0277] R₁₁ has one of the definitions given for R₁₆; and

[0278] the radicals B have independently of one another one of the definitions given for A.

[0279] 3) A compound of the formula (3g)




in which G₁₁ is as defined under (a'), G₂₉ and G₃₂, independently of one another, are a direct bond or a —N(X₁)CO—X₂—CO—N(X₃)— group, where X₁ and X₃, independently of one another, are hydrogen, C₁-C₈alkyl, C₅-C₁₂cycloalkyl, phenyl, C₇-C₉phenylalkyl or a group of the formula





and X₂ is a direct bond or C₁-C₄alkylene, G₃₀, G₃₁, G₃₄ and G₃₅, independently of one another, are hydrogen, C₁-C₃₀alkyl, C₅-C₁₂cycloalkyl or phenyl, G₃₃ is hydrogen, C₁-C₃₀alkyl, C₅-C₁₂cycloalkyl, C₇-C₉phenylalkyl, phenyl or a group of the formula (3g), and m₁₉ is a number from 1 to 50.

[0280] In the compounds of the formula (3g), the end group bonded to the 2,5-dioxypiperidine ring can be, for example, hydrogen, and the end group bonded to the —C(G₃₄)(G₃₅)— radical can be, for example,




[0281] 4) A product obtainable by reacting an intermediate product, obtained by reaction of a polyamine of the formula (4g) with cyanuric chloride, with a compound of the formula (4g')



in which m'₂₀, m''₂₀ and m'''₂₀, independently of one another, are a number from 2 to 12, G₃₆ is hydrogen, C₁-C₁₂alkyl, C₅-C₁₂cycloalkyl, phenyl or C₇-C₉phenylalkyl, and G₁₁ is as defined under (a').

[0282] In general, the above reaction product can be represented for example by a compound of the following 3 formulae. It can also be in the form of a mixture of these three compounds:

[0283] 5) A compound of the formula (5g)




in which G_{11} is as defined under (a'), G_{37} is C_1 - C_{10} alkyl, C_5 - C_{12} cycloalkyl, C_1 - C_4 alkyl-substituted C_5 - C_{12} cycloalkyl, phenyl or C_1 - C_{10} alkyl-substituted phenyl, G_{38} is C_3 - C_{10} alkylene and m_{21} is a number from 1 to 50.

[0284] In the compounds of the formula (5g), the terminal group bonded to the silicon atom can be, for example, $(G_{37})_3Si-O-$, and the terminal group bonded to the oxygen can be, for example, $-Si(G_{37})_3$.


[0285] The compounds of the formula (5g) can also be in the form of cyclic compounds if m_{21} is a number from 3 to 10, i.e. the free valences shown in the structural formula then form a direct bond.

[0286] 6) A compound of the formula (6g)



where E is $-O-$ or $-ND^m-$ as defined under (e'), T_3 is ethylene or 1,2-propylene, is the repeating structural unit derived from an alpha-olefin copolymer with an alkyl acrylate or methacrylate; preferably a copolymer of ethylene and ethyl acrylate, and where k is 2 to 100.

[0287] 7) A compound of the formula (7g)




[0288] wherein m is 1 to 100;

[0289] G_{50} is straight or branched chain alkylene of 1 to 18 carbon atoms, cycloalkylene of 5 to 8 carbon atoms,


cycloalkenylene of 5 to 8 carbon atoms, alkenylene of 3 to 18 carbon atoms, a straight or branched chain alkylene of 1 to 4 carbon atoms substituted by phenyl or by phenyl substituted by one or two alkyl of 1 to 4 carbon atoms, with the proviso that in formula (7g) successive hindered amine moieties can be oriented in either a head to head or head to tail fashion;

[0290] T_4 is hydrogen or



[0291] G_{55} is a straight or branched chain alkylene of 1 to 18 carbon atoms, cycloalkylene or cycloalkenylene of 5 to 8 carbon atoms, phenylene or $-NH$ -alkylene- $NH-$ of 2 to 18 carbon atoms including 5-amino-1-aminomethyl-1,3,3-trimethylcyclohexane and $-NH$ -xylylene- $NH-$;

[0292] T_5 is alkyl of 1 to 4 carbon atoms;



[0293] In the above shown oligomeric and polymeric compounds,


[0294] examples of alkyl are methyl, ethyl, propyl, isopropyl, n-butyl, sec-butyl, isobutyl, tert-butyl, 2-ethylbutyl, n-pentyl, isopentyl, 1-methylpentyl, 1,3-dimethylbutyl, n-hexyl, 1-methylhexyl, n-heptyl, isoheptyl, 1,1,3,3-tetramethylbutyl, 1-methylheptyl, 3-methylheptyl, n-octyl, 2-ethyl-hexyl, 1,1,3-trimethylhexyl, 1,1,3,3-tetramethylpentyl, nonyl, decyl, undecyl, 1-methylundecyl, dodecyl, 1,1,3,3,5,5-hexamethylhexyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, octadecyl, eicosyl and docosyl;

[0295] examples of cycloalkyl are cyclopentyl, cyclohexyl, cycloheptyl and cyclooctyl;

[0296] an example of C_7 - C_9 phenylalkyl is benzyl; and


[0297] examples of alkylene are ethylene, propylene, trimethylene, tetramethylene, pentamethylene, 2,2-dimethyltrimethylene, hexamethylene, trimethylhexamethylene, octamethylene and decamethylene.

[0298] (h') A compound of the formula (1h)




in which n_6 is the number 1 or 2, G and G_{11} , are as defined under (a'), and G_{14} is as defined under (b'), but G_{14} cannot be $-\text{CONH}-\text{Z}$ and $-\text{CH}_2-\text{CH}(\text{OH})-\text{CH}_2-\text{O}-\text{D}-\text{O}-$.

[0299] (i') A compound of the formula (1i)



wherein the radicals G_{39} , independently of one another, are a group of the formula (1i-1)



in which G_{40} is C_1-C_{12} alkyl or C_5-C_{12} cycloalkyl, G_{41} is C_2-C_{12} alkylene and G_{42} is as defined for G_{11} above.

[0300] Alkyl is for example C_1-C_4 alkyl, in particular methyl, ethyl, propyl or butyl.

[0301] Cycloalkyl is preferably cyclohexyl.


[0302] Alkylene is for example ethylene, propylene, trimethylene, tetramethylene, pentamethylene, 2,2dimethyltrimethylene or hexamethylene.

[0303] Alkenyl is preferably allyl.

[0304] Phenylalkyl is preferably benzyl.

[0305] Acyl is preferably acetyl.

[0306] (j') A compound of the formula (1j)




wherein G, G_{11} are as defined above and

[0307] when n_7 is 1, T_7 is hydrogen, C_1-C_{12} alkyl, C_3-C_5 alkenyl, C_7-C_9 aralkyl, C_5-C_7 cycloalkyl, C_2-C_4 hydroxyalkyl, C_2-C_6 alkoxyalkyl, C_6-C_{10} aryl, glycidyl, a group of the formula $-(\text{CH}_2)_t-\text{COO}-\text{Q}$ or of the formula $-(\text{CH}_2)_t-\text{O}-\text{CO}-\text{Q}$ wherein t is 1 or 2, and Q is C_1-C_4 alkyl or phenyl; or


[0308] when n_7 is 2, T_7 is C_2-C_{12} alkylene, C_6-C_{12} arylene, a group $-\text{CH}_2\text{CH}(\text{OH})-\text{CH}_2-\text{O}-\text{X}-\text{O}-\text{CH}_2-\text{CH}(\text{OH})-\text{CH}_2-$ wherein X is C_2-C_{10} alkylene, C_6-C_{12} arylene or C_6-C_{12} cycloalkylene, or a group $-\text{CH}_2\text{CH}(\text{OZ}')\text{CH}_2-(\text{OCH}_2-\text{CH}(\text{OZ}')\text{CH}_2)_2-$ wherein Z' is hydrogen, C_1-C_{18} alkyl, allyl, benzyl, C_2-C_{12} alkanoyl or benzoyl.

[0309] (k') A compound of the formula (1k)



wherein G, G_{11} are as defined above.

[0310] (l') A compound of the formula (1l)



wherein G, G_{11} are as defined above.

[0311] Examples for HALS are the compounds bis(2,2,6,6-tetramethyl-4-piperidyl)sebacate, bis(2,2,6,6-tetramethyl-4-piperidyl)succinate, bis(1,2,2,6,6-pentamethyl-4-piperidyl)sebacate, bis(1-octyloxy-2,2,6,6-tetramethyl-4-

piperidyl)sebacate, bis(1,2,2,6,6-pentamethyl-4-piperidyl) n-butyl-3,5-di-tert-butyl-4-hydroxybenzylmalonate, the condensate of 1-(2-hydroxyethyl)-2,2,6,6-tetramethyl-4-hydroxypiperidine and succinic acid, linear or cyclic condensates of N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-tert-octylamino-2,6-dichloro-1,3,5-triazine, tris(2,2,6,6-tetramethyl-4-piperidyl)nitrotriacetate, tetrakis(2,2,6,6-tetramethyl-4-piperidyl)-1,2,3,4-butanetetracarboxylate, 1,1'-(1,2-ethanediyl)-bis(3,3,5,5-tetramethylpiperazinone), 4-benzoyl-2,2,6,6-tetramethylpiperidine, 4-stearoyloxy-2,2,6,6-tetramethylpiperidine, bis(1,2,2,6,6-pentamethylpiperidyl)-2-n-butyl-2-(2-hydroxy-3,5-di-tert-butylbenzyl)-malonate, 3-n-octyl-7,7,9,9-tetramethyl-1,3,8-triazaspiro [4.5]decane-2,4-dione, bis(1-octyloxy-2,2,6,6-tetramethylpiperidyl)sebacate, bis(1-octyloxy-2,2,6,6-tetramethylpiperidyl)succinate, linear or cyclic condensates of N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-morpholino-2,6-dichloro-1,3,5-triazine, the condensate of 2-chloro-4,6-bis(4-n-butylamino-2,2,6,6-tetramethylpiperidyl)1,3,5-triazine and 1,2-bis(3-aminopropylamino)-ethane, the condensate of 2-chloro-4,6-di-(4-n-butylamino-1,2,2,6,6-pentamethylpiperidyl)-1,3,5-triazine and 1,2-bis(3-aminopropylamino)ethane, 8-acetyl-3-dodecyl-7,7,9,9-tetramethyl-1,3,8-triazaspiro[4.5]decane-2,4-dione, 3-dodecyl-1-(2,2,6,6-tetramethyl-4-piperidyl)pyrrolidine-2,5-dione, 3-dodecyl-1-(1,2,2,6,6-pentamethyl-4-piperidyl)pyrrolidine-2,5-dione, 5-(2-ethylhexanoyl)-oxymethyl-3,3,5-trimethyl-2-morpholinone, 1-(2-hydroxy-2-methylpropoxy)-4-octadecanoyloxy-2,2,6,6-tetramethylpiperidine, 1,3,5-tris(N-cyclohexyl-N-(2,2,6,6-tetramethylpiperazin-3-on-4-yl)amino)-s-triazine, 1,3,5-tris(N-cyclohexyl-N-(1,2,2,6,6-pentamethylpiperazin-3-on-4-yl)amino)-s-triazine, the reaction product of 2,4-bis[(1-cyclohexyloxy-2,2,6,6-piperidin-4-yl)butylamino]-6-chloro-s-triazine with N,N'-bis(3-aminopropyl)ethylenediamine), a mixture of 4-hexadecyloxy- and 4-stearoyloxy-2,2,6,6-tetramethylpiperidine, a condensate of N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-cyclohexylamino-2,6-dichloro-1,3,5-triazine, a condensate of 1,2-bis(3-aminopropylamino)ethane and 2,4,6-trichloro-1,3,5-triazine as well as 4-butylamino-2,2,6,6-tetramethylpiperidine (CAS Reg. No. [136504-96-6]); a condensate of 1,6-hexanediamine and 2,4,6-trichloro-1,3,5-triazine as well as N,N-dibutylamine and 4-butylamino-2,2,6,6-tetramethylpiperidine (CAS Reg. No. [192268-64-7]); N-(2,2,6,6-tetramethyl-4-piperidyl)-n-dodecylsuccinimide; N-(1,2,2,6,6-pentamethyl-4-piperidyl)-n-dodecylsuccinimide; 2-undecyl-7,7,9,9-tetramethyl-1-oxa-3,8-diaza-4-oxo-spiro [4.5]decane; 5-(2-ethylhexanoyl)oxymethyl-3,3,5-trimethyl-2-morpholinone; a reaction product of 7,7,9,9-tetramethyl-2-cycloundecyl-1-oxa-3,8-diaza-4-oxospiro-[4.5]decane and epichlorohydrin, 1,1-bis(1,2,2,6,6-pentamethyl-4-piperidyl)oxycarbonyl-2-(4-methoxyphenyl)ethene, N,N'-bis-formyl-N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine, a diester of 4-methoxymethylenemalonic acid with 1,2,2,6,6-pentamethyl-4-hydroxypiperidine, poly[methylpropyl-3-oxy-4-(2,2,6,6-tetramethyl-4-piperidyl)]siloxane, a reaction product of maleic acid anhydride- α -olefin copolymer with 2,2,6,6-tetramethyl-4-aminopiperidine or 1,2,2,6,6-pentamethyl-4-aminopiperidine.

[0312] Preferred HALS are of molecular weight 400 g/mol or higher; especially preferred are oligomeric HALS of the classes mentioned above, e.g. of molecular weight of 1000 g/mol or higher, e.g. 1500-15000 g/mol.

[0313] Especially preferred are those of the alkoxyamine class (NOR-HALS), e.g. compound H1 as used in the examples below (also disclosed in Example 2 of U.S. Pat. No. 6,117,995).

[0314] An appropriate combination of the photochromic dyes with UV absorber and a HALS provides an exceptional improvement of the long-term photostability, achieving a lifetime thirty times longer than the unstabilized system.

[0315] The components used in the invention can be pure or mixtures of compounds.

[0316] Components (c) to be used within present invention basically are known materials, many are commercially available.

[0317] Optional further ingredients include further stabilizers, antioxidants, softeners, flame retardants etc. as commonly used for polymeric material, such as the following components:

1. Antioxidants

[0318] 1.1. Alkylated monophenols, for example 2,6-di-tert-butyl-4-methylphenol, 2-tert-butyl-4,6-di-methylphenol, 2,6-di-tert-butyl-4-ethylphenol, 2,6-di-tert-butyl-4-n-butylphenol, 2,6-di-tert-butyl-4-isobutylphenol, 2,6-dicyclopentyl-4-methylphenol, 2-(α -methylcyclohexyl)-4,6-dimethylphenol, 2,6-dioctadecyl-4-methylphenol, 2,4,6-tricyclohexylphenol, 2,6-di-tert-butyl-4-methoxymethylphenol, nonylphenols which are linear or branched in the side chains, for example 2,6-dinonyl-4-methylphenol, 2,4-dimethyl-6-(1'-methylundec-1'-yl)phenol, 2,4-dimethyl-6-(1'-methylheptadec-1'-yl)phenol, 2,4-dimethyl-6-(1'-methyltridec-1'-yl)phenol and mixtures thereof.

[0319] 1.2. Alkylthiomethylphenols, for example 2,4-dioctylthiomethyl-6-tert-butylphenol, 2,4-dioctylthiomethyl-6-methylphenol, 2,4-dioctylthiomethyl-6-ethylphenol, 2,6-di-dodecylthiomethyl-4-nonylphenol.

[0320] 1.3. Hydroquinones and alkylated hydroquinones, for example 2,6-di-tert-butyl-4-methoxyphenol, 2,5-di-tert-butylhydroquinone, 2,5-di-tert-amylhydroquinone, 2,6-diphenyl-4-octadecyloxyphenol, 2,6-di-tert-butylhydroquinone, 2,5-di-tert-butyl-4-hydroxyanisole, 3,5-di-tert-butyl-4-hydroxyanisole, 3,5-di-tert-butyl-4-hydroxyphenyl stearate, bis(3,5-di-tert-butyl-4-hydroxyphenyl) adipate.

[0321] 1.4. Tocopherols, for example α -tocopherol, β -tocopherol, γ -tocopherol, δ -tocopherol and mixtures thereof (vitamin E).

[0322] 1.5. Hydroxylated thiodiphenyl ethers, for example 2,2'-thiobis(6-tert-butyl-4-methylphenol), 2,2'-thiobis(4-octylphenol), 4,4'-thiobis(6-tert-butyl-3-methylphenol), 4,4'-thiobis(6-tert-butyl-2-methylphenol) 4,4'-thiobis(3,6-di-sec-amylphenol), 4,4'-bis(2,6-dimethyl-4-hydroxyphenyl)-disulfide.

[0323] 1.6. Alkylidenebisphenols, for example 2,2'-methylenebis(6-tert-butyl-4-methylphenol), 2,2'-methyl-

- enebis(6-tert-butyl-4-ethylphenol), 2,2'-methylenebis[4-methyl-6-(α -methylcyclohexyl)-phenol], 2,2'-methylenebis(4-methyl-6-cyclohexylphenol), 2,2'-methylenebis(6-nonyl-4-methylphenol), 2,2'-methylenebis(4,6-di-tert-butylphenol), 2,2'-ethylidenebis(4,6-di-tert-butylphenol), 2,2'-ethylidenebis(6-tert-butyl-4-isobutylphenol), 2,2'-methylenebis[6-(α -methylbenzyl)-4-nonylphenol], 2,2'-methylenebis[6-(α,α -dimethylbenzyl)-4-nonylphenol], 4,4'-methylenebis(2,6-di-tert-butylphenol), 4,4'-methylenebis(6-tert-butyl-2-methylphenol), 1,1-bis(5-tert-butyl-4-hydroxy-2-methylphenyl)butane, 2,6-bis(3-tert-butyl-5-methyl-2-hydroxybenzyl)-4-methylphenol, 1,1,3-tris(5-tert-butyl-4-hydroxy-2-methylphenyl)butane, 1,1-bis(5-tert-butyl-4-hydroxy-2-methylphenyl)-3-n-dodecylmercaptobutane, ethylene glycol bis[3,3-bis(3'-tert-butyl-4'-hydroxyphenyl)butyrate], bis(3-tert-butyl-4-hydroxy-5-methylphenyl)dicyclopentadiene, bis[2-(3'-tert-butyl-2'-hydroxy-5'-methylbenzyl)-6-tert-butyl-4-methylphenyl]terephthalate, 1,1-bis-(3,5-dimethyl-2-hydroxyphenyl)butane, 2,2-bis(3,5-di-tert-butyl-4-hydroxyphenyl)propane, 2,2-bis-(5-tert-butyl-4-hydroxy-2-methylphenyl)-4-n-dodecylmercaptobutane, 1,1,5,5-tetra(5-tert-butyl-4-hydroxy-2-methylphenyl)-pentane.
- [0324] 1.7. O-, N- and S-benzyl compounds, for example 3,5,3',5'-tetra-tert-butyl-4,4'-dihydroxydibenzyl ether, octadecyl-4-hydroxy-3,5-dimethylbenzylmercaptoacetate, tridecyl-4-hydroxy-3,5-di-tert-butylbenzylmercaptoacetate, tris(3,5-di-tert-butyl-4-hydroxybenzyl)amine, bis(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl)dithioerephthalate, bis(3,5-di-tert-butyl-4-hydroxybenzyl)sulfide, isooctyl-3,5-di-tert-butyl-4-hydroxybenzylmercaptoacetate.
- [0325] 1.8. Hydroxybenzoate malonates, for example dioctadecyl-2,2-bis(3,5-di-tert-butyl-2-hydroxybenzyl)malonate, di-octadecyl-2-(3-tert-butyl-4-hydroxy-5-methylbenzyl)malonate, didodecylmercaptoethyl-2,2-bis(3,5-di-tert-butyl-4-hydroxybenzyl)malonate, bis[4-(1,1,3,3-tetramethylbutyl)phenyl]-2,2-bis(3,5-di-tert-butyl-4-hydroxybenzyl)malonate.
- [0326] 1.9. Aromatic hydroxybenzyl compounds, for example 1,3,5-tris(3,5-di-tert-butyl-4-hydroxybenzyl)-2,4,6-trimethylbenzene, 1,4-bis(3,5-di-tert-butyl-4-hydroxybenzyl)-2,3,5,6-tetramethylbenzene, 2,4,6-tris(3,5-di-tert-butyl-4-hydroxybenzyl)phenol.
- [0327] 1.10. Triazine compounds, for example 2,4-bis(octylmercapto)-6-(3,5-di-tert-butyl-4-hydroxyanilino)-1,3,5-triazine, 2-octylmercapto-4,6-bis(3,5-di-tert-butyl-4-hydroxyanilino)-1,3,5-triazine, 2-octylmercapto-4,6-bis(3,5-di-tert-butyl-4-hydroxyphenoxy)-1,3,5-triazine, 2,4,6-tris-(3,5-di-tert-butyl-4-hydroxyphenoxy)-1,2,3-triazine, 1,3,5-tris(3,5-di-tert-butyl-4-hydroxybenzyl)isocyanurate, 1,3,5-tris(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl)isocyanurate, 2,4,6-tris-(3,5-di-tert-butyl-4-hydroxyphenylethyl)-1,3,5-triazine, 1,3,5-tris(3,5-di-tert-butyl-4-hydroxy-phenylpropionyl)-hexahydro-1,3,5-triazine, 1,3,5-tris(3,5-dicyclohexyl-4-hydroxybenzyl)isocyanurate.
- [0328] 1.11. Benzylphosphonates, for example dimethyl-2,5-di-tert-butyl-4-hydroxybenzylphosphonate, diethyl-3,5-di-tert-butyl-4-hydroxybenzylphosphonate, dioctadecyl-3,5-di-tert-butyl-4-hydroxybenzylphosphonate, the calcium salt of the monoethyl ester of 3,5-di-tert-butyl-4-hydroxybenzylphosphonic acid.
- [0329] 1.12. Acylaminophenols, for example 4-hydroxy-lauranilide, 4-hydroxystearanilide, octyl N-(3,5-di-tert-butyl-4-hydroxyphenyl)carbamate.
- [0330] 1.13. Esters of β -(3,5-di-tert-butyl-4-hydroxyphenyl)propionic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, n-octanol, i-octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl)isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.
- [0331] 1.14. Esters of β -(5-tert-butyl-4-hydroxy-3-methylphenyl)propionic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, n-octanol, i-octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl)isocyanurate, N,N'-bis-(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.
- [0332] 1.15. Esters of β -(3,5-dicyclohexyl-4-hydroxyphenyl)propionic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl)isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.
- [0333] 1.16. Esters of 3,5-di-tert-butyl-4-hydroxyphenyl acetic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl)isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.
- [0334] 1.17. Amides of β -(3,5-di-tert-butyl-4-hydroxyphenyl)propionic acid e.g. N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)hexamethylenediamide, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)trimethylenediamide, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)hydrazide, N,N'-bis[2-(3-[3,5-di-tert-butyl-4-hydroxyphenyl]propionyloxy)ethyl]oxamide (Naugard®XL-1, supplied by Uniroyal).

[0335] 1.18. Ascorbic acid (vitamin C)

[0336] 1.19. Aminic antioxidants, for example N,N'-di-isopropyl-p-phenylenediamine, N,N'-di-sec-butyl-p-phenylenediamine, N,N'-bis(1,4-dimethylpentyl)-p-phenylenediamine, N,N'-bis(1-ethyl-3-methylpentyl)-p-phenylenediamine, N,N'-bis(1-methylheptyl)-p-phenylenediamine, N,N'-dicyclohexyl-p-phenylenediamine, N,N'-diphenyl-p-phenylenediamine, N,N'-bis(2-naphthyl)-p-phenylenediamine, N-isopropyl-N'-phenyl-p-phenylenediamine, N-(1,3-dimethylbutyl)-N'-phenyl-p-phenylenediamine, N-(1-methylheptyl)-N'-phenyl-p-phenylenediamine, N-cyclohexyl-N'-phenyl-p-phenylenediamine, 4-(p-toluenesulfamoyl)diphenylamine, N,N'-dimethyl-N,N'-di-sec-butyl-p-phenylenediamine, diphenylamine, N-allyldiphenylamine, 4-isopropoxy-diphenylamine, N-phenyl-1-naphthylamine, N-(4-tert-octylphenyl)-1-naphthylamine, N-phenyl-2-naphthylamine, octylated diphenylamine, for example p,p'-di-tert-octyldiphenylamine, 4-n-butylaminophenol, 4-butyrylaminophenol, 4-nonanoylaminophenol, 4-dodecanoyl-aminophenol, 4-octadecanoylaminophenol, bis(4-methoxyphenyl)amine, 2,6-di-tert-butyl-4-dimethylaminomethylphenol, 2,4'-diaminodiphenylmethane, 4,4'-diaminodiphenylmethane, N,N,N',N'-tetramethyl-4,4'-diaminodiphenylmethane, 1,2-bis[(2-methylphenyl)amino]ethane, 1,2-bis(phenylamino)propane, (o-tolyl)biguanide, bis[4-(1',3'-dimethylbutyl)phenyl]amine, tert-octylated N-phenyl-1-naphthylamine, a mixture of mono- and dialkylated tert-butyl/tert-octyldiphenylamines, a mixture of mono- and dialkylated nonyldiphenylamines, a mixture of mono- and dialkylated dodecyldiphenylamines, a mixture of mono- and dialkylated isopropyl/isohexyldiphenylamines, a mixture of mono- and dialkylated tert-butyl-diphenylamines, 2,3-dihydro-3,3-dimethyl-4H-1,4-benzothiazine, phenothiazine, a mixture of mono- and dialkylated tert-butyl/tert-octylphenothiazines, a mixture of mono- and dialkylated tert-octyl-phenothiazines, N-allylphenothiazine, N,N,N',N'-tetraphenyl-1,4-diaminobut-2-ene, N,N-bis-(2,2,6,6-tetramethyl-piperid-4-yl)-hexamethylenediamine, bis(2,2,6,6-tetramethylpiperid-4-yl)-sebacate, 2,2,6,6-tetramethylpiperidin-4-one, 2,2,6,6-tetramethylpiperidin-4-ol.

2. UV Absorbers and Light Stabilisers

[0337] 2.1. 2-(2'-Hydroxyphenyl)benzotriazoles, for example 2-(2'-hydroxy-5'-methylphenyl)benzotriazole, 2-(3',5'-di-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(5'-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(2'-hydroxy-5'-(1,1,3,3-tetramethylbutyl)phenyl)benzotriazole, 2-(3',5'-di-tert-butyl-2'-hydroxyphenyl)-5-chlorobenzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-methylphenyl)-5-chlorobenzotriazole, 2-(3'-sec-butyl-5'-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(2'-hydroxy-4'-octyloxyphenyl)benzotriazole, 2-(3',5'-di-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(3',5'-bis(α,α -dimethylbenzyl)-2'-hydroxyphenyl)benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-octyloxyranyl)phenyl)-5-chlorobenzotriazole, 2-(3'-tert-butyl-5'-[2-(2-ethylhexyloxy)carbonyl]ethyl)-2'-hydroxyphenyl)-5-chlorobenzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-methoxycarbonyl)phenyl)-5-chlorobenzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-

butyl-2'-hydroxy-5'-(2-octyloxy)carbonyl)phenyl)benzotriazole, 2-(3'-tert-butyl-5'-[2-(2-ethylhexyloxy)carbonyl]ethyl)-2'-hydroxyphenyl)benzotriazole, 2-(3'-dodecyl-2'-hydroxy-5'-methylphenyl)benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-isooctyloxy)carbonyl)phenyl)benzotriazole, 2,2'-methylenebis[4-(1,1,3,3-tetramethylbutyl)-6-benzotriazole-2-yl]phenol]; the transesterification product of 2-[3'-tert-butyl-5'-(2-methoxycarbonyl)ethyl]-2'-hydroxyphenyl]-2H-benzotriazole with polyethylene glycol 300;



where R=3'-tert-butyl-4'-hydroxy-5'-2H-benzotriazol-2-ylphenyl, 2-[2'-hydroxy-3'-(α,α -dimethylbenzyl)-5'-(1,1,3,3-tetramethylbutyl)phenyl]-benzotriazole; 2-[2'-hydroxy-3'-(1,1,3,3-tetramethylbutyl)-5'-(α,α -dimethylbenzyl)phenyl]benzotriazole.

[0338] 2.2. 2-Hydroxybenzophenones, for example the 4-hydroxy, 4-methoxy, 4-octyloxy, 4-decyloxy, 4-dodecyloxy, 4-benzyloxy, 4,2',4'-trihydroxy and 2'-hydroxy-4,4'-dimethoxy derivatives.

[0339] 2.3. Esters of substituted and unsubstituted benzoic acids, for example 4-tert-butylphenyl salicylate, phenyl salicylate, octylphenyl salicylate, dibenzoyl resorcinol, bis(4-tert-butylbenzoyl)resorcinol, benzoyl resorcinol, 2,4-di-tert-butylphenyl 3,5-di-tert-butyl-4-hydroxybenzoate, hexadecyl 3,5-di-tert-butyl-4-hydroxybenzoate, octadecyl 3,5-di-tert-butyl-4-hydroxybenzoate, 2-methyl-4,6-di-tert-butylphenyl 3,5-di-tert-butyl-4-hydroxybenzoate.

[0340] 2.4. Acrylates, for example ethyl α -cyano- β,β -diphenylacrylate, isooctyl α -cyano- β,β -diphenylacrylate, methyl α -carbomethoxycinnamate, methyl α -cyano- β -methyl-p-methoxycinnamate, butyl α -cyano- β -methyl-p-methoxycinnamate, methyl α -carbomethoxy-p-methoxycinnamate and N-(β -carbomethoxy- β -cyanovinyl)-2-methylindoline.


[0341] 2.5. Nickel compounds, for example nickel complexes of 2,2'-thiobis[4-(1,1,3,3-tetramethylbutyl)phenol], such as the 1:1 or 1:2 complex, with or without additional ligands such as n-butylamine, triethanolamine or N-cyclohexyldiethanolamine, nickel dibutyldithiocarbamate, nickel salts of the monoalkyl esters, e.g. the methyl or ethyl ester, of 4-hydroxy-3,5-di-tert-butylbenzylphosphonic acid, nickel complexes of ketoximes, e.g. of 2-hydroxy-4-methylphenylundecylketoxime, nickel complexes of 1-phenyl-4-lauroyl-5-hydroxypyrazole, with or without additional ligands.

[0342] 2.6. Oxamides, for example 4,4'-dioctyloxyoxanilide, 2,2'-diethoxyoxanilide, 2,2'-dioctyloxy-5,5'-di-tert-butoxanilide, 2,2'-didodecyloxy-5,5'-di-tert-butoxanilide, 2-ethoxy-2'-ethylloxanilide, N,N'-bis(3-dimethylaminopropyl)oxamide, 2-ethoxy-5-tert-butyl-2'-ethoxanilide and its mixture with 2-ethoxy-2'-ethyl-5,4'-di-tert-butoxanilide, mixtures of o- and p-methoxy-disubstituted oxanilides and mixtures of o- and p-ethoxy-disubstituted oxanilides.


[0343] 4. Phosphites and phosphonites, for example triphenyl phosphite, diphenylalkyl phosphites, phenyldialkyl

phosphites, tris(nonylphenyl) phosphite, trilauryl phosphite, trioctadecyl phosphite, distearyl pentaerythritol diphosphite, tris(2,4-di-tert-butylphenyl) phosphite, diisodecyl pentaerythritol diphosphite, bis(2,4-di-tert-butylphenyl) pentaerythritol diphosphite, bis(2,4-di-cumylphenyl) pentaerythritol diphosphite, bis(2,6-di-tert-butyl-4-methylphenyl) pentaerythritol diphosphite, diisodecyl oxypentaerythritol diphosphite, bis(2,4-di-tert-butyl-4-methylphenyl) pentaerythritol diphosphite, bis(2,4,6-tris(tert-butylphenyl) pentaerythritol diphosphite, tristearyl sorbitol triphosphite, tetrakis(2,4-di-tert-butylphenyl) 4,4'-biphenylene diphosphonite, 6-isooctyloxy-2,4,8,10-tetra-tert-butyl-1,2H-dibenz[d,g]-1,3,2-dioxaphosphocin, bis(2,4-di-tert-butyl-6-methylphenyl) methyl phosphite, bis(2,4-di-tert-butyl-6-methylphenyl) ethyl phosphite, 6-fluoro-2,4,8,10-tetra-tert-butyl-1,2-methyl-dibenz[d,g]-1,3,2-dioxaphosphocin, 2,2',2''-nitrido-[triethyltris(3,3',5,5'-tetra-tert-butyl-1,1'-biphenyl-2,2'-diyl) phosphite], 2-ethylhexyl(3,3',5,5'-tetra-tert-butyl-1,1'-biphenyl-2,2'-diyl) phosphite, 5-butyl-5-ethyl-2-(2,4,6-tri-tert-butylphenoxy)-1,3,2-dioxaphosphirane.

[0344] The following phosphites are especially preferred: Tris(2,4-di-tert-butylphenyl) phosphite (Irgafoso®168, Ciba-Geigy), tris(nonylphenyl) phosphite,



-continued



[0345] 5. Hydroxylamines, for example N,N-dibenzylhydroxylamine, N,N-diethylhydroxylamine, N,N-dioctylhydroxylamine, N,N-dilaurylhydroxylamine, N,N-ditetradecylhydroxylamine, N,N-dihexadecylhydroxylamine, N,N-dioctadecylhydroxylamine, N-hexadecyl-N-octadecylhydroxylamine, N-heptadecyl-N-octadecylhydroxylamine, N,N-dialkylhydroxylamine derived from hydrogenated tallow amine.

[0346] 6. Nitrones, for example N-benzyl-alpha-phenylnitronone, N-ethyl-alpha-methylnitronone, N-octyl-alpha-heptylnitronone, N-lauryl-alpha-undecylnitronone, N-tetradecyl-alpha-tridecynitronone, N-hexadecyl-alpha-pentadecynitronone, N-octadecyl-alpha-heptadecynitronone, N-hexadecyl-alpha-heptadecynitronone, N-octadecyl-alpha-heptadecynitronone, N-octadecyl-alpha-hexadecynitronone, nitronone derived from N,N-dialkylhydroxylamine derived from hydrogenated tallow amine.

[0347] 7. Thiosynergists, for example dilauryl thiodipropionate or distearyl thiodipropionate.

[0348] 8. Peroxide scavengers, for example esters of beta-thiodipropionic acid, for example the lauryl, stearyl, myristyl or tridecyl esters, mercaptobenzimidazole or the zinc salt of 2-mercaptobenzimidazole, zinc dibutyldithiocarbamate, dioctadecyl disulfide, pentaerythritol tetrakis(beta-dodecylmercapto)propionate.

[0349] 9. Polyamide stabilisers, for example copper salts in combination with iodides and/or phosphorus compounds and salts of divalent manganese.

[0350] 10. Basic co-stabilisers, for example melamine, polyvinylpyrrolidone, dicyandiamide, triallyl cyanurate,

urea derivatives, hydrazine derivatives, amines, polyamides, polyurethanes, alkali metal salts and alkaline earth metal salts of higher fatty acids, for example calcium stearate, zinc stearate, magnesium behenate, magnesium stearate, sodium ricinoleate and potassium palmitate, antimony pyrocatecholate or zinc pyrocatecholate.

[0351] 11. Nucleating agents, for example inorganic substances, such as talcum, metal oxides, such as titanium dioxide or magnesium oxide, phosphates, carbonates or sulfates of, preferably, alkaline earth metals; organic compounds, such as mono- or polycarboxylic acids and the salts thereof, e.g. 4-tert-butylbenzoic acid, adipic acid, diphenylacetic acid, sodium succinate or sodium benzoate; polymeric compounds, such as ionic copolymers (ionomers). Especially preferred are 1,3:2,4-bis(3',4'-dimethylbenzylidene)sorbitol, 1,3:2,4-di(paramethyldibenzylidene)sorbitol, and 1,3:2,4-di(benzylidene)sorbitol.

[0352] 12. Fillers and reinforcing agents, for example calcium carbonate, silicates, glass fibres, glass beads, asbestos, talc, kaolin, mica, barium sulfate, metal oxides and hydroxides, carbon black, graphite, wood flour and flours or fibers of other natural products, synthetic fibers.

[0353] 13. Other additives, for example plasticisers, lubricants, emulsifiers, pigments, rheology additives, catalysts, flow-control agents, optical brighteners, flameproofing agents, antistatic agents and blowing agents.

[0354] 14. Benzofuranones and indolinones, for example those disclosed in U.S. Pat No. 4,325,863; U.S. Pat No. 4,338,244; U.S. Pat No. 5,175,312; U.S. Pat No. 5,216,052; U.S. Pat No. 5,252,643; DE-A-4316611; DE-A-4316622; DE-A-4316876; EP-A-0589839 or EP-A-0591102 or 3-[4-(2-acetoxyethoxy)phenyl]-5,7-di-tert-butyl-benzofuran-2-one, 5,7-di-tert-butyl-3-[4-(2-stearoyloxyethoxy)phenyl]benzofuran-2-one, 3,3'-bis[5,7-di-tert-butyl-3-(4-[2-hydroxyethoxy]phenyl)benzofuran-2-one], 5,7-di-tert-butyl-3-(4-ethoxyphenyl)benzofuran-2-one, 3-(4-acetoxy-3,5-dimethylphenyl)-5,7-di-tert-butyl-benzofuran-2-one, 3-(3,5-dimethyl-4-pivaloyloxyphenyl)-5,7-di-tert-butyl-benzofuran-2-one, 3-(3,4-dimethylphenyl)-5,7-di-tert-butyl-benzofuran-2-one, 3-(2,3-di-methylphenyl)-5,7-di-tert-butyl-benzofuran-2-one.

[0355] Conventional additives such as listed components listed above under 1.-11. and 14. are often added in concentrations of from 0.01 to 10%, based on the overall weight of the composition (components a, b and c). Further additives of items 12. and 13., such as fillers or flame retardants, may be contained in much higher amounts, e.g. from 0.1 to about 50% or even 80% by weight of the total composition.

[0356] Preferably, the compositions of the present invention do not contain polyphenolic antioxidants. Such polyphenolic antioxidants are for example described in U.S. Pat No. 5,770,115.

[0357] The polymeric material usually contains 0.001 to 10% by weight, most preferably 0.01 to 5% by weight of the stabilizer component (c). The polymeric material can con-

tain mixtures of two or more of the HALS (ii) and/or the hydroxyphenyl UV absorber (i).

[0358] The amount of photochromic dye in the polymeric material usually is in the range of about 0.001 to 10% by weight, most preferably 0.01 to 5% by weight, with respect to the total weight of the polymeric material. The polymeric material can contain mixtures of two or more photochromic dyes.

[0359] The ratio of component (c) to component (b) can e.g. be in the range of 0.01 to 100 parts, preferably 0.1 to 10 parts, of stabilizer (c) per part of photochromic dye (b).

[0360] The ratio of UVA component (i) to HALS component (ii) can e.g. be in the range of 0.01 to 100 parts, most preferably 0.1 to 2 parts, of UV absorber (i) per part of HALS (ii).

[0361] The polymeric material, the dye (b) and the stabilizer components (c) often form a homogenous mixture. For specific applications, however, compositions can be made in which components (b) and especially (c) are enriched in a part of the polymeric material, e.g. in the surface areas, or wherein the UV absorber component (i) is enriched in the surface areas while the remaining components are mixed homogeneously. Of specific technical importance are 2- or multilayer systems wherein the UV absorber (i) is enriched in an upper layer containing no photochromic dye, while a lower layer contains the dye (b) and HALS (ii), and the UV absorber merely as an optional component. These systems may be obtained by conventional techniques, e.g. coextrusion, adhesion or stacking of layers containing UV absorber (i) or UV absorber (i) and HALS (ii) on one hand, and HALS (ii) and dye (b) on the other hand, and possible further layers, which may improve further properties such as scratch resistance, surface gloss and reflection, adhesion, base colour etc.

[0362] The additives/components of the invention and optional further components may be added to the polymer material individually or mixed with one another. If desired, the individual components can be mixed with one another before incorporation into the polymer for example by dry blending, compaction or in the melt.

[0363] The incorporation of the components of the invention and optional further components into the polymer is carried out by known methods such as dry blending in the form of a powder, or wet mixing in the form of solutions, dispersions or suspensions for example in an inert solvent, water or oil. The additives of the invention and optional further additives may be incorporated, for example, before or after molding or also by applying the dissolved, melted (soaking process) or dispersed additive or additive mixture to the polymer material, with or without subsequent evaporation of the solvent or the suspension/dispersion agent. They may be added directly into the processing apparatus (e.g. extruders, internal mixers, etc), e.g. as a dry mixture or powder or as solution or dispersion or suspension or melt.

[0364] The incorporation can be carried out in any heatable container equipped with a stirrer, e.g. in a closed

apparatus such as a kneader, mixer or stirred vessel. The incorporation is preferably carried out in an extruder or in a kneader. It is immaterial whether processing takes place in an inert atmosphere or in the presence of oxygen.

[0365] The addition of the additive or additive blend to the polymer can be carried out in all customary mixing machines in which the polymer is melted and mixed with the additives. Suitable machines are known to those skilled in the art. They are predominantly mixers, kneaders and extruders.

[0366] The process is preferably carried out in an extruder by introducing the additive during processing.

[0367] Particularly preferred processing machines are single-screw extruders, contrarotating and corotating twin-screw extruders, planetary-gear extruders, ring extruders or cokneaders. It is also possible to use processing machines provided with at least one gas removal compartment to which a vacuum can be applied.

[0368] Suitable extruders and kneaders are described, for example, in *Handbuch der Kunststoffextrusion*, Vol. 1 Grundlagen, Editors F. Hensen, W Knappe, H. Potente, 1989, pp. 3-7, ISBN:3-446-14339-4 (Vol. 2 Extrusionsanlagen 1986, ISBN 3-446-14329-7).

[0369] For example, the screw length is 1-60 screw diameters, preferably 35-48 screw diameters. The rotational speed of the screw is preferably 10-600 rotations per minute (rpm), very particularly preferably 25-300 rpm.

[0370] The maximum throughput is dependent on the screw diameter, the rotational speed and the driving force. The process of the present invention can also be carried out at a level lower than maximum throughput by varying the parameters mentioned or employing weighing machines delivering dosage amounts.

[0371] Components to be added can be premixed or added individually.

[0372] The additives/components of the invention and optional further additives can also be sprayed onto the polymer material. They are able to dilute other additives (for example the conventional additives indicated above) or their melts so that they can be sprayed also together with these additives onto the material. Addition by spraying during the deactivation of the polymerization catalysts is particularly advantageous; in this case, the steam evolved may be used for deactivation of the catalyst. In the case of spherically polymerized polyolefins it may, for example, be advantageous to apply the additives of the invention, optionally together with other additives, by spraying.

[0373] The components of the invention and optional further additives can also be added to the polymer in the form of a concentrate, e.g. a masterbatch, which contains the components in a concentration of, for example, about 1% to about 40% and preferably 2% to about 20% by weight incorporated in a polymer. The polymer must not be necessarily of identical structure than the polymer where the

additives are added finally. In such operations, the polymer can be used in the form of powder, granules, solutions, suspensions or in the form of latices.

[0374] Incorporation can take place prior to or during the shaping operation, or by applying the dissolved, melted (soaking process) or dispersed compound to the polymer, with or without subsequent evaporation of the solvent. In the case of elastomers, these can also be stabilized as latices. A further possibility for incorporating the additives of the invention into polymers is to add them before, during or directly after the polymerization of the corresponding monomers or prior to crosslinking. In this context the additive of the invention can be added as it is or else in encapsulated form (for example in waxes, oils or polymers).


[0375] The materials containing the additives/components of the invention described herein can be used for the production of moldings, rotomolded articles, injection molded articles, blow molded articles, films, tapes, monofilaments, fibers, nonwovens, profiles, adhesives or putties, surface coatings and the like.

[0376] The invention also pertains to a process for stabilizing a photochromic system containing a photochromic dye in a polymer matrix against colour fading induced by irradiation, which process comprises incorporation of a hydroxyphenyl triazine UV absorber and optionally a sterically hindered amine light stabilizer into the polymer matrix and/or into a polymer layer covering said polymer matrix, as well as to the use of a hydroxyphenyl triazine UV absorber and optionally a sterically hindered amine for improving the stability of a photochromic system containing a photochromic dye in a polymer matrix. Preferred processes and uses are in analogy to the compositions described further above or in the examples.


[0377] Percentages refer to weight percentages except otherwise stated.

Materials used in the examples:


[0378] Compound UV1 is of the formula




[0379] Compound HALS H1 is of the formula




[0380] Compound HALS H2 is of the formula



[0381] Chromene1 is of the formula



[0382] Chromene 2 is of the formula



EXAMPLES

Example 1

[0383] Each compound reported in the table below is mixed in a turbo mixer with EVA (ethylene-vinylacetate copolymers) Greenflex® ML30 pellets (containing 9% of vinyl acetate, supplied by Polimeri Europa, Italy), characterized by a melt flow index of 2.5 (190° C./16 Kg; ASTM D1238).

Formulation	EVA		Chromene1		HALS H1	
	g		g	%	g	%
1	1998		2	0.1	—	—
2	1992		2	0.1	6	0.3

[0384] The mixtures are blow extruded (using a mono layer Formac Lab. 25 blow extruder) at 160° C. and films of 200 micron thickness are obtained.

[0385] The films thus prepared are mounted on a white card and exposed outdoor in the sunshine; a film with formulation 1 covered with a 150 micron thickness film containing 0.15% of the UV absorber UV1 is exposed in the same conditions (formulation: 1 plus UV1).

[0386] The covering film is a LDPE film containing as the only added additive 0.15% of UV1. The covering film is prepared by mixing 15 g of UV1 and 9850 g of LDPE Riblene FF 29 supplied by Polimeri Europa; they are mixed in a 'turbomixer' for 10 minutes and blow extruded with a Dolci extruder operating at 210° C.

[0387] The table below shows the performance of the three sample films as regards the persistency of the color after light irradiation: the stabilizing effect of UV1 on the chromene1 itself and on the chromene1 mixed with HALS H1 is evident.

Formulation	KJ/m2
1	42
1 plus UV1	198
2 plus UV1	1250

Example 2

[0388] The formulations are prepared as in example 1 but with a different chromene. The formulation compositions and results are shown in the tables below.

Formulation	EVA		Chromene2		HALS H1	
	g	%	g	%	g	%
3	1998	2	0.1	—	—	—
4	1992	2	0.1	6	0.3	—

[0389]

Formulation	KJ/m2
3	388
3 plus UV1	626
4 plus UV1	668

Example 3

[0390] The formulations are prepared as in example 1 but a different sterically hindered amine is used in this example and UV1 is mixed with the other components, i.e. formulation 7 does not have a covering film.

Formulation	EVA		Chromene1		HALS H2		UV1	
	g	%	g	%	g	%	g	%
6	1998	2	0.1	—	—	—	—	—
7	1484.25	1.5	0.1	12	0.8	2.25	0.15	—


[0391]

Formulation	KJ/m2
6	42
7	709


[0392] The examples show that the lifetime of the photochromic system is dramatically enhanced by the stabilization system of the invention using a sterically hindered amine in combination with a hydroxyphenyl triazine UV absorber (i).

1. Photochromic composition comprising


- a polymeric material,
- a photochromic dye and
- a hydroxyphenyl triazine UV absorber (i) conforming to formula I, II, III, IV, V or (100)




I



II



III



wherein

Y is phenyl, naphthyl, or said phenyl or said naphthyl substituted by one to three alkyl of 1 to 6 carbon atoms, by halogen, by hydroxy or by alkoxy of 1 to 6 carbon atoms or by mixtures thereof; or Y is Z₁ or Z₂;

X is Z₁ or Z₂;


R₁ is hydrogen, straight or branched chain alkyl of 1 to 24 carbon atoms, cycloalkyl of 5 to 12 carbon atoms, phenylalkyl of 7 to 15 carbon atoms, halogen, —SR₃, —SOR₃ or —SO₂R₃; or said alkyl, said cycloalkyl or said phenylalkyl substituted by one to three halogen, —R₄, —OR₅, —N(R₅)₂, —COR₅, —COOR₅, —OCOR₅, —CN, —NO₂, —SR₅, —SOR₅, —SO₂R₅ or —P(O)(OR₅)₂, morpholinyl, piperidinyl, 2,2,6,6-tetramethylpiperidinyl, piperazinyl or N-methylpiperidinyl groups or combinations thereof; or said alkyl or said cycloalkyl interrupted by one to four phenylene, —O—, —NR₅—, —CONR₅—, —COO—, —OCO— or —CO groups or combinations thereof; or said alkyl or said cycloalkyl both substituted and interrupted by combinations of the groups mentioned above;

R₃ is alkyl of 1 to 20 carbon atoms, alkenyl of 3 to 18 carbon atoms, cycloalkyl of 5 to 12 carbon atoms, phenylalkyl of 7 to 15 carbon atoms, aryl of 6 to 10 carbon atoms or said aryl substituted by one or two alkyl of 1 to 4 carbon atoms;

R₄ is aryl of 6 to 10 carbon atoms or said aryl substituted by one to three halogen, alkyl of 1 to 8 carbon atoms, alkoxy of 1 to 8 carbon atoms or combinations thereof; cycloalkyl of 5 to 12 carbon atoms; phenylalkyl of 7 to 15 carbon atoms or said phenylalkyl substituted on the phenyl ring by one to three halogen, alkyl of 1 to 8 carbon atoms, alkoxy of 1 to 8 carbon atoms or

combinations thereof; or straight or branched chain alkenyl of 2 to 18 carbon atoms;


R₅ is defined as is R₄; or R₅ is also hydrogen or straight or branched chain alkyl of 1 to 24 carbon atoms, alkenyl of 2 to 24 carbon atoms; or R₅ is a group for formula



T is hydrogen, oxyl, hydroxyl, —OT₁, alkyl of 1 to 24 carbon atoms, said alkyl substituted by one to three hydroxy; benzyl or alkanoyl of 2 to 18 carbon atoms;

T₁ is alkyl of 1 to 24 carbon atoms, cycloalkyl of 5 to 12 carbon atoms, alkenyl of 2 to 24 carbon atoms, cycloalkenyl of 5 to 12 carbon atoms, phenylalkyl of 7 to 15 carbon atoms, a radical of a saturated or unsaturated bicyclic or tricyclic hydrocarbon of 7 to 12 carbon atoms or aryl of 6 to 10 carbon atoms or said aryl substituted by one to three alkyl of 1 to 4 carbon atoms;

R₂ is hydrogen, straight or branched chain alkyl of 1 to 24 carbon atoms or cycloalkyl of 5 to 12 carbon atoms; or said alkyl or said cycloalkyl substituted by one to four halogen, epoxy, glycidyl, furyloxy, —R₄, —OR₅, —N(R₅)₂, —CON(R₅)₂, —COR₅, —COOR₅, —OCOR₅, —OCOC(R₅)=C(R₅)₂, —C(R₅)=CCOOR₅, —CN, —NCO, or




or combinations thereof; or said alkyl or said cycloalkyl interrupted by one to four epoxy, —O—, —NR₅—, —CONR₅—, —COO—, —OCO—, —CO—, —C(R₅)=C(R₅)COO—, —OCOC(R₅)=C(R₅)—, —C(R₅)=C(R₅)—, phenylene or phenylene-G-phenylene in which G is —O—, —S—, —SO₂—, —CH₂— or —C(CH₃)₂— or combinations thereof, or said alkyl or said cycloalkyl both substituted and interrupted by combinations of the groups mentioned above; or R₂ is —SO₂R₃ or —COR₆;

R₆ is straight or branched chain alkyl of 1 to 18 carbon atoms, straight or branched chain alkenyl of 2 to 12 carbon atoms, phenoxy, alkylamino of 1 to 12 carbon atoms, arylamino of 6 to 12 carbon atoms, —R₇COOH or —NH—R₈—NCO;

R₇ is alkylene of 2 to 14 carbon atoms or phenylene;

R₈ is alkylene of 2 to 24 carbon atoms, phenylene, tolylene, diphenylmethane or a group




R_1 and R_1' are the same or different and are as defined for R_1 ;

R_2 and R_2' are the same or different and are as defined for R_2 ;

X and X' are the same or different and are as defined for X ; Y and Y' are the same or different and are as defined for Y ;

t is 0 to 9;


L is straight or branched alkylene of 1 to 12 carbon atoms, cycloalkylene of 5 to 12 carbon atoms or alkylene substituted or interrupted by cyclohexylene or phenylene; or L is benzylidene; or L is $-S-$, $-S-S-$, $-S-E-S-$, $-SO-$, $-SO_2-$, $-SO-E-SO-$, $-SO_2-E-SO_2-$, $-CH_2-NH-E-NH-CH_2-$ or



E is alkylene of 2 to 12 carbon atoms, cycloalkylene of 5 to 12 carbon atoms or alkylene interrupted or terminated by cycloalkylene of 5 to 12 carbon atoms;

n is 2, 3 or 4;

when n is 2; Q is straight or branched alkylene of 2 to 16 carbon atoms; or said alkylene substituted by one to three hydroxy groups; or said alkylene interrupted by one to three $-CH=CH-$ or $-O-$; or said alkylene both substituted and interrupted by combinations of the groups mentioned above; or Q is xylylene or a group $-CONH-R_8-NHCO-$, $-CH_2CH(OH)CH_2O-$, $R_9-OCH_2CH(OH)CH_2-$, $-CO-R_{10}-CO-$, or $-(CH_2)_m-COO-R_{11}-OOC-(CH_2)_m-$, where m is 1 to 3; or Q is



R_9 is alkylene of 2 to 50 carbon atoms; or said alkylene interrupted by one to ten $-O-$, phenylene or a group

-phenylene-G-phenylene in which G is $-O-$, $-S-$, $-SO_2-$, $-CH_2-$ or $-C(CH_3)_2-$;


R_{10} is alkylene of 2 to 10 carbon atoms; or said alkylene interrupted by one to four $-O-$, $-S-$ or $-CH=CH-$; or R_{10} is arylene of 6 to 12 carbon atoms;

R_{11} is alkylene of 2 to 20 carbon atoms; or said alkylene interrupted by one to eight $-O-$;


when n is 3, Q is a group $-[(CH_2)_mCOO]_3-R_{12}$ where m is 1 to 3, and R_{12} is an alkanetriyl of 3 to 12 carbon atoms;

when n is 4, Q is a group $-[(CH_2)_mCOO]_4-R_{13}$ where m is 1 to 3, and R_{14} is an alkanetetrayl of 4 to 12 carbon atoms;

Z_1 is a group of formula



Z_2 is a group of formula




where

r_1 and r_2 are 1;

R_{14} , R_{15} , R_{16} , R_{17} , R_{18} , R_{19} , R_{20} , R_{21} , R_{22} and R_{23} are independently of one another hydrogen, hydroxy, cyano, alkyl of 1 to 20 carbon atoms, alkoxy of 1 to 20 carbon atoms, phenylalkyl of 7 to 15 carbon atoms, cycloalkyl of 5 to 12 carbon atoms, cycloalkoxy of 5 to 12 carbon atoms, halogen, haloalkyl of 1 to 5 carbon atoms, sulfo, carboxy, acylamino of 2 to 12 carbon atoms, acyloxy of 2 to 12 carbon atoms, alkoxy-carbonyl of 2 to 12 carbon atoms or aminocarbonyl; or R_{17} and R_{18} or R_{22} and R_{23} together with the phenyl radical to which they are attached are a cyclic radical interrupted by one to three $-O-$ or $-NR_5-$;

x_2 is a number from 1 to 50;

A₁ is a group of the formula (101)



or has one of the meanings given for T₁₀;

D₁ is C₄-C₁₂ alkylene or said alkylene substituted by OH or interrupted by O or both substituted by OH and interrupted by O;

L₁ is C₁-C₁₈alkylene; C₅-C₁₂cycloalkylene; C₃-C₁₈alkenylyne; or one of said residues substituted by phenyl, C₇-C₁₁alkylphenyl, C₅-C₁₂cycloalkyl, OH, halogen, C₁-C₁₈alkoxy, C₅-C₁₂cycloalkoxy, C₃-C₁₈alkenyloxy, COOH;

the R₅₀ are independently of each other H, OR₅₄ or OH, with the proviso that at least one of R₅₀ or R₅₃ is OH;

the R₅₄ are independently of each other hydrogen, C₁-C₁₂alkyl or a radical of formula —L₁—CO—O—R₅₅;

R₅₅ is H, C₁-C₁₈alkyl, C₂-C₁₂hydroxyalkyl;

R₅₁ is hydrogen, C₁-C₄alkyl, Cl, phenyl or a group —OR₅₄;

R₅₂ is hydrogen or methyl;

R₅₃ is hydrogen, methyl, OH or OR₅₄; and

T₁₀ is the divalent acyl residue of an aliphatic or cycloaliphatic dicarboxylic acid of 13 to 60 carbon atoms;

and which contains at least one moiety of formula (101) and at least one moiety T₁₀.

2. A composition according to claim 1 comprising

a) a polymeric material containing a photochromic dye and

c) a stabilizer combination of

i) a hydroxyphenyl triazine UV absorber and

ii) at least one further light stabilizer selected from the sterically hindered amines.




3. Composition according to claim 1, which is an optical device, an architectural or vehicle glazing, a greenhouse film, a coating, or a construction element, in particular an ophthalmic lense.

4. Composition according to claim 1, wherein component (a) is selected from polyolefines, polycarbonate, polyesters, styrene polymers or copolymers, polyacrylates, cellulose esters, polyvinylalcohol, polyurethanes; in particular from polyethylene, polypropylene, polyethylene terephthalate,

polystyrene, high impact polystyrene, polyvinylbutyrate, styrene-methacrylate, styrene-acrylonitrile, glycole modified polyethyleneterephthalate, polycarbonate, polymethylmethacrylate, polyvinylbutyral, ethylene-vinyl acetate copolymer, ethylene-butyl acrylate copolymer, and blends thereof.

5. Composition according to claim 1 containing a photochromic dye selected from the naphthopyranes, benzopyranes, spiropyranes or spirooxazines as component (b) in an amount of 0.001 to 10% by weight, with respect to the total weight of the polymeric material (a).

6. Composition of claim 2 wherein the sterically hindered amine (ii) is a compound comprising at least one radical of the formula IX, X and/or XI



in which

G is hydrogen or methyl, and

G₁ and G₂ are hydrogen, methyl or together are oxygen, and having a molecular weight of 400 g/mol or higher.

7. Composition of claim 1 which is a 2- or multilayer system wherein the UV absorber (i) is enriched in an upper layer containing no photochromic dye, while a lower layer contains the dye (b) and optionally the sterically hindered amine (ii).





8. Composition of claim 1 wherein the polymeric material (a) contains 0.001 to 10% by weight of the stabilizer component (c) comprising a ratio of UVA component (i) to sterically hindered amine component (ii) in the range 0.01 to 100 parts (i) per 1 part (ii).

9. Composition of claim 1 comprising as component (d) at least one further additive selected from antioxidants, phosphites and phosphonites, processing stabilizers, fillers, pigments, dyes, clarifiers, modifiers, acid scavengers, flame retardants, further light stabilizers.

10. Process of stabilizing a photochromic system containing a photochromic dye in a polymer matrix against colour fading induced by irradiation, which process comprises incorporation of a hydroxyphenyl triazine UV absorber (i)


and optionally a sterically hindered amine light stabilizer into the polymer matrix and/or into a polymer layer covering said polymer matrix,

wherein the hydroxyphenyl triazine UV absorber (i) is of formula I, II, III, IV, V or (100)



-continued

V



wherein

Y is phenyl, naphthyl, or said phenyl or said naphthyl substituted by one to three alkyl of 1 to 6 carbon atoms, by halogen, by hydroxy or by alkoxy of 1 to 6 carbon atoms or by mixtures thereof; or Y is Z₁ or Z₂;


X is Z₁ or Z₂;

R₁ is hydrogen, straight or branched chain alkyl of 1 to 24 carbon atoms, cycloalkyl of 5 to 12 carbon atoms, phenylalkyl of 7 to 15 carbon atoms, halogen, —SR₃, —SOR₃ or —SO₂R₃; or said alkyl, said cycloalkyl or said phenylalkyl substituted by one to three halogen, —R₄, —OR₅, —N(R₅)₂, —COR₅, —COOR₅, —OCOR₅, —CN, —NO₂, —SR₅, —SOR₅, —SO₂R₅ or —P(O)(OR₅)₂, morpholinyl, piperidinyl, 2,2,6,6-tetramethylpiperidinyl, piperazinyl or N-methylpiperidinyl groups or combinations thereof; or said alkyl or said cycloalkyl interrupted by one to four phenylene, —O—, —NR₅—, —CONR₅—, —COO—, —OCO— or —CO groups or combinations thereof; or said alkyl or said cycloalkyl both substituted and interrupted by combinations of the groups mentioned above;

III R₃ is alkyl of 1 to 20 carbon atoms, alkenyl of 3 to 18 carbon atoms, cycloalkyl of 5 to 12 carbon atoms, phenylalkyl of 7 to 15 carbon atoms, aryl of 6 to 10 carbon atoms or said aryl substituted by one or two alkyl of 1 to 4 carbon atoms;

R₄ is aryl of 6 to 10 carbon atoms or said aryl substituted by one to three halogen, alkyl of 1 to 8 carbon atoms, alkoxy of 1 to 8 carbon atoms or combinations thereof; cycloalkyl of 5 to 12 carbon atoms; phenylalkyl of 7 to 15 carbon atoms or said phenylalkyl substituted on the phenyl ring by one to three halogen, alkyl of 1 to 8 carbon atoms, alkoxy of 1 to 8 carbon atoms or combinations thereof; or straight or branched chain alkenyl of 2 to 18 carbon atoms;


R₅ is defined as is R₄; or R₅ is also hydrogen or straight or branched chain alkyl of 1 to 24 carbon atoms, alkenyl of 2 to 24 carbon atoms; or R₅ is a group for formula



T is hydrogen, oxyl, hydroxyl, $-\text{OT}_1$, alkyl of 1 to 24 carbon atoms, said alkyl substituted by one to three hydroxy, benzyl or alkanoyl of 2 to 18 carbon atoms;

T_1 is alkyl of 1 to 24 carbon atoms, cycloalkyl of 5 to 12 carbon atoms, alkenyl of 2 to 24 carbon atoms, cycloalkenyl of 5 to 12 carbon atoms, phenylalkyl of 7 to 15 carbon atoms, a radical of a saturated or unsaturated bicyclic or tricyclic hydrocarbon of 7 to 12 carbon atoms or aryl of 6 to 10 carbon atoms or said aryl substituted by one to three alkyl of 1 to 4 carbon atoms;

R_2 is hydrogen, straight or branched chain alkyl of 1 to 24 carbon atoms or cycloalkyl of 5 to 12 carbon atoms; or said alkyl or said cycloalkyl substituted by one to four halogen, epoxy, glycidyloxy, furyloxy, $-\text{R}_4$, $-\text{OR}_5$, $-\text{N}(\text{R}_5)_2$, $-\text{CON}(\text{R}_5)_2$, $-\text{COR}_5$, $-\text{COOR}_5$, $-\text{OCOR}_5$, $-\text{OCOC}(\text{R}_5)=\text{C}(\text{R}_5)_2$, $-\text{C}(\text{R}_5)=\text{CCOOR}_5$, $-\text{CN}$, $-\text{NCO}$, or




or combinations thereof; or said alkyl or said cycloalkyl interrupted by one to four epoxy, $-\text{O}-$, $-\text{NR}_5-$, $-\text{CONR}_5-$, $-\text{COO}-$, $-\text{OCO}-$, $-\text{CO}-$, $-\text{C}(\text{R}_5)=\text{C}(\text{R}_5)\text{COO}-$, $-\text{OCOC}(\text{R}_5)=\text{C}(\text{R}_5)-$, $-\text{C}(\text{R}_5)=\text{C}(\text{R}_5)-$, phenylene or phenylene-G-phenylene in which G is $-\text{O}-$, $-\text{S}-$, $-\text{SO}_2-$, $-\text{CH}_2-$ or $-\text{C}(\text{CH}_3)_2-$ or combinations thereof, or said alkyl or said cycloalkyl both substituted and interrupted by combinations of the groups mentioned above; or R_2 is $-\text{SO}_2\text{R}_3$ or $-\text{COR}_6$;

R_6 is straight or branched chain alkyl of 1 to 18 carbon atoms, straight or branched chain alkenyl of 2 to 12 carbon atoms, phenoxy, alkylamino of 1 to 12 carbon atoms, arylamino of 6 to 12 carbon atoms, $-\text{R}_7\text{COOH}$ or $-\text{NH}-\text{R}_8-\text{NCO}$;

R_7 is alkylene of 2 to 14 carbon atoms or phenylene;

R_8 is alkylene of 2 to 24 carbon atoms, phenylene, tolylene, diphenylmethane or a group




R_1 and R_1' are the same or different and are as defined for R_1 ;

R_2 and R_2' are the same or different and are as defined for R_2 ;

X and X' are the same or different and are as defined for X; Y and Y' are the same or different and are as defined for Y;

t is 0 to 9;


L is straight or branched alkylene of 1 to 12 carbon atoms, cycloalkylene of 5 to 12 carbon atoms or alkylene substituted or interrupted by cyclohexylene or phenylene; or L is benzylidene; or L is $-\text{S}-$, $-\text{S}-\text{S}-$, $-\text{S}-\text{E}-\text{S}-$, $-\text{SO}-$, $-\text{SO}_2-$, $-\text{SO}-\text{E}-\text{SO}-$, $-\text{SO}_2-\text{E}-\text{SO}_2-$, $-\text{CH}_2-\text{NH}-\text{E}-\text{NH}-\text{CH}_2-$ or



E is alkylene of 2 to 12 carbon atoms, cycloalkylene of 5 to 12 carbon atoms or alkylene interrupted or terminated by cycloalkylene of 5 to 12 carbon atoms;

n is 2, 3 or 4;

when n is 2; Q is straight or branched alkylene of 2 to 16 carbon atoms; or said alkylene substituted by one to three hydroxy groups; or said alkylene interrupted by one to three $-\text{CH}=\text{CH}-$ or $-\text{O}-$; or said alkylene both substituted and interrupted by combinations of the groups mentioned above; or Q is xylylene or a group $-\text{CONH}-\text{R}_8-\text{NHCO}-$, $-\text{CH}_2\text{CH}(\text{OH})\text{CH}_2\text{O}-$, $\text{R}_9-\text{OCH}_2\text{CH}(\text{OH})\text{CH}_2-$, $-\text{CO}-\text{R}_{10}-\text{CO}-$, or $-(\text{CH}_2)_m-\text{COO}-\text{R}_{11}-\text{OOC}-(\text{CH}_2)_m-$, where m is 1 to 3; or Q is



R_9 is alkylene of 2 to 50 carbon atoms; or said alkylene interrupted by one to ten $-\text{O}-$, phenylene or a group -phenylene-G-phenylene in which G is $-\text{O}-$, $-\text{S}-$, $-\text{SO}_2-$, $-\text{CH}_2-$ or $-\text{C}(\text{CH}_3)_2-$;


R_{10} is alkylene of 2 to 10 carbon atoms; or said alkylene interrupted by one to four $-\text{O}-$, $-\text{S}-$ or $-\text{CH}=\text{CH}-$; or R_{10} is arylene of 6 to 12 carbon atoms;

R_{11} is alkylene of 2 to 20 carbon atoms; or said alkylene interrupted by one to eight $-\text{O}-$;


when n is 3, Q is a group $-(\text{CH}_2)_m\text{COO}]_3-\text{R}_{12}$ where m is 1 to 3, and R_{12} is an alkanetriyl of 3 to 12 carbon atoms;

when n is 4, Q is a group $-(\text{CH}_2)_m\text{COO}]_4-\text{R}_{13}$ where m is 1 to 3, and R_{14} is an alkanetetrayl of 4 to 12 carbon atoms;

Z₁ is a group of formula



Z₂ is a group of formula



where


r₁ and r₂ are 1;

R₁₄, R₁₅, R₁₆, R₁₇, R₁₈, R₁₉, R₂₀, R₂₁, R₂₂ and R₂₃ are independently of one another hydrogen, hydroxy, cyano, alkyl of 1 to 20 carbon atoms, alkoxy of 1 to 20 carbon atoms, phenylalkyl of 7 to 15 carbon atoms, cycloalkyl of 5 to 12 carbon atoms, cycloalkoxy of 5 to 12 carbon atoms, halogen, haloalkyl of 1 to 5 carbon atoms, sulfo, carboxy, acylamino of 2 to 12 carbon atoms, acyloxy of 2 to 12 carbon atoms, alkoxy-carbonyl of 2 to 12 carbon atoms or aminocarbonyl; or R₁₇ and R₁₈ or R₂₂ and R₂₃ together with the phenyl radical to which they are attached are a cyclic radical interrupted by one to three —O— or —NR₅—;

x₂ is a number from 1 to 50;

A₁ is a group of the formula (101)

(101)



or has one of the meanings given for T₁₀;

D₁ is C₄-C₁₂ alkylene or said alkylene substituted by OH or interrupted by O or both substituted by OH and interrupted by O;

L₁ is C₁-C₁₈alkylene; C₅-C₁₂cycloalkylene; C₃-C₁₈alkenylene; or one of said residues substituted by phenyl, C₇-C₁₁alkylphenyl, C₅-C₁₂cycloalkyl, OH, halogen, C₁-C₁₈alkoxy, C₅-C₁₂cycloalkoxy, C₃-C₁₈alkenyloxy, COOH;

the R₅₀ are independently of each other H, OR₅₄ or OH, with the proviso that at least one of R₅₀ or R₅₃ is OH;

the R₅₄ are independently of each other hydrogen, C₁-C₁₂alkyl or a radical of formula —L₁—CO—O—R₅₅;

R₅₅ is H, C₁-C₁₈alkyl, C₂-C₁₂hydroxyalkyl;

R₅₁ is hydrogen, C₁-C₄alkyl, Cl, phenyl or a group —OR₅₄;

R₅₂ is hydrogen or methyl;

R₅₃ is hydrogen, methyl, OH or OR₅₄; and

T₁₀ is the divalent acyl residue of an aliphatic or cycloaliphatic dicarboxylic acid of 13 to 60 carbon atoms;

and which contains at least one moiety of formula (101) and at least one moiety T₁₀.

11. (canceled)

* * * * *