

264659/MM

PATENT APPLICATION FORM **604835**
 COMMONWEALTH OF AUSTRALIA
 Patents Act 1952 Regulation 9

We, G-C SHIKA KOGYO KABUSHIKI KAISHA
 of 76-1, Hasunuma-cho, Itabashi-ku, Tokyo, Japan

hereby apply for the grant of a Standard Patent for an invention
 entitled GLASS POWDERS FOR DENTAL GLASS IONOMER CEMENTS which is
 described in the accompanying complete specification.

For a Convention application - details of basic application-

<u>Number</u>	<u>Country</u>	<u>Date of Application</u>
29788/87	Japan	13th February, 1987

Our address for service is ARTHUR S. CAVE & CO., Patent and Trade
 Mark Attorneys, Level 10, 10 Barrack Street, Sydney, New South
 Wales, Australia 2000.

DATED this 18th day of September, 1990.

G-C SHIKA KOGYO KABUSHIKI
KAISHA
 By Its Patent Attorneys
ARTHUR S. CAVE & CO.

P.R. Taylor
P.R. TAYLOR, F.I.C.P.A.A.

To:
 Commissioner of Patents
ARTHUR S. CAVE & CO.
 PATENT AND TRADE MARK ATTORNEYS
 SYDNEY

APPLICATION ACCEPTED AND AMENDMENTS
 ALLOWED.....21-9-90.....

ASC 1



COMMONWEALTH OF AUSTRALIA PATENTS ACT, 1952-1973
DECLARATION IN SUPPORT OF A CONVENTION APPLICATION FOR A PATENT

In support of the Convention Application No. 11429/88 made

(a) Here Insert (In full) Name of Company.

by (a) G-C Shika Kogyo Kabushiki Kaisha

(hereinafter referred to as "Applicant") for a patent for an invention entitled:

(b) Here Insert Title of Invention.

(b) Glass Powders for Dental Glass Ionomer Cements

(c) and (d) Here Insert Full Name and Address of Company Official authorised to make declaration.

(c) Makoto Nakao, President of G-C Shika Kogyo Kabushiki Kaisha

(d) No. 76-1, Hasunuma-cho, Itabashi-ku, Tokyo, Japan

do solemnly and sincerely declare as follows:

1. I am authorised by Applicant to make this declaration on its behalf.

2. The basic Application(s) as defined by section 141 of the Act was/were made

(e) Here Insert Basic Country or Countries followed by date or dates of Basic Application(s).

in (e) Japan on the 13th day of February 19 87.

..... on the day of 19

(f) Here Insert Full Name(s) of Applicant(s) in Basic Country.

by (f) G-C Shika Kogyo Kabushiki Kaisha

(g) Here Insert (In full) Name and Address of actual Inventor or Inventors.

3. (1) Shoji Akahane (2) Satoshi Tosaki (3) Kazuo Hirota (3) Kentaro Tomioka

of (1) No. 58-201, Hibarigaokadanchi, Higashikurume-shi, Tokyo, Japan

(2) No. 3-160, Sakuragicho, Omiya-shi, Saitama-ken, Japan

(3) No. 18-3-302, Kitasenzoku 2-chome, Ohta-ku, Tokyo, Japan

(4) No. 24-23, Jindaijihigashimachi 6-chome, Chofu-shi, Tokyo, Japan

..... is/are the actual Inventor(s) of the invention and the facts upon which Applicant is entitled to make the Application are as follows:

~~Applicant is the Assignee of the said Inventor(s).~~


The Applicant is the assignee of the invention from the actual inventors.

4. The basic Application(s) referred to in paragraph 2 of this Declaration was/were the first Application(s) made in a Convention country in respect of the invention, the subject of the Application.

DECLARED at Tokyo, .. Japan

this 23rd day of .. December 1987.

(h) Personal Signature of Declarant (or, no seal, witness or legalisation).

(h) 

(Signature of Declarant)
Makoto Nakao, President

To THE COMMISSIONER OF PATENTS.

(12) PATENT ABRIDGMENT (11) Document No. AU-B-11429/88
(19) AUSTRALIAN PATENT OFFICE (10) Acceptance No. 604835

(54) Title
GLASS POWDERS FOR DENTAL GLASS IONOMER CEMENTS

International Patent Classification(s)
(51)⁴ A61K 006/06

(21) Application No. : 11429/88 (22) Application Date : 08.02.88

(30) Priority Data

(31) Number	(32) Date	(33) Country
62-29788	13.02.87	JP JAPAN

(43) Publication Date : 18.08.88

(44) Publication Date of Accepted Application : 03.01.91

(71) Applicant(s)
G-C SHIKA KOGYO KABUSHIKI KAISHA

(72) Inventor(s)
SHOJI AKAHANE; SATOSHI TOSAKI; KAZUO HIROTA; KENTARO TOMIOKA

(74) Attorney or Agent
ARTHUR S CAVE & CO, GPO Box 3876, SYDNEY NSW 2001

(56) Prior Art Documents
AU 71118/87 A61K 6/06
AU 587864 63011/87 A61K 6/06
AU 80388/87 A61K 6/06

(57) Claim

1. A fluoroaluminosilicate glass powder for dental glass ionomer cements, which has a specific gravity of 2.4 to 3.5 and a mean particle size of 0.02 to 10µm and which, as its components, contains 20 to 50% by weight of SiO₂, 20 to 40% by weight of Al₂O₃, 15 to 40% by weight of SrO, 1 to 20% by weight of F₂ and 0 to 15% by weight of P₂O₅ on the converted oxide basis, and which is substantially free from alkali metal ions and Be, Mg and Ba ions of alkali earth metal ions.

3. A fluoroaluminosilicate glass powder for dental glass ionomer cements, having a specific gravity of 2.4 to 3.5 and a mean particle size of 0.02 to 10µm, and containing as its components 20 to 50% by weight of SiO₂, 20 to 40% by weight

(11) AU-B-11429/88
(10) 604835

-2-

of Al_2O_3 , 15 to 40% by weight of SrO , 1 to 20% by weight of F_2 and 0 to 15% by weight of P_2O_5 on the converted oxide basis and substantially free from alkali metal ions and Be, Mg and Ba ions of alkali earth metal ions, wherein 100 parts by weight of said glass powder are treated on its surface with 0.01 to 5 parts by weight of an acid and/or fluoride.

60 48 35

AUSTRALIA

PATENTS ACT 1952

COMPLETE SPECIFICATION

(ORIGINAL)

FOR OFFICE USE

Application Number:
Lodged:

Complete Specification Lodged:
Accepted:
Published:

Priority:
Related Art:

This document contains the
amendments made under
Section 49 and is correct for
printing.

TO BE COMPLETED BY APPLICANT

Name of Applicant: G-C SHIKA KOGYO KABUSHIKI
KAISHA

Address of Applicant: 76-1, Hasunuma-cho,
Itabashi-ku, Tokyo, Japan

Actual Inventor: SHOJI AKAHANE;
SATOSHI TOSAKI;
KAZUO HIROTA; and
KENTARO TOMIOKA

Address for Service: ARTHUR S. CAVE & CO.
Patent & Trade Mark Attorneys
Level 10
10 Barrack Street
SYDNEY N.S.W. 2000
AUSTRALIA

Complete Specification for the invention entitled GLASS POWDERS
FOR DENTAL GLASS IONOMER CEMENTS.

The following statement is a full description of this invention
including the best method of performing it known to me:-

- 1 -

ASC 49
3074U/SC



GLASS POWDERS FOR DENTAL GLASS IONOMER CEMENTS

BACKGROUND OF THE INVENTION

Field of the Invention

5 The present invention relates to dental cements and, in particular, to dental glass ionomer cements. More specifically, the present invention is concerned with fluoroaluminosilicate glass powders designed for use as dental glass ionomer cements.

Statement of the Prior Art

10
15
20
25
30
35
40
45
50
55
60
65
70
75
80
85
90
95
100
105
110
115
120
125
130
135
140
145
150
155
160
165
170
175
180
185
190
195
200
205
210
215
220
225
230
235
240
245
250
255
260
265
270
275
280
285
290
295
300
305
310
315
320
325
330
335
340
345
350
355
360
365
370
375
380
385
390
395
400
405
410
415
420
425
430
435
440
445
450
455
460
465
470
475
480
485
490
495
500
505
510
515
520
525
530
535
540
545
550
555
560
565
570
575
580
585
590
595
600
605
610
615
620
625
630
635
640
645
650
655
660
665
670
675
680
685
690
695
700
705
710
715
720
725
730
735
740
745
750
755
760
765
770
775
780
785
790
795
800
805
810
815
820
825
830
835
840
845
850
855
860
865
870
875
880
885
890
895
900
905
910
915
920
925
930
935
940
945
950
955
960
965
970
975
980
985
990
995

Dental glass ionomer cements are basically obtained by allowing an acid component composed mainly of polyacrylic acid to react with fluoroaluminosilicate glass powders in the presence of water for setting, and are one of the materials which have been widely used in the dental field. With the glass ionomer cements characterized in that they are of very excellent biocompatibility, show chemical bond to tooth substance and provide a hardened mass which is translucent and of excellent estheticity, they are further expected to reinforce or strengthen tooth due to the fluorine contained therein. Because of their outstanding advantages the glass ionomer cements have been widely used for many purposes, like restorative filling, cementation of crowns, inlays and bridges or orthodontic bands, lining of cavities, core build-up and pits and fissure sealing.

20
25
30
35
40
45
50
55
60
65
70
75
80
85
90
95
100
105
110
115
120
125
130
135
140
145
150
155
160
165
170
175
180
185
190
195
200
205
210
215
220
225
230
235
240
245
250
255
260
265
270
275
280
285
290
295
300
305
310
315
320
325
330
335
340
345
350
355
360
365
370
375
380
385
390
395
400
405
410
415
420
425
430
435
440
445
450
455
460
465
470
475
480
485
490
495
500
505
510
515
520
525
530
535
540
545
550
555
560
565
570
575
580
585
590
595
600
605
610
615
620
625
630
635
640
645
650
655
660
665
670
675
680
685
690
695
700
705
710
715
720
725
730
735
740
745
750
755
760
765
770
775
780
785
790
795
800
805
810
815
820
825
830
835
840
845
850
855
860
865
870
875
880
885
890
895
900
905
910
915
920
925
930
935
940
945
950
955
960
965
970
975
980
985
990
995

However, only a combination of aluminosilicate glass powders with polyacrylic acid produces cement paste, poor in both flow and working property. In addition, since the cement requires a long time for complete set, it disintegrates on the surface when contact with saliva or water in a patient mouth and becomes brittle, thus failing to produce its final strength and estheticity. As well-known in the previous report, numerous methods have been investigated so as to

overcome these disadvantages. For instance, Japanese Patent Laid-Open No. 52(1977)-101893 for public inspection discloses a setting liquid containing a 45 to 60 % aqueous solution of polyacrylic acid or acrylic copolymer and one or more of polybasic carboxylic acids in an amount 7 to 25 % of the total weight. With this liquid, higher reaction rates and improved crushing strength were achievable. Japanese Patent Laid-Open No. 57(1982)-2210 for public inspection discloses a setting liquid for glass ionomer cements which contains tartaric acid and a fluoro complex salt with an acrylic acid copolymer, and is found to produce the aforesaid effects and result in less solubility. On the other hand, Japanese Patent Application No. 60(1985)-206299 discloses dental glass ionomer cements containing glass powders treated on the surfaces with a fluoride, and shows that a cement paste just after mixing is improved in its flow as well as in mixing property.

As stated in the foregoing, various investigations have been made on improvements in dental glass ionomer cements, but the dental cements developed by now are found to have many disadvantages and to be far from the ideal. For instance, while the solubility of dental zinc phosphate cements to distilled water is about 0.03 %, as measured according to JIS T 6602, that of glass ionomer cements are 0.2 % and more. In this respect, there is left much to be modified. When glass ionomer cements are actually applied in the mouth for clinical purposes, reduction of their solubility seems indispensable for their better durability in the mouth. In the case of current glass ionomer cements, a cement-surface embrittling phenomenon, which is believed to correlate with the solubility, occurs when they contact with saliva in an early stage of the process of setting. The surface of cement, which is not completely hardened, is easily affected by water, and dissolve therein, thus offering a problem of losing its translucency.

This problem leads to a grave defect in view of aestheticity, when that cement is used for restorative filling. For that reason, it is necessary to apply a varnish capable of being resistant to water on the surface of cement just after filling so as to shut off the influence of water. Further, hardened cements have had somewhat improved crushing strength, but have still been insufficient, compared with that of tooth substance. There is thus an increasing demand toward further improving its crushing strength.

Referring to the general properties of dental materials supplied to clinicians in the form of half-made products, working time should be preferably long and, contrary, setting time should be short. In other words, cement paste should preferably retain flowability for only the required time, and be set as sharply as possible. However, current glass ionomer cements are still far from ideal in this regard.

SUMMARY OF THE INVENTION

As a result of investigations made on the fluoroaluminosilicate glass powders used for dental glass ionomer cements with a view to improve in the foregoing points, it has unexpectedly been found that certain glasses containing no alkali metal fit for the object of the present invention.

According to one aspect of the present invention, there is provided a fluoroaluminosilicate glass powder for dental glass ionomer cements, which has a specific gravity of 2.4 to 3.5 and a mean particle size of 0.02 to 10 μm and which, in its components, contains 20 to 50 % by weight of SiO_2 , 20 to 40 % by weight of Al_2O_3 , 15 to 40 % by weight of SrO , 1 to 20 % by weight of F_2 and 0 to 15 % by weight of P_2O_5 , on the converted oxide basis, and is substantially free from alkali metal ions such as Li, Na, K, Rb and Cs ions and Be, Mg and Ba ions of alkali earth metal ions. The glass powder according to the first aspect of the present invention is found to be of less



solubility, to excel in water resistance and to be very low in the sensitivity to water in the initial stage of setting. Further, a glass ionomer cement obtained using the present glass powders has a sufficient working time, namely a sufficient time allowed for manipulation, and sets more rapidly. Still further, this glass ionomer cement has many other advantages inclusive of improvements in physical properties such as crushing strength, and radio-opacity are imparted thereto.

According to another aspect of the present invention, there is provided a glass powder in which CaO is excluded from the glass powder according to the first aspect of the invention. That is, there is provided a fluoroaluminosilicate glass powder for dental glass ionomer cements, which has a specific gravity of 2.4 to 3.5 and a mean particle size of 0.02 to 10 μm and which, in its components, contains 20 to 50 % by weight of SiO_2 , 20 to 40 % by weight of Al_2O_3 , 15 to 40 % by weight of SrO , 1 to 20 % by weight of F_2 and 0 to 15 % by weight of P_2O_5 on the converted oxide basis, and is substantially free from alkali metal ions such as Li, Na, K, Rb and Cs ions, and Be, Mg, Ca and Ba ions of alkali earth metal ions. A glass ionomer cement making use of this glass powder is found to be much more improved in the aforesaid effects. The glass ionomer cement making use of the Ca-free glass powder is much more improved in the water resistance, sensitivity to water in the initial stage of setting, mixing manipulation, setting properties, radio-opacity and physical properties.

According to yet another aspect of the invention, there is provided a fluoroaluminosilicate glass powder for dental glass ionomer cements, which is characterized in that the glass powder, according to the first or second aspect of the invention, is treated on the surface with an acid and/or a fluoride in an amount of 0.01 to 5 parts by

weight with respect to 100 parts by weight thereof.

In addition to the effects such as improvements in solubility and decrease of sensitivity to water in the initial stage of setting, glass ionomer cements containing the glass powders surface-treated according to the present invention are effective in further improving the flowability and, hence, mixing manipulation of cement paste.

Dental glass ionomer cements, in which the fluoroaluminosilicate glass powders of the present invention are used, are decreased in solubility but improved in durability, as already mentioned. In addition, the glass ionomer cements is decreased in the sensitivity to water in the initial setting just after mixing.

The setting properties of glass ionomer cements are extremely improved and the flowability of cement pastes are sustained over an increased time length, so that their setting proceeds more rapidly. Therefore, clinical manipulations for luting, filling, etc. can be carried out satisfactory with sufficient time. Further, the glass ionomer cements combine much more improved physical properties such as higher crushing strength and resistance to disintegration with radio-opacity. Still further, the flowability of cement pastes is sufficient.

DETAILED DESCRIPTION OF PREFERRED EMBODIMENT

It is desired that the glass powder used in the present invention has a true specific gravity in a range of 2.4 to 3.5. The true specific gravity of glass powders may be measured by usually employed methods using a specific gravity bottle. When the powder has a specific gravity of 2.4 or less, its weight becomes too light to be mixed with the liquid, so that difficulty is encountered in mixing. For that reason, the powder should preferably have a specific gravity exceeding 2.4. When the powder has a specific gravity of greater than 3.5, on the other hand, the proportion of Al_2O_3 , SiO_2 and F_2 , having

an influence upon reactivity, departs from the preferred scope of the present invention, thus resulting in a less reactivity. It is therefore preferred that the specific gravity of the glass powder is 2.4 to 3.5 inclusive.

5 In the present invention, it is required that the glass powders is 10 to 0.02 μm in the mean particle size. The use of glass powders having a mean particle size exceeding 10 μm is unpreferred, since they cause misfit of a precision cast crown when used as a luting cement. In this case, a crown, inlay or bridge is seated excessively away from tooth cavity. This makes occlusal equilibration difficult and has an unfavorable influence upon the durability of the cement in the mouth. Also, when powders having a mean particle size more than 10 μm are used for restorative filling, a problem arises in connection with a contact feeling, since it is impossible to obtain the desirable surface smoothness of the filled material by usual polishing method. 15 Further, the setting reaction of such powders with a liquid is so slow that their sensitibility to water in the initial stage of setting becomes higher. For these reasons, the glass powders should have a mean particle size of 10 μm or less. With fine glass powders having a mean particle size of 0.02 μm or less, on the other hand, mixing manipulation drops to an extreme so that it is very difficult to realize effective mixing. This means that the powder to liquid ratio decrease as a result of difficulty involved in the incorporating and mixing of powder with liquid. For these reasons, the mean particle size of the glass powders used is limited to 0.02 to 10 μm inclusive. 25 Direct measurement of the mean particle size of glass powders may easily be achieved with an electron microscope. By the term "particle size" is here meant the so-called averaged long-to-short diameter value of particles.

30 The aluminosilicate glass powders generally used in the glass

ionomer cements are a so-called silicate glass. Due to the structure in which Al is replaced at the Si position, the presence of metal ions is essentially required for electric balance. Of these metal ions, alkali metal ions are especially effective for reduction in the melting points of glasses, and also make it easy to make glasses. It has been found, however, that the alkali metal ions give an unfavorable influence upon the nature of glass ionomer cements. For instance, it has been noted that a hardened mass of glass ionomer cements making use of glass powders containing these metal ions shows a high solubility in water. In other words, such glass powders are responsible for deteriorations in water resistance, when used in the mouth. Hence, a glass ionomer cement, which contains glass powders free from such alkali metal ions, extremely decreases in solubility. This implies that when such a cement is applied in the mouth cavity over a long period, favorable results are obtained in connection with the retention and water resistance of the hardened cement. The sensitivity of the cement to water in the initial stage of setting was also reduced by the removal of alkali metal ions. Consequently, even when the cement surface comes into contact with water during the initial setting, a surface-clouding phenomenon leading to deteriorations in translucency and aesthetic characteristics can substantially be suppressed.

In the present invention, therefore, the content of alkali metal ions such as Li, Na, K, Rb and Cs ions is substantially null. In other words, alkali metal compounds cannot intentionally be used as the raw material for making glasses according to the present invention. The fluoroaluminosilicate glass powders free from alkali metal ions according to the present invention also have a favorable influence upon setting characteristics. It is thus possible to increase the time length during which a cement paste keeps its

sufficient flow, i.e., the working time. Conversely speaking, the glass ionomer cements including alkali metal ion-containing glass powders is short in the working time, since the viscosity of a cement paste obtained therefrom just after mixing increases rapidly.

5 In general, the alkali earth metal ions contained in glass powders react more rapidly than the aluminium ions do in the course of setting of glass ionomer cements. Hence, the alkali earth metal ions take noticeable part in the initial reaction stage. Since Ba^{2+} ions are known to possess toxicity, however, it is unpreferred to add them to the reactants in the glass powders of dental glass ionomer cements in the present invention, which are one of biomaterials. When Be and Mg ions are added to the aluminosilicate glass of the present invention, its setting reaction is so retarded that any sharp setting characteristics are not expected. Further, various physical properties also deteriorate. Suitable for such alkali earth metal ions are Ca and Sr ions, but preference is given to Sr ions. The aluminosilicate glass containing Sr ions, rather than Ca ions, undergoes sharper setting reaction and excels in various physical properties including crushing strength. In the present invention, Sr ions are an essential component. Ca ions may not necessarily be added. The aluminosilicate glass containing Sr ions has an additional advantage of imparting radio-opacity thereto. The radio-opacity are important in the diagnosis of prognosis, because it is required to confirm the locations for filling, lining, etc., when the cement is used for such purposes.

15
20
25
30 The glass according to the present invention should be composed mainly of Si, Al, Sr, F and O ions and, preferably, contain P ions. In the present disclosure, as usual with the case where the composition of glasses is generally expressed in terms of percent by weight, ions such as Si, Al, Sr and P ions except for F ions are

converted to their oxides and F ions are done as such. The percentages of the respective ions in the composition are then defined on the basis of the total weight of 100 %. Therefore, the main components of the present invention are SiO_2 , Al_2O_3 , SrO , P_2O_5 and F_2 .

5 In the glass composition of the present invention, the proportion of SiO_2 amounts to 20 to 50 % by weight of the total weight of the glass powders.

Containing SiO_2 in a proportion of greater than 50 % by weight, glass compositions are decreased in both strength and reactivity, and are thus cannot be used as part of glass ionomer cements. Further, the hardened mass are increased in solubility and poor in water resistance. Glass compositions containing SiO_2 in an amount of below 20 % by weight render glass-making difficult, and provide glass ionomer cements which are rather increased in solubility and, hence, decreased in strength. The raw materials of SiO_2 mainly include silica sand (SiO_2), kaolin ($\text{Al}_2\text{O}_3 \cdot 2\text{SiO}_2 \cdot 2\text{H}_2\text{O}$) and the like.

15 In the glass compositions of the present invention, the proportion of Al_2O_3 ranges from 20 to 40 % by weight of the total weight of the glass powders. Containing Al_2O_3 in an amount of below 20 % by weight, glass compositions provide glass ionomer cements which set at a very slow reaction rate and, once set, deteriorate in physical properties. Glass compositions having an Al_2O_3 content of greater than 40 % by weight have too high melting point, and provide dental cements which are poor in translucency and aesthetic properties. Hence, the compositional range of Al_2O_3 is limited to a range of 20 to 40 % by weight of the total weight of the glass powders.

20
25
30 The raw materials of Al_2O_3 may include, for instance, alumina (Al_2O_3), aluminium hydroxide [$\text{Al}(\text{OH})_3$], kaolin ($\text{Al}_2\text{O}_3 \cdot 2\text{SiO}_2 \cdot 2\text{H}_2\text{O}$), aluminium fluoride (AlF_3), aluminium phosphate (AlPO_4) and the like.

The proportion of SrO used in the present invention is limited to a range of 15 to 40 % by weight based on the total weight of the glass powders. Glass compositions containing SrO in an amount of below 15 % by weight render cement paste less active and glass-making difficult. Also, there is found a lowering of radio-opacity. Glass compositions containing SrO in an amount of greater than 40 % by weight again make glass-making difficult, and provide dental cements which should be manipulated within a shorter time, are decreased in physical properties, and cannot practically be used. The raw materials of SrO, used in the present invention may include strontium carbonate (SrCO_3), strontium hydroxide [$\text{Sr}(\text{OH})_2$], strontium oxide (SrO), strontium fluoride (SrF_2), strontium phosphate [$\text{Sr}_3(\text{PO}_4)_2$] and the like.

In the present invention, the proportion of F_2 is limited to a range of 1 to 20 % by weight based on the total weight of the glass powders. Glass compositions having a fluorine content of below 1 % by weight show too high a glass melting point. Fluorine is required for glass melting. In other words, fluorine is very effective for lowering the melting point of glasses, and acts as a flux. In an amount of below 1 % by weight, fluorine has no marked effect upon a lowering of the melting point of glasses. In an amount of below 1 % by weight, the reactivity of the powders also drops. When fluorine (F_2) is incorporated into glass compositions in an amount of greater than 20 % by weight, on the other hand, the reactivity of the glass powders again drops so that the resulting hardened cements are decreased in physical properties. The cements are also increased in solubility. For these reasons, the fluorine content is limited to the range of 1 to 20 % by weight. The raw materials of fluorine may include strontium fluoride (SrF_2), aluminium fluoride (AlF_3) and the like.

Phosphates may be used so as to lower the melting points of

5 glasses, but may not necessarily be added to glass compositions. It is to be noted, however, that the phosphates may serve to increase a working time of cement pastes. For that reason, the phosphates may preferably be added to glass compositions in a certain amount so as to improve the mixing manipulation of cement paste. However, the incorporation of the phosphate in an amount of greater than 15 % by weight, calculated as P_2O_5 , is unsuitable, since the setting reaction proceeds too slowly for dental cements. Hence, the proportion of the phosphate is limited to a range of 0 to 15 % by weight, calculated as P_2O_5 . The raw materials of P_2O_5 may include, for example, aluminium phosphate ($AlPO_4$), strontium phosphate [$Sr_3(PO_4)_2$] and the like.

10
15
20
25
As stated in the foregoing, the aluminosilicate glasses of the present invention contain SiO_2 , Al_2O_3 , SrO , F_2 and P_2O_5 as the main components, and are substantially free from ~~neither~~ ^{and} alkali metal ions such as Li, Na, K, Rb and Cs ions nor alkali earth metal ions such as Be, Mg and Ba ions. It is to be understood, however, that any limitation is not imposed upon other elements. As already detailed, the proportions of SiO_2 , Al_2O_3 , SrO , F_2 and P_2O_5 affect diverse aspects such as the working time, the initial setting time, physical properties such as solubility, translucency and specific gravity. The raw materials of such substances are not limited to the said ones, and may be preestimated and formulated based on the composition for formulation. What is essential in the present invention is that the critical components in glasses may come under the scope defined by the present invention.

30 The glass powders of the present invention may be obtained by melting the raw materials, cooling and then pulverizing it in a conventional manner. For instance, the raw materials may be weighed and blended together, molten at a higher temperature exceeding $1000^\circ C$, cooled off in the air, and pulverized with a ball mill, etc. More



preferably, the resulting powders may be passed through a sieve so as to remove larger particles. Usually, the powders may be passed preferably through an 80# sieve, or more preferably through an 120-mesh sieve.

5 For the acids used for surface treatment according to the present invention, mentioned are phosphoric acid, hydrochloric acid, pyrophosphoric acid, tartaric acid, citric acid, glutaric acid, malic acid, acetic acid, etc. For the same purpose, monobasic or dibasic phosphates that are acidic substances may also be used. For fluorides
10 used for surface treatment according to the present invention, the fluorides disclosed in Japanese Patent Application No. 60(1985)-206229 may be used. If the aluminosilicate glass powders free from containing alkali metal ions and a part of alkali earth metal ions, such as those disclosed in the present invention, are surface-treated with these acids and/or fluorides, not only are the physical properties improved, but the flowability and manipulatability of cement paste are also enhanced. Thus, when the aluminosilicate glasses disclosed in the present invention are surface-treated with the acids and/or fluorides, the obtained dental glass ionomer cements are much more improved in performance over the known dental cements. In view of the physical properties, the fluorides are preferred to the acids. It is a matter of course that the aluminosilicate glasses may be treated simultaneously or successively with the acids and fluorides. The surface treatment may be achieved by mechanical mixing with a mill,
15 etc. Alternatively, the acids or fluorides may be dissolved in distilled water or some solvents, which are then mixed with the glass powders, followed by the removal thereof by drying.

20
25
30 As the polymer acids used in combination with the glass powders of the present invention, when preparing dental glass ionomers, use may be made of the known liquids for glass ionomer cements. For

instance, polyacrylic acid, acrylic acid copolymers, polymaleic acid, etc. may be used. In addition, the known improved setting liquids may be used as well. For example, particular preference is given to the setting liquids containing polybasic carboxylic acids disclosed in Japanese Patent Laid-Open No. 52(1977)-101893. These polymer acids or polybasic carboxylic acids may partly or wholly be powdered and mixed with the glass powders of the present invention for practical purposes. In this case, any problem will not arise, if mixing is carried out in the presence of a suitable amount of water.

EXAMPLES

The present invention will now be explained in further detail with reference to the following examples and comparative examples.

Example 1

Sufficiently mixed in a mortar were 25.6 g of aluminium hydroxide $[Al(OH)_3]$, 37.4 g of silica sand (SiO_2) , 2.1 g of strontium carbonate $(SrCO_3)$, 11.0 g of aluminium fluoride (AlF_3) and 23.9 g of strontium phosphate $[Sr_3(PO_4)_2]$. After mixing, the mixture was put in a porcelain crucible, which was then fixed in an electrical furnace. The furnace was brought up to $1200^\circ C$, and was constantly controlled at that temperature for 3 hours. After air-cooling, the product was pulverized in a ball mill for 20 hours. The powders were passed through an 120-mesh sieve to obtain cement powders found to have a specific gravity of 2.68 and a mean particle size of $3.4 \mu m$. The cement powders were then mixed with a commercially available setting liquid for glass ionomer cements (Fuji Ionomer Type I Liquid sold from G-C Dental Industrial Corp. and produced under batch No. 120641) in a proportion of 1.8 g to 1.0 g for the measurement of physical properties. The initial setting time, crushing strength and rate of disintegration were measured according to JIS T-6602 for dental zinc phosphate cement. The working time was determined by making the end

of a spatula contact with a surface of a mixed cement paste. The rate of disintegration just after the initial setting was measured between 10 minutes and 60 minutes after the start of mixing according to JIS T-6602. Ten minutes after the commencement of mixing, the hardened cement was immersed in distilled water, and pulled up therefrom after 60 minutes. To measure the flowability of a cement paste, an 120-gram load was applied to 0.5 ml of the cement paste by the method for the measurement of standard consistency according to JIS T-6602, and the diameter (averaged long-short diameter) of the cement paste thus spread was measured. However, it was 1.5 minutes after the commencement of mixing that the load was applied to the cement paste. Thus measured consistency, working time, initial setting time, crushing strength, rate of disintegration and rate of disintegration just after the initial setting were 30 mm, 2 minutes 55 seconds, 5 minutes 15 seconds, 1650 ± 80 Kg/cm², 0.09 % and 0.52 %, respectively. The cement is thus found to provide an excellent dental luting cement.

Example 2

Sufficiently mixed in a mortar were 34.0 g of kaolin ($Al_2O_3 \cdot 2SiO_2 \cdot 2H_2O$), 25.8 g of strontium carbonate ($SrCO_3$), 15.6 g of aluminium phosphate ($AlPO_4$), 13.3 g of aluminium fluoride (AlF_3) and 11.3 g of silica sand (SiO_2). After mixing, the mixture was put in a platinum crucible, which was then heated in an electrical furnace. After heating, the furnace was kept constant at an in-furnace temperature of 1250°C for 3 hours. After melting, the melt was cooled off in the air, pulverized in a ball mill for 25 hours, and was passed through an 120-mesh sieve to obtain cement powders which were found to have a specific gravity of 2.77 and a mean particle size of 2.8 μm. The cement powders were then mixed with a commercially available setting liquid for glass ionomer cements (Fuji Ionomer Type I Liquid sold from G-C Dental Industrial Corp. and produced under batch No.

120641) in a proportion of 1.8 g to 1.0 g. Thus measured consistency, working time, initial setting time, crushing strength, rate of disintegration and rate of disintegration just after the initial setting, measured by the procedures of Ex. 1, were 31 mm, 3 minutes 05 seconds, 5 minutes 15 seconds, 1780 ± 90 Kg/cm², 0.07 % and 0.42 %, respectively. The cement was thus found to provide an excellent dental luting cement.

Example 3

Sufficiently mixed in a mortar were 52.3 g of kaolin ($Al_2O_3 \cdot 2SiO_2 \cdot 2H_2O$), 31.9 g of strontium fluoride (SrF_2), 8.3 g of aluminium phosphate ($AlPO_4$) and 7.5 g of silica sand (SiO_2). After mixing, the mixture was put in a platinum crucible, which was then heated in an electrical furnace. After heating, the furnace was kept constant at an in-furnace temperature of 1280°C for 3 hours. After melting, the melt was cooled off in the air, pulverized in a ball mill for 20 hours, and was passed through an 120-mesh sieve to obtain cement powders which were found to have a specific gravity of 2.87 and a mean particle size of 2.9 μ m. The cement powders were then mixed with a commercially available setting liquid for glass ionomer cements (Fuji Ionomer Type I Liquid sold from G-C Dental Industrial Corp. and produced under batch No. 120641) in a proportion of 1.8 g to 1.0 g. Thus measured consistency, working time, initial setting time, crushing strength, rate of disintegration and rate of disintegration just after the initial setting, measured by the procedures of Ex. 1, were 30 mm, 3 minutes 00 second, 5 minutes 15 seconds, 1750 ± 80 Kg/cm², 0.08 % and 0.45 %, respectively. The cement was thus found to provide an excellent dental luting cement.

Example 4

Sufficiently mixed in a mortar were 45.4 g of kaolin ($Al_2O_3 \cdot 2SiO_2 \cdot 2H_2O$), 8.1 g of silica sand (SiO_2), 20.2 g of strontium

oxide (SrCO_3), 8.8 g of calcium fluoride (CaF_2), 6.8 g of aluminium fluoride (AlF_3) and 10.7 g of calcium hydrogen phosphate ($\text{CaHPO}_4 \cdot 2\text{H}_2\text{O}$). After mixing, the mixture was put in a porcelain crucible, which was fixed in an electrical furnace. The furnace was increased in temperature, and was controlled at a constant temperature of 1150°C for 5 hours. After cooling off in the air, the melt was pulverized in a ball mill for 20 hours, and was passed through an 120-mesh sieve to obtain cement powders which were found to have a specific gravity of 2.61 and a mean particle size of $3.2 \mu\text{m}$. The cement powders were then mixed with a commercially available setting liquid for glass ionomer cements (Fuji Ionomer Type I Liquid sold from G-C Dental Industrial Corp. and produced under batch No. 120641) in a proportion of 1.8 g to 1.0 g. Thus measured consistency, working time, initial setting time, crushing strength, rate of disintegration and rate of disintegration just after the initial setting, measured by the procedures of Ex. 1, were 29 mm, 2 minutes 35 seconds, 5 minutes 30 seconds, $1580 \pm 60 \text{ Kg/cm}^2$, 0.12 % and 0.65 %, respectively. The cement was thus found to provide an excellent dental luting cement.

Examples 5 to 8

One hundred (100) g of the glass powders prepared in each of Examples 1 to 4 were mixed with 100 g of a 1 % aqueous solution of potassium hexafluorotitanate to make a slurry, which was then surface-treated by drying it in a dryer having a temperature of 120°C for the evaporation of moisture. The thus obtained respective powders were then mixed with a commercially available setting liquid for glass ionomer cements (Fuji Ionomer Type I Liquid sold from G-C Dental Industrial Corp. and produced under batch No. 120641) in a proportion of 1.9 g to 1.0 g to measure consistency, working time, initial setting time, crushing strength, rate of disintegration and rate of disintegration just after the initial setting by the procedures of Ex.

1. The results are set out in Table 1, and indicates that the cements are not only excellent as a luting cement, but are superior in manipulatability to the those of Examples 1 to 4, which were not subjected to any surface treatment.

Table I

Example No.	Consistency (mm)	Working time (min.sec.)	Initial setting time (min.sec.)	Crushing strength (kg/cm ²)	Rate of disintegration (%)	Rate of disintegration just after initial setting (%)
5	34	3 min. 30 sec.	5 min. 30 sec.	1960± 90	0.07	0.41
6	35	3 min. 35 sec.	5 min. 30 sec.	2020±100	0.06	0.32
7	34	3 min. 30 sec.	5 min. 30 sec.	2010±100	0.06	0.35
8	32	3 min. 05 sec.	5 min. 45 sec.	1820± 80	0.10	0.50
9	35	3 min. 35 sec.	5 min. 45 sec.	1920±100	0.09	0.40
10	33	3 min. 10 sec.	6 min. 00 sec.	1750± 70	0.13	0.55

Examples 9 and 10

5 One hundred (100) g of the glass powders prepared in each of Examples 3 and 4 were mixed with 100 g of a 1 % aqueous solution of aluminium dihydrogenphosphate [$Al(H_2PO_4)_3$]. Each of the thus obtained slurries was then surface-treated by drying it in a dryer having a temperature of 120°C for the complete evaporation of moisture. The thus obtained respective powders were then mixed with a commercially available setting liquid for glass ionomer cements (Fuji Ionomer Type I Liquid sold from G-C Dental Industrial Corp. and produced under batch No. 120641) in a proportion of 1.9 g to 1.0 g to measure consistency, working time, initial setting time, crushing strength, rate of disintegration and rate of disintegration just after the initial setting by the procedures of Ex. 1. The results are also set out in Table 1. The cements were found to provide excellent dental luting cement.

Examples 11 to 14

10 The glass powders surface-treated as in Examples 5 to 8 were mixed with a commercially available setting liquid for glass ionomer cements (Fuji Ionomer Type II (for filling) Liquid sold from G-C Dental Industrial Corp. and produced under batch No. 220641) in a proportion of 2.7 g to 1.0 g to measure the physical properties as in Example 1. The results are set out in Table 2. It is noted that the consistency was determined under a load of 2.5 Kg.

15 In consequence, the cements obtained in these examples were found to be excellent as the glass ionomer cements for filling.




Table 2

Example No.	Consistency (mm)	Working time (min.sec.)	Initial setting time (min.sec.)	Crushing strength (kg/cm ²)	Rate of disintegration (%)	Rate of disintegration just after initial setting (%)
11	31	3 min. 15 sec.	4 min. 00 sec.	2260±110	0.05	0.31
12	33	3 min. 25 sec.	4 min. 00 sec.	2370±120	0.04	0.22
13	32	3 min. 15 sec.	4 min. 00 sec.	2320±120	0.04	0.25
14	30	2 min. 50 sec.	4 min. 15 sec.	2100±110	0.08	0.36

Comparative Example 1

Sufficiently mixed in a mortar were 40 g of silica sand (SiO_2), 26 g of alumina (Al_2O_3), 12 g of sodium fluoride (NaF), 15 g of calcium carbonate (CaCO_3) and 7 g of calcium phosphate [$\text{Ca}_3(\text{PO}_4)_2$].

5 After mixing, the mixture was put in a porcelain crucible, and was molten at 1150°C for 3 hours in an electrical furnace. After melting, the melt was cooled off in the air, pulverized in a ball mill for 20 hours, and was passed through an 120-mesh sieve to obtain cement powders. The cement powders were then mixed with a commercially available setting liquid for glass ionomer cements (Fuji Ionomer Type

10 I Liquid sold from G-C Dental Industrial Corp. and produced under batch No. 120641) in a proportion of 1.4 g to 1.0 g for the measurement of physical properties. Consistency, working time, initial setting time, crushing strength, rate of disintegration and rate of disintegration just after the initial setting, measured by the procedures of Ex. 1, were 27 mm, 1 minute 30 seconds, 5 minutes 30

15 seconds, $1350 \pm 70 \text{ Kg/cm}^2$, 0.65 % and 1.52 %, respectively. The products of Examples 1 to 8 were found to be superior in all the physical properties to those of Comparative Example 1 and excellent as the dental luting cements.

20

Comparative Example 2

One hundred (100) g of the glass powders of Comparative Example 1 were mixed with 100 g of an 1 % aqueous solution of potassium hexafluorotitanate to make a slurry, which was then surface-treated by

25 drying it in a dryer having a temperature of 120°C for the evaporation of moisture. The thus obtained powders were then mixed with a commercially available setting liquid for glass ionomer cements (Fuji Ionomer Type I Liquid sold from G-C Dental Industrial Corp. and produced under batch No. 120641) in a proportion of 1.5 g to 1.0 g.

30 Consistency, working time, initial setting time, crushing strength,

rate of disintegration and rate of disintegration just after the initial setting, determined by the procedures of Ex. 1, were respectively 28 mm, 1 minute 45 seconds, 6 minutes 00 second, 1470 ± 80 Kg/cm², 0.40 % and 1.22 %. The dental luting cements according to Examples 1 to 10 are found to be improved in the physical properties over those of Comparative Example 2.

Comparative Example 3

Cement powders and a setting liquid similar to those used in Comparative Example 2 were provided and mixed together in a proportion of 2.2 g powders to 1.0 g liquid to obtain the consistency fit for filling. The physical properties were determined as in Examples 11 to 14.

Consistency, working time, initial setting time, crushing strength, rate of disintegration and rate of disintegration just after the initial setting were respectively 30 mm, 2 minutes 20 seconds, 4 minutes 15 seconds, 1680 ± 100 Kg/cm², 0.32 % and 0.75 %. It is believed that the products of Examples 11 to 14 are cements excellent for dental filling which are superior in all the physical properties to those of Comparative Example 3.

Experimental Example 1

The mixed cement paste of Examples 1 to 10 and Comparative Example 1 was hardened to a thickness of 1 mm, while teeth were cut to a thickness of 1 mm. Roentgenographs were taken of the samples with a roentgenographical device for dental purposes to compare them as regards the radio-opacity. As a result, it was found that the products of Examples 1 to 10 showed stronger radio-opacity than did the enamel of teeth, whereas the product of Comparative Example 1 showed no radio-opacity at all.

The claims defining the invention are as follows:

1. A fluoroaluminosilicate glass powder for dental glass ionomer cements, which has a specific gravity of 2.4 to 3.5 and a mean particle size of 0.02 to 10 μ m and which, as its components, contains 20 to 50% by weight of SiO₂, 20 to 40% by weight of Al₂O₃, 15 to 40% by weight of SrO, 1 to 20% by weight of F₂ and 0 to 15% by weight of P₂O₅ on the converted oxide basis, and which is substantially free from alkali metal ions and Be, Mg and Ba ions of alkali earth metal ions.

2. A fluoroaluminosilicate glass powder for dental glass ionomer cements, which has a specific gravity of 2.4 to 3.5 and a mean particle size of 0.02 to 10 μ m and which, as its components, contains 20 to 50% by weight of SiO₂, 20 to 40% by weight of Al₂O₃, 15 to 40% by weight of SrO, 1 to 20% by weight of F₂ and 0 to 15% by weight of P₂O₅ on the converted oxide basis, and which is substantially free from alkali metal ions and Be, Mg, Ca and Ba ions of alkali earth metal ions.

3. A fluoroaluminosilicate glass powder for dental glass ionomer cements, having a specific gravity of 2.4 to 3.5 and a mean particle size of 0.02 to 10 μ m, and containing as its components 20 to 50% by weight of SiO₂, 20 to 40% by weight of Al₂O₃, 15 to 40% by weight of SrO, 1 to 20% by weight of F₂ and 0 to 15% by weight of P₂O₅ on the converted oxide basis and substantially free from alkali metal ions and Be, Mg and Ba ions of alkali earth metal ions, wherein 100 parts by weight of said glass powder are treated on its surface with 0.01 to 5 parts by weight of an acid and/or fluoride.



4. A fluoroaluminosilicate glass powder for dental glass ionomer cements, having a specific gravity of 2.4 to 3.5 and a mean particle size of 0.02 to 10 μ m, and containing as its components 20 to 50% by weight of SiO₂, 20 to 40% by weight of Al₂O₃, 15 to 40% by weight of SrO, 1 to 20% by weight of F₂ and 0 to 15% by weight of P₂O₅ on the converted oxide basis and which is substantially free from alkali metal ions and Be, Mg, Ca and Ba ions of alkali earth metal ions, wherein 100 parts by weight of said glass powder are treated on its surface with 0.01 to 5 parts by weight of an acid and/or a fluoride.

5. A fluoroaluminosilicate glass powder for dental glass ionomer cements substantially as herein described with reference to the examples.

DATED this 1st day of August, 1990.

G-C SHIKA KOGYO KABUSHIKI
KAISHA
By Its Patent Attorneys
ARTHUR S. CAVE & CO.

