



US011495754B2

(12) **United States Patent**
Brooks et al.

(10) **Patent No.:** **US 11,495,754 B2**

(45) **Date of Patent:** ***Nov. 8, 2022**

(54) **ORGANIC ELECTROLUMINESCENT MATERIALS AND DEVICES**

(71) Applicant: **Universal Display Corporation**,
Ewing, NJ (US)

(72) Inventors: **Jason Brooks**, Philadelphia, PA (US);
Geza Szigethy, Newtown, PA (US);
Glenn Morello, Pittsburgh, PA (US);
Jun Deng, Murrysville, PA (US); **Peter I. Djurovich**, Long Beach, CA (US);
Hsiao-Fan Chen, Lawrence Township, NJ (US)

(73) Assignee: **UNIVERSAL DISPLAY CORPORATION**, Ewing, NJ (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 299 days.

This patent is subject to a terminal disclaimer.

(21) Appl. No.: **16/775,578**

(22) Filed: **Jan. 29, 2020**

(65) **Prior Publication Data**

US 2020/0185625 A1 Jun. 11, 2020

Related U.S. Application Data

(63) Continuation of application No. 16/295,739, filed on Mar. 7, 2019, now Pat. No. 10,636,983, which is a continuation-in-part of application No. 15/948,031, filed on Apr. 9, 2018, now Pat. No. 10,301,338, and a continuation-in-part of application No. 15/825,798, filed on Nov. 29, 2017, now Pat. No. 10,276,805, and a continuation-in-part of application No. 15/399,724, filed on Jan. 5, 2017, now Pat. No. 10,403,830, and a continuation-in-part of application No. 15/291,381, filed on Oct. 12, 2016, now Pat. No. 10,263,198, and a continuation-in-part of application No. 14/933,684, filed on Nov. 5, 2015, now Pat. No. 10,256,419, which is a continuation-in-part of application No. PCT/US2015/029269, filed on May 5, 2015.

(60) Provisional application No. 62/488,406, filed on Apr. 21, 2017, provisional application No. 62/488,107, filed on Apr. 21, 2017, provisional application No. 62/251,447, filed on Nov. 5, 2015, provisional application No. 62/082,970, filed on Nov. 21, 2014, provisional application No. 61/990,239, filed on May 8, 2014.

(51) **Int. Cl.**
H01L 51/54 (2006.01)
H01L 51/00 (2006.01)
H01L 51/50 (2006.01)
H01L 51/52 (2006.01)
C07F 15/00 (2006.01)

(52) **U.S. Cl.**

CPC **H01L 51/0085** (2013.01); **C07F 15/0033** (2013.01); **H01L 51/0087** (2013.01); **H01L 51/5016** (2013.01); **H01L 51/5092** (2013.01); **H01L 51/5096** (2013.01); **H01L 51/5206** (2013.01); **H01L 51/5221** (2013.01); **H01L 51/5056** (2013.01); **H01L 51/5072** (2013.01); **H01L 2251/5353** (2013.01); **H01L 2251/558** (2013.01)

(58) **Field of Classification Search**

None
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,769,292 A	9/1988	Tang et al.
5,061,569 A	10/1991	VanSlyke et al.
5,247,190 A	9/1993	Friend et al.
5,703,436 A	12/1997	Forrest et al.
5,707,745 A	1/1998	Forrest et al.
5,834,893 A	11/1998	Bulovic et al.
5,844,363 A	12/1998	Gu et al.
6,013,982 A	1/2000	Thompson et al.
6,087,196 A	7/2000	Sturm et al.
6,091,195 A	7/2000	Forrest et al.
6,097,147 A	8/2000	Baldo et al.
6,294,398 B1	9/2001	Kim et al.
6,303,238 B1	10/2001	Thompson et al.
6,337,102 B1	1/2002	Forrest et al.
6,468,819 B1	10/2002	Kim et al.
6,528,187 B1	3/2003	Okada
6,687,266 B1	2/2004	Ma et al.

(Continued)

FOREIGN PATENT DOCUMENTS

CN	106117269	11/2016
CN	108299505	7/2018

(Continued)

OTHER PUBLICATIONS

International Preliminary Report on Patentability issued in connection with International patent application No. PCT/US15/29269, dated Nov. 8, 2016, 10 pages.

(Continued)

Primary Examiner — Andrew K Bohaty

(74) *Attorney, Agent, or Firm* — Duane Morris LLP

(57) **ABSTRACT**

Imidazophenanthridine ligands and metal complexes are provided. The compounds exhibit improved stability through a linking substitution that links a nitrogen bonded carbon of an imidazole ring to a carbon on the adjacent fused aryl ring. The compounds may be used in OLEDs, particularly as emissive dopants in the emissive region in the OLEDs, providing devices with improved efficiency, stability, and manufacturing. In particular, the compounds provided herein may be used in blue devices having high efficiency.

(56)

References Cited

U.S. PATENT DOCUMENTS

6,835,469 B2 12/2004 Kwong et al.
 6,921,915 B2 7/2005 Takiguchi et al.
 7,087,321 B2 8/2006 Kwong et al.
 7,090,928 B2 8/2006 Thompson et al.
 7,154,114 B2 12/2006 Brooks et al.
 7,250,226 B2 7/2007 Tokito et al.
 7,279,704 B2 10/2007 Walters et al.
 7,332,232 B2 2/2008 Ma et al.
 7,338,722 B2 3/2008 Thompson et al.
 7,393,599 B2 7/2008 Thompson et al.
 7,396,598 B2 7/2008 Takeuchi et al.
 7,431,968 B1 10/2008 Shtein et al.
 7,445,855 B2 11/2008 Mackenzie et al.
 7,534,505 B2 5/2009 Lin et al.
 10,256,419 B2 4/2019 Brooks et al.
 10,263,198 B2 4/2019 Brooks et al.
 10,276,805 B2 4/2019 Brooks et al.
 2002/0034656 A1 3/2002 Thompson et al.
 2002/0134984 A1 9/2002 Igarashi
 2002/0158242 A1 10/2002 Son et al.
 2003/0138657 A1 7/2003 Li et al.
 2003/0152802 A1 8/2003 Tsuboyama et al.
 2003/0162053 A1 8/2003 Marks et al.
 2003/0175553 A1 9/2003 Thompson et al.
 2003/0230980 A1 12/2003 Forrest et al.
 2004/0036077 A1 2/2004 Ise
 2004/0137267 A1 7/2004 Igarashi et al.
 2004/0137268 A1 7/2004 Igarashi et al.
 2004/0174116 A1 9/2004 Lu et al.
 2004/0247933 A1 12/2004 Thoms
 2005/0025993 A1 2/2005 Thompson et al.
 2005/0112407 A1 5/2005 Ogasawara et al.
 2005/0238919 A1 10/2005 Ogasawara
 2005/0244673 A1 11/2005 Satoh et al.
 2005/0260441 A1 11/2005 Thompson et al.
 2005/0260449 A1 11/2005 Walters et al.
 2006/0008670 A1 1/2006 Lin et al.
 2006/0202194 A1 9/2006 Jeong et al.
 2006/0240279 A1 10/2006 Adamovich et al.
 2006/0251923 A1 11/2006 Lin et al.
 2006/0263635 A1 11/2006 Ise
 2006/0280965 A1 12/2006 Kwong et al.
 2007/0082284 A1 4/2007 Stoessel et al.
 2007/0190359 A1 8/2007 Knowles et al.
 2007/0278938 A1 12/2007 Yabunouchi et al.
 2008/0015355 A1 1/2008 Schafer et al.
 2008/0018221 A1 1/2008 Egen et al.
 2008/0106190 A1 5/2008 Yabunouchi et al.
 2008/0124572 A1 5/2008 Mizuki et al.
 2008/0220265 A1 9/2008 Xia et al.
 2008/0297033 A1 12/2008 Knowles et al.
 2009/0008605 A1 1/2009 Kawamura et al.
 2009/0009065 A1 1/2009 Nishimura et al.
 2009/0017330 A1 1/2009 Iwakuma et al.
 2009/0030202 A1 1/2009 Iwakuma et al.
 2009/0039776 A1 2/2009 Yamada et al.
 2009/0045730 A1 2/2009 Nishimura et al.
 2009/0045731 A1 2/2009 Nishimura et al.
 2009/0101870 A1 4/2009 Prakash et al.
 2009/0108737 A1 4/2009 Kwong et al.
 2009/0115316 A1 5/2009 Zheng et al.
 2009/0165846 A1 7/2009 Johannes et al.
 2009/0167162 A1 7/2009 Lin et al.
 2009/0179554 A1 7/2009 Kuma et al.
 2010/0148663 A1 6/2010 Tsai et al.
 2010/0295032 A1 11/2010 Kwong
 2012/0223276 A1 9/2012 Parham et al.
 2012/0223634 A1 9/2012 Xia et al.
 2012/0292607 A1 11/2012 Watanabe et al.
 2012/0302753 A1 11/2012 Li
 2013/0026909 A1 1/2013 Zeng
 2013/0168656 A1 7/2013 Tsai et al.
 2014/0014930 A1 1/2014 Hirose et al.
 2014/0110642 A1 4/2014 Stoessel et al.
 2014/0364605 A1 12/2014 Li et al.

2015/0105556 A1 4/2015 Li
 2015/0194616 A1 7/2015 Li et al.
 2015/0207086 A1 7/2015 Li et al.
 2015/0295189 A1 10/2015 Brooks
 2016/0072082 A1 3/2016 Brooks
 2017/0162802 A1 6/2017 Weaver et al.
 2017/0183368 A1 6/2017 Hara
 2018/0090691 A1 3/2018 Brooks
 2018/0305384 A1 10/2018 Chen
 2018/0370978 A1 12/2018 Wolohan

FOREIGN PATENT DOCUMENTS

EP 0650955 5/1995
 EP 1725079 11/2006
 EP 2034538 3/2009
 JP 200511610 1/2005
 JP 2007123392 5/2007
 JP 2007254297 10/2007
 JP 2008074939 4/2008
 JP 2012-004529 1/2012
 WO 01/39234 5/2001
 WO 02/02714 1/2002
 WO 02015654 2/2002
 WO 03040257 5/2003
 WO 03060956 7/2003
 WO 2004093207 10/2004
 WO 2004107822 12/2004
 WO 2005014551 2/2005
 WO 2005019373 3/2005
 WO 2005030900 4/2005
 WO 2005089025 9/2005
 WO 2005123873 12/2005
 WO 2006009024 1/2006
 WO 2006056418 6/2006
 WO 2006072092 7/2006
 WO 2006082742 8/2006
 WO 2006098120 9/2006
 WO 2006100298 9/2006
 WO 2006103874 10/2006
 WO 2006114966 11/2006
 WO 2006132173 12/2006
 WO 2007002683 1/2007
 WO 2007004380 1/2007
 WO 2007063754 6/2007
 WO 2007063796 6/2007
 WO 2008056746 5/2008
 WO 2008101842 8/2008
 WO 2008132085 11/2008
 WO 2008/156879 12/2008
 WO 2009000673 12/2008
 WO 2009003898 1/2009
 WO 2009008311 1/2009
 WO 2009018009 2/2009
 WO 2009021126 2/2009
 WO 2009050290 4/2009
 WO 2009062578 5/2009
 WO 2009063833 5/2009
 WO 2009066778 5/2009
 WO 2009066779 5/2009
 WO 2009086028 7/2009
 WO 2009100991 8/2009
 WO 2015/171627 11/2015

OTHER PUBLICATIONS

Notice of Reasons for Rejection dated Jul. 3, 2018 for corresponding Japanese Patent Application No. 2016-567017.
 Li, G.ujie et al. "Modifying Emission Spectral Bandwidth of Phosphorescent Platinum(II) Complexes Through Synthetic Control" Inorg. Chem. 2017, 56, pp. 8244-8256.
 Fleetham, Tyler et al., "Efficient "Pure" Blue OLEDs Employing Tetradentate Pt Complexes with a Narrow Spectral Bandwidth" Adv. Mater. 2014, 26, pp. 7116-7121.
 Zhu, Zhi-Qiang et al., "Efficient Cyclometalated Platinum(II) Complex with Superior Operational Stability" Adv. Mater. 2017, 29, 1605002, pp. 1-5.

(56)

References Cited

OTHER PUBLICATIONS

- Fleetham, Tyler B. et al. "Tetradentate Pt(II) Complexes with 6-Membered Chelate Rings: A New Route for Stable and Efficient Blue Organic Light Emitting Diodes" *Chem. Mater.* 2016, 28, pp. 3276-3282.
- Fleetham, Tyler et al. "Efficient and stable single-doped white OLEDs using a palladium-based phosphorescent excimer*" *Chem. Sci.* 2017, 8, pp. 7983-7990.
- Extended European Search Report dated Aug. 31, 2016 for corresponding European Application No. 16001000.5.
- International Search Report and Written Opinion dated Jul. 24, 2015 for corresponding PCT Application No. PCT/US15/29269.
- Extended European Search Report dated Jun. 19, 2020 for corresponding EP Application No. 20165219.5.
- Marie-Paule Van Den Eede et al. "Controlled Polymerization of a Cyclopentadithiophene-Phenylene Alternating Copolymer", *Macromolecules*, vol. 51, No. 21, Nov. 13, 2018 (Nov. 13, 2018), pp. 9043-9051, XP55702090, Washington, DC, United States ISSN: 0024-9297, DOI: 10.1021/acs.macromol.8b01820 Figure 1 [Pd-PEPPSI-(Anisole)C12].
- Joydev Dinda et al. "NHC", *New Journal of Chemistry*, vol. 37, No. 2, Jan. 1, 2013 (Jan. 1, 2013), pp. 431-438, XP55702144, GB ISSN: 1144-0546, DOI: 10.1039/C2NJ40740J the whole document.
- Adachi, Chihaya et al., "Organic Electroluminescent Device Having a Hole Conductor as an Emitting Layer," *Appl. Phys. Lett.*, 55(15): 1489-1491 (1989).
- Adachi, Chihaya et al., "Nearly 100% Internal Phosphorescence Efficiency in an Organic Light Emitting Device," *J. Appl. Phys.*, 90(10): 5048-5051 (2001).
- Adachi, Chihaya et al., "High-Efficiency Red Electrophosphorescence Devices," *Appl. Phys. Lett.*, 78(11):1622-1624 (2001).
- Aonuma, Masaki et al., "Material Design of Hole Transport Materials Capable of Thick-Film Formation in Organic Light Emitting Diodes," *Appl. Phys. Lett.*, 90, Apr. 30, 2007, 183503-1-183503-3.
- Baldo et al., "Highly Efficient Phosphorescent Emission from Organic Electroluminescent Devices," *Nature*, vol. 395, 151-154, (1998).
- Baldo et al., "Very high-efficiency green organic light-emitting devices based on electro phosphorescence," *Appl. Phys. Lett.*, vol. 75, No. 1, 4-6 (1999).
- Gao, Zhiqiang et al., "Bright-Blue Electroluminescence From a Silyl-Substituted ter-(phenylene-vinylene) derivative," *Appl. Phys. Lett.*, 74(6): 865-867 (1999).
- Guo, Tzung-Fang et al., "Highly Efficient Electrophosphorescent Polymer Light-Emitting Devices," *Organic Electronics*, 1: 15-20(2000).
- Hamada, Yuji et al., "High Luminance in Organic Electroluminescent Devices with Bis(10-hydroxybenzo[h]quinolinato) beryllium as an Emitter," *Chem. Lett.*, 905-906 (1993).
- Holmes, R.J. et al., "Blue Organic Electrophosphorescence Using Exothermic Host-Guest Energy Transfer," *Appl. Phys. Lett.*, 82(15):2422-2424 (2003).
- Hu, Nan-Xing et al., "Novel High Tg Hole-Transport Molecules Based on Indolo[3,2-b]carbazoles for Organic Light-Emitting Devices," *Synthetic Metals*, 111-112:421-424 (2000).
- Huang, Jinsong et al., "Highly Efficient Red-Emission Polymer Phosphorescent Light-Emitting Diodes Based on Two Novel Tris(1-phenylisoquinolinato-C2,N)iridium(III) Derivatives," *Adv. Mater.*, 19:739-743 (2007).
- Huang, Wei-Sheng et al., "Highly Phosphorescent Bis-Cyclometalated Iridium Complexes Containing Benzoimidazole-Based Ligands," *Chem. Mater.*, 16(12):2480-2488 (2004).
- Hung, L.S. et al., "Anode Modification in Organic Light-Emitting Diodes by Low-Frequency Plasma Polymerization of CHF₃," *Appl. Phys. Lett.*, 78(5):673-675 (2001).
- Ikai, Masamichi et al., "Highly Efficient Phosphorescence From Organic Light-Emitting Devices with an Exciton-Block Layer," *Appl. Phys. Lett.*, 79(2):156-158 (2001).
- Ikeeda, Hisao et al., "P-185 Low-Drive-Voltage OLEDs with a Buffer Layer Having Molybdenum Oxide," *SID Symposium Digest*, 37:923-926 (2006).
- Inada, Hiroshi and Shirota, Yasuhiko, "1,3,5-Tris[4-(diphenylamino)phenyl]benzene and its Methylsubstituted Derivatives as a Novel Class of Amorphous Molecular Materials," *J. Mater. Chem.*, 3(3):319-320 (1993).
- Kanno, Hiroshi et al., "Highly Efficient and Stable Red Phosphorescent Organic Light-Emitting Device Using bis[2-(2-benzothiazoyl)phenolato]zinc(II) as host material," *Appl. Phys. Lett.*, 90:123509-1-123509-3 (2007).
- Kido, Junji et al., "1,2,4-Triazole Derivative as an Electron Transport Layer in Organic Electroluminescent Devices," *Jpn. J. Appl. Phys.*, 32:L917-L920 (1993).
- Kuwabara, Yoshiyuki et al., "Thermally Stable Multilayered Organic Electroluminescent Devices Using Novel Starburst Molecules, 4,4',4'-Tri(N-carbazoyl)triphenylamine (TCTA) and 4,4',4'-Tris(3-methylphenylphenyl-amino)triphenylamine (m-MTDATA), as Hole-Transport Materials," *Adv. Mater.*, 6(9):677-679 (1994).
- Kwong, Raymond C. et al., "High Operational Stability of Electrophosphorescent Devices," *Appl. Phys. Lett.*, 81(1) 162-164 (2002).
- Lamansky, Sergey et al., "Synthesis and Characterization of Phosphorescent Cyclometalated Iridium Complexes," *Inorg. Chem.*, 40(7):1704-1711 (2001).
- Lee, Chang-Lyool et al., "Polymer Phosphorescent Light-Emitting Devices Doped with Tris(2-phenylpyridine) Iridium as a Triplet Emitter," *Appl Phys Lett.*, 77(15):2280-2282 (2000).
- Lo, Shih-Chun et al., "Blue Phosphorescence from Iridium(III) Complexes at Room Temperature," *Chem. Mater.*, 18 (21)5119-5129 (2006).
- Ma, Yuguang et al., "Triplet Luminescent Dinuclear-Gold(I) Complex-Based Light-Emitting Diodes with Low Turn-On Voltage," *Appl. Phys. Lett.*, 74(10):1361-1363 (1999).
- Mi, Bao-Xiu et al., "Thermally Stable Hole-Transporting Material for Organic Light-Emitting Diode an Isoindole Derivative," *Chem. Mater.*, 15(16):3148-3151 (2003).
- Nishida, Jun-ichi et al., "Preparation, Characterization, and Electroluminescence Characteristics of α -Diimine-type Platinum(II) Complexes with Perfluorinated Phenyl Groups as Ligands," *Chem. Lett.*, 34(4): 592-593 (2005).
- Niu, Yu-Hua et al., "Highly Efficient Electrophosphorescent Devices with Saturated Red Emission from a Neutral Osmium Complex," *Chem. Mater.*, 17(13):3532-3536 (2005).
- Noda, Tetsuya and Shirota, Yasuhiko, "5,5'-Bis(dimesitylboryl)-2,2'-bithiophene and 5,5'-Bis(dimesitylboryl)-2,2',2''-terthiophene as a Novel Family of Electron-Transporting Amorphous Molecular Materials," *J. Am. Chem. Soc.*, 120 (37):9714-9715 (1998).
- Okumoto, Kenji et al., "Green Fluorescent Organic Light-Emitting Device with External Quantum Efficiency of Nearly 10%," *Appl. Phys. Lett.*, 89:063504-1-063504-3 (2006).
- Palilis, Leonidas C., "High Efficiency Molecular Organic Light-Emitting Diodes Based On Silole Derivatives And Their Exciplexes," *Organic Electronics*, 4:113-121 (2003).
- Paulose, Betty Marie Jennifer S. et al., "First Examples of Alkenyl Pyridines as Organic Ligands for Phosphorescent Iridium Complexes," *Adv. Mater.*, 16(22):2003-2007 (2004).
- Ranjan, Sudhir et al., "Realizing Green Phosphorescent Light-Emitting Materials from Rhenium(I) Pyrazolato Diimine Complexes," *Inorg. Chem.*, 42(4):1248-1255 (2003).
- Sakamoto, Youichi et al., "Synthesis, Characterization, and Electron-Transport Property of Perfluorinated Phenylene Dendrimers," *J. Am. Chem. Soc.*, 122(8):1832-1833 (2000).
- Salbeck, J. et al., "Low Molecular Organic Glasses for Blue Electroluminescence," *Synthetic Metals*, 91:209-215 (1997).
- Shirota, Yasuhiko et al., "Starburst Molecules Based on pi-Electron Systems as Materials for Organic Electroluminescent Devices," *Journal of Luminescence*, 72-74:985-991 (1997).
- Sotoyama, Wataru et al., "Efficient Organic Light-Emitting Diodes with Phosphorescent Platinum Complexes Containing NCN-Coordinating Tridentate Ligand," *Appl. Phys. Lett.*, 86:153505-1-153505-3 (2005).
- Sun, Yiru and Forrest, Stephen R., "High-Efficiency White Organic Light Emitting Devices with Three Separate Phosphorescent Emission Layers," *Appl. Phys. Lett.*, 91:263503-1-263503-3 (2007).

(56)

References Cited

OTHER PUBLICATIONS

- T. Östergård et al., "Langmuir-Blodgett Light-Emitting Diodes Of Poly(3-Hexylthiophene) Electro-Optical Characteristics Related to Structure," *Synthetic Metals*, 88:171-177 (1997).
- Takizawa, Shin-ya et al., "Phosphorescent Iridium Complexes Based on 2-Phenylimidazo[1,2- α]pyridine Ligands Tuning of Emission Color toward the Blue Region and Application to Polymer Light-Emitting Devices," *Inorg. Chem.*, 46(10):4308-4319 (2007).
- Tang, C.W. and VanSlyke, S.A., "Organic Electroluminescent Diodes," *Appl. Phys. Lett.*, 51(12):913-915 (1987).
- Tung, Yung-Liang et al., "Organic Light-Emitting Diodes Based on Charge-Neutral Ru II Phosphorescent Emitters," *Adv. Mater.*, 17(8):1059-1064 (2005).
- Van Slyke, S. A. et al., "Organic Electroluminescent Devices with Improved Stability," *Appl. Phys. Lett.*, 69 (15):2160-2162 (1996).
- Wang, Y. et al., "Highly Efficient Electroluminescent Materials Based on Fluorinated Organometallic Iridium Compounds," *Appl. Phys. Lett.*, 79(4):449-451 (2001).
- Wong, Keith Man-Chung et al., A Novel Class of Phosphorescent Gold(III) Alkynyl-Based Organic Light-Emitting Devices with Tunable Colour, *Chem. Commun.*, 2906-2908 (2005).
- Wong, Wai-Yeung, "Multifunctional Iridium Complexes Based on Carbazole Modules as Highly Efficient Electrophosphors," *Angew. Chem. Int. Ed.*, 45:7800-7803 (2006).




FIG. 1




FIG. 2




FIG. 3a




FIG. 3b




FIG. 4




FIG. 5




FIG. 6




FIG. 7

ORGANIC ELECTROLUMINESCENT MATERIALS AND DEVICES

CROSS-REFERENCE TO RELATED APPLICATIONS

This application is a continuation of co-pending U.S. application Ser. No. 16/295,739, filed Mar. 7, 2019, which is (1) a continuation-in-part of U.S. application Ser. No. 14/933,684, filed Nov. 5, 2015, now U.S. Pat. No. 10,256,419, issued Apr. 9, 2019, which is a continuation-in-part of PCT application Serial No. PCT/US15/29269, filed on May 5, 2015, which claims priority to U.S. Provisional Application Ser. No. 61/990,239, filed on May 8, 2014, and to U.S. Provisional Application Ser. No. 62/082,970, filed on Nov. 21, 2014, (2) a continuation-in-part of U.S. application Ser. No. 15/291,381, filed Oct. 12, 2016, now U.S. Pat. No. 10,263,198, issued Apr. 16, 2019, (3) a continuation-in-part of U.S. application Ser. No. 15/399,724, filed Jan. 5, 2017, now U.S. Pat. No. 10,403,830, issued Sep. 3, 2019, which claims priority to U.S. Provisional Application No. 62/251,447, filed Nov. 5, 2015, (4) a continuation-in-part of U.S. application Ser. No. 15/825,798, filed Nov. 29, 2017, now U.S. Pat. No. 10,276,805, issued Apr. 30, 2019, (5) a continuation-in-part of U.S. application Ser. No. 15/948,031, filed Apr. 9, 2018, now U.S. Pat. No. 10,301,338, issued May 28, 2019, which claims priority to U.S. Provisional Application No. 62/488,107, filed Apr. 21, 2017, and U.S. Provisional Application No. 62/488,406, filed Apr. 21, 2017, the entire contents of which are incorporated herein by reference.

FIELD OF THE INVENTION

The present invention generally relates to novel compounds, compositions comprising the same, and applications of the compounds and compositions, including organic electroluminescent devices comprising the compounds and/or compositions.

JOINT RESEARCH AGREEMENT

The claimed inventions were made by, on behalf of, and/or in connection with one or more of the following parties to a joint university corporation research agreement: University of Southern California, and the Universal Display Corporation. The agreement was in effect on and before the date the claimed inventions were made, and the claimed inventions were made as a result of activities undertaken within the scope of the agreement.

BACKGROUND OF THE INVENTION

Generally, an OLED comprises at least one organic layer disposed between and electrically connected to an anode and a cathode. When a current is applied, the anode injects holes and the cathode injects electrons into the organic layer(s). The injected holes and electrons each migrate toward the oppositely charged electrode. When an electron and hole localize on the same molecule, an "exciton," which is a localized electron-hole pair having an excited energy state, is formed. Light is emitted when the exciton relaxes via a photoemissive mechanism. In some cases, the exciton may be localized on an excimer or an exciplex. Non-radiative mechanisms, such as thermal relaxation, may also occur, but are generally considered undesirable.

The initial OLEDs used emissive molecules that emitted light from their singlet states ("fluorescence") as disclosed, for example, in U.S. Pat. No. 4,769,292, which is incorporated by reference in its entirety. Fluorescent emission generally occurs in a time frame of less than 10 nanoseconds.

More recently, OLEDs having emissive materials that emit light from triplet states ("phosphorescence") have been demonstrated. Baldo et al., "Highly Efficient Phosphorescent Emission from Organic Electroluminescent Devices," *Nature*, vol. 395, 151-154, 1998; ("Baldo-I") and Baldo et al., "Very high-efficiency green organic light-emitting devices based on electrophosphorescence," *Appl. Phys. Lett.*, vol. 75, No. 3, 4-6 (1999) ("Baldo-II"), which are incorporated by reference in their entireties. Phosphorescence may be referred to as a "forbidden" transition because the transition requires a change in spin states, and quantum mechanics indicates that such a transition is not favored. As a result, phosphorescence generally occurs in a time frame exceeding at least 10 nanoseconds, and typically greater than 100 nanoseconds. If the natural radiative lifetime of phosphorescence is too long, triplets may decay by a non-radiative mechanism, such that no light is emitted. Organic phosphorescence is also often observed in molecules containing heteroatoms with unshared pairs of electrons at very low temperatures. 2,2'-bipyridine is such a molecule. Non-radiative decay mechanisms are typically temperature dependent, such that an organic material that exhibits phosphorescence at liquid nitrogen temperatures typically does not exhibit phosphorescence at room temperature. But, as demonstrated by Baldo, this problem may be addressed by selecting phosphorescent compounds that do phosphoresce at room temperature. Representative emissive layers include doped or un-doped phosphorescent organometallic materials such as disclosed in U.S. Pat. Nos. 6,303,238; 6,310,360; 6,830,828 and 6,835,469; U.S. Patent Application Publication No. 2002-0182441; and WO 2002/074015.

Phosphorescence may be preceded by a transition from a triplet excited state to an intermediate non-triplet state from which the emissive decay occurs. For example, organic molecules coordinated to lanthanide elements often phosphoresce from excited states localized on the lanthanide metal. However, such materials do not phosphoresce directly from a triplet excited state but instead emit from an atomic excited state centered on the lanthanide metal ion. The europium diketonate complexes illustrate one group of these types of species.

Phosphorescence from triplets can be enhanced over fluorescence by confining, preferably through bonding, the organic molecule in close proximity to an atom of high atomic number. This phenomenon, called the heavy atom effect, is created by a mechanism known as spin-orbit coupling. Such a phosphorescent transition may be observed from an excited metal-to-ligand charge transfer (MLCT) state of an organometallic molecule such as tris(2-phenylpyridine)iridium(III).

Opto-electronic devices that make use of organic materials are becoming increasingly desirable for a number of reasons. Many of the materials used to make such devices are relatively inexpensive, so organic opto-electronic devices have the potential for cost advantages over inorganic devices. In addition, the inherent properties of organic materials, such as their flexibility, may make them well suited for particular applications such as fabrication on a flexible substrate. Examples of organic opto-electronic devices include organic light emitting devices (OLEDs), organic phototransistors, organic photovoltaic cells, and


3

organic photodetectors. For OLEDs, the organic materials may have performance advantages over conventional materials. For example, the wavelength at which an organic emissive layer emits light may generally be readily tuned with appropriate dopants.

OLEDs make use of thin organic films that emit light when voltage is applied across the device. OLEDs are becoming an increasingly interesting technology for use in applications such as flat panel displays, illumination, and backlighting. Several OLED materials and configurations are described in U.S. Pat. Nos. 5,844,363, 6,303,238, and 5,707,745, which are incorporated herein by reference in their entirety.

One application for phosphorescent emissive molecules is a full color display. Industry standards for such a display call for pixels adapted to emit particular colors, referred to as “saturated” colors. In particular, these standards call for saturated red, green, and blue pixels. Alternatively, the OLED can be designed to emit white light. In conventional liquid crystal displays, emission from a white backlight is filtered using absorption filters to produce red, green and blue emission. The same technique can also be used with OLEDs. The white OLED can be either a single EML device or a stacked structure. Color may be measured using CIE coordinates, which are well known to the art.

One example of a green emissive molecule is tris(2-phenylpyridine) iridium, denoted Ir(ppy)₃, which has the following structure:



In this, and later figures herein, we depict the dative bond from nitrogen to metal (here, Ir) as a straight line.

As used herein, the term “organic” includes polymeric materials as well as small molecule organic materials that may be used to fabricate organic opto-electronic devices. “Small molecule” refers to any organic material that is not a polymer, and “small molecules” may actually be quite large. Small molecules may include repeat units in some circumstances. For example, using a long chain alkyl group as a substituent does not remove a molecule from the “small molecule” class. Small molecules may also be incorporated into polymers, for example as a pendent group on a polymer backbone or as a part of the backbone. Small molecules may also serve as the core moiety of a dendrimer, which consists of a series of chemical shells built on the core moiety. The core moiety of a dendrimer may be a fluorescent or phosphorescent small molecule emitter. A dendrimer may be a “small molecule,” and it is believed that all dendrimers currently used in the field of OLEDs are small molecules.

As used herein, “top” means furthest away from the substrate, while “bottom” means closest to the substrate. Where a first layer is described as “disposed over” a second layer, the first layer is disposed further away from substrate. There may be other layers between the first and second layer, unless it is specified that the first layer is “in contact with”

4

the second layer. For example, a cathode may be described as “disposed over” an anode, even though there are various organic layers in between.

As used herein, “solution processible” means capable of being dissolved, dispersed, or transported in and/or deposited from a liquid medium, either in solution or suspension form.

A ligand may be referred to as “photoactive” when it is believed that the ligand directly contributes to the photoactive properties of an emissive material. A ligand may be referred to as “ancillary” when it is believed that the ligand does not contribute to the photoactive properties of an emissive material, although an ancillary ligand may alter the properties of a photoactive ligand.


As used herein, and as would be generally understood by one skilled in the art, a first “Highest Occupied Molecular Orbital” (HOMO) or “Lowest Unoccupied Molecular Orbital” (LUMO) energy level is “greater than” or “higher than” a second HOMO or LUMO energy level if the first energy level is closer to the vacuum energy level. Since ionization potentials (IP) are measured as a negative energy relative to a vacuum level, a higher HOMO energy level corresponds to an IP having a smaller absolute value (an IP that is less negative). Similarly, a higher LUMO energy level corresponds to an electron affinity (EA) having a smaller absolute value (an EA that is less negative). On a conventional energy level diagram, with the vacuum level at the top, the LUMO energy level of a material is higher than the HOMO energy level of the same material. A “higher” HOMO or LUMO energy level appears closer to the top of such a diagram than a “lower” HOMO or LUMO energy level.

As used herein, and as would be generally understood by one skilled in the art, a first work function is “greater than” or “higher than” a second work function if the first work function has a higher absolute value. Because work functions are generally measured as negative numbers relative to vacuum level, this means that a “higher” work function is more negative. On a conventional energy level diagram, with the vacuum level at the top, a “higher” work function is illustrated as further away from the vacuum level in the downward direction. Thus, the definitions of HOMO and LUMO energy levels follow a different convention than work functions.

More details on OLEDs, and the definitions described above, can be found in U.S. Pat. No. 7,279,704, which is incorporated herein by reference in its entirety.

SUMMARY OF THE INVENTION

According to an aspect of the present disclosure, a compound having a structure $(L_A)_n ML_m$ according to the following Formula 1 is disclosed:



Formula 1

5

In Formula 1, M is a metal having an atomic weight greater than 40, n has a value of at least 1 and m+n is the maximum number of ligands that may be attached to the metal M; wherein A is a linking group having two to three linking atoms, wherein the linking atoms are each independently selected from the group consisting of C, Si, O, S, N, B or combinations thereof; wherein the linking atoms form at least one single bond between two linking atoms; wherein R^{1a} - R^{1g} are each independently selected from the group consisting of hydrogen, deuterium, alkyl, cycloalkyl, heteroalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aralkyl, CN, CF_3 , CO_2R , $C(O)R$, $C(O)NR_2$, NR_2 , NO_2 , OR, SR, SO_2 , SOR, SO_3R , halo, aryl, heteroaryl, a heterocyclic group, and combinations thereof;


wherein each R is independently selected from the group consisting of hydrogen, deuterium, halo, alkyl, cycloalkyl, heteroalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aralkyl, aryl, heteroaryl, and combinations thereof;

wherein any one of the ring atoms to which R^{1b} to R^{1g} are attached may be replaced with a nitrogen atom, wherein when the ring atom is replaced with a nitrogen atom the corresponding R group is not present; and wherein L is a substituted or unsubstituted cyclometallated ligand.

According to another aspect of the present disclosure, an organic light emitting device is disclosed. The OLED comprises an anode; a cathode; and an organic layer disposed between the anode and the cathode, wherein the organic layer comprises the compound having the structure according to Formula 1.

According to another aspect of the present disclosure, a formulation comprising the compound having the structure according to Formula 1 is also disclosed.

According to another aspect of the present disclosure, a compound having a structure according to Formula (1a) shown below is disclosed.



Formula (1a)

In Formula (1a), A is a linking group having two to three linking atoms, wherein the linking atoms are each independently selected from the group consisting of C, Si, O, S, N, B or combinations thereof;

wherein R^{ab} , R^{ga} , and R^{1b} to R^{1f} are each independently selected from the group consisting of hydrogen, deuterium, alkyl, cycloalkyl, heteroalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aralkyl, CN, CF_3 , CO_2R , $C(O)R$, $C(O)NR_2$, NR_2 , NO_2 , OR, SR, SO_2 , SOR, SO_3R , halo, aryl, heteroaryl, a heterocyclic group, and combinations thereof; wherein each R is independently selected from the group consisting of hydrogen, deuterium, halo, alkyl, cycloalkyl, heteroalkyl, alkoxy, aryloxy, amino,


6

silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aralkyl, aryl, heteroaryl, and combinations thereof; and


wherein any one of the ring atoms to which R^{ab} , R^{ga} , and R^{1b} to R^{1f} are attached may be replaced with a nitrogen atom, wherein when the ring atom is replaced with a nitrogen atom the corresponding R group is not present.

According to another aspect of the present disclosure, the compound of Formula (1a) can be a compound having a structure represented by structural formulas, Formula (2a) and Formula (2b) tethered together as defined below:

Formula (2a)



Formula (2b)




wherein A^1 and A^2 are each a first linking group having two to three linking atoms, wherein the linking atoms are each independently selected from the group consisting of C, Si, O, S, N, B and combinations thereof, and

wherein R^{ac} , R^{gb} , and R^{2b} to R^{2f} are each independently selected from the group consisting of hydrogen, deuterium, alkyl, cycloalkyl, heteroalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aralkyl, CN, CF_3 , CO_2R , $C(O)R$, $C(O)NR_2$, NR_2 , NO_2 , OR, SR, SO_2 , SOR, SO_3R , halo, aryl, heteroaryl, a heterocyclic group, and combinations thereof; wherein the compound is tethered together via at least one second linking group formed between R^{ab} and R^{ac} and/or R^{ga} and R^{gb} , wherein at least one second linking group has one to three linking atoms and each linking atom is independently selected from the group consisting of B, N, P, O, S, Se, C, Si, Ge and combinations thereof; and any one of the ring atoms to which R^{1b} to R^{1f} and R^{2b} to R^{2f} are attached may be replaced with a nitrogen atom, wherein when the ring atom is replaced with a nitrogen atom the corresponding R group is not present.

According to another aspect of the present disclosure, the compound of Formula (1a) can be a compound having a structure represented by Formula (3a) shown below:

Formula (3a)



wherein L and L are each independently selected from the group consisting of a single bond, BR¹, NR¹, PR¹, O, S, Se, C=O, S=O, SO₂, CR¹R², SiR¹R², and GeR¹R²;

wherein R^{3a} to R^{3f} are each independently selected from the group consisting of hydrogen, deuterium, alkyl, cycloalkyl, heteroalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, heteroalkenyl, alkynyl, aralkyl, CN, CF₃, CO₂R, C(O)R, C(O)NR₂, NR₂, NO₂, OR, SR, SO₂, SOR, SO₃R, halo, aryl, heteroaryl, a heterocyclic group, and combinations thereof;

wherein each R¹ and R² is independently selected from the group consisting of hydrogen, deuterium, halo, alkyl, cycloalkyl, heteroalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aralkyl, aryl, heteroaryl, and combinations thereof;

wherein any two adjacent R^{1f}, R^{3a}, R^{3c}, R^{3d}, R¹ and R² are optionally joined to form a ring; wherein L² and R^{1f}, L² and R^{3a}, or L² and both R^{1f} and R^{3a} are optionally joined to form one or more rings; and wherein L³ and R^{3c}, L³ and R^{3d}, or L³ and both R^{3c} and R^{3d} are optionally joined to form one or more rings.

BRIEF DESCRIPTION OF THE DRAWINGS

The foregoing summary, as well as the following detailed description of exemplary embodiments of the compounds, compositions and devices in accordance with the present invention, will be better understood when read in conjunction with the appended drawings of exemplary embodiments. It should be understood, however, that the invention is not limited to the precise arrangements and instrumentalities shown.

In the drawings:

FIG. 1 shows an exemplary organic light emitting device **100**; and

FIG. 2 illustrates an exemplary organic light emitting device **200** according to the present disclosure.

FIGS. 3a and 3b illustrate a computational model of minimized bond-broken geometry (top) and minimized non-bond broken geometry (bottom) for comparative example 1.

FIG. 4 illustrates a MALDI negative mode mass spectrum for comparative compound 4. The highest intensity peak corresponds to fragmentation of the imidazole ring.

FIG. 5 illustrates the x-ray crystal structure of 3,4-dihydrodibenzo[b,i]imidazo[2,1,5-de]quinolizine.

FIG. 6 illustrates the x-ray crystal structure of 3,3-dimethyl-3,4-dihydro-1,2a1-diaza-3-silabenzo[fg]aceanthrylene.

FIG. 7 depicts Emission spectrum of Compound 49 in 77 K and room temperature 2-methyl THF solvent and solid state PMMA matrix.

DETAILED DESCRIPTION

Generally, an OLED comprises at least one organic layer disposed between and electrically connected to an anode and a cathode. When a current is applied, the anode injects holes and the cathode injects electrons into the organic layer(s). The injected holes and electrons each migrate toward the oppositely charged electrode. When an electron and hole localize on the same molecule, an "exciton," which is a localized electron-hole pair having an excited energy state, is formed. Light is emitted when the exciton relaxes via a photoemissive mechanism. In some cases, the exciton may be localized on an excimer or an exciplex. Non-radiative mechanisms, such as thermal relaxation, may also occur, but are generally considered undesirable.

The initial OLEDs used emissive molecules that emitted light from their singlet states ("fluorescence") as disclosed, for example, in U.S. Pat. No. 4,769,292, which is incorporated by reference in its entirety. Fluorescent emission generally occurs in a time frame of less than 10 nanoseconds.

More recently, OLEDs having emissive materials that emit light from triplet states ("phosphorescence") have been demonstrated. Baldo et al., "Highly Efficient Phosphorescent Emission from Organic Electroluminescent Devices," *Nature*, vol. 395, 151-154, 1998; ("Baldo-I") and Baldo et al., "Very high-efficiency green organic light-emitting devices based on electrophosphorescence," *Appl. Phys. Lett.*, vol. 75, No. 3, 4-6 (1999) ("Baldo-II"), which are incorporated by reference in their entireties. Phosphorescence is described in more detail in U.S. Pat. No. 7,279,704 at cols. 5-6, which are incorporated by reference.

Imidazophenanthridines are useful ligands that can provide 460 nm emission when ligated to both platinum and iridium metals. Phosphorescent imidazophenanthridine complexes can provide deep blue emission with tunable photoluminescent quantum yield ranging from nearly zero to unity. Unfortunately, the device lifetime is limited for both iridium and platinum based blue-emitting complexes. We provide a strategy herein to improve the stability of the imidazophenanthridine ligand by addressing a bond on the ligand that is shown by computational theory, mass spec fragmentation analysis, and photooxidative studies to be a weak bond due to polycyclic ring strain and electronic structure.

FIG. 1 shows an organic light emitting device **100**. The figures are not necessarily drawn to scale. Device **100** may include a substrate **110**, an anode **115**, a hole injection layer **120**, a hole transport layer **125**, an electron blocking layer **130**, an emissive layer **135**, a hole blocking layer **140**, an electron transport layer **145**, an electron injection layer **150**, a protective layer **155**, a cathode **160**, and a barrier layer **170**. Cathode **160** is a compound cathode having a first conductive layer **162** and a second conductive layer **164**. Device **100** may be fabricated by depositing the layers described, in order. The properties and functions of these various layers, as well as example materials, are described in more detail in U.S. Pat. No. 7,279,704 at cols. 6-10, which are incorporated by reference.

More examples for each of these layers are available. For example, a flexible and transparent substrate-anode combination is disclosed in U.S. Pat. No. 5,844,363, which is incorporated by reference in its entirety. An example of a

p-doped hole transport layer is m-MTDATA doped with F₄-TCNQ at a molar ratio of 50:1, as disclosed in U.S. Patent Application Publication No. 2003/0230980, which is incorporated by reference in its entirety. Examples of emissive and host materials are disclosed in U.S. Pat. No. 6,303,238 to Thompson et al., which is incorporated by reference in its entirety. An example of an n-doped electron transport layer is BPhen doped with Li at a molar ratio of 1:1, as disclosed in U.S. Patent Application Publication No. 2003/0230980, which is incorporated by reference in its entirety. U.S. Pat. Nos. 5,703,436 and 5,707,745, which are incorporated by reference in their entireties, disclose examples of cathodes including compound cathodes having a thin layer of metal such as Mg:Ag with an overlying transparent, electrically-conductive, sputter-deposited ITO layer. The theory and use of blocking layers is described in more detail in U.S. Pat. No. 6,097,147 and U.S. Patent Application Publication No. 2003/0230980, which are incorporated by reference in their entireties. Examples of injection layers are provided in U.S. Patent Application Publication No. 2004/0174116, which is incorporated by reference in its entirety. A description of protective layers may be found in U.S. Patent Application Publication No. 2004/0174116, which is incorporated by reference in its entirety.

FIG. 2 shows an inverted OLED **200**. The device includes a substrate **210**, a cathode **215**, an emissive layer **220**, a hole transport layer **225**, and an anode **230**. Device **200** may be fabricated by depositing the layers described, in order. Because the most common OLED configuration has a cathode disposed over the anode, and device **200** has cathode **215** disposed under anode **230**, device **200** may be referred to as an “inverted” OLED. Materials similar to those described with respect to device **100** may be used in the corresponding layers of device **200**. FIG. 2 provides one example of how some layers may be omitted from the structure of device **100**.

The simple layered structure illustrated in FIGS. 1 and 2 is provided by way of non-limiting example, and it is understood that embodiments of the invention may be used in connection with a wide variety of other structures. The specific materials and structures described are exemplary in nature, and other materials and structures may be used. Functional OLEDs may be achieved by combining the various layers described in different ways, or layers may be omitted entirely, based on design, performance, and cost factors. Other layers not specifically described may also be included. Materials other than those specifically described may be used. Although many of the examples provided herein describe various layers as comprising a single material, it is understood that combinations of materials, such as a mixture of host and dopant, or more generally a mixture, may be used. Also, the layers may have various sublayers. The names given to the various layers herein are not intended to be strictly limiting. For example, in device **200**, hole transport layer **225** transports holes and injects holes into emissive layer **220**, and may be described as a hole transport layer or a hole injection layer. In one embodiment, an OLED may be described as having an “organic layer” disposed between a cathode and an anode. This organic layer may comprise a single layer, or may further comprise multiple layers of different organic materials as described, for example, with respect to FIGS. 1 and 2.

Structures and materials not specifically described may also be used, such as OLEDs comprised of polymeric materials (PLEDs) such as disclosed in U.S. Pat. No. 5,247,190 to Friend et al., which is incorporated by reference in its entirety. By way of further example, OLEDs having a single

organic layer may be used. OLEDs may be stacked, for example as described in U.S. Pat. No. 5,707,745 to Forrest et al, which is incorporated by reference in its entirety. The OLED structure may deviate from the simple layered structure illustrated in FIGS. 1 and 2. For example, the substrate may include an angled reflective surface to improve out-coupling, such as a mesa structure as described in U.S. Pat. No. 6,091,195 to Forrest et al., and/or a pit structure as described in U.S. Pat. No. 5,834,893 to Bulovic et al., which are incorporated by reference in their entireties.

Unless otherwise specified, any of the layers of the various embodiments may be deposited by any suitable method. For the organic layers, preferred methods include thermal evaporation, ink-jet, such as described in U.S. Pat. Nos. 6,013,982 and 6,087,196, which are incorporated by reference in their entireties, organic vapor phase deposition (OVPD), such as described in U.S. Pat. No. 6,337,102 to Forrest et al., which is incorporated by reference in its entirety, and deposition by organic vapor jet printing (OVJP), such as described in U.S. Pat. No. 7,431,968, which is incorporated by reference in its entirety. Other suitable deposition methods include spin coating and other solution based processes. Solution based processes are preferably carried out in nitrogen or an inert atmosphere. For the other layers, preferred methods include thermal evaporation. Preferred patterning methods include deposition through a mask, cold welding such as described in U.S. Pat. Nos. 6,294,398 and 6,468,819, which are incorporated by reference in their entireties, and patterning associated with some of the deposition methods such as ink-jet and OVJD. Other methods may also be used. The materials to be deposited may be modified to make them compatible with a particular deposition method. For example, substituents such as alkyl and aryl groups, branched or unbranched, and preferably containing at least 3 carbons, may be used in small molecules to enhance their ability to undergo solution processing. Substituents having 20 carbons or more may be used, and 3-20 carbons is a preferred range. Materials with asymmetric structures may have better solution processability than those having symmetric structures, because asymmetric materials may have a lower tendency to recrystallize. Dendrimer substituents may be used to enhance the ability of small molecules to undergo solution processing.

Devices fabricated in accordance with embodiments of the present invention may further optionally comprise a barrier layer. One purpose of the barrier layer is to protect the electrodes and organic layers from damaging exposure to harmful species in the environment including moisture, vapor and/or gases, etc. The barrier layer may be deposited over, under or next to a substrate, an electrode, or over any other parts of a device including an edge. The barrier layer may comprise a single layer, or multiple layers. The barrier layer may be formed by various known chemical vapor deposition techniques and may include compositions having a single phase as well as compositions having multiple phases. Any suitable material or combination of materials may be used for the barrier layer. The barrier layer may incorporate an inorganic or an organic compound or both. The preferred barrier layer comprises a mixture of a polymeric material and a non-polymeric material as described in U.S. Pat. No. 7,968,146, PCT Pat. Application Nos. PCT/US2007/023098 and PCT/US2009/042829, which are herein incorporated by reference in their entireties. To be considered a “mixture”, the aforesaid polymeric and non-polymeric materials comprising the barrier layer should be deposited under the same reaction conditions and/or at the same time. The weight ratio of polymeric to non-polymeric

material may be in the range of 95:5 to 5:95. The polymeric material and the non-polymeric material may be created from the same precursor material. In one example, the mixture of a polymeric material and a non-polymeric material consists essentially of polymeric silicon and inorganic silicon.

Devices fabricated in accordance with embodiments of the invention can be incorporated into a wide variety of electronic component modules (or units) that can be incorporated into a variety of electronic products or intermediate components. Examples of such electronic products or intermediate components include display screens, lighting devices such as discrete light source devices or lighting panels, etc. that can be utilized by the end-user product manufacturers. Such electronic component modules can optionally include the driving electronics and/or power source(s). Devices fabricated in accordance with embodiments of the invention can be incorporated into a wide variety of consumer products that have one or more of the electronic component modules (or units) incorporated therein. Such consumer products would include any kind of products that include one or more light source(s) and/or one or more of some type of visual displays. Some examples of such consumer products include flat panel displays, computer monitors, medical monitors, televisions, billboards, lights for interior or exterior illumination and/or signaling, heads-up displays, fully or partially transparent displays, flexible displays, laser printers, telephones, cell phones, tablets, phablets, personal digital assistants (PDAs), wearable devices, laptop computers, digital cameras, camcorders, viewfinders, micro-displays, 3-D displays, vehicles, a large area wall, theater or stadium screen, or a sign. Various control mechanisms may be used to control devices fabricated in accordance with the present invention, including passive matrix and active matrix. Many of the devices are intended for use in a temperature range comfortable to humans, such as 18 degrees C. to 30 degrees C., and more preferably at room temperature (20-25 degrees C.), but could be used outside this temperature range, for example, from -40 degree C. to +80 degree C.

The materials and structures described herein may have applications in devices other than OLEDs. For example, other optoelectronic devices such as organic solar cells and organic photodetectors may employ the materials and structures. More generally, organic devices, such as organic transistors, may employ the materials and structures.

The term "halo," "halogen," or "halide" as used herein includes fluorine, chlorine, bromine, and iodine.

The term "alkyl" as used herein means a straight or branched chain saturated acyclic hydrocarbon radical, which may optionally be substituted with any suitable substituent. Accordingly, an alkyl radical in accordance with the present invention can comprise any combination of primary, secondary, tertiary and quaternary carbon atoms. Exemplary alkyl radicals include, but are not limited to, C₁-C₂₀-alkyl, C₁-C₁₈-alkyl, C₁-C₁₆-alkyl, C₁-C₁₄-alkyl, C₁-C₁₂-alkyl, C₁-C₁₀-alkyl, C₁-C₈-alkyl, C₁-C₆-alkyl, C₁-C₄-alkyl, C₁-C₃-alkyl, and C₂-alkyl. Specific examples include methyl, ethyl, 1-propyl, 2-propyl, 2-methyl-1-propyl, 1-butyl, 2-butyl, t-butyl, n-octyl, n-decyl, and n-hexadecyl.

As used herein, the term "heteroalkyl" refers to an alkyl group as described herein in which one or more carbon atoms is replaced by a heteroatom. Suitable heteroatoms include oxygen, sulfur, nitrogen, phosphorus, and the like. Examples of heteroalkyl groups include, but are not limited to, alkoxy, amino, thioester, poly(ethylene glycol), and alkyl-substituted amino.

The term "cycloalkyl" as used herein contemplates cyclic alkyl radicals. Preferred cycloalkyl groups are those containing 3 to 7 carbon atoms and includes cyclopropyl, cyclopentyl, cyclohexyl, and the like. Additionally, the cycloalkyl group may be optionally substituted.

As used herein, the term "alkenyl" means acyclic branched or unbranched hydrocarbon radical having one or more carbon-carbon double bonds. Exemplary alkenyl radicals include, but are not limited to, C₁-C₂₀-alkenyl radical, C₂-C₁₈-alkenyl radical, C₂-C₁₆-alkenyl radical, C₂-C₁₄-alkenyl radical, C₂-C₁₂-alkenyl radical, C₂-C₁₀-alkenyl radical, C₂-C₈-alkenyl radical, C₂-C₆-alkenyl radical, C₂-C₄-alkenyl radical, C₂-C₃-alkenyl radical, and C₂-alkenyl radical. Specific examples include, but are not limited to, ethylenyl, propylenyl, 1-butenyl, 2-butenyl, isobutylenyl, 1-pentenyl, 2-pentenyl, 3-methyl-1-butenyl, 2-methyl-2-butenyl, and 2,3-dimethyl-2-butenyl.

As used herein, the term "alkylene" means an optionally substituted saturated straight or branched chain hydrocarbon radical. Exemplary alkylene radicals include, but are not limited to, C₁-C₂₀-alkylene, C₂-C₁₈-alkylene, C₂-C₁₆-alkylene, C₂-C₁₄-alkylene, C₂-C₁₂-alkylene, C₂-C₁₀-alkylene, C₂-C₈-alkylene, C₂-C₆-alkylene, C₂-C₄-alkylene, C₂-C₃-alkylene, and C₂-alkylene. Specific examples of alkylene include, but are not limited to, methylene, dimethylene, and trimethylene.

As used herein, the term "alkynyl" means an acyclic branched or unbranched hydrocarbon having at least one carbon-carbon triple bond. Exemplary alkylene radicals include, but are not limited to, C₁-C₂₀-alkynyl radical, C₂-C₁₈-alkynyl radical, C₂-C₁₆-alkynyl radical, C₂-C₁₄-alkynyl radical, C₂-C₁₂-alkynyl radical, C₂-C₁₀-alkynyl radical, C₂-C₈-alkynyl radical, C₂-C₆-alkynyl radical, C₂-C₄-alkynyl radical, C₂-C₃-alkynyl radical, and C₂-alkynyl radical. Specific examples of alkynyl include, but are not limited to, propargyl, and 3-pentynyl, acetylenyl, propynyl, 1-butylnyl, 2-butylnyl, 1-pentylnyl, 2-pentylnyl, and 3-methyl-1-butylnyl.

As used herein, the term "aralkyl" means one or more aryl radicals as defined herein attached through an alkyl bridge (e.g., -alkyl-(aryl)_j, wherein j is 1, 2 or 3). Specific examples of aralkyl include, but are not limited to, benzyl (—CH₂-phenyl, i.e., Bn), diphenyl methyl (—CH(phenyl)₂) and trityl (—C(phenyl)₃). Additionally, the aralkyl group may be optionally substituted.

Unless stated otherwise, as used herein, the term "heterocycle" and variants of the term, including "heterocyclic group" and "heterocyclyl," means an optionally substituted monocyclic or polycyclic ring system having as ring members atoms of at least two different elements and wherein the monocyclic or polycyclic ring system is either saturated, unsaturated or aromatic. In some embodiments, heterocycle comprises carbon atoms and at least one heteroatom. In some embodiments, heterocycle comprises carbon atoms and at least one heteroatom selected from nitrogen, oxygen, silicon, selenium, and sulfur, and wherein the nitrogen, oxygen, silicon, selenium, and sulfur heteroatoms may be optionally oxidized, and the nitrogen heteroatom may be optionally quaternized. Examples of heterocycle include, but are not limited to, furyl, benzofuranyl, thiophenyl, benzothiophenyl, pyrrolyl, indolyl, isoindolyl, azaindolyl, pyridyl, quinolinyl, isoquinolinyl, oxazolyl, isooxazolyl, benzoxazolyl, pyrazolyl, imidazolyl, benzimidazolyl, thiazolyl, benzothiazolyl, isothiazolyl, pyridazinyl, pyrimidinyl, pyrazinyl, triazinyl, cinnolinyl, phthalazinyl, and quinazolinyl. Thus, in addition to the aromatic heteroaryls listed above, heterocycles also include (but are not limited to)

13

morpholinyl, pyrrolidinonyl, pyrrolidinyl, piperizinyl, piperidinyl, hydantoinyl, valerolactamyl, oxiranyl, oxetanyl, tetrahydrofuranlyl, tetrahydropyranlyl, tetrahydropyridinyl, tetrahydropyrimidinyl, tetrahydrothiophenyl, tetrahydrothiopyranlyl, tetrahydropyrimidinyl, tetrahydrothiophenyl, and tetrahydrothiopyranlyl.

As used herein, the term “aryl” means an optionally substituted monocyclic or polycyclic aromatic hydrocarbon. Specific examples of aryl include, but are not limited to, phenyl, phenyl, 4-methylphenyl, 2,6-dimethylphenyl, naphthyl, anthracenyl, and phenanthrenyl. The term “aryl” or “aromatic group” as used herein contemplates single-ring groups and polycyclic ring systems. The polycyclic rings may have two or more rings in which two carbons are common to two adjoining rings (the rings are “fused”) wherein at least one of the rings is aromatic, e.g., the other rings can be cycloalkyls, cycloalkenyls, aryl, heterocycles, and/or heteroaryls. Additionally, the aryl group may be optionally substituted.

As used herein, the term “heteroaryl” means an optionally substituted monocyclic or polycyclic aromatic hydrocarbon having at least one heteroatom and at least one carbon atom. In some embodiments, the at least one heteroatom is selected from nitrogen, oxygen, silicon, selenium, and sulfur. Specific examples of heteroaryl include, but are not limited to, furyl, benzofuranlyl, thiophenyl, benzothiophenyl, pyrrolyl, indolyl, isoindolyl, azaindolyl, pyridyl, quinolinyl, isoquinolinyl, oxazolyl, isooxazolyl, benzoxazolyl, pyrazolyl, imidazolyl, benzimidazolyl, thiazolyl, benzothiazolyl, isothiazolyl, pyridazinyl, pyrimidinyl, pyrazinyl, triazinyl, cinnolinyl, phthalazinyl, and quinazolinyl.

The alkyl, cycloalkyl, alkenyl, alkynyl, aralkyl, heterocyclic group, aryl, and heteroaryl may be optionally substituted with one or more substituents selected from the group consisting of hydrogen, deuterium, halogen, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, cyclic amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acid, ether, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof.

The terms “substituted” and “substitution” refer to a substituent other than H that is bonded to the relevant position, e.g., a carbon or nitrogen. For example, when R¹ represents mono-substitution, then one R¹ must be other than H (i.e., a substitution). Similarly, when R¹ represents di-substitution, then two of R¹ must be other than H. Similarly, when R¹ represents no substitution, R¹, for example, can be a hydrogen for available valencies of ring atoms, as in carbon atoms for benzene and the nitrogen atom in pyrrole, or simply represents nothing for ring atoms with fully filled valencies, e.g., the nitrogen atom in pyridine. The maximum number of substitutions possible in a ring structure will depend on the total number of available valencies in the ring atoms. As used herein, “combinations thereof” indicates that one or more members of the applicable list are combined to form a known or chemically stable arrangement that one of ordinary skill in the art can envision from the applicable list. For example, an alkyl and deuterium can be combined to form a partial or fully deuterated alkyl group; a halogen and alkyl can be combined to form a halogenated alkyl substituent; and a halogen, alkyl, and aryl can be combined to form a halogenated arylalkyl. In one instance, the term substitution includes a combination of two to four of the listed groups. In another instance, the term substitution includes a combination of two to three groups. In yet another instance, the term substitution includes a combination of two groups. Preferred combinations of substituent

14

groups are those that contain up to fifty atoms that are not hydrogen or deuterium, or those which include up to forty atoms that are not hydrogen or deuterium, or those that include up to thirty atoms that are not hydrogen or deuterium. In many instances, a preferred combination of substituent groups will include up to twenty atoms that are not hydrogen or deuterium.


The “aza” designation in the fragments described herein, i.e. aza-dibenzofuran, aza-dibenzothiophene, etc. means that one or more of the C—H groups in the respective aromatic ring can be replaced by a nitrogen atom, for example, and without any limitation, azatriphenylene encompasses both dibenzo[f,h]quinoxaline and dibenzo[f,h]quinoline. One of ordinary skill in the art can readily envision other nitrogen analogs of the aza-derivatives described above, and all such analogs are intended to be encompassed by the terms as set forth herein.

It is to be understood that when a molecular fragment is described as being a substituent or otherwise attached to another moiety, its name may be written as if it were a fragment (e.g. phenyl, phenylene, naphthyl, dibenzofuryl) or as if it were the whole molecule (e.g. benzene, naphthalene, dibenzofuran). As used herein, these different ways of designating a substituent or attached fragment are considered to be equivalent.

As used herein, and as would be generally understood by one skilled in the art, a first “Highest Occupied Molecular Orbital” (HOMO) or “Lowest Unoccupied Molecular Orbital” (LUMO) energy level is “greater than” or “higher than” a second HOMO or LUMO energy level if the first energy level is closer to the vacuum energy level. Since ionization potentials (IP) are measured as a negative energy relative to a vacuum level, a higher HOMO energy level corresponds to an IP having a smaller absolute value (an IP that is less negative). Similarly, a higher LUMO energy level corresponds to an electron affinity (EA) having a smaller absolute value (an EA that is less negative). On a conventional energy level diagram, with the vacuum level at the top, the LUMO energy level of a material is higher than the HOMO energy level of the same material. A “higher” HOMO or LUMO energy level appears closer to the top of such a diagram than a “lower” HOMO or LUMO energy level.

As used herein, the term “triplet energy” refers to an energy corresponding to the highest energy feature discernable in the phosphorescence spectrum of a given material. The highest energy feature is not necessarily the peak having the greatest intensity in the phosphorescence spectrum, and could, for example, be a local maximum of a clear shoulder on the high energy side of such a peak.

According to an aspect of the present disclosure, a compound having a structure (L_A)_nML_m, according to Formula 1 shown below is disclosed.



Formula 1

15

In Formula I, M is a metal having an atomic weight greater than 40, n has a value of at least 1 and m+n is the maximum number of ligands that may be attached to the metal;

wherein A is a linking group having two to three linking atoms, wherein the linking atoms are each independently selected from the group consisting of C, Si, O, S, N, B or combinations thereof;

wherein the linking atoms form at least one single bond between two linking atoms;

wherein R^{1a} to R^{1g} are each independently selected from the group consisting of hydrogen, deuterium, alkyl, cycloalkyl, heteroalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aralkyl, CN, CF₃, CO₂R, C(O)R, C(O)NR₂, NR₂, NO₂, OR, SR, SO₂, SOR, SO₃R, halo, aryl, heteroaryl, a heterocyclic group, and combinations thereof;

wherein each R is independently selected from the group consisting of hydrogen, deuterium, halo, alkyl, cycloalkyl, heteroalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aralkyl, aryl, heteroaryl, and combinations thereof;

wherein any one of the ring atoms to which R^{1b} to R^{1g} are attached may be replaced with a nitrogen atom, wherein when the ring atom is replaced with a nitrogen atom the corresponding R group is not present; and

wherein L is a substituted or unsubstituted cyclometalated ligand.


In some embodiments of the compound of Formula 1, one of the ring atoms to which R^{1b} to R^{1g} are attached is a nitrogen atom. In some embodiments, the ring atom to which R^{1e} is attached a nitrogen atom.

In one embodiment, the compound has a triplet excited state and wherein the linking group A stabilizes the bond between N² and C^{1b} from cleavage when the compound is in the triplet excited state.

In one embodiment, the compound has a peak emissive wavelength less than 500 nm. In another embodiment, the compound has a peak emissive wavelength less than 480 nm. In yet another embodiment, the compound has a peak emissive wavelength ranging from 400 nm to 500 nm.


In some embodiments of the compound of Formula 1, the linking group A is a saturated group.

In one embodiment of the compound of Formula 1, the linking group A is independently selected from the group consisting of —CR¹R²—CR³R⁴—, —CR¹R²—CR³R⁴—CR⁵R⁶—, —CR¹R²—NR³—, —CR¹—CR²—CR³R⁴—, —O—SiR¹R²—, —CR¹R²—S—, —CR¹R²—O—, and —C—SiR¹R²—, wherein the substituents R¹ to R⁶ can be same or different, and are independently selected from the group consisting of hydrogen, deuterium, alkyl, cycloalkyl, aryl, heteroaryl, and combinations thereof; wherein any adjacent R¹ to R⁶ are optionally connected to form a saturated five membered ring or a saturated six membered ring. Any adjacent substituents refers to any two of substituents that are possible to form the ring. The two adjacent substituents can be on the same atom, or on different atoms. The linking group A can be selected from the group consisting of:















16

-continued















19

-continued



20

-continued



A4

5

A5

10

A6

15

A7

20

A8

25

A9

30

A10

35

A11

40

A12

45

A13

50

A14

55

A15

60

A15

65

A16

A17

A18

A19

A20

A21

A22

























A23

A24

A25













A28

A29

21		22	
-continued	A30	-continued	A53
	5		
	A31		A54
	A32		A55
	A33		A56
	A34		A57
	A35		A58
	A36		A59
	A37		A60
	A38		A61
	A39		A62
	A40		A63
	A41		A64
	65		













23

-continued



24

-continued



A65

5

A66

10

A67

15

A68

20

A71

25

A72

30

A72

35

A73

40

A74

45

A74

50

A75

55

A76

60

A76

65

A78

A79

A80

A81

A82

A83

A84

A85











A86

A87

A88











25

-continued



26

-continued



A89

5

A90

10

A91

15

20

A92

25

A93

30

A94

35

40

A95

45

A96

50

A97

55

60

A98

65

A99

A100

A101

A102

A103

A104

A105












A106

A107

A108












27

-continued



28

-continued



A172

5

A173

10

174

15

A175

20

A176

25

A177

30

A178

35

A179

40

A180

45

A196

50

A197

60

A197

65

A198

A199

A200

A201

A202

A203

A204


A205

A206

A207

A208

29



In some embodiments where the linking group A is independently selected from the group consisting of $-\text{CR}^1\text{R}^2-\text{CR}^3\text{R}^4-$, $-\text{CR}^1\text{R}^2-\text{CR}^3\text{R}^4-\text{CR}^5\text{R}^6-$, $-\text{CR}^1\text{R}^2-\text{NR}^3-$, $-\text{CR}^1=\text{CR}^2-\text{CR}^3\text{R}^4-$, $-\text{O}-\text{SiR}^1\text{R}^2-$, $-\text{CR}^1\text{R}^2-\text{S}-$, $-\text{CR}^1\text{R}^2-\text{O}-$, and $-\text{C}-\text{SiR}^1\text{R}^2-$, wherein the substituents R^1 to R^6 can be same or different, and are independently selected from the group consisting of hydrogen, deuterium, alkyl, cycloalkyl, aryl, heteroaryl, and combinations thereof; at least one adjacent R^1 to R^6 are connected to form a saturated five membered ring or a saturated six membered ring. In some embodiments, at least two adjacent R^1 to R^6 , if present, are connected to form a saturated five membered ring or a saturated six membered ring. In some embodiments, each R^1 to R^6 are independently selected from the group consisting of alkyl, cycloalkyl, aryl, heteroaryl, partially or fully deuterated variants thereof, and combinations thereof; wherein any adjacent R^1 to R^6 are optionally connected to form a saturated five membered ring or a saturated six membered ring.

In some embodiments where the linking group A is independently selected from the group consisting of $-\text{CR}^1\text{R}^2-\text{CR}^3\text{R}^4-$, $-\text{CR}^1\text{R}^2-\text{CR}^3\text{R}^4-\text{CR}^5\text{R}^6-$, $-\text{CR}^1\text{R}^2-\text{NR}^3-$, $-\text{CR}^1=\text{CR}^2-\text{CR}^3\text{R}^4-$, $-\text{O}-\text{SiR}^1\text{R}^2-$, $-\text{CR}^1\text{R}^2-\text{S}-$, $-\text{CR}^1\text{R}^2-\text{O}-$, and $-\text{C}-\text{SiR}^1\text{R}^2-$, wherein the substituents R^1 to R^6 can be same or different, and are independently selected from the group consisting of hydrogen, deuterium, alkyl, cycloalkyl, aryl, heteroaryl, and combinations thereof; each R^1 to R^6 are independently selected from the group consisting of methyl, ethyl, propyl, 1-methylethyl, butyl, 1-methylpropyl, 2-methylpropyl, pentyl, 1-methylbutyl, 2-methylbutyl, 3-methylbutyl, 1,1-dimethylpropyl, 1,2-dimethylpropyl, 2,2-dimethylpropyl, cyclopentyl, cyclohexyl, phenyl, 2,6-dimethylphenyl, 2,4,6-trimethylphenyl, 2,6-diisopropylphenyl, partially or fully deuterated variants thereof and combinations thereof. In some embodiments, each R^1 to R^6 are independently selected from the group consisting of alkyl, partially or fully deuterated variants thereof, and combinations thereof; wherein any adjacent R^1 to R^6 are optionally connected to form a saturated five membered ring or a saturated six membered ring.

In some embodiments of the compound of Formula 1, at least one of R^{1a} to R^{1g} is selected from the group consisting of alkyl, cycloalkyl, aryl, heteroaryl, partially or fully deuterated variants thereof, and combinations thereof. In other embodiments, at least one of R^{1b} , R^{1d} and R^{1e} is selected from the group consisting of alkyl, cycloalkyl, aryl, heteroaryl, partially or fully deuterated variants thereof, and combinations thereof. In other embodiments, R^{1d} is selected from the group consisting of alkyl, cycloalkyl, aryl, heteroaryl, partially or fully deuterated variants thereof, and

30

combinations thereof. In other embodiments, R^{1a} is selected from the group consisting of alkyl, cycloalkyl, aryl, heteroaryl, partially or fully deuterated variants thereof, and combinations thereof.

In some embodiments, R^{1a} is selected from the group consisting of non-deuterated aryl, partially deuterated aryl, and fully deuterated aryl. In some embodiments, R^{1a} is selected from the group consisting of non-deuterated phenyl, partially deuterated phenyl, and fully deuterated phenyl. In some embodiments, R^{1d} is selected from the group consisting of methyl, deuterated methyl, and isopropyl. In some embodiments, R^{1f} is selected from the group consisting of methyl, deuterated methyl, and isopropyl.

In some embodiments of the compound of Formula 1, the metal M is selected from the group consisting of Re, Ru, Os, Rh, Ir, Pd, Pt, and Au. In some embodiments, the metal M is selected from the group consisting of Ir and Pt.


In some embodiments of the compound of Formula 1, the ligand L_A is selected from the group consisting of:

L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_{A1}		H	H	H	H	H	H	H
L_{A2}		Me	H	H	H	H	H	H
L_{A3}		H	Me	H	H	H	H	H
L_{A4}		H	H	Me	H	H	H	H
L_{A5}		H	H	H	Me	H	H	H
L_{A6}		H	H	H	H	Me	H	H
L_{A7}		CD_3	H	H	H	H	H	H
L_{A8}		H	CD_3	H	H	H	H	H
L_{A9}		H	H	CD_3	H	H	H	H
L_{A10}		H	H	H	CD_3	H	H	H
L_{A11}		H	H	H	H	CD_3	H	H
L_{A12}		^iPr	H	H	H	H	H	H
L_{A13}		H	^iPr	H	H	H	H	H
L_{A14}		H	H	^iPr	H	H	H	H
L_{A15}		H	H	H	^iPr	H	H	H
L_{A16}		H	H	H	H	^iPr	H	H
L_{A17}		Ph	H	H	H	H	H	H
L_{A18}		H	Ph	H	H	H	H	H
L_{A19}		H	H	Ph	H	H	H	H
L_{A20}		H	H	H	Ph	H	H	H
L_{A21}		H	H	H	H	Ph	H	H
L_{A22}		Me	Me	H	H	H	H	H
L_{A23}		Me	H	Me	H	H	H	H
L_{A24}		Me	H	H	Me	H	H	H
L_{A25}		Me	H	H	H	Me	H	H
L_{A26}		Me	CD_3	H	H	H	H	H
L_{A27}		Me	H	CD_3	H	H	H	H
L_{A28}		Me	H	H	CD_3	H	H	H
L_{A29}		Me	H	H	H	CD_3	H	H
L_{A30}		Me	^iPr	H	H	H	H	H
L_{A31}		Me	H	^iPr	H	H	H	H
L_{A32}		Me	H	H	^iPr	H	H	H
L_{A33}		Me	H	H	H	^iPr	H	H
L_{A34}		Me	Ph	H	H	H	H	H
L_{A35}		Me	H	Ph	H	H	H	H
L_{A36}		Me	H	H	Ph	H	H	H
L_{A37}		Me	H	H	H	Ph	H	H
L_{A38}		CD_3	Me	H	H	H	H	H
L_{A39}		CD_3	H	Me	H	H	H	H
L_{A40}		CD_3	H	H	Me	H	H	H
L_{A41}		CD_3	H	H	H	Me	H	H
L_{A42}		CD_3	CD_3	H	H	H	H	H
L_{A43}		CD_3	H	CD_3	H	H	H	H
L_{A44}		CD_3	H	H	CD_3	H	H	H
L_{A45}		CD_3	H	H	H	CD_3	H	H
L_{A46}		CD_3	^iPr	H	H	H	H	H
L_{A47}		CD_3	H	^iPr	H	H	H	H
L_{A48}		CD_3	H	H	^iPr	H	H	H
L_{A49}		CD_3	H	H	H	^iPr	H	H
L_{A50}		CD_3	Ph	H	H	H	H	H
L_{A51}		CD_3	H	Ph	H	H	H	H
L_{A52}		CD_3	H	H	Ph	H	H	H
L_{A53}		CD_3	H	H	H	Ph	H	H

31

-continued



L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_{A54}		iPr	Me	H	H	H	H	H
L_{A55}		iPr	H	Me	H	H	H	H
L_{A56}		iPr	H	H	Me	H	H	H
L_{A57}		iPr	H	H	H	Me	H	H
L_{A58}		iPr	CD_3	H	H	H	H	H
L_{A59}		iPr	H	CD_3	H	H	H	H
L_{A60}		iPr	H	H	CD_3	H	H	H
L_{A61}		iPr	H	H	H	CD_3	H	H
L_{A62}		iPr	iPr	H	H	H	H	H
L_{A63}		iPr	H	iPr	H	H	H	H
L_{A64}		iPr	H	H	iPr	H	H	H
L_{A65}		iPr	H	H	H	iPr	H	H
L_{A66}		iPr	Ph	H	H	H	H	H
L_{A67}		iPr	H	Ph	H	H	H	H
L_{A68}		iPr	H	H	Ph	H	H	H
L_{A69}		iPr	H	H	H	Ph	H	H
L_{A70}		Ph	Me	H	H	H	H	H
L_{A71}		Ph	H	Me	H	H	H	H
L_{A72}		Ph	H	H	Me	H	H	H
L_{A73}		Ph	H	H	H	Me	H	H
L_{A74}		Ph	CD_3	H	H	H	H	H
L_{A75}		Ph	H	CD_3	H	H	H	H
L_{A76}		Ph	H	H	CD_3	H	H	H
L_{A77}		Ph	H	H	H	CD_3	H	H
L_{A78}		Ph	iPr	H	H	H	H	H
L_{A79}		Ph	H	iPr	H	H	H	H
L_{A80}		Ph	H	H	iPr	H	H	H
L_{A81}		Ph	H	H	H	iPr	H	H
L_{A82}		Ph	Ph	H	H	H	H	H
L_{A83}		Ph	H	Ph	H	H	H	H
L_{A84}		Ph	H	H	Ph	H	H	H
L_{A85}		Ph	H	H	H	Ph	H	H
L_{A86}		H	Me	Me	H	H	H	H
L_{A87}		H	Me	H	Me	H	H	H
L_{A88}		H	Me	H	H	Me	H	H
L_{A89}		H	Me	CD_3	H	H	H	H
L_{A90}		H	Me	H	CD_3	H	H	H
L_{A91}		H	Me	H	H	CD_3	H	H
L_{A92}		H	Me	iPr	H	H	H	H
L_{A93}		H	Me	H	iPr	H	H	H
L_{A94}		H	Me	H	H	iPr	H	H
L_{A95}		H	Me	Ph	H	H	H	H
L_{A96}		H	Me	H	Ph	H	H	H
L_{A97}		H	Me	H	H	Ph	H	H
L_{A98}		H	CD_3	Me	H	H	H	H
L_{A99}		H	CD_3	H	Me	H	H	H
L_{A100}		H	CD_3	H	H	Me	H	H
L_{A101}		H	CD_3	CD_3	H	H	H	H
L_{A102}		H	CD_3	H	CD_3	H	H	H
L_{A103}		H	CD_3	H	H	CD_3	H	H
L_{A104}		H	CD_3	iPr	H	H	H	H
L_{A105}		H	CD_3	H	iPr	H	H	H
L_{A106}		H	CD_3	H	H	iPr	H	H
L_{A107}		H	CD_3	Ph	H	H	H	H
L_{A108}		H	CD_3	H	Ph	H	H	H
L_{A109}		H	CD_3	H	H	Ph	H	H
L_{A110}		H	iPr	Me	H	H	H	H
L_{A111}		H	iPr	H	Me	H	H	H
L_{A112}		H	iPr	H	H	Me	H	H
L_{A113}		H	iPr	CD_3	H	H	H	H
L_{A114}		H	iPr	H	CD_3	H	H	H
L_{A115}		H	iPr	H	H	CD_3	H	H
L_{A116}		H	iPr	iPr	H	H	H	H
L_{A117}		H	iPr	H	iPr	H	H	H
L_{A118}		H	iPr	H	H	iPr	H	H
L_{A119}		H	iPr	Ph	H	H	H	H
L_{A120}		H	iPr	H	Ph	H	H	H
L_{A121}		H	iPr	H	H	Ph	H	H
L_{A122}		H	Ph	Me	H	H	H	H
L_{A123}		H	Ph	H	Me	H	H	H
L_{A124}		H	Ph	H	H	Me	H	H
L_{A125}		H	Ph	CD_3	H	H	H	H
L_{A126}		H	Ph	H	CD_3	H	H	H



32

-continued



L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}	
L_{A127}		H	Ph	H	H	CD_3	H	H	
L_{A128}		H	Ph	iPr	H	H	H	H	
L_{A129}		H	Ph	H	iPr	H	H	H	
L_{A130}		H	Ph	H	H	iPr	H	H	
L_{A131}		H	Ph	Ph	H	H	H	H	
L_{A132}		H	Ph	H	Ph	H	H	H	
L_{A133}		H	Ph	H	H	Ph	H	H	
L_{A134}		H	H	Me	Me	H	H	H	
L_{A135}		H	H	CD_3	Me	H	H	H	
L_{A136}		H	H	iPr	Me	H	H	H	
L_{A137}		H	H	Ph	Me	H	H	H	
L_{A138}		H	H	Me	CD_3	H	H	H	
L_{A139}		H	H	CD_3	CD_3	H	H	H	
L_{A140}		H	H	iPr	CD_3	H	H	H	
L_{A141}		H	H	Ph	CD_3	H	H	H	
L_{A142}		H	H	Me	iPr	H	H	H	
L_{A143}		H	H	CD_3	iPr	H	H	H	
L_{A144}		H	H	iPr	iPr	H	H	H	
L_{A145}		H	H	Ph	iPr	H	H	H	
L_{A146}		H	H	Me	Ph	H	H	H	
L_{A147}		H	H	CD_3	Ph	H	H	H	
L_{A148}		H	H	iPr	Ph	H	H	H	
L_{A149}		H	H	Ph	Ph	H	H	H	
L_{A150}		H	H	Me	H	Me	H	H	
L_{A151}		H	H	CD_3	H	Me	H	H	
L_{A152}		H	H	iPr	H	Me	H	H	
L_{A153}		H	H	Ph	H	Me	H	H	
L_{A154}		H	H	Me	H	CD_3	H	H	
L_{A155}		H	H	CD_3	H	CD_3	H	H	
L_{A156}		H	H	iPr	H	CD_3	H	H	
L_{A157}		H	H	Ph	H	CD_3	H	H	
L_{A158}		H	H	H	Me	H	iPr	H	H
L_{A159}		H	H	CD_3	H	iPr	H	H	
L_{A160}		H	H	iPr	H	iPr	H	H	
L_{A161}		H	H	Ph	H	iPr	H	H	
L_{A162}		H	H	Me	H	Ph	H	H	
L_{A163}		H	H	CD_3	H	Ph	H	H	
L_{A164}		H	H	iPr	H	Ph	H	H	
L_{A165}		H	H	Ph	H	Ph	H	H	
L_{A166}		Me	Me	H	Me	H	H	H	
L_{A167}		H	Me	Me	Me	H	H	H	
L_{A168}		CD_3	Me	H	Me	H	H	H	
L_{A169}		H	Me	CD_3	Me	H	H	H	
L_{A170}		iPr	Me	H	Me	H	H	H	
L_{A171}		H	Me	iPr	Me	H	H	H	
L_{A172}		Ph	Me	H	Me	H	H	H	
L_{A173}		H	Me	Ph	Me	H	H	H	
L_{A174}		Me	CD_3	H	CD_3	H	H	H	
L_{A175}		H	CD_3	Me	CD_3	H	H	H	
L_{A176}		CD_3	CD_3	H	CD_3	H	H	H	
L_{A177}		H	CD_3	CD_3	CD_3	H	H	H	
L_{A178}		iPr	CD_3	H	CD_3	H	H	H	
L_{A179}		H	CD_3	iPr	CD_3	H	H	H	
L_{A180}		Ph	CD_3	H	CD_3	H	H	H	
L_{A181}		H	CD_3	Ph	CD_3	H	H	H	
L_{A182}		Me	iPr	H	iPr	H	H	H	
L_{A183}		H	iPr	Me	iPr	H	H	H	
L_{A184}		CD_3	iPr	H	iPr	H	H	H	
L_{A185}		H	iPr	CD_3	iPr	H	H	H	
L_{A186}		iPr	iPr	H	iPr	H	H	H	
L_{A187}		H	iPr	iPr	iPr	H	H	H	
L_{A188}		Ph	iPr	H	iPr	H	H	H	
L_{A189}		H	iPr	Ph	iPr	H	H	H	
L_{A190}		Me	Ph	H	Ph	H	H	H	
L_{A191}		H	Ph	Me	Ph	H	H	H	
L_{A192}		CD_3	Ph	H	Ph	H	H	H	
L_{A193}		H	Ph	CD_3	Ph	H	H	H	
L_{A194}		iPr	Ph	H	Ph	H	H	H	
L_{A195}		H	Ph	iPr	Ph	H	H	H	
L_{A196}		Ph	Ph	H	Ph	H	H	H	
L_{A197}		H	Ph	Ph	Ph	H	H	H	
L_{A198}		H	H	H	H	H	H	H	
L_{A199}		Me	H	H	H	H	H	H	
L_{A200}		H	Me	H	H	H	H	H	
L_{A201}		H	H	Me	H	H	H	H	
L_{A202}		H	H	H	Me	H	H	H	



33

-continued

L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_{A203}		H	H	H	H	Me	H	H
L_{A204}		CD_3	H	H	H	H	H	H
L_{A205}		H	CD_3	H	H	H	H	H
L_{A206}		H	H	CD_3	H	H	H	H
L_{A207}		H	H	H	CD_3	H	H	H
L_{A208}		H	H	H	H	CD_3	H	H
L_{A209}		iPr	H	H	H	H	H	H
L_{A210}		H	iPr	H	H	H	H	H
L_{A211}		H	H	iPr	H	H	H	H
L_{A212}		H	H	H	iPr	H	H	H
L_{A213}		H	H	H	H	iPr	H	H
L_{A214}		Ph	H	H	H	H	H	H
L_{A215}		H	Ph	H	H	H	H	H
L_{A216}		H	H	Ph	H	H	H	H
L_{A217}		H	H	H	Ph	H	H	H
L_{A218}		H	H	H	H	Ph	H	H
L_{A219}		Me	Me	H	H	H	H	H
L_{A220}		Me	H	Me	H	H	H	H
L_{A221}		Me	H	H	Me	H	H	H
L_{A222}		Me	H	H	H	Me	H	H
L_{A223}		Me	CD_3	H	H	H	H	H
L_{A224}		Me	H	CD_3	H	H	H	H
L_{A225}		Me	H	H	CD_3	H	H	H
L_{A226}		Me	H	H	H	CD_3	H	H
L_{A227}		Me	iPr	H	H	H	H	H
L_{A228}		Me	H	iPr	H	H	H	H
L_{A229}		Me	H	H	iPr	H	H	H
L_{A230}		Me	H	H	H	iPr	H	H
L_{A231}		Me	Ph	H	H	H	H	H
L_{A232}		Me	H	Ph	H	H	H	H
L_{A233}		Me	H	H	Ph	H	H	H
L_{A234}		Me	H	H	H	Ph	H	H
L_{A235}		CD_3	Me	H	H	H	H	H
L_{A236}		CD_3	H	Me	H	H	H	H
L_{A237}		CD_3	H	H	Me	H	H	H
L_{A238}		CD_3	H	H	H	Me	H	H
L_{A239}		CD_3	CD_3	H	H	H	H	H
L_{A240}		CD_3	H	CD_3	H	H	H	H
L_{A241}		CD_3	H	H	CD_3	H	H	H
L_{A242}		CD_3	H	H	H	CD_3	H	H
L_{A243}		CD_3	iPr	H	H	H	H	H
L_{A244}		CD_3	H	iPr	H	H	H	H
L_{A245}		CD_3	H	H	iPr	H	H	H
L_{A246}		CD_3	H	H	H	iPr	H	H
L_{A247}		CD_3	Ph	H	H	H	H	H
L_{A248}		CD_3	H	Ph	H	H	H	H
L_{A249}		CD_3	H	H	Ph	H	H	H
L_{A250}		CD_3	H	H	H	Ph	H	H
L_{A251}		iPr	Me	H	H	H	H	H
L_{A252}		iPr	H	Me	H	H	H	H
L_{A253}		iPr	H	H	Me	H	H	H
L_{A254}		iPr	H	H	H	Me	H	H
L_{A255}		iPr	CD_3	H	H	H	H	H
L_{A256}		iPr	H	CD_3	H	H	H	H
L_{A257}		iPr	H	H	CD_3	H	H	H
L_{A258}		iPr	H	H	H	CD_3	H	H
L_{A259}		iPr	iPr	H	H	H	H	H
L_{A260}		iPr	H	iPr	H	H	H	H
L_{A261}		iPr	H	H	iPr	H	H	H
L_{A262}		iPr	H	H	H	iPr	H	H
L_{A263}		iPr	Ph	H	H	H	H	H
L_{A264}		iPr	H	Ph	H	H	H	H
L_{A265}		iPr	H	H	Ph	H	H	H
L_{A266}		iPr	H	H	H	Ph	H	H
L_{A267}		Ph	Me	H	H	H	H	H
L_{A268}		Ph	H	Me	H	H	H	H
L_{A269}		Ph	H	H	Me	H	H	H
L_{A270}		Ph	H	H	H	Me	H	H
L_{A271}		Ph	CD_3	H	H	H	H	H
L_{A272}		Ph	H	CD_3	H	H	H	H
L_{A273}		Ph	H	H	CD_3	H	H	H
L_{A274}		Ph	H	H	H	CD_3	H	H
L_{A275}		Ph	iPr	H	H	H	H	H
L_{A276}		Ph	H	iPr	H	H	H	H
L_{A277}		Ph	H	H	iPr	H	H	H
L_{A278}		Ph	H	H	H	iPr	H	H



34




-continued

L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_{A279}		Ph	Ph	H	H	H	H	H
L_{A280}		Ph	H	Ph	H	H	H	H
L_{A281}		Ph	H	H	Ph	H	H	H
L_{A282}		Ph	H	H	H	Ph	H	H
L_{A283}		H	Me	Me	H	H	H	H
L_{A284}		H	Me	H	Me	H	H	H
L_{A285}		H	Me	H	H	Me	H	H
L_{A286}		H	Me	CD_3	H	H	H	H
L_{A287}		H	Me	H	CD_3	H	H	H
L_{A288}		H	Me	H	H	CD_3	H	H
L_{A289}		H	Me	iPr	H	H	H	H
L_{A290}		H	Me	H	iPr	H	H	H
L_{A291}		H	Me	H	H	iPr	H	H
L_{A292}		H	Me	Ph	H	H	H	H
L_{A293}		H	Me	H	Ph	H	H	H
L_{A294}		H	Me	H	H	Ph	H	H
L_{A295}		H	CD_3	Me	H	H	H	H
L_{A296}		H	CD_3	H	Me	H	H	H
L_{A297}		H	CD_3	H	H	Me	H	H
L_{A298}		H	CD_3	CD_3	H	H	H	H
L_{A299}		H	CD_3	H	CD_3	H	H	H
L_{A300}		H	CD_3	H	H	CD_3	H	H
L_{A301}		H	CD_3	iPr	H	H	H	H
L_{A302}		H	CD_3	H	iPr	H	H	H
L_{A303}		H	CD_3	H	H	iPr	H	H
L_{A304}		H	CD_3	Ph	H	H	H	H
L_{A305}		H	CD_3	H	Ph	H	H	H
L_{A306}		H	CD_3	H	H	Ph	H	H
L_{A307}		H	iPr	Me	H	H	H	H
L_{A308}		H	iPr	H	Me	H	H	H
L_{A309}		H	iPr	H	H	Me	H	H
L_{A310}		H	iPr	CD_3	H	H	H	H
L_{A311}		H	iPr	H	CD_3	H	H	H
L_{A312}		H	iPr	H	H	CD_3	H	H
L_{A313}		H	iPr	iPr	H	H	H	H
L_{A314}		H	iPr	H	iPr	H	H	H
L_{A315}		H	iPr	H	H	iPr	H	H
L_{A316}		H	iPr	Ph	H	H	H	H
L_{A317}		H	iPr	H	Ph	H	H	H
L_{A318}		H	iPr	H	H	Ph	H	H
L_{A319}		H	Ph	Me	H	H	H	H
L_{A320}		H	Ph	H	Me	H	H	H
L_{A321}		H	Ph	H	H	Me	H	H
L_{A322}		H	Ph	CD_3	H	H	H	H
L_{A323}		H	Ph	H	CD_3	H	H	H
L_{A324}		H	Ph	H	H	CD_3	H	H
L_{A325}		H	Ph	iPr	H	H	H	H
L_{A326}		H	Ph	H	iPr	H	H	H
L_{A327}		H	Ph	H	H	iPr	H	H
L_{A328}		H	Ph	Ph	H	H	H	H
L_{A329}		H	Ph	H	Ph	H	H	H
L_{A330}		H	Ph	H	H	Ph	H	H
L_{A331}		H	H	Me	Me	H	H	H
L_{A332}		H	H	CD_3	Me	H	H	H
L_{A333}		H	H	iPr	Me	H	H	H
L_{A334}		H	H	Ph	Me	H	H	H
L_{A335}		H	H	Me	CD_3	H	H	H
L_{A336}		H	H	CD_3	CD_3	H	H	H
L_{A337}		H	H	iPr	CD_3	H	H	H
L_{A338}		H	H	Ph	CD_3	H	H	H
L_{A339}		H	H	Me	iPr	H	H	H
L_{A340}		H	H	CD_3	iPr	H	H	H
L_{A341}		H	H	H	iPr	H	H	H
L_{A342}		H	H	Ph	iPr	H	H	H
L_{A343}		H	H	Me	Ph	H	H	H
L_{A344}		H	H	CD_3	Ph	H	H	H
L_{A345}		H	H	iPr	Ph	H	H	H
L_{A346}		H	H	Ph	Ph	H	H	H
L_{A347}		H	H	Me	H	Me	H	H
L_{A348}		H	H	CD_3	H	Me	H	H
L_{A349}		H	H	iPr	H	Me	H	H
L_{A350}		H	H	Ph	H	Me	H	H
L_{A351}		H	H	Me	H	CD_3	H	H
L_{A352}		H	H	CD_3	H	CD_3	H	H
L_{A353}		H	H	iPr	H	CD_3	H	H
L_{A354}		H	H	Ph	H	CD_3	H	H
L_{A355}		H	H	Me	H	iPr	H	H

35

-continued

L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_{A356}		H	H	CD ₃	H	^t Pr	H	H
L_{A357}		H	H	^t Pr	H	^t Pr	H	H
L_{A358}		H	H	Ph	H	^t Pr	H	H
L_{A359}		H	H	Me	H	Ph	H	H
L_{A360}		H	H	CD ₃	H	Ph	H	H
L_{A361}		H	H	^t Pr	H	Ph	H	H
L_{A362}		H	H	Ph	H	Ph	H	H
L_{A363}		Me	Me	H	Me	H	H	H
L_{A364}		H	Me	Me	Me	H	H	H
L_{A365}		CD ₃	Me	H	Me	H	H	H
L_{A366}		H	Me	CD ₃	Me	H	H	H
L_{A367}		^t Pr	Me	H	Me	H	H	H
L_{A368}		H	Me	^t Pr	Me	H	H	H
L_{A369}		Ph	Me	H	Me	H	H	H
L_{A370}		H	Me	Ph	Me	H	H	H
L_{A371}		Me	CD ₃	H	CD ₃	H	H	H
L_{A372}		H	CD ₃	Me	CD ₃	H	H	H
L_{A373}		CD ₃	CD ₃	H	CD ₃	H	H	H
L_{A374}		H	CD ₃	CD ₃	CD ₃	H	H	H
L_{A375}		^t Pr	CD ₃	H	CD ₃	H	H	H
L_{A376}		H	CD ₃	^t Pr	CD ₃	H	H	H
L_{A377}		Ph	CD ₃	H	CD ₃	H	H	H
L_{A378}		H	CD ₃	Ph	CD ₃	H	H	H
L_{A379}		Me	^t Pr	H	^t Pr	H	H	H
L_{A380}		H	^t Pr	Me	^t Pr	H	H	H
L_{A381}		CD ₃	^t Pr	H	^t Pr	H	H	H
L_{A382}		H	^t Pr	CD ₃	^t Pr	H	H	H
L_{A383}		^t Pr	^t Pr	H	^t Pr	H	H	H
L_{A384}		H	^t Pr	iPr	^t Pr	H	H	H
L_{A385}		Ph	^t Pr	H	^t Pr	H	H	H
L_{A386}		H	^t Pr	Ph	^t Pr	H	H	H
L_{A387}		Me	Ph	H	Ph	H	H	H
L_{A388}		H	Ph	Me	Ph	H	H	H
L_{A389}		CD ₃	Ph	H	Ph	H	H	H
L_{A390}		H	Ph	CD ₃	Ph	H	H	H
L_{A391}		^t Pr	Ph	H	Ph	H	H	H
L_{A392}		H	Ph	^t Pr	Ph	H	H	H
L_{A393}		Ph	Ph	H	Ph	H	H	H
L_{A394}		H	Ph	Ph	Ph	H	H	H
L_{A395}		H	H	H	H	H	H	H
L_{A396}		Me	H	H	H	H	H	H
L_{A397}		H	Me	H	H	H	H	H
L_{A398}		H	H	Me	H	H	H	H
L_{A399}		H	H	H	Me	H	H	H
L_{A400}		H	H	H	Me	H	H	H
L_{A401}		CD ₃	H	H	H	H	H	H
L_{A402}		H	CD ₃	H	H	H	H	H
L_{A403}		H	H	CD ₃	H	H	H	H
L_{A404}		H	H	H	CD ₃	H	H	H
L_{A405}		H	H	H	H	CD ₃	H	H
L_{A406}		^t Pr	H	H	H	H	H	H
L_{A407}		H	^t Pr	H	H	H	H	H
L_{A408}		H	H	^t Pr	H	H	H	H
L_{A409}		H	H	H	^t Pr	H	H	H
L_{A410}		H	H	H	H	^t Pr	H	H
L_{A411}		Ph	H	H	H	H	H	H
L_{A412}		H	Ph	H	H	H	H	H
L_{A413}		H	H	Ph	H	H	H	H
L_{A414}		H	H	H	Ph	H	H	H
L_{A415}		H	H	H	H	Ph	H	H
L_{A416}		Me	Me	H	H	H	H	H
L_{A417}		Me	H	Me	H	H	H	H
L_{A418}		Me	H	H	Me	H	H	H
L_{A419}		Me	H	H	Me	H	H	H
L_{A420}		Me	CD ₃	H	H	H	H	H
L_{A421}		Me	H	CD ₃	H	H	H	H
L_{A422}		Me	H	H	CD ₃	H	H	H
L_{A423}		Me	H	H	H	CD ₃	H	H
L_{A424}		Me	^t Pr	H	H	H	H	H
L_{A425}		Me	H	^t Pr	H	H	H	H
L_{A426}		Me	H	H	^t Pr	H	H	H
L_{A427}		Me	H	H	H	^t Pr	H	H
L_{A428}		Me	Ph	H	H	H	H	H
L_{A429}		Me	H	Ph	H	H	H	H
L_{A430}		Me	H	H	Ph	H	H	H
L_{A431}		Me	H	H	H	Ph	H	H



36


-continued

L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_{A432}		CD ₃	Me	H	H	H	H	H
L_{A433}		CD ₃	H	Me	H	H	H	H
L_{A434}		CD ₃	H	H	Me	H	H	H
L_{A435}		CD ₃	H	H	H	Me	H	H
L_{A436}		CD ₃	CD ₃	H	H	H	H	H
L_{A437}		CD ₃	H	CD ₃	H	H	H	H
L_{A438}		CD ₃	H	H	CD ₃	H	H	H
L_{A439}		CD ₃	H	H	H	CD ₃	H	H
L_{A440}		CD ₃	^t Pr	H	H	H	H	H
L_{A441}		CD ₃	H	^t Pr	H	H	H	H
L_{A442}		CD ₃	H	H	^t Pr	H	H	H
L_{A443}		CD ₃	H	H	H	^t Pr	H	H
L_{A444}		CD ₃	Ph	H	H	H	H	H
L_{A445}		CD ₃	H	Ph	H	H	H	H
L_{A446}		CD ₃	H	H	Ph	H	H	H
L_{A447}		CD ₃	H	H	H	Ph	H	H
L_{A448}		^t Pr	Me	H	H	H	H	H
L_{A449}		^t Pr	H	Me	H	H	H	H
L_{A450}		^t Pr	H	H	Me	H	H	H
L_{A451}		^t Pr	H	H	H	Me	H	H
L_{A452}		^t Pr	CD ₃	H	H	H	H	H
L_{A453}		^t Pr	H	CD ₃	H	H	H	H
L_{A454}		^t Pr	H	H	CD ₃	H	H	H
L_{A455}		^t Pr	H	H	H	CD ₃	H	H
L_{A456}		^t Pr	^t Pr	H	H	H	H	H
L_{A457}		^t Pr	H	^t Pr	H	H	H	H
L_{A458}		^t Pr	H	H	^t Pr	H	H	H
L_{A459}		^t Pr	H	H	H	^t Pr	H	H
L_{A460}		^t Pr	Ph	H	H	H	H	H
L_{A461}		^t Pr	H	Ph	H	H	H	H
L_{A462}		^t Pr	H	H	Ph	H	H	H
L_{A463}		^t Pr	H	H	H	Ph	H	H
L_{A464}		Ph	Me	H	H	H	H	H
L_{A465}		Ph	H	Me	H	H	H	H
L_{A466}		Ph	H	H	Me	H	H	H
L_{A467}		Ph	H	H	H	Me	H	H
L_{A468}		Ph	CD ₃	H	H	H	H	H
L_{A469}		Ph	H	CD ₃	H	H	H	H
L_{A470}		Ph	H	H	CD ₃	H	H	H
L_{A471}		Ph	H	H	H	CD ₃	H	H
L_{A472}		Ph	^t Pr	H	H	H	H	H
L_{A473}		Ph	H	^t Pr	H	H	H	H
L_{A474}		Ph	H	H	^t Pr	H	H	H
L_{A475}		Ph	H	H	H	^t Pr	H	H
L_{A476}		Ph	Ph	H	H	H	H	H
L_{A477}		Ph	H	Ph	H	H	H	H
L_{A478}		Ph	H	H	Ph	H	H	H
L_{A479}		Ph	H	H	H	Ph	H	H
L_{A480}		H	Me	Me	H	H	H	H
L_{A481}		H	Me	H	Me	H	H	H
L_{A482}		H	Me	H	H	Me	H	H
L_{A483}		H	Me	CD ₃	H	H	H	H
L_{A484}		H	Me	H	CD ₃	H	H	H
L_{A485}		H	Me	H	H	CD ₃	H	H
L_{A486}		H	Me	^t Pr	H	H	H	H
L_{A487}		H	Me	H	^t Pr	H	H	H
L_{A488}		H	Me	H	H	^t Pr	H	H
L_{A489}		H	Me	Ph	H	H	H	H
L_{A490}		H	Me	H	Ph	H	H	H
L_{A491}		H	Me	H	H	Ph	H	H
L_{A492}		H	CD ₃	Me	H	H	H	H
L_{A493}		H	CD ₃	H	Me	H	H	H
L_{A494}		H	CD ₃	H	H	Me	H	H
L_{A495}		H	CD ₃	CD ₃	H	H	H	H
L_{A496}		H	CD ₃	H	CD ₃	H	H	H
L_{A497}		H	CD ₃	H	H	CD ₃	H	H
L_{A498}		H	CD ₃	^t Pr	H	H	H	H
L_{A499}		H	CD ₃	H	^t Pr	H	H	H
L_{A500}		H	CD ₃	H	H	^t Pr	H	H
L_{A501}		H	CD ₃	Ph	H	H	H	H
L_{A502}		H	CD ₃	H	Ph	H	H	H
L_{A503}		H	CD ₃	H	H	Ph	H	H
L_{A504}		H	^t Pr	Me	H	H	H	H
L_{A505}		H	^t Pr	H	Me	H	H	H
L_{A506}		H	^t Pr	H	H	Me	H	H
L_{A507}		H	^t Pr	CD ₃	H	H	H	H

37

-continued



L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_{A508}		H	i Pr	H	CD_3	H	H	H
L_{A509}		H	i Pr	H	CD_3	H	H	H
L_{A510}		H	i Pr	i Pr	H	H	H	H
L_{A511}		H	i Pr	H	i Pr	H	H	H
L_{A512}		H	i Pr	H	H	i Pr	H	H
L_{A513}		H	i Pr	Ph	H	H	H	H
L_{A514}		H	i Pr	H	Ph	H	H	H
L_{A515}		H	i Pr	H	H	Ph	H	H
L_{A516}		H	Ph	Me	H	H	H	H
L_{A517}		H	Ph	H	Me	H	H	H
L_{A518}		H	Ph	H	H	Me	H	H
L_{A519}		H	Ph	CD_3	H	H	H	H
L_{A520}		H	Ph	H	CD_3	H	H	H
L_{A521}		H	Ph	H	H	CD_3	H	H
L_{A522}		H	Ph	i Pr	H	H	H	H
L_{A523}		H	Ph	H	i Pr	H	H	H
L_{A524}		H	Ph	H	H	i Pr	H	H
L_{A525}		H	Ph	Ph	H	H	H	H
L_{A526}		H	Ph	H	Ph	H	H	H
L_{A527}		H	Ph	H	H	Ph	H	H
L_{A528}		H	H	Me	Me	H	H	H
L_{A529}		H	H	CD_3	Me	H	H	H
L_{A530}		H	H	i Pr	Me	H	H	H
L_{A531}		H	H	Ph	Me	H	H	H
L_{A532}		H	H	Me	CD_3	H	H	H
L_{A533}		H	H	CD_3	CD_3	H	H	H
L_{A534}		H	H	i Pr	CD_3	H	H	H
L_{A535}		H	H	Ph	CD_3	H	H	H
L_{A536}		H	H	Me	i Pr	H	H	H
L_{A537}		H	H	CD_3	i Pr	H	H	H
L_{A538}		H	H	i Pr	i Pr	H	H	H
L_{A539}		H	H	Ph	i Pr	H	H	H
L_{A540}		H	H	Me	Ph	H	H	H
L_{A541}		H	H	CD_3	Ph	H	H	H
L_{A542}		H	H	i Pr	Ph	H	H	H
L_{A543}		H	H	Ph	Ph	H	H	H
L_{A544}		H	H	Me	H	Me	H	H
L_{A545}		H	H	CD_3	H	Me	H	H
L_{A546}		H	H	i Pr	H	Me	H	H
L_{A547}		H	H	Ph	H	Me	H	H
L_{A548}		H	H	Me	H	CD_3	H	H
L_{A549}		H	H	CD_3	H	CD_3	H	H
L_{A550}		H	H	i Pr	H	CD_3	H	H
L_{A551}		H	H	Ph	H	CD_3	H	H
L_{A552}		H	H	Me	H	i Pr	H	H
L_{A553}		H	H	CD_3	H	i Pr	H	H
L_{A554}		H	H	i Pr	H	i Pr	H	H
L_{A555}		H	H	Ph	H	i Pr	H	H
L_{A556}		H	H	Me	H	Ph	H	H
L_{A557}		H	H	CD_3	H	Ph	H	H
L_{A558}		H	H	i Pr	H	Ph	H	H
L_{A559}		H	H	Ph	H	Ph	H	H
L_{A560}		Me	Me	H	Me	H	H	H
L_{A561}		H	Me	Me	Me	H	H	H
L_{A562}		CD_3	Me	H	Me	H	H	H
L_{A563}		H	Me	CD_3	Me	H	H	H
L_{A564}		i Pr	Me	H	Me	H	H	H
L_{A565}		H	Me	i Pr	Me	H	H	H
L_{A566}		Ph	Me	H	Me	H	H	H
L_{A567}		H	Me	Ph	Me	H	H	H
L_{A568}		Me	CD_3	H	CD_3	H	H	H
L_{A569}		H	CD_3	Me	CD_3	H	H	H
L_{A570}		CD_3	CD_3	H	CD_3	H	H	H
L_{A571}		H	CD_3	CD_3	CD_3	H	H	H
L_{A572}		i Pr	CD_3	H	CD_3	H	H	H
L_{A573}		H	CD_3	i Pr	CD_3	H	H	H
L_{A574}		Ph	CD_3	H	CD_3	H	H	H
L_{A575}		H	CD_3	Ph	CD_3	H	H	H
L_{A576}		Me	i Pr	H	i Pr	H	H	H
L_{A577}		H	i Pr	Me	i Pr	H	H	H
L_{A578}		CD_3	i Pr	H	i Pr	H	H	H
L_{A579}		H	i Pr	CD_3	i Pr	H	H	H
L_{A580}		i Pr	i Pr	H	i Pr	H	H	H
L_{A581}		H	i Pr	i Pr	i Pr	H	H	H
L_{A582}		Ph	i Pr	H	i Pr	H	H	H
L_{A583}		H	i Pr	Ph	i Pr	H	H	H
L_{A584}		Me	Ph	H	Ph	H	H	H



38

-continued


L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_{A585}		H	Ph	Me	Ph	H	H	H
L_{A586}		CD_3	Ph	H	Ph	H	H	H
L_{A587}		H	Ph	CD_3	Ph	H	H	H
L_{A588}		i Pr	Ph	H	Ph	H	H	H
L_{A589}		H	Ph	i Pr	Ph	H	H	H
L_{A590}		Ph	Ph	H	Ph	H	H	H
L_{A591}		H	Ph	Ph	Ph	H	H	H
L_{A592}		H	H	H	H	H	H	H
L_{A593}		Me	H	H	H	H	H	H
L_{A594}		H	Me	H	H	H	H	H
L_{A595}		H	H	Me	H	H	H	H
L_{A596}		H	H	H	Me	H	H	H
L_{A597}		H	H	H	H	Me	H	H
L_{A598}		CD_3	H	H	H	H	H	H
L_{A599}		H	CD_3	H	H	H	H	H
L_{A600}		H	H	CD_3	H	H	H	H
L_{A601}		H	H	H	CD_3	H	H	H
L_{A602}		H	H	H	H	CD_3	H	H
L_{A603}		i Pr	H	H	H	H	H	H
L_{A604}		H	i Pr	H	H	H	H	H
L_{A605}		H	H	i Pr	H	H	H	H
L_{A606}		H	H	H	i Pr	H	H	H
L_{A607}		H	H	H	H	i Pr	H	H
L_{A608}		Ph	H	H	H	H	H	H
L_{A609}		H	Ph	H	H	H	H	H
L_{A610}		H	H	Ph	H	H	H	H
L_{A611}		H	H	H	Ph	H	H	H
L_{A612}		H	H	H	H	Ph	H	H
L_{A613}		Me	Me	H	H	H	H	H
L_{A614}		Me	H	Me	H	H	H	H
L_{A615}		Me	H	H	Me	H	H	H
L_{A616}		Me	H	H	H	Me	H	H
L_{A617}		Me	CD_3	H	H	H	H	H
L_{A618}		Me	H	CD_3	H	H	H	H
L_{A619}		Me	H	H	CD_3	H	H	H
L_{A620}		Me	H	H	H	CD_3	H	H
L_{A621}		Me	i Pr	H	H	H	H	H
L_{A622}		Me	H	i Pr	H	H	H	H
L_{A623}		Me	H	H	i Pr	H	H	H
L_{A624}		Me	H	H	H	i Pr	H	H
L_{A625}		Me	Ph	H	H	H	H	H
L_{A626}		Me	H	Ph	H	H	H	H
L_{A627}		Me	H	H	Ph	H	H	H
L_{A628}		Me	H	H	H	Ph	H	H
L_{A629}		CD_3	Me	H	H	H	H	H
L_{A630}		CD_3	H	Me	H	H	H	H
L_{A631}		CD_3	H	H	Me	H	H	H
L_{A632}		CD_3	H	H	H	Me	H	H
L_{A633}		CD_3	CD_3	H	H	H	H	H
L_{A634}		CD_3	H	CD_3	H	H	H	H
L_{A635}		CD_3	H	H	CD_3	H	H	H
L_{A636}		CD_3	H	H	H	CD_3	H	H
L_{A637}		CD_3	i Pr	H	H	H	H	H
L_{A638}		CD_3	H	i Pr	H	H	H	H
L_{A639}		CD_3	H	H	i Pr	H	H	H
L_{A640}		CD_3	H	H	H	i Pr	H	H
L_{A641}		CD_3	Ph	H	H	H	H	H
L_{A642}		CD_3	H	Ph	H	H	H	H
L_{A643}		CD_3	H	H	Ph	H	H	H
L_{A644}		CD_3	H	H	H	Ph	H	H
L_{A645}		i Pr	Me	H	H	H	H	H
L_{A646}		i Pr	H	Me	H	H	H	H
L_{A647}		i Pr	H	H	Me	H	H	H
L_{A648}		i Pr	H	H	H	Me	H	H
L_{A649}		i Pr	CD_3	H	H	H	H	H
L_{A650}		i Pr	H	CD_3	H	H	H	H
L_{A651}		i Pr	H	H	CD_3	H	H	H
L_{A652}		i Pr	H	H	H	CD_3	H	H
L_{A653}		i Pr	i Pr	H	H	H	H	H
L_{A654}		i Pr	H	i Pr	H	H	H	H
L_{A655}		i Pr	H	H	i Pr	H	H	H
L_{A656}		i Pr	H	H	H	i Pr	H	H
L_{A657}		i Pr	Ph	H	H	H	H	H
L_{A658}		i Pr	H	Ph	H	H	H	H
L_{A659}		i Pr	H	H	Ph	H	H	H
L_{A660}		i Pr	H	H	H	Ph	H	H



39

-continued



L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_{A661}		Ph	Me	H	H	H	H	H
L_{A662}		Ph	H	Me	H	H	H	H
L_{A663}		Ph	H	H	Me	H	H	H
L_{A664}		Ph	H	H	H	Me	H	H
L_{A665}		Ph	CD ₃	H	H	H	H	H
L_{A666}		Ph	H	CD ₃	H	H	H	H
L_{A667}		Ph	H	H	CD ₃	H	H	H
L_{A668}		Ph	H	H	H	CD ₃	H	H
L_{A669}		Ph	ⁱ Pr	H	H	H	H	H
L_{A670}		Ph	H	ⁱ Pr	H	H	H	H
L_{A671}		Ph	H	H	ⁱ Pr	H	H	H
L_{A672}		Ph	H	H	H	ⁱ Pr	H	H
L_{A673}		Ph	Ph	H	H	H	H	H
L_{A674}		Ph	H	Ph	H	H	H	H
L_{A675}		Ph	H	H	Ph	H	H	H
L_{A676}		Ph	H	H	H	Ph	H	H
L_{A677}		H	Me	Me	H	H	H	H
L_{A678}		H	Me	H	Me	H	H	H
L_{A679}		H	Me	H	H	Me	H	H
L_{A680}		H	Me	CD ₃	H	H	H	H
L_{A681}		H	Me	H	CD ₃	H	H	H
L_{A682}		H	Me	H	H	CD ₃	H	H
L_{A683}		H	Me	ⁱ Pr	H	H	H	H
L_{A684}		H	Me	H	ⁱ Pr	H	H	H
L_{A685}		H	Me	H	H	ⁱ Pr	H	H
L_{A686}		H	Me	Ph	H	H	H	H
L_{A687}		H	Me	H	Ph	H	H	H
L_{A688}		H	Me	H	H	Ph	H	H
L_{A689}		H	CD ₃	Me	H	H	H	H
L_{A690}		H	CD ₃	H	Me	H	H	H
L_{A691}		H	CD ₃	H	H	Me	H	H
L_{A692}		H	CD ₃	CD ₃	H	H	H	H
L_{A693}		H	CD ₃	H	CD ₃	H	H	H
L_{A694}		H	CD ₃	H	H	CD ₃	H	H
L_{A695}		H	CD ₃	ⁱ Pr	H	H	H	H
L_{A696}		H	CD ₃	H	ⁱ Pr	H	H	H
L_{A697}		H	CD ₃	H	H	ⁱ Pr	H	H
L_{A698}		H	CD ₃	Ph	H	H	H	H
L_{A699}		H	CD ₃	H	Ph	H	H	H
L_{A700}		H	CD ₃	H	H	Ph	H	H
L_{A701}		H	ⁱ Pr	Me	H	H	H	H
L_{A702}		H	ⁱ Pr	H	Me	H	H	H
L_{A703}		H	ⁱ Pr	H	H	Me	H	H
L_{A704}		H	ⁱ Pr	CD ₃	H	H	H	H
L_{A705}		H	ⁱ Pr	H	CD ₃	H	H	H
L_{A706}		H	ⁱ Pr	H	H	CD ₃	H	H
L_{A707}		H	ⁱ Pr	ⁱ Pr	H	H	H	H
L_{A708}		H	ⁱ Pr	H	ⁱ Pr	H	H	H
L_{A709}		H	ⁱ Pr	H	H	ⁱ Pr	H	H
L_{A710}		H	ⁱ Pr	Ph	H	H	H	H
L_{A711}		H	ⁱ Pr	H	Ph	H	H	H
L_{A712}		H	ⁱ Pr	H	H	Ph	H	H
L_{A713}		H	Ph	Me	H	H	H	H
L_{A714}		H	Ph	H	Me	H	H	H
L_{A715}		H	Ph	H	H	Me	H	H
L_{A716}		H	Ph	CD ₃	H	H	H	H
L_{A717}		H	Ph	H	CD ₃	H	H	H
L_{A718}		H	Ph	H	H	CD ₃	H	H
L_{A719}		H	Ph	ⁱ Pr	H	H	H	H
L_{A720}		H	Ph	H	ⁱ Pr	H	H	H
L_{A721}		H	Ph	H	H	ⁱ Pr	H	H
L_{A722}		H	Ph	Ph	H	H	H	H
L_{A723}		H	Ph	H	Ph	H	H	H
L_{A724}		H	Ph	H	H	Ph	H	H
L_{A725}		H	H	Me	Me	H	H	H
L_{A726}		H	H	CD ₃	Me	H	H	H
L_{A727}		H	H	ⁱ Pr	Me	H	H	H
L_{A728}		H	H	Ph	Me	H	H	H
L_{A729}		H	H	Me	CD ₃	H	H	H
L_{A730}		H	H	CD ₃	CD ₃	H	H	H
L_{A731}		H	H	ⁱ Pr	CD ₃	H	H	H
L_{A732}		H	H	Ph	CD ₃	H	H	H
L_{A733}		H	H	Me	ⁱ Pr	H	H	H
L_{A734}		H	H	CD ₃	ⁱ Pr	H	H	H
L_{A735}		H	H	H	ⁱ Pr	ⁱ Pr	H	H
L_{A736}		H	H	Ph	ⁱ Pr	H	H	H
L_{A737}		H	H	Me	Ph	H	H	H



40

-continued

L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_{A738}		H	H	CD ₃	Ph	H	H	H
L_{A739}		H	H	ⁱ Pr	Ph	H	H	H
L_{A740}		H	H	Ph	Ph	H	H	H
L_{A741}		H	H	Me	H	Me	H	H
L_{A742}		H	H	CD ₃	H	Me	H	H
L_{A743}		H	H	ⁱ Pr	H	Me	H	H
L_{A744}		H	H	Ph	H	Me	H	H
L_{A745}		H	H	Me	H	CD ₃	H	H
L_{A746}		H	H	CD ₃	H	CD ₃	H	H
L_{A747}		H	H	ⁱ Pr	H	CD ₃	H	H
L_{A748}		H	H	Ph	H	CD ₃	H	H
L_{A749}		H	H	Me	H	ⁱ Pr	H	H
L_{A750}		H	H	CD ₃	H	Pr	H	H
L_{A751}		H	H	ⁱ Pr	H	ⁱ Pr	H	H
L_{A752}		H	H	Ph	H	ⁱ Pr	H	H
L_{A753}		H	H	Me	H	Ph	H	H
L_{A754}		H	H	CD ₃	H	Ph	H	H
L_{A755}		H	H	ⁱ Pr	H	Ph	H	H
L_{A756}		H	H	Ph	H	Ph	H	H
L_{A757}		Me	Me	H	Me	H	H	H
L_{A758}		H	Me	Me	Me	H	H	H
L_{A759}		CD ₃	Me	H	Me	H	H	H
L_{A760}		H	Me	CD ₃	Me	H	H	H
L_{A761}		ⁱ Pr	Me	H	Me	H	H	H
L_{A762}		H	Me	ⁱ Pr	Me	H	H	H
L_{A763}		Ph	Me	H	Me	H	H	H
L_{A764}		H	Me	Ph	Me	H	H	H
L_{A765}		Me	CD ₃	H	CD ₃	H	H	H
L_{A766}		H	CD ₃	Me	CD ₃	H	H	H
L_{A767}		CD ₃	CD ₃	H	CD ₃	H	H	H
L_{A768}		H	CD ₃	CD ₃	CD ₃	H	H	H
L_{A769}		ⁱ Pr	CD ₃	H	CD ₃	H	H	H
L_{A770}		H	CD ₃	ⁱ Pr	CD ₃	H	H	H
L_{A771}		Ph	CD ₃	H	CD ₃	H	H	H
L_{A772}		H	CD ₃	Ph	CD ₃	H	H	H
L_{A773}		Me	ⁱ Pr	H	ⁱ Pr	H	H	H
L_{A774}		H	ⁱ Pr	Me	ⁱ Pr	H	H	H
L_{A775}		CD ₃	ⁱ Pr	H	ⁱ Pr	H	H	H
L_{A776}		H	ⁱ Pr	CD ₃	ⁱ Pr	H	H	H
L_{A777}		ⁱ Pr	ⁱ Pr	H	ⁱ Pr	H	H	H
L_{A778}		H	ⁱ Pr	iPr	ⁱ Pr	H	H	H
L_{A779}		Ph	ⁱ Pr	H	ⁱ Pr	H	H	H
L_{A780}		H	ⁱ Pr	Ph	ⁱ Pr	H	H	H
L_{A781}		Me	Ph	H	Ph	H	H	H
L_{A782}		H	Ph	Me	Ph	H	H	H
L_{A783}		CD ₃	Ph	H	Ph	H	H	H
L_{A784}		H	Ph	CD ₃	Ph	H	H	H
L_{A785}		ⁱ Pr	Ph	H	Ph	H	H	H
L_{A786}		H	Ph	ⁱ Pr	Ph	H	H	H
L_{A787}		Ph	Ph	H	Ph	H	H	H
L_{A788}		H	Ph	Ph	Ph	H	H	H
L_{A789}		H	H	H	H	H	H	H
L_{A790}		Me	H	H	H	H	H	H
L_{A791}		H	Me	H	H	H	H	H
L_{A792}		H	H	Me	H	H	H	H
L_{A793}		H	H	H	Me	H	H	H
L_{A794}		H	H	H	H	Me	H	H
L_{A795}		CD ₃	H	H	H	H	H	H
L_{A796}		H	CD ₃	H	H	H	H	H
L_{A797}		H	H	CD ₃	H	H	H	H
L_{A798}		H	H	H	CD ₃	H	H	H
L_{A799}		H	H	H	H	CD ₃	H	H
L_{A800}		ⁱ Pr	H	H	H	H	H	H
L_{A801}		H	ⁱ Pr	H	H	H	H	H
L_{A802}		H	H	ⁱ Pr	H	H	H	H
L_{A803}		H	H	H	ⁱ Pr	H	H	H
L_{A804}		H	H	H	H	ⁱ Pr	H	H
L_{A805}		Ph	H	H	H	H	H	H
L_{A806}		H	Ph	H	H	H	H	H
L_{A807}		H	H	Ph	H	H	H	H
L_{A808}		H	H	H	Ph	H	H	H
L_{A809}		H	H	H	H	Ph	H	H
L_{A810}		Me	Me	H	H	H	H	H
L_{A811}		Me	H	Me	H	H	H	H
L_{A812}		Me	H	H	Me	H	H	H
L_{A813}		Me	H	H	H	Me	H	H



41

-continued

L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_{A814}		Me	CD ₃	H	H	H	H	H
L_{A815}		Me	H	CD ₃	H	H	H	H
L_{A816}		Me	H	H	CD ₃	H	H	H
L_{A817}		Me	H	H	H	CD ₃	H	H
L_{A818}		Me	^t Pr	H	H	H	H	H
L_{A819}		Me	H	^t Pr	H	H	H	H
L_{A820}		Me	H	H	^t Pr	H	H	H
L_{A821}		Me	H	H	H	^t Pr	H	H
L_{A822}		Me	Ph	H	H	H	H	H
L_{A823}		Me	H	Ph	H	H	H	H
L_{A824}	Me	H	H	Ph	H	H	H	
L_{A825}	Me	H	H	H	Ph	H	H	
L_{A826}	CD ₃	Me	H	H	H	H	H	
L_{A827}	CD ₃	H	Me	H	H	H	H	
L_{A828}	CD ₃	H	H	Me	H	H	H	
L_{A829}	CD ₃	H	H	H	Me	H	H	
L_{A830}	CD ₃	CD ₃	H	H	H	H	H	
L_{A831}	CD ₃	H	CD ₃	H	H	H	H	
L_{A832}	CD ₃	H	H	CD ₃	H	H	H	
L_{A833}	CD ₃	H	H	H	CD ₃	H	H	
L_{A834}	CD ₃	ⁱ Pr	H	H	H	H	H	
L_{A835}	CD ₃	H	^t Pr	H	H	H	H	
L_{A836}	CD ₃	H	H	^t Pr	H	H	H	
L_{A837}	CD ₃	H	H	H	^t Pr	H	H	
L_{A838}	CD ₃	Ph	H	H	H	H	H	
L_{A839}	CD ₃	H	Ph	H	H	H	H	
L_{A840}	CD ₃	H	H	Ph	H	H	H	
L_{A841}	CD ₃	H	H	H	Ph	H	H	
L_{A842}	^t Pr	Me	H	H	H	H	H	
L_{A843}	^t Pr	H	Me	H	H	H	H	
L_{A844}	^t Pr	H	H	Me	H	H	H	
L_{A845}	^t Pr	H	H	H	Me	H	H	
L_{A846}	^t Pr	CD ₃	H	H	H	H	H	
L_{A847}	^t Pr	H	CD ₃	H	H	H	H	
L_{A848}	^t Pr	H	H	CD ₃	H	H	H	
L_{A849}	^t Pr	H	H	H	CD ₃	H	H	
L_{A850}	^t Pr	^t Pr	H	H	H	H	H	
L_{A851}	^t Pr	H	^t Pr	H	H	H	H	
L_{A852}	^t Pr	H	H	^t Pr	H	H	H	
L_{A853}	^t Pr	H	H	H	^t Pr	H	H	
L_{A854}	^t Pr	Ph	H	H	H	H	H	
L_{A855}	^t Pr	H	Ph	H	H	H	H	
L_{A856}	^t Pr	H	H	Ph	H	H	H	
L_{A857}	^t Pr	H	H	H	Ph	H	H	
L_{A858}	Ph	Me	H	H	H	H	H	
L_{A859}	Ph	H	Me	H	H	H	H	
L_{A860}	Ph	H	H	Me	H	H	H	
L_{A861}	Ph	H	H	H	Me	H	H	
L_{A862}	Ph	CD ₃	H	H	H	H	H	
L_{A863}	Ph	H	CD ₃	H	H	H	H	
L_{A864}	Ph	H	H	CD ₃	H	H	H	
L_{A865}	Ph	H	H	H	CD ₃	H	H	
L_{A866}	Ph	^t Pr	H	H	H	H	H	
L_{A867}	Ph	H	^t Pr	H	H	H	H	
L_{A868}	Ph	H	H	^t Pr	H	H	H	
L_{A869}	Ph	H	H	H	^t Pr	H	H	
L_{A870}	Ph	Ph	H	H	H	H	H	
L_{A871}	Ph	H	Ph	H	H	H	H	
L_{A872}	Ph	H	H	Ph	H	H	H	
L_{A873}	Ph	H	H	H	Ph	H	H	
L_{A874}	H	Me	Me	H	H	H	H	
L_{A875}	H	Me	H	Me	H	H	H	
L_{A876}	H	Me	H	H	Me	H	H	
L_{A877}	H	Me	CD ₃	H	H	H	H	
L_{A878}	H	Me	H	CD ₃	H	H	H	
L_{A879}	H	Me	H	H	CD ₃	H	H	
L_{A880}	H	Me	^t Pr	H	H	H	H	
L_{A881}	H	Me	H	^t Pr	H	H	H	
L_{A882}	H	Me	H	H	^t Pr	H	H	
L_{A883}	H	Me	Ph	H	H	H	H	
L_{A884}	H	Me	H	Ph	H	H	H	
L_{A885}	H	Me	H	H	Ph	H	H	
L_{A886}	H	CD ₃	Me	H	H	H	H	
L_{A887}	H	CD ₃	H	Me	H	H	H	
L_{A888}	H	CD ₃	H	H	Me	H	H	
L_{A889}	H	CD ₃	CD ₃	H	H	H	H	

42



-continued

L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_{A890}		H	CD ₃	H	CD ₃	H	H	H
L_{A891}		H	CD ₃	H	H	CD ₃	H	H
L_{A892}		H	CD ₃	^t Pr	H	H	H	H
L_{A893}		H	CD ₃	H	^t Pr	H	H	H
L_{A894}		H	CD ₃	H	H	^t Pr	H	H
L_{A895}		H	CD ₃	Ph	H	H	H	H
L_{A896}		H	CD ₃	H	Ph	H	H	H
L_{A897}		H	CD ₃	H	H	Ph	H	H
L_{A898}		H	^t Pr	Me	H	H	H	H
L_{A899}		H	^t Pr	H	Me	H	H	H
L_{A900}	H	^t Pr	H	H	Me	H	H	
L_{A901}	H	^t Pr	CD ₃	H	H	H	H	
L_{A902}	H	^t Pr	H	CD ₃	H	H	H	
L_{A903}	H	^t Pr	H	H	H	CD ₃	H	
L_{A904}	H	^t Pr	^t Pr	H	H	H	H	
L_{A905}	H	^t Pr	H	^t Pr	H	H	H	
L_{A906}	H	^t Pr	H	H	^t Pr	H	H	
L_{A907}	H	^t Pr	Ph	H	H	H	H	
L_{A908}	H	^t Pr	H	Ph	H	H	H	
L_{A909}	H	^t Pr	H	H	Ph	H	H	
L_{A910}	H	Ph	Me	H	H	H	H	
L_{A911}	H	Ph	H	Me	H	H	H	
L_{A912}	H	Ph	H	H	Me	H	H	
L_{A913}	H	Ph	CD ₃	H	H	H	H	
L_{A914}	H	Ph	H	CD ₃	H	H	H	
L_{A915}	H	Ph	H	H	CD ₃	H	H	
L_{A916}	H	Ph	^t Pr	H	H	H	H	
L_{A917}	H	Ph	H	^t Pr	H	H	H	
L_{A918}	H	Ph	H	H	^t Pr	H	H	
L_{A919}	H	Ph	Ph	H	H	H	H	
L_{A920}	H	Ph	H	Ph	H	H	H	
L_{A921}	H	Ph	H	H	Ph	H	H	
L_{A922}	H	H	Me	Me	H	H	H	
L_{A923}	H	H	CD ₃	Me	H	H	H	
L_{A924}	H	H	H	^t Pr	Me	H	H	
L_{A925}	H	H	Ph	Me	H	H	H	
L_{A926}	H	H	Me	CD ₃	H	H	H	
L_{A927}	H	H	CD ₃	CD ₃	H	H	H	
L_{A928}	H	H	^t Pr	CD ₃	H	H	H	
L_{A929}	H	H	Ph	CD ₃	H	H	H	
L_{A930}	H	H	Me	^t Pr	H	H	H	
L_{A931}	H	H	CD ₃	^t Pr	H	H	H	
L_{A932}	H	H	^t Pr	^t Pr	H	H	H	
L_{A933}	H	H	Ph	^t Pr	H	H	H	
L_{A934}	H	H	Me	Ph	H	H	H	
L_{A935}	H	H	CD ₃	Ph	H	H	H	
L_{A936}	H	H	^t Pr	Ph	H	H	H	
L_{A937}	H	H	Ph	Ph	H	H	H	
L_{A938}	H	H	Me	H	Me	H	H	
L_{A939}	H	H	CD ₃	H	Me	H	H	
L_{A940}	H	H	^t Pr	H	Me	H	H	
L_{A941}	H	H	Ph	H	Me	H	H	
L_{A942}	H	H	Me	H	CD ₃	H	H	
L_{A943}	H	H	CD ₃	H	CD ₃	H	H	
L_{A944}	H	H	^t Pr	H	CD ₃	H	H	
L_{A945}	H	H	Ph	H	CD ₃	H	H	
L_{A946}	H	H	Me	H	^t Pr	H	H	
L_{A947}	H	H	CD ₃	H	^t Pr	H	H	
L_{A948}	H	H	^t Pr	H	^t Pr	H	H	
L_{A949}	H	H	Ph	H	^t Pr	H	H	
L_{A950}	H	H	Me	H	Ph	H	H	
L_{A951}	H	H	CD ₃	H	Ph	H	H	
L_{A952}	H	H	^t Pr	H	Ph	H	H	
L_{A953}	H	H	Ph	H	Ph	H	H	
L_{A954}	Me	Me	H	Me	H	H	H	
L_{A955}	H	Me	Me	Me	H	H	H	
L_{A956}	CD ₃	Me	H	Me	H	H	H	
L_{A957}	H	Me	CD ₃	Me	H	H	H	
L_{A958}	^t Pr	Me	H	Me	H	H	H	
L_{A959}	H	Me	^t Pr	Me	H	H	H	
L_{A960}	Ph	Me	H	Me	H	H	H	
L_{A961}	H	Me	Ph	Me	H	H	H	
L_{A962}	Me	CD ₃	H	CD ₃	H	H	H	
L_{A963}	H	CD ₃	Me	CD ₃	H	H	H	
L_{A964}	CD ₃	CD ₃	H	CD ₃	H	H	H	
L_{A965}	H	CD ₃	CD ₃	CD ₃	H	H	H	
L_{A966}	^t Pr	CD ₃	H	CD ₃	H	H	H	

43

-continued



L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_{A967}		H	CD_3	iPr	CD_3	H	H	H
L_{A968}		Ph	CD_3	H	CD_3	H	H	H
L_{A969}		H	CD_3	Ph	CD_3	H	H	H
L_{A970}		Me	iPr	H	iPr	H	H	H
L_{A971}		H	iPr	Me	iPr	H	H	H
L_{A972}		CD_3	iPr	H	iPr	H	H	H
L_{A973}		H	iPr	CD_3	iPr	H	H	H
L_{A974}		iPr	iPr	H	iPr	H	H	H
L_{A975}		H	iPr	iPr	iPr	H	H	H
L_{A976}		Ph	iPr	H	iPr	H	H	H
L_{A977}		H	iPr	Ph	iPr	H	H	H
L_{A978}		Me	Ph	H	Ph	H	H	H
L_{A979}		H	Ph	Me	Ph	H	H	H
L_{A980}		CD_3	Ph	H	Ph	H	H	H
L_{A981}		H	Ph	CD_3	Ph	H	H	H
L_{A982}		iPr	Ph	H	Ph	H	H	H
L_{A983}		H	Ph	iPr	Ph	H	H	H
L_{A984}		Ph	Ph	H	Ph	H	H	H
L_{A985}		H	Ph	Ph	Ph	H	H	H
L_{A986}		H	H	H	H	H	H	H
L_{A987}		Me	H	H	H	H	H	H
L_{A988}		H	Me	H	H	H	H	H
L_{A989}		H	H	Me	H	H	H	H
L_{A990}		H	H	H	Me	H	H	H
L_{A991}		H	H	H	H	Me	H	H
L_{A992}		CD_3	H	H	H	H	H	H
L_{A993}		H	CD_3	H	H	H	H	H
L_{A994}		H	H	CD_3	H	H	H	H
L_{A995}		H	H	H	CD_3	H	H	H
L_{A996}		H	H	H	H	CD_3	H	H
L_{A997}		iPr	H	H	H	H	H	H
L_{A998}		H	iPr	H	H	H	H	H
L_{A999}		H	H	iPr	H	H	H	H
L_{A1000}		H	H	H	iPr	H	H	H
L_{A1001}		H	H	H	H	iPr	H	H
L_{A1002}		Ph	H	H	H	H	H	H
L_{A1003}		H	Ph	H	H	H	H	H
L_{A1004}		H	H	Ph	H	H	H	H
L_{A1005}		H	H	H	Ph	H	H	H
L_{A1006}		H	H	H	H	Ph	H	H
L_{A1007}		Me	Me	H	H	H	H	H
L_{A1008}		Me	H	Me	H	H	H	H
L_{A1009}		Me	H	H	Me	H	H	H
L_{A1010}		Me	H	H	H	Me	H	H
L_{A1011}		Me	CD_3	H	H	H	H	H
L_{A1012}		Me	H	CD_3	H	H	H	H
L_{A1013}		Me	H	H	CD_3	H	H	H
L_{A1014}		Me	H	H	H	CD_3	H	H
L_{A1015}		Me	iPr	H	H	H	H	H
L_{A1016}		Me	H	iPr	H	H	H	H
L_{A1017}		Me	H	H	iPr	H	H	H
L_{A1018}		Me	H	H	H	iPr	H	H
L_{A1019}		Me	Ph	H	H	H	H	H
L_{A1020}		Me	H	Ph	H	H	H	H
L_{A1021}		Me	H	H	Ph	H	H	H
L_{A1022}		Me	H	H	H	Ph	H	H
L_{A1023}		CD_3	Me	H	H	H	H	H
L_{A1024}		CD_3	H	Me	H	H	H	H
L_{A1025}		CD_3	H	H	Me	H	H	H
L_{A1026}		CD_3	H	H	H	Me	H	H
L_{A1027}		CD_3	CD_3	H	H	H	H	H
L_{A1028}		CD_3	H	CD_3	H	H	H	H
L_{A1029}		CD_3	H	H	CD_3	H	H	H
L_{A1030}		CD_3	H	H	H	CD_3	H	H
L_{A1031}		CD_3	iPr	H	H	H	H	H
L_{A1032}		CD_3	H	iPr	H	H	H	H
L_{A1033}		CD_3	H	H	iPr	H	H	H
L_{A1034}		CD_3	H	H	H	iPr	H	H
L_{A1035}		CD_3	Ph	H	H	H	H	H
L_{A1036}		CD_3	H	Ph	H	H	H	H
L_{A1037}		CD_3	H	H	Ph	H	H	H



44

-continued



L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_{A1038}		CD_3	H	H	H	Ph	H	H
L_{A1039}		iPr	Me	H	H	H	H	H
L_{A1040}		iPr	H	Me	H	H	H	H
L_{A1041}		iPr	H	H	Me	H	H	H
L_{A1042}		iPr	H	H	H	Me	H	H
L_{A1043}		iPr	CD_3	H	H	H	H	H
L_{A1044}		iPr	H	CD_3	H	H	H	H
L_{A1045}		iPr	H	H	CD_3	H	H	H
L_{A1046}		iPr	H	H	H	CD_3	H	H
L_{A1047}		iPr	iPr	H	H	H	H	H
L_{A1048}		iPr	H	iPr	H	H	H	H
L_{A1049}		iPr	H	H	iPr	H	H	H
L_{A1050}		iPr	H	H	H	iPr	H	H
L_{A1051}		iPr	Ph	H	H	H	H	H
L_{A1052}		iPr	H	Ph	H	H	H	H
L_{A1053}		iPr	H	H	Ph	H	H	H
L_{A1054}		iPr	H	H	H	Ph	H	H
L_{A1055}		Ph	Me	H	H	H	H	H
L_{A1056}		Ph	H	Me	H	H	H	H
L_{A1057}		Ph	H	H	Me	H	H	H
L_{A1058}		Ph	H	H	H	Me	H	H
L_{A1059}		Ph	CD_3	H	H	H	H	H
L_{A1060}		Ph	H	CD_3	H	H	H	H
L_{A1061}		Ph	H	H	CD_3	H	H	H
L_{A1062}		Ph	H	H	H	CD_3	H	H
L_{A1063}		Ph	iPr	H	H	H	H	H
L_{A1064}		Ph	H	iPr	H	H	H	H
L_{A1065}		Ph	H	H	iPr	H	H	H
L_{A1066}		Ph	H	H	H	iPr	H	H
L_{A1067}		Ph	Ph	H	H	H	H	H
L_{A1068}		Ph	H	Ph	H	H	H	H
L_{A1069}		Ph	H	H	Ph	H	H	H
L_{A1070}		Ph	H	H	H	Ph	H	H
L_{A1071}		H	Me	Me	H	H	H	H
L_{A1072}		H	Me	H	Me	H	H	H
L_{A1073}		H	Me	H	H	Me	H	H
L_{A1074}		H	Me	CD_3	H	H	H	H
L_{A1075}		H	Me	H	CD_3	H	H	H
L_{A1076}		H	Me	H	H	CD_3	H	H
L_{A1077}		H	Me	iPr	H	H	H	H
L_{A1078}		H	Me	H	iPr	H	H	H
L_{A1079}		H	Me	H	H	iPr	H	H
L_{A1080}		H	Me	Ph	H	H	H	H
L_{A1081}		H	Me	H	Ph	H	H	H
L_{A1082}		H	Me	H	H	Ph	H	H
L_{A1083}		H	CD_3	Me	H	H	H	H
L_{A1084}		H	CD_3	H	Me	H	H	H
L_{A1085}		H	CD_3	H	H	Me	H	H
L_{A1086}		H	CD_3	CD_3	H	H	H	H
L_{A1087}		H	CD_3	H	CD_3	H	H	H
L_{A1088}		H	CD_3	H	H	CD_3	H	H
L_{A1089}		H	CD_3	iPr	H	H	H	H
L_{A1090}		H	CD_3	H	iPr	H	H	H
L_{A1091}		H	CD_3	H	H	iPr	H	H
L_{A1092}		H	CD_3	Ph	H	H	H	H
L_{A1093}		H	CD_3	H	Ph	H	H	H
L_{A1094}		H	CD_3	H	H	Ph	H	H
L_{A1095}		H	iPr	Me	H	H	H	H
L_{A1096}		H	iPr	H	Me	H	H	H
L_{A1097}		H	iPr	H	H	Me	H	H
L_{A1098}		H	iPr	CD_3	H	H	H	H
L_{A1099}		H	iPr	H	CD_3	H	H	H
L_{A1100}		H	iPr	H	H	CD_3	H	H
L_{A1101}		H	iPr	iPr	H	H	H	H
L_{A1102}		H	iPr	H	iPr	H	H	H
L_{A1103}		H	iPr	H	H	iPr	H	H
L_{A1104}		H	iPr	Ph	H	H	H	H
L_{A1105}		H	iPr	H	Ph	H	H	H
L_{A1106}		H	iPr	H	H	Ph	H	H
L_{A1107}		H	Ph	Me	H	H	H	H
L_{A1108}		H	Ph	H	Me	H	H	H
L_{A1109}		H	Ph	H	H	Me	H	H
L_{A1110}		H	Ph	CD_3	H	H	H	H
L_{A1111}		H	Ph	H	CD_3	H	H	H
L_{A1112}		H	Ph	H	H	CD_3	H	H
L_{A1113}		H	Ph	iPr	H	H	H	H
L_{A1114}		H	Ph	H	H	iPr	H	H
L_{A1115}		H	Ph	H	H	iPr	H	H



45

-continued



L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_A 1116		H	Ph	Ph	H	H	H	H
L_A 1117		H	Ph	H	Ph	H	H	H
L_A 1118		H	Ph	H	H	Ph	H	H
L_A 1119		H	H	Me	Me	H	H	H
L_A 1120		H	H	CD ₃	Me	H	H	H
L_A 1121		H	H	^t Pr	Me	H	H	H
L_A 1122		H	H	Ph	Me	H	H	H
L_A 1123		H	H	Me	CD ₃	H	H	H
L_A 1124		H	H	CD ₃	CD ₃	H	H	H
L_A 1125		H	H	^t Pr	CD ₃	H	H	H
L_A 1126		H	H	Ph	CD ₃	H	H	H
L_A 1127		H	H	Me	^t Pr	H	H	H
L_A 1128		H	H	CD ₃	^t Pr	H	H	H
L_A 1129		H	H	^t Pr	^t Pr	H	H	H
L_A 1130		H	H	Ph	^t Pr	H	H	H
L_A 1131		H	H	Me	Ph	H	H	H
L_A 1132		H	H	CD ₃	Ph	H	H	H
L_A 1133		H	H	^t Pr	Ph	H	H	H
L_A 1134		H	H	Ph	Ph	H	H	H
L_A 1135		H	H	Me	H	Me	H	H
L_A 1136		H	H	CD ₃	H	Me	H	H
L_A 1137		H	H	^t Pr	H	Me	H	H
L_A 1138		H	H	Ph	H	Me	H	H
L_A 1139		H	H	Me	H	CD ₃	H	H
L_A 1140		H	H	CD ₃	H	CD ₃	H	H
L_A 1141		H	H	^t Pr	H	CD ₃	H	H
L_A 1142		H	H	Ph	H	CD ₃	H	H
L_A 1143		H	H	Me	H	^t Pr	H	H
L_A 1144		H	H	CD ₃	H	^t Pr	H	H
L_A 1145		H	H	^t Pr	H	^t Pr	H	H
L_A 1146		H	H	Ph	H	^t Pr	H	H
L_A 1147		H	H	Me	H	Ph	H	H
L_A 1148		H	H	CD ₃	H	Ph	H	H
L_A 1149		H	H	^t Pr	H	Ph	H	H
L_A 1150		H	H	Ph	H	Ph	H	H
L_A 1151		Me	Me	H	Me	H	H	H
L_A 1152		H	Me	Me	Me	H	H	H
L_A 1153		CD ₃	Me	H	Me	H	H	H
L_A 1154		H	Me	CD ₃	Me	H	H	H
L_A 1155		^t Pr	Me	H	Me	H	H	H
L_A 1156		H	Me	^t Pr	Me	H	H	H
L_A 1157		Ph	Me	H	Me	H	H	H
L_A 1158		H	Me	Ph	Me	H	H	H
L_A 1159		Me	CD ₃	H	CD ₃	H	H	H
L_A 1160		H	CD ₃	Me	CD ₃	H	H	H
L_A 1161		CD ₃	CD ₃	H	CD ₃	H	H	H
L_A 1162		H	CD ₃	CD ₃	H	H	H	H
L_A 1163		^t Pr	CD ₃	H	CD ₃	H	H	H
L_A 1164		H	CD ₃	iPr	CD ₃	H	H	H
L_A 1165		Ph	CD ₃	H	CD ₃	H	H	H
L_A 1166		H	CD ₃	Ph	CD ₃	H	H	H
L_A 1167		Me	^t Pr	H	^t Pr	H	H	H
L_A 1168		H	^t Pr	Me	^t Pr	H	H	H
L_A 1169		CD ₃	^t Pr	H	^t Pr	H	H	H
L_A 1170		H	^t Pr	CD ₃	^t Pr	H	H	H
L_A 1171		^t Pr	^t Pr	H	^t Pr	H	H	H
L_A 1172		H	^t Pr	iPr	^t Pr	H	H	H
L_A 1173		Ph	^t Pr	H	^t Pr	H	H	H
L_A 1174		H	^t Pr	Ph	^t Pr	H	H	H
L_A 1175		Me	Ph	H	Ph	H	H	H
L_A 1176		H	Ph	Me	Ph	H	H	H
L_A 1177		CD ₃	Ph	H	Ph	H	H	H
L_A 1178		H	Ph	CD ₃	Ph	H	H	H
L_A 1179		^t Pr	Ph	H	Ph	H	H	H
L_A 1180		H	Ph	^t Pr	Ph	H	H	H
L_A 1181		Ph	Ph	H	Ph	H	H	H
L_A 1182		H	Ph	Ph	Ph	H	H	H
L_A 1183		H	H	H	H	H	H	H
L_A 1184		Me	H	H	H	H	H	H
L_A 1185		H	Me	H	H	H	H	H
L_A 1186		H	H	Me	H	H	H	H
L_A 1187		H	H	H	Me	H	H	H
L_A 1188		CD ₃	H	H	H	H	H	H
L_A 1189		H	CD ₃	H	H	H	H	H
L_A 1190		H	H	CD ₃	H	H	H	H
L_A 1191		H	H	H	CD ₃	H	H	H
L_A 1192		H	H	H	H	CD ₃	H	H
L_A 1193		H	H	H	H	CD ₃	H	H



46


-continued

L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_A 1194		^t Pr	H	H	H	H	H	H
L_A 1195		H	^t Pr	H	H	H	H	H
L_A 1196		H	H	^t Pr	H	H	H	H
L_A 1197		H	H	H	^t Pr	H	H	H
L_A 1198		H	H	H	H	^t Pr	H	H
L_A 1199		Ph	H	H	H	H	H	H
L_A 1200		H	Ph	H	H	H	H	H
L_A 1201		H	H	Ph	H	H	H	H
L_A 1202		H	H	H	Ph	H	H	H
L_A 1203		H	H	H	H	Ph	H	H
L_A 1204		Me	Me	H	H	H	H	H
L_A 1205		Me	H	Me	H	H	H	H
L_A 1206		Me	H	H	Me	H	H	H
L_A 1207		Me	H	H	H	Me	H	H
L_A 1208		Me	CD ₃	H	H	H	H	H
L_A 1209		Me	H	CD ₃	H	H	H	H
L_A 1210		Me	H	H	CD ₃	H	H	H
L_A 1211		Me	H	H	H	CD ₃	H	H
L_A 1212		Me	^t Pr	H	H	H	H	H
L_A 1213		Me	H	^t Pr	H	H	H	H
L_A 1214		Me	H	H	^t Pr	H	H	H
L_A 1215		Me	H	H	H	^t Pr	H	H
L_A 1216		Me	Ph	H	H	H	H	H
L_A 1217		Me	H	Ph	H	H	H	H
L_A 1218		Me	H	H	Ph	H	H	H
L_A 1219		Me	H	H	H	Ph	H	H
L_A 1220		CD ₃	Me	H	H	H	H	H
L_A 1221		CD ₃	H	Me	H	H	H	H
L_A 1222		CD ₃	H	H	Me	H	H	H
L_A 1223		CD ₃	H	H	H	Me	H	H
L_A 1224		CD ₃	CD ₃	H	H	H	H	H
L_A 1225		CD ₃	H	CD ₃	H	H	H	H
L_A 1226		CD ₃	H	H	CD ₃	H	H	H
L_A 1227		CD ₃	H	H	H	CD ₃	H	H
L_A 1228		CD ₃	^t Pr	H	H	H	H	H
L_A 1229		CD ₃	H	^t Pr	H	H	H	H
L_A 1230		CD ₃	H	H	^t Pr	H	H	H
L_A 1231		CD ₃	H	H	H	^t Pr	H	H
L_A 1232		CD ₃	Ph	H	H	H	H	H
L_A 1233		CD ₃	H	Ph	H	H	H	H
L_A 1234		CD ₃	H	H	Ph	H	H	H
L_A 1235		CD ₃	H	H	H	Ph	H	H
L_A 1236		^t Pr	Me	H	H	H	H	H
L_A 1237		^t Pr	H	Me	H	H	H	H
L_A 1238		^t Pr	H	H	Me	H	H	H
L_A 1239		^t Pr	H	H	H	Me	H	H
L_A 1240		^t Pr	CD ₃	H	H	H	H	H
L_A 1241		^t Pr	H	CD ₃	H	H	H	H
L_A 1242		^t Pr	H	H	CD ₃	H	H	H
L_A 1243		^t Pr	H	H	H	CD ₃	H	H
L_A 1244		^t Pr	^t Pr	H	H	H	H	H
L_A 1245		^t Pr	H	^t Pr	H	H	H	H
L_A 1246		^t Pr	H	H	^t Pr	H	H	H
L_A 1247		^t Pr	H	H	H	^t Pr	H	H
L_A 1248		^t Pr	Ph	H	H	H	H	H
L_A 1249		^t Pr	H	Ph	H	H	H	H
L_A 1250		^t Pr	H	H	Ph	H	H	H
L_A 1251		^t Pr	H	H	H	Ph	H	H
L_A 1252		Ph	Me	H	H	H	H	H
L_A 1253		Ph	H	Me	H	H	H	H
L_A 1254		Ph	H	H	Me	H	H	H
L_A 1255		Ph	H	H	H	Me	H	H
L_A 1256		Ph	CD ₃	H	H	H	H	H
L_A 1257		Ph	H	CD ₃	H	H	H	H
L_A 1258		Ph	H	H	CD ₃	H	H	H
L_A 1259		Ph	H	H	H	CD ₃	H	H
L_A 1260		Ph	H	^t Pr	H	H	H	H
L_A 1261		Ph	H	H	^t Pr	H	H	H
L_A 1262		Ph	H	H	H	^t Pr	H	H
L_A 1263		Ph	H	H	H	H	^t Pr	H
L_A 1264		Ph	Ph	H	H	H	H	H
L_A 1265		Ph	H	Ph	H	H	H	H
L_A 1266		Ph	H	H	Ph	H	H	H
L_A 1267		Ph	H	H	H	Ph	H	H
L_A 1268		H	Me	Me	H	H	H	H
L_A 1269		H	Me	H	Me	H	H	H
L_A 1270		H	Me	H	H	Me	H	H
L_A 1271		H	Me	CD ₃	H	H	H	H





-continued

L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_A1272		H	Me	H	CD_3	H	H	H
L_A1273		H	Me	H	CD_3	H	H	H
L_A1274		H	Me	iPr	H	H	H	H
L_A1275		H	Me	H	iPr	H	H	H
L_A1276		H	Me	H	H	iPr	H	H
L_A1277		H	Me	Ph	H	H	H	H
L_A1278		H	Me	H	Ph	H	H	H
L_A1279		H	Me	H	H	Ph	H	H
L_A1280		H	CD_3	Me	H	H	H	H
L_A1281		H	CD_3	H	Me	H	H	H
L_A1282		H	CD_3	H	H	Me	H	H
L_A1283		H	CD_3	CD_3	H	H	H	H
L_A1284		H	CD_3	H	CD_3	H	H	H
L_A1285		H	CD_3	H	H	CD_3	H	H
L_A1286		H	CD_3	iPr	H	H	H	H
L_A1287		H	CD_3	H	iPr	H	H	H
L_A1288		H	CD_3	H	H	iPr	H	H
L_A1289		H	CD_3	Ph	H	H	H	H
L_A1290		H	CD_3	H	Ph	H	H	H
L_A1291		H	CD_3	H	H	Ph	H	H
L_A1292		H	iPr	Me	H	H	H	H
L_A1293		H	iPr	H	Me	H	H	H
L_A1294		H	iPr	H	H	Me	H	H
L_A1295		H	iPr	CD_3	H	H	H	H
L_A1296		H	iPr	H	CD_3	H	H	H
L_A1297		H	iPr	H	H	CD_3	H	H
L_A1298		H	iPr	iPr	H	H	H	H
L_A1299		H	iPr	H	iPr	H	H	H
L_A1300		H	iPr	H	H	iPr	H	H
L_A1301		H	iPr	Ph	H	H	H	H
L_A1302		H	iPr	H	Ph	H	H	H
L_A1303		H	iPr	H	H	Ph	H	H
L_A1304		H	Ph	Me	H	H	H	H
L_A1305		H	Ph	H	Me	H	H	H
L_A1306		H	Ph	H	H	Me	H	H
L_A1307		H	Ph	CD_3	H	H	H	H
L_A1308		H	Ph	H	CD_3	H	H	H
L_A1309		H	Ph	H	H	CD_3	H	H
L_A1310		H	Ph	iPr	H	H	H	H
L_A1311		H	Ph	H	iPr	H	H	H
L_A1312		H	Ph	H	H	iPr	H	H
L_A1313		H	Ph	Ph	H	H	H	H
L_A1314		H	Ph	H	Ph	H	H	H
L_A1315		H	Ph	H	H	Ph	H	H
L_A1316		H	H	Me	Me	H	H	H
L_A1317		H	H	CD_3	Me	H	H	H
L_A1318		H	H	iPr	Me	H	H	H
L_A1319		H	H	Ph	Me	H	H	H
L_A1320		H	H	Me	CD_3	H	H	H
L_A1321		H	H	CD_3	CD_3	H	H	H
L_A1322		H	H	iPr	CD_3	H	H	H
L_A1323		H	H	Ph	CD_3	H	H	H
L_A1324		H	H	Me	iPr	H	H	H
L_A1325		H	H	CD_3	iPr	H	H	H
L_A1326		H	H	iPr	iPr	H	H	H
L_A1327		H	H	Ph	iPr	H	H	H
L_A1328		H	H	Me	Ph	H	H	H
L_A1329		H	H	CD_3	Ph	H	H	H
L_A1330		H	H	iPr	Ph	H	H	H
L_A1331		H	H	Ph	Ph	H	H	H
L_A1332		H	H	Me	H	Me	H	H
L_A1333		H	H	CD_3	H	Me	H	H
L_A1334		H	H	iPr	H	Me	H	H
L_A1335		H	H	Ph	H	Me	H	H
L_A1336		H	H	Me	H	CD_3	H	H
L_A1337		H	H	CD_3	H	CD_3	H	H
L_A1338		H	H	iPr	H	CD_3	H	H
L_A1339		H	H	Ph	H	CD_3	H	H
L_A1340		H	H	Me	H	iPr	H	H
L_A1341		H	H	CD_3	H	iPr	H	H
L_A1342		H	H	iPr	H	H	H	H
L_A1343		H	H	Ph	H	iPr	H	H
L_A1344		H	H	Me	H	Ph	H	H
L_A1345		H	H	CD_3	H	Ph	H	H
L_A1346		H	H	iPr	H	Ph	H	H
L_A1347		H	H	Ph	H	Ph	H	H
L_A1348		Me	Me	H	Me	H	H	H
L_A1349		H	Me	Me	Me	H	H	H




-continued


L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_A1350		CD_3	Me	H	Me	H	H	H
L_A1351		H	Me	CD_3	Me	H	H	H
L_A1352		iPr	Me	H	Me	H	H	H
L_A1353		H	Me	iPr	Me	H	H	H
L_A1354		Ph	Me	H	Me	H	H	H
L_A1355		H	Me	Ph	Me	H	H	H
L_A1356		Me	CD_3	H	CD_3	H	H	H
L_A1357		H	CD_3	Me	CD_3	H	H	H
L_A1358		CD_3	CD_3	H	CD_3	H	H	H
L_A1359		H	CD_3	CD_3	CD_3	H	H	H
L_A1360		iPr	CD_3	H	CD_3	H	H	H
L_A1361		H	CD_3	iPr	CD_3	H	H	H
L_A1362		Ph	CD_3	H	CD_3	H	H	H
L_A1363		H	CD_3	Ph	CD_3	H	H	H
L_A1364		Me	iPr	H	iPr	H	H	H
L_A1365		H	iPr	Me	iPr	H	H	H
L_A1366		CD_3	iPr	H	iPr	H	H	H
L_A1367		H	iPr	CD_3	iPr	H	H	H
L_A1368		iPr	iPr	H	iPr	H	H	H
L_A1369		H	iPr	iPr	iPr	H	H	H
L_A1370		Ph	iPr	H	iPr	H	H	H
L_A1371		H	iPr	Ph	iPr	H	H	H
L_A1372		Me	Ph	H	Ph	H	H	H
L_A1373		H	Ph	Me	Ph	H	H	H
L_A1374		CD_3	Ph	H	Ph	H	H	H
L_A1375		H	Ph	CD_3	Ph	H	H	H
L_A1376		iPr	Ph	H	Ph	H	H	H
L_A1377		H	Ph	iPr	Ph	H	H	H
L_A1378		Ph	Ph	H	Ph	H	H	H
L_A1379		H	Ph	Ph	Ph	H	H	H
L_A1380		H	H	H	H	H	H	H
L_A1381		Me	H	H	H	H	H	H
L_A1382		H	Me	H	H	H	H	H
L_A1383		H	H	Me	H	H	H	H
L_A1384		H	H	H	Me	H	H	H
L_A1385		H	H	H	H	Me	H	H
L_A1386		CD_3	H	H	H	H	H	H
L_A1387		H	CD_3	H	H	H	H	H
L_A1388		H	H	CD_3	H	H	H	H
L_A1389		H	H	H	CD_3	H	H	H
L_A1390		H	H	H	H	CD_3	H	H
L_A1391		iPr	H	H	H	H	H	H
L_A1392		H	iPr	H	H	H	H	H
L_A1393		H	H	iPr	H	H	H	H
L_A1394		H	H	H	iPr	H	H	H
L_A1395		H	H	H	H	iPr	H	H
L_A1396		Ph	H	H	H	H	H	H
L_A1397		H	Ph	H	H	H	H	H
L_A1398		H	H	Ph	H	H	H	H
L_A1399		H	H	H	Ph	H	H	H
L_A1400		H	H	H	H	Ph	H	H
L_A1401		Me	Me	H	H	H	H	H
L_A1402		Me	H	Me	H	H	H	H
L_A1403		Me	H	H	Me	H	H	H
L_A1404		Me	H	H	H	Me	H	H
L_A1405		Me	CD_3	H	H	H	H	H
L_A1406		Me	H	CD_3	H	H	H	H
L_A1407		Me	H	H	CD_3	H	H	H
L_A1408		Me	H	H	H	CD_3	H	H
L_A1409		Me	iPr	H	H	H	H	H
L_A1410		Me	H	iPr	H	H	H	H
L_A1411		Me	H	H	iPr	H	H	H
L_A1412		Me	H	H	H	iPr	H	H
L_A1413		Me	Ph	H	H	H	H	H
L_A1414		Me	H	Ph	H	H	H	H
L_A1415		Me	H	H	Ph	H	H	H
L_A1416		Me	H	H	H	Ph	H	H
L_A1417		CD_3	Me	H	H	H	H	H
L_A1418		CD_3	H	Me	H	H	H	H
L_A1419		CD_3	H	H	Me	H	H	H
L_A1420		CD_3	H	H	H	Me	H	H
L_A1421		CD_3	CD_3	H	H	H	H	H
L_A1422		CD_3	H	CD_3	H	H	H	H



49



-continued

L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_A1423		CD_3	H	H	CD_3	H	H	H
L_A1424		CD_3	H	H	CD_3	H	H	CD_3
L_A1425		CD_3	iPr	H	H	H	H	H
L_A1426		CD_3	H	iPr	H	H	H	H
L_A1427		CD_3	H	H	iPr	H	H	H
L_A1428		CD_3	H	H	H	iPr	H	H
L_A1429		CD_3	Ph	H	H	H	H	H
L_A1430		CD_3	H	Ph	H	H	H	H
L_A1431		CD_3	H	H	Ph	H	H	H
L_A1432		CD_3	H	H	H	Ph	H	H
L_A1433	iPr	Me	H	H	H	H	H	
L_A1434	iPr	H	Me	H	H	H	H	
L_A1435	iPr	H	H	Me	H	H	H	
L_A1436	iPr	H	H	H	Me	H	H	
L_A1437	iPr	CD_3	H	H	H	H	H	
L_A1438	iPr	H	CD_3	H	H	H	H	
L_A1439	iPr	H	H	CD_3	H	H	H	
L_A1440	iPr	H	H	H	CD_3	H	H	
L_A1441	iPr	iPr	H	H	H	H	H	
L_A1442	iPr	H	iPr	H	H	H	H	
L_A1443	iPr	H	H	iPr	H	H	H	
L_A1444	iPr	H	H	H	iPr	H	H	
L_A1445	iPr	Ph	H	H	H	H	H	
L_A1446	iPr	H	Ph	H	H	H	H	
L_A1447	iPr	H	H	Ph	H	H	H	
L_A1448	iPr	H	H	H	Ph	H	H	
L_A1449	Ph	Me	H	H	H	H	H	
L_A1450	Ph	H	Me	H	H	H	H	
L_A1451	Ph	H	H	Me	H	H	H	
L_A1452	Ph	H	H	H	Me	H	H	
L_A1453	Ph	CD_3	H	H	H	H	H	
L_A1454	Ph	H	CD_3	H	H	H	H	
L_A1455	Ph	H	H	CD_3	H	H	H	
L_A1456	Ph	H	H	H	CD_3	H	H	
L_A1457	Ph	H	iPr	H	H	H	H	
L_A1458	Ph	H	iPr	H	H	H	H	
L_A1459	Ph	H	H	iPr	H	H	H	
L_A1460	Ph	H	H	H	iPr	H	H	
L_A1461	Ph	Ph	H	H	H	H	H	
L_A1462	Ph	H	Ph	H	H	H	H	
L_A1463	Ph	H	H	Ph	H	H	H	
L_A1464	Ph	H	H	H	Ph	H	H	
L_A1465	H	Me	Me	H	H	H	H	
L_A1466	H	Me	H	Me	H	H	H	
L_A1467	H	Me	H	H	Me	H	H	
L_A1468	H	Me	CD_3	H	H	H	H	
L_A1469	H	Me	H	CD_3	H	H	H	
L_A1470	H	Me	H	H	CD_3	H	H	
L_A1471	H	Me	iPr	H	H	H	H	
L_A1472	H	Me	H	iPr	H	H	H	
L_A1473	H	Me	H	H	iPr	H	H	
L_A1474	H	Me	Ph	H	H	H	H	
L_A1475	H	Me	H	Ph	H	H	H	
L_A1476	H	Me	H	H	Ph	H	H	
L_A1477	H	CD_3	Me	H	H	H	H	
L_A1478	H	CD_3	H	Me	H	H	H	
L_A1479	H	CD_3	H	H	Me	H	H	
L_A1480	H	CD_3	CD_3	H	H	H	H	
L_A1481	H	CD_3	H	CD_3	H	H	H	
L_A1482	H	CD_3	H	H	CD_3	H	H	
L_A1483	H	CD_3	iPr	H	H	H	H	
L_A1484	H	CD_3	H	iPr	H	H	H	
L_A1485	H	CD_3	H	H	iPr	H	H	
L_A1486	H	CD_3	Ph	H	H	H	H	
L_A1487	H	CD_3	H	Ph	H	H	H	
L_A1488	H	CD_3	H	H	Ph	H	H	
L_A1489	H	iPr	Me	H	H	H	H	
L_A1490	H	iPr	H	Me	H	H	H	
L_A1491	H	iPr	H	H	Me	H	H	
L_A1492	H	iPr	CD_3	H	H	H	H	
L_A1493	H	iPr	H	CD_3	H	H	H	
L_A1494	H	iPr	H	H	CD_3	H	H	
L_A1495	H	iPr	iPr	H	H	H	H	
L_A1496	H	iPr	H	iPr	H	H	H	
L_A1497	H	iPr	H	H	iPr	H	H	
L_A1498	H	iPr	Ph	H	H	H	H	
L_A1499	H	iPr	H	Ph	H	H	H	
L_A1500	H	iPr	H	H	Ph	H	H	



50

-continued

L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_A1501		H	Ph	Me	H	H	H	H
L_A1502		H	Ph	H	Me	H	H	H
L_A1503		H	Ph	H	H	Me	H	H
L_A1504		H	Ph	CD_3	H	H	H	H
L_A1505		H	Ph	H	CD_3	H	H	H
L_A1506		H	Ph	H	H	CD_3	H	H
L_A1507		H	Ph	iPr	H	H	H	H
L_A1508		H	Ph	H	iPr	H	H	H
L_A1509		H	Ph	H	H	iPr	H	H
L_A1510		H	Ph	Ph	H	H	H	H
L_A1511	H	Ph	H	Ph	H	H	H	
L_A1512	H	Ph	H	H	Ph	H	H	
L_A1513	H	H	Me	Me	H	H	H	
L_A1514	H	H	H	CD_3	Me	H	H	
L_A1515	H	H	iPr	Me	H	H	H	
L_A1516	H	H	Ph	Me	H	H	H	
L_A1517	H	H	Me	CD_3	H	H	H	
L_A1518	H	H	CD_3	CD_3	H	H	H	
L_A1519	H	H	iPr	CD_3	H	H	H	
L_A1520	H	H	Ph	CD_3	H	H	H	
L_A1521	H	H	Me	iPr	H	H	H	
L_A1522	H	H	CD_3	iPr	H	H	H	
L_A1523	H	H	iPr	iPr	H	H	H	
L_A1524	H	H	Ph	iPr	H	H	H	
L_A1525	H	H	Me	Ph	H	H	H	
L_A1526	H	H	CD_3	Ph	H	H	H	
L_A1527	H	H	iPr	Ph	H	H	H	
L_A1528	H	H	Ph	Ph	H	H	H	
L_A1529	H	H	Me	H	Me	H	H	
L_A1530	H	H	CD_3	H	Me	H	H	
L_A1531	H	H	iPr	H	Me	H	H	
L_A1532	H	H	Ph	H	Me	H	H	
L_A1533	H	H	Me	H	CD_3	H	H	
L_A1534		H	H	CD_3	H	CD_3	H	H
L_A1535		H	H	iPr	H	CD_3	H	H
L_A1536		H	H	Ph	H	CD_3	H	H
L_A1537		H	H	Me	H	iPr	H	H
L_A1538		H	H	CD_3	H	iPr	H	H
L_A1539		H	H	iPr	H	iPr	H	H
L_A1540		H	H	Ph	H	iPr	H	H
L_A1541		H	H	Me	H	Ph	H	H
L_A1542		H	H	CD_3	H	Ph	H	H
L_A1543		H	H	iPr	H	Ph	H	H
L_A1544	H	H	Ph	H	Ph	H	H	
L_A1545	Me	Me	H	Me	H	H	H	
L_A1546	H	Me	Me	Me	H	H	H	
L_A1547	CD_3	Me	H	Me	H	H	H	
L_A1548	H	Me	CD_3	Me	H	H	H	
L_A1549	iPr	Me	H	Me	H	H	H	
L_A1550	H	Me	iPr	Me	H	H	H	
L_A1551	Ph	Me	H	Me	H	H	H	
L_A1552	H	Me	Ph	Me	H	H	H	
L_A1553	Me	CD_3	H	CD_3	H	H	H	
L_A1554	H	CD_3	Me	CD_3	H	H	H	
L_A1555	CD_3	CD_3	H	CD_3	H	H	H	
L_A1556	H	CD_3	CD_3	CD_3	H	H	H	
L_A1557	iPr	CD_3	H	CD_3	H	H	H	
L_A1558	H	CD_3	iPr	CD_3	H	H	H	
L_A1559	Ph	CD_3	H	CD_3	H	H	H	
L_A1560	H	CD_3	Ph	CD_3	H	H	H	
L_A1561	Me	iPr	H	iPr	H	H	H	
L_A1562	H	iPr	Me	iPr	H	H	H	
L_A1563	CD_3	iPr	H	iPr	H	H	H	
L_A1564	H	iPr	CD_3	iPr	H	H	H	
L_A1565	iPr	iPr	H	iPr	H	H	H	
L_A1566	H	iPr	iPr	iPr	H	H	H	
L_A1567	Ph	iPr	H	iPr	H	H	H	
L_A1568	H	iPr	Ph	iPr	H	H	H	
L_A1569	Me	Ph	H	Ph	H	H	H	
L_A1570	H	Ph	Me	Ph	H	H	H	
L_A1571	CD_3	Ph	H	Ph	H	H	H	
L_A1572	H	Ph	CD_3	Ph	H	H	H	

51

-continued

L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_A1573		tPr	Ph	H	Ph	H	H	H
L_A1574		H	Ph	tPr	Ph	H	H	H
L_A1575		Ph	Ph	H	Ph	H	H	H
L_A1576		H	Ph	Ph	Ph	H	H	H
L_A1577		H	H	H	H	H	H	H
L_A1578		Me	H	H	H	H	H	H
L_A1579		H	Me	H	H	H	H	H
L_A1580		H	H	Me	H	H	H	H
L_A1581		H	H	H	Me	H	H	H
L_A1582		H	H	H	H	Me	H	H
L_A1583		CD_3	H	H	H	H	H	H
L_A1584		H	CD_3	H	H	H	H	H
L_A1585		H	H	CD_3	H	H	H	H
L_A1586		H	H	H	CD_3	H	H	H
L_A1587		H	H	H	H	CD_3	H	H
L_A1588		tPr	H	H	H	H	H	H
L_A1589		H	tPr	H	H	H	H	H
L_A1590		H	H	tPr	H	H	H	H
L_A1591		H	H	H	tPr	H	H	H
L_A1592		H	H	H	H	tPr	H	H
L_A1593	Ph	H	H	H	H	H	H	
L_A1594	H	Ph	H	H	H	H	H	
L_A1595	H	H	Ph	H	H	H	H	
L_A1596	H	H	H	Ph	H	H	H	
L_A1597	H	H	H	H	Ph	H	H	
L_A1598	Me	Me	H	H	H	H	H	
L_A1599	Me	H	Me	H	H	H	H	
L_A1600	Me	H	H	Me	H	H	H	
L_A1601	Me	H	H	H	Me	H	H	
L_A1602	Me	CD_3	H	H	H	H	H	
L_A1603	Me	H	CD_3	H	H	H	H	
L_A1604	Me	H	H	CD_3	H	H	H	
L_A1605	Me	H	H	H	CD_3	H	H	
L_A1606	Me	tPr	H	H	H	H	H	
L_A1607	Me	H	tPr	H	H	H	H	
L_A1608	Me	H	H	tPr	H	H	H	
L_A1609	Me	H	H	H	tPr	H	H	
L_A1610	Me	Ph	H	H	H	H	H	
L_A1611	Me	H	Ph	H	H	H	H	
L_A1612	Me	H	H	Ph	H	H	H	
L_A1613	Me	H	H	H	Ph	H	H	
L_A1614	CD_3	Me	H	H	H	H	H	
L_A1615	CD_3	H	Me	H	H	H	H	
L_A1616	CD_3	H	H	Me	H	H	H	
L_A1617	CD_3	H	H	H	Me	H	H	
L_A1618	CD_3	CD_3	H	H	H	H	H	
L_A1619	CD_3	H	CD_3	H	H	H	H	
L_A1620	CD_3	H	H	CD_3	H	H	H	
L_A1621	CD_3	H	H	H	CD_3	H	H	
L_A1622	CD_3	tPr	H	H	H	H	H	
L_A1623	CD_3	H	tPr	H	H	H	H	
L_A1624	CD_3	H	H	tPr	H	H	H	
L_A1625	CD_3	H	H	H	tPr	H	H	
L_A1626	CD_3	Ph	H	H	H	H	H	
L_A1627	CD_3	H	Ph	H	H	H	H	
L_A1628	CD_3	H	H	Ph	H	H	H	
L_A1629	CD_3	H	H	H	Ph	H	H	
L_A1630	tPr	Me	H	H	H	H	H	
L_A1631	tPr	H	Me	H	H	H	H	
L_A1632	tPr	H	H	Me	H	H	H	
L_A1633	tPr	H	H	H	Me	H	H	
L_A1634	tPr	CD_3	H	H	H	H	H	
L_A1635	tPr	H	CD_3	H	H	H	H	
L_A1636	tPr	H	H	CD_3	H	H	H	
L_A1637	tPr	H	H	H	CD_3	H	H	
L_A1638	tPr	tPr	H	H	H	H	H	
L_A1639	tPr	H	tPr	H	H	H	H	
L_A1640	tPr	H	H	tPr	H	H	H	
L_A1641	tPr	H	H	H	tPr	H	H	
L_A1642	tPr	Ph	H	H	H	H	H	



52

-continued

L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_A1643		tPr	H	Ph	H	H	H	H
L_A1644		tPr	H	H	Ph	H	H	H
L_A1645		tPr	H	H	H	Ph	H	H
L_A1646		Ph	Me	H	H	H	H	H
L_A1647		Ph	H	Me	H	H	H	H
L_A1648		Ph	H	H	Me	H	H	H
L_A1649		Ph	H	H	H	Me	H	H
L_A1650		Ph	CD_3	H	H	H	H	H
L_A1651		Ph	H	CD_3	H	H	H	H
L_A1652		Ph	H	H	CD_3	H	H	H
L_A1653	Ph	H	H	H	CD_3	H	H	
L_A1654	Ph	tPr	H	H	H	H	H	
L_A1655	Ph	H	tPr	H	H	H	H	
L_A1656	Ph	H	H	tPr	H	H	H	
L_A1657	Ph	H	H	H	tPr	H	H	
L_A1658	Ph	Ph	H	H	H	H	H	
L_A1659	Ph	H	Ph	H	H	H	H	
L_A1660	Ph	H	H	Ph	H	H	H	
L_A1661	Ph	H	H	H	Ph	H	H	
L_A1662	H	Me	Me	H	H	H	H	
L_A1663	H	Me	H	Me	H	H	H	
L_A1664	H	Me	H	H	Me	H	H	
L_A1665	H	Me	CD_3	H	H	H	H	
L_A1666	H	Me	H	CD_3	H	H	H	
L_A1667	H	Me	H	H	CD_3	H	H	
L_A1668	H	Me	tPr	H	H	H	H	
L_A1669	H	Me	H	tPr	H	H	H	
L_A1670	H	Me	H	H	tPr	H	H	
L_A1671	H	Me	Ph	H	H	H	H	
L_A1672	H	Me	H	Ph	H	H	H	
L_A1673	H	Me	H	H	Ph	H	H	
L_A1674	H	CD_3	Me	H	H	H	H	
L_A1675	H	CD_3	H	Me	H	H	H	
L_A1676	H	CD_3	H	H	Me	H	H	
L_A1677	H	CD_3	CD_3	H	H	H	H	
L_A1678	H	CD_3	H	CD_3	H	H	H	
L_A1679	H	CD_3	H	H	CD_3	H	H	
L_A1680	H	CD_3	tPr	H	H	H	H	
L_A1681	H	CD_3	H	tPr	H	H	H	
L_A1682	H	CD_3	H	H	tPr	H	H	
L_A1683	H	CD_3	Ph	H	H	H	H	
L_A1684	H	CD_3	H	Ph	H	H	H	
L_A1685	H	CD_3	H	H	Ph	H	H	
L_A1686	H	tPr	Me	H	H	H	H	
L_A1687	H	tPr	H	Me	H	H	H	
L_A1688	H	tPr	H	H	Me	H	H	
L_A1689	H	tPr	CD_3	H	H	H	H	
L_A1690	H	tPr	H	CD_3	H	H	H	
L_A1691	H	tPr	H	H	CD_3	H	H	
L_A1692	H	tPr	tPr	H	H	H	H	
L_A1693	H	tPr	H	tPr	H	H	H	
L_A1694	H	tPr	H	H	tPr	H	H	
L_A1695	H	tPr	Ph	H	H	H	H	
L_A1696	H	tPr	H	Ph	H	H	H	
L_A1697	H	tPr	H	H	Ph	H	H	
L_A1698	H	Ph	Me	H	H	H	H	
L_A1699	H	Ph	H	Me	H	H	H	
L_A1700	H	Ph	H	H	Me	H	H	
L_A1701	H	Ph	CD_3	H	H	H	H	
L_A1702	H	Ph	H	CD_3	H	H	H	
L_A1703	H	Ph	H	H	CD_3	H	H	
L_A1704	H	Ph	tPr	H	H	H	H	
L_A1705	H	Ph	H	tPr	H	H	H	
L_A1706	H	Ph	H	H	tPr	H	H	
L_A1707	H	Ph	Ph	H	H	H	H	
L_A1708	H	Ph	H	Ph	H	H	H	
L_A1709	H	Ph	H	H	Ph	H	H	
L_A1710	H	H	Me	Me	H	H	H	
L_A1711	H	H	CD_3	Me	H	H	H	
L_A1712	H	H	tPr	Me	H	H	H	
L_A1713	H	H	Ph	Me	H	H	H	
L_A1714	H	H	Me	CD_3	H	H	H	
L_A1715	H	H	CD_3	CD_3	H	H	H	
L_A1716	H	H	tPr	CD_3	H	H	H	
L_A1717	H	H	Ph	CD_3	H	H	H	
L_A1718	H	H	Me	tPr	H	H	H	



-continued

L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_A1719		H	H	CD_3	iPr	H	H	H
L_A1720		H	H	iPr	iPr	H	H	H
L_A1721		H	H	Ph	iPr	H	H	H
L_A1722		H	H	Me	Ph	H	H	H
L_A1723		H	H	CD_3	Ph	H	H	H
L_A1724		H	H	iPr	Ph	H	H	H
L_A1725		H	H	Ph	Ph	H	H	H
L_A1726		H	H	Me	H	Me	H	H
L_A1727		H	H	CD_3	H	Me	H	H
L_A1728		H	H	iPr	H	Me	H	H
L_A1729		H	H	Ph	H	Me	H	H
L_A1730		H	H	Me	H	CD_3	H	H
L_A1731		H	H	CD_3	H	CD_3	H	H
L_A1732		H	H	iPr	H	CD_3	H	H
L_A1733		H	H	Ph	H	CD_3	H	H
L_A1734		H	H	Me	H	iPr	H	H
L_A1735		H	H	CD_3	H	iPr	H	H
L_A1736		H	H	iPr	H	iPr	H	H
L_A1737		H	H	Ph	H	iPr	H	H
L_A1738		H	H	Me	H	Ph	H	H
L_A1739		H	H	CD_3	H	Ph	H	H
L_A1740		H	H	iPr	H	Ph	H	H
L_A1741		H	H	Ph	H	Ph	H	H
L_A1742		Me	Me	H	Me	H	H	H
L_A1743		H	Me	Me	Me	H	H	H
L_A1744		CD_3	Me	H	Me	H	H	H
L_A1745		H	Me	CD_3	Me	H	H	H
L_A1746		iPr	Me	H	Me	H	H	H
L_A1747		H	Me	iPr	Me	H	H	H
L_A1748		Ph	Me	H	Me	H	H	H
L_A1749		H	Me	Ph	Me	H	H	H
L_A1750		Me	CD_3	H	CD_3	H	H	H
L_A1751		H	CD_3	Me	CD_3	H	H	H
L_A1752		CD_3	CD_3	H	CD_3	H	H	H
L_A1753		H	CD_3	CD_3	CD_3	H	H	H
L_A1754		iPr	CD_3	H	CD_3	H	H	H
L_A1755		H	CD_3	iPr	CD_3	H	H	H
L_A1756		Ph	CD_3	H	CD_3	H	H	H
L_A1757		H	CD_3	Ph	CD_3	H	H	H
L_A1758		Me	iPr	H	iPr	H	H	H
L_A1759		H	iPr	Me	iPr	H	H	H
L_A1760		CD_3	iPr	H	iPr	H	H	H
L_A1761		H	iPr	CD_3	iPr	H	H	H
L_A1762		iPr	iPr	H	iPr	H	H	H
L_A1763		H	iPr	iPr	iPr	H	H	H
L_A1764		Ph	iPr	H	iPr	H	H	H
L_A1765		H	iPr	Ph	iPr	H	H	H
L_A1766		Me	Ph	H	Ph	H	H	H
L_A1767		H	Ph	Me	Ph	H	H	H
L_A1768		CD_3	Ph	H	Ph	H	H	H
L_A1769		H	Ph	CD_3	Ph	H	H	H
L_A1770		iPr	Ph	H	Ph	H	H	H
L_A1771		H	Ph	iPr	Ph	H	H	H
L_A1772		Ph	Ph	H	Ph	H	H	H
L_A1773		H	Ph	Ph	Ph	H	H	H
L_A1774		H	H	H	H	H	H	H
L_A1775		Me	H	H	H	H	H	H
L_A1776		H	Me	H	H	H	H	H
L_A1777		H	H	Me	H	H	H	H
L_A1778		H	H	H	Me	H	H	H
L_A1779		H	H	H	H	Me	H	H
L_A1780		CD_3	H	H	H	H	H	H
L_A1781		H	CD_3	H	H	H	H	H
L_A1782		H	H	CD_3	H	H	H	H
L_A1783		H	H	H	CD_3	H	H	H
L_A1784		H	H	H	H	CD_3	H	H
L_A1785		iPr	H	H	H	H	H	H
L_A1786		H	iPr	H	H	H	H	H
L_A1787		H	H	iPr	H	H	H	H
L_A1788		H	H	H	iPr	H	H	H
L_A1789		H	H	H	H	iPr	H	H
L_A1790		Ph	H	H	H	H	H	H
L_A1791		H	Ph	H	H	H	H	H
L_A1792		H	H	Ph	H	H	H	H
L_A1793		H	H	H	Ph	H	H	H
L_A1794		H	H	H	H	Ph	H	H



-continued


L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_A1795		Me	Me	H	H	H	H	H
L_A1796		Me	H	Me	H	H	H	H
L_A1797		Me	H	H	Me	H	H	H
L_A1798		Me	H	H	H	Me	H	H
L_A1799		Me	CD_3	H	H	H	H	H
L_A1800		Me	H	CD_3	H	H	H	H
L_A1801		Me	H	H	CD_3	H	H	H
L_A1802		Me	H	H	H	CD_3	H	H
L_A1803		Me	iPr	H	H	H	H	H
L_A1804		Me	H	iPr	H	H	H	H
L_A1805		Me	H	H	iPr	H	H	H
L_A1806		Me	H	H	H	iPr	H	H
L_A1807		Me	Ph	H	H	H	H	H
L_A1808		Me	H	Ph	H	H	H	H
L_A1809		Me	H	H	Ph	H	H	H
L_A1810		Me	H	H	H	Ph	H	H
L_A1811		CD_3	Me	H	H	H	H	H
L_A1812		CD_3	H	Me	H	H	H	H
L_A1813		CD_3	H	H	Me	H	H	H
L_A1814		CD_3	H	H	H	Me	H	H
L_A1815		CD_3	CD_3	H	H	H	H	H
L_A1816		CD_3	H	CD_3	H	H	H	H
L_A1817		CD_3	H	H	CD_3	H	H	H
L_A1818		CD_3	H	H	H	CD_3	H	H
L_A1819		CD_3	iPr	H	H	H	H	H
L_A1820		CD_3	H	iPr	H	H	H	H
L_A1821		CD_3	H	H	iPr	H	H	H
L_A1822		CD_3	H	H	H	iPr	H	H
L_A1823		CD_3	Ph	H	H	H	H	H
L_A1824		CD_3	H	Ph	H	H	H	H
L_A1825		CD_3	H	H	Ph	H	H	H
L_A1826		CD_3	H	H	H	Ph	H	H
L_A1827		iPr	Me	H	H	H	H	H
L_A1828		iPr	H	Me	H	H	H	H
L_A1829		iPr	H	H	Me	H	H	H
L_A1830		iPr	H	H	H	Me	H	H
L_A1831		iPr	CD_3	H	H	H	H	H
L_A1832		iPr	H	CD_3	H	H	H	H
L_A1833		iPr	H	H	CD_3	H	H	H
L_A1834		iPr	H	H	H	CD_3	H	H
L_A1835		iPr	iPr	H	H	H	H	H
L_A1836		iPr	H	iPr	H	H	H	H
L_A1837		iPr	H	H	iPr	H	H	H
L_A1838		iPr	H	H	H	iPr	H	H
L_A1839		iPr	Ph	H	H	H	H	H
L_A1840		iPr	H	Ph	H	H	H	H
L_A1841		iPr	H	H	Ph	H	H	H
L_A1842		iPr	H	H	H	Ph	H	H
L_A1843		Ph	Me	H	H	H	H	H
L_A1844		Ph	H	Me	H	H	H	H
L_A1845		Ph	H	H	Me	H	H	H
L_A1846		Ph	H	H	H	Me	H	H
L_A1847		Ph	CD_3	H	H	H	H	H
L_A1848		Ph	H	CD_3	H	H	H	H
L_A1849		Ph	H	H	CD_3	H	H	H
L_A1850		Ph	H	H	H	CD_3	H	H
L_A1851		Ph	iPr	H	H	H	H	H
L_A1852		Ph	H	iPr	H	H	H	H
L_A1853		Ph	H	H	iPr	H	H	H
L_A1854		Ph	H	H	H	iPr	H	H
L_A1855		Ph	Ph	H	H	H	H	H
L_A1856		Ph	H	Ph	H	H	H	H
L_A1857		Ph	H	H	Ph	H	H	H
L_A1858		Ph	H	H	H	Ph	H	H
L_A1859		H	Me	Me	H	H	H	H
L_A1860		H	Me	H	Me	H	H	H
L_A1861		H	Me	H	H	Me	H	H
L_A1862		H	Me	CD_3	H	H	H	H
L_A1863		H	Me	H	CD_3	H	H	H
L_A1864		H	Me	H	H	CD_3	H	H
L_A1865		H	Me	iPr	H	H	H	H
L_A1866		H	Me	H	iPr	H	H	H
L_A1867		H	Me	H	H	iPr	H	H
L_A1868		H	Me	Ph	H	H	H	H
L_A1869		H	Me	H	Ph	H	H	H
L_A1870		H	Me	H	H	Ph	H	H



55

-continued


L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_A 1871		H	CD ₃	Me	H	H	H	H
L_A 1872		H	CD ₃	H	Me	H	H	H
L_A 1873		H	CD ₃	H	H	Me	H	H
L_A 1874		H	CD ₃	CD ₃	H	H	H	H
L_A 1875		H	CD ₃	H	CD ₃	H	H	H
L_A 1876		H	CD ₃	H	H	CD ₃	H	H
L_A 1877		H	CD ₃	^t Pr	H	H	H	H
L_A 1878		H	CD ₃	H	^t Pr	H	H	H
L_A 1879		H	CD ₃	H	H	^t Pr	H	H
L_A 1880		H	CD ₃	Ph	H	H	H	H
L_A 1881		H	CD ₃	H	Ph	H	H	H
L_A 1882		H	CD ₃	H	H	Ph	H	H
L_A 1883		H	^t Pr	Me	H	H	H	H
L_A 1884		H	^t Pr	H	Me	H	H	H
L_A 1885		H	^t Pr	H	H	Me	H	H
L_A 1886		H	^t Pr	CD ₃	H	H	H	H
L_A 1887		H	^t Pr	H	CD ₃	H	H	H
L_A 1888		H	^t Pr	H	H	CD ₃	H	H
L_A 1889		H	^t Pr	^t Pr	H	H	H	H
L_A 1890		H	^t Pr	H	^t Pr	H	H	H
L_A 1891		H	^t Pr	H	H	^t Pr	H	H
L_A 1892		H	^t Pr	Ph	H	H	H	H
L_A 1893		H	^t Pr	H	Ph	H	H	H
L_A 1894		H	^t Pr	H	H	Ph	H	H
L_A 1895		H	Ph	Me	H	H	H	H
L_A 1896		H	Ph	H	Me	H	H	H
L_A 1897		H	Ph	H	H	Me	H	H
L_A 1898		H	Ph	CD ₃	H	H	H	H
L_A 1899		H	Ph	H	CD ₃	H	H	H
L_A 1900		H	Ph	H	H	CD ₃	H	H
L_A 1901		H	Ph	^t Pr	H	H	H	H
L_A 1902		H	Ph	H	^t Pr	H	H	H
L_A 1903		H	Ph	H	H	^t Pr	H	H
L_A 1904		H	Ph	Ph	H	H	H	H
L_A 1905		H	Ph	H	Ph	H	H	H
L_A 1906		H	Ph	H	H	Ph	H	H
L_A 1907		H	H	Me	Me	H	H	H
L_A 1908		H	H	CD ₃	Me	H	H	H
L_A 1909		H	H	^t Pr	Me	H	H	H
L_A 1910		H	H	Ph	Me	H	H	H
L_A 1911		H	H	H	Me	CD ₃	H	H
L_A 1912		H	H	CD ₃	CD ₃	H	H	H
L_A 1913		H	H	^t Pr	CD ₃	H	H	H
L_A 1914		H	H	H	Ph	CD ₃	H	H
L_A 1915		H	H	Me	^t Pr	H	H	H
L_A 1916		H	H	CD ₃	^t Pr	H	H	H
L_A 1917		H	H	H	^t Pr	H	H	H
L_A 1918		H	H	Ph	^t Pr	H	H	H
L_A 1919		H	H	Me	Ph	H	H	H
L_A 1920		H	H	CD ₃	Ph	H	H	H
L_A 1921		H	H	^t Pr	Ph	H	H	H
L_A 1922		H	H	Ph	Ph	H	H	H
L_A 1923		H	H	Me	H	Me	H	H
L_A 1924		H	H	CD ₃	H	Me	H	H
L_A 1925		H	H	^t Pr	H	Me	H	H
L_A 1926		H	H	Ph	H	Me	H	H
L_A 1927		H	H	Me	H	CD ₃	H	H
L_A 1928		H	H	CD ₃	H	CD ₃	H	H
L_A 1929		H	H	^t Pr	H	CD ₃	H	H
L_A 1930		H	H	Ph	H	CD ₃	H	H
L_A 1931		H	H	Me	H	^t Pr	H	H
L_A 1932		H	H	CD ₃	H	^t Pr	H	H
L_A 1933		H	H	^t Pr	H	^t Pr	H	H
L_A 1934		H	H	Ph	H	^t Pr	H	H
L_A 1935		H	H	Me	H	Ph	H	H
L_A 1936		H	H	CD ₃	H	Ph	H	H
L_A 1937		H	H	^t Pr	H	Ph	H	H
L_A 1938		H	H	Ph	H	Ph	H	H
L_A 1939		Me	Me	H	Me	H	H	H
L_A 1940		H	Me	Me	Me	H	H	H
L_A 1941		CD ₃	Me	H	Me	H	H	H
L_A 1942		H	Me	CD ₃	Me	H	H	H
L_A 1943		^t Pr	Me	H	Me	H	H	H
L_A 1944		H	Me	^t Pr	Me	H	H	H
L_A 1945		Ph	Me	H	Me	H	H	H
L_A 1946		H	Me	Ph	Me	H	H	H
L_A 1947		Me	CD ₃	H	CD ₃	H	H	H



56

-continued



L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_A 1948		H	CD ₃	Me	CD ₃	H	H	H
L_A 1949		CD ₃	CD ₃	H	CD ₃	H	H	H
L_A 1950		H	CD ₃	CD ₃	CD ₃	H	H	H
L_A 1951		^t Pr	CD ₃	H	CD ₃	H	H	H
L_A 1952		H	CD ₃	^t Pr	CD ₃	H	H	H
L_A 1953		Ph	CD ₃	H	CD ₃	H	H	H
L_A 1954		H	CD ₃	Ph	CD ₃	H	H	H
L_A 1955		Me	^t Pr	H	^t Pr	H	H	H
L_A 1956		H	^t Pr	Me	^t Pr	H	H	H
L_A 1957		CD ₃	^t Pr	H	^t Pr	H	H	H
L_A 1958		H	^t Pr	CD ₃	^t Pr	H	H	H
L_A 1959		iPr	^t Pr	H	^t Pr	H	H	H
L_A 1960		H	^t Pr	^t Pr	^t Pr	H	H	H
L_A 1961		Ph	^t Pr	H	^t Pr	H	H	H
L_A 1962		H	^t Pr	Ph	^t Pr	H	H	H
L_A 1963		Me	Ph	H	Ph	H	H	H
L_A 1964		H	Ph	Me	Ph	H	H	H
L_A 1965		CD ₃	Ph	H	Ph	H	H	H
L_A 1966		H	Ph	CD ₃	Ph	H	H	H
L_A 1967		iPr	Ph	H	Ph	H	H	H
L_A 1968		H	Ph	^t Pr	Ph	H	H	H
L_A 1969		Ph	Ph	H	Ph	H	H	H
L_A 1970		H	Ph	Ph	Ph	H	H	H
L_A 1971		H	H	H	H	H	H	H
L_A 1972		Me	H	H	H	H	H	H
L_A 1973		H	Me	H	H	H	H	H
L_A 1974		H	H	Me	H	H	H	H
L_A 1975		H	H	H	Me	H	H	H
L_A 1976		H	H	H	H	Me	H	H
L_A 1977		CD ₃	H	H	H	H	H	H
L_A 1978		H	CD ₃	H	H	H	H	H
L_A 1979		H	H	CD ₃	H	H	H	H
L_A 1980		H	H	H	CD ₃	H	H	H
L_A 1981		H	H	H	H	CD ₃	H	H
L_A 1982		^t Pr	H	H	H	H	H	H
L_A 1983		H	^t Pr	H	H	H	H	H
L_A 1984		H	H	^t Pr	H	H	H	H
L_A 1985		H	H	H	^t Pr	H	H	H
L_A 1986		H	H	H	H	^t Pr	H	H
L_A 1987		Ph	H	H	H	H	H	H
L_A 1988		H	Ph	H	H	H	H	H
L_A 1989		H	H	Ph	H	H	H	H
L_A 1990		H	H	H	Ph	H	H	H
L_A 1991		H	H	H	H	Ph	H	H
L_A 1992		Me	Me	H	H	H	H	H
L_A 1993		Me	H	Me	H	H	H	H
L_A 1994		Me	H	H	Me	H	H	H
L_A 1995		Me	H	H	H	Me	H	H
L_A 1996		Me	CD ₃	H	H	H	H	H
L_A 1997		Me	H	CD ₃	H	H	H	H
L_A 1998		Me	H	H	CD ₃	H	H	H
L_A 1999		Me	H	H	H	CD ₃	H	H
L_A 2000		Me	^t Pr	H	H	H	H	H
L_A 2001		Me	H	^t Pr	H	H	H	H
L_A 2002		Me	H	H	^t Pr	H	H	H
L_A 2003		Me	H	H	H	^t Pr	H	H
L_A 2004		Me	Ph	H	H	H	H	H
L_A 2005		Me	H	Ph	H	H	H	H
L_A 2006		Me	H	H	Ph	H	H	H
L_A 2007		Me	H	H	H	Ph	H	H
L_A 2008		CD ₃	Me	H	H	H	H	H
L_A 2009		CD ₃	H	Me	H	H	H	H
L_A 2010		CD ₃	H	H	Me	H	H	H
L_A 2011		CD ₃	H	H	H	Me	H	H
L_A 2012		CD ₃	CD ₃	H	H	H	H	H
L_A 2013		CD ₃	H	CD ₃	H	H	H	H
L_A 2014		CD ₃	H	H	CD ₃	H	H	H
L_A 2015		CD ₃	H	H	H	CD ₃	H	H
L_A 2016		CD ₃	^t Pr	H	H	H	H	H
L_A 2017		CD ₃	H	^t Pr	H	H	H	H
L_A 2018		CD ₃	H	H	^t Pr	H	H	H



57

-continued

L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_{A2019}		CD_3	H	H	H	iPr	H	H
L_{A2020}		CD_3	Ph	H	H	H	H	H
L_{A2021}		CD_3	H	Ph	H	H	H	H
L_{A2022}		CD_3	H	H	Ph	H	H	H
L_{A2023}		CD_3	H	H	H	Ph	H	H
L_{A2024}		iPr	Me	H	H	H	H	H
L_{A2025}		iPr	H	Me	H	H	H	H
L_{A2026}		iPr	H	H	Me	H	H	H
L_{A2027}		iPr	H	H	H	Me	H	H
L_{A2028}		iPr	CD_3	H	H	H	H	H
L_{A2029}		iPr	H	CD_3	H	H	H	H
L_{A2030}		iPr	H	H	CD_3	H	H	H
L_{A2031}		iPr	H	H	H	CD_3	H	H
L_{A2032}		iPr	iPr	H	H	H	H	H
L_{A2033}		iPr	H	iPr	H	H	H	H
L_{A2034}		iPr	H	H	iPr	H	H	H
L_{A2035}		iPr	H	H	H	iPr	H	H
L_{A2036}		iPr	Ph	H	H	H	H	H
L_{A2037}		iPr	H	Ph	H	H	H	H
L_{A2038}		iPr	H	H	Ph	H	H	H
L_{A2039}		iPr	H	H	H	Ph	H	H
L_{A2040}		Ph	Me	H	H	H	H	H
L_{A2041}		Ph	H	Me	H	H	H	H
L_{A2042}		Ph	H	H	Me	H	H	H
L_{A2043}		Ph	H	H	H	Me	H	H
L_{A2044}		Ph	CD_3	H	H	H	H	H
L_{A2045}		Ph	H	CD_3	H	H	H	H
L_{A2046}		Ph	H	H	CD_3	H	H	H
L_{A2047}		Ph	H	H	H	CD_3	H	H
L_{A2048}		Ph	iPr	H	H	H	H	H
L_{A2049}		Ph	H	H	iPr	H	H	H
L_{A2050}		Ph	H	H	H	iPr	H	H
L_{A2051}		Ph	H	H	H	iPr	H	H
L_{A2052}		Ph	Ph	H	H	H	H	H
L_{A2053}		Ph	H	Ph	H	H	H	H
L_{A2054}		Ph	H	H	Ph	H	H	H
L_{A2055}		Ph	H	H	H	Ph	H	H
L_{A2056}		H	Me	Me	H	H	H	H
L_{A2057}		H	Me	H	Me	H	H	H
L_{A2058}		H	Me	H	H	Me	H	H
L_{A2059}		H	Me	CD_3	H	H	H	H
L_{A2060}		H	Me	H	CD_3	H	H	H
L_{A2061}		H	Me	H	H	CD_3	H	H
L_{A2062}		H	Me	iPr	H	H	H	H
L_{A2063}		H	Me	H	iPr	H	H	H
L_{A2064}		H	Me	H	H	iPr	H	H
L_{A2065}		H	Me	Ph	H	H	H	H
L_{A2066}		H	Me	H	Ph	H	H	H
L_{A2067}		H	Me	H	H	Ph	H	H
L_{A2068}		H	CD_3	Me	H	H	H	H
L_{A2069}		H	CD_3	H	Me	H	H	H
L_{A2070}		H	CD_3	H	H	Me	H	H
L_{A2071}		H	CD_3	CD_3	H	H	H	H
L_{A2072}		H	CD_3	H	CD_3	H	H	H
L_{A2073}		H	CD_3	H	H	CD_3	H	H
L_{A2074}		H	CD_3	iPr	H	H	H	H
L_{A2075}		H	CD_3	H	iPr	H	H	H
L_{A2076}		H	CD_3	H	H	iPr	H	H
L_{A2077}		H	CD_3	Ph	H	H	H	H
L_{A2078}		H	CD_3	H	Ph	H	H	H
L_{A2079}		H	CD_3	H	H	Ph	H	H
L_{A2080}		H	iPr	Me	H	H	H	H
L_{A2081}		H	iPr	H	Me	H	H	H
L_{A2082}		H	iPr	H	H	Me	H	H
L_{A2083}		H	iPr	CD_3	H	H	H	H
L_{A2084}		H	iPr	H	CD_3	H	H	H
L_{A2085}		H	iPr	H	H	CD_3	H	H
L_{A2086}		H	iPr	iPr	H	H	H	H
L_{A2087}		H	iPr	H	iPr	H	H	H
L_{A2088}		H	iPr	H	H	iPr	H	H
L_{A2089}		H	iPr	Ph	H	H	H	H
L_{A2090}		H	iPr	H	Ph	H	H	H
L_{A2091}		H	iPr	H	H	Ph	H	H
L_{A2092}		H	Ph	Me	H	H	H	H
L_{A2093}		H	Ph	H	Me	H	H	H
L_{A2094}		H	Ph	H	H	Me	H	H




58

-continued

L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_{A2095}		H	Ph	CD_3	H	H	H	H
L_{A2096}		H	Ph	H	CD_3	H	H	H
L_{A2097}		H	Ph	H	H	CD_3	H	H
L_{A2098}		H	Ph	iPr	H	H	H	H
L_{A2099}		H	Ph	H	iPr	H	H	H
L_{A2100}		H	Ph	H	H	iPr	H	H
L_{A2101}		H	Ph	Ph	H	H	H	H
L_{A2102}		H	Ph	H	Ph	H	H	H
L_{A2103}		H	Ph	H	H	Ph	H	H
L_{A2104}		H	H	Me	Me	H	H	H
L_{A2105}		H	H	CD_3	Me	H	H	H
L_{A2106}		H	H	iPr	Me	H	H	H
L_{A2107}		H	H	Ph	Me	H	H	H
L_{A2108}		H	H	Me	CD_3	H	H	H
L_{A2109}		H	H	CD_3	CD_3	H	H	H
L_{A2110}		H	H	iPr	CD_3	H	H	H
L_{A2111}		H	H	Ph	CD_3	H	H	H
L_{A2112}		H	H	Me	iPr	H	H	H
L_{A2113}		H	H	CD_3	iPr	H	H	H
L_{A2114}		H	H	iPr	iPr	H	H	H
L_{A2115}		H	H	Ph	iPr	H	H	H
L_{A2116}		H	H	Me	Ph	H	H	H
L_{A2117}		H	H	CD_3	Ph	H	H	H
L_{A2118}		H	H	iPr	Ph	H	H	H
L_{A2119}		H	H	Ph	Ph	H	H	H
L_{A2120}		H	H	Me	H	Me	H	H
L_{A2121}		H	H	CD_3	H	Me	H	H
L_{A2122}		H	H	iPr	H	Me	H	H
L_{A2123}		H	H	Ph	H	Me	H	H
L_{A2124}		H	H	Me	H	CD_3	H	H
L_{A2125}		H	H	CD_3	H	CD_3	H	H
L_{A2126}		H	H	iPr	H	CD_3	H	H
L_{A2127}		H	H	Ph	H	CD_3	H	H
L_{A2128}		H	H	Me	H	iPr	H	H
L_{A2129}		H	H	CD_3	H	iPr	H	H
L_{A2130}		H	H	iPr	H	iPr	H	H
L_{A2131}		H	H	Ph	H	iPr	H	H
L_{A2132}		H	H	Me	H	Ph	H	H
L_{A2133}		H	H	CD_3	H	Ph	H	H
L_{A2134}		H	H	iPr	H	Ph	H	H
L_{A2135}		H	H	Ph	H	Ph	H	H
L_{A2136}		Me	Me	H	Me	H	H	H
L_{A2137}		H	Me	Me	Me	H	H	H
L_{A2138}		CD_3	Me	H	Me	H	H	H
L_{A2139}		H	Me	CD_3	Me	H	H	H
L_{A2140}		iPr	Me	H	Me	H	H	H
L_{A2141}		H	Me	iPr	Me	H	H	H
L_{A2142}		Ph	Me	H	Me	H	H	H
L_{A2143}		H	Me	Ph	Me	H	H	H
L_{A2144}		Me	CD_3	H	CD_3	H	H	H
L_{A2145}		H	CD_3	Me	CD_3	H	H	H
L_{A2146}		CD_3	CD_3	H	CD_3	H	H	H
L_{A2147}		H	CD_3	CD_3	CD_3	H	H	H
L_{A2148}		iPr	CD_3	H	CD_3	H	H	H
L_{A2149}		H	CD_3	iPr	CD_3	H	H	H
L_{A2150}		Ph	CD_3	H	CD_3	H	H	H
L_{A2151}		H	CD_3	Ph	CD_3	H	H	H
L_{A2152}		Me	iPr	H	iPr	H	H	H
L_{A2153}		H	iPr	Me	iPr	H	H	H
L_{A2154}		CD_3	iPr	H	iPr	H	H	H
L_{A2155}		H	iPr	CD_3	iPr	H	H	H
L_{A2156}		iPr	iPr	H	iPr	H	H	H
L_{A2157}		H	iPr	iPr	iPr	H	H	H
L_{A2158}		Ph	iPr	H	iPr	H	H	H
L_{A2159}		H	iPr	Ph	iPr	H	H	H
L_{A2160}		Me	Ph	H	Ph	H	H	H
L_{A2161}		H	Ph	Me	Ph	H	H	H
L_{A2162}		CD_3	Ph	H	Ph	H	H	H
L_{A2163}		H	Ph	CD_3	Ph	H	H	H
L_{A2164}		iPr	Ph	H	Ph	H	H	H
L_{A2165}		H	Ph	iPr	Ph	H	H	H
L_{A2166}		Ph	Ph	H	Ph	H	H	H
L_{A2167}		H	Ph	Ph	Ph	H	H	H


59

-continued

L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_A 2168		H	H	H	H	H	H	H
L_A 2169		Me	H	H	H	H	H	H
L_A 2170		H	Me	H	H	H	H	H
L_A 2171		H	H	Me	H	H	H	H
L_A 2172		H	H	H	Me	H	H	H
L_A 2173		H	H	H	H	Me	H	H
L_A 2174		CD ₃	H	H	H	H	H	H
L_A 2175		H	CD ₃	H	H	H	H	H
L_A 2176		H	H	CD ₃	H	H	H	H
L_A 2177		H	H	H	CD ₃	H	H	H
L_A 2178	H	H	H	H	CD ₃	H	H	
L_A 2179	^t Pr	H	H	H	H	H	H	
L_A 2180	H	ⁱ Pr	H	H	H	H	H	
L_A 2181	H	H	^p Pr	H	H	H	H	
L_A 2182	H	H	H	^t Pr	H	H	H	
L_A 2183	H	H	H	H	ⁱ Pr	H	H	
L_A 2184	Ph	H	H	H	H	H	H	
L_A 2185	H	Ph	H	H	H	H	H	
L_A 2186	H	H	Ph	H	H	H	H	
L_A 2187	H	H	H	Ph	H	H	H	
L_A 2188	H	H	H	H	Ph	H	H	
L_A 2189	Me	Me	H	H	H	H	H	
L_A 2190	Me	H	Me	H	H	H	H	
L_A 2191	Me	H	H	Me	H	H	H	
L_A 2192	Me	H	H	H	Me	H	H	
L_A 2193	Me	CD ₃	H	H	H	H	H	
L_A 2194	Me	H	CD ₃	H	H	H	H	
L_A 2195	Me	H	H	CD ₃	H	H	H	
L_A 2196	Me	H	H	H	CD ₃	H	H	
L_A 2197	Me	ⁱ Pr	H	H	H	H	H	
L_A 2198	Me	H	ⁱ Pr	H	H	H	H	
L_A 2199	Me	H	H	ⁱ Pr	H	H	H	
L_A 2200	Me	H	H	H	ⁱ Pr	H	H	
L_A 2201	Me	Ph	H	H	H	H	H	
L_A 2202	Me	H	Ph	H	H	H	H	
L_A 2203	Me	H	H	Ph	H	H	H	
L_A 2204	Me	H	H	H	Ph	H	H	
L_A 2205	CD ₃	Me	H	H	H	H	H	
L_A 2206	CD ₃	H	Me	H	H	H	H	
L_A 2207	CD ₃	H	H	Me	H	H	H	
L_A 2208	CD ₃	H	H	H	Me	H	H	
L_A 2209	CD ₃	CD ₃	H	H	H	H	H	
L_A 2210	CD ₃	H	CD ₃	H	H	H	H	
L_A 2211	CD ₃	H	H	CD ₃	H	H	H	
L_A 2212	CD ₃	H	H	H	CD ₃	H	H	
L_A 2213	CD ₃	ⁱ Pr	H	H	H	H	H	
L_A 2214	CD ₃	H	ⁱ Pr	H	H	H	H	
L_A 2215	CD ₃	H	H	ⁱ Pr	H	H	H	
L_A 2216	CD ₃	H	H	H	^p Pr	H	H	
L_A 2217	CD ₃	Ph	H	H	H	H	H	
L_A 2218	CD ₃	H	Ph	H	H	H	H	
L_A 2219	CD ₃	H	H	Ph	H	H	H	
L_A 2220	CD ₃	H	H	H	Ph	H	H	
L_A 2221	ⁱ Pr	Me	H	H	H	H	H	
L_A 2222	ⁱ Pr	H	Me	H	H	H	H	
L_A 2223	ⁱ Pr	H	H	Me	H	H	H	
L_A 2224	ⁱ Pr	H	H	H	Me	H	H	
L_A 2225	ⁱ Pr	CD ₃	H	H	H	H	H	
L_A 2226	ⁱ Pr	H	CD ₃	H	H	H	H	
L_A 2227	ⁱ Pr	H	H	CD ₃	H	H	H	
L_A 2228	ⁱ Pr	H	H	H	CD ₃	H	H	
L_A 2229	ⁱ Pr	ⁱ Pr	H	H	H	H	H	
L_A 2230	ⁱ Pr	H	ⁱ Pr	H	H	H	H	
L_A 2231	ⁱ Pr	H	H	ⁱ Pr	H	H	H	
L_A 2232	ⁱ Pr	H	H	H	ⁱ Pr	H	H	
L_A 2233	ⁱ Pr	Ph	H	H	H	H	H	
L_A 2234	ⁱ Pr	H	Ph	H	H	H	H	
L_A 2235	ⁱ Pr	H	H	Ph	H	H	H	
L_A 2236	ⁱ Pr	H	H	H	Ph	H	H	
L_A 2237	Ph	Me	H	H	H	H	H	
L_A 2238	Ph	H	Me	H	H	H	H	
L_A 2239	Ph	H	H	Me	H	H	H	
L_A 2240	Ph	H	H	H	Me	H	H	
L_A 2241	Ph	CD ₃	H	H	H	H	H	
L_A 2242	Ph	H	CD ₃	H	H	H	H	
L_A 2243	Ph	H	H	CD ₃	H	H	H	
L_A 2244	Ph	H	H	H	CD ₃	H	H	

60



-continued

L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_A 2245		Ph	ⁱ Pr	H	H	H	H	H
L_A 2246		Ph	H	ⁱ Pr	H	H	H	H
L_A 2247		Ph	H	H	ⁱ Pr	H	H	H
L_A 2248		Ph	H	H	H	ⁱ Pr	H	H
L_A 2249		Ph	Ph	H	H	H	H	H
L_A 2250		Ph	H	Ph	H	H	H	H
L_A 2251		Ph	H	H	Ph	H	H	H
L_A 2252		Ph	H	H	H	Ph	H	H
L_A 2253		H	Me	Me	H	H	H	H
L_A 2254		H	Me	H	Me	H	H	H
L_A 2255	H	Me	H	H	Me	H	H	
L_A 2256	H	Me	CD ₃	H	H	H	H	
L_A 2257	H	Me	H	CD ₃	H	H	H	
L_A 2258	H	Me	H	H	CD ₃	H	H	
L_A 2259	H	Me	ⁱ Pr	H	H	H	H	
L_A 2260	H	Me	H	ⁱ Pr	H	H	H	
L_A 2261	H	Me	H	H	^p Pr	H	H	
L_A 2262	H	Me	Ph	H	H	H	H	
L_A 2263	H	Me	H	Ph	H	H	H	
L_A 2264	H	Me	H	H	Ph	H	H	
L_A 2265	H	CD ₃	Me	H	H	H	H	
L_A 2266	H	CD ₃	H	Me	H	H	H	
L_A 2267	H	CD ₃	H	H	Me	H	H	
L_A 2268	H	CD ₃	CD ₃	H	H	H	H	
L_A 2269	H	CD ₃	H	CD ₃	H	H	H	
L_A 2270	H	CD ₃	H	H	CD ₃	H	H	
L_A 2271	H	CD ₃	ⁱ Pr	H	H	H	H	
L_A 2272	H	CD ₃	H	ⁱ Pr	H	H	H	
L_A 2273	H	CD ₃	H	H	^p Pr	H	H	
L_A 2274	H	CD ₃	Ph	H	H	H	H	
L_A 2275	H	CD ₃	H	Ph	H	H	H	
L_A 2276	H	CD ₃	H	H	Ph	H	H	
L_A 2277	H	ⁱ Pr	Me	H	H	H	H	
L_A 2278	H	ⁱ Pr	H	Me	H	H	H	
L_A 2279	H	ⁱ Pr	H	H	Me	H	H	
L_A 2280	H	ⁱ Pr	CD ₃	H	H	H	H	
L_A 2281	H	ⁱ Pr	H	CD ₃	H	H	H	
L_A 2282	H	ⁱ Pr	H	H	CD ₃	H	H	
L_A 2283	H	ⁱ Pr	ⁱ Pr	H	H	H	H	
L_A 2284	H	ⁱ Pr	H	ⁱ Pr	H	H	H	
L_A 2285	H	ⁱ Pr	H	H	^p Pr	H	H	
L_A 2286	H	ⁱ Pr	Ph	H	H	H	H	
L_A 2287	H	ⁱ Pr	H	Ph	H	H	H	
L_A 2288	H	ⁱ Pr	H	H	Ph	H	H	
L_A 2289	H	Ph	Me	H	H	H	H	
L_A 2290	H	Ph	H	Me	H	H	H	
L_A 2291	H	Ph	H	H	Me	H	H	
L_A 2292	H	Ph	CD ₃	H	H	H	H	
L_A 2293	H	Ph	H	CD ₃	H	H	H	
L_A 2294	H	Ph	H	H	CD ₃	H	H	
L_A 2295	H	Ph	ⁱ Pr	H	H	H	H	
L_A 2296	H	Ph	H	ⁱ Pr	H	H	H	
L_A 2297	H	Ph	H	H	ⁱ Pr	H	H	
L_A 2298	H	Ph	Ph	H	H	H	H	
L_A 2299	H	Ph	H	Ph	H	H	H	
L_A 2300	H	Ph	H	H	Ph	H	H	
L_A 2301	H	H	Me	Me	H	H	H	
L_A 2302	H	H	CD ₃	Me	H	H	H	
L_A 2303	H	H	ⁱ Pr	Me	H	H	H	
L_A 2304	H	H	Ph	Me	H	H	H	
L_A 2305	H	H	Me	CD ₃	H	H	H	
L_A 2306	H	H	CD ₃	CD ₃	H	H	H	
L_A 2307	H	H	ⁱ Pr	CD ₃	H	H	H	
L_A 2308	H	H	Ph	CD ₃	H	H	H	
L_A 2309	H	H	Me	ⁱ Pr	H	H	H	
L_A 2310	H	H	CD ₃	ⁱ Pr	H	H	H	
L_A 2311	H	H	ⁱ Pr	ⁱ Pr	H	H	H	
L_A 2312	H	H	Ph	ⁱ Pr	H	H	H	
L_A 2313	H	H	Me	Ph	H	H	H	
L_A 2314	H	H	CD ₃	Ph	H	H	H	
L_A 2315	H	H	ⁱ Pr	Ph	H	H	H	
L_A 2316	H	H	Ph	Ph	H	H	H	
L_A 2317	H	H	Me	H	Me	H	H	
L_A 2318	H	H	CD ₃	H	Me	H	H	
L_A 2319	H	H	ⁱ Pr	H	Me	H	H	
L_A 2320	H	H	Ph	H	Me	H	H	
L_A 2321	H	H	Me	H	CD ₃	H	H	

61

-continued



L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_A2322		H	H	CD_3	H	CD_3	H	H
L_A2323		H	H	iPr	H	CD_3	H	H
L_A2324		H	H	Ph	H	CD_3	H	H
L_A2325		H	H	Me	H	iPr	H	H
L_A2326		H	H	CD_3	H	iPr	H	H
L_A2327		H	H	iPr	H	iPr	H	H
L_A2328		H	H	Ph	H	iPr	H	H
L_A2329		H	H	Me	H	Ph	H	H
L_A2330		H	H	CD_3	H	Ph	H	H
L_A2331		H	H	iPr	H	Ph	H	H
L_A2332		H	H	Ph	H	Ph	H	H
L_A2333		Me	Me	H	Me	H	H	H
L_A2334		H	Me	Me	Me	H	H	H
L_A2335		CD_3	Me	H	Me	H	H	H
L_A2336		H	Me	CD_3	Me	H	H	H
L_A2337		iPr	Me	H	Me	H	H	H
L_A2338		H	Me	iPr	Me	H	H	H
L_A2339		Ph	Me	H	Me	H	H	H
L_A2340		H	Me	Ph	Me	H	H	H
L_A2341		Me	CD_3	H	CD_3	H	H	H
L_A2342		H	CD_3	Me	CD_3	H	H	H
L_A2343		CD_3	CD_3	H	CD_3	H	H	H
L_A2344		H	CD_3	CD_3	CD_3	H	H	H
L_A2345		iPr	CD_3	H	CD_3	H	H	H
L_A2346		H	CD_3	iPr	CD_3	H	H	H
L_A2347		Ph	CD_3	H	CD_3	H	H	H
L_A2348		H	CD_3	Ph	CD_3	H	H	H
L_A2349		Me	iPr	H	iPr	H	H	H
L_A2350		H	iPr	Me	iPr	H	H	H
L_A2351		CD_3	iPr	H	iPr	H	H	H
L_A2352		H	iPr	CD_3	iPr	H	H	H
L_A2353		iPr	iPr	H	iPr	H	H	H
L_A2354		H	iPr	iPr	iPr	H	H	H
L_A2355		Ph	iPr	H	iPr	H	H	H
L_A2356		H	iPr	Ph	iPr	H	H	H
L_A2357		Me	Ph	H	Ph	H	H	H
L_A2358		H	Ph	Me	Ph	H	H	H
L_A2359		CD_3	Ph	H	Ph	H	H	H
L_A2360		H	Ph	CD_3	Ph	H	H	H
L_A2361		iPr	Ph	H	Ph	H	H	H
L_A2362		H	Ph	iPr	Ph	H	H	H
L_A2363		Ph	Ph	H	Ph	H	H	H
L_A2364		H	Ph	Ph	Ph	H	H	H
L_A2365		H	H	H	H	H	H	H
L_A2366		Me	H	H	H	H	H	H
L_A2367		H	Me	H	H	H	H	H
L_A2368		H	H	Me	H	H	H	H
L_A2369		H	H	Me	H	H	H	H
L_A2370		H	H	H	H	Me	H	H
L_A2371		CD_3	H	H	H	H	H	H
L_A2372		H	CD_3	H	H	H	H	H
L_A2373		H	H	CD_3	H	H	H	H
L_A2374		H	H	H	CD_3	H	H	H
L_A2375		H	H	H	CD_3	H	H	H
L_A2376		iPr	H	H	H	H	H	H
L_A2377		H	iPr	H	H	H	H	H
L_A2378		H	H	iPr	H	H	H	H
L_A2379		H	H	H	iPr	H	H	H
L_A2380		H	H	H	H	iPr	H	H
L_A2381		Ph	H	H	H	H	H	H
L_A2382		H	Ph	H	H	H	H	H
L_A2383		H	H	Ph	H	H	H	H
L_A2384		H	H	H	Ph	H	H	H
L_A2385		H	H	H	H	Ph	H	H
L_A2386		Me	Me	H	H	H	H	H
L_A2387		Me	H	Me	H	H	H	H
L_A2388		Me	H	H	Me	H	H	H
L_A2389		Me	H	H	Me	H	H	H
L_A2390		Me	CD_3	H	H	H	H	H
L_A2391		Me	H	CD_3	H	H	H	H
L_A2392		Me	H	H	CD_3	H	H	H
L_A2393		Me	H	H	H	CD_3	H	H
L_A2394		Me	iPr	H	H	H	H	H
L_A2395		Me	H	iPr	H	H	H	H
L_A2396		Me	H	H	iPr	H	H	H
L_A2397		Me	H	H	H	iPr	H	H



62

-continued


L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_A2398		Me	Ph	H	H	H	H	H
L_A2399		Me	H	Ph	H	H	H	H
L_A2400		Me	H	H	Ph	H	H	H
L_A2401		Me	H	H	H	Ph	H	H
L_A2402		CD_3	Me	H	H	H	H	H
L_A2403		CD_3	H	Me	H	H	H	H
L_A2404		CD_3	H	H	Me	H	H	H
L_A2405		CD_3	H	H	H	Me	H	H
L_A2406		CD_3	CD_3	H	H	H	H	H
L_A2407		CD_3	H	CD_3	H	H	H	H
L_A2408		CD_3	H	H	CD_3	H	H	H
L_A2409		CD_3	H	H	H	CD_3	H	H
L_A2410		CD_3	iPr	H	H	H	H	H
L_A2411		CD_3	H	iPr	H	H	H	H
L_A2412		CD_3	H	H	iPr	H	H	H
L_A2413		CD_3	H	H	H	iPr	H	H
L_A2414		CD_3	Ph	H	H	H	H	H
L_A2415		CD_3	H	Ph	H	H	H	H
L_A2416		CD_3	H	H	Ph	H	H	H
L_A2417		CD_3	H	H	H	Ph	H	H
L_A2418		iPr	Me	H	H	H	H	H
L_A2419		iPr	H	Me	H	H	H	H
L_A2420		iPr	H	H	Me	H	H	H
L_A2421		iPr	H	H	H	Me	H	H
L_A2422		iPr	CD_3	H	H	H	H	H
L_A2423		iPr	H	CD_3	H	H	H	H
L_A2424		iPr	H	H	CD_3	H	H	H
L_A2425		iPr	H	H	H	CD_3	H	H
L_A2426		iPr	iPr	H	H	H	H	H
L_A2427		iPr	H	iPr	H	H	H	H
L_A2428		iPr	H	H	iPr	H	H	H
L_A2429		iPr	H	H	H	iPr	H	H
L_A2430		iPr	Ph	H	H	H	H	H
L_A2431		iPr	H	Ph	H	H	H	H
L_A2432		iPr	H	H	Ph	H	H	H
L_A2433		iPr	H	H	H	Ph	H	H
L_A2434		Ph	Me	H	H	H	H	H
L_A2435		Ph	H	Me	H	H	H	H
L_A2436		Ph	H	H	Me	H	H	H
L_A2437		Ph	H	H	H	Me	H	H
L_A2438		Ph	CD_3	H	H	H	H	H
L_A2439		Ph	H	CD_3	H	H	H	H
L_A2440		Ph	H	H	CD_3	H	H	H
L_A2441		Ph	H	H	H	CD_3	H	H
L_A2442		Ph	iPr	H	H	H	H	H
L_A2443		Ph	H	iPr	H	H	H	H
L_A2444		Ph	H	H	iPr	H	H	H
L_A2445		Ph	H	H	H	iPr	H	H
L_A2446		Ph	Ph	H	H	H	H	H
L_A2447		Ph	H	Ph	H	H	H	H
L_A2448		Ph	H	H	Ph	H	H	H
L_A2449		Ph	H	H	H	Ph	H	H
L_A2450		H	Me	Me	H	H	H	H
L_A2451		H	Me	H	Me	H	H	H
L_A2452		H	Me	H	H	Me	H	H
L_A2453		H	Me	CD_3	H	H	H	H
L_A2454		H	Me	H	CD_3	H	H	H
L_A2455		H	Me	H	H	CD_3	H	H
L_A2456		H	Me	iPr	H	H	H	H
L_A2457		H	Me	H	iPr	H	H	H
L_A2458		H	Me	H	H	iPr	H	H
L_A2459		H	Me	Ph	H	H	H	H
L_A2460		H	Me	H	Ph	H	H	H
L_A2461		H	Me	H	H	Ph	H	H
L_A2462		H	CD_3	Me	H	H	H	H
L_A2463		H	CD_3	H	Me	H	H	H
L_A2464		H	CD_3	H	H	Me	H	H
L_A2465		H	CD_3	CD_3	H	H	H	H
L_A2466		H	CD_3	H	CD_3	H	H	H
L_A2467		H	CD_3	H	H	CD_3	H	H
L_A2468		H	CD_3	iPr	H	H	H	H
L_A2469		H	CD_3	H	iPr	H	H	H
L_A2470		H	CD_3	H	H	iPr	H	H
L_A2471		H	CD_3	Ph	H	H	H	H
L_A2472		H	CD_3	H	Ph	H	H	H
L_A2473		H	CD_3	H	H	Ph	H	H



63

-continued



L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_A2474		H	iPr	Me	H	H	H	H
L_A2475		H	iPr	H	Me	H	H	H
L_A2476		H	iPr	H	H	Me	H	H
L_A2477		H	iPr	CD_3	H	H	H	H
L_A2478		H	iPr	H	CD_3	H	H	H
L_A2479		H	iPr	H	H	CD_3	H	H
L_A2480		H	iPr	iPr	H	H	H	H
L_A2481		H	iPr	H	iPr	H	H	H
L_A2482		H	iPr	H	H	iPr	H	H
L_A2483		H	iPr	Ph	H	H	H	H
L_A2484		H	iPr	H	Ph	H	H	H
L_A2485		H	iPr	H	H	Ph	H	H
L_A2486		H	Ph	Me	H	H	H	H
L_A2487		H	Ph	H	Me	H	H	H
L_A2488		H	Ph	H	H	Me	H	H
L_A2489		H	Ph	CD_3	H	H	H	H
L_A2490		H	Ph	H	CD_3	H	H	H
L_A2491		H	Ph	H	H	CD_3	H	H
L_A2492		H	Ph	iPr	H	H	H	H
L_A2493		H	Ph	H	iPr	H	H	H
L_A2494		H	Ph	H	H	iPr	H	H
L_A2495		H	Ph	Ph	H	H	H	H
L_A2496		H	Ph	H	Ph	H	H	H
L_A2497		H	Ph	H	H	Ph	H	H
L_A2498		H	H	Me	Me	H	H	H
L_A2499		H	H	CD_3	Me	H	H	H
L_A2500		H	H	iPr	Me	H	H	H
L_A2501		H	H	Ph	Me	H	H	H
L_A2502		H	H	Me	CD_3	H	H	H
L_A2503		H	H	CD_3	CD_3	H	H	H
L_A2504		H	H	iPr	CD_3	H	H	H
L_A2505		H	H	Ph	CD_3	H	H	H
L_A2506		H	H	Me	iPr	H	H	H
L_A2507		H	H	CD_3	iPr	H	H	H
L_A2508		H	H	H	iPr	H	H	H
L_A2509		H	H	Ph	iPr	H	H	H
L_A2510		H	H	Me	Ph	H	H	H
L_A2511		H	H	CD_3	Ph	H	H	H
L_A2512		H	H	iPr	Ph	H	H	H
L_A2513		H	H	Ph	Ph	H	H	H
L_A2514		H	H	Me	H	Me	H	H
L_A2515		H	H	CD_3	H	Me	H	H
L_A2516		H	H	iPr	H	Me	H	H
L_A2517		H	H	Ph	H	Me	H	H
L_A2518		H	H	Me	H	CD_3	H	H
L_A2519		H	H	CD_3	H	CD_3	H	H
L_A2520		H	H	iPr	H	CD_3	H	H
L_A2521		H	H	Ph	H	CD_3	H	H
L_A2522		H	H	Me	H	iPr	H	H
L_A2523		H	H	CD_3	H	iPr	H	H
L_A2524		H	H	iPr	H	iPr	H	H
L_A2525		H	H	Ph	H	iPr	H	H
L_A2526		H	H	Me	H	iPr	H	H
L_A2527		H	H	CD_3	H	Ph	H	H
L_A2528		H	H	iPr	H	Ph	H	H
L_A2529		H	H	Ph	H	Ph	H	H
L_A2530		Me	Me	H	Me	H	H	H
L_A2531		H	Me	Me	Me	H	H	H
L_A2532		CD_3	Me	H	Me	H	H	H
L_A2533		H	Me	CD_3	Me	H	H	H
L_A2534		iPr	Me	H	Me	H	H	H
L_A2535		H	Me	iPr	Me	H	H	H
L_A2536		Ph	Me	H	Me	H	H	H
L_A2537		H	Me	Ph	Me	H	H	H
L_A2538		Me	CD_3	H	CD_3	H	H	H
L_A2539		H	CD_3	Me	CD_3	H	H	H
L_A2540		CD_3	CD_3	H	CD_3	H	H	H
L_A2541		H	CD_3	CD_3	CD_3	H	H	H
L_A2542		iPr	CD_3	H	CD_3	H	H	H
L_A2543		H	CD_3	iPr	CD_3	H	H	H
L_A2544		Ph	CD_3	H	CD_3	H	H	H
L_A2545		H	CD_3	Ph	CD_3	H	H	H
L_A2546		Me	iPr	H	iPr	H	H	H
L_A2547		H	iPr	Me	iPr	H	H	H
L_A2548		CD_3	iPr	H	iPr	H	H	H
L_A2549		H	iPr	CD_3	iPr	H	H	H
L_A2550		iPr	iPr	H	iPr	H	H	H



64

-continued

L_A	Linker A	R^{1a}	R^{1b}	R^{1c}	R^{1d}	R^{1e}	R^{1f}	R^{1g}
L_A2551		H	iPr	iPr	iPr	H	H	H
L_A2552		Ph	iPr	H	iPr	H	H	H
L_A2553		H	iPr	Ph	iPr	H	H	H
L_A2554		Me	Ph	H	Ph	H	H	H
L_A2555		H	Ph	Me	Ph	H	H	H
L_A2556		CD_3	Ph	H	Ph	H	H	H
L_A2557		H	Ph	CD_3	Ph	H	H	H
L_A2558		iPr	Ph	H	Ph	H	H	H
L_A2559		H	Ph	iPr	Ph	H	H	H
L_A2560		Ph	Ph	H	Ph	H	H	H
L_A2561		H	Ph	Ph	Ph	H	H	H
L_A2562		H	H	H	H	H	H	H
L_A2563		Me	H	H	H	H	H	H
L_A2564		H	Me	H	H	H	H	H
L_A2565		H	H	Me	H	H	H	H
L_A2566		H	H	H	Me	H	H	H
L_A2567		H	H	H	H	Me	H	H
L_A2568		CD_3	H	H	H	H	H	H
L_A2569		H	CD_3	H	H	H	H	H
L_A2570		H	H	CD_3	H	H	H	H
L_A2571		H	H	H	CD_3	H	H	H
L_A2572		H	H	H	H	CD_3	H	H
L_A2573		iPr	H	H	H	H	H	H
L_A2574		H	iPr	H	H	H	H	H
L_A2575		H	H	iPr	H	H	H	H
L_A2576		H	H	H	iPr	H	H	H
L_A2577		H	H	H	H	iPr	H	H
L_A2578		Ph	H	H	H	H	H	H
L_A2579		H	Ph	H	H	H	H	H
L_A2580		H	H	Ph	H	H	H	H
L_A2581		H	H	H	Ph	H	H	H
L_A2582		H	H	H	Ph	H	H	H
L_A2583		Me	Me	H	H	H	H	H
L_A2584		Me	H	Me	H	H	H	H
L_A2585		Me	H	H	Me	H	H	H
L_A2586		Me	H	H	H	Me	H	H
L_A2587		Me	CD_3	H	H	H	H	H
L_A2588		Me	H	CD_3	H	H	H	H
L_A2589		Me	H	H	CD_3	H	H	H
L_A2590		Me	H	H	H	CD_3	H	H
L_A2591		Me	iPr	H	H	H	H	H
L_A2592		Me	H	iPr	H	H	H	H
L_A2593		Me	H	H	iPr	H	H	H
L_A2594		Me	H	H	H	iPr	H	H
L_A2595		Me	Ph	H	H	H	H	H
L_A2596		Me	H	Ph	H	H	H	H
L_A2597		Me	H	H	Ph	H	H	H
L_A2598		Me	H	H	H	Ph	H	H
L_A2599		CD_3	Me	H	H	H	H	H
L_A2600		CD_3	H	Me	H	H	H	H
L_A2601		CD_3	H	H	Me	H	H	H
L_A2602		CD_3	H	H	H	Me	H	H
L_A2603		CD_3	CD_3	H	H	H	H	H
L_A2604		CD_3	H	CD_3	H	H	H	H
L_A2605		CD_3	H	H	CD_3	H	H	H
L_A2606		CD_3	H	H	H	CD_3	H	H
L_A2607		CD_3	iPr	H	H	H	H	H
L_A2608		CD_3	H	iPr	H	H	H	H
L_A2609		CD_3	H	H	iPr	H	H	H
L_A2610		CD_3	H	H	H	iPr	H	H
L_A2611		CD_3	Ph	H	H	H	H	H
L_A2612		CD_3	H	Ph	H	H	H	H
L_A2613		CD_3	H	H	Ph	H	H	H
L_A2614		CD_3	H	H	H	Ph	H	H
L_A2615		iPr	Me	H	H	H	H	H
L_A2616		iPr	H	Me	H	H	H	H
L_A2617		iPr	H	H	Me	H	H	H
L_A2618		iPr	H	H	H	Me	H	H
L_A2619		iPr	CD_3	H	H	H	H	H
L_A2620		iPr	H	CD_3	H	H	H	H
L_A2621		iPr	H	H	CD_3	H	H	H
L_A2622		iPr	H	H	H	CD_3	H	H
L_A2623		iPr	iPr	H	H	H	H	H
L_A2624		iPr	H	iPr	H	H	H	H
L_A2625		iPr	H	H	iPr	H	H	H
L_A2626		iPr	H	H	H	iPr	H	H




-continued

L _A	Linker A	R ^{1a}	R ^{1b}	R ^{1c}	R ^{1d}	R ^{1e}	R ^{1f}	R ^{1g}
L _A 2627		ⁱ Pr	Ph	H	H	H	H	H
L _A 2628		ⁱ Pr	H	Ph	H	H	H	H
L _A 2629		ⁱ Pr	H	H	Ph	H	H	H
L _A 2630		ⁱ Pr	H	H	H	Ph	H	H
L _A 2631		Ph	Me	H	H	H	H	H
L _A 2632		Ph	H	Me	H	H	H	H
L _A 2633		Ph	H	H	Me	H	H	H
L _A 2634		Ph	H	H	H	Me	H	H
L _A 2635		Ph	CD ₃	H	H	H	H	H
L _A 2636		Ph	H	CD ₃	H	H	H	H
L _A 2637	Ph	H	H	CD ₃	H	H	H	
L _A 2638	Ph	H	H	H	CD ₃	H	H	
L _A 2639	Ph	ⁱ Pr	H	H	H	H	H	
L _A 2640	Ph	H	ⁱ Pr	H	H	H	H	
L _A 2641	Ph	H	H	ⁱ Pr	H	H	H	
L _A 2642	Ph	H	H	H	ⁱ Pr	H	H	
L _A 2643	Ph	Ph	H	H	H	H	H	
L _A 2644	Ph	H	Ph	H	H	H	H	
L _A 2645	Ph	H	H	Ph	H	H	H	
L _A 2646	Ph	H	H	H	Ph	H	H	
L _A 2647	H	Me	Me	H	H	H	H	
L _A 2648	H	Me	H	Me	H	H	H	
L _A 2649	H	Me	H	H	Me	H	H	
L _A 2650	H	Me	CD ₃	H	H	H	H	
L _A 2651	H	Me	H	CD ₃	H	H	H	
L _A 2652	H	Me	H	H	CD ₃	H	H	
L _A 2653	H	Me	ⁱ Pr	H	H	H	H	
L _A 2654	H	Me	H	ⁱ Pr	H	H	H	
L _A 2655	H	Me	H	H	ⁱ Pr	H	H	
L _A 2656	H	Me	Ph	H	H	H	H	
L _A 2657	H	Me	H	Ph	H	H	H	
L _A 2658	H	Me	H	H	Ph	H	H	
L _A 2659	H	CD ₃	Me	H	H	H	H	
L _A 2660	H	CD ₃	H	Me	H	H	H	
L _A 2661	H	CD ₃	H	H	Me	H	H	
L _A 2662	H	CD ₃	CD ₃	H	H	H	H	
L _A 2663	H	CD ₃	H	CD ₃	H	H	H	
L _A 2664	H	CD ₃	H	H	CD ₃	H	H	
L _A 2665	H	CD ₃	ⁱ Pr	H	H	H	H	
L _A 2666	H	CD ₃	H	ⁱ Pr	H	H	H	
L _A 2667	H	CD ₃	H	H	ⁱ Pr	H	H	
L _A 2668	H	CD ₃	Ph	H	H	H	H	
L _A 2669	H	CD ₃	H	Ph	H	H	H	
L _A 2670	H	CD ₃	H	H	Ph	H	H	
L _A 2671	H	ⁱ Pr	Me	H	H	H	H	
L _A 2672	H	ⁱ Pr	H	Me	H	H	H	
L _A 2673	H	ⁱ Pr	H	H	Me	H	H	
L _A 2674	H	ⁱ Pr	CD ₃	H	H	H	H	
L _A 2675	H	ⁱ Pr	H	CD ₃	H	H	H	
L _A 2676	H	ⁱ Pr	H	H	CD ₃	H	H	
L _A 2677	H	ⁱ Pr	ⁱ Pr	H	H	H	H	
L _A 2678	H	ⁱ Pr	H	ⁱ Pr	H	H	H	
L _A 2679	H	ⁱ Pr	H	H	ⁱ Pr	H	H	
L _A 2680	H	ⁱ Pr	Ph	H	H	H	H	
L _A 2681	H	ⁱ Pr	H	Ph	H	H	H	
L _A 2682	H	ⁱ Pr	H	H	Ph	H	H	
L _A 2683	H	Ph	Me	H	H	H	H	
L _A 2684	H	Ph	H	Me	H	H	H	
L _A 2685	H	Ph	H	H	Me	H	H	
L _A 2686	H	Ph	CD ₃	H	H	H	H	
L _A 2687	H	Ph	H	CD ₃	H	H	H	
L _A 2688	H	Ph	H	H	CD ₃	H	H	
L _A 2689	H	Ph	ⁱ Pr	H	H	H	H	
L _A 2690	H	Ph	H	ⁱ Pr	H	H	H	
L _A 2691	H	Ph	H	H	ⁱ Pr	H	H	
L _A 2692	H	Ph	Ph	H	H	H	H	
L _A 2693	H	Ph	H	Ph	H	H	H	
L _A 2694	H	Ph	H	H	Ph	H	H	
L _A 2695	H	H	Me	Me	H	H	H	
L _A 2696	H	H	CD ₃	Me	H	H	H	
L _A 2697	H	H	ⁱ Pr	Me	H	H	H	
L _A 2698	H	H	Ph	Me	H	H	H	
L _A 2699	H	H	Me	CD ₃	H	H	H	
L _A 2700	H	H	CD ₃	CD ₃	H	H	H	
L _A 2701	H	H	ⁱ Pr	CD ₃	H	H	H	
L _A 2702	H	H	Ph	CD ₃	H	H	H	

-continued


L _A	Linker A	R ^{1a}	R ^{1b}	R ^{1c}	R ^{1d}	R ^{1e}	R ^{1f}	R ^{1g}
L _A 2703		H	H	Me	ⁱ Pr	H	H	H
L _A 2704		H	H	CD ₃	ⁱ Pr	H	H	H
L _A 2705		H	H	ⁱ Pr	ⁱ Pr	H	H	H
L _A 2706		H	H	Ph	ⁱ Pr	H	H	H
L _A 2707		H	H	Me	Ph	H	H	H
L _A 2708		H	H	CD ₃	Ph	H	H	H
L _A 2709		H	H	ⁱ Pr	Ph	H	H	H
L _A 2710		H	H	Ph	Ph	H	H	H
L _A 2711		H	H	Me	H	Me	H	H
L _A 2712		H	H	CD ₃	H	Me	H	H
L _A 2713	H	H	ⁱ Pr	H	Me	H	H	
L _A 2714	H	H	Ph	H	Me	H	H	
L _A 2715	H	H	Me	H	CD ₃	H	H	
L _A 2716	H	H	CD ₃	H	CD ₃	H	H	
L _A 2717	H	H	ⁱ Pr	H	CD ₃	H	H	
L _A 2718	H	H	Ph	H	CD ₃	H	H	
L _A 2719	H	H	Me	H	ⁱ Pr	H	H	
L _A 2720	H	H	CD ₃	H	ⁱ Pr	H	H	
L _A 2721	H	H	ⁱ Pr	H	ⁱ Pr	H	H	
L _A 2722	H	H	Ph	H	ⁱ Pr	H	H	
L _A 2723	H	H	Me	H	Ph	H	H	
L _A 2724	H	H	CD ₃	H	Ph	H	H	
L _A 2725	H	H	ⁱ Pr	H	Ph	H	H	
L _A 2726	H	H	Ph	H	Ph	H	H	
L _A 2727	Me	Me	H	Me	H	H	H	
L _A 2728	H	Me	Me	Me	H	H	H	
L _A 2729	CD ₃	Me	H	Me	H	H	H	
L _A 2730	H	Me	CD ₃	Me	H	H	H	
L _A 2731	ⁱ Pr	Me	H	Me	H	H	H	
L _A 2732	H	Me	ⁱ Pr	Me	H	H	H	
L _A 2733	Ph	Me	H	Me	H	H	H	
L _A 2734	H	Me	Ph	Me	H	H	H	
L _A 2735	Me	CD ₃	H	CD ₃	H	H	H	
L _A 2736	H	CD ₃	Me	CD ₃	H	H	H	
L _A 2737	CD ₃	CD ₃	H	CD ₃	H	H	H	
L _A 2738	H	CD ₃	CD ₃	CD ₃	H	H	H	
L _A 2739	ⁱ Pr	CD ₃	H	CD ₃	H	H	H	
L _A 2740	H	CD ₃	iPr	CD ₃	H	H	H	
L _A 2741	Ph	CD ₃	H	CD ₃	H	H	H	
L _A 2742	H	CD ₃	Ph	CD ₃	H	H	H	
L _A 2743	Me	ⁱ Pr	H	ⁱ Pr	H	H	H	
L _A 2744	H	ⁱ Pr	Me	ⁱ Pr	H	H	H	
L _A 2745	CD ₃	ⁱ Pr	H	ⁱ Pr	H	H	H	
L _A 2746	H	ⁱ Pr	CD ₃	ⁱ Pr	H	H	H	
L _A 2747	ⁱ Pr	ⁱ Pr	H	ⁱ Pr	H	H	H	
L _A 2748	H	ⁱ Pr	iPr	ⁱ Pr	H	H	H	
L _A 2749	Ph	ⁱ Pr	H	ⁱ Pr	H	H	H	
L _A 2750	H	ⁱ Pr	Ph	ⁱ Pr	H	H	H	
L _A 2751	Me	Ph	H	Ph	H	H	H	
L _A 2752	H	Ph	Me	Ph	H	H	H	
L _A 2753	CD ₃	Ph	H	Ph	H	H	H	
L _A 2754	H	Ph	CD ₃	Ph	H	H	H	
L _A 2755	ⁱ Pr	Ph	H	Ph	H	H	H	
L _A 2756	H	Ph	ⁱ Pr	Ph	H	H	H	
L _A 2757	Ph	Ph	H	Ph	H	H	H	
L _A 2758	H	Ph	Ph	Ph	H	H	H	

In some embodiments of the compound of Formula 1, the ligand L is selected from the group consisting of:




67

-continued



68

-continued



wherein each X^1 to X^{13} are independently selected from the group consisting of carbon and nitrogen;

wherein X is selected from the group consisting of BR', NR', PR', O, S, Se, C=O, S=O, SO₂, CR'R'', SiR'R'', and GeR'R'';

wherein R' and R'' are optionally fused or joined to form a ring;




wherein each R_a , R_b , R_c , and R_d may represent from mono substitution to the possible maximum number of substitution, or no substitution;

69


wherein R', R'', R_a, R_b, R_c, and R_d are each independently selected from the group consisting of hydrogen, deuterium, halide, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acids, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof; and

wherein any two adjacent substituents of R_a, R_b, R_c, and R_d are optionally fused or joined to form a ring or form a multidentate ligand.

In some embodiments of the compound of Formula 1, the ligand L is selected from the group consisting of:





and



wherein R_a and R_b are as defined above.


In some embodiments of the compound of Formula 1, the ligand L is selected from the group consisting of:




wherein R_a and R_b are as defined above.

In some embodiments of the compound of Formula 1, the ligand L is selected from the group consisting of:

55



60




65


70

-continued

5



10



15

20


25

30


35

40

45








and




71

-continued




72

-continued








wherein R_a , R_b , and R_c are as defined above.

In some embodiments of the compound of Formula 1, ligand L is selected from the group consisting of:



73

-continued



74

-continued

L₅

5

10

L₆

15

20

L₇

25

30

35

L₈

40

45







50

L₉

55

60

65



L₁₀

L₁₁

L₁₂






L₁₃

L₁₄

L₁₅

75

-continued



76

-continued

L16

5

10

15

L17

20

25

L18

30

35

L19

45

50

L20

60

65






L21

L22

L23







L24

L25



77

-continued




78

-continued

L₂₆


5



L₃₂

L₂₇


15



L₃₃

L₂₈


20



L₃₄

L₂₉


35



L₃₅

L₃₀


45



L₃₆

L₃₁


60



L₃₇

65

79
-continued



L₃₈

5

10

L₃₉

15

20

25

30

In some embodiments of the compound of Formula 1, the compound is (L_A)₃Ir, wherein L_A is as defined above.


In some embodiments of the compound of Formula 1, the compound is (L_A)Ir(L)₂ or (L_A)₂Ir(L), wherein L_A and L are as defined above.

In some embodiments of the compound of Formula 1, where L_A is as defined above, the compound is Compound Ax having the formula Ir(L_{Ai})₃; wherein x=i, i is an integer from 1 to 2758.

In some embodiments of the compound of Formula 1, where L_A is as defined above, the compound is Compound By having the formula Ir(L_{Ai})(L_j)₂ or Compound Cz having the formula Ir(L_{Ai})₂(L_j);

wherein y=39i+j-39, i is an integer from 1 to 2758, and j is an integer from 1 to 39;

wherein z=39i+j-39, i is an integer from 1 to 2758, and j is an integer from 1 to 39; and wherein L₁ to L₃₉ have the following structure:



L₁


55

L₂


60

65


80
-continued




L₃




L₄




L₅



L₆









L₇



L₈

81

-continued



82

-continued

L₉

5

10

L₁₀

15

20

L₁₁

25

30

L₁₂

35

40

L₁₃

45

50

L₁₄

55

60

65






L₁₅

L₁₆

L₁₇






L₁₈

L₁₉



83

-continued



84

-continued

L₂₀

5

10

L₂₁

20

25

L₂₂

30

35

L₂₃

45

50

55

L₂₄

60

65

L₂₅







L₂₆

L₂₇

L₂₈







L₂₉

L₃₀



85

-continued



86

-continued

L₃₁

5

10

L₃₂ 15

20

L₃₃

25

30

L₃₄

35

40

L₃₅

50

55

L₃₆

60

65




L₃₇

L₃₈



L₃₉

Compound 1

Compound 2




In some embodiments of the compound of Formula 1, the compound is selected from the group consisting of:



87

-continued




Compound 3

5

88

-continued




Compound 7

10

Compound 4

15




Compound 8

20


Compound 5

35




Compound 9

30



Compound 10


40



45


Compound 6

55




Compound 11

60








65



89

-continued



90

-continued

Compound 12

5

10

Compound 13

20

Compound 14

35

40

Compound 15

45






50

55

Compound 16

60

65



Compound 17

Compound 18







Compound 19

Compound 20

Compound 21

91

-continued



92

-continued

Compound 22

5

Compound 23

10

Compound 24

15

Compound 25

20

Compound 26

25


Compound 27

30


35

40


45




Compound 28




Compound 29




Compound 30



Compound 31




Compound 32



Compound 33

93


-continued



5

10


Compound 35



15


20

Compound 36



30


Compound 37



40

45


Compound 38



50

55

Compound 39




60

65

94


-continued

Compound 34




Compound 40

Compound 35




Compound 41

Compound 36




Compound 42

Compound 37




Compound 43

Compound 38








Compound 44

Compound 39



95


-continued



96


-continued

Compound 45




Compound 50

Compound 46




Compound 51

Compound 47




Compound 52

Compound 48




Compound 53

Compound 49




Compound 54

97
-continued




Compound 55

5




Compound 56

15



Compound 57


25



Compound 58


35

98
-continued




Compound 60

10




Compound 61

20



Compound 62

30



Compound 63

40

50

55







60

65

m

99

-continued




100

-continued

Compound 64


5



10

Compound 65


15



20

Compound 66


25



30

Compound 67


35



40

Compound 68


45



50


Compound 69

55



60

65



Compound 70

Compound 71


Compound 72

Compound 73

Compound 74

101

-continued




Compound 75

5

10

Compound 76




Compound 77

15

20


25



Compound 78

30


35



Compound 79

40

45



Compound 80


55

60


65

102


-continued




Compound 81




Compound 82



Compound 83









Compound 84



Compound 85

103

-continued



104

-continued

Compound 86

5

10

Compound 87

15

20

Compound 88

25

Compound 89

35

40

Compound 90

45







50

55

Compound 91

60

65



Compound 92

Compound 93


Compound 94

Compound 95


Compound 96

105


-continued



Compound 97

and
Compound 98

In some embodiments of the compound of Formula 1, the compound has a structure of Formula 2:



Formula 2

wherein M is Pt;

wherein A¹ and A² are each independently a first linking group having two to three linking atoms, wherein the linking atoms are each independently selected from the group consisting of C, Si, O, S, N, B or combinations thereof;

wherein R^{1b} to R^{1f} and R^{2b} to R^{2f} are each independently selected from the group consisting of hydrogen, deuterium, alkyl, cycloalkyl, heteroalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aralkyl, CN, CF₃, CO₂R, C(O)R, C(O)NR₂, NR₂, NO₂, OR, SR, SO₂, SOR, SO₃R, halo, aryl, heteroaryl, a heterocyclic group, and combinations thereof;

wherein each R is independently selected from the group consisting of hydrogen, deuterium, halo, alkyl, cycloalkyl, heteroalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aralkyl, aryl, heteroaryl, and combinations thereof;

wherein any one of the ring atoms to which R^{1b} to R^{1f} and R^{2b} to R^{2f} are attached may be replaced with a nitrogen atom, wherein when the ring atom is replaced with a nitrogen atom the corresponding R group is not present; and

wherein R^{ab} and R^{ac} and/or R^{ga} and R^{gb} may bond to form a second linking group having one to three linking atoms

106


each independently selected from the group consisting of B, N, P, O, S, Se, C, Si, Ge or combinations thereof.

In some embodiments of the compound of Formula 2, each of the first linking groups A¹ and A² is independently selected from the group consisting of —CR¹R²—CR³R⁴—, —CR¹R²—CR³R⁴—CR⁵R⁶—, —CR¹R²—NR³—, —CR¹—CR²—CR³R⁴—, —O—SiR¹R²—, —CR¹R²—S—, —CR¹R²—O—, and —C—SiR¹R²—, wherein each RI to R⁶ can be same or different, and are independently selected from the group consisting of hydrogen, deuterium, alkyl, cycloalkyl, aryl, heteroaryl, and combinations thereof; and wherein any adjacent R¹ to R⁶ are optionally connected to form a saturated five membered ring or a saturated six membered ring.

In some embodiments of the compound of Formula 2, the compound has a triplet excited state and wherein the linking group stabilizes the bond between N² and C^{1b} from cleavage when the compound is in the triplet excited state.


In some embodiments of the compound of Formula 2, the compound has a peak emissive wavelength less than 500 nm. In some embodiments, the compound has a peak emissive wavelength less than 480 nm. In some embodiments, the compound has a peak emissive wavelength ranging from 400 nm to 500 nm.

In some embodiments of the compound of Formula 2, each of the first linking groups A¹ and A² is independently selected from the Linker Group consisting of:




107

-continued




108

-continued



109


-continued



In some embodiments of the compound of Formula 2, the second linking group is independently selected from the group consisting of: BR', NR', PR', O, S, Se, C=O, S=O, SO₂, CR¹R², —CR¹R²—CR³R⁴—, —CR¹R²—CR³R⁴—CR⁵R⁶—, —CR¹R²—NR³—, —CR¹—CR²—CR³R⁴—, —O—SiR¹R²—, —CR¹R²—S—, —CR¹R²—O—, —C—SiR¹R²—, SiR¹R², and GeR¹R², wherein each R¹ to R⁶ can be same or different, and are independently selected from the group consisting of hydrogen, deuterium, alkyl, cycloalkyl, alkenyl, alkenyl, alkynyl, heteroalkyl, aralkyl, aryl, heteroaryl, and combinations thereof; and wherein any adjacent R¹ to R⁶ are optionally connected to form a saturated five membered ring or a saturated six membered ring.


In some embodiments of the compound of Formula 2, the compound is selected from the group consisting of:

Compound 99



and


Compound 100



110

In some embodiments of the compound of Formula 1, the compound has Formula 3:

Formula 3



wherein M is Pt;

wherein L² and L³ are each independently selected from the group consisting of a single bond, BR, NR, PR, O, S, Se, C—O, S—O, SO₂, CR¹R², SiR¹R², and GeR¹R²;

wherein R^{3a} to R^{3f}, are each independently selected from the group consisting of hydrogen, deuterium, alkyl, cycloalkyl, heteroalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aralkyl, CN, CF₃, CO₂R, C(O)R, C(O)NR₂, NR₂, NO₂, OR, SR, SO₂, SOR, SO₃R, halo, aryl, heteroaryl, a heterocyclic group, and combinations thereof;

wherein each R is independently selected from the group consisting of hydrogen, deuterium, halo, alkyl, cycloalkyl, heteroalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aralkyl, aryl, heteroaryl, and combinations thereof;


wherein any two adjacent R^{1f}, R^{3a}, R^{3c}, R^{3d}, R¹ and R² are optionally joined to form a ring; wherein L² and R^{1f}, L² and R^{3a}, or L² and both R^{1f} and R^{3a} are optionally joined to form one or more rings; and

wherein L³ and R^{3c}, L³ and R^{3d}, or L³ and both R^{3c} and R^{3d} are optionally joined to form one or more rings.

In some embodiments of the compound of Formula 3, L² and L³ are each independently selected from the group consisting of BR', NR', PR', O, S, Se, C=O, S=O, SO₂, CR¹R², SiR¹R², and GeR¹R². In some embodiments of the compound of Formula 3, R¹ or R^{3a} and R¹ or R² are joined to form a ring. In some embodiments of the compound of Formula 3, R^{3c} or R^{3d} and R¹ or R² are joined to form a ring.


In some embodiments of the compound of Formula 3, the compound is selected from the group consisting of:

Compound 101




111


-continued




Compound 102




Compound 103



Compound 104



Compound 105



Compound 106

According to another aspect of the present disclosure, an organic light emitting device (OLED) is disclosed. The OLED comprises an anode; a cathode; and an organic layer

112

disposed between the anode and the cathode, wherein the organic layer comprising a compound having a structure $(L_A)_nML_m$ according to Formula 1:

5

Formula 1

10

15

20

25

30

35


40

45

50

55

60



wherein M is a metal having an atomic weight greater than 40, n has a value of at least 1 and m+n is the maximum number of ligands that may be attached to the metal;

wherein A is a linking group having two to three linking atoms, wherein the linking atoms are each independently selected from the group consisting of C, Si, O, S, N, B or combinations thereof;

wherein the linking atoms form at least one single bond between two linking atoms; wherein R^{1a} to R^{1g} are each independently selected from the group consisting of hydrogen, deuterium, alkyl, cycloalkyl, heteroalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aralkyl, CN, CF_3 , CO_2R , $C(O)R$, $C(O)NR_2$, NR_2 , NO_2 , OR, SR, SO_2 , SOR, SO_3R , halo, aryl, heteroaryl, a heterocyclic group, and combinations thereof;

wherein each R is independently selected from the group consisting of hydrogen, deuterium, halo, alkyl, cycloalkyl, heteroalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aralkyl, aryl, heteroaryl, and combinations thereof;

wherein any one of the ring atoms to which R^{1b} to R^{1g} are attached may be replaced with a nitrogen atom, wherein when the ring atom is replaced with a nitrogen atom the corresponding R group is not present; and

wherein L is a substituted or unsubstituted cyclometalated ligand.

In some embodiments of the OLED, the OLED is incorporated into a device selected from the group consisting of a consumer product, an electronic component module, and a lighting panel.

In some embodiments of the OLED, the organic layer is an emissive layer and the compound is an emissive dopant or a non-emissive dopant.

In some embodiments of the OLED, the organic layer further comprises a host, wherein the host comprises a triphenylene containing benzo-fused thiophene or benzo-fused furan;

wherein any substituent in the host is an unfused substituent independently selected from the group consisting of C_nH_{2n+1} , OC_nH_{2n+1} , OAr_1 , $N(C_nH_{2n+1})_2$, $N(Ar_1)(Ar_2)$, $CH=CH-C_nH_{2n+1}$, $C\equiv CC_nH_{2n+1}$, Ar_1 , Ar_1-Ar_2 , $C_nH_{2n-Ar_1}$, or no substitution;


wherein n is from 1 to 10; and

wherein Ar_1 and Ar_2 are independently selected from the group consisting of benzene, biphenyl, naphthalene, triphenylene, carbazole, and heteroaromatic analogs thereof.

113


In some embodiments of the OLED, the organic layer further comprises a host, wherein host comprises at least one chemical group selected from the group consisting of triphenylene, carbazole, dibenzothiophene, dibenzofuran, dibenzoselenophene, azatriphenylene, azacarbazole, azacarbazole, aza-dibenzothiophene, aza-dibenzofuran, and aza-dibenzoselenophene.

In some embodiments of the OLED, the organic layer further comprises a host, wherein the host is selected from the group consisting of:









114

-continued











115

-continued



116

-continued




55 and combinations thereof.

In some embodiments of the OLED, the organic layer further comprises a host, wherein the host comprises a metal complex.

60 According to another aspect of the present disclosure, a formulation comprising a compound of Formula 1 is also disclosed. The formulation can include one or more components selected from the group consisting of a solvent, a host, a hole injection material, hole transport material, and an electron transport layer material, disclosed herein.

65 According to another aspect of the present disclosure, a compound having Formula (1a) shown below is disclosed.

117



In Formula (1a), A is a linking group having two to three linking atoms, wherein the linking atoms are each independently selected from the group consisting of C, Si, O, S, N, B or combinations thereof;

wherein R^{ab} , R^{ga} , R^{1b} to R^{1f} are each independently selected from the group consisting of hydrogen, deuterium, alkyl, cycloalkyl, heteroalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aralkyl, CN, CF_3 , CO_2R , $C(O)R$, $C(O)NR_2$, NR_2 , NO_2 , OR, SR, SO_2 , SOR, SO_3R , halo, aryl, heteroaryl, a heterocyclic group, and combinations thereof;

wherein each R is independently selected from the group consisting of hydrogen, deuterium, halo, alkyl, cycloalkyl, heteroalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aralkyl, aryl, heteroaryl, and combinations thereof; and


wherein any one of the ring atoms to which R^{ab} , R^{ga} , R^{1b} to R^{1f} are attached may be replaced with a nitrogen atom, wherein when the ring atom is replaced with a nitrogen atom the corresponding R group is not present.

In some embodiments of the compound of Formula 1a, the linking group A is independently selected from the group consisting of $-CR^1R^2-CR^3R^4-$, $-CR^1R^2-CR^3R^4-CR^5R^6-$, $-CR^1R^2-NR^3-$, $-CR^1-CR^2-CR^3R^4-$, $-O-SiR^1R^2-$, $-CR^1R^2-S-$, $-CR^1R^2-O-$, and $-C-SiR^1R^2-$, wherein each R^1 to R^6 can be same or different, and are independently selected from the group consisting of hydrogen, deuterium, alkyl, cycloalkyl, aryl, heteroaryl, and combinations thereof; wherein any adjacent R^1 to R^6 are optionally connected to form a saturated five membered ring or a saturated six membered ring.

In some embodiments of the compound of Formula (1a), the compound has a triplet excited state and wherein the linking group stabilizes the bond between N^2 and C^{1b} from cleavage when the compound is in the triplet excited state.

In some embodiments of the compound of Formula (1a), the linking group A is selected from the Linker Group defined above.

In some embodiments of the compound of Formula (1a), the compound is selected from the group consisting of.



Compound (1-1)

5

10

15

20

25

30

35

40

45

50

55

60


65

118


-continued

Formula (1a)


Compound (1-2)




Compound (1-3)




Compound (1-4)



Compound (1-5)








Compound (1-6)



119

-continued




120

-continued

Compound (1-7)

5




10

15

Compound (1-8)

20

25




Compound (1-9)

30

35

40




Compound (1-10)

45

50


55



Compound (1-11)

60

65



Compound (1-12)

Compound (1-13)







Compound (1-14)

Compound (1-15)

Compound (1-16)

121

-continued



122

-continued

Compound (1-17)

5

10

Compound (1-18)

15

20

Compound (1-19)

25

30

Compound (1-20)

35

Compound (1-21)

40

Compound (1-22)

45






50

55

Compound (1-22)

60

65



Compound (1-23)

Compound (1-24)







Compound (1-25)

Compound (1-26)

Compound (1-27)

123

-continued



Compound (1-28)

5

Compound (1-29)

15

Compound (1-30)

25

Compound (1-31)

35

Compound (1-32)

45







Compound (1-33)

60

65

124

-continued



Compound (1-34)

Compound (1-35)

Compound (1-36)





Compound (1-37)

Compound (1-38)

Compound (1-39)

125

-continued



Compound (1-40)

5

10

15

Compound (1-41)

20

25

30

Compound (1-42)

35

40

45

Compound (1-43)

50







55

60

65

126

-continued



Compound (1-44)

Compound (1-45)

Compound (1-46)







Compound (1-47)

Compound (1-48)

Compound (1-49)

127

-continued




128

-continued

Compound (1-50)

5




Compound (1-56)

10

Compound (1-51)

20




Compound (1-57)

25

Compound (1-52)

30



Compound (1-58)

35

Compound (1-53)


40

Compound (1-59)

45

Compound (1-54)

50




55

Compound (1-55)

60







Compound (1-60)

65



129

-continued



130

-continued

Compound (1-61)

5

10

15

Compound (1-62)

20

25

Compound (1-63)

30

35

Compound (1-64)

40

45

Compound (1-65)


50

55

Compound (1-66)


60

65




Compound (1-67)


Compound (1-68)




Compound (1-69)



Compound (1-70)








Compound (1-71)



131

-continued



132

-continued

Compound (1-72)

5

10

Compound (1-73)

15

20

Compound (1-74)

25

30

35

Compound (1-75)

40

45






50

Compound (1-76)

55

60

65



Compound (1-77)

Compound (1-78)


Compound (1-79)

Compound (1-80)

Compound (1-81)

133


-continued



Compound (1-82)


5

Compound (1-83)




15

Compound (1-84)




25

Compound (1-85)



40

Compound (1-86)




55

60

65

134


-continued



Compound (1-87)


10

Compound (1-88)



20


Compound (1-89)



30

35


Compound (1-90)



45


50

Compound (1-91)




135

-continued




Compound (1-92)

5




Compound (1-93)

15




Compound (1-94)

25



Compound (1-95)

40



Compound (1-96)


55

60


65

136

-continued




Compound (1-97)



Compound (1-98)


20



Compound (1-99)

30

35




Compound (1-100)

45





50

Compound (1-101)



137

-continued



138

-continued

Compound (1-102)

5

10

15

Compound (1-103)

20

25

Compound (1-104)

30

35

40

Compound (1-105)






45

50

55

60

65



Compound (1-106)

Compound (1-107)







Compound (1-108)

Compound (1-109)

Compound (1-110)

139

-continued



140

-continued

Compound (1-111)

5

10

Compound (1-112)

15

20

25

Compound (1-113)

30

35

Compound (1-115)

40

45

Compound (1-116)







50

55

Compound (117)

60

65



Compound (1-118)

Compound (1-119)

Compound (1-120)







Compound (1-121)

Compound (1-122)

Compound (1-123)

141

-continued



142

-continued

Compound (1-124)

5

10

Compound (1-125)

15

20

Compound (1-126)

25

30

35

Compound (1-127)

40

45

Compound (1-128)







50

55

Compound (1-130)

60

65



Compound (1-131)

Compound (1-132)

Compound (1-133)


Compound (1-134)

Compound (1-135)

Compound (1-136)

143


-continued



Compound (1-137)


5

Compound (1-138)




15

Compound (1-139)




25

Compound (1-140)



40

Compound (1-141)




55

60

65

144


-continued



Compound (1-142)


10

Compound (1-143)



20


Compound (1-144)



30

35

Compound (1-145)




40

45






50

Compound (1-146)



145

-continued




146

-continued

Compound (1-147)

5




Compound (1-148)

15

Compound (1-149)

25




Compound (1-152)

Compound (1-153)

20

30



Compound (1-154)


35

Compound (1-150)

40

Compound (1-155)

45




50

Compound (1-151)

55

Compound (1-156)






60



65

147

-continued



148

-continued

Compound (1-157)

5

10

Compound (1-158)

15

20

25

Compound (1-159)

30

35

40

Compound (1-160)

45







50

55

Compound (1-161)

60

65



Compound (1-162)

Compound (1-163)

Compound (1-164)






Compound (1-165)

Compound (1-166)

Compound (1-167)

149

-continued




150

-continued

Compound (1-168)


5



10

Compound (1-169)


15



20

Compound (1-170)


25



30


Compound (1-171)

40



35

45




50

55

Compound (1-172)

60



65

Compound (1-173)

Compound (1-174)

Compound (1-175)


Compound (1-176)

Compound (1-177)


Compound (1-178)

151


-continued



Compound (1-179)




Compound (1-180)




Compound (1-181)

In some embodiments of the compound having Formula (1a), the compound has the structure of Formula (2a) and Formula (2b) tethered together as defined below:



Formula (2a)



Formula (2b)

wherein A¹ and A² are each a first linking group having two to three linking atoms, wherein the linking atoms are each independently selected from the group consisting of C, Si, O, S, N, B and combinations thereof, and

152

wherein R^{ac}, R^{gb}, and R^{2b} to R^{2f} are each independently selected from the group consisting of hydrogen, deuterium, alkyl, cycloalkyl, heteroalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aralkyl, CN, CF₃, CO₂R, C(O)R, C(O)NR₂, NR₂, NO₂, OR, SR, SO₂, SOR, SO₃R, halo, aryl, heteroaryl, a heterocyclic group, and combinations thereof;

wherein the compound is tethered together via at least one second linking group formed between R^{ab} and R^{ac} and/or R^{ga} and R^{gb}, wherein at least one second linking group has one to three linking atoms and each linking atom is independently selected from the group consisting of B, N, P, O, S, Se, C, Si, Ge and combinations thereof; and any one of the ring atoms to which R^{1b} to R^{1f} and R^{2b} to R^{2f} are attached may be replaced with a nitrogen atom, wherein when the ring atom is replaced with a nitrogen atom the corresponding R group is not present.

In some embodiments of the compound having the structure of Formula (2a) and Formula (2b) tethered together as defined above, the at least one second linking group is formed between R^{ab} and R^{ac}.

In some embodiments of the compound having the structure of Formula (2a) and Formula (2b) tethered together as defined above, the at least one second linking group is formed between R^{ga} and R^{gb}.

In some embodiments of the compound having the structure of Formula (2a) and Formula (2b) tethered together as defined above, the at least one second linking group are formed between R^{ga} and R^{gb} and R^{ab} and R^{ac}.

In some embodiments of the compound having the structure of Formula (2a) and Formula (2b) tethered together as defined above, each of the first linking groups A¹ and A² is independently selected from the group consisting of —CR¹R²—CR³R⁴—, —CR¹R²—CR³R⁴—CR⁵R⁶—, —CR¹R²—NR³—, —CR¹—CR²—CR³R⁴—, —O—SiR¹R²—, —CR¹R²—S—, —CR¹R²—O—, and —C—SiR¹R²—, wherein each R¹ to R⁶ can be same or different, and are independently selected from the group consisting of hydrogen, deuterium, alkyl, cycloalkyl, aryl, heteroaryl, and combinations thereof;

wherein any adjacent R¹ to R⁶ are optionally connected to form a saturated five membered ring or a saturated six membered ring.


In some embodiments of the compound having the structure of Formula (2a) and Formula (2b) tethered together as defined above, each of the first linking groups A¹ and A² is independently selected from the Linker Group defined above.

In some embodiments of the compound having the structure of Formula (2a) and Formula (2b) tethered together as defined above, the second linking group is independently selected from the group consisting of BR¹, NR¹, PR¹, O, S, Se, C=O, S=O, SO₂, CR¹R², —CR¹R²—CR³R⁴—, —CR¹R²—CR³R⁴—CR⁵R⁶—, —CR¹R²—NR³—, —CR¹—CR²—CR³R⁴—, —O—SiR¹R²—, —CR¹R²—S—, —CR¹R²—, —C—SiR¹R²—, SiR¹R², and GeR¹R², wherein each R¹ to R⁶ can be same or different, and are independently selected from the group consisting of hydrogen, deuterium, alkyl, cycloalkyl, aryl, heteroaryl, and combinations thereof; wherein any adjacent R¹ to R⁶ are optionally connected to form a saturated five membered ring or a saturated six membered ring.


In some embodiments of the compound having the structure of Formula (2a) and Formula (2b) tethered together as defined above, the compound is selected from the group consisting of:

153


Compound (2-1)



Compound (2-2)




Compound (2-3)



In some embodiments of the compound having the structure of Formula (2a) and Formula (2b) tethered together as defined above, the compound has Formula (3a):

Formula (3a)



wherein L^2 and L^3 are each independently selected from the group consisting of a single bond, BR^1 , NR^1 , PR^1 , O, S, Se, C=O, S=O, SO_2 , CR^1R^2 , SiR^1R^2 , and GeR^1R^2 ;

wherein R^{3a} - R^{3f} , are each independently selected from the group consisting of hydrogen, deuterium, alkyl, cycloalkyl, heteroalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aralkyl, CN, CF_3 , CO_2R , $C(O)R$, $C(O)NR_2$, NR_2 , NO_2 , OR, SR, SO_2 , SOR, SO_3R , halo, aryl, heteroaryl, a heterocyclic group, and combinations thereof;

wherein each R^1 and R^2 is independently selected from the group consisting of hydrogen, deuterium, halo, alkyl,

154

cycloalkyl, heteroalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aralkyl, aryl, heteroaryl, and combinations thereof;

wherein any two adjacent R^{1f} , R^{3a} , R^{3c} , R^{3d} , R^1 , and R^2 are optionally joined to form a ring; wherein L^2 and R^{1f} , L^2 and R^{3a} , or L^2 and both R^{1f} and R^{3a} are optionally joined to form one or more rings; and

wherein L^3 and R^{3c} , L^3 and R^{3d} , or L^3 and both R^{3c} and R^{3d} are optionally joined to form one or more rings.


In some embodiments of the compound having Formula (3a), L^2 and L^3 are independently selected from the group consisting of BR^1 , NR^1 , PR^1 , O, S, Se, C=O, S=O, SO_2 , CR^1R^2 , SiR^1R^2 , and GeR^1R^2 .

In some embodiments of the compound having Formula (3a), R^1 or R^{3a} and R^1 or R^2 are joined to form a ring.


In some embodiments of the compound having Formula (3a), R^{3c} or R^{3d} and R^1 or R^2 are joined to form a ring.

In some embodiments of the compound having Formula (3a), the compound is selected from the group consisting of:


Compound (3-1)




Compound (3-2)



Compound (3-3)



Compound (3-4)



a high quantum efficiency, with a narrow spectral width, and with a peak emission wavelength located within a desirable range of wavelengths, such as the visible range or the near infrared range. Also, these photoluminescent characteristics can be relatively invariant over a wide range of excitation wavelengths. The organic light-emitting materials can have other desirable characteristics, such as relating to their band gap energies and electrical conductivities. Advantageously, the organic light-emitting materials can be inexpensively and readily formed for use in various applications, including consumer products and lighting panels.

In some embodiments, the content of a photoluminescent substance in a light emitting material according to the present invention (e.g., one or more metal complexes having the structure of Formula 1, Formula 2, or Formula 3) is between 0.1% by mass to 50% by mass inclusive with respect to the total mass of a light emitting layer comprising the light emitting material. In some embodiments, the content of a photoluminescent substance in a light emitting material according to the present invention is between 0.3% by mass to 40% by mass inclusive with respect to the total mass of a light emitting layer comprising the light emitting material. In some embodiments, the content of a photoluminescent substance in a light emitting material according to the present invention is between 0.5% by mass to 30% by mass inclusive with respect to the total mass of a light emitting layer comprising the light emitting material. In some embodiments, the photoluminescent substance in a light emitting material according to the present invention is appended to a polymer chain or incorporated in a dendrimer material.

IV. Devices

In some aspects, the present invention provides an organic electroluminescence device which comprises at least one metal complex having the structure of Formula 1, Formula 2, or Formula 3. In some embodiments, an organic electroluminescence device according to the present invention comprises a first organic light emitting device, which further comprises an anode; a cathode; an organic layer disposed between the anode and the cathode, and comprising at least one metal complex having the structure of Formula 1, Formula 2, or Formula 3. In some preferred embodiments of the organic electroluminescence device, the organic layer further comprises a host material. In some preferred embodiments of the organic electroluminescence device, the host material comprises an organic compound. In some preferred embodiments of the organic electroluminescence device, the host material comprises an organic compound having a molecule containing at least one group selected from the group consisting of carbazole, dibenzothiphene, dibenzofuran, azacarbazole, aza-dibenzothiphene, and aza-dibenzofuran.

Generally, an organic layer suitable for use in the organic electroluminescence device of the present may have any suitable configuration of layer depending, for example, on application and purpose of the organic electroluminescence device. Accordingly, in some embodiments of the organic electroluminescence device, the organic layer is formed on a transparent electrode or a semitransparent electrode. In some such embodiments, the organic layer is formed on a top surface or any suitable surface of the transparent electrode or the semitransparent electrode. Also, suitable shape, size and/or thickness of the organic layer may be employed depending, for example, on application and the purpose of the organic electroluminescence device. Specific examples of configurations of an organic electroluminescence device of the present invention, having a substrate, a cathode, an

anode and an organic layer include, but are not limited to, the following: (A) Anode/hole transporting layer/light emitting layer/electron transporting layer/cathode;

(B) Anode/hole transporting layer/light emitting layer/block layer/electron transporting layer/cathode;

(C) Anode/hole transporting layer/light emitting layer/block layer/electron transporting layer/electron injection layer/cathode;

(D) Anode/hole injection layer/hole transporting layer/light emitting layer/block layer/electron transporting layer/cathode; and

(E) Anode/hole injection layer/hole transporting layer/light emitting layer/block layer/electron transporting layer/electron injection layer/cathode.

(F) Anode/hole injection layer/electron blocking layer/hole transporting layer/light emitting layer/block layer/electron transporting layer/electron injection layer/cathode.

Additional device configuration, including substrate, cathode and anode of an organic electroluminescence device, is described in Japanese Patent Publication No. 2008-270736.

<Substrate>

A suitable substrate usable in an organic electroluminescence device of the present invention is preferably a substrate which does not scatter or decrease light emitted from an organic layer when used for display applications. When used for lighting or certain display applications, substrates that scatter light are acceptable. In some embodiments, the substrate preferably is composed of an organic material which exhibits superior heat resistance, dimensional stability, solvent resistance, electrical insulating property and/or processability.

The substrate suitable for use in the present invention is preferably one which does not scatter or attenuate light emitted from the organic compound layer. Specific examples of materials for the substrate, include but are not limited to, inorganic materials such as zirconia-stabilized yttrium (YSZ) and glass; polyesters such as polyethylene terephthalate, polybutylene phthalate, and polyethylene naphthalate; and organic materials such as polystyrene, polycarbonate, polyethersulfone, polyarylate, polyimide, polycycloolefin, norbornene resin, polychlorotrifluoroethylene, and the like.

In some embodiments, when glass is used as the substrate, alkali free glass is preferably used. Specific examples of suitable alkali free glass are found in US patent application publication no. 2013/0237401 by Takahiro Kawaguchi, which published Sep. 12, 2013. In some embodiments, when soda-lime glass is used as the substrate, it is preferred to use glass on which a barrier coat of silica or the like has been applied. In some embodiments, when an organic material is used as the substrate, it is preferred to use a material having one or more of the attributes: excellent in heat resistance, dimensional stability, solvent resistance, electric insulation performance, and workability.

Generally, there is no particular limitation as to the shape, the structure, the size or the like of the substrate, but any of these attributes may be suitably selected according to the application, purposes and the like of the light-emitting element. In general, a plate-like substrate is preferred as the shape of the substrate. A structure of the substrate may be a monolayer structure or a laminate structure. Furthermore, the substrate may be formed from a single member or two or more members.

Although the substrate may be transparent and colorless, or transparent and colored, it is preferred that the substrate is transparent and colorless from the viewpoint that the

substrate does not scatter or attenuate light emitted from the organic light-emitting layer. In some embodiments, a moisture permeation preventive layer (gas barrier layer) may be provided on the top surface or the bottom surface of the substrate. Examples of a material of the moisture permeation preventive layer (gas barrier layer), include, but are not limited to, inorganic substances such as silicon nitride and silicon oxide. The moisture permeation preventive layer (gas barrier layer) may be formed in accordance with, for example, a high-frequency sputtering method or the like.

In the case of applying a thermoplastic substrate, a hard-coat layer or an under-coat layer may be further provided as needed.

<Anode>

Any anode may be used in an organic electroluminescence device of the present invention so long as it serves as an electrode supplying holes into an organic layer. In some embodiments of the organic electroluminescence device of the present invention, any suitable shape, structure and/or size of known electrode material may be used depending, for example, on the application and purpose of the organic electroluminescence device. In some embodiments, a transparent anode is preferred.

The anode may generally be any material as long as it has a function as an electrode for supplying holes to the organic compound layer, and there is no particular limitation as to the shape, the structure, the size or the like. However, it may be suitably selected from among well-known electrode materials according to the application and purpose of the light-emitting element. In some embodiments, the anode is provided as a transparent anode.

Materials for the anode preferably include, for example, metals, alloys, metal oxides, electric conductive compounds, and mixtures thereof. Materials having a work function of 4.0 eV or more are preferable. Specific examples of the anode materials include electric conductive metal oxides such as tin oxides doped with antimony, fluorine or the like (ATO and FTO), tin oxide, zinc oxide, indium oxide, indium tin oxide (ITO), and indium zinc oxide (IZO); metals such as gold, silver, chromium, aluminum, copper, and nickel; mixtures or laminates of these metals and the electric conductive metal oxides; inorganic electric conductive materials such as copper iodide and copper sulfide; organic electric conductive materials such as polyaniline, polythiophene, and polypyrrole; and laminates of these inorganic or organic electron-conductive materials with ITO. Among these, the electric conductive metal oxides are preferred, and particularly, ITO is preferable in view of productivity, high electric conductivity, transparency and the like.

The anode may be formed on the substrate in accordance with a method which is appropriately selected from among wet methods such as printing methods, coating methods and the like; physical methods such as vacuum deposition methods, sputtering methods, ion plating methods and the like; and chemical methods such as CVD (chemical vapor deposition) and plasma CVD methods and the like, in consideration of the suitability to a material constituting the anode. For instance, when ITO is selected as a material for the anode, the anode may be formed in accordance with a DC or high-frequency sputtering method, a vacuum deposition method, an ion plating method or the like.

In the organic electroluminescence element of the present invention, a position at which the anode is to be formed is not particularly limited, but it may be suitably selected according to the application and purpose of the light-

emitting element. The anode may be formed on either the whole surface or a part of the surface on either side of the substrate.

For patterning to form the anode, a chemical etching method such as photolithography, a physical etching method such as etching by laser, a method of vacuum deposition or sputtering through superposing masks, or a lift-off method or a printing method may be applied.

A thickness of the anode may be suitably selected according to the material constituting the anode and is therefore not definitely decided, but it is usually in a range of from 10 nm to 50 μm , and preferably from 50 nm to 20 μm . The thickness of the anode layer may be properly controlled depending on the material used therefor. The resistance of the anode is preferably $10^3 \Omega/\text{square}$ or less, and more preferably $10^2 \Omega/\text{square}$ or less, more preferably 30 Ω/square or less. In the case where the anode is transparent, it may be either transparent and colorless, or transparent and colored. For extracting luminescence from the transparent anode side, it is preferred that a light transmittance of the anode is 60% or higher, and more preferably 70% or higher. A detailed description of transparent anodes can be found in "TOUMEI DENNKYOKU-MAKU NO SHINTENKAI (Novel Developments in Transparent Electrode Films)" edited by Yutaka Sawada, published by C.M.C. in 1999.

In the case where a plastic substrate having a low heat resistance is used in the present invention, it is preferred that ITO or IZO is used to obtain a transparent anode prepared by forming the film at a low temperature of 150° C. or lower.

<Cathode>

Any cathode may be used in an organic electroluminescence device of the present invention so long as it serves as an electrode supplying electrons into the organic layer. In some embodiments of the organic electroluminescence device of the present invention, any suitable shape, structure and/or size of known electrode material may be used depending, for example, on the application and purpose of the organic electroluminescence device. In some embodiments, a transparent cathode is preferred.

The cathode may generally be any material as long as it has a function as an electrode for injecting electrons to the organic compound layer, and there is no particular limitation as to the shape, the structure, the size or the like. However it may be suitably selected from among well-known electrode materials according to the application and purpose of the light-emitting element.

Materials constituting the cathode include, for example, metals, alloys, metal oxides, electric conductive compounds, and mixtures thereof. Materials having a work function of 4.0 eV or more are preferable. Specific examples thereof include alkali metals (e.g., Li, Na, K, Cs or the like), alkaline earth metals (e.g., Mg, Ca or the like), gold, silver, lead, aluminum, sodium-potassium alloys, lithium-aluminum alloys, magnesium-silver alloys, rare earth metals such as indium, and ytterbium, and the like. They may be used alone, but it is preferred that two or more of them are used in combination from the viewpoint of satisfying both stability and electron injectability.

In some embodiments, as the materials for constituting the cathode, alkaline metals or alkaline earth metals are preferred in view of electron injectability, and materials containing aluminum as a major component are preferred in view of excellent preservation stability.

The term "material containing aluminum as a major component" refers to a material constituted by aluminum alone; alloys comprising aluminum and 0.01% by weight to 10% by weight of an alkaline metal or an alkaline earth

metal; or mixtures thereof (e.g., lithium-aluminum alloys, magnesium-aluminum alloys and the like). Exemplary materials for the cathode are described in detail in JP-A Nos. 2-15595 and 5-121172.

A method for forming the cathode is not particularly limited, but it may be formed in accordance with a well-known method. For instance, the cathode may be formed in accordance with a method which is appropriately selected from among wet methods such as printing methods, coating methods and the like; physical methods such as vacuum deposition methods, sputtering methods, ion plating methods and the like; and chemical methods such as CVD and plasma CVD methods and the like, in consideration of the suitability to a material constituting the cathode. For example, when a metal (or metals) is (are) selected as a material (or materials) for the cathode, one or two or more of them may be applied at the same time or sequentially in accordance with a sputtering method or the like.

For patterning to form the cathode, a chemical etching method such as photolithography, a physical etching method such as etching by laser, a method of vacuum deposition or sputtering through superposing masks, or a lift-off method or a printing method may be applied.

In the present invention, a position at which the cathode is to be formed is not particularly limited, and it may be formed on either the whole or a part of the organic compound layer.

Furthermore, a dielectric material layer made of fluorides, oxides or the like of an alkaline metal or an alkaline earth metal may be inserted between the cathode and the organic compound layer with a thickness of from 0.1 nm to 5 nm. The dielectric material layer may be considered to be a kind of electron injection layer. The dielectric material layer may be formed in accordance with, for example, a vacuum deposition method, a sputtering method, an ionplating method or the like.

A thickness of the cathode may be suitably selected according to materials for constituting the cathode and is therefore not definitely decided, but it is usually in a range of from 10 nm to 5 μ m, and preferably from 50 nm to 1 μ m.

Moreover, the cathode may be transparent or opaque. A transparent cathode may be formed by preparing a material for the cathode with a small thickness of from 1 nm to 10 nm, and further laminating a transparent electric conductive material such as ITO or IZO thereon.

<Protective Layer>

A whole body of the organic EL element of the present invention may be protected by a protective layer. Any materials may be applied in the protective layer as long as the materials have a function to protect a penetration of ingredients such as moisture, oxygen or the like which accelerates deterioration of the element into the element. Specific examples of materials for the protective layer include metals such as In, Sn, Pb, Au, Cu, Ag, Al, Ti, Ni and the like; metal oxides such as MgO, SiO, SiO₂, Al₂O₃, GeO, NiO, CaO, BaO, Fe₂O₃, Y₂O₃, TiO₂ and the like; metal nitrides such as SiN_x, SiN_xO_y, and the like; metal fluorides such as MgF₂, LiF, AlF₃, CaF₂ and the like; polyethylene; polypropylene; polymethyl methacrylate; polyimide; polyurea; polytetrafluoroethylene; polychlorotrifluoroethylene; polydichlorodifluoroethylene; a copolymer of chlorotrifluoroethylene and dichlorodifluoroethylene; copolymers obtained by copolymerizing a monomer mixture containing tetrafluoroethylene and at least one comonomer; fluorine-containing copolymers each having a cyclic structure in the copolymerization main chain; water-absorbing materials each having a coefficient of water absorption of 1% or more;

moisture permeation preventive substances each having a coefficient of water absorption of 0.1% or less; and the like.

There is no particular limitation as to a method for forming the protective layer. For instance, a vacuum deposition method, a sputtering method, a reactive sputtering method, an MBE (molecular beam epitaxial) method, a cluster ion beam method, an ion plating method, a plasma polymerization method (high-frequency excitation ion plating method), a plasma CVD method, a laser CVD method, a thermal CVD method, a gas source CVD method, a coating method, a printing method, or a transfer method may be applied.

<Sealing>

The whole organic electroluminescence element of the present invention may be sealed with a sealing cap. Furthermore, a moisture absorbent or an inert liquid may be used to seal a space defined between the sealing cap and the light-emitting element. Although the moisture absorbent is not particularly limited, specific examples thereof include barium oxide, sodium oxide, potassium oxide, calcium oxide, sodium sulfate, calcium sulfate, magnesium sulfate, phosphorus pentoxide, calcium chloride, magnesium chloride, copper chloride, cesium fluoride, niobium fluoride, calcium bromide, vanadium bromide, molecular sieve, zeolite, magnesium oxide and the like. Although the inert liquid is not particularly limited, specific examples thereof include paraffins; liquid paraffins; fluorine-based solvents such as perfluoroalkanes, perfluoroamines, perfluoroethers and the like; chlorine-based solvents; silicone oils; and the like.

<Driving>

In the organic electroluminescence element of the present invention, when a DC (AC components may be contained as needed) voltage (usually 2 volts to 15 volts) or DC is applied across the anode and the cathode, luminescence can be obtained. For the driving method of the organic electroluminescence element of the present invention, driving methods described in JP-A Nos. 2-148687, 6-301355, 5-29080, 7-134558, 8-234685, and 8-241047; Japanese Patent No. 2784615, U.S. Pat. Nos. 5,828,429 and 6,023,308 are applicable.

<Applications>

Devices fabricated in accordance with embodiments of the inventions described herein may be incorporated into a wide variety of consumer products, including but not limited to flat panel displays, computer monitors, televisions, billboards, lights for interior or exterior illumination and/or signaling, heads up displays, fully transparent displays, flexible displays, laser printers, telephones, cell phones, personal digital assistants (PDAs), laptop computers, digital cameras, camcorders, viewfinders, micro-displays, vehicles, a large area wall, theater or stadium screen, or a sign.

<Organic Layer>

An organic layer suitable for use in an organic electroluminescence device of the present invention may comprise a plurality of layers, including, for example, light emitting layer, host material, electric charge transporting layer, hole injection layer, and hole transporting layer. Blocking layers may also be included e.g. hole (and or exciton) blocking layers (HBL) or electron (and or exciton) blocking layers (EBL). In some embodiments of an organic electroluminescence device of the present invention, each organic layer may be formed by a dry-type film formation method such as a deposition method or a sputtering method, or a solution coating process such as a transfer method, a printing method, a spin coating method, or a bar coating method. In some embodiments of an organic electroluminescence

device of the present invention, at least one layer of the organic layer is preferably formed by a solution coating process.

A. Light Emitting Layer

Light Emitting Material:

A light emitting material in accordance with the present invention preferably includes at least one metal complex having the structure of Formula 1, Formula 2, or Formula 3. Some embodiments of an organic electroluminescence device of the present invention comprises the light emitting material in an amount of about 0.1% by mass to about 50% by mass with respect to the total mass of the compound constituting the light emitting layer. In some embodiments, an organic electroluminescence device of the present invention comprises the light emitting material in an amount of about 1% by mass to about 50% by mass with respect to the total mass of the compound constituting the light emitting layer. In some embodiments, an organic electroluminescence device of the present invention comprises the light emitting material in an amount of about 2% by mass to about 40% by mass with respect to the total mass of the compound constituting the light emitting layer. In some embodiments, a total amount of the light-emitting materials in the light-emitting layer is preferably from about 0.1% by weight to about 30% by weight with respect to the entire amount of compounds contained in the light-emitting layer. In some embodiments, a total amount of the light-emitting materials in the light-emitting layer is preferably from about 1% by weight to about 20% by weight in view of durability and external quantum efficiency. In some embodiments, a total amount of the host materials in the light-emitting layer is preferably from about 70% by weight to about 99.9% by weight. In some embodiments, a total amount of the host materials in the light-emitting layer is preferably from about 80% by weight to 99% by weight in view of durability and external quantum efficiency. In some embodiments, graded light emitting layers or graded interfaces within the light emitting layer may be used. Grading may be formed, for example, by mixing two or more distinct materials in a fashion that an abrupt change from one layer to another is not formed. Graded light emitting layers and or interfaces have been shown to improve device lifetime and this device architecture may be beneficial to improving PHOLED lifetime and general performance. In this instance the the light emitting material may be present in an amount of about 0% by mass to about 100% by mass at any given position within the light emitting layer.

In some embodiments, a light-emitting layer in the present invention may include the light-emitting materials and a host material contained in the light-emitting layer as a combination of a fluorescent light-emitting material which emits light (fluorescence) through a singlet exciton and a host material, or a combination of a phosphorescent light-emitting material which emits light (phosphorescence) through a triplet exciton and a host material. In some embodiments, a light-emitting layer in the present invention may include the light-emitting materials and a host material contained in the light-emitting layer as a combination of a phosphorescent light-emitting material and a host material.


In some embodiments, the first compound can be an emissive dopant. In some embodiments, the compound can produce emissions via phosphorescence, fluorescence, thermally activated delayed fluorescence, i.e., TADF (also referred to as E-type delayed fluorescence), triplet-triplet annihilation, or combinations of these processes.

B. Host Material

A suitable host material for use in the present invention, may be a hole transporting host material (sometimes referred to as a hole transporting host), and/or an electron transporting host material (sometimes referred to as an electron transporting host).


The organic layer can also include a host. In some embodiments, two or more hosts are preferred. In some embodiments, the hosts used maybe a) bipolar, b) electron transporting, c) hole transporting or d) wide band gap materials that play little role in charge transport. In some embodiments, the host can include a metal complex. The host can be a triphenylene containing benzo-fused thiophene or benzo-fused furan. Any substituent in the host can be an unfused substituent independently selected from the group consisting of C_nH_{2n+1} , OC_nH_{2n+1} , OAr_1 , $N(C_nH_{2n+1})_2$, $N(Ar_1)(Ar_2)$, $CH=CH-C_nH_{2n+1}$, $C\equiv C-C_nH_{2n+1}$, Ar_1 , Ar_1-Ar_2 , and $C_nH_{2n}-Ar_1$, or no substitution. In the preceding substituents n can range from 1 to 10; and Ar_1 and Ar_2 can be independently selected from the group consisting of benzene, biphenyl, naphthalene, triphenylene, carbazole, and heteroaromatic analogs thereof. In some embodiment, the host can also be an inorganic compound. For example a Zn containing inorganic material, e.g. ZnS.

The host can be a compound comprising at least one chemical group selected from the group consisting of triphenylene, carbazole, dibenzothiophene, dibenzofuran, dibenzoselenophene, azatriphenylene, azacarbazole, aza-dibenzothiophene, aza-dibenzofuran, and aza-dibenzoselenophene. The host can include a metal complex. The host can be a specific compound selected from the group consisting of:




165

-continued








166

-continued








167

-continued



168

-continued



55

and combinations thereof.

Hole Transporting Host Material

Specific examples of the hole transporting host materials include, but are not limited to pyrrole, carbazole, azacarbazole, pyrazole, indole, azaindole, imidazole, polyaryllkane, pyrazoline, pyrazolone, phenylenediamine, arylamine, amino-substituted chalcone, styrylanthracene, fluorenone, hydrazone, stilbene, silazane, aromatic tertiary amine compounds, styrylamine compounds, aromatic dimethylidene compounds, porphyrin compounds, polysilane compounds, poly(N-vinylcarbazole), aniline copolymers, electric conductive high-molecular oligomers such as thiophene oli-

60

65

gomers, polythiophenes and the like, organic silanes, carbon films, derivatives thereof, and the like. Some preferred host materials include carbazole derivatives, indole derivatives, imidazole derivatives, aromatic tertiary amine compounds, and thiophene derivatives.

Specific examples of the electron transporting host materials include, but are not limited to pyridine, pyrimidine, triazine, imidazole, pyrazole, triazole, oxazole, oxadiazole, fluorenone, anthraquinonedimethane, anthrone, diphenylquinone, thiopyrandioxide, carbodiimide, fluorenylidene-methane, distyrylpyrazine, fluorine-substituted aromatic compounds, aromacyclic tetracarboxylic anhydrides of naphthalene, perylene or the like, phthalocyanine, derivatives thereof, including a variety of metal complexes represented by metal complexes of 8-quinolinol derivatives, metal phthalocyanine, and metal complexes having benzoxazole or benzothiazole as the ligand.

Preferable electron transporting hosts are metal complexes, azole derivatives (benzimidazole derivatives, imidazopyridine derivatives and the like), and azine derivatives (pyridine derivatives, pyrimidine derivatives, triazine derivatives and the like).

C. Film Thickness

In some embodiments, the film thickness of the light-emitting layer is preferably from about 10 nm to about 500 nm. In some embodiments, the film thickness of the light-emitting layer is preferably from about 20 nm to about 100 nm depending, for example, on desired brightness uniformity, driving voltage and brightness. In some embodiments, the light-emitting layer is configured to have a thickness that optimizes passage of charges from the light-emitting layer to adjacent layers without lowering light-emission efficiency. In some embodiments, the light-emitting layer is configured to have a thickness that maintains minimum driving voltage maximum light-emission efficiency.

D. Layer Configuration

The light-emitting layer may be composed of a single layer or two or more layers, and the respective layers may cause light emission in different light-emitting colors. Also, in the case where the light-emitting layer has a laminate structure, though the film thickness of each of the layers configuring the laminate structure is not particularly limited, it is preferable that a total film thickness of each of the light-emitting layers falls within the foregoing range. In some embodiments, graded layers or graded interfaces within the layers may be used.

E. Hole Injection Layer and Hole Transport Layer

The hole injection layer and hole transport layer are layers functioning to receive holes from an anode or from an anode side and to transport the holes to the emitting layer. Materials to be introduced into a hole injection layer or a hole transport layer is not particularly limited, but either of a low molecular compound or a high molecular compound may be used.

Specific examples of the material contained in the hole injection layer and the hole transport layer include, but are not limited to, pyrrole derivatives, carbazole derivatives, azacarbazole derivatives, indole derivatives, azaindole derivatives, imidazole derivatives, polyarylalkane derivatives, pyrazoline derivatives, pyrazolone derivatives, phenylenediamine derivatives, arylamine derivatives, amino-substituted chalcone derivatives, styrylanthracene derivatives, fluorenone derivatives, hydrazone derivatives, stilbene derivatives, silazane derivatives, aromatic tertiary amine compounds, styrylamine compounds, aromatic dim-

ethylidene compounds, phthalocyanine compounds, porphyrin compounds, organosilane derivatives, carbon, and the like.

An electron-accepting dopant may be introduced into the hole injection layer or the hole transport layer in the organic EL element of the present invention. As the electron-accepting dopant to be introduced into the hole injection layer or the hole transport layer, either of an inorganic compound or an organic compound may be used as long as the compound has electron accepting property and a function for oxidizing an organic compound.

Specifically, the inorganic compound includes metal halides such as ferric chloride, aluminum chloride, gallium chloride, indium chloride, antimony pentachloride and the like, and metal oxides such as vanadium pentoxide, molybdenum trioxide and the like.

In case of employing the organic compounds, compounds having a substituent such as a nitro group, a halogen, a cyano group, a trifluoromethyl group or the like; quinone compounds; acid anhydride compounds; fullerenes; and the like may be preferably applied.

Specific examples hole injection and hole transport materials include compounds described in patent documents such as JP-A Nos. 6-212153, 11-111463, 11-251067, 2000-196140, 2000-286054, 2000-315580, 2001-102175, 2001-160493, 2002-252085, 2002-56985, 2003-157981, 2003-217862, 2003-229278, 2004-342614, 2005-72012, 2005-166637, 2005-209643 and the like.

Specific examples of hole injection and hole transport materials include the organic compounds: hexacyanobutadiene, hexacyanobenzene, tetracyanoethylene, tetracyanoquinodimethane, tetrafluorotetracyanoquinodimethane, p-fluoranil, p-chloranil, p-bromanil, p-benzoquinone, 2,6-dichlorobenzoquinone, 2,5-dichlorobenzoquinone, 1,2,4,5-tetracyanobenzene, 1,4-dicyanotetrafluorobenzene, 2,3-dichloro-5,6-dicyanobenzoquinone, p-dinitrobenzene, m-dinitrobenzene, o-dinitrobenzene, 1,4-naphthoquinone, 2,3-dichloronaphthoquinone, 1,3-dinitronaphthalene, 1,5-dinitronaphthalene, 9,10-anthraquinone, 1,3,6,8-tetranitrocarbazole, 2,4,7-trinitro-9-fluorenone, 2,3,5,6-tetracyanopyridine and fullerene C60. Among these, hexacyanobutadiene, hexacyanobenzene, tetracyanoethylene, tetracyanoquinodimethane, tetrafluorotetracyanoquinodimethane, p-fluoranil, p-chloranil, p-bromanil, 2,6-dichlorobenzoquinone, 2,5-dichlorobenzoquinone, 2,3-dichloronaphthoquinone, 1,2,4,5-tetracyanobenzene, 2,3-dichloro-5,6-dicyanobenzoquinone and 2,3,5,6-tetracyanopyridine are more preferable, and tetrafluorotetracyanoquinodimethane.

As one or more electron-accepting dopants may be introduced into the hole injection layer or the hole transport layer in the organic EL element of the present invention, these electron-accepting dopants may be used alone or in combinations of two or more. Although precise amount of these electron-accepting dopants used will depend on the type of material, about 0.01% by weight to about 50% by weight of the total weight of the hole transport layer or the hole injection layer is preferred. In some embodiments, the amount of these electron-accepting dopants range from about 0.05% by weight to about 20% by weight of the total weight of the hole transport layer or the hole injection layer. In some embodiments, the amount of these electron-accepting dopants range from about 0.1% by weight to about 10% by weight of the total weight of the hole transport layer or the hole injection layer.

In some embodiments, a thickness of the hole injection layer and a thickness of the hole transport layer are each

preferably about 500 nm or less in view of decreasing driving voltage or optimizing for optical outcoupling. In some embodiments, the thickness of the hole transport layer is preferably from about 1 nm to about 500 nm. In some embodiments, the thickness of the hole transport layer is preferably from about 5 nm to about 50 nm. In some embodiments, the thickness of the hole transport layer is preferably from about 10 nm to about 40 nm. In some embodiments, the thickness of the hole injection layer is preferably from about 0.1 nm to about 500 nm. In some embodiments, the thickness of the hole injection layer is preferably from about 0.5 nm to about 300 nm. In some embodiments, the thickness of the hole injection layer is preferably from about 1 nm to about 200 nm.

The hole injection layer and the hole transport layer may be composed of a monolayer structure comprising one or two or more of the above-mentioned materials, or a multilayer structure composed of plural layers of a homogeneous composition or a heterogeneous composition.

F. Electron Injection Layer and Electron Transport Layer

The electron injection layer and the electron transport layer are layers having functions for receiving electrons from a cathode or a cathode side, and transporting electrons to the light emitting layer. An electron injection material or an electron transporting material used for these layers may be a low molecular compound or a high molecular compound. Specific examples of the materials suitable for use in electron injection and electron transport layers include, but are not limited to, pyridine derivatives, quinoline derivatives, pyrimidine derivatives, pyrazine derivatives, phthalazine derivatives, phenanthroline derivatives, triazine derivatives, triazole derivatives, oxazole derivatives, oxadiazole derivatives, imidazole derivatives, fluorenone derivatives, anthraquinodimethane derivatives, anthrone derivatives, diphenylquinone derivatives, thiopyrandioxide derivatives, carbodiimide derivatives, fluorenylidene methane derivatives, distyrylpyrazine derivatives, aromatic cyclic tetracarboxylic anhydrides of perylene, naphthalene or the like, phthalocyanine derivatives, metal complexes represented by metal complexes of 8-quinolinol derivatives, metal phthalocyanine, and metal complexes containing benzoxazole, or benzothiazole as the ligand, organic silane derivatives exemplified by silole, and the like.

The electron injection layer or the electron transport layer may contain an electron donating dopant. Suitable electron donating dopant for use in the electron injection layer or the electron transport layer, include any suitable material that may be used as long as it has an electron-donating property and a property for reducing an organic compound. Specific examples of electron donating dopants include an alkaline metal such as Li, an alkaline earth metal such as Mg, a transition metal including a rare-earth metal, and a reducing organic compound. Other examples of metal donating dopants include, metals having a work function of 4.2 V or less, for example, Li, Na, K, Be, Mg, Ca, Sr, Ba, Y, Cs, La, Sm, Gd, Yb, and the like. Specific examples of the reducing organic compounds include nitrogen-containing compounds, sulfur-containing compounds, phosphorus-containing compounds, and the like.

The electron donating dopants may be used alone or in combinations of two or more. In some embodiments, an electron donating dopant is contained in the electron injection layer or the electron transport layer in an amount ranging from about 0.1% by weight to about 99% by weight of the total weight of the electron transport layer material or the electron injecting layer mater. In some embodiments, an electron donating dopant is contained in the electron injection

layer or the electron transport layer in an amount ranging from about 1.0% by weight to about 80% by weight of the total weight of the electron transport layer material or the electron injecting layer material. In some embodiments, an electron donating dopant is contained in the electron injection layer or the electron transport layer in an amount ranging from about 2.0% by weight to about 70% by weight of the total weight of the electron transport layer material or the electron injecting layer material.

A thickness of the electron injection layer and a thickness of the electron transport layer are each preferably 500 nm or less in view of decrease in driving voltage. The thickness of the electron transport layer is preferably from 1 nm to 500 nm, more preferably from 5 nm to 200 nm, and even more preferably from 10 nm to 100 nm. A thickness of the electron injection layer is preferably from 0.1 nm to 200 nm, more preferably from 0.2 nm to 100 nm, and even more preferably from 0.5 nm to 50 nm.

The electron injection layer and the electron-transport may be composed of a monolayer structure comprising one or two or more of the above-mentioned materials, or a multilayer structure composed of plural layers of a homogeneous composition or a heterogeneous composition.


Combination with Other Materials


The materials described herein as useful for a particular layer in an organic light emitting device may be used in combination with a wide variety of other materials present in the device. For example, emissive dopants disclosed herein may be used in conjunction with a wide variety of hosts, transport layers, blocking layers, injection layers, electrodes and other layers that may be present. The materials described or referred to below are non-limiting examples of materials that may be useful in combination with the compounds disclosed herein, and one of skill in the art can readily consult the literature to identify other materials that may be useful in combination.

HIL/HTL:

A hole injecting/transporting material to be used in the present invention is not particularly limited, and any compound may be used as long as the compound is typically used as a hole injecting/transporting material. Examples of the material include, but are not limited to: a phthalocyanine or porphyrin derivative; an aromatic amine derivative; an indolocarbazole derivative; a polymer containing fluorohydrocarbon; a polymer with conductivity dopants; a conducting polymer, such as PEDOT/PSS; a self-assembly monomer derived from compounds such as phosphonic acid and silane derivatives; a metal oxide derivative, such as MoOx; a p-type semiconducting organic compound, such as 1,4,5,8,9,12-Hexaazatriphenylenehexacarbonitrile; a metal complex, and a cross-linkable compound.




Examples of aromatic amine derivatives used in HIL or HTL include, but are not limited to the following general structures:






Each of Ar¹ to Ar⁹ is selected from the group consisting of aromatic hydrocarbon cyclic compounds such as benzene, biphenyl, triphenyl, triphenylene, naphthalene, anthracene, phenalene, phenanthrene, fluorene, pyrene, chrysene, perylene, and azulene; the group consisting of aromatic heterocyclic compounds such as dibenzothiophene, dibenzofuran, dibenzoselenophene, furan, thiophene, benzofuran, benzothiophene, benzoselenophene, carbazole, indolocarbazole, pyridylindole, pyrrolodipyridine, pyrazole, imidazole, triazole, oxazole, thiazole, oxadiazole, oxatriazole, dioxazole, thiadiazole, pyridine, pyridazine, pyrimidine, pyrazine, triazine, oxazine, oxathiazine, oxadiazine, indole, benzimidazole, indazole, indoxazine, benzoxazole, benzisoxazole, benzothiazole, quinoline, isoquinoline, cinnoline, quinazoline, quinoxaline, naphthyridine, phthalazine, pteridine, xanthene, acridine, phenazine, phenothiazine, phenoxazine, benzofuropyridine, furodipyridine, benzothienopyridine, thienodipyridine, benzoselenophenopyridine, and selenophenodipyridine; and the group consisting of 2 to 10 cyclic structural units which are groups of the same type or different types selected from the aromatic hydrocarbon cyclic group and the aromatic heterocyclic group and are bonded to each other directly or via at least one of oxygen atom, nitrogen atom, sulfur atom, silicon atom, phosphorus atom, boron atom, chain structural unit and the aliphatic cyclic group. Wherein each Ar is further substituted by a substituent selected from the group consisting of hydrogen, deuterium, halide, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acids, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof.

In one aspect, Ar¹ to Ar⁹ is independently selected from the group consisting of:



wherein k is an integer from 1 to 20; X¹⁰¹ to X¹⁰⁸ is C (including CH) or N; Z¹⁰¹ is NAr¹, O, or S; Ar¹ has the same group defined above.

Examples of metal complexes used in HIL or HTL include, but are not limited to the following general formula:



wherein Met is a metal, which can have an atomic weight greater than 40; (Y¹⁰¹-Y¹⁰²) is a bidentate ligand, Y¹⁰¹ and Y¹⁰² are independently selected from C, N, O, P, and S; L¹⁰¹ is an ancillary ligand; k' is an integer value from 1 to the maximum number of ligands that may be attached to the metal; and k'+k'' is the maximum number of ligands that may be attached to the metal.

In one aspect, (Y¹⁰¹-Y¹⁰²) is a 2-phenylpyridine derivative. In another aspect, (Y¹⁰¹-Y¹⁰²) is a carbene ligand. In another aspect, Met is selected from Ir, Pt, Os, and Zn. In a further aspect, the metal complex has a smallest oxidation potential in solution vs. Fc⁺/Fc couple less than about 0.6 V.

EBL:


An electron blocking layer (EBL) may be used to reduce the number of electrons and/or excitons that leave the emissive layer. The presence of such a blocking layer in a device may result in substantially higher efficiencies, and or longer lifetime, as compared to a similar device lacking a blocking layer. Also, a blocking layer may be used to confine emission to a desired region of an OLED. In some embodiments, the EBL material has a higher LUMO (closer to the vacuum level) and or higher triplet energy than the emitter closest to the EBL interface. In some embodiments, the EBL material has a higher LUMO (closer to the vacuum level) and or higher triplet energy than one or more of the hosts closest to the EBL interface. In one aspect, compound used in EBL contains the same molecule or the same functional groups used as one of the hosts described below.

Host:

The light emitting layer of the organic EL device of the present invention preferably contains at least a metal complex as light emitting material, and may contain a host material using the metal complex as a dopant material. In some embodiments, two or more hosts are preferred. In some embodiments, the hosts used maybe a) bipolar, b) electron transporting, c) hole transporting or d) wide band gap materials that play little role in charge transport. Examples of the host material are not particularly limited, and any metal complexes or organic compounds may be used as long as the triplet energy of the host is larger than that of the dopant. While the Table below categorizes host materials as preferred for devices that emit various colors, any host material may be used with any dopant so long as the triplet criteria is satisfied.


175

Examples of metal complexes used as host are preferred to have the following general formula:



wherein Met is a metal; (Y¹⁰³-Y¹⁰⁴) is a bidentate ligand, Y¹⁰³ and Y¹⁰⁴ are independently selected from C, N, O, P, and S; L¹⁰¹ is an another ligand; k' is an integer value from 1 to the maximum number of ligands that may be attached to the metal; and k'+k'' is the maximum number of ligands that may be attached to the metal.

In one aspect, the metal complexes are:




wherein (O—N) is a bidentate ligand, having metal coordinated to atoms O and N.

In another aspect, Met is selected from Ir and Pt. In a further aspect, (Y¹⁰³-Y¹⁰⁴) is a carbene ligand.

Examples of organic compounds used as host are selected from the group consisting of aromatic hydrocarbon cyclic compounds such as benzene, biphenyl, triphenyl, triphenylene, naphthalene, anthracene, phenalene, phenanthrene, fluorene, pyrene, chrysene, perylene, and azulene; the group consisting of aromatic heterocyclic compounds such as dibenzothiophene, dibenzofuran, dibenzoselenophene, furan, thiophene, benzofuran, benzothiophene, benzoselenophene, carbazole, indolocarbazole, pyridylindole, pyrrolodipyridine, pyrazole, imidazole, triazole, oxazole, thiazole, oxadiazole, oxatriazole, dioxazole, thiadiazole, pyridine, pyridazine, pyrimidine, pyrazine, triazine, oxazine, oxathiazine, oxadiazine, indole, benzimidazole, indazole, indoxazine, benzoxazole, benzisoxazole, benzothiazole, quinoline, isoquinoline, cinnoline, quinazoline, quinoxaline, naphthyridine, phthalazine, pteridine, xanthene, acridine, phenazine, phenothiazine, phenoxazine, benzofuopyridine, furodipyridine, benzothienopyridine, thienodipyridine, benzoselenophenopyridine, and selenophenodipyridine; and the group consisting of 2 to 10 cyclic structural units which are groups of the same type or different types selected from the aromatic hydrocarbon cyclic group and the aromatic heterocyclic group and are bonded to each other directly or via at least one of oxygen atom, nitrogen atom, sulfur atom, silicon atom, phosphorus atom, boron atom, chain structural unit and the aliphatic cyclic group. Wherein each group is further substituted by a substituent selected from the group consisting of hydrogen, deuterium, halide, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acids, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof.


176

In one aspect, the host compound contains at least one of the following groups in the molecule:



Ar's mentioned above. k is an integer from 1 to 20. X^{101} to X^{108} is selected from C (including CH) or N.

In another aspect, the metal complexes used in ETL include, but are not limited to the following general formula:



wherein (O—N) or (N—N) is a bidentate ligand, having metal coordinated to atoms O, N or N, N; L^{101} is another ligand; k' is an integer value from 1 to the maximum number of ligands that may be attached to the metal.

Charge Generation Layer (CGL):

In tandem or stacked OLEDs, the CGL plays an essential role in the performance, which is composed of an n-doped layer and a p-doped layer for injection of electrons and holes, respectively. Electrons and holes are supplied from

the CGL and electrodes. The consumed electrons and holes in the CGL are refilled by the electrons and holes injected from the cathode and anode, respectively; then, the bipolar currents reach a steady state gradually. Typical CGL materials include n and p conductivity dopants used in the transport layers.

In any above-mentioned compounds used in each layer of the OLED device, the hydrogen atoms can be partially or fully deuterated. Thus, any specifically listed substituent, such as, without limitation, methyl, phenyl, pyridyl, etc. encompasses undeuterated, partially deuterated, and fully deuterated versions thereof. Similarly, classes of substituents such as, without limitation, alkyl, aryl, cycloalkyl, heteroaryl, etc. also encompass undeuterated, partially deuterated, and fully deuterated versions thereof.

In addition to and/or in combination with the materials disclosed herein, many hole injection materials, hole transporting materials, host materials, dopant materials, exciton/hole blocking layer materials, electron transporting and electron injecting materials may be used in an OLED. Non-limiting examples of the materials that may be used in an OLED in combination with materials disclosed herein are listed in Table A below. Table A lists non-limiting classes of materials, non-limiting examples of compounds for each class, and references that disclose the materials.

TABLE A



MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
	Hole injection materials	
Phthalocyanine and porphyrin compounds		Appl. Phys. Lett. 69, 2160 (1996)
Starburst triarylaminines		J. Lumin. 72-74, 985 (1997)

TABLE A-continued





MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
CF _x	$\text{---}[\text{CH}_2\text{F}_y]\text{---}$	Appl. Phys.
Fluorohydrocarbon polymer		Lett. 78, 673 (2001)
Conducting polymers (e.g., PEDOT: PSS, polyaniline, polythiophene)	 <p>The image shows two chemical structures. On the left is a thiophene-based polymer repeat unit with a sulfur atom in a five-membered ring and two oxygen atoms in a six-membered ring fused to it. On the right is a polymer chain with a sulfonate group (SO₃⁻(H⁺)) attached to a benzene ring, which is further connected to a polymer backbone.</p>	Synth. Met. 87, 171 (1997) WO2007002683
Phosphonic acid and silane SAMs	 <p>The image shows a chemical structure of a phosphonic acid and silane SAM, represented as N-(C₆H₄-SiCl₃)₃.</p>	US20030162053
Triarylamine or polythiophene polymers with conductivity dopants	 <p>The image shows two chemical structures. The top structure is a triarylamine polymer with a central nitrogen atom bonded to three phenyl rings, one of which is further substituted with a methoxy group. The bottom structure is a polythiophene polymer with a central nitrogen atom bonded to three phenyl rings, one of which is further substituted with a bromine atom. The word "and" is placed between the two structures.</p>	EP1725079A1
	 <p>The image shows a chemical structure of a boron-doped polymer, featuring a central boron atom (B⁻) bonded to four fluorinated phenyl rings.</p>	

TABLE A-continued





MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Organic compounds with conductive inorganic compounds, such as molybdenum and tungsten oxides		US20050123751 SID Symposium Digest, 37, 923 (2006) WO2009018009
n-type semiconducting organic complexes		US20020158242
Metal organometallic complexes		US20060240279
Cross-linkable compounds		US20080220265

TABLE A-continued





MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Polythiophene based polymers and copolymers		WO 2011075644 EP2350216
Hole transporting materials		
Triarylamines (e.g., TPD, α -NPD)		Appl. Phys. Lett. 51, 913 (1987)
		US5061569
		EP650955

TABLE A-continued

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		J. Mater. Chem. 3, 319 (1993)
		Appl. Phys. Lett. 90, 183503 (2007)
		Appl. Phys. Lett. 90, 183503 (2007)
Triarylamine on spirofluorene core		Synth. Met. 91, 209 (1997)

TABLE A-continued

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Arylamine carbazole compounds		Adv. Mater. 6, 677 (1994), US20080124572
Triarylamine with (di)benzothiophene/ (di)benzofuran		US20070278938, US20080106190 US20110163302
Indolocarbazoles		Synth. Met. 111, 421 (2000)
Isoindole compounds		Chem. Mater. 15, 3148 (2003)

TABLE A-continued







MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Metal carbene complexes		US20080018221
Phosphorescent OLED host materials		
Red hosts		
Arylcarbazoles		Appl. Phys. Lett. 78, 1622 (2001)
Metal 8-hydroxyquinolates (e.g., Alq ₃ , BAlq)		Nature 395, 151 (1998)
		US20060202194
		WO2005014551
		WO2006072002

TABLE A-continued

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Metal phenoxy-benzothiazole compounds		Appl. Phys. Lett. 90, 123509 (2007)
Conjugated oligomers and polymers (e.g., polyfluorene)		Org. Electron. 1, 15 (2000)
Aromatic fused rings		WO2009066779, WO2009066778, WO2009063833, US20090045731, US20090045730, WO2009008311, US20090008605, US20090009065
Zinc complexes		WO2010056066
Chrysene based compounds		WO2011086863
Green hosts		
Arylcarbazoles		Appl. Phys. Lett. 78, 1622 (2001)
		US20030175553

TABLE A-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Aryltriphenylene compounds		WO2001039234
Aryltriphenylene compounds		US20060280965
Aryltriphenylene compounds		US20060280965
Poly-fused heteroaryl compounds		WO2009021126
Poly-fused heteroaryl compounds		US20090309488 US20090302743 US20100012931

TABLE A-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Donor acceptor type molecules		WO2008056746
		WO2010107244
Aza-carbazole/ DBT/ DBF		JP2008074939
		US20100187984
Polymers (e.g., PVK)		Appl. Phys. Lett. 77, 2280(2000)

TABLE A-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Spirofluorene compounds		WO2004093207
Metal phenoxybenzoxazole compounds		WO2005089025
Metal phenoxybenzoxazole compounds		WO2006132173
Metal phenoxybenzoxazole compounds		JP200511610
Spirofluorene-carbazole compounds		JP2007254297

TABLE A-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Indolo- carbazoles		JP2007254297
		WO2007063796
		WO2007063754
5-member ring electron deficient heterocycles (e.g., triazole, oxadiazole)		J. Appl. Phys. 90, 5048 (2001)
		WO2004107822

TABLE A-continued





MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Tetra-phenylene complexes		US20050112407
Metal phenoxy-pyridine compounds		WO2005030900
Metal coordination complexes (e.g., Zn, Al with N ² N ligands)		US20040137268, US20040137267
Arylcarbazoles		Appl. Phys. Lett., 82, 2422 (2003) US20070190359

TABLE A-continued







MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Dibenzo- thiophene/ Dibenzofuran- carbazole compounds		WO2006114966, US20090167162
		US20090167162
		WO2009086028
		US20090030202, US20090017330
		US20100084966
Silicon aryl compounds		US20050238919

TABLE A-continued





MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Silicon/ Germanium aryl compounds		WO2009003898
Aryl benzoyl ester		EP2034538A
Carbazole linked by non- conjugated groups		WO2006100298
Aza- carbazoles		US20040115476
		US20060121308

TABLE A-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
High triplet metal organo-metallic complex	 <p style="text-align: center;">Phosphorescent dopants</p>	US7154114
Red dopants		
Heavy metal porphyrins (e.g., PtOEP)		Nature 395, 151 (1998)
Iridium (III) organo-metallic complexes		Appl. Phys. Lett. 78, 1622 (2001)
		US20030072964
		US20030072964

TABLE A-continued

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		US20060202194
		US20060202194
		US20070087321
		US20080261076 US20100090591
		US20070087321

TABLE A-continued

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		Adv. Mater. 19, 739 (2007)
		WO2009100991
		WO2008101842
		US7232618
Platinum (II) organo- metallic complexes		WO2003040257

TABLE A-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Osmium (III) complexes	 	US20070103060 Chem. Mater. 17, 3532 (2005)
Ruthenium (II) complexes		Adv. Mater. 17, 1059 (2005)
Rhenium (I), (II), and (III) complexes		US20050244673
Green dopants		
Iridium (III) organo- metallic complexes	 and its derivatives	Inorg. Chem. 40, 1704 (2001)

TABLE A-continued




MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		US20020034656
		US7332232
		US20090108737

TABLE A-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
	 <p>The structure shows an Ir(III) center coordinated to two phenylpyridine ligands (each in brackets with a subscript 2) and a 3-phenylphenyl ligand.</p>	WO2010028151
	 <p>The structure shows an Ir(III) center coordinated to two phenylpyridine ligands (each in brackets with a subscript 2) and a 1-phenyl-1H-imidazole ligand.</p>	EP1841834B
	 <p>The structure shows a trimeric Ir(III) complex where each Ir center is coordinated to two phenylpyridine ligands (each in brackets with a subscript 3) and a phenyl ring.</p>	US20060127696
	 <p>The structure shows a trimeric Ir(III) complex where each Ir center is coordinated to two phenylpyridine ligands (each in brackets with a subscript 3) and a phenyl ring.</p>	US20090039776
	 <p>The structure shows a trimeric Ir(III) complex where each Ir center is coordinated to two phenylpyridine ligands (each in brackets with a subscript 3) and a benzothiophene ligand.</p>	US6921915

TABLE A-continued

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
	<p>The structure shows an iridium (Ir) center coordinated to two terpyridine-like ligands (each with a benzene ring fused to a pyridine ring) and one thienopyridine ligand (a benzene ring fused to a pyridine ring with a sulfur atom at the 2-position).</p>	US20100244004
	<p>The structure shows an iridium (Ir) center coordinated to two terpyridine-like ligands (each with a benzene ring fused to a pyridine ring) and one 2,6-dimethylphenoxide ligand (a benzene ring with two methyl groups and an oxygen atom).</p>	US6687266
	<p>The structure shows an iridium (Ir) center coordinated to three terpyridine-like ligands (each with a benzene ring fused to a pyridine ring).</p>	Chem. Mater. 16, 2480 (2004)
	<p>The structure shows an iridium (Ir) center coordinated to three terpyridine-like ligands (each with a benzene ring fused to a pyridine ring).</p>	US20070190359
	<p>The structure shows an iridium (Ir) center coordinated to three terpyridine-like ligands (each with a benzene ring fused to a pyridine ring).</p>	US 20060008670 JP2007123392
	<p>The structure shows an iridium (Ir) center coordinated to three terpyridine-like ligands (each with a benzene ring fused to a pyridine ring).</p>	WO2010086089, WO2011044988

TABLE A-continued

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		Adv. Mater. 16, 2003 (2004)
		Angew. Chem. Int. Ed. 2006, 45, 7800
		WO2009050290
		US20090165846
		US20080015355
		US20010015432

TABLE A-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		US20100295032
Monomer for polymeric metal organo-metallic compounds		US7250226, US7396598
Pt (II) organo-metallic complexes, including polydentate ligands		Appl. Phys. Lett. 86, 153505 (2005)
		Appl. Phys. Lett. 86, 153505 (2005)
		Chem. Lett. 34, 592 (2005)

TABLE A-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		WO2002015645
		US20060263635
		US20060182992 US20070103060
Cu complexes		WO2009000673
		US20070111026

TABLE A-continued

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Gold complexes		Chem. Commun. 2906 (2005)
Rhenium(III) complexes		Inorg. Chem. 42, 1248 (2003)
Osmium(II) complexes		US7279704
Deuterated organo-metallic complexes		US20030138657

TABLE A-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Organo-metallic complexes with two or more metal centers		US20030152802
		US7090928
Blue dopants		
Iridium(III) organo-metallic complexes		WO2002002714
		WO2006009024
		US20060251923 US20110057559 US20110204333

TABLE A-continued

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		US7393599, WO2006056418, US20050260441, WO2005019373
		US7534505
		WO2011051404
		US7445855
		US20070190359, US20080297033 US20100148663

TABLE A-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		US7338722
		US20020134984
		Angew. Chem. Int. Ed. 47, 4542 (2008)
		Chem. Mater. 18, 5119 (2006)
		Inorg. Chem. 46, 4308 (2007)

TABLE A-continued






MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		WO2005123873
		WO2005123873
		WO2007004380
		WO2006082742
Osmium(II) complexes		US7279704

TABLE A-continued








MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		Organo-metallics 23, 3745 (2004)
Gold complexes		Appl. Phys. Lett. 74, 1361 (1999)
Platinum (II) complexes		WO2006098120, WO2006103874
Pt tetradentate complexes with at least one metal-carbene bond		US7655323
Exciton/hole blocking layer materials		
Bathocuproine compounds (e.g., BCP, BPhen)		Appl. Phys. Lett. 75, 4 (1999)
		Appl. Phys. Lett. 79, 449 (2001)
Metal 8-hydroxy-quinolates (e.g., BAlq)		Appl. Phys. Lett. 81, 162 (2002)

TABLE A-continued




MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
5-member ring electron deficient heterocycles such as triazole, oxadiazole, imidazole, benzoimidazole		Appl. Phys. Lett. 81, 162 (2002)
Triphenylene compounds		US20050025993
Fluorinated aromatic compounds		Appl. Phys. Lett. 79, 156 (2001)

TABLE A-continued

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Phenothiazine-S-oxide		WO2008132085
Silylated five-membered nitrogen, oxygen, sulfur or phosphorus dibenzo-heterocycles		WO2010079051
Aza-carbazoles		US20060121308
Electron transporting materials		
Anthracene-benzoimidazole compounds		WO2003060956
		US20090179554

TABLE A-continued










MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Aza triphenylene derivatives		US20090115316
Anthracene-benzothiazole compounds		Appl. Phys. Lett. 89, 063504 (2006)
Metal 8-hydroxy-quinolates (e.g., Alq ₃ , Zrq ₄)		Appl. Phys. Lett. 51, 913 (1987) US7230107
Metal hydroxy-benzo-quinolates		Chem. Lett. 5, 905 (199.3)
Bathocuproine compounds such as BCP, BPhen, etc		Appl. Phys. Lett. 91, 263503 (2007)
		Appl. Phys. Lett. 79, 449 (2001)

TABLE A-continued

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
5-member ring electron deficient heterocycles (e.g., triazole, oxadiazole, imidazole, benzoimidazole)		Appl. Phys. Lett. 74, 865 (1999)
		Appl. Phys. Lett. 55, 1489 (1989)
		Jpn. J. Apply. Phys. 32, L917 (1993)
Silole compounds		Org. Electron. 4, 113 (2003)
Arylborane compounds		J. Am. Chem. Soc. 120, 9714 (1998)
Fluorinated aromatic compounds		J. Am. Chem. Soc. 122, 1832 (2000)

TABLE A-continued

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Fullerene (e.g., C ₆₀)		US20090101870
Triazine complexes		US20040036077
Zn (N [^] N) complexes		US6528187

The invention is explained in greater detail by the following examples, without wishing to restrict it thereby. The person skilled in the art will be able to produce further electronic devices on the basis of the descriptions without inventive step and will thus be able to carry out the invention throughout the range claimed.

EXAMPLES


The following syntheses are carried out, unless indicated otherwise, in dried solvents under a protective-gas atmo-

sphere. The metal complexes are additionally handled with exclusion of light. The solvents and reagents can be purchased, for example, from Sigma-ALDRICH or ABCR.

50



EXAMPLE 1: Synthesis of 3,4-dihydrodibenzo[b,i]imidazo[2,1,5-de]quinolizine was prepared in accordance with Scheme 1.

Scheme 1




251

252



A. Synthesis of 4-chlorobutanol


ics separated. Solvent removal followed by distillation yielded the product as a colorless oil, 8 g.



B. Synthesis of 2-bromo-4-chlorobutanol

30


35



A solution of oxalyl chloride (22.54 ml, 263 mmol) in DCM (400 ml) was cooled in an i PrOH/ CO_2 bath. DMSO (37.3 ml, 525 mmol) was slowly via syringe and stirred cold for 1 hour. A solution of 4-chlorobutan-1-ol (19 g, 175 mmol) in 50 mL DCM was added dropwise. The col mixture was stirred for one hour, then, triethylamine (110 ml, 788 mmol) was slowly added. The suspension was stirred cold for 30 minutes, then allowed to warm to room temperature. The reaction was quenched with water, acidified and organ-

4-chlorobutanol (7.939 g, 74.5 mmol) was dissolved in DCM (300 ml) and cooled in an ice bath. A solution of dibromine (4.00 ml, 78 mmol) in DCM (50 ml) was added over about 1 hr. After addition the red solution was stirred cold for 30 minutes, then warmed slowly to room temperature and stirred one more hour. Water was added, the organics were separated, and drying and solvent removal yielded the crude product as a pale yellow oil, 1.57 g (80%).


C. Synthesis of 4-bromophenanthridin-6-amine



253


2,6-dibromoaniline (15.33 g, 61.1 mmol), 2-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)benzotrile (7.0 g, 30.6 mmol), and potassium phosphate monohydrate (21.11 g, 92 mmol) were combined in dioxane (120 ml) and water (7.49 ml). The mixture was degassed, then added (dppf)PdCl₂ complex with DCM (0.749 g, 0.917 mmol) was added and the mixture was refluxed for 4 hours. The black mixture was partitioned between EtOAc and water/brine. The organic layer was washed with brine, dried, and solvent was removed. Dissolution in 500 mL EtOAc followed by elution through a silica plug using EtOAc and solvent removal yielded an orange residue that was purified by column chromatography to yield the product as a yellow/orange solid, 5.86 g, 70%.

D. Synthesis of 5-bromo-3-(2-chloroethyl)imidazo[1,2-f]phenanthridine




4-bromophenanthridin-6-amine (5.86, 21.46 mmol), 2-bromo-4-chlorobutanal (5.36 g, 28.9 mmol), and sodium bicarbonate (3.60 g, 42.9 mmol) were combined in 2-propanol (102 ml) and water (5.11 ml). The suspension was stirred at room temperature for 4 hours, then at reflux for 16 hours. Solvent was removed under vacuum and the residue coated on celite. Column chromatography yielded a mixture of the product and starting amidine, which was treated with excess acetyl chloride and triethylamine in DCM. After workup the desired product was extracted from the acetamide by repeated extraction into heptanes, yielding 3.93 g of yellow, tacky residue (51%).

E. Synthesis of 3,4-dihydrodibenzo[b,ij]imidazo[2,1,5-de]quinolizine



254

-continued



5-bromo-3-(2-chloroethyl)imidazo[1,2-f]phenanthridine (3.93 g, 10.93 mmol) was dissolved in THF (200 ml), cooled in an ice bath, and isopropylmagnesium chloride solution in THF (2.0M, 6.01 ml, 12.02 mmol) was slowly added. The solution was stirred for 30 minutes cold, then warmed to room temperature and stirred for 2 more hours. The reaction was quenched, extracted into DCM, and the reaction product was purified using column chromatography to yield 1.90 g of a pale beige, crystalline solid (71%).


An X-ray structure of 3,4-dihydrodibenzo[b,ij]imidazo[2,1,5-de]quinolizine is shown in FIG. 5. The crystal structure of 3,4-dihydrodibenzo[b,ij]imidazo[2,1,5-de]quinolizine may be defined by one or more of the characteristics listed in the following table.

Formula	C ₁₇ H ₁₂ N ₂	Data/restr./param.	2107/0/173
MW	244.29	T [K]	100(1)
Crystal system	Orthorhombic	ρ_{calc} [g cm ⁻³]	1.410
Space group	P2 ₁ 2 ₁ 2 ₁	μ_{calc} [mm ⁻¹]	0.084
Color	Colorless	Total reflections	22768
a [Å]	6.6974(5)	Z	4
b [Å]	11.0502(8)	F(000)	512
c [Å]	15.5459(10)	T _{min} /T _{max}	0.894
α [°]	90	Cryst. Size [mm ³]	0.42 × 0.22 × 0.08
β [°]	90	R ₁ [I > 2 σ (I)] ^a	0.0405
γ [°]	90	wR ₂ (all data) ^a	0.1173
V [Å ³]	1150.52(14)	GOF ^a	1.075

$$^a R_1 = \frac{\sum (|F_o| - |F_c|)}{\sum |F_o|}; wR_2 = \frac{[\sum (w(F_o^2 - F_c^2))^2]}{[\sum (w(F_o^2))^2]}^{1/2}; GOF = \frac{[\sum w(F_o - |F_c|)^2 / (n - m)]^{1/2}}{[\sum w(F_o^2)]^{1/2}}$$



$$^a R_1 = \frac{\sum (|F_o| - |F_c|)}{\sum |F_o|}; wR_2 = \frac{[\sum (w(F_o^2 - F_c^2))^2]}{[\sum (w(F_o^2))^2]}^{1/2}; GOF = \frac{[\sum w(|F_o| - |F_c|)^2 / (n - m)]^{1/2}}{[\sum w(F_o^2)]^{1/2}}$$

EXAMPLE 2: Synthesis of 4,4-dimethyl-3,4-dihydro-1,2a1-diaza-4-silabenzof[fg]aceanthrylene and 3,3-dimethyl-3,4-dihydro-1,2a1-diaza-3-silabenzof[fg]aceanthrylene:



The ligands above are prepared in accordance with Scheme 2 below.

Scheme 2



A. Synthesis of
5-bromoimidazo[1,2-f]phenanthridineB. Synthesis of
3,5-dibromoimidazo[1,2-f]phenanthridine

4-bromophenanthridin-6-amine (4.0 g, 14.7 mmol) was dissolved in 100 mL of *i*PrOH. Chloroacetaldehyde (50% in water, 3.6 g, 22 mmol, 1.5 equiv.) was added, followed by NaHCO_3 (2.5 g, 2 equiv.), and the mixture was refluxed for 2 hours, then cooled in an ice bath. The tan solid was filtered off, washing with MeOH. The receiving flask was changed and the solid was washed with water, resulting in clean, off-white product, 3.2 g. The aqueous washes were extracted with EtOAc and these extracts were combined with the alcoholic washes from the initial filtration. Solvent was removed to yield 1.3 g of an orange solid which was recrystallized from EtOAc, yielding more clean product as tan needles, 0.46 g. Total yield: 3.5 g (80%).

Dissolved 5-bromoimidazo[1,2-f]phenanthridine (2.0 g, 6.73 mmol) in DMF (125 ml), then added a solution of NBS (1.318 g, 7.40 mmol) in 10 mL of DMF slowly under nitrogen. After stirring for 3 hours at room temperature, then gentle heating for 16 hours, the reaction mixture was partitioned between 300 mL of water and EtOAc. The aqueous layer was further extracted with EtOAc, the organics washed with water, and the product was isolated by column chromatography as a pale yellow solid, 1.99 g (79%).


257

C. Synthesis of 5-bromo-3-((chloromethyl)dimethylsilyl)imidazo[1,2-f]phenanthridine




3,5-dibromoimidazo[1,2-f]phenanthridine (0.48 g, 1.28 mmol) and chloro(chloromethyl)dimethylsilane (0.17 ml, 1.28 mmol) were dissolved in THF (25 ml) and cooled in iPrOH/CO₂ bath. Butyllithium solution in hexanes (2.5 M, 0.51 ml, 1.28 mmol) was added slowly, the mixture was stirred cold for 30 minutes, then allowed to warm to room temperature. Brine was added to quench the reaction, the organics were extracted into EtOAc and purified by column chromatography to yield the product as a colorless, tacky residue, 0.16 g (31%).

D. Synthesis of 4,4-dimethyl-3,4-dihydro-1,2a1-diaza-4-silabenzof[fg]aceanthrylene and 3,3-dimethyl-3,4-dihydro-1,2a1-diaza-3-silabenzof[fg]aceanthrylene



258

-continued



5-bromo-3-((chloromethyl)dimethylsilyl)imidazo[1,2-f]phenanthridine (0.13 g, 0.322 mmol) was dissolved in THF (25 ml) and cooled in an ice bath. Isopropylmagnesium chloride solution in THF (2.0 M, 0.18 ml, 0.36 mmol) was added slowly, then warmed to room temperature. The reaction was quenched with brine, organics were extracted with DCM, and the mixture chromatographed to yield 16 mg of 4,4-dimethyl-3,4-dihydro-1,2a1-diaza-4-silabenzof[fg]aceanthrylene as a tacky residue (17%), and 33 mg of 3,3-dimethyl-3,4-dihydro-1,2a1-diaza-3-silabenzof[fg]aceanthrylene as a crystalline solid (36%).

Furthermore, all organic materials used in this example were sublimation-purified and analyzed by high-performance liquid chromatography (Tosoh TSKgel ODS-100Z), and materials having 99.9% or higher of an absorption intensity area ratio at 254 nm were used.

An X-ray structure of 3,3-dimethyl-3,4-dihydro-1,2a1-diaza-3-silabenzof[fg]aceanthrylene is shown in FIG. 6. The crystal structure of 3,3-dimethyl-3,4-dihydro-1,2a1-diaza-3-silabenzof[fg]aceanthrylene may be defined by one or more of the characteristics listed in the following table.

Formula	C ₁₈ H ₁₆ N ₂ Si	Data/restr./param.	5211/0/384
MW	288.42	T [K]	100(1)
Crystal system	Triclinic	ρ_{calc} [g cm ⁻³]	1.341
Space group	P-1	μ_{calc} [mm ⁻¹]	0.159
Color	Colorless	Total reflections	54823
a [Å]	9.1888(8)	Z	4
b [Å]	12.5217(11)	F(000)	608
c [Å]	12.5428(12)	T _{min} /T _{max}	0.954
α [°]	82.769(4)	Cryst. Size [mm ³]	0.28 × 0.18 × 0.15
β [°]	89.062(4)	R ₁ [I > 2 σ (I)] ^a	0.0324
γ [°]	86.121(2)	wR ₂ (all data) ^a	0.0892
V [Å ³]	1428.4(2)	GOF ^a	1.055


^aR₁ = $\sum(|F_o| - |F_c|)/\sum|F_o|$; wR₂ = $[\sum(w(F_o^2 - F_c^2)^2)/\sum(w(F_o^2)^2)]^{1/2}$; GOF = $[\sum w(|F_o| - |F_c|)^2/(n - m)]^{1/2}$

EXAMPLE 3: Synthesis of platinum(II) complex of 6-isopropyl-10-((9-(4-isopropylpyridin-2-yl)-9H-carbazol-2-yl)oxy)-3,4-dihydrodibenzo[b,i]imidazo[2,1,5-de]quinoxaline:

259



260

Scheme 3




A. Synthesis of 2-Bromo-5-methoxybenzonitrile


B. Synthesis of 5-Methoxy-2-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)benzonitrile



40



50




A mixture of 2-bromo-5-methoxybenzaldehyde (100 g, 0.47 mol, 1 equiv), hydroxylamine hydrochloride (64.8 g, 0.93 mol, 2 equiv), sodium acetate (76.42 g, 0.93 mol, 2 equiv) and glacial acetic acid (500 mL) was refluxed for 16 hours. The acetic acid was removed under reduced pressure and the residue was extracted with dichloromethane (~400 mL). The organic layer was washed with saturated brine (3×200 mL), dried over sodium sulfate and concentrated under reduced pressure. The resulting residue was triturated with heptanes (50 mL) and solids washed with additional heptanes (2×50 mL) to give the desired product as a white powder (82.6 g, 86% yield).

A mixture of 2-bromo-5-methoxybenzonitrile (82.6 g, 0.39 mol, 1 equiv), bis(pinacolato)diboron (109.1 g, 0.43 mol, 1.1 equiv) and potassium acetate (115.3 g, 1.17 mol, 3 equiv) in a mixture of 1,4-dioxane (400 mL) and DMSO (40 mL) was sparged with nitrogen for 1 hour. Pd(dppf)Cl₂ (7.13 g, 5 mol %) was added and reaction mixture was gently heated at 60° C. for 2 hours then refluxed for 16 hours. The mixture was filtered through celite and the solids isolated from the filtrates were washed with isopropanol and heptanes to give the desired product as an off-white solid (57.41 g, 57% yield). Additional product (~10 g) was isolated from the filtrates.

261


C. Synthesis of

4-Bromo-2-isopropyl-8-methoxyphenanthridin-6-amine



A mixture of 5-methoxy-2-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)benzo-nitrile (57.41 g, 0.22 mol, 1 equiv), 2,6-dibromo-4-isopropylaniline (64.92 g, 0.22 mol, 1 equiv) and potassium phosphate (153.1 g, 0.66 mol, 3 equiv) in a 4:1 mixture of toluene and water (1250 mL) was sparged with nitrogen for 1 hour. *trans*-Pd(PPh₃)₂Cl₂ (7.8 g, 11 mmol, 0.05 equiv) was added and the reaction mixture was refluxed for 20 hours. Additional potassium phosphate (77 g, 0.33 mol, 1.5 equiv) and *trans*-Pd(PPh₃)₂Cl₂ (1 g, 1.43 mmol, 0.0065 equiv) were added and the reaction mixture was refluxed for an additional 3 hours. The layers were separated and the organic layer was washed with hot water (2×400 mL). The organic layer was dried over sodium sulfate and concentrated under reduced pressure. The resulting solid was triturated sequentially with dichloromethane and heptanes. Column chromatography gave the desired product (30 g).

D. Synthesis of 6-Isopropyl-10-((9-(4-isopropylpyridin-2-yl)-9H-carbazol-2-yl)oxy)-3,4-dihydro-dibenzo[b,ij]imidazo[2,1,5-de]quinolizine




A suspension of 4-bromo-2-isopropyl-8-methoxyphenanthridin-6-amine (8.9 g, 25.8 mmol, 1 equiv), *p*-toluenesulfonic acid monohydrate (348 mg), freshly prepared

262


2-bromo-4-chlorobutanal (24 g, 129 mmol, 5 equiv) and iso-propanol (500 mL) was stirred at room temperature for 2.5 hours. Sodium carbonate (6.5 g, 77.4 mmol, 3 equiv) and deionized water (32 ml) were added, and the reaction mixture was refluxed for 16 hours. After cooling to room temperature, the volume of reaction mixture was reduced to ~100 mL under reduced pressure. The mixture was diluted with ethyl acetate (350 mL) and washed with saturated brine (200 mL). The organic layer was dried over sodium sulfate and concentrated under reduced pressure. The crude product was purified by column chromatography to yield 8.44 g of product (76% yield).

E. Synthesis of 6-Isopropyl-10-methoxy-3,4-dihydro-dibenzo[b,ij]imidazo[2,1,5-de]quinolizine




A solution of 6-Isopropyl-10-((9-(4-isopropylpyridin-2-yl)-9H-carbazol-2-yl)oxy)-3,4-dihydro-dibenzo[b,ij]imidazo[2,1,5-de]quinolizine (8.44 g, 19.6 mmol, 1.0 equiv) in dry THF (250 mL) was sparged with nitrogen for 30 minutes). After cooling to 0° C., 2M isopropylmagnesium chloride (14.7 mL, 29.4 mmol, 1.5 equiv) in THF was added dropwise. The reaction mixture was warmed up to room temperature and stirred for 16 hours. The reaction was quenched with water (10 mL) and the THF was removed under reduced pressure. The residue was diluted with ethyl acetate (400 mL) and washed with saturated brine (2×200 mL). The organic layer was dried over sodium sulfate and the residue was purified by column chromatography to give 3.6 g of product (58% yield).

F. Synthesis of 6-Isopropyl-3,4-dihydrodibenzo[b,ij]imidazo[2,1,5-de]quinolizine-10-ol




263

-continued



Boron tribromide (5.4 mL, 56.78 mmol, 5 equiv) was added dropwise at -78°C . to a solution of 6-Isopropyl-10-methoxy-3,4-dihydrodibenzo[b,i]imidazo[2,1,5-de]quinoxaline (3.6 g, 11.36 mmol, 1 equiv) in dichloromethane (200 mL). The reaction was warmed to room temperature and stirred for 16 hours. The reaction mixture was carefully poured into 300 ml of ice water and the resulting solid was filtered and washed sequentially with water (70 mL), ethyl acetate (40 mL) and heptanes (40 mL) to give 3.6 g of product (quantitative yield).


G. Synthesis of 4'-Bromo-2-nitro-1,1'-biphenyl



A solution of potassium carbonate (84 g, 608 mmol, 3.0 equiv) in water (450 mL) was added to a mixture of 2-iodo-nitrobenzene (50 g, 200 mmol, 1.0 equiv) and 4-bromobenzeneboronic acid (40.7 g, 202 mol, 1.0 equiv) in 1,2-dimethoxyethane (660 mL). The reaction was sparged with nitrogen for 5.0 minutes. Tetrakis(triphenylphosphine) palladium(0) (2.32 g, 2 mmol, 1 mol %) was added and the mixture was sparged with nitrogen for an additional 10 minutes. After refluxing for 16 hours, the reaction was cooled to room temperature and the layers were separated. The aqueous layer was extracted with ethyl acetate (500 mL). The combined organic extracts were washed with saturated brine (500 mL), dried over sodium sulfate, filtered and concentrated under reduced pressure. The residue was dissolved in 25% ethyl acetate in heptanes (300 mL) and vacuum filtered through a pad of silica gel (135 g). The pad was rinsed with 25% ethyl acetate in heptanes (3x350 mL). The combined filtrates were concentrated under reduced pressure giving an orange solid. This residue was suspended in heptanes (150 mL) and heated to 40°C . for 20 minutes. The suspension was allowed to cool to room temperature for 1.0 hour. The solid was collected by vacuum filtration, washed with heptanes (50 mL) and dried to give 4'-bromo-2-nitro-1,1'-biphenyl as a yellow solid (49.16 g, 88.4% yield).


264

H. Synthesis of 2-Bromo-9H-carbazole



Triphenylphosphine (156.3 g, 596 mmol, 2.5 equiv) was added over 5 minutes to a solution of 4'-bromo-2-nitro-1,1'-biphenyl (66.25 g, 238 mmol, 1.0 equiv) in 1,2-dichlorobenzene (460 mL). The reaction was sparged with nitrogen 5 minutes, then refluxed for 16 hours. The reaction was cooled to room temperature and vacuum distilled to remove most of the 1,2-dichlorobenzene (450 mL). This dark residue was dissolved in ethyl acetate (1.5 L) and treated with decolorizing carbon (50 g) at 50°C . for 30 minutes. After cooling, the mixture was filtered through Celite (200 g), then washed with ethyl acetate washes (2x650 mL). The combined filtrates were concentrated under reduced pressure to a volume of ~ 500 mL. The solution was cooled to room temperature and after 1.5 hours, the resulting pale tan solid (triphenylphosphine oxide) was removed by filtration and discarded. The filtrate was concentrated under reduced pressure. The residue was dissolved in methanol (600 mL) and stored at room temperature for 16 hours. The resulting tan solid was filtered, washed with methanol (2x100 mL) and dried under vacuum at 40°C . to give 2-bromo-9H-carbazole as a pale tan solid (33.5 g, 57.2% yield).

I. Synthesis of 2-Bromo-9-(4-isopropylpyridin-2-yl)-9H-carbazole




A suspension of 2-bromo-9H-carbazole (13.9 g, 56.5 mmol, 1 equiv), 4-isopropyl-2-chloropyridine (15.86 g, 101.7 mmol, 1.8 equiv), L-proline (1.3 g, 11.3 mmol, 0.2 equiv), copper (I) iodide (0.95 g, 5.65 mmol, 0.1 equiv), potassium carbonate (19.48 g, 141.25 mmol, 2.5 equiv) and

265

DMSO (80 mL) was sparged with nitrogen for 5 minutes. The mixture was heated at 95° C. for 16 hours. Additional 4-isopropyl-2-chloropyridine (1.58 g, 10.12 mmol, 0.18 equiv) was added, the reaction mixture was heated at 155° C. for an additional 24 hours. The reaction mixture was cooled to room temperature, diluted with ethyl acetate (750 mL), and vacuum filtered through celite (70 g). The celite pad was washed with ethyl acetate washes (2×100 mL). The combined filtrates were washed with saturated brine (3×500 mL), dried over sodium sulfate, filtered and concentrated under reduced pressure. This residue was purified by column chromatography to give 1.8 g of product as a brown oil (8.6% yield).


J. Synthesis of 6-Isopropyl-10-((9-(4-isopropylpyridin-2-yl)-9H-carbazol-2-yl)oxy)-3,4-dihydrodibenzo[b,i]imidazo[2,1,5-de]quinolizine



A mixture of 6-Isopropyl-3,4-dihydrodibenzo[b,i]imidazo[2,1,5-de]quinolin-10-ol (1.5 g, 4.93 mmol, 1 equiv), 2-Bromo-9-(4-isopropylpyridin-2-yl)-9H-carbazole (1.8 g, 4.93 mmol, 1 equiv), potassium phosphate (5.68 g, 24.65 mmol, 5 equiv), copper(I) iodide (0.47 g, 2.47 mmol, 0.5 equiv), picolinic acid (1.52 g, 12.33 mmol, 2.5 equiv) and DMSO (150 mL) was heated at 150° C. for 4.5 hours. After cooling to room temperature, the reaction mixture was poured into water (700 mL) and extracted with ethyl acetate (4×150 mL). The combined organic layers were dried over sodium sulfate and concentrated in under reduced pressure. The crude product was purified by column chromatography to yield product as a tan solid, 1.25 g (43% yield).


266


K. Synthesis of platinum(II) complex of 6-isopropyl-10-((9-(4-isopropylpyridin-2-yl)-9H-carbazol-2-yl)oxy)-3,4-dihydrodibenzo[b,i]imidazo[2,1,5-de]quinolizine



6-Isopropyl-10-((9-(4-isopropylpyridin-2-yl)-9H-carbazol-2-yl)oxy)-3,4-dihydrodibenzo[b,i]imidazo[2,1,5-de]quinolizine (400 mg, 0.68 mmol, 1 equiv) was dissolved in 60 ml of glacial acetic acid and sparged with nitrogen for 30 minutes. Then K₂PtCl₄ (283 mg, 0.68 mmol, 1 equiv) was added, and the reaction mixture was refluxed for 40 hours. After cooling to room temperature, the orange precipitate was filtered and washed sequentially with water (3×15 mL) and heptanes (10 ml×2 times). The crude product (340 mg) was dissolved in 10 ml of dichloromethane and filtered through a plug of silica gel to remove residual K₂PtCl₄, eluting with additional dichloromethane (10 mL). The filtrate was reduced to half its volume and diluted with heptanes (10 mL). The product was filtered and triturated with a 10% solution of dichloromethane in heptanes (10 mL) to give product as a light yellow solid (140 mg, 26% yield). Additional product was isolated from the acetic acid and dichloromethane/heptane filtrates.

EXAMPLE 4: Synthesis of (3-phenyl-1H-pyrazole)₂Ir(MeOH)₂(OTf).







A. Synthesis of (3-phenyl-1H-pyrazole)₂IrCl₂
Dimer


Iridium chloride hydrate (6.00 g, 17.02 mmol) and 1-phenyl-1H-pyrazole (5.89 g, 40.9 mmol) were combined in 2-ethoxyethanol (120 ml) and water (40 ml). The reaction mixture was heated to reflux for 16 hours under nitrogen. The resulting solid was filtered off and washed with methanol and dried to yield 8.3 g of the iridium dimer.

The iridium dimer of Example 4A (8.3 g, 8.07 mmol) was dissolved in 100 mL of DCM and a solution of silver triflate (4.36 g, 16.96 mmol) in 20 mL of methanol was added. The reaction mixture was stirred at room temperature under nitrogen for 1 hour. The mixture was filtered through celite and the cake was washed with DCM. The filtrates were evaporated to yield 10.85 g of (3-phenyl-1H-pyrazole)₂Ir (MeOH)₂(OTf) (97%).


EXAMPLE 5: Exemplary Compound 35 was Prepared According to Scheme 5.



269



A. Synthesis of imidazo[1,2-f]phenanthridine




A mixture of 2-phenyl-1H-imidazole (10.0 g, 69.3 mmol, 1 equiv), 1,2-dibromobenzene (19.63 g, 83.2 mmol, 1.2 equiv), cesium carbonate (67.79 g, 208.0 mmol, 3 equiv), Xantphos (4.01 g, 6.9 mmol, 0.1 equiv) and tetrakis(triphenylphosphine)palladium (8.01 g, 6.9 mmol, 0.1 equiv) in DMF (550 mL) was sparged with a stream of nitrogen for 15 minutes. The mixture was heated at 140° C. for 24 hours, then concentrated under reduced pressure. The residue was

270


purified by column chromatography to imidazo[1,2-f]phenanthridine (10 g, 67% yield) as pale yellow solid.

B. Synthesis of 3-Bromoimidazo[1,2-f]phenanthridine



N-bromosuccinimide (1.62 g, 9.1 mmol, 1 equiv) was added to a solution of 15 (1.99 g, 9.1 mmol, 1 equiv) in DMF (32 mL) at 0° C. After stirring at room temperature for 18 hours, the reaction was diluted with water (300 mL) and sequentially extracted with 10% dichloromethane in methyl t-butyl ether (3×500 mL), ethyl acetate (2×300 mL) and dichloromethane (400 mL). The combined organic layers were dried over sodium sulfate, filtered and concentrated under reduced pressure. The residue was purified by column chromatography to yield 3-Bromoimidazo[1,2-f]phenanthridine (1.66 g, 65% yield) as an off-white solid.


C. Synthesis of tert-Butyl 2-(imidazo[1,2-f]phenanthridin-3-yl)acetate



Di-p-bromobis(tri-t-butylphosphino)dipalladium (I) (2.01 g, 2.5 mmol, 0.05 equiv) was added to a solution of 16 (15.4 g, 51.8 mmol, 1 equiv) in anhydrous tetrahydrofuran (220 mL) and the solution was sparged with a stream of nitrogen for 15 minutes. 0.5M 2-tert-butoxy-2-oxoethylzinc bromide in diethyl ether (155 mL, 77.7 mmol, 1.5 equiv) was added under nitrogen. The reaction was stirred at 60° C. for 16 hours. Additional 0.5M 2-tert-butoxy-2-oxoethylzinc chloride solution (155 mL, 77.7 mmol, 1.5 equiv) and di-g-bromobis(tri-t-butylphosphino)-dipalladium (I) (2.01 g, 2.5 mmol, 0.05 equiv) were added and the reaction was stirred at 60° C. until LC/MS analysis indicated it was complete. The reaction mixture was concentrated under reduced pressure. The residue was dissolved in dichloromethane (1 L) and filtered through a Celite pad. The filtrate was concentrated under reduced pressure. The residue was purified by column chromatography to give tert-Butyl 2-(imidazo[1,2-f]phenanthridin-3-yl)acetate (5 g, 30% yield) as an orange solid.


271

D. Synthesis of Methyl 2-(imidazo[1,2-f]phenanthridin-3-yl)acetate hydrochloride



A solution of 17 (2.8 g, 8.4 mmol, 1 equiv) in 1.25M HCl (55 mL, 68.7 mmol, 6.5 equiv) in methanol was stirred at 60° C. for 16 hours. The reaction mixture was concentrated under reduced pressure. The residue was washed with diethyl ether and dried under vacuum for 16 hours at 40° C. to give methyl 2-(imidazo[1,2-f]phenanthridin-3-yl)acetate hydrochloride (2.5 g, 100% yield) as an off-white solid.


E. Synthesis of Methyl 2-(imidazo[1,2-f]phenanthridin-3-yl)-2-methylpropanoate



A 60% dispersion of sodium hydride in mineral oil (2.45 g, 61.2 mmol, 5 equiv) and iodomethane (2 mL, 32.1 mmol, 2.6 equiv) were sequentially added to a solution of methyl 2-(imidazo[1,2-f]phenanthridin-3-yl)acetate hydrochloride (4.0 g, 12.24 mmol, 1 equiv) in anhydrous DMF (45 mL) at 5° C. The mixture was stirred in a cooling bath for 30 minutes, warmed to room temperature and stirred for 6 hours. Additional iodomethane (1.2 mL, 19.2 mmol, 1.6 equiv) was added. The reaction was stirred at room temperature over a weekend, quenched with methanol (32 mL) and concentrated under reduced pressure. The residual oil was diluted with dichloromethane (350 mL) and washed with water (100 mL). The aqueous layer was extracted with dichloromethane (2×100 mL). The combined organic layers were washed with saturated ammonium chloride (100 mL), dried over sodium sulfate, filtered and concentrated under reduced pressure. The residue was purified by column chromatography to give methyl 2-(imidazo[1,2-f]phenanthridin-3-yl)-2-methylpropanoate (1.6 g, 41% yield) as an off-white solid.


272

F. Synthesis of 2-(Imidazo[1,2-f]phenanthridin-3-yl)-2-methylpropanoic acid




A solution of methyl 2-(imidazo[1,2-f]phenanthridin-3-yl)-2-methylpropanoate (1.6 g, 5.0 mmol, 1 equiv) in methanol (100 mL) was treated with aqueous 1N sodium hydroxide (30 mL, 30 mmol, 6 equiv) and further diluted with water (100 mL). After refluxing for 5 days, the reaction was concentrated under reduced pressure. The residue was dissolved in water (100 mL) and acidified with conc. HCl to pH 5-6. The resulting white suspension was extracted with 1 to 2 mixture of isopropanol and dichloro-methane (4×200 mL). The combined organic layers were dried over sodium sulfate, filtered, concentrated under reduced pressure. The residue was dried under high vacuum at 40° C. for 16 hours to give 2-(Imidazo[1,2-f]phenanthridin-3-yl)-2-methylpropanoic acid (1.3 g, 82% yield) as white solid.

G. Synthesis of 2-(Imidazo[1,2-f]phenanthridin-3-yl)-2-methylpropanoyl chloride




Thionyl chloride (1 mL, 13.7 mmol, 2 equiv) and anhydrous DMF (0.05 mL, 0.6 mmol, 0.11 equiv) were added to a suspension of 2-(Imidazo[1,2-f]phenanthridin-3-yl)-2-methylpropanoic acid (1.3 g, 4.2 mmol, 1 equiv) in anhydrous dichloromethane (100 mL). After stirring at room temperature for 16 hours, the mixture was concentrated under reduced pressure to give the 2-(Imidazo[1,2-f]phenanthridin-3-yl)-2-methylpropanoyl chloride (1.37 g, 100% yield) as an off-white solid.

273


H. Synthesis of 3,3-Dimethyldibenzo[b,ij]imidazo
[2,1,5-de]quinolizin-4(3H)-one

A mixture of 2-(Imidazo[1,2-f]phenanthridin-3-yl)-2-methylpropanoyl chloride (1.37 g, 4.2 mmol, 1 equiv) and anhydrous aluminum chloride (6.0 g, 44.9 mmol, 10 equiv) in anhydrous dichloromethane (60 mL) was stirred at room temperature for 6 hours. The reaction was cooled with an ice-water bath, quenched with ice, diluted with saturated sodium bicarbonate (300 mL) and extracted with dichloromethane (4×400 mL). The combined organic layers were dried over sodium sulfate, filtered and concentrated under reduced pressure. The residue was purified using column chromatography to give 3,3-dimethyldibenzo[b,ij]imidazo[2,1,5-de]quinolizin-4(3H)-one (1 g, 81% yield) as a white solid.


I. Synthesis of 3,3-Dimethyl-3,4-dihydrodibenzo[b,
ij]imidazo[2,1,5-de]quinolizin-4-ol

Sodium borohydride (0.24 g, 6.3 mmol, 2 equiv) was added in one portion to a solution of 3,3-dimethyldibenzo[b,ij]imidazo[2,1,5-de]quinolizin-4(3H)-one (0.9 g, 3.1 mmol, 1 equiv) in ethanol (70 mL) at 5° C. The reaction was stirred at room temperature for 1.5 hours and then quenched with acetone (2 mL). The reaction mixture was concentrated under reduced pressure. The residue was dissolved in methyl t-butyl ether (300 mL), washed with saturated sodium bicarbonate (2×60 mL) and saturated brine (60 mL). The organic layer was dried over sodium sulfate, filtered and concentrated under reduced pressure. The crude product was purified by column chromatography to give 3,3-Dimethyl-3,4-dihydrodibenzo[b,ij]imidazo[2,1,5-de]quinolizin-4-ol (0.9 g, 100% yield) as a white solid.

274

J. o-(3,3-Dimethyl-3,4-dihydrodibenzo[b,ij]imidazo
[2,1,5-de]quinolizin-4-yl) S-methyl carbonodithioate


A 60% dispersion of sodium hydride (0.48 g, 20.2 mmol, 5 equiv) in mineral oil was added to a solution of 3,3-Dimethyl-3,4-dihydrodibenzo[b,ij]imidazo[2,1,5-de]quinolizin-4-ol (0.71 g, 2.46 mmol, 1 equiv) in anhydrous THF (70 mL) at 0° C. After stirring for 30 minutes at 5° C., a solution of imidazole (0.0168 g, 0.24 mmol, 0.1 equiv) in anhydrous tetrahydrofuran (3.2 mL) was added, followed by the dropwise addition of carbon disulfide (0.89 mL, 14.8 mmol, 6 equiv). The reaction was allowed to slowly warm to 12° C. over 30 minutes. Iodomethane (0.92 mL, 14.7 mmol, 6 equiv) was added dropwise (exothermic) and the reaction was stirred at room temperature for 1 hour. The reaction mixture was cooled to 5° C., diluted with saturated brine (140 mL) and extracted with dichloromethane (5×100 mL). The combined organic layers were dried over sodium sulfate, filtered and concentrated under reduced pressure. The crude product was purified by column chromatography to give o-(3,3-Dimethyl-3,4-dihydrodibenzo[b,ij]imidazo[2,1,5-de]quinolizin-4-yl) S-methyl carbonodithioate (0.86 g, 93% yield) as a white solid.

K. Synthesis of 3,3-Dimethyl-3,4-dihydrodibenzo[b,
ij]imidazo[2,1,5-de]quinolizine

A solution of o-(3,3-Dimethyl-3,4-dihydrodibenzo[b,ij]imidazo[2,1,5-de]quinolizin-4-yl) S-methyl carbonodithioate (0.98 g, 2.6 mmol, 1 equiv), 2,2'-azabis(2-methylpropanitrile) (0.098 g, 0.6 mmol, 0.2 equiv) and tributyltin hydride (1.81 mL, 6.7 mmol, 2.6 equiv) in anhydrous toluene (70 mL) was stirred at 80° C. for 3.5 hours. After cooling to room temperature, the reaction mixture was concentrated under reduced pressure at 35° C. and absorbed onto silica gel (10 g). The crude material was purified by column chromatography to give 3,3-Dimethyl-3,4-dihydrodibenzo[b,ij]imidazo[2,1,5-de]quinolizine (0.53 g, 72% yield) as a white solid.


275

L. Synthesis of (3-chloropropyl)(methyl)sulfane






Sodium methanethiolate (6.14 g, 88 mmol) was dissolved in 50 mL of EtOH, cooled in an ice bath, then 1-bromo-3-chloropropane (8.6 ml, 87 mmol) was added. The solution was warmed to room temperature and stirred for 2 hours. The precipitated solids were filtered and the filtrates condensed under vacuum. The residue was distilled under vacuum to yield the product as a colorless oil, 36%.

M. Synthesis of tris-[(3-methylthio)propyl]iridium(III)



(3-chloropropyl)(methyl)sulfane was synthesized by stirring the Grignard made from (3-chloropropyl)(methyl)sulfane and magnesium turnings with $\text{IrCl}_3(\text{THT})_3$ in THF, followed by column chromatography to yield a white solid, 32%.

N. Synthesis of Compound 35



Compound 35


tris-[(3-methylthio)propyl]iridium(III) from Example 5M (0.020 g, 0.044 mmol) and 3,3-Dimethyl-3,4-dihydro-*benzo*[b,*ij*]imidazo[2,1,5-*de*]quinolizine from Example 5K (0.036 g, 0.131 mmol) were combined in ethylene glycol (0.5 ml), degassed by vacuum/backfill cycles, and stirred at reflux, turning yellow then black. The cooled residue was partitioned between water and DCM, the organics were

276

dried and coated on celite. Purification by column chromatography yielded 4 mg of Compound 35 as a beige solid (9%).

EXAMPLE 6: Synthesis of Compound 48 was Carried Out as in Scheme 6.



Scheme 6





Compound 48


(3-phenyl-1H-pyrazole) $_2$ Ir(MeOH) $_2$ (OTf) from Example 4 (0.031 g, 0.045 mmol) and 3,3-Dimethyl-3,4-dihydro-*benzo*[b,*ij*]imidazo[2,1,5-*de*]quinolizine from Example 5K (0.024 g, 0.090 mmol) were combined in 2-ethoxyethanol (0.5 ml), vacuum/backfill quickly three times, then heated at reflux under nitrogen for 2 hours. The reaction mixture was dissolved in DCM, coated on celite, and purified by column chromatography to yield Compound 35 as a nearly colorless residue, 6 mg (18%).

EXAMPLE 7: Synthesis of Compound 49 was carried out according to Scheme 7 below.






A. Synthesis of 1-Methylphenanthridin-6-amine



A mixture of 2-bromo-3-methylaniline (38.8 g, 208 mmol, 1 equiv), (chloro(2-dicyclohexylphosphino-2',6'-dimethoxy-1,1'-biphenyl)[2-(2'-amino-1,1'-biphenyl)]palladium(II) (2.99 g, 4.16 mmol, 0.02 equiv), 2-dicyclohexylphosphino-2',6'-dimethoxybiphenyl (1.71 g, 4.16 mmol, 0.02 equiv) in THF (832 mL) was sparged with nitrogen for 15 minutes. (2-Cyanophenyl)zinc bromide solution (500 mL, 0.5 M in THF, 250 mmol, 1.2 equiv) was added to the mixture and the reaction was refluxed for 16 hours. After cooling to room temperature, the reaction was diluted with saturated brine (10 mL) and concentrated under reduced pressure. The solids were dissolved in 10% methanol in dichloromethane (500 mL) and 24% wt. aqueous sodium hydroxide (500 mL). The layers were separated and the aqueous was extracted with dichloromethane (3×500 mL). The combined organic layers were dried over sodium sulfate, and concentrated under reduced pressure. The brown solid was sequentially triturated with 25% MTBE in heptanes (1.5 L) and dichloromethane (5×25 mL) to give 26 (10.7 g, 25% yield, >95% purity) as a pale yellow solid.


55

B. Synthesis of 8-Methylimidazo[1,2-f]phenanthridine





279

-continued



A mixture of 1-methylphenanthridin-6-amine (10.7 g, 51 mmol, 1 equiv), 50% wt chloroacetaldehyde in water (16 mL, 102 mmol, 2 equiv), sodium carbonate (13.5 g, 128 mmol, 2.5 equiv) in isopropanol (340 mL) was refluxed for 2 hours. The reaction was cooled to 4° C. and diluted with dichloromethane (250 mL) and saturated sodium bicarbonate (500 mL). The layers were separated and the aqueous layer was extracted with dichloromethane (3×250 mL). The combined organics layers were dried over sodium sulfate, and concentrated under reduced pressure to give crude 8-methylimidazo[1,2-f]phenanthridine (23.8 g) as a brown solid, which was used subsequently.


C. Synthesis of 3-Bromo-8-methylimidazo[1,2-f]phenanthridine



A mixture of crude 8-methylimidazo[1,2-j]phenanthridine (23.8 g), N-bromosuccinimide (9.1 g, 51 mmol, 1 equiv) in dichloromethane (306 mL) was stirred at room temperature for 2 hours. Water (500 mL) was added and the layers were separated. The aqueous was extracted with dichloromethane (3×500 mL). The combined organic layers were dried over sodium sulfate and concentrated under reduced pressure. The solids were pre-absorbed onto silica gel and purified by column chromatography to give 3-bromo-8-methylimidazo[1,2-j]phenanthridine (12 g, 98% purity) as a light brown solid.


280

D. Synthesis of 8-Methyl-3-(2-methylprop-1-en-1-yl)imidazo[1,2-f]phenanthridine



A mixture of 3-bromo-8-methylimidazo[1,2-f]phenanthridine (12 g, 38.5 mmol, 1 equiv), 4,4,5,5-tetramethyl-2-(2-methylprop-1-en-1-yl)-1,3,2-dioxaborolane (10.5 g, 58 mmol, 1.5 equiv), and potassium carbonate (16 g, 115.5 mmol, 3 equiv) in a 5 to 1 mixture of 1,4-dioxane and water (185 mL) was sparged with nitrogen for 15 minutes. (Chloro(2-dicyclohexylphosphino-2',6'-dimethoxy-1,1'-biphenyl)[2-(2'-amino-1,1'-biphenyl)]palladium(II) (4.16 g, 5.78 mmol, 0.15 equiv) and 2-dicyclohexylphosphino-2',6'-dimethoxybiphenyl (2.38 g, 5.78 mmol, 0.15 equiv) were added and the reaction was refluxed for 36 hours. After cooling to room temperature, the reaction was diluted with water (200 mL). The layers were separated and the aqueous was extracted with ethyl acetate (3×200 mL). The combined organics layers were dried over sodium sulfate and concentrated under reduced pressure. The crude solid was purified by column chromatography to give 8-methyl-3-(2-methylprop-1-en-1-yl)imidazo[1,2-f]phenanthridine (8.5 g, 70% yield, 90% purity) as a light brown solid.

E. Synthesis of 4,4,7-Trimethyl-3,4-dihydrodibenzo[b,i]imidazo[2,1,5-de]quinolizine




A mixture of 8-methyl-3-(2-methylprop-1-en-1-yl)imidazo[1,2-f]phenanthridine (1.6 g, 5.69 mmol, 1 equiv) and anhydrous aluminum chloride (3.8 g, 28.4 mmol, 5 equiv) in

281


dichloromethane (57 mL) were stirred at room temperature for 16 hours. The reaction was cooled in an ice bath and water (10 mL) was added dropwise. The layers were separated and the aqueous layer was extracted with dichloromethane (3x50 mL). The combined organic layers were dried over sodium sulfate and concentrated under reduced pressure. The crude solids purified by column chromatography to give 4,4,7-Trimethyl-3,4-dihydrodibenzo[b,i]imidazo[2,1,5-de]quinolizine (1.43 g, 88% yield, 98% purity) as a light yellow solid.

F. Synthesis of 2-Bromo-4,4,7-trimethyl-3,4-dihydrodibenzo[b,i]imidazo[2,1,5-de]quinolizine



A mixture of 4,4,7-Trimethyl-3,4-dihydrodibenzo[b,i]imidazo[2,1,5-de]quinolizine (500 mg, 1.75 mmol, 1 equiv) and N-bromosuccinimide (311 mg, 1.75 mmol, 1 equiv) in dichloromethane (11 mL) was stirred at room temperature for 2 hours. The reaction was diluted with water (20 mL) and dichloromethane (10 mL). The layers were separated and the aqueous were extracted with dichloromethane (3x20 mL). The combined organic layers were dried over sodium sulfate and concentrated under reduced pressure. The residue was purified by column chromatography to give 2-bromo-4,4,7-trimethyl-3,4-dihydrodibenzo[b,i]imidazo[2,1,5-de]quinolizine (575 mg, 90% yield, 97% purity) as a light brown solid.

G. Synthesis of 2,4,4,7-Tetramethyl-3,4-dihydrodibenzo[b,i]imidazo[2,1,5-de]quinolizine




A mixture of 2-bromo-4,4,7-trimethyl-3,4-dihydrodibenzo[b,i]imidazo[2,1,5-de]quinolizine (265 mg, 0.73 mmol, 1 equiv), trimethylboroxine (0.6 mL, 4.4 mmol, 6 equiv) and potassium carbonate (608 mg, 4.4 mmol, 6 equiv) in a 10 to 1 mixture of 1,4-dioxane and water (7 mL) was sparged with nitrogen for 15 minutes. Chloro(2-dicyclohexylphosphino-2',6'-dimethoxy-1,1'-biphenyl)[2-(2'-amino-1,1'-biphenyl)]palladium(II) (108 mg, 0.15 mmol, 0.2 equiv) and 2-dicyclohexylphosphino-2',6'-dimethoxybiphenyl (62 mg, 0.15 mmol, 0.2 equiv) were added and the

282


reaction was refluxed for 16 hours. After cooling to room temperature, the reaction was diluted with water (10 mL) and ethyl acetate (10 mL). The layers were separated and the aqueous were extracted with ethyl acetate (3x20 mL). The combined organic layers were dried over sodium sulfate and concentrated under reduced pressure. The residue was purified by column chromatography to give 2,4,4,7-Tetramethyl-3,4-dihydrodibenzo[b,i]imidazo[2,1,5-de]quinolizine (100 mg, 46% yield, 95% purity) as a pale yellow solid.

H. Synthesis of Compound 49




Compound 49 was synthesized in an analogous way to Compound 35, yielding 13 mg of yellow powder (15%).

EXAMPLE 8: Synthesis of Compound 50 was carried out according to Scheme 8 below.




283

-continued




Compound 50

A. Synthesis of 1-chlorophenanthridin-6-amine



284

-continued



5

10 A mixture of 3-chloro-2-iodoaniline (8.77 g, 34.6 mmol), CyJohnPhos (0.462 g, 1.319 mmol), and $\text{Pd}(\text{CH}_3\text{CN})_2\text{Cl}_2$ (0.171 g, 0.659 mmol) was dissolved in dioxane (80 ml). Triethylamine (13.78 ml, 99 mmol) and 4,4,5,5-tetramethyl-1,3,2-dioxaborolane (10.04 ml, 69.2 mmol) were added to the solution in sequence via syringe. The reaction was reflux

15 for 4 h. The reaction was cooled to room temperature and a solid mixture of 2-bromobenzonitrile (6 g, 33.0 mmol), S-Phos Pd G2 (0.475 g, 0.659 mmol), S-Phos (0.271 g, 0.659 mmol), and potassium carbonate (9.11 g, 65.9 mmol) was added to the reaction mixture followed by dioxane (20 ml) and water (20 ml) and the reaction was heated to 85° C.


20 for 16 hours. The crude product was extracted with DCM and vacuumed down to yield an orange oil. This was dissolved in THE (80 mL) and sodium hydride (1.978 g, 49.4 mmol) was added at 0° C. and stirred for 20 min. The reaction was quenched with brine and extracted with DCM. Evaporation of the reaction mixture followed by trituration with ether yielded 1-chlorophenanthridin-6-amine as an off-white solid (52% yield).

25

30

B. Synthesis of 8-chloroimidazo[1,2-f]phenanthridine

35



40

45


50


55

60


65

1-chlorophenanthridin-6-amine (864 mg, 3.78 mmol), 2-chloroacetaldehyde (50 wt % in water, 1.02 mL, 7.56 mmol), and sodium bicarbonate (635 mg, 7.56 mmol) were combined in iPrOH and refluxed for 1 h. The mixture was cooled to room temperature and poured into water and filtered (99% yield).




285C. Synthesis of
8-phenylimidazo[1,2-f]phenanthridine

A mixture of 8-chloroimidazo[1,2-f]phenanthridine (955 mg, 3.78 mmol), phenylboronic acid (829 mg, 6.80 mmol), S-Phos Pd G2 (109 mg, 0.151 mmol), S-Phos (62.1 mg, 0.151 mmol), and potassium carbonate (522 mg, 3.78 mmol) was vacuumed and back-filled with nitrogen several times. Dioxane (20 ml) and water (4 ml) were added and refluxed for 1 h. The crude product was extracted with DCM and brine and purified by column chromatography to yield product (99% yield).


D. Synthesis of 3-bromo-8-phenylimidazo[1,2-f]
phenanthridine

8-phenylimidazo[1,2-f]phenanthridine (1.15 mg, 3.91 mmol) and NBS (0.765 g, 4.30 mmol) were combined in DMF and stirred at room temperature for 30 minutes, followed by quenching with water. The resultant solid was filtered and dried in vacuum, yielding 3-bromo-8-phenylimidazo[1,2-f]phenanthridine in 75% yield.


E. Synthesis of 3-(2-methylprop-1-en-1-yl)-8-phenylimidazo[1,2-f]phenanthridine

5
10
15**286**

-continued

20
25
30

A mixture of 3-bromo-8-phenylimidazo[1,2-f]phenanthridine (980 mg, 2.63 mmol), SPhos Pd G2 (76 mg, 0.105 mmol), SPhos (43.1 mg, 0.105 mmol), and potassium carbonate (363 mg, 2.63 mmol) was vacuumed and back-filled with nitrogen several times. Toluene (15 ml), Water (3 ml), and 4,4,5,5-tetramethyl-2-(2-methylprop-1-en-1-yl)-1,3,2-dioxaborolane (1.077 ml, 5.25 mmol) were added and heated at reflux for 16 hours. The product was extracted with DCM and brine and purified by column chromatography to give 3-(2-methylprop-1-en-1-yl)-8-phenylimidazo[1,2-f]phenanthridine in 20% yield.



F. Synthesis of 4,4-dimethyl-7-phenyl-3,4-dihydro-
ibenzo[b,i]imidazo[2,1,5-de]quinolizine35
40
45
50
55

3-(2-methylprop-1-en-1-yl)-8-phenylimidazo[1,2-f]phenanthridine (160 mg, 0.459 mmol) was dissolved in DCM (10 ml) and aluminum trichloride (184 mg, 1.378 mmol) was added. The reaction for 40 min at room temperature. The mixture was quenched with KOH (aq)/brine and extracted several times with DCM. The product was purified by column chromatography to give 4,4-dimethyl-7-phenyl-3,4-dihydroibenzo[b,i]imidazo[2,1,5-de]quinolizine in 63% yield.

60
65

287

G. Synthesis of Compound 50





Compound 50

(3-phenyl-1H-pyrazole)₂Ir(MeOH)₂(OTf) from Example 4 (0.03 g, 0.043 mmol) and 4,4-dimethyl-7-phenyl-3,4-dihydrodibenzo[b,i]imidazo[2,1,5-de]quinolizine (0.030 g, 0.087 mmol) were combined in 2-ethoxyethanol (0.5 ml), vacuum/backfilled quickly three times with nitrogen, then heated at reflux under nitrogen for 2 h. The product was purified by column chromatography to give Compound 50 in 56% yield.






EXAMPLE 9: Synthesis of Compound 108 was carried out according to Scheme 8 below.

Scheme 9




288


-continued



289




A. Synthesis of tert-Butyl
4-((triisopropylsilyl)oxy)phenyl)carbamate



Triisopropylchlorosilane (32 mL, 0.15 mol, 1.2 equiv) and triethylamine (21 mL, 0.15 mol, 1.2 equiv) were sequentially added to a solution of tert-butyl (4-hydroxyphenyl) carbamate (26.1 g, 0.125 mol, 1 equiv) in THF (200 mL). The reaction mixture was stirred for 16 hours at room temperature. The reaction was filtered and the solids were washed with THF (2×30 mL). The combined filtrates were concentrated under reduced pressure. The crude product was purified by column chromatography to give tert-Butyl 4-((triisopropylsilyl)oxy)phenyl)carbamate (39.66 g, 87% yield) as yellow oil.


B. Synthesis of 4-((Triisopropylsilyl)oxy)aniline



290


Trifluoroacetic acid (41.51 mL, 0.54 mol, 5 equiv) was added at room temperature to a solution of tert-Butyl 4-((triisopropylsilyl)oxy)phenyl)carbamate (39.66 g, 0.1085 mol, 1 equiv) in dichloromethane (400 mL). After stirring for 16 hours the solvent was removed under reduced pressure. The residue was azeotroped with toluene (3×50 mL). The crude product was purified over silica to give 4-((Triisopropylsilyl)oxy)aniline (25 g, 87% yield).

C. Synthesis of
2,6-Dibromo-4-((triisopropylsilyl)oxy)aniline



Bromine (8.2 mL, 0.16 mol, 2.5 equiv) was added dropwise at 0° C. to a solution of 4-((Triisopropylsilyl)oxy)aniline (17 g, 64.4 mmol, 1 equiv) in a 1:1 mixture of dichloromethane and methanol (60 mL). The reaction mixture was allowed to warm up to room temperature and stirred for 16 hours. The reaction mixture was diluted with dichloromethane (200 mL) and washed sequentially with 1M NaOH (2×100 mL) and saturated brine (2×100 mL). The organic layer was dried over sodium sulfate and concentrated under reduced pressure to give 2,6-Dibromo-4-((triisopropylsilyl)oxy)aniline (26.37 g, 97% yield) as a brown oil, which was used subsequently.

D. Synthesis of 4-Bromo-8-methoxy-2-((triisopropylsilyl)oxy)phenanthridin-6-amine





A mixture of 5-methoxy-2-((4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)benzotrile (16.14 g, 62.3 mmol, 1 equiv), 2,6-dibromo-4-((triisopropylsilyl)oxy)aniline (26.37 g, 62.3 mmol, 1 equiv) and potassium phosphate (43.04 g, 0.187 mol, 3 equiv) in a 4 to 1 mixture of toluene and water (500 mL) was sparged with nitrogen for 1 hour. trans-Pd(PPh₃)₂Cl₂ (2.8 g, 3.11 mmol, 0.05 equiv) was

291

added and the reaction mixture was refluxed for 20 hours. Additional 5-methoxy-2-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)benzotrile (2.2 g, 8.5 mmol, 0.14 equiv) and trans-Pd(PPh₃)₂Cl₂ (0.3 g, 0.43 mmol, 0.0069 equiv) were added and the reaction mixture was refluxed for an additional 4 hours. The layers were separated and the organic layer was washed with hot water (2×200 mL). The organic layer was dried over sodium sulfate and concentrated under reduced pressure. The residue was purified by column chromatography to yield 4-bromo-8-methoxy-2-((triisopropylsilyl)oxy)phenanthridin-6-amine in 20% yield.


E. Synthesis of 5-Bromo-3-(2-chloroethyl)-11-methoxy-7-((triisopropylsilyl)oxy)imidazo[1,2-f]phenanthridine



A suspension of 4-bromo-8-methoxy-2-((triisopropylsilyl)oxy)phenanthridin-6-amine (5.95 g, 12.53 mmol, 1 equiv), p-toluenesulfonic acid monohydrate (175 mg) and fresh prepared 2 (6.67 g, 62.63 mmol, 5 equiv) in i-propanol (500 mL) was stirred at the room temperature for 2 hours. Sodium carbonate (3.25 g, 37.6 mmol, 3 equiv) and deionized water (12 ml) were added and the reaction mixture was refluxed for 16 hours. After cooling to room temperature, the volume of reaction mixture was reduced to ~60 ml under reduced pressure. The mixture was diluted with ethyl acetate (300 mL) and washed with saturated brine (200 mL). The organic layer was dried over sodium sulfate and concentrated under reduced pressure. The crude product was purified by column chromatography to give 5-bromo-3-(2-chloroethyl)-11-methoxy-7-((triisopropylsilyl)oxy)imidazo[1,2-f]phenanthridine (5.53 g, 79% yield).


292

F. Synthesis of 10-Methoxy-6-((triisopropylsilyl)oxy)-3,4-dihydrodibenzo[b,j]imidazo[2,1,5-de]quinolizine



A solution of 5-bromo-3-(2-chloroethyl)-11-methoxy-7-((triisopropylsilyl)oxy)imidazo[1,2-f]phenanthridine (5.53 g, 9.84 mmol, 1.0 equiv) in dry THF (300 mL) was sparged with nitrogen for 30 minutes. After cooling to 0° C., 2M isopropylmagnesium chloride in THF (7.4 mL, 14.76 mmol, 1.5 equiv) was added dropwise via syringe. The reaction mixture was warmed to the room temperature and stirred for 16 hours. The reaction was quenched with water (10 mL) and the THF was removed under reduced pressure. The residue was extracted with dichloromethane (500 mL). The organic layer was washed with water (2×200 mL), dried over sodium sulfate and concentrated under reduced pressure. The crude product was purified by column chromatography to give 10-methoxy-6-((triisopropylsilyl)oxy)-3,4-dihydrodibenzo[b,j]imidazo[2,1,5-de]quinolizine (3 g, 68% yield).


G. Synthesis of 10-Methoxy-3,4-dihydrodibenzo[b,j]imidazo[2,1,5-de]quinolizine-6-ol



293


Tetrabutylammonium fluoride trihydrate in THF (30 mL) was added dropwise to a solution of 10-methoxy-6-((triisopropylsilyl)oxy)-3,4-dihydrodibenzo[b,ij]imidazo[2,1,5-de]quinolizine (3 g, 6.72 mmol, 1 equiv) in THE (100 mL). After stirring at room temperature for 16 hours, the solvent was removed under reduced pressure and the residue was extracted with dichloromethane. (80 mL). The organic layer was washed with saturated brine (2×100 mL). Upon washing with saturated brine, a large precipitate started to form in the organic layer. The precipitation was filtered and washed with heptanes (2×10 mL) to give pure 10-methoxy-3,4-dihydrodibenzo[b,ij]imidazo[2,1,5-de]quinolizin-6-ol (1.83 g, 94% yield).

H. Synthesis of 10-Methoxy-3,4-dihydrodibenzo[b,ij]imidazo[2,1,5-de]quinolizin-6-yl trifluoromethanesulfonate




Trifluoroacetic anhydride (1.14 mL, 6.77 mmol, 1.1 equiv) and pyridine (0.744 mL, 9.24 mmol, 1.5 equiv) were sequentially added at 0° C. to a mixture of 10-methoxy-3,4-dihydrodibenzo[b,ij]imidazo[2,1,5-de]quinolizin-6-ol (1.79 g, 6.16 mmol, 1 equiv) in dichloromethane (100 mL). After stirring for 15 minutes, the reaction was warmed to room temperature and stirred for 6 hours. The reaction mixture was diluted with dichloromethane (200 mL) and washed with water (3×100 mL). The organic layer was dried over sodium sulfate and solvent was removed under reduced pressure. The residue was triturated with a 10 to 1 mixture of heptanes and dichloromethane (10 mL) to give 10-methoxy-3,4-dihydrodibenzo[b,ij]imidazo[2,1,5-de]quinolizin-6-yl trifluoromethanesulfonate (2.17 g, 83% yield).

I. Synthesis of 10-Methoxy-6-phenyl-3,4-dihydrodibenzo[b,ij]imidazo[2,1,5-de]quinolizine




294

-continued



A mixture of 10-methoxy-3,4-dihydrodibenzo[b,ij]imidazo[2,1,5-de]quinolizin-6-yl trifluoromethanesulfonate (0.65 g, 1.54 mmol, 1 equiv), phenylboronic acid (0.188 g, 1.54 mmol, 1 equiv) and potassium phosphate (1.06 g, 4.62 mmol, 3 equiv) in a 3:1:1 mixture of toluene:1,4-dioxane:water (500 mL) was sparged with nitrogen for 1 hour. Trans-Pd(PPh₃)₂Cl₂ (54 mg, 0.077 mmol, 0.05 equiv) was added and the reaction mixture was refluxed for 16 hours. The reaction mixture was diluted with dichloromethane (200 mL). The organic layer was washed with warm water (2×100 mL), dried over sodium sulfate and concentrated under reduced pressure to give 10-methoxy-6-phenyl-3,4-dihydrodibenzo[b,ij]imidazo[2,1,5-de]quinolizine (0.527 g, 97% yield).



J. Synthesis of 6-Phenyl-3,4-dihydrodibenzo[b,ij]imidazo[2,1,5-de]quinolizin-10-ol



1M Boron tribromide in dichloromethane (7.5 mL, 7.5 mmol, 5 equiv) was added dropwise at -78° C. to a solution of 10-methoxy-6-phenyl-3,4-dihydrodibenzo[b,ij]imidazo[2,1,5-de]quinolizine (0.527 g, 1.5 mmol, 1 equiv) in dichloromethane (100 mL). The reaction mixture was warmed to the room temperature and stirred for 16 hours. The reaction mixture was carefully poured in ice water (150 mL) and the resulting solid was filtered and washed sequentially with water (30 mL) and heptanes (10 mL) to give 6-phenyl-3,4-dihydrodibenzo[b,ij]imidazo[2,1,5-de]quinolizin-10-ol (0.47 g, 93% yield).

295



K. Synthesis of 10-((9-(4-isopropylpyridin-2-yl)-9H-carbazol-2-yl)oxy)-6-phenyl-3,4-dihydro-dibenzo[b,ij]imidazo[2,1,5-de]quinolizine



A mixture of 2-Bromo-9-(4-isopropylpyridin-2-yl)-9H-carbazole (0.528 g, 1.446 mmol, 1 equiv), 6-phenyl-3,4-dihydrodibenzo[b,ij]imidazo[2,1,5-de]quinolizine-10-ol (0.486 g, 1.446 mmol, 1 equiv), potassium phosphate (1.67 g, 7.23 mmol, 5 equiv), copper (I) iodide (0.138 g, 0.723 mmol, 0.5 equiv), and picolinic acid (0.445 g, 3.62 mmol, 2.5 equiv) in DMSO (50 mL) was heated at 150° C. for 4.5 hours. After cooling to room temperature, the reaction mixture was poured into water (300 mL) and extracted with ethyl acetate (4×100 mL). The combined organic layers were dried over sodium sulfate and concentrated under reduced pressure. The crude product was purified by column chromatography to give 10-((9-(4-isopropylpyridin-2-yl)-9H-carbazol-2-yl)oxy)-6-phenyl-3,4-dihydro-dibenzo[b,ij]imidazo[2,1,5-de]quinolizine as a tan solid (0.55 g, 61% yield).

296


L. Synthesis of Compound 108



A solution of 10-((9-(4-isopropylpyridin-2-yl)-9H-carbazol-2-yl)oxy)-6-phenyl-3,4-dihydro-dibenzo[b,ij]imidazo[2,1,5-de]quinolizine (350 mg, 0.564 mmol, 1 equiv) glacial acetic acid (60 mL) was sparged with argon for 40 minutes. K_2PtCl_4 (234 mg, 0.564 mmol, 1 equiv) was added and the reaction mixture was refluxed for 16 hours. After cooling to room temperature, the yellow-greenish precipitate was filtered and washed sequentially with water (4×15 mL) and heptanes (2×10 mL) and dried under vacuum at 20° C. for 18 hours. The crude product was dissolved in dichloromethane (500 mL) and passed through a plug of silica gel (10 g) to remove residual K_2PtCl_4 . The solvent was removed under reduced pressure. The residue was triturated with a 1 to 1 mixture of dichloromethane and heptanes (20 mL), filtered and washed with dichloromethane (2×3 mL) to give Compound 108 (40 mg, yield 8.7% yield, 83.2%).

DISCUSSION: The general structure of one embodiment of the metal-coordinated imidazophenanthridine ligand is shown below. The bonds of interest in the computational study are the four carbon-nitrogen (C—N) single bonds. They are labeled as C—Ni, C—N2, C—N_h for the nitrogen that has three single C—N bonds, and C—Nm for the nitrogen that is coordinated to the metal.

297




Geometry optimizations of all complexes and ligands were performed in the Gaussian 09 software package using the hybrid B3LYP functional with the CEP-31 g effective core potential basis set. All results use this method unless otherwise stated in the results and discussion.


Bond strengths were calculated by breaking a bond to form a diradical species on the imidazophenanthridine ligand. The bond-broken diradical species was calculated as a triplet state as this is normally lower in energy than a diradical singlet and therefore the more likely product formed in a bond breaking event. Calculations were performed at the B3LYP/6-31 g(d) level and thermodynamics reported for the ground state singlet→bond broken triplet and a lowest energy triplet (excited state)→bond broken triplet.

Calculated TD-DFT values for the lowest triplet excited state (T₁) were also performed at the B3LYP/CEP-31 g level of theory but included the CPCM continuum solvent field using THF as the solvent which has been shown to better match experimental results.

Bond strength calculations were performed on the following compounds:



Comparative compound 1




comparative compound 2


298

-continued


comparative compound 3




comparative compound 4




comparative compound 5



comparative compound 6




comparative compound 7



299

-continued

comparative compound 8




5

10

300

-continued

Comparative Ligand 1



Calculated bond strengths are shown in Table 1.

TABLE 1




Structure	C-N ₁					
	Calc bond T1 (nm)	bond strength (kcal/mol)	C-N _{ph} bond strength (kcal/mol)	C-N ₂ bond strength (kcal/mol)	C-N _m bond strength (kcal/mol)	Weakest bond (kcal/mol)
Comparative compound 1 	468	11.81 74.06	25.92 88.17	n/a	39.80 102.05	11.81
Comparative compound 2 	474	-1.54 61.26	22.00 84.79	n/a	46.85 109.64	-1.54
Comparative compound 3 	476	-0.55 60.08	22.34 82.96	n/a	45.18 105.80	-0.55

TABLE 1-continued





Structure	Calc T1 (nm)	C-N ₁ bond strength (kcal/mol)	C-N _{ph} bond strength (kcal/mol)	C-N ₂ bond strength (kcal/mol)	C-N _m bond strength (kcal/mol)	Weakest bond (kcal/mol)
Comparative compound 4 		5.31	28.66	n/a	45.57	5.31
Compound 1 	468	35.38	90.51	n/a	36.56	35.38
Comparative ligand 1 	470	18.73 83.76	34.85 99.87	n/a	45.62 110.64	48.73
Compound (1-3) 	472					

Table 1 shows calculated bond strengths for a series of comparative examples and invention Compound 1. Where two numbers are seen in the same cell, the top number represents the thermodynamic difference between the excited state triplet→bond broken triplet. The lower number represents the ground state singlet→bond broken triplet. If there is only one number in the cell, it represents the triplet→triplet bond strength (T→T). For all comparative compounds 1-4, the C—N₁ bond is shown to be the weakest bond. Bond strengths are found to be weaker in the excited triplet state compared to the ground state singlet. This is due to the complex having the energy of the excited state available as the starting point to the, generally, higher energy bond broken state. In some cases, as shown for comparative compound 2 and 3, the bond broken state is lower in energy than the starting triplet state. Therefore a bond breaking event may be considered thermodynamically favorable or

exothermic. It is found that when aryl substitutions are added at the C—N₁ bond carbon atom, the bond strength decreases, as seen comparing comparative compound 1 to comparative compounds 2 and 3. This effect may be due to resonance stabilization of the radical species at the bond breaking site which is stabilized by the aryl substitution.

Stabilization of the weak C—N₁ bond can be achieved by a linking substitution that links the C—N₁ carbon to the carbon on the adjacent fused aryl ring as depicted by "A" in Formula (1a). This linking group is preferably comprised of elements that provide the proper structural geometry to form a bridge across the two carbons of the phenanthridine ring system, providing the necessary rigidity to stabilize the C—N₁ bond while not lowering the triplet energy of the resulting ligand and complex.

The effect of the stabilizing linker is shown in Table 1 for invention Compound 1. Here the triplet C—N₁ bond

strength has greatly improved from 11.81 kcal/mol, for the analogous comparative Compound 1, to 35.38 kcal/mol for the invention compound, an increase in thermodynamic bond strength of >20 kcal/mol. The two carbon linking substituent prevents the ligand from being able to obtain the appropriate relaxed geometry of a CN_1 bond broken state. Importantly, the triplet energy is not affected by this substitution as both invention Compound 1 and Comparative Compound 1 both have identical triplet energies of 468 nm by calculation.

The minimized non bond-broken and bond-broken geometries of comparative example 1 are shown in FIGS. 3a and 3b. It can be seen that the bond broken geometry relaxes the ring strain of the fused ring system of the imidazophenanthridine ligand. The tethering substitution, as shown for invention Compound 1, inhibits the relaxed bond broken geometry, thereby increasing the thermodynamic bond strength of the $C-N_1$ bond.

Further experimental evidence of the weakness of the $C-N_1$ bond is shown by matrix assisted laser desorption ionization mass spectroscopy (MALDI-MS). MALDI-MS can be used to probe weaknesses in bonds in the excited states of molecules. It is believed that as a measure of photochemical stability, MALDI-MS can simulate some of the conditions found inside an OLED device, where both charged and excited states are present. FIG. 3 shows the MALDI-MS taken in the negative mode for comparative compound 3. The peak for the parent ion is identified at 1529

amu. However the highest intensity peak is found at 1275 amu. This mass corresponds to a fragment of comparative compound 3 where the imidazole ring has lost the mass of two carbons and the terphenyl substitution. The structure of proposed fragment is shown in FIG. 3. The isotopic pattern confirms this fragment contains iridium and is consistent with the chemical formula of the proposed fragment. Further fragments are identified for ligand loss at 1083 amu and imidazole ring decomposition for two ligands at 1020 amu, as shown in FIG. 4. The data suggests that the formation of the major fragment requires the rupture of the $C-N_1$ bond that is predicted to be a weak bond by calculation.

Photophysical Properties of the Compounds of the Invention

The measured photophysical properties of the invention compounds are reported in the Table 2 below. Complexes were measured at 77K and at room temperature in 2-methyl tetrahydrofuran solvent at highly dilute concentrations. Photoluminescent quantum yields (PLQY, Φ_{PL}) were measured at 1 wt % in polymethylmethacrylate (PMMA) solid state matrix or 0.4 wt % polystyrene (PS) solid state matrix using a Hamamatsu C9920 system equipped with a xenon lamp, integrating sphere and a model C10027 photonic multi-channel analyzer. PL transient measurements (τ) were carried out by time correlated single photon counting method using a Horiba Jobin Yvon Fluorolog-3 integrated with an IBH datastation hub using a 335 nm nanoLED as the excitation source.

TABLE 2



Compound	λ_{max} (nm)	τ (μ s)	λ_{max} (nm)	Φ_{PL}	Φ_{PL}
	@ 77 K	@ 77 K	@ 298 K	PMMA	PS
 Compound 35	451	5.1	461	0.05	—
 Compound 48	440	9.5	448	0.04	—

TABLE 2-continued








Compound	λ_{max} (nm) @ 77 K	τ (μ s) @ 77 K	λ_{max} (nm) @ 298 K	Φ_{PL} PMMA	Φ_{PL} PS
 Compound 49	464	2.9	467	0.62	—
 Compound 50	—	—	—	0.09	—
 Compound 105	444	7.5	448	—	0.85
 Compound 106	448	6.7	452	—	—

TABLE 2-continued

Compound	λ_{max} (nm) @ 77 K	τ (μ s) @ 77 K	λ_{max} (nm) @ 298 K	Φ_{PL} PMMA	Φ_{PL} PS
 Comparative compound 6	—	—	—	0.68	—
 Comparative compound 7	—	—	—	—	0.87
 Comparative Compound 8	441	18	447	0.14	—

Compound 35 was measured to have deep blue emission, with a highest energy peak at 77 K of 451 nm, however, the PLQY for the complex is only 5%. Compound 49 demonstrates how modifications to the ligand can be used to improve PLQY. The methyl substitution on the imidazole ring has been found to improve the PLQY of non-ethyl bridged phenanthridine imidazole analogues. In addition, methyl substitution on the exterior phenyl ring is shown by calculation to affect the ligand bite angle due to the steric influence of the methyl substituent and the proton on the adjacent aryl ring. This steric effect pushes the phenanthridine imidazole polycyclic ring system geometry closer to the geometry of a non-bridged ligand where the coordinating sites can more closely connect to the metal. This subtle change in the geometry of the ligand allows for a stronger interaction between the metal and neutrally coordinated nitrogen, improving the metal-nitrogen bond strength. It is believed that a stronger metal-nitrogen bond strength can improve the emissivity of a complex by reducing metal-nitrogen bond breaking non-radiative decay. Therefore both methyl substitutions might be responsible for enhancing the PLQY of Compound 49 compared to Compound 35. Compound 49 was measured to have a PLQY of 62% in PMMA matrix, which is very close to the PLQY value of the

non-bridged analog, Comparative Compound 6, which is measured to have a PLQY of 68%. In addition, Compound 49 is measured to have a much shorter excited state lifetime at 77 K of 2.9 microseconds, compared to an excited state lifetime of 5.1 microseconds for Compound 35. This further demonstrates that the methyl substituents improved the radiative properties of Compound 49.

Heteroleptic examples with phenylpyrazole ligands (ppz), Compound 48 and Compound 50, are measured to have deep blue emission, but low PLQY. However, the non-bridged reference compound, Comparative Compound 8, is also measured to have a low PLQY of 14%. It is believed that the low efficiency may be due to the weak metal-nitrogen bond of the pyrazole ligand. To further support this assumption, tris Ir(ppz)₃ has been shown in the literature to be non-emissive in room temperature solution, but highly emissive at 77 K. The non emissivity at room temperature is attributed to a weak metal nitrogen bond.

Platinum complexes with bridged phenanthridine imidazole ligands are also found to be highly emissive with deep blue color. Compound 105 and Comparative Compound 7 are both measured to have high PLQY values of 85% and 87%, respectively, in the optically inert polystyrene matrix. Platinum complexes may not require the ligand modifica-

309

tions for improving PLQY as described for the iridium analogue, Compound 49, due to a relatively stronger platinum-nitrogen bond strength compared to iridium.

It will be appreciated by those skilled in the art that changes could be made to the exemplary embodiments shown and described above without departing from the broad inventive concept thereof. It is understood, therefore, that this invention is not limited to the exemplary embodiments shown and described, but it is intended to cover modifications within the spirit and scope of the present invention as defined by the claims. For example, specific features of the exemplary embodiments may or may not be part of the claimed invention and features of the disclosed embodiments may be combined. Unless specifically set forth herein, the terms "a", "an" and "the" are not limited to one element but instead should be read as meaning "at least one".


It is to be understood that at least some of the figures and descriptions of the invention have been simplified to focus on elements that are relevant for a clear understanding of the invention, while eliminating, for purposes of clarity, other elements that those of ordinary skill in the art will appreciate may also comprise a portion of the invention. However, because such elements are well known in the art, and because they do not necessarily facilitate a better understanding of the invention, a description of such elements is not provided herein.

Further, to the extent that any methods of the present invention do not rely on the particular order of steps set forth herein, the particular order of the steps should not be construed as limitation on the claims. The claims directed to such methods should not be limited to the performance of their steps in the order written, and one skilled in the art can readily appreciate that the steps may be varied and still remain within the spirit and scope of the present invention.

All references, including publications, patent applications, and patents, cited herein are hereby incorporated by reference to the same extent as if each reference were individually and specifically indicated to be incorporated by reference and were set forth in its entirety herein.

We claim:

1. An organic light emitting device (OLED) comprising: an anode; a cathode; and an organic layer, disposed between the anode and the cathode, comprising a compound having a structure $(L_A)_nML_m$ according to Formula 1:



wherein M is a metal having an atomic weight greater than 40, n as a value of at least 1 and m+n is the maximum number of ligands that may be attached to the metal;

310

wherein A is a linking group selected from the group consisting of $-CR'R''-CR'R''-$, $-CR'R'-CR'R''-$, and $-CR'R'-CR'R'-CR'R''-$;

wherein each R' is independently selected from the group consisting of H, D, alkyl, cycloalkyl, aryl, heteroaryl, and combinations thereof,

wherein each R'' is independently selected from the group consisting of alkyl, cycloalkyl, aryl, heteroaryl, partially or fully deuterated variants thereof, and combinations thereof,

wherein R's and R''s are optionally connected to form a saturated five membered ring or a saturated six membered ring, and combinations thereof,

wherein R^{1a} to R^{1g} are each independently selected from the group consisting of hydrogen, deuterium, alkyl, cycloalkyl, aryl, heteroaryl, and combinations thereof; wherein any one of the ring atoms to which R^{1b} to R^{1g} are attached may be replaced with a nitrogen atom, wherein when the ring atom is replaced with a nitrogen atom the corresponding R group is not present;

wherein L is a substituted or unsubstituted cyclometalated ligand,

wherein L can be joined to R^{1g} through a linking group L^2 ; wherein L^2 is selected from the group consisting of a single bond, NR, O, S, CR^1R^2 , and SiR^1R^2 ;


wherein R, R^1 , and R^2 can be same or different, and are independently selected from the group consisting of hydrogen, deuterium, alkyl, cycloalkyl, aryl, heteroaryl, and combinations thereof; wherein any adjacent R^1 and R^2 are optionally connected to form a saturated five membered ring or a saturated six membered ring.

2. The OLED of claim 1, wherein A is selected from the group consisting of $-CR'R''-CR'R''-$ and $-CR'R'-CR'R''-$.

3. The OLED of claim 2, wherein each of R' and R'' is independently selected from the group consisting of undeuterated alkyl, partially deuterated alkyl, and fully deuterated alkyl.


4. The OLED of claim 1, wherein the compound has a peak emissive wavelength less than 500 nm.

5. The OLED of claim 1, wherein the linking group is selected from the group consisting of:




311

-continued




312

-continued




313

-continued



314



6. The OLED of claim 1, wherein at least one of R^{1a} to R^{1g} is selected from the group consisting of alkyl, cycloalkyl, aryl, heteroaryl, partially or fully deuterated variants thereof, and combinations thereof.

7. The OLED of claim 6, wherein at least one of R^{1b} , R^{1d} and R^{1c} is selected from the group consisting of alkyl, cycloalkyl, aryl, heteroaryl, partially or fully deuterated variants thereof, and combinations thereof.

8. The OLED of claim 6, wherein R^{1d} is selected from the group consisting of alkyl, cycloalkyl, aryl, heteroaryl, partially or fully deuterated variants thereof, and combinations thereof.

9. The OLED of claim 6, wherein R^{1a} is selected from the group consisting of alkyl, cycloalkyl, aryl, heteroaryl, partially or fully deuterated variants thereof, and combinations thereof.

10. The OLED of claim 8, wherein R^{1d} is selected from the group consisting of non-deuterated alkyl, partially deuterated alkyl, and fully deuterated alkyl.

11. The OLED of claim 9, wherein R^{1a} is selected from the group consisting of non-deuterated aryl, partially deuterated aryl, and fully deuterated aryl.

12. The OLED of claim 10, wherein R^{1d} is selected from the group consisting of $-\text{CH}_3$, $-\text{CD}_3$, and isopropyl.

13. The OLED of claim 7, wherein R^{1f} is selected from the group consisting of $-\text{CH}_3$, $-\text{CD}_3$, and isopropyl.

14. The OLED of claim 1, wherein the metal is Ir.

15. The OLED of claim 1, wherein the ligand L is selected from the group consisting of:


wherein each X^1 to X^{13} are independently selected from the group consisting of carbon and nitrogen;
 wherein each R_a , R_b , R_c , and R_d may represent from mono substitution to the possible maximum number of substitution, or no substitution;
 wherein R_a , R_b , R_c , and R_d are each independently selected from the group consisting of hydrogen, deuterium, halide, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl,

315

heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acids, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof; and


wherein any two adjacent substituents of R_a , R_b , R_c , and R_d are optionally fused or joined to form a ring or form a multidentate ligand.

16. The OLED of claim 1, wherein ligand L is selected from the group consisting of.




L17

15




L18

30



L19

45




L20


60

316


-continued




L21



L22




L23



L24

and




L25

17. The OLED of claim 15, wherein the compound has a structure selected from the group consisting of $(L_A)_3Ir$, $(L_A)Ir(L)_2$ or $(L_A)_2Ir(L)$.

317

18. A consumer product comprising an organic light-emitting device comprising:
 an anode;
 a cathode; and
 an organic layer, disposed between the anode and the cathode, comprising a compound having a structure $(L_A)_n ML_m$ according to Formula 1:

Formula 1



wherein M is a metal having an atomic weight greater than 40, n has a value of at least 1 and m+n is the maximum number of ligands that may be attached to the metal;

wherein A is a linking group selected from the group consisting of $-CR'R''-CR'R''-$, $-CR'R'-CR'R''-$, and $-CR'R'-CR'R'-CR'R'-$;

wherein each R' is independently selected from the group consisting of H, D, alkyl, cycloalkyl, aryl, heteroaryl, and combinations thereof,

wherein each R'' is independently selected from the group consisting of alkyl, cycloalkyl, aryl, heteroaryl, partially or fully deuterated variants thereof, and combinations thereof,

wherein R's and R''s are optionally connected to form a saturated five membered ring or a saturated six membered ring, and combinations thereof,

wherein R^{1a} to R^{1g} are each independently selected from the group consisting of hydrogen, deuterium, alkyl, cycloalkyl, aryl, heteroaryl, and combinations thereof;

wherein any one of the ring atoms to which R^{1b} to R^{1g} are attached may be replaced with a nitrogen atom, wherein when the ring atom is replaced with a nitrogen atom the corresponding R group is not present;

wherein L is a substituted or unsubstituted cyclometalated ligand,

wherein L can be joined to R^{1g} through a linking group L²;

wherein L² is selected from the group consisting of a single bond, NR, O, S, CR¹R², and SiR¹R²;

wherein R, R¹, and R² can be same or different, and are independently selected from the group consisting of hydrogen, deuterium, alkyl, cycloalkyl, aryl, heteroaryl, and combinations thereof; wherein any adjacent R¹ and R² are optionally connected to form a saturated five membered ring or a saturated six membered ring.


19. The consumer product of claim 18, wherein the consumer product is one of a flat panel display, a curved display, a computer monitor, a medical monitor, a television, a billboard, a light for interior or exterior illumination and/or signaling, a heads-up display, a fully or partially transparent display, a flexible display, a rollable display, a foldable

318

display, a stretchable display, a laser printer, a telephone, a mobile phone, a tablet, a phablet, a personal digital assistant (PDA), a wearable device, a laptop computer, a digital camera, a camcorder, a viewfinder, a micro-display (displays that are less than 2 inches diagonal), a 3-D display, a virtual reality or augmented reality display, a vehicle, a video wall comprising multiple displays tiled together, a theater or stadium screen, a light therapy device, and a sign.

20. An emissive region in an organic light emitting device, the emissive region comprising a compound having a structure $(L_A)_n ML_m$ according to Formula 1:

Formula 1



wherein M is a metal having an atomic weight greater than 40, n has a value of at least 1 and m+n is the maximum number of ligands that may be attached to the metal;

wherein A is a linking group selected from the group consisting of $-CR'R''-CR'R''-$, $-CR'R'-CR'R''-$, and $-CR'R'-CR'R'-CR'R'-$;

wherein each R' is independently selected from the group consisting of H, D, alkyl, cycloalkyl, aryl, heteroaryl, and combinations thereof,

wherein each R'' is independently selected from the group consisting of alkyl, cycloalkyl, aryl, heteroaryl, partially or fully deuterated variants thereof, and combinations thereof, wherein R's and R''s are optionally connected to form a saturated five membered ring or a saturated six membered ring, and combinations thereof,

wherein R^{1a} to R^{1g} are each independently selected from the group consisting of hydrogen, deuterium, alkyl, cycloalkyl, aryl, heteroaryl, and combinations thereof;

wherein any one of the ring atoms to which R^{1b} to R^{1g} are attached may be replaced with a nitrogen atom, wherein when the ring atom is replaced with a nitrogen atom the corresponding R group is not present;

wherein L is a substituted or unsubstituted cyclometalated ligand,

wherein L can be joined to R^{1g} through a linking group L²;

wherein L² is selected from the group consisting of a single bond, NR, O, S, CR¹R², and SiR¹R²;

wherein R, R¹, and R² can be same or different, and are independently selected from the group consisting of hydrogen, deuterium, alkyl, cycloalkyl, aryl, heteroaryl, and combinations thereof; wherein any adjacent R¹ and R² are optionally connected to form a saturated five membered ring or a saturated six membered ring.

* * * * *