



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>5</sup> :</b>  <b>C08F 4/64, 10/00</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 92/13009</b>  <b>(43) International Publication Date:</b> 6 August 1992 (06.08.92)
<b>(21) International Application Number:</b> PCT/US91/09589 <b>(22) International Filing Date:</b> 18 December 1991 (18.12.91) <b>(30) Priority data:</b> 644,053                      18 January 1991 (18.01.91)      US <b>(71) Applicant:</b> THE DOW CHEMICAL COMPANY [US/US]; 2030 Dow Center, Abbott Road, Midland, MI 48640 (US). <b>(72) Inventors:</b> KOLTHAMMER, Brian, W., S. ; 54 Royal Oak Circle, Lake Jackson, TX 77566 (US). SPENCER, Lee ; 4903 Clover Lane, Pearland, Texas 77584 (US). <b>(74) Agent:</b> CARTER, James, G.; The Dow Chemical Company, 2301 Brazosport Boulevard, The Patent Department, B-1211 Building, Freeport, TX 77541 (US).		<b>(81) Designated States:</b> AT, AT (European patent), AU, BB, BE (European patent), BF (OAPI patent), BG, BJ (OAPI patent), BR, CA, CF (OAPI patent), CG (OAPI patent), CH, CH (European patent), CI (OAPI patent), CM (OAPI patent), DE, DE (European patent), DK, DK (European patent), ES, ES (European patent), FI, FR (European patent), GA (OAPI patent), GB, GB (European patent), GN (OAPI patent), GR (European patent), HU, IT (European patent), JP, KP, KR, LK, LU, LU (European patent), MC (European patent), MG, ML (OAPI patent), MR (OAPI patent), MW, NL, NL (European patent), NO, PL, RO, SD, SE, SE (European patent), SN (OAPI patent), SU, TD (OAPI patent), TG (OAPI patent).  <b>Published</b> <i>With international search report.          Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
<b>(54) Title:</b> SILICA SUPPORTED TRANSITION METAL CATALYST		
<b>(57) Abstract</b>		
<p>A transition metal containing catalyst useful for the polymerization of <math>\alpha</math>-olefins is prepared by (A) forming in an inert atmosphere which excludes oxygen and moisture a slurry of (1) a porous inorganic oxide support material selected from the group consisting of silica, alumina, or a combination of silica and alumina, said support material containing not greater than 5 millimoles of hydroxyl groups per gram of support material and a particle size not greater than 10 microns and a surface area of from 50 to 800 m<sup>2</sup>/g in an inert organic liquid medium; (B) mixing said slurry with (2) an organomagnesium compound and stirring the resultant mixture at a temperature of from -20 °C to 120 °C for a time sufficient to saturate the surface of the support material; (C) mixing the product from (B) with (3) a titanium compound or a combination of a titanium compound and (4) a vanadium compound and stirring the resultant mixture at a temperature of from -20 °C to 120 °C for a time sufficient to allow complete reaction of the titanium compound and the vanadium compound with the organomagnesium moieties remained on the solid support; (D) mixing the product from (C) with an inert organic solution of (5) a Group IIIA metal alkyl halide at a temperature of from -20 °C to 120 °C for a time sufficient to complete the reduction of the titanium and vanadium, if present, compounds to their final oxidation state.</p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	ES	Spain	MG	Madagascar
AU	Australia	FI	Finland	ML	Mali
BB	Barbados	FR	France	MN	Mongolia
BE	Belgium	GA	Gabon	MR	Mauritania
BF	Burkina Faso	GB	United Kingdom	MW	Malawi
BG	Bulgaria	GN	Guinea	NL	Netherlands
BJ	Benin	GR	Greece	NO	Norway
BR	Brazil	HU	Hungary	PL	Poland
CA	Canada	IT	Italy	RO	Romania
CF	Central African Republic	JP	Japan	RU	Russian Federation
CG	Congo	KP	Democratic People's Republic of Korea	SD	Sudan
CH	Switzerland	KR	Republic of Korea	SE	Sweden
CI	Côte d'Ivoire	LI	Liechtenstein	SN	Senegal
CM	Cameroon	LK	Sri Lanka	SU	Soviet Union
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
DE	Germany	MC	Monaco	TG	Togo
DK	Denmark			US	United States of America

5

## SILICA SUPPORTED TRANSITION METAL CATALYST

10

The present invention pertains to silica supported transition metal catalysts and process for polymerizing olefins in their presence.

15

The polymerization of ethylene and the copolymerization of ethylene with other olefins is known to be carried out by solution and suspension (slurry) polymerization processes. Advantages of the solution process include short reaction times, improved heat removal and monomer conversion for mass and energy control of polymerizations and single-phase reaction environments for controlling reaction dynamics. A most advantageous solution polymerization would be conducted at even higher reaction temperatures yet with a polymerization catalyst that yields sufficiently high molecular weight polymers with a high catalyst efficiency at these higher temperatures which lowers catalyst residues in the product an/or permits complete omission of the catalyst removal step.

20

25

30

In the suspension (slurry) polymerization of olefins, the advantages are low pressures, low temperatures and the ability to make very high molecular weight polymers. It is advantageous to carryout these

reactions with sufficiently high polymerization efficiencies such that residues from the polymerization catalyst do not have to be removed from the resulting polymer.

5           There are many polymerization catalysts for suspension polymerization known in the art. Hagerty et al. in U.S. Patent 4,562,169 disclose the preparation of a supported catalyst by treating a solid porous carrier having reactive OH groups such as silica in a liquid  
10 medium with an organomagnesium compound to react with the OH groups on the carrier; evaporating said liquid to precipitate magnesium onto the carrier and recovering a supported magnesium composition in the form of a dry,  
15 free-flowing powder; reacting the powder with a tetravalent titanium compound in a liquid medium. The catalyst is useful in the polymerization of olefins.

Nowlin in U.S. Patent 4,593,009 and U.S. Patent  
20 4,672,096 discloses a catalyst for polymerizing olefins which catalyst is prepared by treating a carrier containing OH groups with an organomagnesium composition and contacting the thus-formed magnesium-containing carrier with a solution of at least one tetravalent  
25 vanadium compound or a solution containing both a vanadium compound and a titanium compound.

Gessel in U.S. 4,244,838 describes catalysts prepared from an organomagnesium compound, an organic  
30 hydroxyl-containing material and a transition metal halide. These solids produced by this reaction are isolated and washed prior to use in a polymerization.

Fuentes et al. in U.S. 4,544,647 disclose catalyst compositions prepared from an organomagnesium

material, an organic hydroxyl-containing material, a reducing halide source and a transition metal compound.

Marchand et al. in U.S. 4,910,272 describe a process for polymerizing olefins in the presence of a catalyst prepared from an inorganic oxide, an organomagnesium material, an organic hydroxyl-containing material, a reducing halide source and a transition metal compound.

The catalyst efficiency of these catalysts is, in general, decreased with increased polymerization temperatures, specifically temperatures above 140°C.

The catalysts known for solution polymerization comprise an organomagnesium component, an aluminum halide and/or an additional halide source and a transition metal compound. Lowery et al in US 4,250,288 describes such compositions that are useful in the polymerization of  $\alpha$ -olefins above 140°C.

Sakurai et al. in U.S. 4,330,646 describes similar catalysts containing a titanium or a titanium and/or a vanadium compound as the transition metal component. These catalysts are useful at polymerization temperatures of at least 180°C. The disadvantage of these catalysts is that the reactions that produce the catalyst solids are highly exothermic and difficult to control and reproduce. These catalyst compositions also contain a large excess of halide with respect to the transition metal component and yield polymers with a relatively high halide content. The composition as a whole is used directly in the polymerization of olefins.

It would be desirable to have available catalyst compositions which exhibit significantly higher

polymerization efficiencies based on the transition metal and the halide. It would also be desirable to have available catalyst compositions which exhibit these high efficiencies while being prepared in a manner which did not require the isolation and/or washing of the solid catalytic product. It would be further desirable to ease the process of preparation of the catalyst in order to increase reproducibility and quality of the catalyst. It would also be desirable to have available such catalysts which would provide polymers having a high molecular weight and a relatively narrow molecular weight distribution and which exhibit more tolerance to hydrogen at polymerization temperatures of at least 180°C and even greater than 200°C.

One aspect of the present invention pertains to a supported transition metal catalyst component which comprises an inert liquid medium having slurried therein a composition comprising the product resulting from contacting (1) a porous solid inorganic oxide support material selected from the group consisting of silica, alumina, or a combination of silica and alumina, said support material containing not greater than 5 millimoles of hydroxyl groups per gram of support material and a particle size not greater than 10 microns and a surface area of from 50 to 800 m<sup>2</sup>/g; (2) a hydrocarbon soluble organomagnesium alkoxide or hydrocarbon soluble magnesium dialkoxide; (3) a titanium compound; optionally (4) a vanadium compound; and (5) a Group IIIA metal alkyl halide; and wherein the components are employed in amounts which provide the following atomic ratios:

Si+Al (from the inorganic oxide support):Mg of from 1:1 to 30:1;

Mg:Ti of from 0.2:1 to 10:1;

Mg:V of from 0:1 to 10:1;

Mg:IIIA metal of from 0.05:1 to 5:1; and

V:Ti of from 0:1 to 5:1.

5                   Another aspect of the present invention  
pertains to a process for preparing a supported  
transition metal catalyst component slurried in an inert  
liquid medium, which process comprises (A) forming in an  
10 inert atmosphere which excludes oxygen and moisture a  
slurry of (1) a porous inorganic oxide support material  
selected from the group consisting of silica, alumina,  
or a combination of silica and alumina, said support  
material containing not greater than 5 millimoles of  
15 hydroxyl groups per gram of support material and a  
particle size not greater than 10 microns and a surface  
area of from 50 to 800 m<sup>2</sup>/g in an inert organic liquid  
medium; (B) mixing said slurry with (2) a hydrocarbon  
soluble organomagnesium alkoxide or hydrocarbon soluble  
20 magnesium dialkoxide and stirring the resulting mixture  
at a temperature of from 20°C to 120°C for a time  
sufficient to saturate the surface of the support  
material; (C) mixing the product from (B) with (3) a  
25 titanium compound or a combination of a titanium  
compound and (4) a vanadium compound or adding the  
titanium compound and vanadium compound separately and  
stirring the resultant mixture at a temperature of from  
20°C to 120°C for a time sufficient to allow complete  
30 reaction of the titanium compound and the vanadium  
compound with the organomagnesium moieties remaining on  
the solid support; (D) mixing the product from (C) with  
an inert organic solution of (5) a Group IIIA metal  
alkyl halide at a temperature of from 20°C to 120°C for a  
time sufficient to complete the reduction of the

titanium and vanadium, if present, compounds to their final oxidation state.

A further aspect of the present invention pertains to a process for polymerizing one or more  $\alpha$ -olefins and optionally one or more polymerizable ethylenically unsaturated compounds other than an  $\alpha$ -olefin which process comprises contacting the materials to be polymerized with (A) a supported transition metal containing catalyst component comprising the product resulting from contacting (1) a porous inorganic oxide support material selected from the group consisting of silica, alumina, or a combination of silica and alumina, said support material containing not greater than 5 millimoles of hydroxyl groups per gram of support material and a particle size less than 10 microns and a surface area of from 50 to 800 m<sup>2</sup>/g; (2) a hydrocarbon soluble organomagnesium alkoxide or hydrocarbon soluble magnesium dialkoxide; (3) a titanium compound; optionally (4) a vanadium compound; and (5) a Group IIIA metal alkyl halide; and wherein the components are employed in amounts which provide the following atomic ratios:

- Si+Al:Mg of from 1:1 to 30:1;  
Mg:Ti of from 0.2:1 to 10:1;  
Mg:V of from 0.2:1 to 10:1;  
Mg:IIIA metal of from 0.05:1 to 5:1;  
V:Ti of from 0:1 to 5:1; and  
(B) a cocatalyst or activator for component (A).

The present invention provides catalyst compositions which exhibit high polymerization efficiencies based on the transition metal and the halide and are prepared in a manner which do not require



the isolation and/or washing of the solid catalytic product. The catalysts which contain vanadium produce a polymer having a high molecular weight and a relatively narrow molecular weight distribution when the polymers are prepared by the solution process.

5

The present invention provides catalyst compositions which exhibit high polymerization efficiencies based on the transition metal and the halide and are prepared in a manner which do not require the isolation and/or washing of the solid catalytic product. The catalysts which contain vanadium produce a polymer having a relatively broad molecular weight distribution when the polymers are prepared by the slurry process.

10  
15

All references herein to elements or metals belonging to a certain Group refers to the Periodic Table Of The Elements published by the Sargent-Welch Scientific Company, Skokie Illinois, catalog number S-18806 (1968).

20

The term hydrocarbyl as employed herein means any aliphatic, cycloaliphatic, aromatic, aryl substituted aliphatic, aryl substituted cycloaliphatic, aliphatic substituted aromatic or aliphatic substituted cycloaliphatic groups.

25

30

The term hydrocarbyloxy means a hydrocarbyl group having an oxygen linkage between it and the carbon atom to which it is attached.

PREPARATION OF TRANSITION METAL CATALYST

The transition metal catalyst of the present invention can be prepared in the following manner.

5 The porous inorganic oxide support material is slurried in an inert organic diluent under conditions which exclude oxygen (air) and moisture at a temperature of from 20°C to 120°C, preferably from 0°C to 100°C, more preferably from 20°C to 70°C. No particular time is  
10 required other than that to form a uniform slurry of the support in the diluent. This depends upon the amounts involved, but usually a good uniform slurry can be formed in 1 hour in a concentration range from 0.1 to 15, preferably from 0.5 to 10, more preferably from 1 to  
15 7, weight percent.

To this slurry is then added the hydrocarbon soluble magnesium alkoxide or hydrocarbon soluble dialkoxide, again under conditions which exclude oxygen  
20 (air) and moisture, and the mixture stirred at a temperature of from -20°C to 120°C, preferably from 0°C to 100°C, more preferably from 20°C to 70°C for a time sufficient to react the magnesium compound with surface  
25 of the solid support, usually from 0.1 to 10, preferably from 0.2 to 8, more preferably from 0.5 to 4, hours.

After the above addition of the magnesium compound, a titanium compound or a combination of a titanium compound and a vanadium compound is added,  
30 again under conditions which excludes oxygen (air) and moisture, and the mixture stirred at a temperature of from -20°C to 120°C, preferably from 0°C to 100°C, more preferably from 20°C to 70°C for a time sufficient to completely react the titanium compound and the vanadium compound with the reactive silica and magnesium

functionalities, usually from 0.1 to 100, preferably from 0.5 to 20, more preferably from 1 to 10, hours. The titanium and vanadium compounds can be premixed prior to their addition or they can be added separately in any order to the product resulting from blending the magnesium compound with the slurry of the inorganic oxide support material.

Following the addition and mixing of the titanium and/or vanadium compounds, a Group IIIA metal alkyl halide is added and the mixture is stirred at a temperature of from 20°C to 120°C, preferably from 0°C to 100°C, more preferably from 20°C to 70°C for a time sufficient to reduce the titanium compound and vanadium compound, if present, to their final oxidation states, usually from 1 to 100, preferably from 2 to 50, more preferably from 5 to 20, hours.

Upon completion of the addition and mixing of the Group IIIA metal alkyl halide, the thus formed transition metal catalyst component can be employed in the polymerization of  $\alpha$ -olefins as is without isolation of the solid components from the liquid components. The transition metal catalyst component can be employed immediately upon its preparation or the component can be stored under inert conditions for some length of time, usually for periods of time as long as 90 days.

The components can also, if desired, be added in the order as follows: SiO<sub>2</sub> + Mg compound + Ti compound + Al compound + V compound.

The components can also, if desired, be added in the order as follows: SiO<sub>2</sub> + Mg compound + Al compound + Ti compound + V compound.

5 Oxygen (air) and moisture can be excluded during catalyst preparation by conducting the preparation in an inert atmosphere such as, for example, nitrogen, argon, xenon, methane or any combination thereof.

10 COMPONENTS OF THE TRANSITION METAL CATALYST

Porous Support Material

15 Suitable porous silica or alumina support materials which can be employed herein include, those containing not greater than 5, preferably not greater than 4, more preferably not greater than 3, millimoles of hydroxyl groups (OH) per gram of support material. These hydroxyl (OH) groups are isolated silanol groups  
20 on the silica surface.

The hydroxyl groups can be reduced or eliminated by treating the support material either thermally or chemically. Thermally, the support  
25 material can be heated at temperatures of from about 250°C to 870°C, more preferably from 600°C to 800°C for a time sufficient to reach the equilibrium hydroxyl group concentration, usually from 1 to 24, preferably from 2 to  
30 20, more preferably from 3 to 12, hours.

The hydroxyl (OH) groups can be removed or reduced chemically by treating the support material with SiCl<sub>4</sub>, chlorosilanes, silylamines, or any combination thereof at a temperature of from 20°C to 120°C, more

preferably from 0°C to 40°C for a time sufficient to reduce the hydroxyl content to the desired value, usually less than 30 minutes.

5 The porous support material has a particle size of not greater than 10, preferably from 0.1 to 10, more preferably from 1 to 9, most preferably from 2 to 8, microns and a surface area in the range of from 50 to 800, preferably from 150 to 600, more preferably from 10 300 to 500, m<sup>2</sup>/g.

The particle size of the support is important as it has surprisingly been discovered that lowering the particle size of the support below 10 microns while 15 maintaining the support surface area and porosity results in an unexpected increase in the catalyst productivity and hence a reduction in product chloride and titanium residues relative to products of the same catalyst made on a support of equivalent surface area 20 and porosity but larger particle size.

#### Inert Liquid Diluent

Suitable inert liquid diluents which can be 25 employed to slurry the inorganic oxide support material and as a diluent for any of the other components employed in the preparation of the catalyst include, for example, aliphatic hydrocarbons, aromatic hydrocarbons, naphthinic hydrocarbons, or any combination thereof. 30 Particularly suitable solvents include, for example, pentane, isopentane, hexane, heptane, octane, isooctane, nonane, isononane, decane, cyclohexane, methylcyclohexane, toluene, any combination of any two or more of such diluents.

Organomagnesium Compound

Suitable magnesium compounds which can be employed in the preparation of the transition metal catalyst component include, for example, those hydrocarbon soluble organomagnesium compounds represented by the formulas  $R_xMg(OR)_y$ ; wherein each R is independently a hydrocarbyl group having from 1 to 20, preferably from 1 to 10, more preferably from 2 to 8, carbon atoms;  $x+y=2$ ; and  $0.5 \leq y \leq 2$ . Preferably, x has a value of zero or 1 and y has a value of 1 or 2 and most preferably, x has a value of 1 and y has a value of 2. Particularly suitable magnesium compounds include, for example, n-butylmagnesium butoxide, ethylmagnesium butoxide, butylmagnesium ethoxide, octylmagnesium ethoxide, butylmagnesium i-propoxide, ethylmagnesium i-propoxide, butylmagnesium n-propoxide, ethylmagnesium n-propoxide, s-butylmagnesium butoxide, butylmagnesium 2,4-dimethylpent-3-oxide, n-butylmagnesium octoxide, s-butylmagnesium octoxide, or any combination thereof.

Also suitable are the hydrocarbon soluble reaction product (dialkoxide) of a magnesium dihydrocarbyl ( $MgR_2$ ) compound and an oxygen-containing compound (ROH) such as, for example, an aliphatic or cycloaliphatic or acyclic  $C_5-C_{18}$  beta or gamma alkyl-substituted secondary or tertiary monohydric alcohol, as disclosed by Kamienski in U.S. Patent 4,748,283 which is incorporated by reference. The reaction is preferably conducted in the presence of a liquid hydrocarbon media. The alcohol is usually employed in slightly more than twice the molar equivalent, based on magnesium. The reaction is usually conducted at temperatures not in excess of  $50^\circ C$ , preferably below  $40^\circ C$ . Particularly suitable oxygen containing compounds include, for

example, 2,4-dimethyl-3-pentanol, 2,3-dimethyl-2-butanol, 2,4-dimethyl-3-hexanol, 2,6-dimethyl-4-heptanol, 2,6-dimethyl-cyclohexanol, or any combination thereof. Particularly suitable magnesium dialkyl compounds include, for example, butylethylmagnesium, 5 dibutylmagnesium, dihexylmagnesium, butyloctylmagnesium, or any combination thereof.

#### Titanium Compound

10 Suitable titanium compounds which can be employed in the preparation of the transition metal catalyst component include, for example, those represented by the formula  $TiX_{4-a}(OR')_a$ ; wherein each R' is independently an alkyl group having from 1 to 20, 15 preferably from 1 to 10, more preferably from 2 to 8 carbon atoms; X is a halogen atom, preferably chlorine; and a has a value from zero to 4. Particularly suitable titanium compounds include, for example, titanium 20 tetrachloride ( $TiCl_4$ ), titanium tetraisopropoxide ( $Ti(O-i-C_3H_7)_4$ ), titanium tetraethoxide ( $Ti(OC_2H_5)_4$ ), titanium tetrabutoxide ( $Ti(OC_4H_9)_4$ ), titanium triisopropoxidechloride ( $Ti(O-i-C_3H_7)_3Cl$ ), or any combination thereof.

#### Vanadium Compound

25 In the solution process, when it is desirable to produce  $\alpha$ -olefin polymers which have a high molecular weight and a relatively narrower molecular weight 30 distribution than that produced with the catalyst containing only titanium as the transition metal, a vanadium compound can be added as a portion of the transition metal component during preparation of the catalyst. A narrowing of the molecular weight

distribution is indicated by a lowering of the  $I_{10}/I_2$  value of the polymer.

5 By the term "relatively narrow molecular weight distribution" it is meant that the resulting polymer produced in the presence of a catalyst containing both titanium and vanadium has a narrower molecular weight distribution than the polymer produced under similar conditions with a similar catalyst prepared without the  
10 vanadium component.

In the slurry process when it is desirable to produce  $\alpha$ -olefin polymers which have a high molecular weight and a relatively broad molecular weight  
15 distribution than that produced with the catalyst containing only titanium as the transition metal, a vanadium compound can be added as a portion of the transition metal component during preparation of the catalyst. A broadening of the molecular weight  
20 distribution is indicated by an increase of the  $I_{20}/I_2$ , high load melt flow ratio (HLMFR), value of the polymer.

25 By the term "relatively broad molecular weight distribution" it is meant that the resulting polymer produced in the presence of a catalyst containing both titanium and vanadium has a broader molecular weight distribution than the polymer produced under similar conditions with a similar catalyst prepared without the  
30 vanadium component.

Suitable vanadium compounds which can be employed in the preparation of the transition metal catalyst include, for example, those represented by the formulas  $VX_4$  and  $V(O)X_3$ ; wherein each X is



independently OR or a halogen atom, preferably chlorine; each R is independently an alkyl group having from 1 to 20, preferably from 2 to 8, more preferably from 2 to 4, carbon atoms. Particularly suitable vanadium compounds include, for example, vanadium tetrachloride (VCl<sub>4</sub>),  
5 vanadium trichloride oxide (V(O)Cl<sub>3</sub>), vanadium triisopropoxide oxide (V(O)(O-i-C<sub>3</sub>H<sub>7</sub>)<sub>3</sub>), vanadium triethoxide oxide (V(O)(OC<sub>2</sub>H<sub>5</sub>)<sub>3</sub>), or any combination thereof.

#### 10 Organo Halide Compounds of a Group IIIA Metal

Suitable organo halide compounds of a group IIIA Metal which can be employed in the preparation of the transition metal catalyst include, for example,  
15 those represented by the formula R'<sub>y</sub>MX<sub>z</sub>; wherein M is a metal from Group IIIA of the Periodic Table of the Elements, preferably aluminum or boron; each R' is independently an alkyl group having from 1 to 20,  
20 preferably from 1 to 10, more preferably from 2 to 8, carbon atoms; X is a halogen atom, preferably chlorine; y and z each independently have a value from 1 to a value equal to the valence of M minus 1 and y+z has a value equal to the valence of M. Particularly suitable  
25 such organo halide compounds include, for example, ethylaluminum dichloride, ethylaluminum sesquichloride, diethylaluminum chloride, isobutylaluminum dichloride, diisobutylaluminum chloride, octylaluminum dichloride, or any combination thereof.

#### 30 Component Amounts

For use in the solution process, the components are employed in quantities which provide an atomic ratio as follows:

Si and/or Al(from the inorganic oxide support):Mg of from 1:1 to 50:1, preferably from 2:1 to 40:1, more preferably from 4:1 to 20:1;

5 Mg:group IIIA metal of from 0.01:1 to 100:1, preferably from 0.05:1 to 10:1, more preferably from 0.1:1 to 5:1.

Mg:Ti of from 0.05:1 to 40:1, preferably from 0.1:1 to 20:1, more preferably from 0.2:1 to 10:1;

10 Mg:V, when V is present, of from 0.05:1 to 40:1, preferably from 0.1:1 to 20:1, more preferably from 0.2:1 to 10:1;

15 V:Ti of from 0:1 to 20:1, preferably from 0.1:1 to 10:1, more preferably from 0.2:1 to 5:1.

For use in the suspension (slurry) process, the components are employed in quantities which provide an atomic ratio as follows:

20 Si and/or Al(from the inorganic oxide support):Mg of from 1:1 to 50:1, preferably from 2:1 to 40:1, more preferably from 4:1 to 20:1;

25 Mg:group IIIA metal of from 0.01:1 to 100:1, preferably from 0.05:1 to 10:1, more preferably from 0.1:1 to 5:1.

Mg:Ti of from 0.05:1 to 40:1, preferably from 0.1:1 to 20:1, more preferably from 0.2:1 to 10:1;

30 Mg:V, when V is present, of from 0.05:1 to 40:1, preferably from 0.1:1 to 20:1, more preferably from 0.2:1 to 10:1;

V:Ti of from 0:1 to 20:1, preferably from 0:1 to 10:1, more preferably from 0:1 to 3:1.

The compound employed as the liquid medium can be employed in any amount which provides the catalyst component with the desired consistency which does not interfere with the polymerization behavior of the catalyst.

#### COCATALYST or ACTIVATOR

The transition metal catalyst component described above requires a cocatalyst or activator in order to efficiently polymerize the  $\alpha$ -olefin monomer(s). Suitable cocatalysts or activator compounds include, for example, Group IIIA metal alkyl, metal alkoxide or metal alkyl halide compounds, particularly C<sub>1</sub>-C<sub>10</sub> alkyl compounds of aluminum. Particularly suitable such compounds include, for example, triethylaluminum, trimethylaluminum, triisobutylaluminum, trihexylaluminum, trioctylaluminum, diethylaluminum chloride, diethylaluminum ethoxide, or any combination of any two or more of such compounds.

Also suitable are the aluminoxanes such as those represented by the formula  $(Al(O)R)_x$ ; wherein R is an alkyl group having from 1 to 8 carbon atoms and x has a value greater than 4. Particularly suitable aluminoxanes include, for example, methylaluminoxane, hexaisobutyltetraluminoxane, or any combination of any two or more of such compounds. Also, mixtures of these aluminoxanes with alkyl aluminum compounds such as, for example, triethylaluminum or tributylaluminum can be employed.

The cocatalyst or activator compound can be employed in the solution process in amounts which

provide a ratio of atoms of Group IIIA metal per combined atoms of Ti and V of from 0.1:1 to 50:1, preferably from 1:1 to 20:1, more preferably from 2:1 to 15:1.

5           The cocatalyst or activator compound can be employed in the suspension (slurry) process in amounts which provide a ratio of atoms of Group IIIA metal per combined atoms of Ti and V of from 1:1 to 1000:1, preferably from 5:1 to 500:1, more preferably from 10:1  
10 to 200:1.

#### POLYMERIZABLE MONOMERS

15           Suitable polymerizable monomers include, for example  $\alpha$ -olefins having from 2 to 20, preferably from 2 to 12, more preferably from 2 to 8, carbon atoms and any combination of any two or more of such  $\alpha$ -olefins. Particularly suitable such  $\alpha$ -olefins include, for  
20 example, ethylene, propylene, 1-butene, 1-pentene, 4-methylpentene-1, 1-hexene, 1-heptene, 1-octene, 1-nonene, 1-decene, 1-undecene, 1-dodecene, 1-tridecene, 1-tetradecene, 1-pentadecene, or any combination thereof. Preferably, the  $\alpha$ -olefins are ethylene,  
25 propene, 1-butene, 4-methyl-pentene-1, 1-hexene, 1-octene, and combination of any two or more of such  $\alpha$ -olefins.

#### POLYMERIZATION

30           The catalysts of the present invention can be advantageously employed in the polymerization of monomers by the solution or slurry process. The slurry process is employed at temperatures of from 0°C up to a temperature just below the temperature at which the

5 resulting polymer becomes soluble in the inert polymerization medium, preferably at temperatures of from 60°C to 105°C, more preferably from 80°C to 95°C. The solution process is employed at temperatures from the temperature at which the resulting polymer is soluble in the inert reaction medium up to 275°C, preferably at temperatures of from 145°C to 260°C, more preferably from 180°C to 240°C.

10 The polymerization can be employed at pressures of from 1 to 2,000, preferably from 5 to 500, more preferably from 10 to 50, atmospheres.

15 Molecular weight control agents such as hydrogen can be employed in the manner known to those skilled in the art of polymerizing  $\alpha$ -olefins. Usually the greater the amount of hydrogen or terminating agent employed the lower the molecular weight of the resulting polymer. The hydrogen is employed in that quantity  
20 which will provide the resulting polymer with the desired molecular weight as indicated by the desired  $I_2$  value.

25 The solution polymerization can be employed in the presence of any suitable inert reaction medium such as, for example, aromatic hydrocarbons, aliphatic hydrocarbons, naphthinic hydrocarbons, or any combination thereof. Particularly suitable inert  
30 reaction medium include, for example, hexane, heptane, octane, isooctane, nonane, isononane, decane, undecane, dodecane, tridecane, tetradecane, cyclohexane, methylcyclohexane, or any combination thereof.

The suspension (slurry) polymerization can be employed in the presence of any suitable inert reaction medium such as, for example, aromatic hydrocarbons, aliphatic hydrocarbons, naphthinic hydrocarbons, liquified  $\alpha$ -olefins, liquified hydrocarbons, or any combination thereof. Particularly suitable inert reaction medium include, for example, isobutane, isopentane, pentane, hexane, heptane, octane, isooctane, nonane, isononane, decane, cyclopentane, cyclohexane, or any combination thereof.

The following examples are illustrative of the invention, but are not to be construed as to limiting the scope thereof in any manner.

The following components were employed in the examples and comparative experiments.

5        Silica Support #1 is a silica having a mean particle size of  $3\mu$ , a surface area of  $337 \text{ m}^2/\text{g}$ , subjected to heating in a fluidized bed under a nitrogen atmosphere at  $600^\circ\text{C}$  for 12 hours resulting in a silica support material having a hydroxyl content of 3.2 millimoles/gram.

10        Silica Support #2 is a silica having a mean particle size of  $70\mu$ , a surface area of  $310 \text{ m}^2/\text{g}$ , subjected to heating in a fluidized bed under a nitrogen atmosphere at  $600^\circ\text{C}$  for 12 hours resulting in a silica  
15 support material having a hydroxyl content of 1.9 millimoles/gram.

20        Silica Support #3 is a sieve fraction of a silica having a mean particle size of  $145\mu$ , a surface area of  $310 \text{ m}^2/\text{g}$ , subjected to heating in a fluidized bed under a nitrogen atmosphere at  $800^\circ\text{C}$  for 12 hours resulting in a silica support material having a hydroxyl  
content of 1.8 millimoles/gram.

25        Silica Support #4 is a sieve fraction of a silica having a mean particle size of  $85\mu$ , a surface area of  $310 \text{ m}^2/\text{g}$ , subjected to heating in a fluidized bed under a nitrogen atmosphere at  $800^\circ\text{C}$  for 12 hours  
30 resulting in a silica support material having a hydroxyl content of 1.8 millimoles/gram.

Silica Support #5 is a sieve fraction of a silica having a mean particle size of  $40\mu$ , a surface area of  $310 \text{ m}^2/\text{g}$ , subjected to heating in a fluidized

bed under a nitrogen atmosphere at 800°C for 12 hours resulting in a silica support material having a hydroxyl content of 1.8 millimoles/gram.

5        Silica Support #6 is a sieve fraction of a silica having a mean particle size of 3 $\mu$ , a surface area of 310 m<sup>2</sup>/g, subjected to heating in a fluidized bed under a nitrogen atmosphere at 800°C for 12 hours resulting in a silica support material having a hydroxyl  
10        content of 1.8 millimoles/gram.

15        Silica Support #7 is a small size silica having a mean particle size of 3 $\mu$ , a surface area of 430 m<sup>2</sup>/g, subjected to heating in a rotary kiln under a nitrogen atmosphere at 800°C for 5 hours resulting in a silica support material having a hydroxyl content of 2.8 millimoles/gram.

20        ISOPAR™ E is a fractionated isoparaffinic solvent having a boiling range of 113-143°C available from Exxon Corporation.

25        The polymer properties were obtained by the following methods.

I<sub>2</sub> by ASTM D 1230-86 condition "E".

I<sub>10</sub> by ASTM D 1230-86 condition "N".

I<sub>20</sub> by ASTM D 1230-86 condition "F".

Density by ASTM D 1248-84.

30

#### Polymerization (Solution Conditions)

A stirred, one-gallon (3.79L) autoclave reactor was charged with two liters of ISOPAR™ E and the required amount of the alpha-olefin comonomer, octene-1, in an amount such that its molar concentration in the



reactor was 0.99M before heating to the desired  
temperature. The required amount of hydrogen, 2 psig (13.8 kPa), was then added to the reactor followed by ethylene sufficient to bring the total pressure to 450 psig (3,103 kPa). An amount of the activated catalyst  
5 was injected into the reactor. The reactor temperature and pressure were maintained constant at the initial pressure and temperature, as indicated, by continually feeding ethylene during the polymerization run and  
10 cooling the reactor as necessary. After a 10 minute reaction time (unless otherwise indicated), the ethylene was shut off and the hot solution transferred into a nitrogen-purged resin kettle. After drying, the samples were then weighed to determine catalyst efficiencies  
15 followed by melt flow and density measurements via standard procedures.

20

25

30

Polymerization (Slurry Conditions)

A stirred, 1.4 liter autoclave reactor was charged with 700 mL of ISOPAR™ E before heating to the desired temperature. The vapor space was swept with hydrogen and then hydrogen was added to the reactor until the desired partial pressure was reached. This was followed by ethylene sufficient to bring the total pressure to 175 psig (1,207 kPa). An amount of the activated catalyst as described under preparation of activated catalyst was injected into the reactor. The reactor temperature and pressure were maintained constant at the initial pressure and temperature by continually feeding ethylene during the polymerization run and cooling the reactor as necessary. After a 45 minute reaction time (unless otherwise indicated), the ethylene was shut off and the polymer slurry transferred into a nitrogen-purged resin kettle. After drying, the samples were then weighed to determine catalyst efficiencies followed by melt flow and density measurements.

**EXAMPLE 1**A. Preparation of Transition Metal Catalyst Component

To 1 g of Silica Support #1 slurried in 50 ml of ISOPAR™ E was added the required amount of butyloctylmagnesium ethoxide (BOMAG-0 from Schering A.G.). The resulting slurry was stirred for 1 hour after which an amount of titanium tetrachloride (TiCl<sub>4</sub>) was added. The slurry rapidly darkens to a deep brown color and was stirred for a further two hours. An aliquot of a solution of 25percent ethylaluminum dichloride was then added and the final mixture stirred for 17 hours. The complete mixtures prepared in this manner were used without further isolation or

washing. The catalysts have the atomic ratios as indicated in Table I.

#### B. Preparation of Activated Catalyst

5 An activated catalyst was prepared by slurring  
4 mL of the transition metal catalyst component in 40 mL  
of ISOPAR™ E in a 100 mL septum-capped bottle in a  
glove box. To this mixture was added the required  
amount of 0.15 M solution of triethylaluminum in hexane  
10 as a cocatalyst or activator. The resulting slurry was  
made up to 50 mL total volume with ISOPAR™ E and the  
mixture injected into the batch reactor to effect the  
polymerization.

The atomic ratio of Al from the cocatalyst to titanium  
15 is provided in Table I.

#### C. Polymerization (Solution Conditions)

The polymerization procedure under solution  
conditions was employed at a polymerization temperature  
20 of 185°C. The catalyst efficiency is provided in Table  
I.

#### D. (Comparative)

25 A catalyst was prepared as described in U.S.  
Patent 4,562,169 in the following manner.

30 Davison Silica Gel, Grade 952, was  
dehydroxylated by fluidizing with nitrogen and heating  
at 800°C for 12 hours and cooled to room temperature  
under nitrogen.

10 grams of the activated silica was slurried  
in 100 mL of anhydrous degassed hexane, brought to a  
reflux temperature of 60°C and 7 mL of a 2.6 M solution

of ethylmagnesium chloride in tetrahydrofuran (THF) added slowly followed by further refluxing for 120 minutes. The solvents were removed by distillation and the silica dried at 80°C under a nitrogen purge.

5 This product was slurried with a premixed solution of 6 mL of TiCl<sub>4</sub> dissolved in 100 mL of Isopar™E and the slurry stirred at 50°C for two hours. This mixture was allowed to cool to room temperature and the solids washed twice with 100 mL portions of  
10 Isopar™E and twice with 100 mL portions of hexane and dried under a nitrogen purge to yield a tan colored free-flowing powder. Analysis of the powder indicated that it contained 1.3 mmol/g Mg/g catalyst, 0.9 mmol Ti/g catalyst and 4.5 mmol Cl/g catalyst. The catalyst  
15 was then combined with triethylaluminum (TEA) activator (cocatalyst) by slurrying 2 g of the dry catalyst in 40 ml of Isopar™E in a 4 oz (118.3 mL) septum capped bottle in a glove box. A 2 mL aliquot of this solution was transferred to a second bottle to which was added  
20 the required amount of a 0.15 M solution of triethylaluminum in hexane followed by an additional 20 mL of Isopar™E. The required amount of this slurry was then injected into a batch reactor to effect the  
25 polymerization under solution conditions at 175°C as described earlier. The catalyst efficiency and product data are shown in Table I.

30

Table I

Run No.	Catalyst Source	mmol Mg	mmol Ti	mmol Al	mmol Cl	Atomic Ratio Mg/Ala/Cl/Ti	Atomic Ratio of Alb/Ti	Efficiency (Kg Polymer per gram Ti or Cl)	
								Ti	Cl
A	Ex 1-B	1.4	0.4	4.5	10.6	3.5/11.3/26.5/1	11/1	478	24
B	Ex 1-B	1.9	0.4	4.5	10.6	4.8/11.3/26.5/1	6/1	627	28
C	Ex 1-B	1.8	0.2	3.5	9.4	3.0/5.8/15.7/1	5/1	413	27
D	ex 1-D	1.3	0.9	---	4.5	-----	5/1	30	8

a Aluminum from transition metal catalyst component.

b Aluminum from cocatalyst.

**EXAMPLE 2****A. Preparation of Transition Metal Catalyst Component**

To a 1 g sample of the support designated in  
5 Table II slurried in 50 mL of ISOPAR™E was added 2.0  
mmol of butylethylmagnesium butoxide (BEMB from Texas  
Alkyls Inc.). The mixture was stirred for one hour and  
treated sequentially with 1.0 mmol  $\text{TiCl}_4$  and 1.0 mmol  
10  $\text{V(O)Cl}_3$  as a neat mixture and 6.0 mmol of ethylaluminum  
dichloride (4.0 mL of a 1.5 M solution in hexane). The  
mixture was diluted to 100 mL total volume and then  
stirred for 24 hours. The atomic ratios of the  
components in the transition metal complex were  
15  $\text{Mg/Al/Cl/Ti/V}$  was 2/6/19/1/1. The catalyst components  
were activated (use of cocatalyst) according to the  
procedure described in Example 1 employing Al  
(activator)/Ti ratio of 8/1.

**B. Polymerization**

20 The polymerizations were conducted under  
solution process conditions at 185°C. The results of  
the polymerization reactions are shown in Table II.

25

30

Table II. Effect of Silica Particle Size on Solution Polymerizations

Run No.	Support		Density g/cc	I <sub>2</sub>	Efficiency (Kg Polymer per gram Ti or Cl)	
	No.	Size μ			Ti	Cl
A*	3	145	0.9080	1.16	49	30
B*	5	40	0.9119	1.05	499	35
C	6	3	0.9159	1.13	842	60

\* Not an example of the present invention.

### EXAMPLE 3

#### A. Preparation of Transition Metal Catalyst Component

To 1 g of the indicated silica support of different mean particle sizes slurried in 50 ml of ISOPAR™ E was added 2.0 mmol of butylethylmagnesium butoxide (BEMB from Texas Alkyls Inc). The resulting slurry was stirred for 1 hour after which 0.20 mmol of titanium tetraisopropoxide was added. The slurry was stirred for a further two hours. An aliquot of a solution of 25percent ethylaluminum dichloride (4.0 mmol Al) was then added and the final mixture stirred for 17 hours. The complete mixtures prepared in this manner were used without further isolation or washing. The atomic ratios of Mg/Al/Cl/Ti were 10/20/40/1.

The catalysts were activated with triisobutylaluminum at an atomic ratio of Al/Ti of 100/1 by the procedure described in Example IB.

5        B. Polymerization

      The polymerizations were conducted under slurry conditions using a hydrogen to ethylene ratio of 1:1 and a reactor temperature of 85°C. The results of the polymerization reactions are shown in Table III.

10

15

20

25

30



Table III. Effect of Silica Particle Size on Slurry Polymerizations

Run No.	Catalyst Support		Atomic Ratios				I <sub>2</sub>	I <sub>20</sub> /I <sub>2</sub>	Efficiency (Kg Polymer per gram of Ti or Cl)	
	#	Size (μ)	Transition Metal Catalyst Component		Cocat. Al/Ti	Ti			Cl	
			Mg/Al/Cl/Ti	Si/Mg						
A*	3	145	10/20/40/1	8.3	100:1	0.40	42.8	531	18	
B*	4	85	10/20/40/1	8.3	100:1	0.33	34.7	727	24	
C*	5	40	10/20/40/1	8.3	100:1	0.48	36.9	575	19	
D	6	3	10/20/40/1	8.3	100:1	0.37	38.7	1,500	51	
E	7	3	10/20/40/1	8.3	100:1	0.30	34.2	1,510	51	

\* Not an example of the present invention.

**EXAMPLE 4****A. Preparation of Transition Metal Catalyst Component**

To 1 g of Silica Support #7 slurried in 50 ml  
5 of ISOPAR™ E was added 2.0 mmol of butylethylmagnesium  
butoxide (BEMB from Texas Alkyls Inc). The resulting  
slurry was stirred for 1 hour after which 0.20 mmol of  
titanium tetrachloride (TiCl<sub>4</sub>) was added. The slurry  
10 rapidly darkens to a deep brown color and was stirred  
for a further two hours. An aliquot of a solution  
containing an alkylaluminum chloride (3.5 mmol Al) was  
then added and the final mixture stirred for 17 hours.  
The complete mixtures prepared in this manner were used  
15 without further isolation or washing.

The catalysts were activated with  
triisobutylaluminum at a ratio of Al/Ti of 100/1  
employing the procedure of Example 1B.

20

**B. Polymerization**

The polymerizations were conducted under slurry  
conditions using a hydrogen to ethylene ratio of 1:1, a  
25 reactor temperature of 85°C and a polymerization time of  
one hour. The results of the polymerization reactions  
are shown in Table IV.

30

Table IV. Effect of different Alkylaluminum Halides

Run No.	Aluminum Source	Atomic Ratios			Efficiency (Kg PE per gram of Ti or Cl)		I <sub>20</sub> /I <sub>2</sub>	
		Catalyst		Cocat. Al/Ti	Ti	Cl		
		Mg/Al/Cl/Ti	Si/Mg					
A	EtAlCl <sub>2</sub> <sup>a</sup>	10/17.5/39/1	8.3	100/1	1,150	40	0.71	24.7
B	Et <sub>3</sub> Al <sub>2</sub> Cl <sub>3</sub> <sup>b</sup>	10/17.5/30.3/1	8.3	100/1	986	44	0.80	31.8
C	iBuAlCl <sub>2</sub> <sup>c</sup>	10/17.5/39/1	8.3	100/1	1,010	38	0.69	30.0

<sup>a</sup> Ethylaluminum dichloride.

<sup>b</sup> Ethylaluminum sesquichloride.

<sup>c</sup> Isobutylaluminum dichloride.

## EXAMPLE 5

A. Preparation of Transition Metal Catalyst Component

To 1 g of Silica Support #7 slurried in 50 ml  
5 of ISOPAR™ E was added 2.0 mmol of butylethylmagnesium  
butoxide (BEMB from Texas Alkyls Inc). The resulting  
slurry was stirred for one hour after which an amount of  
titanium tetraisopropoxide was added. The slurry was  
10 stirred for a further two hours. An aliquot of a  
solution of 25percent ethylaluminum dichloride in hexane  
was then added and and the final mixture was stirred for  
17 hours. The complete mixtures prepared in this manner  
were used without further isolation or washing.

15

The catalysts were activated with  
triisobutylaluminum at the ratio given in Table V.

B. Polymerization (Slurry Conditions)

20

The polymerization was conducted under slurry  
polymerization conditions employing a temperature of  
85°C, a hydrogen to ethylene ratio of 1:1 and a  
polymerization time of one hour.

25

The results are shown in Table V.

30

Table V. Effect of Varying Amount of Titanium and Cocatalyst

Run No.	Atomic Ratios			Efficiency (Kg PE per gram of Ti or Cl)	
	Catalyst		Cocat. Al/Ti	Ti	Cl
	Mg/Al/Cl/Ti	Si/Mg			
A	6.7/15/30/1	8.3/1	25/1	1,150	52
B	6.7/11.7/23.3/1	8.3/1	100/1	1,100	64
C	10/35/70/1	8.3/1	100/1	2,140	41

## EXAMPLE 6

A. Preparation of Transition Metal Catalyst Component

To 1 g of Silica Support #7 slurried in 50 ml of ISOPAR™ E was added 2.0 mmol of butylethylmagnesium butoxide (BEMB from Texas Alkyls Inc). The resulting slurry was stirred for 1 hour after 0.20 mmol of titanium tetraisopropoxide ( $\text{Ti}(\text{O}-i\text{C}_3\text{H}_7)_4$ ) was added. The slurry was stirred for a further two hours. An aliquot of a solution of 25percent ethylaluminum dichloride (4.5 mmol) was then added and the final mixture stirred for 17 hours. The complete mixtures prepared in this manner were used without further isolation or washing. The atomic ratio for the catalysts are given in Table VI.

The catalysts were activated with triisobutylaluminum at an Al/Ti ratio of 200:1.

E. Polymerization (Slurry Conditions)

The polymerization was conducted under slurry  
polymerization conditions employing a temperature of  
85°C, a hydrogen to ethylene ratio of as indicated in  
the Table, a pressure of 170 psi (1,172 kPa), and a  
5 polymerization time of one hour. Various solvents were  
employed as the polymerization medium. The results are  
given in Table VI.

10

15

20

25

30

Table VI. Use of Different Solvents as a Polymerization Medium and different Hydrogen to Ethylene Ratios.

Run No.	Solvent	Atomic Ratios			Partial Pressure Ratio of H <sub>2</sub> to C <sub>2</sub> H <sub>4</sub>	I <sub>2</sub>	I <sub>20</sub> /I <sub>2</sub>	Efficiency (Kg Polymer per gram of Ti or Cl)	
		Catalyst		Cocat.				Ti	Cl
		Mg/Al/Cl/Ti	Si/Mg	Al/Ti					
A	n-C <sub>6</sub> H <sub>14</sub>	10/22.5/45/1	8.3/1	200/1	0.36	0.19	39.5	1,020	31
B	i-C <sub>5</sub> H <sub>12</sub>	10/22.5/45/1	8.3/1	200/1	3.0	0.67	38.5	750	22

**EXAMPLE 7****A. Preparation of Transition Metal Catalyst  
Component Containing Vanadium**

To 1 g of Silica Support #7 slurried in 50 ml  
of ISOPAR™ E was added 2.0 mmol of butylethylmagnesium  
butoxide (BEMB from Texas Alkyls Inc). The resulting  
slurry was stirred for one hour after which 0.40 mmol of  
titanium tetrachloride (TiCl<sub>4</sub>) was added. The slurry  
rapidly darkens to a deep brown color and was stirred  
for a further two hours. An aliquot of a solution of  
ethylaluminum dichloride (3.5 mmol Al) was then added  
and the final mixture stirred for 17 hours. The mixture  
was treated with 0.40 mmol of vanadium trichloride oxide  
(VOCl<sub>3</sub>) and then stirred for 4 hours. The Mg/Al/Cl/V/Ti  
atomic ratios of the catalyst was 5/8.8/20.3/1/1. The  
Si/Mg atomic ratio of the catalyst was 8.3/1.

The catalyst was activated with  
triisobutylaluminum at an Al/Ti atomic ratio of 100:1.

**B. Polymerization (Slurry Conditions)**

The slurry polymerization conditions were  
employed. The polymerization temperature was 85°C, the  
hydrogen to ethylene ratio was 2:1, and the  
polymerization time was one hour.

The polymerization efficiency based on titanium  
was found to be 952 Kg PE/g Ti and the polymerization  
efficiency based on chloride was 52 Kg PE/g Cl and the  
polymerization efficiency based on titanium plus  
vanadium was 476 Kg PE/g Ti+V.



## EXAMPLE 8

A. Preparation of Transition Metal Catalyst  
Component Containing Vanadium

To 1 g of Silica Support #7 slurried in 50 ml  
5 of ISOPAR™ E was added 2.0 mmol of butylethylmagnesium  
butoxide (BEMB from Texas Alkyls Inc.). The resulting  
slurry was stirred for one hour after which 1.80 mmol of  
titanium tetrachloride ( $\text{TiCl}_4$ ) was added. The slurry  
10 rapidly darkened to a deep brown color and was stirred  
for a further two hours. An aliquot of a solution of  
ethylaluminum dichloride (3.5 mmol Al) was then added  
and and the final mixture stirred for 17 hours. The  
mixture was treated with 0.40 mmol of vanadium  
15 trichloride oxide ( $\text{VOCl}_3$ ) and then stirred for 4 hours.  
The Mg/Al/Cl/V/Ti atomic ratios of the catalyst was  
1.1/1.9/12.3/0.2/1. The Si/Mg atomic ratio of the  
catalyst was 8.3/1.

20 The catalyst was activated with  
triisobutylaluminum at an atomic ratio of Al/Ti of  
100/1.

B. Polymerization (Slurry Conditions)

25 The slurry polymerization procedure was  
employed using a hydrogen to ethylene mole ratio of 1 to  
1, a polymerization temperature of 85°C, and a  
polymerization time of one hour.

30 The efficiency of the catalyst based on  
titanium was 571 Kg PE/g Ti/hour and the efficiency  
based on chloride was 90 Kg PE/g Cl and the efficiency  
based on titanium plus vanadium was 285 Kg/ g of  
Ti+V/hour.

**EXAMPLE 9****A. Preparation of Transition Metal Catalyst  
Component Containing Vanadium**

5 To 1 g of Silica Support #7 slurried in 50 ml  
of ISOPAR™ E was added 2.0 mmol of butylethylmagnesium  
butoxide (BEMB from Texas Alkyls Inc). The resulting  
slurry was stirred for 1 hour after which 1.00 mmol of  
10 titanium tetrachloride (TiCl<sub>4</sub>) was added. An aliquot of  
a solution of ethylaluminum dichloride (6.0 mmol Al) was  
then added and and the final mixture stirred for 17  
hours. The mixture was treated with 1.00 mmol of  
vanadium trichloride oxide (VOCl<sub>3</sub>) and then stirred for  
15 4 hours. The complete mixtures prepared in this manner  
were used without further isolation or washing. The  
Mg/Al/Cl/V/Ti atomic ratios of the catalyst was  
2/6/19/1/1. The Si/Mg atomic ratio of the catalyst was  
8.3/1.

20

The catalysts were activated with the  
cocatalyst designated in Table VII.

**B. Polymerization (Slurry Conditions)**

25

The slurry polymerization procedure was  
employed at a temperature of 85°C. a hydrogen to  
ethylene ratio of 1:1, and a polymerization time of one  
hour.

30

The catalyst efficiency and properties of the  
resulting polymer are shown in Table VII.

Table VII. Use of Varying Amounts of Vanadium

Run No.	Cat. No.	Bu <sub>3</sub> Al TO Ti Ratio	Efficiency (Kg PE per gram of Ti or Cl)			I <sub>2</sub>	I <sub>20</sub> /I <sub>2</sub>
			Ti	Cl	Ti+V		
A	9A	100	433	31	216	0.12	60.0
B	9B	200	433	31	216	0.12	60.3
C	9C	50	325	23	163	0.09	57.8

This example 9 shows that high I<sub>20</sub>/I<sub>2</sub> ratios can be achieved with the vanadium containing catalysts in slurry polymerizations. These high I<sub>20</sub>/I<sub>2</sub> ratios were indicative of a broad molecular weight distribution.

#### EXAMPLE 10

##### A. Preparation of Transition Metal Catalyst Component

To 1 g of Silica Support #7 slurried in 50 ml of ISOPAR™ E was added 2.0 mmol of butylethylmagnesium butoxide (BEMB from Texas Alkyls Inc). The resulting slurry was stirred for one hour after which titanium tetraisopropoxide was added in the indicated quantities. The slurry was stirred for a further two hours. An aliquot of a solution of 25percent ethylaluminum dichloride in hexane was then added and the final mixture stirred for 17 hours. The atomic ratios of Mg/Al/Cl/Ti for these catalysts were as follows:

Run A= 7.5/15/30/1

Run B= 3.8/8.8/17.5/1

The atomic ratios of Si/Mg for these catalysts were as follows:

Run A= 8.3/1

Run B= 8.3/1.

The catalysts prepared in this manner were used without further isolation or washing.

5 The catalysts were activated with triethylaluminum at atomic ratios of Al/Ti of 8/1 and 6/1.

B. Polymerization (Solution Conditions)

10 The catalysts were used to polymerize ethylene using the solution polymerization procedure employing a polymerization temperature of 185°C, and a polymerization time of one hour.

15 The results are given in Table VIII.

Table VIII

Run No.	Catalyst (millimoles)		Cocat. Atomic Ratio Al/Ti	Efficiency (Kg PE per g Ti or Cl)	
	Ti	Al		Ti	Cl
A	0.20	3.0	8	773	35
B	0.40	3.5	6	641	50

25

**EXAMPLE 11**

A. Preparation of Catalyst

30 To 1 g of Silica Support #7 slurried in 50 ml of ISOPAR™ E was added the required amount of butylethylmagnesium butoxide (BEMB from Texas Alkyls Inc). The resulting slurry was stirred for one hour after which titanium tetrachloride (TiCl<sub>4</sub>) was added. An aliquot of a solution of ethylaluminum dichloride (EADC) was then added and the slurry stirred for 17

hours. The mixture was treated with vanadium tetrachloride ( $\text{VCl}_4$ ) and then stirred for 4 hours. The complete mixtures prepared in this manner were used without further isolation or washing. The composition of these catalysts are given in Table IX. The atomic ratios are given in Table IX.

#### B. Activation and Polymerization

After activating the catalysts prepared above with triethylaluminum in the indicated amounts, polymerizations were conducted under solution polymerization conditions at a polymerization temperature of  $185^\circ\text{C}$  and a polymerization time of ten minutes.

The results are given in Table IX.

Table IX

Run No.	mmol BEMB	mmol TiCl <sub>4</sub>	mmol VC14	mmol EADC	Atomic Ratios			Density g/cm <sup>3</sup>	I <sub>2</sub>	Catalyst Efficiency Kg PE/g Ti or Cl	
					Catalyst		Cocat Al/Ti			Ti	Cl
					Mg/Al/Cl/V/Ti	Si/Mg					
A	1.2	0.2	0.2	1.5	6/7.5/23/1/1	14/1	9.4	0.9334	3.45	552	32
B	1.2	0.6	0.2	1.5	2/2.5/10/0.33/1	14/1	6.2	0.9314	3.74	593	77
C	1.5	0.4	0.4	2.5	3.8/6.3/20.5/1/1	17/1	4.7	0.9250	1.24	1,096	72
D	1.8	0.6	0.6	3.5	3/6/20/1/1	21/1	6.7	0.9241	1.81	1,021	70
E	1.2	0.6	0.6	3.5	2/6/20/1/1	14/1	8.3	0.9228	1.16	958	66
F	1.2	1.0	1.0	3.5	1.2/3.5/15/1/1	14/1	8.3	0.9285	1.21	1,157	104
G	1.2	1.2	1.2	3.5	1/3/14/1/1	14/1	8.3	0.9232	1.84	807	79
H	1.2	0.6	0.2	3.5	2/7/19/0.3/1	14/1	8.3	0.9226	1.47	1,002	80

## EXAMPLE 12

A. Preparation of Transition Metal Catalyst  
Component

To 1 g of Silica Support #7 slurried in 50 ml  
5 of ISOPAR™ E was added 1.2 mmol of butylethylmagnesium  
butoxide (BEMB from Texas Alkyls Inc). The resulting  
slurry was stirred for one hour after which 0.60 mmol of  
titanium tetrachloride (TiCl<sub>4</sub>) was added. The slurry  
10 rapidly darkens to a deep brown color and was stirred  
for a further two hours. An aliquot of a solution of  
ethylaluminum dichloride (3.5 mmol Al) was then added  
and the final mixture was stirred for 17 hours. The  
mixture was treated with 0.60 mmol of vanadium  
15 trichloride oxide (VOCl<sub>3</sub>) and then stirred for 4 hours.

The catalyst had the following ratios:

Mg/Al/Cl/V/Ti of 2/5.8/18/1/1

Si/Mg of 13.9/1

20 B. Activation and Polymerization Under Solution  
Conditions

After activating the catalyst with  
triethylaluminum (Al/Ti = 5/1) the polymerization was  
25 conducted using the solution polymerization procedure.

The polymer product had a density of 0.9239  
g/cm<sup>3</sup> and an I<sub>2</sub> value of 2.36 and was produced at an  
efficiency of 790 Kg PE/g Ti and 57 Kg PE/g Cl.  
30

EXAMPLE 13A. Preparation of Transition Metal Catalyst  
Component

To 1 gram of Silica Support #7 in ISOPAR™ E was  
5 added 1.2 mmol of butylethylmagnesium butoxide. After  
stirring the mixture for two hours, 3.5 mmol of  
ethylaluminum dichloride was added and the mixture was  
stirred for 17 hours. To this mixture was then added a  
10 1:1 molar mixture of  $TiCl_4$  and  $VOCl_3$  (.6 mmol Ti/.6 mmol  
V). This mixture was stirred for 8 hours.

The catalyst had the following ratios:

Mg/Al/Cl/V/Ti of 2/5.8/18/1/1; and

15 Si/Mg of 13.9/1.

B. Activation of Catalyst and Polymerization Under  
Solution Conditions

After activating the catalyst with  
20 triethylaluminum (Al/Ti = 5/1), the polymerization was  
conducted using the solution polymerization procedure.

The polymer product had an efficiency of 742 Kg  
25 PE/g Ti and 54 Kg PE/g Cl.

EXAMPLE 14

30

A. Preparation of Transition Metal Catalyst  
Component

To 1 g of Silica Support Sample #7 slurried in  
ISOPAR™E was added 2.0 mmol of butylethylmagnesium  
butoxide, 1.8 mmol titanium tetrachloride and 1.8 mmole



of vanadium trichloride oxide and the mixture was stirred for 4 hours. The mixture was then treated with 6.5 mmol of ethylaluminum dichloride and the slurry stirred for 24 hours. The atomic ratios of Mg/Al/Cl/Ti/V for this catalyst were 1.1/3.6/13/1/1.

#### B. Activation of Catalyst and Polymerization

An aliquot of the catalyst was diluted and activated according to Example 1B using a triethylaluminum to titanium ratio of 8.5:1. The polymerization was carried out according to the procedure for solution process polymerizations at the temperatures shown in Table X.

Table X

Run No.	Run Temp. °C	Density g/cc	I <sub>2</sub>	Efficiency (Kg PE per gram of Ti or Cl)	
				Ti	Cl
A	185	0.9251	0.81	945	98
B	215	0.9259	0.71	319	33

#### EXAMPLE 15

##### A. Preparation of Transition Metal Catalyst Component

To 1 g of Silica Support #7 slurried in Isopar™E was added 2.0 mmol of magnesium bis(2,6-dimethylcyclohexoxide), 0.2 mmol titanium tetrachloride and the mixture was stirred for 1 hour. The mixture was then treated with 5.5 mmol of ethylaluminum dichloride

and the slurry stirred for 24 hours. The atomic ratio of Mg/Al/Cl/Ti for this catalyst was 10/27.5/59/1.

B. Activation of Catalyst and Polymerization

5           An aliquot of the catalyst was diluted and  
activated according to Example 1B using a  
triethylaluminum to titanium ratio of 12:1. The  
polymerization was carried out according to the  
10 procedure for solution process polymerizations at 185°C.  
The polymer product had a density of 0.9332 g/cm<sup>3</sup> and an  
I<sub>2</sub> value of 2.42 g/10 min, an I<sub>10</sub>/I<sub>2</sub> ratio of 8.00 and  
was produced at an efficiency of 149 Kg PE/g Ti and 3.4  
Kg PE/g Cl.

15

20

25

30

5

10                   1. A supported transition metal catalyst  
component which comprises an inert liquid medium having  
slurried therein a composition comprising the product  
resulting from contacting (1) a porous solid inorganic  
oxide support material selected from the group  
15 consisting of silica, alumina, or a combination of  
silica and alumina; (2) a hydrocarbon soluble  
organomagnesium alkoxide or hydrocarbon soluble  
organomagnesium dialkoxide; (3) a titanium compound;  
optionally (4) a vanadium compound; and (5) a Group IIIA  
20 metal alkyl halide;

c h a r a c t e r i z e d i n t h a t

- (i) the composition is employed without washing and solids removal;
- 25 (ii) said support material contains not greater than 5 millimoles of hydroxyl groups per gram of support material and a particle size not greater than 10 microns and a surface area of from 50 to 800 m<sup>2</sup>/g;
- 30 (iii) .the atomic ratio of Si+Al(from the inorganic oxide support): is from 1:1 to 50:1;
- (iv) the atomic ratio of Mg:IIIA metal is from 0.01:1 to 100:1
- (v) the atomic ratio of Mg:Ti is from 0.05:1 to 40:1;

- (vi) the atomic ratio of Mg:V, when present, is from about 0.1:1 to 40:1; and
- (vii) the atomic ratio of V:Ti is from 0:1 to 10:1.

2. A catalyst of Claim 1 wherein

- 5 (a) said solid support material is silica;
- (b) said organomagnesium alkoxide or dialkoxide is a compound represented by the formulas  $R_xMg(OR)_y$ :  
wherein each R is independently a hydrocarbyl group  
having from 1 to 20 carbon atoms,  $x+y=2$ ,  $0.5 \leq y \leq 2$ ;
- 10 (c) said titanium compound is a compound represented by the formula  $TiX_{4-a}(OR')_a$  wherein each R' is independently an alkyl group having from 1 to 20 carbon atoms, X is a halogen atom, and a has a value from zero to 4;
- 15 (d) said vanadium compound, when present, is a compound represented by the formulas  $VX_4$  or wherein each R' is independently an alkyl group having from 1 to 20 carbon atoms, X is a halogen atom, and a has a value from zero to 4; and
- 20 (e) said Group IIIA metal alkyl halide is a compound represented by the formula  $R'_yMX_z$  wherein M is a metal from Group IIIA of the Periodic Table of the Elements, each R' is independently an alkyl group having from 1 to 20 carbon atoms; X is a halogen atom, y and z each independently have a value from 1 to a value equal to the valence of M minus 1 and  $y+z$  has a value equal to the valence of M.

30

3. A catalyst of Claim 1 wherein

- (a) said solid support material is silica;
- (b) said magnesium compound is ethylmagnesium ethoxide, butylmagnesium ethoxide, octylmagnesium ethoxide, butylmagnesium butoxide, ethylmagnesium butoxide,

butylmagnesium octoxide, s-butylmagnesium octoxide or any combination of such compounds;

- (c) said titanium compound is titanium tetrachloride, titanium tetraisopropoxide, or any combination of such compounds;
- 5 (d) said vanadium compound, when present, is vanadium tetrachloride, vanadium oxytrichloride, or any combination of such compounds; and
- (e) said Group IIIA metal alkyl halide is ethylaluminum dichloride, i-butylaluminum dichloride,
- 10 ethylaluminum sesquichloride or any combination thereof.

4. A process for preparing a supported  
15 transition metal catalyst component slurried in an inert liquid medium,

c h a r a c h t e r i z e d b y

- (A) forming in an inert atmosphere which excludes oxygen  
20 and moisture a slurry of (1) a porous inorganic oxide support material selected from the group consisting of silica, alumina, or a combination of silica and alumina, said support material containing  
25 not greater than 5 millimoles of hydroxyl groups per gram of support material and a particle size not greater than 10 microns and a surface area of from 50 to 800 m<sup>2</sup>/g in an inert organic liquid medium;
- (B) mixing said slurry with (2) a hydrocarbon soluble organomagnesium alkoxide or hydrocarbon soluble  
30 organomagnesium dialkoxide and stirring the resultant mixture at a temperature of from -20°C to 120°C;
- (C) mixing the product from (B) with (3) a titanium compound or a combination of a titanium compound and

- (4) a vanadium compound or adding the titanium compound and the vanadium compound separately and stirring the resultant mixture at a temperature of from  $-20^{\circ}\text{C}$  to  $120^{\circ}\text{C}$  for a time sufficient to allow complete reaction of the titanium compound and the vanadium compound with the organomagnesium moieties remaining on the solid support;
- 5
- (D) mixing the product from (C) with an inert organic solution of (5) a Group IIIA metal alkyl halide at a temperature of from  $-20^{\circ}\text{C}$  to  $120^{\circ}\text{C}$  for a time sufficient to complete the reduction of the titanium and vanadium, if present, compounds to their final oxidation state.
- 10

- 15                   5. A process of Claim 4 wherein
- (a) said solid support material is silica;
- (b) said organomagnesiumalkoxide or organo magnesium dialkoxide is a compound represented by the formulas  $\text{R}_x\text{Mg}(\text{OR})_y$ ; wherein each R is independently a hydrocarbyl group having from 1 to 20 carbon atoms,  $x+y=2$ , and  $0.5 \leq y \leq 2$ ;
- 20
- (c) said titanium compound is a compound represented by the formula  $\text{TiX}_{4-a}(\text{OR}')_a$  wherein each R' is independently an alkyl group having from 1 to 20 carbon atoms. X is a halogen atom, and a has a value from zero to 4;
- 25
- (d) said vanadium compound, when present, is a compound represented by the formula  $\text{VX}_{4-a}(\text{OR})_a$  wherein each R' is independently an alkyl group having from 1 to 20 carbon atoms, X is a halogen atom, and a has a value from zero to 4; and
- 30
- (e) said Group IIIA metal alkyl halide is a compound represented by the formula  $\text{R}'_y\text{MX}_2$  wherein M is a metal from Group IIIA of the Periodic Table of the

Elements, each R' is independently an alkyl group having from 1 to 20 carbon atoms; X is a halogen atom, y and z each independently have a value from 1 to a value equal to the valence of M minus 1 and y+z has a value equal to the valence of M.

5

6. A process of Claim 5 wherein

- (a) said magnesium compound is ethylmagnesium ethoxide, butylmagnesium ethoxide, octylmagnesium ethoxide, butylmagnesium butoxide, ethylmagnesium butoxide, butylmagnesium octoxide, s-butylmagnesium octoxide or any combination of such compounds;
- (b) said titanium compound is titanium tetrachloride, titanium tetraisopropoxide, or any combination of such compounds;
- (c) said vanadium compound, when present is vanadium tetrachloride, vanadium oxytrichloride, or any combination of such compounds; and
- (d) said Group IIIA metal alkyl halide is ethylaluminum dichloride, i-butylaluminum dichloride, ethylaluminum sesquichloride or any combination of such compounds.

10

15

20

25

30


7. A process for polymerizing one or more  $\alpha$ -olefins and optionally one or more polymerizable ethylenically unsaturated compounds other than an  $\alpha$ -olefin by subjecting said olefins and/or compounds to polymerization conditions in the presence of a catalyst,

characterized by

employing as the catalyst, any of the catalysts of the Claims 1-3 or any one of the catalysts prepared by the process of Claims 4-6.

# INTERNATIONAL SEARCH REPORT

International Application No PCT/US 91/09589

<b>I. CLASSIFICATION OF SUBJECT MATTER</b> (if several classification symbols apply, indicate all) <sup>6</sup>		
According to International Patent Classification (IPC) or to both National Classification and IPC		
IPC5: C 08 F 4/64, 10/00		
<b>II. FIELDS SEARCHED</b>		
Minimum Documentation Searched <sup>7</sup>		
Classification System	Classification Symbols	
IPC5	C 08 F	
Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in Fields Searched <sup>8</sup>		
<b>III. DOCUMENTS CONSIDERED TO BE RELEVANT<sup>9</sup></b>		
Category *	Citation of Document, <sup>11</sup> with indication, where appropriate, of the relevant passages <sup>12</sup>	Relevant to Claim No. <sup>13</sup>
Y	US, A, 4672096 (NOWLIN) 9 June 1987, see claims 1,9,12,19,24,29 and abstract  --	1,2,4,5, 7
Y	GB, A, 2053939 (THE BRITISH PETROLEUM COMPANY LIMITED) 11 February 1981, see claims 1,4,7,10,11  --	1,2,4,5, 7
A	US, A, 4849390 (SANO ET AL) 18 July 1989, see column 2 - column 5, line 51; claim 1  --  -----	1-7
<p>* Special categories of cited documents:<sup>10</sup></p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance, the claimed invention cannot be considered novel or cannot be considered to involve an inventive step</p> <p>"Y" document of particular relevance, the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"&amp;" document member of the same patent family</p>		
<b>IV. CERTIFICATION</b>		
Date of the Actual Completion of the International Search	Date of Mailing of this International Search Report	
5th May 1992	10. Oct. 92	
International Searching Authority	Signature of Authorized Officer	
EUROPEAN PATENT OFFICE		Els Vonk



ANNEX TO THE INTERNATIONAL SEARCH REPORT  
ON INTERNATIONAL PATENT APPLICATION NO. PCT/US 91/09589

SA 56459

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report.  
The members are as contained in the European Patent Office EDP file on 28/03/92  
The European Patent office is in no way liable for these particulars which are merely given for the purpose of information.

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A- 4672096	09/06/87	AU-B- 582569	06/04/89
		AU-D- 4047785	10/10/85
		CA-A- 1236820	17/05/88
		EP-A- 0159839	30/10/85
		JP-A- 61000204	06/01/86
		US-A- 4593009	03/06/86
		-----	-----
GB-A- 2053939	11/02/81	NONE	
US-A- 4849390	18/07/89	EP-A-B- 0243190	28/10/87
		JP-A- 63061008	17/03/88

For more details about this annex : see Official Journal of the European patent Office, No. 12/82