



- (51) **International Patent Classification:**
B01J 23/10 (2006.01) *C07C 43/275* (2006.01)
C07C 41/09 (2006.01)
- (21) **International Application Number:** PCT/US2013/055963
- (22) **International Filing Date:** 21 August 2013 (21.08.2013)
- (25) **Filing Language:** English
- (26) **Publication Language:** English
- (30) **Priority Data:** 61/694,833 30 August 2012 (30.08.2012) US
- (71) **Applicant:** DOW GLOBAL TECHNOLOGIES LLC [US/US]; 2040 Dow Center, Midland, MI 48674 (US).
- (72) **Inventors:** BARTON, David G.; 3408 Greenbrier Terrace, Midland, MI 48642 (US). CHOJECKI, Adam; Poelsnepstraat 7 Bus 202, B-9000 Gent (BE). ELOWE, Paul R.; 5417 OakRidge Drive, Midland, MI 48640 (US). KILOS, Beata A.; 3210 Valley Drive, Midland, MI 48640 (US).
- (74) **Agent:** SHALTOUT, Raef; The Dow Chemical Company, Intellectual Property, P.O. Box 1967, Midland, Michigan 48641-1967 (US).
- (81) **Designated States** (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.
- (84) **Designated States** (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).
- Published:**
— *with international search report (Art. 21(3))*



WO 2014/035759 A1

(54) **Title:** CATALYSTS AND METHODS FOR ALCOHOL DEHYDRATION

(57) **Abstract:** Provided is a process for preparing a diaryl ether compound through the dehydration of an aromatic alcohol compound in the presence of a dehydration catalyst. The dehydration catalyst is an oxide of a medium rare earth element, wherein the medium rare earth element is samarium, europium, gadolinium, or mixtures thereof.

CATALYSTS AND METHODS FOR ALCOHOL DEHYDRATION

Cross-Reference to Related Applications

This application claims priority from provisional application serial number 61/694,833, filed August 30, 2012, which is incorporated herein by reference in its entirety.

Background

This invention relates generally to catalysts and methods for the dehydration of aromatic alcohol compounds to ethers. More particularly, the invention uses a dehydration catalyst comprising an oxide of a medium rare earth element for the dehydration of aromatic alcohol compounds to diaryl ethers.

Diaryl ethers are an important class of industrial materials. Diphenyl oxide (DPO), for instance, has many uses, most notably as the major component of the eutectic mixture of DPO and biphenyl, which is the standard heat transfer fluid for the concentrating solar power (CSP) industry. With the current boom in CSP has come a tightening of the supply of DPO globally and questions surrounding the sustainability of the technology have arisen.

Diaryl ethers are currently manufactured commercially via two major routes: reaction of a haloaryl compound with an aryl alcohol; or gas-phase dehydration of an aryl alcohol. The first route, for example where chlorobenzene reacts with phenol in the presence of caustic and a copper catalyst, typically leads to less pure product and requires high pressure (5000 psig), uses an expensive alloy reactor and produces stoichiometric quantities of sodium chloride.

The second route, which is a more desirable approach, accounts for the largest volume of diaryl ethers produced but requires a very active and selective catalytic material. For instance, DPO can be manufactured by the gas-phase dehydration of phenol over a thorium oxide (thoria) catalyst (e.g., U.S. Patent 5,925,798). A major drawback of thoria however is its radioactive nature, which makes its handling difficult and potentially costly. Furthermore, the supply of thoria globally has been largely unavailable in recent years putting at risk existing DPO manufacturers utilizing this technology. Additionally, other catalysts for the gas-phase dehydration of phenol, such as zeolite catalysts, titanium oxide, zirconium oxide and tungsten oxide, generally suffer from lower activity, significantly higher impurity content and fast catalyst deactivation.

With a chronic shortage of diaryl ethers such as DPO in sight and a pressing need to increase capacity, it has become crucial to develop alternate methods to produce such materials in a cost-effective and sustainable manner.

The problem addressed by this invention, therefore, is the provision of new catalysts and methods for manufacture of diaryl ethers from aryl alcohol compounds.

Statement of Invention

We have now found that a catalyst comprising an oxide of a medium rare earth element is effective for the preparation of diaryl ethers from aromatic alcohol compounds. Advantageously, the catalyst exhibits remarkable selectivity for the desired product. Moreover, the catalyst is non-radioactive. This invention, therefore, represents a unique solution for diaryl ether supply issues globally.

In one aspect, there is provided a method for preparing a diaryl ether, the method comprising dehydrating an aromatic alcohol compound over a dehydration catalyst, wherein the dehydration catalyst is an oxide of a medium rare earth element.

In another aspect, there is provided a method for producing a heat transfer fluid, the method comprising: preparing a diaryl ether by contacting an aromatic alcohol compound with a dehydration catalyst, wherein the dehydration catalyst is an oxide of a medium rare earth element; isolating the diaryl ether from the dehydration catalyst; and mixing the isolated diaryl ether with biphenyl such that the mixture forms a eutectic mixture.

Detailed Description

Unless otherwise indicated, numeric ranges, for instance as in "from 2 to 10," are inclusive of the numbers defining the range (e.g., 2 and 10).

Unless otherwise indicated, ratios, percentages, parts, and the like are by weight.

As noted above, in one aspect the invention provides a method for producing a diaryl ether by dehydrating an aromatic alcohol compound over an oxide of a medium rare earth element. It has been discovered that such catalysts exhibit high selectivity for the desired diaryl ether compounds with relatively low formation of undesirable byproducts. For instance, as demonstrated by the examples, in the synthesis of diphenyl oxide from phenol, a selectivity for the DPO of 50% or greater may be achieved. In some embodiments, a selectivity of 80 % or greater may be achieved. In some embodiments, a selectivity of 90 % or greater, or 95 % or greater is possible.

In addition to being highly selective, the catalysts are also advantageous because they are non-radioactive, thus eliminating the safety and environmental issues, as well as higher costs, associated with the handling of radioactive materials, such as the thorium catalysts of the prior art.

The dehydration catalyst of the invention comprises an oxide of a medium rare earth element. By a "medium rare earth element" is meant samarium, europium, gadolinium, or mixtures thereof. By "oxide of medium rare earth element" is meant a compound that contains at least one oxygen-medium rare earth element bond. Examples include Sm_2O_3 , Eu_2O_3 , and Gd_2O_3 .

In some embodiments, the catalyst is an oxide of samarium. In some embodiments, the catalyst is an oxide of europium. In some embodiments, the catalyst is an oxide of gadolinium. Mixtures of oxides, such as mixtures of oxides of one medium rare earth element, or mixtures of oxides of two or more different medium rare earth elements, are also encompassed by the invention.

The catalyst may optionally contain other atoms, such as halogens, including chloride or fluoride. In some embodiments, a preferred catalyst for use in the invention contains a medium rare earth element, oxygen, and chlorine atoms. In some embodiments, the catalyst comprises, in addition to the medium rare earth element and oxygen, chlorine in an amount of less than 42 weight percent, alternatively 30 weight percent or less, alternatively 17 weight percent or less, alternatively 10 weight percent or less, or alternatively 2 weight percent or less. In some embodiments, the catalyst comprises the chlorine in an amount of at least 0.001 weight percent, alternatively at least 0.1 weight percent, alternatively at least 1 weight percent, or alternatively at least 2 weight percent. In some embodiments, the catalyst contains between 1 and 17 weight percent chlorine. The chlorine may be in the form of chloride ion (Cl^-). Non limiting examples of suitable compounds may include samarium oxychloride, europium oxychloride, gadolinium oxychloride, or an oxide of the medium rare earth element also containing a chloride (e.g., from NH_4Cl , HCl , etc., or from chloride containing medium rare earth element precursors). By "oxychloride" is meant a compound that contains metal-oxygen and metal-chlorine bonds. Examples further include, again without limitation, medium rare earth element oxide catalysts based on chlorate oxyanions, such as hypochlorite (ClO^-); chlorite (ClO_2^-); chlorate (ClO_3^-), perchlorate (ClO_4^-) where Cl is oxidized (+2, +3, +4, +5), as well as amorphous materials.

Catalysts suitable for use in the invention may be prepared by those skilled in the art or they may be purchased from commercial vendors.

The catalyst may optionally contain a binder and/or matrix material that is different from the active oxide of the medium rare earth element. Non-limiting examples of binders that are useful alone or in combination include various types of hydrated alumina, silicas and/or other inorganic oxide sols, and carbon. Upon heating, the inorganic oxide sol, preferably having a low viscosity, is converted into an inorganic oxide binder component.

Where the catalyst composition contains a matrix material, this is preferably different from the active catalyst and any binder. Non-limiting examples of matrix materials include clays or clay-type compositions.

The catalyst, including any binder or matrix materials, may be unsupported or supported. Non-limiting examples of suitable support materials include titania, alumina, zirconia, silica, carbons, zeolites, magnesium oxide, and mixtures thereof. Where the catalyst contains a binder, matrix or support material, the amount of oxide of medium rare earth element (the active component of the catalyst) may be between 1 and 99 percent by weight based on the total weight of the catalyst (including the oxide, and any support, binder or matrix materials).

The catalyst may be formed into various shapes and sizes for ease of handling. For instance, the catalyst (plus any binder, matrix, or support) may be in the form of pellets, spheres, or other shapes commonly used in the industry.

Aromatic alcohol compounds suitable for use in the process of this invention include aromatic compounds containing at least one alcohol group and one, two, three or more aromatic moieties. Suitable compounds include phenols and α - and β -hydroxy-substituted fused aromatic ring systems. Apart from the hydroxy substituent, the compounds may be unsubstituted, as in phenol or naphthol. Optionally, however, the compounds may be further substituted with at least one alkyl group containing from 1 to about 10 carbon atoms, preferably, from 1 to 3 carbon atoms, or substituted with at least one alternative substituent which is inert to the dehydration coupling reaction. Suitable inert substituents include cyano, amino, nitro, carboxylic acid (e.g., C₀-C₆-COOH), ester, C₆-C₁₂ aryl, C₂-C₆ alkenyl, alkyloxy, aryloxy, and phenoxy moieties. It is also possible for the aromatic alcohol compound to be substituted with both an alkyl substituent and one of the alternative inert substituents. Each of the aforementioned alkyl substituents and/or alternative inert substituents is attached preferably to an aromatic ring carbon atom which is located in an

ortho, meta or para position relative to the hydroxy moiety. Optionally, the alkyl substituent may contain from 3 to 4 carbon atoms, and in combination with a phenol or fused aromatic ring system may form a saturated ring fused to the aromatic ring. An acceptable feed may contain a mixture of aromatic alcohols, including mixtures of the foregoing.

Non-limiting examples of suitable phenols include unsubstituted phenol, m-cresol, p-cresol, 3,4-xyleneol, 3,5-xyleneol, and 3,4,5-trimethylphenol. Other suitable phenols include compounds corresponding to the above-mentioned examples except that one or more of the methyl substituents are replaced by an ethyl, propyl or butyl substituent. Non-limiting examples of α - and β -hydroxy-substituted fused aromatic ring systems include α - and β -naphthol and 5-tetralinol. Other non-limiting examples of aromatic alcohols include benzenediols (catechol, resorcinol or hydroquinone), *o*-cresol, *o*-phenylphenol, *m*-phenylphenol or *p*-phenylphenol. One skilled in the art may find other phenols and α - and β -hydroxy-substituted fused aromatic ring systems which are also suitable for the purposes of this invention. Preferably, the aromatic alcohol is unsubstituted phenol or a substituted phenol wherein the substituent is methyl, ethyl or hydroxyl. More preferably, the aromatic alcohol is unsubstituted phenol, cresol or a benzenediol. Most preferably, the aromatic alcohol is unsubstituted phenol.

According to the method of the invention for preparing a diaryl ether, a dehydration catalyst as described herein is contacted with the aromatic alcohol compound. The contacting of the catalyst with the aromatic alcohol compound is carried out under reaction conditions such that the diaryl ether is formed.

The catalyst is contacted with the aromatic alcohol compound either in the gas phase or in the liquid phase. In addition, the aromatic alcohol may be diluted with a diluent or it may be neat. Suitable diluents include, without limitation, nitrogen, argon, water vapor, water, oxygen or hydrogen. When a diluent is used, the concentration of the aromatic alcohol compound may be, for instance, 1 volume percent or greater and less than 100 volume percent.

In a preferred embodiment, the aromatic alcohol is contacted with the catalyst in the gas phase. Typically, the aromatic alcohol is introduced into a reactor containing the catalyst at elevated temperature, for instance, between 200 and 800 °C, alternatively between 300 and 600 °C, alternatively between 400 and 600 °C, or alternatively between 450 and 550 °C. The reaction may be conducted at atmospheric pressure, under reduced pressure, or at elevated pressure such as up to 5000 psi. In some embodiments, atmospheric

pressure or slightly above (e.g., up to about 50 psi) is preferred. In some embodiments, the gas flow rate of the aromatic alcohol over the catalyst (weighted hourly space velocity or WHSV) is from 0.01 to 100 grams per gram of catalyst per hour (g/g·h). In some embodiments, WHSV is from 0.1 to 20 g/g·h, alternatively 0.1 to 5 g/g·h, or alternatively 0.1 to 1 g/g·h.

In some embodiments, it may be useful to subject the reactor to startup conditions which may provide various benefits, such as prolonging catalyst life. Suitable startup conditions include, for example, exposing the catalyst to dilute amounts of the aromatic alcohol at lower temperature before changing to full operating conditions as described above and demonstrated by the examples.

Following the reaction, the diaryl ether product is recovered from the catalyst and optionally further purified. Unreacted alcohol and other reaction by-products may be separated using methods known in the art. Such methods include but are not limited to distillation, crystal refining, simulated moving bed technique or a combination thereof.

In some embodiments, the diaryl ether prepared by the process of the invention is diphenyl oxide (DPO). Other diaryl ether compounds that may be prepared by the process of the invention include, without limitation, compounds containing at least one ether functionality whereby two aryl moieties are connected by an oxygen atom (Ar-O-Ar'), including polyaryl compounds and compounds prepared from the aromatic alcohols described above. Specific examples include, but are not limited to, phenoxytoluene isomers, including 3-phenoxytoluene, ditolyl ether isomers, polyphenyl ethers (PPEs), biphenylphenyl ether isomers and naphthyl phenyl ethers.

The diaryl ethers prepared by the invention are useful in a variety of applications, including as high temperature solvents, as intermediates in preparing flame retardants and surfactants, and as components in heat transfer fluids. Furthermore, certain diaryl ethers prepared by the invention are useful as high performance lubricants and as intermediates in preparing pyrethroid insecticides.

In some embodiments, a preferred use of the diaryl ether is in high temperature heat transfer fluids. High temperature heat transfer fluids may be prepared by making the diaryl ether according to the process described above and then mixing the diaryl ether with biphenyl. The amounts necessary to provide a suitable fluid can be readily determined by a person with ordinary skill in the art. For diphenyl oxide and biphenyl, the amount of DPO may be, for instance, from 70 to 75 weight percent based on the total weight of the DPO and

biphenyl. A preferred amount of DPO is that required to form a eutectic mixture with the biphenyl, which is about 73.5 weight percent based on the total weight of the DPO and biphenyl.

Some embodiments of the invention will now be described in detail in the following Examples.

EXAMPLES

Example 1

A 1M SmCl_3 solution, prepared by dissolving 18.254 g SmCl_3 in 50 ml DI H_2O , is added dropwise along with tetrapropylammonium hydroxide (76.288 g, from a 40 wt% TPAOH solution) over 15 min into a 600 ml beaker containing an initial 100 ml DI H_2O . The solution is stirred at 500 rpm on a magnetic stir plate with a 3 inch stir bar. The resulting precipitate is allowed to age in solution for 1 h with stirring, after which it is centrifuged at 5000 rpm for 10 min. The decanted precipitate is placed into an oven, dried at 120 °C for 4 h and calcined at 500 °C for 4 h with a ramp rate of 5 °C/min to yield the solid product.

Example 2

The catalyst from Example 1 is used in the dehydration of phenol. The powder is pressed and sieved to obtain particles that are between 0.60 mm and 0.85 mm in diameter. The particles are loaded into an electrically heated stainless steel reactor tube and heated to the reaction temperature with nitrogen flowing through the tube. After the reaction temperature is reached, vapor-phase phenol is passed through the reactor tube. The conversion of phenol is carried out at a weighted hourly space velocity of 1 (WHSV=gram phenol/gram catalyst·hour) and at 500 °C. Test conditions and results are shown in Table 1.

Table 1

Test Conditions	Conversion [mol. %]	Selectivity [mol. %]					
		Phenol	Diphenyl Oxide	OPP	DBF	O-BIPPE	M-BIPPE
T = 500 °C Feed: PhOH ToS = 1.75 h WHSV 1 h ⁻¹	6.08%	92.99%	0.02%	6.99%	0.00%	0.00%	0.00%
T = 500 °C Feed: PhOH ToS = 2.75 h WHSV 1 h ⁻¹	5.36%	92.16%	0.90%	6.93%	0.00%	0.00%	0.00%
T = 500 °C Feed: PhOH ToS = 5 h WHSV 1 h ⁻¹	5.16%	91.91%	1.49%	6.60%	0.00%	0.00%	0.00%
T = 500 °C Feed: PhOH ToS = 7 h WHSV 1 h ⁻¹	4.91%	92.72%	0.03%	7.24%	0.00%	0.00%	0.00%

OPP: orthophenylphenol. DBF: dibenzofuran. O-BIPPE: ortho-biphenylphenyl ether. M-BIPPE: meta-biphenylphenyl ether. P-BIPPE: para-biphenylphenyl ether. PhOH: phenol. N₂: nitrogen. ToS: time on stream (ToS=0 hours defined as start of phenol flow).

Example 3

A 1M GdCl₃ solution, prepared by dissolving 18.633 g GdCl₃ in 50 ml DI H₂O, is added dropwise along with tetrapropylammonium hydroxide (76.261 g, from a 40 wt% TPAOH solution) over 15 min into a 600 ml beaker containing an initial 100 ml DI H₂O. The solution is stirred at 500 rpm on a magnetic stir plate with a 3 inch stir bar. The resulting precipitate is allowed to age in solution for 1 h with stirring, after which it is centrifuged at 5000 rpm for 10 min. The decanted precipitate is placed into an oven, dried at 120 °C for 4 h and calcined at 500 °C for 4 h with a ramp rate of 5 °C/min to yield the solid product.

Example 4

The catalyst from Example 3 is used in the dehydration of phenol. The powder is pressed and sieved to obtain particles that are between 0.60 mm and 0.85 mm in diameter. The particles are loaded into an electrically heated stainless steel reactor tube and heated to the reaction temperature with nitrogen flowing through the tube. After the reaction temperature is reached, vapor-phase phenol is passed through the reactor tube. The

conversion of phenol is carried out at a weighted hourly space velocity of 1 (WHSV=gram phenol/gram catalyst·hour) and at 500 °C. Test conditions and results are shown in Table 2.

Table 2

Test Conditions	Conversion [mol. %]	Selectivity [mol. %]					
		Phenol	Diphenyl Oxide	OPP	DBF	O-BIPPE	M-BIPPE
T = 500 °C Feed: PhOH ToS = 1 h WHSV 1 h ⁻¹	16.53%	92.44%	0.03%	6.96%	0.13%	0.25%	0.19%
T = 500 °C Feed: PhOH ToS = 2.75 h WHSV 1 h ⁻¹	11.05%	94.78%	0.50%	4.21%	0.11%	0.20%	0.21%
T = 500 °C Feed: PhOH ToS = 3.5 h WHSV 1 h ⁻¹	9.44%	94.64%	0.82%	3.85%	0.13%	0.17%	0.38%
T = 500 °C Feed: PhOH ToS = 4.75 h WHSV 1 h ⁻¹	7.09%	96.00%	0.22%	3.36%	0.04%	0.11%	0.26%

Example 5

The catalyst from Example 3 is used in the dehydration of phenol. The powder is pressed and sieved to obtain particles that were between 0.60 mm and 0.85 mm in diameter. The particles are loaded into an electrically heated stainless steel reactor tube and heated to the reaction temperature with nitrogen flowing through the tube. After the reaction temperature is reached, vapor-phase phenol is passed through the reactor tube. The conversion of phenol is carried out at a weighted hourly space velocity of 1 (WHSV=gram phenol/gram catalyst·hour) and at 500 °C. Test conditions and results are shown in Table 3.

Table 3

Test Conditions	Conversion [mol. %]	Selectivity [mol. %]					
		Phenol	Diphenyl Oxide	OPP	DBF	O-BIPPE	M-BIPPE
T = 500 °C Feed: PhOH ToS = 0.5 h WHSV 1 h ⁻¹	9.98%	96.06%	0.22%	3.40%	0.00%	0.08%	0.23%
T = 500 °C Feed: PhOH ToS = 1.75 h WHSV 1 h ⁻¹	11.87%	96.26%	0.16%	3.34%	0.02%	0.08%	0.15%
T = 500 °C Feed: PhOH ToS = 4 h WHSV 1 h ⁻¹	11.64%	96.52%	0.48%	2.77%	0.00%	0.09%	0.13%

Example 6

Example 5 is repeated with varying the process conditions. Conditions and results are shown in Tables 4-6.

Table 4 Dilute phenol feed at a range of temperatures

WHSV (wt PhOH / wt cat·h)	Feed Composition (vol. %)	Temperature (°C)	Phenol Conversion	DPO Selectivity (%)	DBF Selectivity (%)
1	33% PhOH 67% N ₂	400	0.10%	100.00%	0.00%
1	33% PhOH 67% N ₂	450	1.98%	98.47%	1.50%
1	33% PhOH 67% N ₂	500	7.28%	98.38%	1.42%
1	33% PhOH 67% N ₂	550	15.59%	91.48%	6.34%

Table 5 Neat phenol feed at a range of temperatures.

WHSV (wt PhOH / wt cat·h)	Feed Composition (vol. %)	Temperature (°C)	Phenol Conversion	DPO Selectivity (%)	DBF Selectivity (%)
1	100% PhOH	400	0.31%	83.75%	1.70%
1	100% PhOH	450	2.80%	98.01%	1.67%
1	100% PhOH	500	15.52%	97.86%	1.83%
1	100% PhOH	520	20.79%	95.65%	3.92%
1	100% PhOH	550	38.83%	94.42%	4.51%

Table 6 Neat phenol feed at a range of space velocities.

WHSV (wt PhOH / wt cat·h)	Feed Composition (vol. %)	Temperature (°C)	Phenol Conversion	DPO Selectivity (%)	DBF Selectivity (%)
0.25	100% PhOH	500	24.83%	95.30%	3.69%
0.5	100% PhOH	500	18.01%	95.77%	3.22%
0.75	100% PhOH	500	13.54%	96.16%	3.02%
1.0	100% PhOH	500	13.31%	95.34%	4.35%

Example 7

Preparation of 15 wt% Gd supported on ZrO₂ via incipient wetness impregnation.

Prior to the impregnation process, a hydrous ZrO₂ support with BET surface area of 323 m²/g is pre-dried at 120 °C for 4 hours in static air. 15 wt% Gd on ZrO₂ catalyst is prepared by two step incipient wetness impregnation of the treated ZrO₂ at ambient temperature. A glass beaker is charged with 5 g of pre-dried ZrO₂. A 10-ml graduated cylinder is loaded with 1.7737 g of GdCl₃·6H₂O to yield 15 wt% of Gd and with 1.2 ml of H₂O. The support is impregnated with the aqueous solution of gadolinium being added to the ZrO₂ in small fractions. After each addition, the support is agitated to break up clumps and uniformly disperse gadolinium throughout the carrier material. After the 0.7 ml of solution is added the sample is dried at 110 °C for 4 h. In the next step the remaining solution is added to a 10-ml graduated cylinder and the water level adjusted to 1.2 ml. The solution is then impregnated using small fractions added to the sample after it has cooled to room temperature. After each addition, the support is agitated to break up clumps and uniformly disperse gadolinium throughout the carrier material. The impregnated sample is then treated at 110 °C for 4 hours in flowing air and then at 600 °C for an additional 4 hours at a 5°C/min ramp.

Example 8

The catalyst from Example 7 is used in the dehydration of phenol. The powder is pressed and sieved to obtain particles that are between 0.60 mm and 0.85 mm in diameter. The particles are loaded into an electrically heated stainless steel reactor tube and heated to the reaction temperature with nitrogen flowing through the tube. After the reaction temperature is reached, vapor-phase phenol is passed through the reactor tube. The conversion of phenol is carried out at a weighted hourly space velocity of 1 (WHSV=gram phenol/gram catalyst·hour) and at 500 °C. Test conditions and results are shown in Table 7.

Table 7

Test Conditions	Conversion [mol. %]	Selectivity [mol. %]					
		Phenol	Diphenyl Oxide	OPP	DBF	O-BIPPE	M-BIPPE
T = 500 °C Feed: PhOH ToS = 1.5 h WHSV 1 h ⁻¹	11.46%	78.44%	3.06%	16.77%	0.03%	1.24%	0.47%
T = 500 °C Feed: PhOH ToS = 2.5 h WHSV 1 h ⁻¹	8.32%	78.78%	5.00%	14.33%	0.03%	1.24%	0.63%
T = 500 °C Feed: PhOH ToS = 3.75 h WHSV 1 h ⁻¹	6.82%	72.46%	5.03%	20.10%	0.04%	1.42%	0.95%
T = 500 °C Feed: PhOH ToS = 5.5 h WHSV 1 h ⁻¹	3.70%	93.77%	3.52%	0.10%	1.05%	0.79%	0.79%

Example 9

The synthesis of supported gadolinium oxychloride is carried out via an incipient wetness impregnation of gamma alumina.

Precursors:

Support: gamma alumina (available from Saint-Gobain NorPro) 30-60 mesh size, BET = 178.9 m²/g) that exhibits an incipient wetness condition of approximately 0.75 ml per 1 g.

Solution: Gadolinium(III) chloride hexahydrate (GdCl₃ · 6H₂O) and deionized water (DI water), prepared to c = 0.75 mol/l.

Synthesis:

3.75 ml of the solution is added dropwise to 5 g of the support at ambient conditions under vigorous shaking using a shaker plate. The impregnated material is then dried at 150 °C for 1 h, and the impregnation procedure is repeated three more times (total of 4 × 3.75 ml used for 5 g of carrier) to achieve a high loading of gadolinium inside the pores of the carrier. The preparation is finished off by calcining the impregnated material in a static air calcination oven using the following protocol: ramp 1 °C/min; dwell at T = 550 °C for 3 h,

cool down to room temperature. The chlorine content of the catalyst is assayed by XRF to 3.28 wt.% chlorine.

Example 10

The catalyst from Example 9 is used in the dehydration of phenol. The powder is sieved to obtain particles that are between 0.60 mm and 0.85 mm in diameter. The particles are loaded into an electrically heated stainless steel reactor tube and heated to the reaction temperature with nitrogen flowing through the tube. After the reaction temperature is reached, vapor-phase phenol is passed through the reactor tube. The conversion of phenol is carried out at a weighted hourly space velocity of 1 (WHSV=gram phenol/gram catalyst·hour) and at 500 °C. Test conditions and results are shown in Table 8.

Table 8

Test Conditions	Conversion [mol. %]	Selectivity [mol. %]					
		Phenol	Diphenyl Oxide	OPP	DBF	O-BIPPE	M-BIPPE
T = 500 °C Feed: PhOH ToS = 2.5 h WHSV 1 h ⁻¹	0.19%	90.19%	0.37%	9.43%	0.00%	0.00%	0.00%
T = 500 °C Feed: PhOH ToS = 3.5 h WHSV 1 h ⁻¹	0.19%	88.42%	0.33%	11.24%	0.00%	0.00%	0.00%
T = 500 °C Feed: PhOH ToS = 4.5 h WHSV 1 h ⁻¹	0.15%	88.51%	0.08%	11.42%	0.00%	0.00%	0.00%
T = 500 °C Feed: PhOH ToS = 6 h WHSV 1 h ⁻¹	0.19%	90.74%	0.10%	9.16%	0.00%	0.00%	0.00%

Example 11

The synthesis of supported gadolinium oxide is carried out via an incipient wetness impregnation of gamma alumina.

Precursors:

Support: gamma alumina (available from Saint-Gobain NorPro), 30-60 mesh size, BET = 178.9 m²/g) that exhibits an incipient wetness condition of approximately 0.75 ml per 1 g.

Solution: Gadolinium(III)nitrate hexahydrate (Gd(NO₃)₃·6H₂O) and deionized water (DI water), prepared to c = 2.2155 mol/l.

Synthesis:

3.75 ml of the solution is added dropwise to 5 g of the support at ambient conditions under vigorous shaking using a shaker plate. The impregnated material is then dried at 150 °C for 1 h, and then calcined in a static air calcination oven using the following protocol: ramp 1 °C/min; dwell at T = 550 °C for 3 h, cool down to room temperature. The chlorine content of the catalyst is assayed by XRF to 0.45 wt.% chlorine.

Example 12

The catalyst from Example 11 is used in the dehydration of phenol. The powder is sieved to obtain particles that are between 0.60 mm and 0.85 mm in diameter. The particles are loaded into an electrically heated stainless steel reactor tube and heated to the reaction temperature with nitrogen flowing through the tube. After the reaction temperature is reached, vapor-phase phenol is passed through the reactor tube. The conversion of phenol is carried out at a weighted hourly space velocity of 1 (WHSV=gram phenol/gram catalyst·hour) and at 500 °C. Test conditions and results are shown in Table 9.

Table 9

Test Conditions	Conversion [mol. %]	Selectivity [mol. %]					
		Phenol	Diphenyl Oxide	OPP	DBF	O-BIPPE	M-BIPPE
T = 500 °C Feed: PhOH ToS = 1.75 h WHSV 1 h ⁻¹	11.47%	75.36%	3.61%	19.72%	0.05%	0.27%	0.99%
T = 500 °C Feed: PhOH ToS = 2.75 h WHSV 1 h ⁻¹	10.84%	74.98%	5.90%	17.77%	0.05%	0.29%	1.01%
T = 500 °C Feed: PhOH ToS = 5 h WHSV 1 h ⁻¹	9.78%	74.72%	6.85%	18.08%	0.05%	0.28%	0.03%
T = 500 °C Feed: PhOH ToS = 6.5 h WHSV 1 h ⁻¹	9.00%	74.15%	4.62%	19.94%	0.04%	0.28%	0.98%

Example 13

The supported gadolinium oxide promoted with chlorine is prepared from the gamma alumina-supported gadolinium oxide described in Example 11 by high temperature treatment of the material in the presence of ammonium chloride.

Precursors:

Gamma alumina-supported gadolinium oxide (BET = 145.2 m²/g having elemental composition of 27.73 wt.% Gd, 0.45 wt.% Cl, 35.60 wt.% Al and 36.22 wt.% O (balance) physically mixed with anhydrous ammonium chloride in a weight ratio of 1:1.

Synthesis:

The physical mixture of the gamma alumina-supported gadolinium oxide sample and ammonium chloride is calcined in a static air calcination oven using the following protocol: ramp 1 °C/min; dwell at T = 550 °C for 3 h, cool down to room temperature. The chlorine content of the catalyst is assayed by XRF to 8.51 wt.% chlorine.

Example 14

The catalyst from Example 13 is used in the dehydration of phenol. The powder is sieved to obtain particles that are between 0.60 mm and 0.85 mm in diameter. The particles

are loaded into an electrically heated stainless steel reactor tube and heated to the reaction temperature with nitrogen flowing through the tube. After the reaction temperature is reached, vapor-phase phenol is passed through the reactor tube. The conversion of phenol is carried out at a weighted hourly space velocity of 1 (WHSV=gram phenol/gram catalyst-hour) and at 500 °C. Test conditions and results are shown in Table 10.

Table 10

Test Conditions	Conversion [mol. %]	Selectivity [mol. %]					
		Phenol	Diphenyl Oxide	OPP	DBF	O-BIPPE	M-BIPPE
T = 500 °C Feed: PhOH ToS = 1.75 h WHSV 1 h ⁻¹	4.34%	82.66%	0.17%	17.03%	0.00%	0.13%	0.00%
T = 500 °C Feed: PhOH ToS = 2.75 h WHSV 1 h ⁻¹	3.81%	85.76%	3.83%	10.22%	0.00%	0.18%	0.00%
T = 500 °C Feed: PhOH ToS = 5 h WHSV 1 h ⁻¹	3.67%	85.41%	2.33%	11.20%	0.07%	0.25%	0.74%
T = 500 °C Feed: PhOH ToS = 6.5 h WHSV 1 h ⁻¹	3.71%	84.41%	3.70%	10.32%	0.08%	0.27%	1.23%

We claim:

1. A method for preparing a diaryl ether, the method comprising dehydrating an aromatic alcohol compound over a dehydration catalyst, wherein the dehydration catalyst is an oxide of a medium rare earth element.
2. The method of claim 1 wherein the dehydration catalyst further comprises a halogen.
3. The method of claim 2 wherein the halogen is chloride or fluoride ion.
4. The method of any one of claims 1-3 wherein the dehydration catalyst further comprises a binder.
5. The method of any one of claims 1-4 wherein the dehydration catalyst is supported.
6. The method of any one of claims 1-4 wherein the dehydration catalyst is unsupported.
7. The method of any one of claims 1-6 wherein the dehydration of the alcohol is conducted at a temperature from 250 to 600 °C.
8. The method of any one of claims 1-7 wherein the alcohol feed is diluted with a diluent.
9. The method of any one of claims 1-8 wherein the aromatic alcohol compound is phenol and the diaryl ether produced is diphenyl oxide.
10. A method for producing a heat transfer fluid, the method comprising:
 - preparing a diaryl ether by contacting an aromatic alcohol compound with a dehydration catalyst, wherein the dehydration catalyst is an oxide of a medium rare earth element;
 - isolating the diaryl ether from the dehydration catalyst; and
 - mixing the isolated diaryl ether with biphenyl such that the mixture forms a eutectic mixture.

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2013/055963

A. CLASSIFICATION OF SUBJECT MATTER
 INV. B01J23/10 C07C41/09 C07C43/275
 ADD.
 According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED
 Minimum documentation searched (classification system followed by classification symbols)
 B01J C07C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)
 EPO-Internal, CHEM ABS Data, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 925 798 A (GAMBELL JAMES WILLIAM [US] ET AL) 20 July 1999 (1999-07-20) cited in the application claim 34; examples 1-12 -----	1-10
A	US 3 922 331 A (MACDONALD DAVID J ET AL) 25 November 1975 (1975-11-25) column 1, line 42 - line 50; examples 1-2 -----	1-10
A	WO 00/15730 A1 (DAMIANI ROBERT A [US]; DAMIANI MICHAEL R [US]) 23 March 2000 (2000-03-23) page 1, paragraph 2 -----	1-10

Further documents are listed in the continuation of Box C.

See patent family annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier application or patent but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- "&" document member of the same patent family

Date of the actual completion of the international search 18 November 2013	Date of mailing of the international search report 28/11/2013
-----------------------------------------------------------------------------------	----------------------------------------------------------------------

Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer Lacombe, Céline
----------------------------------------------------------------------------------------------------------------------------------------------------------------------	-------------------------------------------

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No PCT/US2013/055963

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5925798	A	20-07-1999	AT 209961 T 15-12-2001
			CA 2171263 A1 09-09-1996
			DE 69617495 D1 17-01-2002
			EP 0730905 A2 11-09-1996
			US 5925798 A 20-07-1999

US 3922331	A	25-11-1975	NONE

WO 0015730	A1	23-03-2000	AU 5549599 A 03-04-2000
			CA 2344276 A1 23-03-2000
			EP 1114114 A1 11-07-2001
			MX PA01002760 A 24-04-2002
			TW 495546 B 21-07-2002
			WO 0015730 A1 23-03-2000
