

(12) **UK Patent Application** (19) **GB** (11) **2 297 091** (13) **A**

(43) Date of A Publication 24.07.1996

(21) Application No **9600897.4**

(22) Date of Filing **17.01.1996**

(30) Priority Data

(31) **13995** (32) **18.01.1995** (33) **CH**

(71) Applicant(s)

Ciba-Geigy AG

(Incorporated in Switzerland)

Klybeckstrasse 141, CH-4002 Basle, Switzerland

(72) Inventor(s)

Andreas Valet

Gerhard Rytz

Pascal Hayoz

(74) Agent and/or Address for Service

Ciba-Geigy plc

Patent Department, Central Research, Hulley Road,

MACCLESFIELD, Cheshire, SK10 2NX,

United Kingdom

(51) INT CL⁶

C08K 5/3492 5/36 5/524 , C09D 133/00

(52) UK CL (Edition O)

**C3K KCZ K210 K220 K221 K222 K223 K251 K262 K263
K270 K273 K277 K281 K290 K291 K292 K293 K296
K297 K299 K310**

**C3W W100 W111 W112 W113 W114 W216 W217 W218
W225 W308 W314 W316 W321 W322 W328
U1S S1367 S1381 S1391 S1591 S1820**

(56) Documents Cited

EP 0520938 A1 EP 0434608 A1

(58) Field of Search



UK CL (Edition O) **C3K KCC KCZ**

INT CL⁶ **C08K 5/00 5/34 5/3477 5/3492**

ONLINE:Chinese Patents ABS, CLAIMS, JAPIO, WPI

(54) **Stabilizer combination for organic material**

(57) A mixture comprising a compound of the formula I and a compound of the formula II



in which n is 1 or 2;

R₁, R'₁, R₂, R'₂, R₃ and R₄, independently of one another, are H, C₁-C₁₂alkyl; C₂-C₆alkenyl; C₁-C₁₂alkoxy; C₂-C₁₈alkenoxy; halogen; trifluoromethyl; C₇-C₁₁phenylalkyl; phenyl; phenyl which is substituted by C₁-C₁₈alkyl, C₁-C₁₈alkoxy or halogen; phenoxy; or phenoxy which is substituted by C₁-C₁₈alkyl, C₁-C₁₈alkoxy or halogen;

R₆ is hydrogen, C₁-C₂₄alkyl, C₅-C₁₂cycloalkyl or C₇-C₁₅phenylalkyl; R₇, in the case where n = 1, and R'₇, independently of one another, are hydrogen or C₁-C₁₈alkyl; or are C₁-C₁₂alkyl which is substituted by OH, C₁-C₁₈alkoxy, allyloxy, halogen, -COOH, -COOR₈, -CONH₂, -CONHR₉, -CON(R₉)(R₁₀), -NH₂, -NHR₉, -N(R₉)(R₁₀), -NHCOR₁₁, -CN, -OCOR₁₁, phenoxy and/or phenoxy which is substituted by C₁-C₁₈alkyl, C₁-C₁₈alkoxy or halogen; or R₇ is C₃-C₅₀alkyl which is interrupted by -O- and may be substituted by OH; or R₇ is C₃-C₆alkenyl; glycidyl; C₅-C₁₂cycloalkyl; cyclohexyl which is substituted by OH, C₁-C₄alkyl or -OCOR₁₁; C₇-C₁₁phenylalkyl which is unsubstituted or substituted by OH, Cl or CH₃; -CO-R₁₂ or -SO₂-R₁₃;

and R₇, in the case where n = 2, and R₈ to R₂₃ are as defined in claim 1, is highly suitable for stabilizing organic material.

GB 2 297 091 A

Stabilizer combination


The invention relates to a novel stabilizer mixture comprising mono- and bisresorcinyltriazines, to organic material stabilized with the aid of this mixture against damage by light, heat and oxygen and to the corresponding use of the mixture as a stabilizer for organic material.

If it is desired to increase the light stability of an organic material, in particular a coating, a light stabilizer is usually added. A class of light stabilizers which is very frequently employed comprises the UV absorbers, which protect the material by absorbing the harmful radiation via chromophores. An important group of UV absorbers is the triphenyltriazines, as described, inter alia, in EP-A-434 608, EP-A-520 938, US-A-4 619 956, EP-A-483 488, EP-A-500 496, EP-A-502 816 and EP-A-506 615. Some bisresorcinylnyl derivatives from this group are mentioned, for example, in CH-A-480 090, CH-A-484 695, US-A-3 249 608, US-A-3 244 708, US-A-3 843 371, US-A-4 826 978, EP-A-434 608, EP-A-520 938, GB-A-2 273 498 and WO-A-94/18 278

Stabilizer mixtures comprising UV absorbers of the triphenyltriazine and o-hydroxyphenylbenzotriazole type have also already been proposed (EP-A-453 396).


It has now been found that mixtures comprising 2 different types of stabilizer from the triphenyltriazine class surprisingly have particularly good stabilizer properties.

The invention therefore relates to a mixture comprising a compound of the formula I



I

and a compound of the formula II



in which n is 1 or 2;


R_1 , R'_1 , R_2 and R'_2 , independently of one another, are H, C_1 - C_{12} alkyl; C_2 - C_6 alkenyl; C_1 - C_{12} alkoxy; C_2 - C_{18} alkenoxy; halogen; trifluoromethyl; C_7 - C_{11} phenylalkyl; phenyl; phenyl which is substituted by C_1 - C_{18} alkyl, C_1 - C_{18} alkoxy or halogen; phenoxy; or phenoxy which is substituted by C_1 - C_{18} alkyl, C_1 - C_{18} alkoxy or halogen;

R_3 and R_4 , independently of one another, are H, C_1 - C_{12} alkyl; C_2 - C_6 alkenyl; C_1 - C_{12} alkoxy; C_5 - C_{12} cycloalkoxy; C_2 - C_{18} alkenoxy; halogen; trifluoromethyl; C_7 - C_{11} phenylalkyl; phenyl; phenyl which is substituted by C_1 - C_{18} alkyl, C_1 - C_{18} alkoxy or halogen; phenoxy; or phenoxy which is substituted by C_1 - C_{18} alkyl, C_1 - C_{18} alkoxy or halogen;

R_6 is hydrogen, C_1 - C_{24} alkyl, C_5 - C_{12} cycloalkyl or C_7 - C_{15} phenylalkyl;

R_7 , in the case where $n = 1$, and R'_7 , independently of one another, are hydrogen or C_1 - C_{18} alkyl; or are C_1 - C_{12} alkyl which is substituted by OH, C_1 - C_{18} alkoxy, allyloxy, halogen, $-COOH$, $-COOR_8$, $-CONH_2$, $-CONHR_9$, $-CON(R_9)(R_{10})$, $-NH_2$, $-NHR_9$, $-N(R_9)(R_{10})$, $-NHCOR_{11}$, $-CN$, $-OCOR_{11}$, phenoxy and/or phenoxy which is substituted by C_1 - C_{18} alkyl, C_1 - C_{18} alkoxy or halogen; or R_7 is C_3 - C_{50} alkyl which is interrupted by $-O-$ and may be substituted by OH; or R_7 is C_3 - C_6 alkenyl; glycidyl; C_5 - C_{12} cycloalkyl; cyclohexyl which is substituted by OH, C_1 - C_4 alkyl or $-OCOR_{11}$; C_7 - C_{11} phenylalkyl which is unsubstituted or substituted by OH, Cl or CH_3 ; $-CO-R_{12}$ or $-SO_2-R_{13}$;

R_7 , in the case where $n = 2$, is C_2 - C_{16} alkylene, C_4 - C_{12} alkenylene, xylylene, C_3 - C_{20} alkylene which is interrupted by O and/or substituted by OH, or is a group of the formula $-CH_2CH(OH)CH_2O-R_{20}-OCH_2CH(OH)CH_2-$, $-CO-R_{21}-CO-$, $-CO-NH-R_{22}-NH-CO-$ or $-(CH_2)_m-COO-R_{23}-OOC-(CH_2)_m-$, in which m is a number in the range from 1 to 3, or is



R_8 is C_1 - C_{18} alkyl; C_2 - C_{18} alkenyl; C_3 - C_{50} alkyl which is interrupted by O, NH, NR_9 or S and/or is substituted by OH; C_1 - C_4 alkyl which is substituted by $-P(O)(OR_{14})_2$, $-N(R_9)(R_{10})$ or $-OCOR_{11}$ and/or OH; glycidyl; cyclohexyl; phenyl; C_7 - C_{14} alkylphenyl or C_7 - C_{11} phenylalkyl;

R_9 and R_{10} , independently of one another, are C_1 - C_{12} alkyl; C_3 - C_{12} alkoxyalkyl; C_4 - C_{16} dialkylaminoalkyl or C_5 - C_{12} cycloalkyl, or R_9 and R_{10} together are C_3 - C_9 alkylene or -oxaalkylene or -azaalkylene;

R_{11} is C_1 - C_{18} alkyl; C_2 - C_{18} alkenyl or phenyl; or is C_3 - C_{50} alkyl which is interrupted by -O- and may be substituted by OH;

R_{12} is C_1 - C_{18} alkyl; C_2 - C_{18} alkenyl; phenyl; C_1 - C_{18} alkoxy; C_3 - C_1 alkenyloxy; C_3 - C_{50} alkoxy which is interrupted by O, NH, NR_9 or S and/or substituted by OH; cyclohexyloxy; C_7 - C_{14} alkylphenoxy; C_7 - C_{11} phenylalkoxy; phenoxy; C_1 - C_{12} alkylamino; phenylamino; tolylamino or naphthylamino;


R_{13} is C_1 - C_{12} alkyl; phenyl; naphthyl or C_7 - C_{14} alkylphenyl;

R_{14} is C_1 - C_{12} alkyl, methylphenyl or phenyl;

R_{20} is C_2 - C_{10} alkylene; C_4 - C_{50} alkylene which is interrupted by O, phenylene or a -phenylene-X-phenylene- group, in which X is -O-, -S-, $-SO_2$ -, $-CH_2$ - or $-C(CH_3)_2$ -;

R_{21} is C_2 - C_{10} alkylene, C_2 - C_{10} oxaalkylene, C_2 - C_{10} thiaalkylene, C_6 - C_{12} arylene or C_2 - C_6 alkenylylene;

R_{22} is C_2 - C_{10} alkylene, phenylene, tolylene, diphenylenemethane or a



R_{23} is C_2 - C_{10} alkylene or C_4 - C_{20} alkylene which is interrupted by O.

Of particular industrial interest are mixtures of compounds of the formulae I and II whose hydroxyl groups in the p- position to the triazinyl ring are etherified or esterified, i.e. whose radicals R_7 are not hydrogen.

A halogen substituent is -F, -Cl, -Br or I; preferably -F or -Cl, in particular -Cl.

Alkylphenyl is alkyl-substituted phenyl; C₇-C₁₄alkylphenyl includes, for example, methylphenyl (tolyl), dimethylphenyl (xylyl), trimethylphenyl (mesityl), ethylphenyl, propylphenyl, butylphenyl, dibutylphenyl, pentylphenyl, hexylphenyl, heptylphenyl and octylphenyl.

Phenylalkyl is phenyl-substituted alkyl; C₇-C₁₁phenylalkyl includes, for example, benzyl, α -methylbenzyl, α,α -dimethylbenzyl, phenylethyl, phenylpropyl, phenylbutyl and phenylpentyl.

Glycidyl is 2,3-epoxypropyl.

Alkyl which is interrupted by O, NH, NR₉ or S and may be substituted by OH can in general contain one or more of said hetero atoms, although oxygen, nitrogen and sulfur atoms cannot be adjacent to one another. In general, hetero atoms in the alkyl chain and hydroxyl are not vicinal; a carbon atom in the alkyl chain is preferably bonded to at most 1 oxygen, nitrogen or sulfur atom.

Alkyl R₁, R'₁, R'₂, R₂, R₃, R₄, R₇, R'₇, R₈, R₉, R₁₀, R₁₁, R₁₂, R₁₃ and R₁₄ are, within the stated definitions, branched or unbranched alkyl, such as methyl, ethyl, propyl, isopropyl, n-butyl, sec-butyl, isobutyl, t-butyl, 2-ethylbutyl, n-pentyl, isopentyl, 1-methylpentyl, 1,3-dimethylbutyl, n-hexyl, 1-methylhexyl, n-heptyl, isoheptyl, 1,1,3,3-tetramethylbutyl, 1-methylheptyl, 3-methylheptyl, n-octyl, 2-ethylhexyl, 1,1,3-trimethylhexyl, 1,1,3,3-tetramethylpentyl, nonyl, decyl, undecyl, 1-methylundecyl, dodecyl, 1,1,3,3,5,5-hexamethylhexyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl or octadecyl. Alkyl R₁, R'₁, R'₂, R₂, R₃, R₄, R₈, R₉, R₁₀, R₁₁, R₁₂, R₁₃ and R₁₄ are preferably short-chain, for example C₁-C₈alkyl, in particular C₁-C₄alkyl, such as methyl or butyl.

R₁, R'₁, R'₂, R₂, R₃ and R₄ are, independently of one another, particularly preferably hydrogen, methyl, methoxy, ethyl or isopropyl, in particular hydrogen or methyl.

C₄-C₁₆dialkylaminoalkyl R₉ or R₁₀ is alkyl which is substituted by dialkylamino, where the entire radical contains 4 to 16 carbon atoms. Examples thereof are (CH₃)₂N-CH₂CH₂-; (C₂H₅)₂N-CH₂CH₂-; (C₃H₇)₂N-CH₂CH₂-; (C₄H₉)₂N-CH₂CH₂-; (C₅H₁₁)₂N-CH₂CH₂-; (C₆H₁₃)₂N-CH₂CH₂-; (CH₃)₂N-CH₂CH₂CH₂-; (C₂H₅)₂N-CH₂CH₂CH₂-; (C₃H₇)₂N-CH₂CH₂CH₂-; (C₄H₉)₂N-CH₂CH₂CH₂-; (C₅H₁₁)₂N-CH₂CH₂CH₂- and (C₆H₁₃)₂N-CH₂CH₂CH₂-.

C₃-C₉alkylene or -oxaalkylene or -azaalkylene R₉ and R₁₀ together are, together with the nitrogen atom to which they are bonded, generally a 5- to 9-membered ring which contains 3 to 9 carbon atoms and may contain further nitrogen or oxygen atoms, although directly adjacent nitrogen and/or oxygen atoms (structures of hydrazine, oxylamine or peroxide type) are excluded. Examples thereof include pyrrolidino, piperidino, piperazino and morpholino.

The novel mixture frequently comprises compounds of the formulae I and II whose radicals of the same name within the stated definition are different; for example, the novel mixture can be, for example, a mixture of a compound of the formula I in which R₁, R₂, R₃ and R₄ are hydrogen and a compound of the formula II in which R₁ and R₃ are methyl. Of particular industrial interest are mixtures of compounds of the formulae I and II in which radicals having the same name have identical meanings.

Likewise of particular interest for use in the novel mixtures are compounds of the formula I in which R₁ and R₂ are identical and in which R₃ and R₄ are likewise identical and in which R'₁ and R'₂ are likewise identical, in particular those in which R₁ to R₄ are methyl and R'₁ and R'₂ are hydrogen or methyl. n is preferably 1.

Unsubstituted or substituted C₅-C₁₂cycloalkyl R₇ and R'₇ are, for example, cyclopentyl, cyclohexyl, cycloheptyl, cyclooctyl, cyclododecyl, methylcyclohexyl or acetoxycyclohexyl, preferably cyclohexyl or cyclododecyl.

If alkyl radicals carry further substituents or if individual radicals are alkylene, free valences and bonds to substituents can emanate from the same or different carbon atoms. Bonds to hetero atoms preferably emanate from different carbon atoms.

Thus, substituted C₁-C₁₂alkyl R₇ and R'₇ include, for example, hydroxyalkyl, such as 2-hydroxyethyl, 3-hydroxypropyl or 2-hydroxypropyl; alkoxyhydroxyalkyl such as 2-hydroxy-3-methoxypropyl, 2-hydroxy-3-ethoxypropyl, 2-hydroxy-3-butoxypropyl, 2-hydroxy-3-hexyloxypropyl or 2-hydroxy-3-(2-ethylhexyloxy)propyl; alkoxyalkyl, such as methoxycarbonylmethyl, ethoxycarbonylmethyl, butoxycarbonylmethyl, octyloxy-carbonylmethyl, 1-octyloxy-carbonyl-1-methylmethyl, 1-octyloxy-carbonyl-1-ethylmethyl or 1-octyloxy-carbonyl-1-hexylmethyl; or alkanoyloxyalkyl or alkenoyloxyalkyl, such as 2-(acetoxo)ethyl, 2-acryloxyethyl or 2-methacryloxyethyl; or, for example, 3-acryloxy- or 3-methacryloxy-2-hydroxypropyl.

R_7 and R'_7 as alkyl which is substituted by OH, alkoxy, phenoxy, $-\text{COOR}_8$ and/or $-\text{OCOR}_{11}$ include, for example, the following meanings: $-\text{CH}_2\text{CH}(\text{OH})\text{CH}_2\text{O}-R_{19}$, in which R_{19} is as defined above for alkyl or can be, for example, phenyl, acetyl, propionyl, acryloyl or methacryloyl; or alkoxy-carbonylalkyl; examples which may be mentioned of such radicals are $-\text{CH}_2\text{CH}_2\text{OCOCH}=\text{CH}_2$, $-\text{CH}_2\text{CH}(\text{OH})\text{C}_8\text{H}_{17}$, $-\text{CH}_2\text{CH}(\text{OH})\text{C}_{12}\text{H}_{25}$, $-\text{CH}_2\text{CH}(\text{OH})\text{CH}_2\text{O}-n-\text{C}_8\text{H}_{17}$, $-\text{CH}_2\text{CH}(\text{OH})\text{CH}_2\text{O}-\text{C}_6\text{H}_5$, $-\text{CH}_2\text{CH}(\text{OH})\text{CH}_2\text{O}-\text{CH}_2\text{CH}(\text{C}_2\text{H}_5)-(\text{CH}_2)_3-\text{CH}_3$, $-\text{CH}_2\text{CH}(\text{OH})\text{CH}_2\text{O}-(\text{CH}_2)_{12-14}-\text{CH}_3$, $-\text{OCH}_2\text{CH}(\text{OH})\text{CH}_2\text{OCOC}(\text{CH}_3)=\text{CH}_2$ and $-\text{OCH}_2\text{CH}(\text{OH})\text{CH}_2\text{OCOCH}=\text{CH}_2$.

R_7 , R'_7 , R_8 and R_{11} as alkyl which is interrupted by O and may be substituted by OH can be interrupted by one or more O and substituted by one or more OH. These radicals are preferably interrupted by more than one O, for example 2-12 oxygen atoms, and are preferably unsubstituted or substituted by 1-2 OH. In this definition, R_8 and R_{11} preferably conform to the formula $-(\text{CH}_2\text{CHR}_{15}-\text{O})_i-R_{18}$, and R_7 and R'_7 preferably conform to one of the formulae $-(\text{CH}_2\text{CHR}_{15}-\text{O})_i-R_{18}$ or $-\text{CH}_2-\text{CH}(\text{OH})-\text{CH}_2-\text{O}-(\text{CH}_2\text{CHR}_{15}-\text{O})_i-R_{18}$, where i is a number in the range from 1 to 16, especially in the range from 2 to 12, especially in the range from 4 to 10, R_{15} is H or methyl, and R_{18} is H, C_1 - C_{18} alkyl, phenyl or C_7 - C_{10} alkylphenyl. A typical example of such radicals is polyoxyethylene, for example having 4-10 ethylene oxide units, which carries a free hydroxyl group at the chain end or is saturated by alkyl.


R_6 is preferably either hydrogen or the radical is in position 5 (p-position to OH and o-position to OR_7). Of particular importance are compounds in which R_6 is hydrogen, C_1 - C_{10} alkyl or C_7 - C_{15} phenylalkyl, in particular hydrogen.

Alkenyl R_1 , R_2 , R_3 , R_4 , R_7 , R_8 , R_{11} and R_{12} within the stated definitions include allyl, isopropenyl, 2-butenyl, 3-butenyl, isobutenyl, n-penta-2,4-dienyl, 3-methylbut-2-enyl, n-oct-2-enyl, n-dodec-2-enyl, isododecenyl, n-octadec-2-enyl and n-octadec-4-enyl. R_7 , R_{11} and R_{12} can also be, for example, vinyl. Alkenyl R_{11} and R_{12} are particularly preferably $-\text{CH}=\text{CH}_2$ or $-\text{C}(\text{CH}_3)=\text{CH}_2$.


Aryl is generally an aromatic hydrocarbon radical, for example phenyl, biphenyl or naphthyl. Aralkyl generally denotes aryl-substituted alkyl; thus C_7 - C_{12} aralkyl includes, for example, benzyl, phenylethyl, phenylpropyl, phenylbutyl, phenylpentyl and phenylhexyl, preferably benzyl and α -methylbenzyl. Alkylaryl is alkyl-substituted aryl; C_7 - C_{18} alkylaryl includes methylphenyl (tolyl), dimethylphenyl (xylyl), trimethylphenyl,

tetramethylphenyl, pentamethylphenyl, ethylphenyl, propylphenyl (for example cumyl), butylphenyl (for example tert-butylphenyl), methylbutylphenyl, dibutylphenyl, pentylphenyl, hexylphenyl, dihexylphenyl, heptylphenyl, octylphenyl, nonylphenyl, decylphenyl, undecylphenyl, dodecylphenyl, methylnaphthyl, dimethylnaphthyl, ethylnaphthyl, propylnaphthyl, butylnaphthyl, pentylnaphthyl, hexylnaphthyl, heptylnaphthyl and octylnaphthyl; of these, toyl, Xylyl, Propylphenyl and butylphenyl, for example, are of particular importance.

The invention relates, for example, to a mixture comprising a compound of the formula I'



and a compound of the formula II'



in which R_1 and R_2 , independently of one another, are H, C_1 - C_{12} alkyl; C_2 - C_6 alkenyl; C_1 - C_{12} alkoxy; C_2 - C_{18} alkenoxy; halogen; trifluoromethyl; C_7 - C_{11} phenylalkyl; phenyl;

phenyl which is substituted by C₁-C₁₈alkyl, C₁-C₁₈alkoxy or halogen; phenoxy; or phenoxy which is substituted by C₁-C₁₈alkyl, C₁-C₁₈alkoxy or halogen;

R₃ and R₄, independently of one another, are H, C₁-C₁₂alkyl; C₂-C₆alkenyl; C₁-C₁₂alkoxy; C₂-C₁₈alkenoxy; halogen; trifluoromethyl; C₇-C₁₁phenylalkyl; phenyl; phenyl which is substituted by C₁-C₁₈alkyl, C₁-C₁₈alkoxy or halogen; phenoxy; or phenoxy which is substituted by C₁-C₁₈alkyl, C₁-C₁₈alkoxy or halogen;

R₇ is hydrogen or C₁-C₁₈alkyl; or is C₁-C₁₂alkyl which is substituted by OH, C₁-C₁₈alkoxy, halogen, -COOH, -COOR₈, -CONH₂, -CONHR₉, -CON(R₉)(R₁₀), -NH₂, -NHR₉, -N(R₉)(R₁₀), -NHCOR₁₁, -CN, -OCOR₁₁, phenoxy and/or phenoxy which is substituted by C₁-C₁₈alkyl, C₁-C₁₈alkoxy or halogen; or R₇ is C₃-C₅₀alkyl which is interrupted by -O- and may be substituted by OH; or R₇ is C₃-C₆alkenyl; glycidyl; C₅-C₁₂cycloalkyl; cyclohexyl which is substituted by OH, C₁-C₄alkyl or -OCOR₁₁; C₇-C₁₁phenylalkyl which is unsubstituted or substituted by OH, Cl or CH₃; -CO-R₁₂ or -SO₂-R₁₃;

R₈ is C₁-C₁₈alkyl; C₂-C₁₈alkenyl; C₃-C₅₀alkyl which is interrupted by O, NH, NR₉ or S and/or is substituted by OH; C₁-C₄alkyl which is substituted by -P(O)(OR₁₄)₂, -N(R₉)(R₁₀) or -OCOR₁₁ and/or OH; glycidyl; cyclohexyl; phenyl; C₇-C₁₄alkylphenyl or C₇-C₁₁phenylalkyl;

R₉ and R₁₀, independently of one another, are C₁-C₁₂alkyl; C₃-C₁₂alkoxyalkyl; C₄-C₁₆dialkylaminoalkyl or C₅-C₁₂cycloalkyl, or R₉ and R₁₀ together are C₃-C₉alkylene or -oxaalkylene or -azaalkylene;

R₁₁ is C₁-C₁₈alkyl; C₂-C₁₈alkenyl or phenyl; or is C₃-C₅₀alkyl which is interrupted by -O- and may be substituted by OH;

R₁₂ is C₁-C₁₈alkyl; C₂-C₁₈alkenyl; phenyl; C₁-C₁₂alkoxy; phenoxy; C₁-C₁₂alkylamino; phenylamino; tolylamino or naphthylamino;

R₁₃ is C₁-C₁₂alkyl; phenyl; naphthyl or C₇-C₁₄alkylphenyl; and

R₁₄ is C₁-C₁₂alkyl, methylphenyl or phenyl.

The novel mixtures comprise from 0.2 to 5 parts by weight, in particular from 0.3 to 3 parts by weight, of a compound of the formula II per part by weight of a compound of the formula I.

Preference is given to mixtures of compounds of the formulae I and II in which R₁, R'₁, R'₂ and R₂, independently of one another, are H, C₁-C₄alkoxy or C₁-C₄alkyl; R₃ and R₄, independently of one another, are H, C₁-C₁₂alkyl, C₂-C₆alkenyl, C₁-C₁₂alkoxy, Cl, F, phenyl or phenoxy; R₇, in the case where n = 1, and R'₇ are hydrogen, C₁-C₁₈alkyl, allyl, glycidyl or benzyl;

or are C₁-C₁₂alkyl which is substituted by OH, C₁-C₁₈alkoxy, phenoxy, -COOR₈, -CONHR₉, -CON(R₉)(R₁₀) and/or -OCOR₁₁; or R₇ is -(CH₂CHR₁₅-O)_i-R₁₈ or -CH₂-CH(OH)-CH₂-O-(CH₂CHR₁₅-O)_i-R₁₈, where i is a number in the range from 1 to 12;

R₇, in the case where n = 2, is C₂-C₁₆alkylene, C₄-C₁₂alkenylene, xylylene, or C₃-C₂₀alkylene which is interrupted by O and/or is substituted by OH;

R₈ is C₁-C₁₂alkyl; C₃-C₁₈alkenyl; C₃-C₂₀alkyl which is interrupted by O and/or is substituted by OH; or C₁-C₄alkyl which is substituted by -P(O)(OR₁₄)₂;

R₉ and R₁₀, independently of one another, are C₁-C₈alkyl or cyclohexyl; or R₉ and R₁₀ together are pentamethylene or 3-oxapentamethylene;

R₁₁ is C₁-C₈alkyl, C₂-C₅alkenyl or phenyl; or is C₃-C₂₀alkyl which is interrupted by -O- and may be substituted by OH;

R₁₄ is C₁-C₄alkyl;

R₁₅ is H or methyl; and

R₁₈ is H, C₁-C₁₈alkyl, phenyl or C₇-C₁₀alkylphenyl.

Particular preference is given to mixtures of compounds of the formulae I and II in which n is 1;

R₇ and R'₇ are hydrogen; C₁-C₁₈alkyl; C₁-C₁₂alkyl which is substituted by OH, C₁-C₁₈alkoxy, -COOR₈, -CON(R₉)(R₁₀), phenoxy and/or -OCOR₁₁; glycidyl or benzyl; or R₇ is -(CH₂CHR₁₅-O)_i-R₁₈ or -CH₂-CH(OH)-CH₂-O-(CH₂CHR₁₅-O)_i-R₁₈, where i is a number in the range 2-12;

R₈ is C₁-C₁₂alkyl; C₃-C₁₂alkenyl; C₆-C₂₀alkyl which is interrupted by O and/or is substituted by OH; or C₁-C₄alkyl which is substituted by -P(O)(OR₁₄)₂;

R₉ and R₁₀ are C₄-C₈alkyl;

R₁₁ is C₁-C₈alkyl or C₂-C₃alkenyl; or is C₃-C₂₀alkyl which is interrupted by -O- and may be substituted by OH;

R₁₄ is C₁-C₄alkyl;

R₁₅ is hydrogen; and

R₁₈ is H, C₁-C₁₈alkyl, phenyl or C₇-C₁₀alkylphenyl.

Of these, particular preference is given to those in which n is 1;

R₁ and R₂, independently of one another, are hydrogen, methyl or methoxy;

R'₁ and R'₂, independently of one another, are hydrogen or methyl;

R₃ and R₄, independently of one another, are H, Cl, C₁-C₄alkyl, allyl, C₁-C₄alkoxy or phenyl;

R₆ is hydrogen;

R_7 and R'_7 are C_1 - C_{18} alkyl or benzyl; or are C_2 - C_6 alkyl which is substituted by OH, C_1 - C_{18} alkoxy, phenoxy, $-COOR_8$ and/or $OCOR_{11}$;
 R_8 is C_1 - C_8 alkyl or C_3 - C_8 alkenyl; and
 R_{11} is C_1 - C_4 alkyl or C_2 - C_3 alkenyl.

A subject-matter of particularly emphasized interest is a mixture of compounds of the formulae I and II in which n is 1;

R_1 and R_2 , independently of one another, are hydrogen, methoxy or methyl;

R'_1 and R'_2 are hydrogen;

R_3 and R_4 , independently of one another, are hydrogen, phenyl, methoxy or methyl;

R_6 is hydrogen;

R_7 and R'_7 , independently of one another, are C_1 - C_{18} alkyl, or a $-CH_2CH(OH)CH_2O-R_{19}$ group; and R_{19} is C_1 - C_{18} alkyl, phenyl or C_3 - C_5 alkenoyl.

The majority of the compounds of the formulae I and II are known; examples of known compounds include 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2,4-dihydroxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis(4-methylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-dodecyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-butoxypropoxy)phenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-octyloxypropoxy)phenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-dodecyloxypropoxy)phenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-tridecyloxypropoxy)phenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine (formula I) or 2,4-bis-(2-hydroxy-4-propoxyphenyl)-6-(2,4-dimethylphenyl)-1,3,5-triazine (formula II).

The compounds of the formulae I and II can be prepared, for example, by or analogously to one of the methods indicated in EP-A-434 608 or in the publication by H. Brunetti and C.E. Lüthi, *Helv. Chim. Acta* 55, 1566 (1972), by Friedel-Crafts addition of halotriazines onto appropriate phenols. This can be followed by a further reaction by known methods to give compounds of the formula I or II in which R_7 is not hydrogen; such reactions and processes are described, for example, in EP-A-434 608, page 15, line 11, to page 17, line 1.

The novel mixtures can be obtained from the individual compounds of the formulae I and II by methods known in the art, for example by premixing, joint grinding or joint crystallization. Premixing by incorporation of the compounds of the formulae I and II into

the substrate to be stabilized is also possible; the incorporation of the individual compounds can be carried out simultaneously or successively, for example by joint extrusion. It is also possible to prepare a mixture of compounds of the formulae I and II by joint synthesis.

The novel mixture of compounds of the formulae I and II can be used as stabilizer for organic materials against damage by light, oxygen or heat. The novel compounds are very particularly suitable as light stabilizers (UV absorbers).

Particular advantages of the novel mixture include the excellent stability of the stabilized material to weathering and light effects, and the excellent photostability of the incorporated stabilizer mixture. The excellent substrate compatibility of the novel mixture is also worthy of mention.

The materials to be stabilized can be, for example, oils, fats, waxes, cosmetics or biocides. Of particular interest is their use in polymeric materials, such as plastics, rubbers, paints, photographic material or adhesives. Examples of polymers and other substrates which can be stabilized in this way are the following:

1. Polymers of monoolefins and diolefins, for example polypropylene, polyisobutylene, polybut-1-ene, poly-4-methylpent-1-ene, polyisoprene or polybutadiene, as well as polymers of cycloolefins, for instance of cyclopentene or norbornene, polyethylene (which optionally can be crosslinked), for example high density polyethylene (HDPE), high density and high molecular weight polyethylene (HDPE-HMW), high density and ultrahigh molecular weight polyethylene (HDPE-UHMW), medium density polyethylene (MDPE), low density polyethylene (LDPE), linear low density polyethylene (LLDPE), branched low density polyethylene (BLDPE).

Polyolefins, i.e. the polymers of monoolefins exemplified in the preceding paragraph, preferably polyethylene and polypropylene, can be prepared by different, and especially by the following, methods:

- a) radical polymerisation (normally under high pressure and at elevated temperature).
- b) catalytic polymerisation using a catalyst that normally contains one or more than one metal of groups IVb, Vb, VIb or VIII of the Periodic Table. These

metals usually have one or more than one ligand, typically oxides, halides, alcoholates, esters, ethers, amines, alkyls, alkenyls and/or aryls that may be either π - or σ -coordinated. These metal complexes may be in the free form or fixed on substrates, typically on activated magnesium chloride, titanium(III) chloride, alumina or silicon oxide. These catalysts may be soluble or insoluble in the polymerisation medium. The catalysts can be used by themselves in the polymerisation or further activators may be used, typically metal alkyls, metal hydrides, metal alkyl halides, metal alkyl oxides or metal alkyloxanes, said metals being elements of groups Ia, IIa and/or IIIa of the Periodic Table. The activators may be modified conveniently with further ester, ether, amine or silyl ether groups. These catalyst systems are usually termed Phillips, Standard Oil Indiana, Ziegler (-Natta), TNZ (DuPont), metallocene or single site catalysts (SSC).

2. Mixtures of the polymers mentioned under 1), for example mixtures of polypropylene with polyisobutylene, polypropylene with polyethylene (for example PP/HDPE, PP/LDPE) and mixtures of different types of polyethylene (for example LDPE/HDPE).
3. Copolymers of monoolefins and diolefins with each other or with other vinyl monomers, for example ethylene/propylene copolymers, linear low density polyethylene (LLDPE) and mixtures thereof with low density polyethylene (LDPE), propylene/but-1-ene copolymers, propylene/isobutylene copolymers, ethylene/but-1-ene copolymers, ethylene/hexene copolymers, ethylene/methylpentene copolymers, ethylene/heptene copolymers, ethylene/octene copolymers, propylene/butadiene copolymers, isobutylene/isoprene copolymers, ethylene/alkyl acrylate copolymers, ethylene/alkyl methacrylate copolymers, ethylene/vinyl acetate copolymers and their copolymers with carbon monoxide or ethylene/acrylic acid copolymers and their salts (ionomers) as well as terpolymers of ethylene with propylene and a diene such as hexadiene, dicyclopentadiene or ethylidene-norbornene; and mixtures of such copolymers with one another and with polymers mentioned in 1) above, for example polypropylene/ethylene-propylene copolymers, LDPE/ethylene-vinyl acetate copolymers (EVA), LDPE/ethylene-acrylic acid copolymers (EAA), LLDPE/EVA, LLDPE/EAA and alternating or random polyalkylene/carbon monoxide copolymers and mixtures thereof with other polymers, for example polyamides.
4. Hydrocarbon resins (for example C₅-C₉) including hydrogenated modifications thereof (e.g. tackifiers) and mixtures of polyalkylenes and starch.

5. Polystyrene, poly(p-methylstyrene), poly(α -methylstyrene).

6. Copolymers of styrene or α -methylstyrene with dienes or acrylic derivatives, for example styrene/butadiene, styrene/acrylonitrile, styrene/alkyl methacrylate, styrene/butadiene/alkyl acrylate, styrene/butadiene/alkyl methacrylate, styrene/maleic anhydride, styrene/acrylonitrile/methyl acrylate; mixtures of high impact strength of styrene copolymers and another polymer, for example a polyacrylate, a diene polymer or an ethylene/propylene/diene terpolymer; and block copolymers of styrene such as styrene/butadiene/styrene, styrene/isoprene/styrene, styrene/ethylene/butylene/styrene or styrene/ethylene/propylene/styrene.

7. Graft copolymers of styrene or α -methylstyrene, for example styrene on polybutadiene, styrene on polybutadiene-styrene or polybutadiene-acrylonitrile copolymers; styrene and acrylonitrile (or methacrylonitrile) on polybutadiene; styrene, acrylonitrile and methyl methacrylate on polybutadiene; styrene and maleic anhydride on polybutadiene; styrene, acrylonitrile and maleic anhydride or maleimide on polybutadiene; styrene and maleimide on polybutadiene; styrene and alkyl acrylates or methacrylates on polybutadiene; styrene and acrylonitrile on ethylene/propylene/diene terpolymers; styrene and acrylonitrile on polyalkyl acrylates or polyalkyl methacrylates, styrene and acrylonitrile on acrylate/butadiene copolymers, as well as mixtures thereof with the copolymers listed under 6), for example the copolymer mixtures known as ABS, MBS, ASA or AES polymers.

8. Halogen-containing polymers such as polychloroprene, chlorinated rubbers, chlorinated and brominated copolymer of isobutylene-isoprene (halobutyl rubber), chlorinated or sulfochlorinated polyethylene, copolymers of ethylene and chlorinated ethylene, epichlorohydrin homo- and copolymers, especially polymers of halogen-containing vinyl compounds, for example polyvinyl chloride, polyvinylidene chloride, polyvinyl fluoride, polyvinylidene fluoride, as well as copolymers thereof such as vinyl chloride/vinylidene chloride, vinyl chloride/vinyl acetate or vinylidene chloride/vinyl acetate copolymers.

9. Polymers derived from α,β -unsaturated acids and derivatives thereof such as polyacrylates and polymethacrylates; polymethyl methacrylates, polyacrylamides and polyacrylonitriles, impact-modified with butyl acrylate.

10. Copolymers of the monomers mentioned under 9) with each other or with other unsaturated monomers, for example acrylonitrile/butadiene copolymers, acrylonitrile/alkyl acrylate copolymers, acrylonitrile/alkoxyalkyl acrylate or acrylonitrile/vinyl halide

copolymers or acrylonitrile/ alkyl methacrylate/butadiene terpolymers.

11. Polymers derived from unsaturated alcohols and amines or the acyl derivatives or acetals thereof, for example polyvinyl alcohol, polyvinyl acetate, polyvinyl stearate, polyvinyl benzoate, polyvinyl maleate, polyvinyl butyral, polyallyl phthalate or polyallyl melamine; as well as their copolymers with olefins mentioned in 1) above.

12. Homopolymers and copolymers of cyclic ethers such as polyalkylene glycols, polyethylene oxide, polypropylene oxide or copolymers thereof with bisglycidyl ethers.

13. Polyacetals such as polyoxymethylene and those polyoxymethylenes which contain ethylene oxide as a comonomer; polyacetals modified with thermoplastic polyurethanes, acrylates or MBS.

14. Polyphenylene oxides and sulfides, and mixtures of polyphenylene oxides with styrene polymers or polyamides.

15. Polyurethanes derived from hydroxyl-terminated polyethers, polyesters or polybutadienes on the one hand and aliphatic or aromatic polyisocyanates on the other, as well as precursors thereof.

16. Polyamides and copolyamides derived from diamines and dicarboxylic acids and/or from aminocarboxylic acids or the corresponding lactams, for example polyamide 4, polyamide 6, polyamide 6/6, 6/10, 6/9, 6/12, 4/6, 12/12, polyamide 11, polyamide 12, aromatic polyamides starting from m-xylene diamine and adipic acid; polyamides prepared from hexamethylenediamine and isophthalic or/and terephthalic acid and with or without an elastomer as modifier, for example poly-2,4,4,-trimethylhexamethylene terephthalamide or poly-m-phenylene isophthalamide; and also block copolymers of the aforementioned polyamides with polyolefins, olefin copolymers, ionomers or chemically bonded or grafted elastomers; or with polyethers, e.g. with polyethylene glycol, polypropylene glycol or polytetramethylene glycol; as well as polyamides or copolyamides modified with EPDM or ABS; and polyamides condensed during processing (RIM polyamide systems).

17. Polyureas, polyimides, polyamide-imides, polyetherimids, polyesterimids, polyhydantoins and polybenzimidazoles.

18. Polyesters derived from dicarboxylic acids and diols and/or from hydroxycarboxylic

acids or the corresponding lactones, for example polyethylene terephthalate, polybutylene terephthalate, poly-1,4-dimethylcyclohexane terephthalate and polyhydroxybenzoates, as well as block copolyether esters derived from hydroxyl-terminated polyethers; and also polyesters modified with polycarbonates or MBS.

19. Polycarbonates and polyester carbonates.

20. Polysulfones, polyether sulfones and polyether ketones.

21. Crosslinked polymers derived from aldehydes on the one hand and phenols, ureas and melamines on the other hand, such as phenol/formaldehyde resins, urea/formaldehyde resins and melamine/formaldehyde resins.

22. Drying and non-drying alkyd resins.

23. Unsaturated polyester resins derived from copolyesters of saturated and unsaturated dicarboxylic acids with polyhydric alcohols and vinyl compounds as crosslinking agents, and also halogen-containing modifications thereof of low flammability.

24. Crosslinkable acrylic resins derived from substituted acrylates, for example epoxy acrylates, urethane acrylates or polyester acrylates.

25. Alkyd resins, polyester resins and acrylate resins crosslinked with melamine resins, urea resins, isocyanates, isocyanurates, polyisocyanates or epoxy resins.

26. Crosslinked epoxy resins derived from aliphatic, cycloaliphatic, heterocyclic or aromatic glycidyl compounds, e.g. products of diglycidyl ethers of bisphenol A and bisphenol F, which are crosslinked with customary hardeners such as anhydrides or amines, with or without accelerators.

27. Natural polymers such as cellulose, rubber, gelatin and chemically modified homologous derivatives thereof, for example cellulose acetates, cellulose propionates and cellulose butyrates, or the cellulose ethers such as methyl cellulose; as well as rosins and their derivatives.

28. Blends of the aforementioned polymers (polyblends), for example PP/EPDM, Polyamide/EPDM or ABS, PVC/EVA, PVC/ABS, PVC/MBS, PC/ABS, PBTP/ABS,

PC/ASA, PC/PBT, PVC/CPE, PVC/acrylates, POM/thermoplastic PUR, PC/thermoplastic PUR, POM/acrylate, POM/MBS, PPO/HIPS, PPO/PA 6.6 and copolymers, PA/HDPE, PA/PP, PA/PPO, PBT/PC/ABS or PBT/PET/PC.

The invention therefore also relates to a composition comprising

A) an organic material which is sensitive to damage by light, oxygen and/or heat, and
B) as stabilizer, a mixture comprising a compound of the formula I and a compound of the formula II.

The invention also relates to a process for stabilizing organic material against damage by light, oxygen and/or heat, which comprises adding thereto, as stabilizer, a mixture comprising a compound of the formula I and a compound of the formula II, and to the use of a mixture comprising a compound of the formula I and a compound of the formula II for stabilizing organic material.

The amount of stabilizer to be used depends on the organic material to be stabilized and on the intended use of the stabilized material. In general, the novel composition comprises from 0.01 to 15 parts by weight, in particular from 0.05 to 10 parts by weight, especially from 0.05 to 5 parts by weight, of the stabilizer (component B) per 100 parts by weight of component A.

The stabilizer (component B) can also be a mixture of three or more compounds, with the proviso that at least one compound of the type of the formula I and at least one compound of the type of the formula II are present. In addition to the novel compound mixture, the novel compositions can also comprise other stabilizers or other additives, for example antioxidants, further light stabilizers, metal deactivators, phosphites or phosphonites. Examples of these stabilizers are the following:

1. Antioxidants

1.1. Alkylated monophenols, for example 2,6-di-tert-butyl-4-methylphenol, 2-tert-butyl-4,6-dimethylphenol, 2,6-di-tert-butyl-4-ethylphenol, 2,6-di-tert-butyl-4-n-butylphenol, 2,6-di-tert-butyl-4-isobutylphenol, 2,6-dicyclopentyl-4-methylphenol, 2-(α -methylcyclohexyl)-4,6-dimethylphenol, 2,6-dioctadecyl-4-methylphenol, 2,4,6-tricyclohexylphenol, 2,6-di-tert-butyl-4-methoxymethylphenol, nonylphenols which are linear or branched in the side chains, for example, 2,6-di-nonyl-4-methylphenol, 2,4-dimethyl-6-(1'-methylundec-1'-yl)phenol, 2,4-dimethyl-6-(1'-methylheptadec-1'-yl)phenol, 2,4-dimethyl-6-(1'-

methyltridec-1'-yl)phenol and mixtures thereof.

1.2. Alkylthiomethylphenols, for example 2,4-dioctylthiomethyl-6-tert-butylphenol, 2,4-dioctylthiomethyl-6-methylphenol, 2,4-dioctylthiomethyl-6-ethylphenol, 2,6-didodecylthiomethyl-4-nonylphenol.

1.3. Hydroquinones and alkylated hydroquinones, for example 2,6-di-tert-butyl-4-methoxyphenol, 2,5-di-tert-butylhydroquinone, 2,5-di-tert-amylhydroquinone, 2,6-diphenyl-4-octadecyloxyphenol, 2,6-di-tert-butylhydroquinone, 2,5-di-tert-butyl-4-hydroxyanisole, 3,5-di-tert-butyl-4-hydroxyanisole, 3,5-di-tert-butyl-4-hydroxyphenyl stearate, bis-(3,5-di-tert-butyl-4-hydroxyphenyl) adipate.

1.4. Tocopherols, for example α -tocopherol, β -tocopherol, γ -tocopherol, δ -tocopherol and mixtures thereof (Vitamin E).

1.5. Hydroxylated thiodiphenyl ethers, for example 2,2'-thiobis(6-tert-butyl-4-methylphenol), 2,2'-thiobis(4-octylphenol), 4,4'-thiobis(6-tert-butyl-3-methylphenol), 4,4'-thiobis(6-tert-butyl-2-methylphenol), 4,4'-thiobis-(3,6-di-sec-amylphenol), 4,4'-bis-(2,6-dimethyl-4-hydroxyphenyl) disulfide.

1.6. Alkylidenebisphenols, for example 2,2'-methylenebis(6-tert-butyl-4-methylphenol), 2,2'-methylenebis(6-tert-butyl-4-ethylphenol), 2,2'-methylenebis[4-methyl-6-(α -methylcyclohexyl)phenol], 2,2'-methylenebis(4-methyl-6-cyclohexylphenol), 2,2'-methylenebis(6-nonyl-4-methylphenol), 2,2'-methylenebis(4,6-di-tert-butylphenol), 2,2'-ethylidenebis(4,6-di-tert-butylphenol), 2,2'-ethylidenebis(6-tert-butyl-4-isobutylphenol), 2,2'-methylenebis[6-(α -methylbenzyl)-4-nonylphenol], 2,2'-methylenebis[6-(α,α -dimethylbenzyl)-4-nonylphenol], 4,4'-methylenebis(2,6-di-tert-butylphenol), 4,4'-methylenebis(6-tert-butyl-2-methylphenol), 1,1-bis(5-tert-butyl-4-hydroxy-2-methylphenyl)butane, 2,6-bis(3-tert-butyl-5-methyl-2-hydroxybenzyl)-4-methylphenol, 1,1,3-tris(5-tert-butyl-4-hydroxy-2-methylphenyl)butane, 1,1-bis(5-tert-butyl-4-hydroxy-2-methylphenyl)-3-n-dodecylmercaptobutane, ethylene glycol bis[3,3-bis(3'-tert-butyl-4'-hydroxyphenyl)butyrate], bis(3-tert-butyl-4-hydroxy-5-methylphenyl)dicyclopentadiene, bis[2-(3'-tert-butyl-2'-hydroxy-5'-methylbenzyl)-6-tert-butyl-4-methylphenyl]terephthalate, 1,1-bis-(3,5-dimethyl-2-hydroxyphenyl)butane, 2,2-bis-(3,5-di-tert-butyl-4-hydroxyphenyl)propane, 2,2-bis-(5-tert-butyl-4-hydroxy-2-methylphenyl)-4-n-dodecylmercaptobutane, 1,1,5,5-tetra-(5-tert-butyl-4-hydroxy-2-methylphenyl)pentane.

1.7. O-, N- and S-benzyl compounds, for example 3,5,3',5'-tetra-tert-butyl-4,4'-dihydroxydibenzyl ether, octadecyl-4-hydroxy-3,5-dimethylbenzylmercaptoacetate, tridecyl-4-hydroxy-3,5-di-tert-butylbenzylmercaptoacetate, tris(3,5-di-tert-butyl-4-hydroxybenzyl)amine, bis(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl)dithioterephthalate, bis(3,5-di-tert-butyl-4-hydroxybenzyl)sulfide, isooctyl-3,5-di-tert-butyl-4-hydroxybenzylmercaptoacetate.

1.8. Hydroxybenzylated malonates, for example dioctadecyl-2,2-bis-(3,5-di-tert-butyl-2-hydroxybenzyl)-malonate, di-octadecyl-2-(3-tert-butyl-4-hydroxy-5-methylbenzyl)-malonate, di-dodecylmercaptoethyl-2,2-bis-(3,5-di-tert-butyl-4-hydroxybenzyl)malonate, bis-[4-(1,1,3,3-tetramethylbutyl)phenyl]-2,2-bis(3,5-di-tert-butyl-4-hydroxybenzyl)malonate.

1.9. Aromatic hydroxybenzyl compounds, for example 1,3,5-tris-(3,5-di-tert-butyl-4-hydroxybenzyl)-2,4,6-trimethylbenzene, 1,4-bis(3,5-di-tert-butyl-4-hydroxybenzyl)-2,3,5,6-tetramethylbenzene, 2,4,6-tris(3,5-di-tert-butyl-4-hydroxybenzyl)phenol.

1.10. Triazine Compounds, for example 2,4-bis(octylmercapto)-6-(3,5-di-tert-butyl-4-hydroxyanilino)-1,3,5-triazine, 2-octylmercapto-4,6-bis(3,5-di-tert-butyl-4-hydroxyanilino)-1,3,5-triazine, 2-octylmercapto-4,6-bis(3,5-di-tert-butyl-4-hydroxyphenoxy)-1,3,5-triazine, 2,4,6-tris(3,5-di-tert-butyl-4-hydroxyphenoxy)-1,2,3-triazine, 1,3,5-tris(3,5-di-tert-butyl-4-hydroxybenzyl)isocyanurate, 1,3,5-tris(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl)isocyanurate, 2,4,6-tris(3,5-di-tert-butyl-4-hydroxyphenylethyl)-1,3,5-triazine, 1,3,5-tris(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)-hexahydro-1,3,5-triazine, 1,3,5-tris(3,5-dicyclohexyl-4-hydroxybenzyl)isocyanurate.

1.11. Benzylphosphonates, for example dimethyl-2,5-di-tert-butyl-4-hydroxybenzylphosphonate, diethyl-3,5-di-tert-butyl-4-hydroxybenzylphosphonate, dioctadecyl-3,5-di-tert-butyl-4-hydroxybenzylphosphonate, dioctadecyl-5-tert-butyl-4-hydroxy-3-methylbenzylphosphonate, the calcium salt of the monoethyl ester of 3,5-di-tert-butyl-4-hydroxybenzylphosphonic acid.

1.12. Acylaminophenols, for example 4-hydroxylauranilide, 4-hydroxystearanilide, octyl N-(3,5-di-tert-butyl-4-hydroxyphenyl)carbamate.

1.13. Esters of β -(3,5-di-tert-butyl-4-hydroxyphenyl)propionic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, n-octanol, i-octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl) isocyanu-

rate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.

1.14. Esters of β -(5-tert-butyl-4-hydroxy-3-methylphenyl)propionic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, n-octanol, i-octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl)isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.

1.15. Esters of β -(3,5-dicyclohexyl-4-hydroxyphenyl)propionic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl)isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.

1.16. Esters of 3,5-di-tert-butyl-4-hydroxyphenyl acetic acid with mono- or polyhydric alcohols, e.g. with methanol, ethanol, octanol, octadecanol, 1,6-hexanediol, 1,9-nonanediol, ethylene glycol, 1,2-propanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl)isocyanurate, N,N'-bis(hydroxyethyl)oxamide, 3-thiaundecanol, 3-thiapentadecanol, trimethylhexanediol, trimethylolpropane, 4-hydroxymethyl-1-phospha-2,6,7-trioxabicyclo[2.2.2]octane.

1.17. Amides of β -(3,5-di-tert-butyl-4-hydroxyphenyl)propionic acid e.g. N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)hexamethylenediamine, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)trimethylenediamine, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)hydrazine.

1.18. Ascorbic acid (vitamin C)

1.19. Aminic antioxidants, for example N,N'-di-isopropyl-p-phenylenediamine, N,N'-di-sec-butyl-p-phenylenediamine, N,N'-bis(1,4-dimethylpentyl)-p-phenylenediamine, N,N'-bis(1-ethyl-3-methylpentyl)-p-phenylenediamine, N,N'-bis(1-methylheptyl)-p-phenylenediamine, N,N'-dicyclohexyl-p-phenylenediamine, N,N'-diphenyl-p-phenylenediamine,

N,N'-bis(2-naphthyl)-p-phenylenediamine, N-isopropyl-N'-phenyl-p-phenylenediamine, N-(1,3-dimethylbutyl)-N'-phenyl-p-phenylenediamine, N-(1-methylheptyl)-N'-phenyl-p-phenylenediamine, N-cyclohexyl-N'-phenyl-p-phenylenediamine, 4-(p-toluenesulfamoyl)-diphenylamine, N,N'-dimethyl-N,N'-di-sec-butyl-p-phenylenediamine, diphenylamine, N-allyldiphenylamine, 4-isopropoxydiphenylamine, N-phenyl-1-naphthylamine, N-(4-tert-octylphenyl)-1-naphthylamine, N-phenyl-2-naphthylamine, octylated diphenylamine, for example p,p'-di-tert-octyldiphenylamine, 4-n-butylaminophenol, 4-butyrylaminophenol, 4-nonanoylamino-phenol, 4-dodecanoylamino-phenol, 4-octadecanoylamino-phenol, bis(4-methoxyphenyl)amine, 2,6-di-tert-butyl-4-dimethylaminomethylphenol, 2,4'-diaminodiphenylmethane, 4,4'-diaminodiphenylmethane, N,N,N',N'-tetramethyl-4,4'-diaminodiphenylmethane, 1,2-bis[(2-methylphenyl)amino]ethane, 1,2-bis(phenylamino)propane, (o-tolyl)biguanide, Bis[4-(1',3'-dimethylbutyl)phenyl]amine, tert-octylated N-phenyl-1-naphthylamine, a mixture of mono- and dialkylated tert-butyl/tert-octyldiphenylamines, a mixture of mono- and dialkylated nonyldiphenylamines, a mixture of mono- and dialkylated dodecyldiphenylamines, a mixture of mono- and dialkylated isopropyl/isohexyldiphenylamines, a mixture of mono- und dialkylated tert-butyl-diphenylamines, 2,3-dihydro-3,3-dimethyl-4H-1,4-benzothiazine, phenothiazine, a mixture of mono- und dialkylated tert-butyl/tert-octylphenothiazines, a mixture of mono- und dialkylated tert-octylphenothiazines, N-allylphenothiazin, N,N,N',N'-tetraphenyl-1,4-diaminobut-2-ene, N,N-bis(2,2,6,6-tetramethyl-piperid-4-yl)-hexamethylenediamine, bis(2,2,6,6-tetramethylpiperid-4-yl)sebacate, 2,2,6,6-tetramethylpiperidin-4-one, 2,2,6,6-tetramethylpiperidin-4-ol.

2. UV absorbers and light stabilisers

2.1. 2-(2'-Hydroxyphenyl)benzotriazoles, for example 2-(2'-hydroxy-5'-methylphenyl)-benzotriazole, 2-(3',5'-di-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(5'-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(2'-hydroxy-5'-(1,1,3,3-tetramethylbutyl)phenyl)benzotriazole, 2-(3',5'-di-tert-butyl-2'-hydroxyphenyl)-5-chloro-benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-methylphenyl)-5-chloro-benzotriazole, 2-(3'-sec-butyl-5'-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(2'-hydroxy-4'-octyloxyphenyl)benzotriazole, 2-(3',5'-di-tert-amyl-2'-hydroxyphenyl)benzotriazole, 2-(3',5'-bis-(α,α -dimethylbenzyl)-2'-hydroxyphenyl)benzotriazole, mixture of 2-(3'-tert-butyl-2'-hydroxy-5'-(2-octyloxycarbonylethyl)phenyl)-5-chloro-benzotriazole, 2-(3'-tert-butyl-5'-[2-(2-ethylhexyloxy)-carbonylethyl]-2'-hydroxyphenyl)-5-chloro-benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-methoxycarbonylethyl)phenyl)-5-chloro-benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-methoxycarbonylethyl)phenyl)benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-octyloxycarbonylethyl)phenyl)benzotriazole, 2-(3'-tert-butyl-5'-[2-(2-ethylhexyloxy)carbonyl-

ethyl]-2'-hydroxyphenyl)benzotriazole, 2-(3'-dodecyl-2'-hydroxy-5'-methylphenyl)benzotriazole, and 2-(3'-tert-butyl-2'-hydroxy-5'-(2-isooctyloxycarbonylethyl)phenyl)benzotriazole, 2,2'-methylene-bis[4-(1,1,3,3-tetramethylbutyl)-6-benzotriazole-2-ylphenol]; the transesterification product of 2-[3'-tert-butyl-5'-(2-methoxycarbonylethyl)-2'-hydroxyphenyl]-2H-benzotriazole with polyethylene glycol 300; $[R-CH_2CH_2-COO(CH_2)_3]_n$, where R = 3'-tert-butyl-4'-hydroxy-5'-2H-benzotriazol-2-ylphenyl.

2.2. 2-Hydroxybenzophenones, for example the 4-hydroxy, 4-methoxy, 4-octyloxy, 4-decyloxy, 4-dodecyloxy, 4-benzyloxy, 4,2',4'-trihydroxy and 2'-hydroxy-4,4'-dimethoxy derivatives.

2.3. Esters of substituted and unsubstituted benzoic acids, as for example 4-tertbutylphenyl salicylate, phenyl salicylate, octylphenyl salicylate, dibenzoyl resorcinol, bis(4-tert-butylbenzoyl) resorcinol, benzoyl resorcinol, 2,4-di-tertbutylphenyl 3,5-di-tert-butyl-4-hydroxybenzoate, hexadecyl 3,5-di-tert-butyl-4-hydroxybenzoate, octadecyl 3,5-di-tert-butyl-4-hydroxybenzoate, 2-methyl-4,6-di-tert-butylphenyl 3,5-di-tert-butyl-4-hydroxybenzoate.

2.4. Acrylates, for example ethyl α -cyano- β,β -diphenylacrylate, isooctyl α -cyano- β,β -diphenylacrylate, methyl α -carbomethoxycinnamate, methyl α -cyano- β -methyl-p-methoxycinnamate, butyl α -cyano- β -methyl-p-methoxy-cinnamate, methyl α -carbomethoxy-p-methoxycinnamate and N-(β -carbomethoxy- β -cyanovinyl)-2-methylindoline.

2.5. Nickel compounds, for example nickel complexes of 2,2'-thio-bis-[4-(1,1,3,3-tetramethylbutyl)phenol], such as the 1:1 or 1:2 complex, with or without additional ligands such as n-butylamine, triethanolamine or N-cyclohexyldiethanolamine, nickel dibutyldithiocarbamate, nickel salts of the monoalkyl esters, e.g. the methyl or ethyl ester, of 4-hydroxy-3,5-di-tert-butylbenzylphosphonic acid, nickel complexes of ketoximes, e.g. of 2-hydroxy-4-methylphenyl undecylketoxime, nickel complexes of 1-phenyl-4-lauroyl-5-hydroxypyrazole, with or without additional ligands.

2.6. Sterically hindered amines, for example bis(2,2,6,6-tetramethyl-4-piperidyl)sebacate, bis(2,2,6,6-tetramethyl-4-piperidyl)succinate, bis(1,2,2,6,6-pentamethyl-4-piperidyl)sebacate, bis(1-octyloxy-2,2,6,6-tetramethyl-4-piperidyl)sebacate, bis(1,2,2,6,6-pentamethyl-4-piperidyl) n-butyl-3,5-di-tert-butyl-4-hydroxybenzylmalonate, the condensate of 1-(2-hydroxyethyl)-2,2,6,6-tetramethyl-4-hydroxypiperidine and succi-

nic acid,

the condensate of N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-tert-octylamino-2,6-dichloro-1,3,5-triazine,

tris(2,2,6,6-tetramethyl-4-piperidyl)nitrioltriacetate,

tetrakis(2,2,6,6-tetramethyl-4-piperidyl)-1,2,3,4-butane-tetracarboxylate,

1,1'-(1,2-ethanediyl)bis(3,3,5,5-tetramethylpiperazinone),

4-benzoyl-2,2,6,6-tetramethylpiperidine,

4-stearyloxy-2,2,6,6-tetramethylpiperidine,

bis(1,2,2,6,6-pentamethylpiperidyl)-2-n-butyl-2-(2-hydroxy-3,5-di-tert-butyl-benzyl)malonate,

3-n-octyl-7,7,9,9-tetramethyl-1,3,8-triazaspiro[4.5]decan-2,4-dion,

bis(1-octyloxy-2,2,6,6-tetramethylpiperidyl)sebacate,

bis(1-octyloxy-2,2,6,6-tetramethylpiperidyl)succinate,

the condensate of N,N'-bis-(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-morpholino-2,6-dichloro-1,3,5-triazine,

the condensate of 2-chloro-4,6-bis(4-n-butylamino-2,2,6,6-tetramethylpiperidyl)-1,3,5-triazine and 1,2-bis(3-aminopropylamino)ethane,

the condensate of 2-chloro-4,6-di-(4-n-butylamino-1,2,2,6,6-pentamethylpiperidyl)-1,3,5-triazine and 1,2-bis-(3-aminopropylamino)ethane,

8-acetyl-3-dodecyl-7,7,9,9-tetramethyl-1,3,8-triazaspiro[4.5]decane-2,4-dione,

3-dodecyl-1-(2,2,6,6-tetramethyl-4-piperidyl)pyrrolidin-2,5-dione,

3-dodecyl-1-(1,2,2,6,6-pentamethyl-4-piperidyl)pyrrolidine-2,5-dione,

a mixture of 4-hexadecyloxy- and 4-stearyloxy-2,2,6,6-tetramethylpiperidine,

a condensation product of N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-cyclohexylamino-2,6-dichloro-1,3,5-triazine,

a condensation product of 1,2-bis(3-aminopropylamino)ethane and 2,4,6-trichloro-1,3,5-triazine as well as 4-butylamino-2,2,6,6-tetramethylpiperidine (CAS Reg. No. [136504-96-6]);

N-(2,2,6,6-tetramethyl-4-piperidyl)-n-dodecylsuccinimid,

N-(1,2,2,6,6-pentamethyl-4-piperidyl)-n-dodecylsuccinimid,

2-undecyl-7,7,9,9-tetramethyl-1-oxa-3,8-diaza-4-oxo-spiro[4,5]decane,

a reaction product of 7,7,9,9-tetramethyl-2-cycloundecyl-1-oxa-3,8-diaza-4-oxospiro[4,5]decane and epichlorohydrin,

propanedioic acid (4-methoxyphenyl)-methylene-bis(1,2,2,6,6-pentamethyl-4-piperidyl) ester,

N,N'-bis-formyl-N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)-hexamethylenediamine,

poly-[methylpropyl-3-oxy-4-(2,2,6,6-tetramethyl-4-piperidyl)]-siloxane,

a reaction product of maleic acid- α -olefin copolymer and 2,2,6,6-tetramethyl-4-aminopiperidine or 1,2,2,6,6-pentamethyl-4-aminopiperidine.

2.7. Oxamides, for example 4,4'-dioctyloxyoxanilide, 2,2'-diethoxyoxanilide, 2,2'-dioctyloxy-5,5'-di-tert-butoxanilide, 2,2'-didodecyloxy-5,5'-di-tert-butoxanilide, 2-ethoxy-2'-ethyloxanilide, N,N'-bis(3-dimethylaminopropyl)oxamide, 2-ethoxy-5-tert-butyl-2'-ethoxanilide and its mixture with 2-ethoxy-2'-ethyl-5,4'-di-tert-butoxanilide and mixtures of ortho- and para-methoxy-disubstituted oxanilides and mixtures of o- and p-ethoxy-disubstituted oxanilides.

2.8. 2-(2-Hydroxyphenyl)-1,3,5-triazines, for example 2,4,6-tris(2-hydroxy-4-octyloxyphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2,4-dihydroxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2,4-bis(2-hydroxy-4-propyloxyphenyl)-6-(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis(4-methylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-dodecyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-tridecyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-butyloxy-propoxy)phenyl]-4,6-bis(2,4-dimethyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-octyloxy-propyloxy)phenyl]-4,6-bis(2,4-dimethyl)-1,3,5-triazine, 2-[4-(dodecyloxy/tridecyloxy-2-hydroxypropoxy)-2-hydroxy-phenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-dodecyloxy-propoxy)phenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-hexyloxy)phenyl-4,6-diphenyl-1,3,5-triazine, 2-(2-hydroxy-4-methoxyphenyl)-4,6-diphenyl-1,3,5-triazine, 2,4,6-tris[2-hydroxy-4-(3-butoxy-2-hydroxy-propoxy)phenyl]-1,3,5-triazine, 2-(2-hydroxyphenyl)-4-(4-methoxyphenyl)-6-phenyl-1,3,5-triazine.

3. Metal deactivators, for example N,N'-diphenyloxamide, N-salicylal-N'-salicyloyl hydrazine, N,N'-bis(salicyloyl) hydrazine, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenyl-propionyl) hydrazine, 3-salicyloylamino-1,2,4-triazole, bis(benzylidene)oxalyl dihydrazide, oxanilide, isophthaloyl dihydrazide, sebacoyl bisphenylhydrazide, N,N'-diacetyladiopoyl dihydrazide, N,N'-bis(salicyloyl)oxalyl dihydrazide, N,N'-bis(salicyloyl)-thiopropionyl dihydrazide.

4. Phosphites and phosphonites, for example triphenyl phosphite, diphenyl alkyl phosphites, phenyl dialkyl phosphites, tris(nonylphenyl) phosphite, trilauryl phosphite, trioctadecyl phosphite, distearyl pentaerythritol diphosphite, tris(2,4-di-tert-butylphenyl) phos-

phite, diisodecyl pentaerythritol diphosphite, bis(2,4-di-tert-butylphenyl) pentaerythritol diphosphite, bis(2,6-di-tert-butyl-4-methylphenyl)-pentaerythritol diphosphite, diisodecyl-oxy-pentaerythritol diphosphite, bis(2,4-di-tert-butyl-6-methylphenyl)pentaerythritol diphosphite, bis(2,4,6-tris(tert-butylphenyl)pentaerythritol diphosphite, tristearyl sorbitol triphosphite, tetrakis(2,4-di-tert-butylphenyl) 4,4'-biphenylene diphosphonite, 6-isooctyl-oxy-2,4,8,10-tetra-tert-butyl-12H-dibenz[d,g]-1,3,2-dioxaphosphocin, 6-fluoro-2,4,8,10-tetra-tert-butyl-12-methyl-dibenz[d,g]-1,3,2-dioxaphosphocin, bis(2,4-di-tert-butyl-6-methylphenyl)methylphosphite, bis(2,4-di-tert-butyl-6-methylphenyl)ethylphosphite.

5. Hydroxylamines, for example, N,N-dibenzylhydroxylamine, N,N-diethylhydroxylamine, N,N-dioctylhydroxylamine, N,N-dilaurylhydroxylamine, N,N-ditetradecylhydroxylamine, N,N-dihexadecylhydroxylamine, N,N-dioctadecylhydroxylamine, N-hexadecyl-N-octadecylhydroxylamine, N-heptadecyl-N-octadecylhydroxylamine, N,N-dialkylhydroxylamine derived from hydrogenated tallow amine.

6. Nitrones, for example, N-benzyl-alpha-phenyl-nitron, N-ethyl-alpha-methyl-nitron, N-octyl-alpha-heptyl-nitron, N-lauryl-alpha-undecyl-nitron, N-tetradecyl-alpha-tridecyl-nitron, N-hexadecyl-alpha-pentadecyl-nitron, N-octadecyl-alpha-heptadecyl-nitron, N-hexadecyl-alpha-heptadecyl-nitron, N-octadecyl-alpha-pentadecyl-nitron, N-heptadecyl-alpha-heptadecyl-nitron, N-octadecyl-alpha-hexadecyl-nitron, nitron derived from N,N-dialkylhydroxylamine derived from hydrogenated tallow amine.

7. Thiosynergists, for example, dilauryl thiodipropionate or distearyl thiodipropionate.

8. Peroxide scavengers, for example esters of β -thiodipropionic acid, for example the lauryl, stearyl, myristyl or tridecyl esters, mercaptobenzimidazole or the zinc salt of 2-mercaptobenzimidazole, zinc dibutyldithiocarbamate, dioctadecyl disulfide, pentaerythritol tetrakis(β -dodecylmercapto)propionate.

9. Polyamide stabilisers, for example, copper salts in combination with iodides and/or phosphorus compounds and salts of divalent manganese.

10. Basic co-stabilisers, for example, melamine, polyvinylpyrrolidone, dicyandiamide, triallyl cyanurate, urea derivatives, hydrazine derivatives, amines, polyamides, polyurethanes, alkali metal salts and alkaline earth metal salts of higher fatty acids for example calcium stearate, zinc stearate, magnesium behenate, magnesium stearate, sodium ricinoleate and potassium palmitate, antimony pyrocatecholate or tin pyrocatecholate.

11. Nucleating agents, for example, inorganic substances such as talcum, metal oxides such as titanium dioxide or magnesium oxide, phosphates, carbonates or sulfates of, preferably, alkaline earth metals; organic compounds such as mono- or polycarboxylic acids and the salts thereof, e.g. 4-tert-butylbenzoic acid, adipic acid, diphenylacetic acid, sodium succinate or sodium benzoate; polymeric compounds such as ionic copolymers ("ionomers").

12. Fillers and reinforcing agents, for example, calcium carbonate, silicates, glass fibres, glass bulbs, asbestos, talc, kaolin, mica, barium sulfate, metal oxides and hydroxides, carbon black, graphite, wood flour and flours or fibers of other natural products, synthetic fibers.

13. Other additives, for example, plasticisers, lubricants, emulsifiers, pigments, rheology additives, catalysts, flow-control agents, optical brighteners, flameproofing agents, antistatic agents and blowing agents.

14. Benzofuranones and indolinones, for example those disclosed in US-A-4 325 863, US-A-4 338 244, US-A-5 175 312, US-A-5 216 052, US-A-5 252 643, DE-A-4 316 611, DE-A-4 316 622, DE-A-4 316 876, EP-A-0 589 839 or EP-A-0 591 102 or 3-[4-(2-acetoxyethoxy)phenyl]-5,7-di-tert-butyl-benzofuran-2-one, 5,7-di-tert-butyl-3-[4-(2-stearoyloxyethoxy)phenyl]benzofuran-2-one, 3,3'-bis[5,7-di-tert-butyl-3-(4-[2-hydroxyethoxy]phenyl)benzofuran-2-one], 5,7-di-tert-butyl-3-(4-ethoxyphenyl)benzofuran-2-one, 3-(4-acetoxy-3,5-dimethylphenyl)-5,7-di-tert-butyl-benzofuran-2-one, 3-(3,5-dimethyl-4-pivaloyloxyphenyl)-5,7-di-tert-butyl-benzofuran-2-one.

The type and amount of the further stabilizers added is determined by the type of substrate to be stabilized and on its intended use; frequently, from 0.1 to 5 % by weight, based on the polymer to be stabilized, are used.


The novel stabilizer mixture can particularly advantageously be employed in compositions in which component A is a synthetic organic polymer, in particular a thermoplastic polymer, a binder for surface coatings, for example paints, or a photographic material. Examples of thermoplastic polymers are polyolefins and polymers containing hetero atoms in the main chain. Preference is also given to compositions in which component A is a thermoplastic polymer containing nitrogen, oxygen and/or sulfur, in particular nitrogen or oxygen, in the main chain. Examples of such polymers are the following


classes of thermoplastic polymers:

1. Polyacetals, such as polyoxymethylene, and polyoxymethylenes containing comonomers, for example ethylene oxide; polyacetals which have been modified with thermoplastic polyurethanes, acrylates or MBS.
2. Polyphenylene oxides and sulfides, and mixtures thereof with styrene polymers or polyamides.
3. Polyamides and copolyamides, for example those derived from diamines and dicarboxylic acids and/or from aminocarboxylic acids or the corresponding lactams, such as nylon 4, nylon 6, nylon 6/6, 6/10, 6/9, 6/12, 4/6, nylon 11, nylon 12, aromatic polyamides derived from m-xylene, diamine and adipic acid; polyamides prepared from hexamethylenediamine and iso- and/or terephthalic acid and, if desired, an elastomer as modifier, for example poly-2,4,4-trimethylhexamethyleneterephthalamide, poly-m-phenyleneisophthalamide; block copolymers of the abovementioned polyamides with polyolefins, olefin copolymers, ionomers or chemically bonded or grafted elastomers; or with polyethers, for example with polyethylene glycol, polypropylene glycol or polytetramethylene glycol; furthermore polyamides or copolyamides modified with EPDM or ABS; and polyamides condensed during processing ("RIM polyamide systems").
4. Polyureas, polyimides, polyamide-imides and polybenzimidazoles.
5. Polyesters, for example those derived from dicarboxylic acids and dialcohols and/or from hydroxycarboxylic acids or the corresponding lactones, such as polyethylene terephthalate, polybutylene terephthalate, poly-1,4-dimethylolcyclohexane terephthalate, polyhydroxybenzoates, and block polyether-esters derived from polyethers containing hydroxyl terminal groups; furthermore polyesters modified with polycarbonates or MBS.
6. Polycarbonates and polyester carbonates, in particular aromatic polycarbonates, for example those based on 2,2-bis(4-hydroxyphenyl)propane or 1,1-bis(4-hydroxyphenyl)cyclohexane.
7. Polysulfones, polyether sulfones and polyether ketones, in particular aromatic polymers from this class.

8. Mixtures (polyblends) of such polymers with one another or with other polymers, for example with polyolefins, polyacrylates, polydienes or other elastomers as impact modifiers.

Of these, preference is given to polycarbonates, polyesters, polyamides, polyacetals, polyphenylene oxides and polyphenylene sulfides, but in particular to polycarbonates. These are taken to mean, in particular, polymers whose constitutional recurring unit conforms to the formula $\left[\text{O} - \text{A} - \text{O} - \overset{\text{O}}{\parallel}{\text{C}} \right]$, in which A is a divalent phenolic radical. Examples of A are mentioned, inter alia, in US-A-4 960 863 and DE-A-3 922 496. A can be derived, for example, from hydroquinone, resorcinol, from dihydroxybiphenyls or bisphenols in the broadest sense, such as bis(hydroxyphenyl)alkanes, -cycloalkanes, sulfides, ethers, ketones, sulfones, sulfoxides, α, α' -bis(hydroxyphenyl)diisopropylbenzenes, for example from the compounds 2,2-bis(4-hydroxyphenyl)propane, 2,2-bis(3,5-dimethyl-4-hydroxyphenyl)propane, 2,2-bis(3,5-dichloro-4-hydroxyphenyl)propane, 2,2-bis(3,5-dibromo-4-hydroxyphenyl)propane, 1,1-bis(4-hydroxyphenyl)cyclohexane, or from the compounds of the formulae





The polymers of component (A) can be linear or branched. Shaping of these polymers is carried out at a relatively high temperature, for example polycarbonate is injection-moulded at 220-330°C. At these temperatures, most conventional light stabilizers and antioxidants are unstable and begin to decompose. However, the abovementioned novel triazine derivatives are extremely heat-stable and are therefore particularly suitable for stabilizing said polymers.

Also of interest are compositions in which component (A) is a polyolefin, for example polyethylene or polypropylene.

Incorporation into the organic polymers, for example in the synthetic organic, in particular thermoplastic polymers, can be carried out by addition of the novel mixtures and any further additives by the methods conventional in industry. The incorporation can expediently be carried out before or during shaping, for example by mixing the pulverulent components or by addition of the stabilizer to the melt or solution of the polymers, or by application of the dissolved or dispersed compounds to the polymer, if desired with subsequent evaporation of the solvent. In the case of elastomers, these can also be stabilized as lattices. Another way of incorporating the novel mixtures into polymers comprises adding them before or during the polymerization of the corresponding monomers or before the crosslinking.

The novel mixtures can also be added to the plastics to be stabilized in the form of a masterbatch which comprises these compounds, for example, in a concentration of from

2.5 to 25 % by weight.

The novel mixtures can expediently be incorporated by the following methods:

- as an emulsion or dispersion (for example to lattices or emulsion polymers)
- as a dry mix during mixing of additional components or polymer mixtures
- by direct addition into the processing equipment (for example extruder, internal mixer, etc.)
- as a solution or melt.

The stabilized polymer compositions obtained in this way can be converted into shaped articles, for example fibres, films, tapes, sheets, sandwich boards, containers, pipes and other profiles, by conventional methods, for example by hot pressing, spinning, extrusion or injection moulding.

The invention therefore furthermore relates to the use of the novel polymer composition for the production of a shaped article.

Also of interest is the use in multilayer systems. In this case, a novel polymer composition having a relatively high content of novel stabilizer, for example 5-15 % by weight, is applied in a thin film (10-100 μm) to a shaped article made from a polymer containing little or no stabilizer of the formula I. The application can be carried out at the same time as the shaping of the base structure, for example by coextrusion. However, the application can also take place to the ready-shaped base structure, for example by lamination with a film or by coating with a solution. The outer layer or layers of the finished article have the function of a UV filter which protects the interior of the article against UV light. The outer layer preferably comprises 5-15 % by weight, in particular 5-10 % by weight, of at least one compound of the formula I and of a compound of the formula II.

The polymers stabilized in this way are distinguished by high weathering resistance, in particular by high resistance to UV light. This enables them to retain their mechanical properties and their colour and gloss even when used outside for extended periods.

Likewise of particular interest is the use of the novel mixtures comprising compounds of the formula I and formula II as stabilizers for coatings, for example for paints. The invention therefore also relates to compositions whose component A is a film-forming binder for coatings.

The novel coating composition preferably comprises 0.01-10 parts by weight of B, in particular 0.05-10 parts by weight of B, especially 0.1-5 parts by weight of B, per 100 parts by weight of solid binder A.

Multilayer systems are also possible here, where the concentration of the novel stabilizer mixture (component B) in the outer layer can be higher, for example from 1 to 15 parts by weight of B, especially 3-10 parts by weight of B, per 100 parts by weight of solid binder A.

The use of the novel mixture as stabilizer in coatings has the additional advantage that delamination, i.e. peeling-off of the coating from the substrate, is prevented. This advantage is particularly important in the case of metallic substrates, including in the case of multilayer systems on metallic substrates.

The binder (component A) can in principle be any binder which is customary in industry, for example those as described in Ullmann's Encyclopedia of Industrial Chemistry, 5th Edn., Vol. A18, pp. 368-426, VCH, Weinheim, 1991. In general, this is a film-forming binder based on a thermoplastic or thermosetting resin, predominantly based on a thermosetting resin. Examples thereof are alkyd, acrylic, polyester, phenolic, melamine, epoxy and polyurethane resins and mixtures thereof.

Component A can be a cold-curable or hot-curable binder; it may be advantageous to add a curing catalyst. Suitable catalysts which accelerate curing of the binder are described, for example, in Ullmann's Encyclopedia of Industrial Chemistry, Vol. A 18, p. 469, VCH Verlagsgesellschaft, Weinheim, 1991.

Preference is given to coating compositions in which component A is a binder comprising a functional acrylate resin and a crosslinking agent.

Examples of coating compositions containing specific binders are:

1. Paints based on cold- or hot-crosslinkable alkyd, acrylate, polyester, epoxy or melamine resins, or mixtures of such resins, if desired with addition of a curing catalyst;
2. Two-component polyurethane paints based on hydroxyl-containing acrylate, polyester or polyether resins and aliphatic or aromatic isocyanates, isocyanurates or polyisocyanates;
3. One-component polyurethane paints based on blocked isocyanates, isocyanurates or


polyisocyanates which are deblocked during baking;

4. Two-component paints based on (poly)ketimines and aliphatic or aromatic isocyanates, isocyanurates or polyisocyanates;
5. Two-component paints based on (poly)ketimines and an unsaturated acrylate resin or a polyacetoacetate resin or a methacrylamidoglycolate methyl ester;
6. Two-component paints based on carboxyl- or amino-containing polyacrylates and polyepoxides;
7. Two-component paints based on anhydride-containing acrylate resins and a polyhydroxyl or polyamino component;
8. Two-component paints based on acrylate-containing anhydrides and polyepoxides;
9. Two-component paints based on (poly)oxazolines and anhydride-containing acrylate resins or unsaturated acrylate resins or aliphatic or aromatic isocyanates, isocyanurates or polyisocyanates;
10. Two-component paints based on unsaturated polyacrylates and polymalonates;
11. Thermoplastic polyacrylate paints based on thermoplastic acrylate resins or externally crosslinking acrylate resins in combination with etherified melamine resins;
12. Paint systems based on siloxane-modified or fluorine-modified acrylate resins.

In addition to components A and B, the novel coating composition preferably comprises, as component C, a light stabilizer of the sterically hindered amine and/or 2-hydroxyphenyl-2H-benzotriazole type, for example as mentioned in the above list under points 2.1, and 2.6.

In order to achieve maximum light stability, it is of particular interest to add sterically hindered amines, as mentioned in the above list under 2.6. The invention therefore also relates to a coating composition which, in addition to components A and B, comprises, as component C, a light stabilizer of the sterically hindered amine type.

This is preferably a 2,2,6,6-tetraalkylpiperidine derivative containing at least one group of the formula









in which R is hydrogen or methyl, in particular hydrogen.



Component C is preferably used in an amount of 0.05-5 parts by weight, per 100 parts by weight of the solid binder.

Examples of tetraalkylpiperidine derivatives which can be used as component C are given in EP-A-356 677, pages 3-17, sections a) to f). These sections of this EP-A are regarded as part of the present description. It is particularly expedient to employ the following tetraalkylpiperidine derivatives:


bis(2,2,6,6-tetramethylpiperidin-4-yl) succinate,
bis(2,2,6,6-tetramethylpiperidin-4-yl) sebacate,
bis(1,2,2,6,6-pentamethylpiperidin-4-yl) sebacate,
di(1,2,2,6,6-pentamethylpiperidin-4-yl) butyl(3,5-di-tert-butyl-4-hydroxybenzyl)malonate,
bis(1-octyloxy-2,2,6,6-tetramethylpiperidin-4-yl) sebacate,
tetra(2,2,6,6-tetramethylpiperidin-4-yl) butane-1,2,3,4-tetracarboxylate,
tetra(1,2,2,6,6-pentamethylpiperidin-4-yl) butane-1,2,3,4-tetracarboxylate,
2,2,4,4-tetramethyl-7-oxa-3,20-diaza-21-oxodispiro[5.1.11.2]heneicosane,
8-acetyl-3-dodecyl-1,3,8-triaza-7,7,9,9-tetramethylspiro[4,5]decane-2,4-dione,
or a compound of the formulae







or



where m has a value of 5-50.

In addition to components A, B and, if used, C, the coating composition can comprise further components, for example solvents, pigments, dyes, plasticizers, stabilizers, thixotropic agents, drying catalysts and/or flow-control agents. Examples of possible components are those as described in Ullmann's Encyclopedia of Industrial Chemistry, 5th Edn., Vol. A18, pp. 429-471, VCH, Weinheim, 1991.

Possible drying catalysts or curing catalysts are, for example, organometallic compounds, amines, amino-containing resins and/or phosphines. Examples of organometallic compounds are metal carboxylates, in particular those of the metals Pb, Mn, Co, Zn, Zr and Cu, or metal chelates, in particular those of the metals Al, Ti and Zr, or organometallic compounds, for example organotin compounds.

Examples of metal carboxylates are the stearates of Pb, Mn and Zn, the octanoates of Co, Zn and Cu, the naphthenates of Mn and Co and the corresponding linoleates, resinates and tallates.

Examples of metal chelates are the aluminium, titanium and zirconium chelates of acetylacetone, ethyl acetylacetate, salicyl aldehyde, salicyl aldoxime, o-hydroxyacetophenone and ethyl trifluoroacetylacetate, and the alkoxides of these metals.

Examples of organotin compounds are dibutyltin oxide, dibutyltin dilaurate and dibutyltin dioctanoate.

Examples of amines are in particular tertiary amines, for example tributylamine, triethanolamine, N-methyldiethanolamine, N-dimethylethanolamine, N-ethylmorpholine, N-methylmorpholine and diazabicyclooctane (triethylenediamine) and salts thereof. Further examples are quaternary ammonium salts, for example trimethylbenzylammonium chloride.

Amino-containing resins are simultaneously binder and curing catalyst. Examples thereof are amino-containing acrylate copolymers.

The curing catalyst can also be a phosphine, for example triphenylphosphine.

The novel coating compositions can also be radiation-curable. In this case, the binder essentially comprises monomeric or oligomeric compounds containing ethylenically unsaturated bonds which are cured, after application, by actinic radiation, i.e. are converted into a crosslinked, high-molecular-weight form. UV-curing systems generally additionally contain a photoinitiator. Corresponding systems are described in the abovementioned publication, Ullmann's Encyclopedia of Industrial Chemistry, 5th Edn. Vol. A18, pages 451-453. In radiation-curable coating compositions, the novel stabilizer mixtures can also be employed without addition of sterically hindered amines.

The novel coating compositions can be applied to any desired substrates, for example to metal, wood, plastic or ceramic materials. They are preferably used as top coat in the painting of automobiles. If the top coat comprises two layers, of which the lower layer is pigmented and the upper layer is not pigmented, the novel coating composition can be used for either the upper or the lower layer or for both layers, but preferably for the upper layer.

The novel coating compositions can be applied to the substrates by conventional processes, for example by brushing, spraying, pouring, dipping or electrophoresis; see also Ullmann's Encyclopedia of Industrial Chemistry, 5th Edn., Vol. A18, pp. 491-500.

The curing of the coatings can - depending on the binder system - be carried out at room temperature or by warming. The coatings are preferably cured at 50-150°C, powder coatings also at higher temperatures.

The coatings obtained in accordance with the invention have excellent resistance to the harmful effects of light, oxygen and heat; particular mention should be made of the good light and weathering resistance of the coatings, for example paints, obtained in this way.

The invention therefore also relates to a coating, in particular a paint, which has been stabilized against the harmful effects of light, oxygen and heat by a content of the novel mixture comprising compounds of the formulae I and II. The paint is preferably a top coat for automobiles. The invention furthermore relates to a process for stabilizing a coating based on organic polymers against damage by light, oxygen and/or heat, which comprises admixing a mixture comprising a compound of the formula I and a compound of the formula II with the coating composition, and to the use of a mixture comprising compounds of the formulae I and II in coating compositions as stabilizers against damage by light, oxygen and/or heat.

The coating compositions can comprise an organic solvent or solvent mixture in which the binder is soluble. However, the coating composition can also be an aqueous solution or dispersion. The vehicle can also be a mixture of an organic solvent and water. The coating composition can also be a high-solids paint or contain no solvent (powder paint).


The pigments can be inorganic, organic or metallic pigments. The novel coating compositions preferably contain no pigments and are used as clear coats.

Likewise preferred is the use of the coating composition as top coat for applications in the automobile industry, in particular as a pigmented or unpigmented top coat of the finish. However, use for underlying layers is also possible.

The examples below describe the invention in greater detail without representing a limitation. In the examples, parts and percentages are by weight; room temperature is taken to mean a temperature in the range from 20 to 25°C. These definitions apply unless stated otherwise in each case.

The following compounds are examples of individual compounds of the formula I (the prefix n in each case denotes a straight-chain radical):

Compounds of the




type:

Compound No.	R ₇
I/1	-CH ₂ -phenyl
I/2	-CH ₂ CH ₂ OH
I/2a	-n-C ₈ H ₁₇
I/3	-CH ₂ CH ₂ OCOCH ₃
I/4	-CH ₂ CH ₂ OCOCH=CH ₂
I/5	-CH ₂ CH(OH)CH ₂ O-n-C ₈ H ₁₇
I/5a	-CH ₂ CH(OH)CH ₂ O-CH ₂ -CH(C ₂ H ₅)-(CH ₂) ₃ -CH ₃
I/6	-CH ₂ CH(OH)CH ₂ O(CH ₂) ₁₁₋₁₂ CH ₃
I/7	-CH ₂ CH(OH)CH ₂ O phenyl
I/8	-CH ₂ CH(OH)CH ₂ OCOC(CH ₃)=CH ₂
I/8a	-CH ₂ CH(OH)CH ₂ OCOCH=CH ₂




I/9	
I/10	-CH ₂ COOH
I/11	-CH ₂ CH ₂ COOC ₄ H ₉
I/12	-CH ₂ COOC ₈ H ₁₇
I/13	-CH ₂ COO(CH ₂ CH ₂ O) ₇ H
I/14	-CH ₂ COOCH ₂ CH(CH ₃)OCH ₂ CH(CH ₃)OCH(CH ₃)CH ₃
I/15	-CH ₂ COOCH ₂ P(O)(OC ₂ H ₅) ₂
I/16	-CH ₂ COOCH ₂ CH(OH)CH ₂ P(O)(OC ₄ H ₉) ₂
I/17	-CH ₂ COO(CH ₂) ₇ CH=CHC ₈ H ₁₇
I/18	-CH ₂ COOCH ₂ CH ₂ OCH ₂ CH ₂ OC ₆ H ₁₃
I/19	-CH ₂ CON(C ₂ H ₅) ₂
I/20	-CH ₂ CH ₂ CON
I/21	-CH ₂ CONHCH ₂ CH ₂ CH ₂ N(CH ₃) ₂
I/22	-CH ₂ CONHC ₈ H ₁₇
I/23	-CH ₂ CON(C ₈ H ₁₇) ₂
I/24	-(CH ₂) ₇ CH ₃
I/25	-(CH ₂) ₅ CH ₃

Compounds of the

type:





I/26	R ₇ = -CH ₂ COOC ₂ H ₅
I/26a	-CH ₂ COOCH ₂ CH ₂ OCH ₃
I/27	-CH ₂ COOCH ₂ CH=CH-phenyl
I/28	-CH ₂ CH(OH)CH ₂ O(CH ₂) ₁₁₋₁₂ CH ₃ (mixture)
I/28a	-CH ₂ CH(OH)CH ₂ OC ₈ H ₁₇

I/29	$-\text{CH}_2\text{COOCH}_2-\text{CH}-\text{CH}_2$ 
I/30	$-\text{CH}_2\text{COOCH}_2\text{CH}(\text{OH})\text{CH}_2\text{OC}_8\text{H}_{17}$
I/31	$-\text{CH}_2\text{phenyl}$
I/32	$-\text{CH}_2\text{CH}=\text{CH}_2$
I/33	$-\text{CH}_2\text{CON}(\text{C}_4\text{H}_9)_2$
I/34	$-\text{CH}_2\text{CH}_2\text{CONHC}_8\text{H}_{17}$
I/35	$-(\text{CH}_2)_3-\text{CONH}-$ 
I/36	$-(\text{CH}_2)_3-\text{CO}-\text{N}$ 
I/37	$-\text{CO}-\text{OC}_6\text{H}_{13}$
I/38	$-\text{CH}_2\text{CH}_2\text{Cl}$
I/39	$-\text{CH}_2\text{CH}_2\text{CN}$

Compounds of the


type:



I/40	$\text{R}_7 = -(\text{CH}_2)_5\text{CH}_3$
I/41	$-\text{CH}_2\text{CH}(\text{OH})\text{phenyl}$
I/42	$-\text{CH}_2\text{CH}(\text{OH})\text{CH}_2\text{O}(\text{CH}_2)_{11-12}\text{CH}_3$ (mixture)
I/42a	$-\text{CH}_2\text{CH}(\text{OH})\text{CH}_2\text{OC}_8\text{H}_{17}$
I/43	$-\text{CH}_2\text{CH}(\text{OH})\text{CH}_2\text{OCophenyl}$
I/44	$-\text{CH}_2\text{CH}(\text{CH}_3)\text{OCOCH}_3$
I/45	$-\text{SO}_2-\text{C}_{12}\text{H}_{15}$
I/46	$-\text{SO}_2-$ 


- I/47 -CH₂COOC₁₀H₂₁
I/48 -CH₂CONHCH₂CH₂OCH₃
I/49 -CH₂CH₂CONHCH₂phenyl
I/50 -(CH₂)₃CONH(CH₂)₃N(C₂H₅)₂
I/51 -CH₂CONHC₁₂H₂₅

Compounds of the



- I/52 R₇ = -CH₃

Compounds of the



- I/53 R₇ = -CH₃
I/54 -(CH₂)₅-CH₃
I/55 -CH₂-CH(OH)-CH₂-O-(CH₂)₃-CH₃
I/56 -(CH₂)₇-CH₃


I/57




The following compounds are examples of individual compounds of the formula II:

Compounds of the

type:




II/1



II/2



II/3



II/4




II/5




II/6



II/7




II/8




Compounds of the

type:



II/11




II/12



II/13	-CH ₂ CH ₂ COC ₂ H ₅
II/14	-CH ₂ COOC ₈ H ₁₇
II/15	-CH ₂ CH(OH)CH ₂ OC ₄ H ₉
II/15a	-CH ₂ CH(OH)CH ₂ OC ₈ H ₁₇
II/16	-CH ₂ CH(OH)CH ₂ Ophenyl
II/17	-(CH ₂) ₅ CH ₃
II/18	-(CH ₂) ₇ CH ₃

Compounds of the

type:



II/19

R₇ = -n-C₈H₁₇

II/20


-CH₂CH(OH)CH₂OCH₂-CH(C₂H₅)-C₄H₉

II/21

-CH₂CH(OH)CH₂O-n-C₁₂H₂₅/n-C₁₃H₂₇ (mixture)

Compounds of the

type:



II/22

R₇ = H.

Mixtures are prepared as shown in Table A below by dissolving the stated compounds in xylene:

Table A: Mixtures of compounds of the formula I and compounds of the formula II in xylene; amounts in parts by weight (pbw)

Compound of the formula I	Compound of the formula II
1 pbw I/5a	1 pbw II/17
1 pbw I/6	1 pbw II/17
1 pbw I/24	1 pbw II/17
1 pbw I/40	1 pbw II/17
3 pbw I/5a	1 pbw II/17
3 pbw I/6	1 pbw II/17
3 pbw I/24	1 pbw II/17
3 pbw I/40	1 pbw II/17
1 pbw I/6	1 pbw II/21
1 pbw I/24	1 pbw II/19
1 pbw I/6	1 pbw II/19
2 pbw I/24	1 pbw II/21
3 pbw I/5a	1 pbw II/15
1 pbw I/5a	3 pbw II/15

Use examples

1. Gloss retention of a 2-coat metallic finish

The novel stabilizer mixtures are tested in a clear coat having the following composition:

Synthacryl [®] SC 303 ¹⁾	27.51
Synthacryl [®] SC 370 ²⁾	23.34
Maprenal [®] MF 650 ³⁾	27.29
Butyl acetate/butanol (37/8)	4.33
Isobutanol	4.87
Solvesso [®] 150 ⁴⁾	2.72
Crystal Oil K-30 ⁵⁾	8.74
Baysilon [®] MA flow-control agent ⁶⁾	1.20
	100.00 g


1) Acrylate resin, Hoechst AG; 65 % solution in xylene/butanol 26:9

2) Acrylate resin, Hoechst AG; 75 % solution in Solvesso[®] 100⁴⁾

- 3) Melamine resin. Hoechst AG; 55 % solution in isobutanol
- 4) Aromatic hydrocarbon mixture, boiling range 182-203°C (Solvesso[®] 150) or 161-178°C (Solvesso[®] 100); manufacturer ESSO
- 5) Aliphatic hydrocarbon mixture, boiling range 145-200°C; manufacturer Shell
- 6) 1 % in Solvesso[®] 150⁴⁾; manufacturer Bayer AG

1.5 % of the mixture to be tested are added to the coating composition as a solution in approx. 5-10 g of xylene, based on the solids content of the varnish.

Some further varnish samples are prepared which, in addition to the novel mixture, contain 0.5 % of the compound



(compound A), based on the solids content of the coating composition. The comparison is a varnish containing no light stabilizer.

The varnish is diluted to spraying consistency using Solvesso[®] 100 and sprayed onto a prepared aluminium sheet (coil coat, filler, pale-blue metallic base coat) and baked at 130°C for 30 minutes. A dry film thickness of 40-50 µm of varnish is obtained.

The samples are then weathered in an Atlas UVCON[®] weathering unit (UVB-313 lamps) in a cycle comprising UV irradiation at 70°C for 8 hours and condensation at 50°C for 4 hours. Further samples are subjected to outdoor weathering.

The surface gloss (20° gloss as defined in DIN 67530) of the samples is measured at regular intervals. The results are shown in Table 1 below.

Table 1: 20° gloss as defined in DIN 67530 after UVCON weathering

Amount of stabilizers		20° gloss after weathering for					
Type I	Type II	A	0	400	800	1200	1600 h
none	none	none	87	74	62	24	
0.75 % I/6	0.75 % II/21	none	87	82	78	62	
0.75 % I/24	0.75 % II/19	none	87	79	74	63	
0.75 % I/6	0.75 % II/19	none	87	77	68	68	
1.00 % I/24	0.5 % II/21	none	87	80	71	71	
1.125 % I/5a	0.375 % II/15	none	87	79	79	69	
0.375 % I/5a	1.125 % II/15	none	87	88	81	60	
none	none	0.5 % A	89	83	68	54	2*
0.75 % I/6	0.75 % II/21	0.5 % A	89	90	87	89	89
0.75 % I/24	0.75 % II/19	0.5 % A	89	90	87	91	
0.75 % I/6	0.75 % II/19	0.5 % A	89	90	87	90	89
1.00 % I/24	0.5 % II/21	0.5 % A	89	90	87	91	89
1.125 % I/5a	0.375 % II/15	0.5 % A	89	89	87	90	88
0.375 % I/5a	1.125 % II/15	0.5 % A	89	90	88	91	89

* cracking

The samples stabilized in accordance with the invention have better weathering stability (gloss retention, cracking resistance) than the unstabilized comparative sample.

2. Loss of UV absorber during weathering

A clear coat as described under 1. is sprayed onto prepared glass plates and baked at 130°C for 30 minutes. A dry film thickness of 20 µm of coating is obtained.

The samples are then weathered in an Atlas UVCON[®] weathering unit (UVB-313 lamps) in a cycle comprising UV irradiation at 70°C for 8 hours and condensation at 50°C for 4 hours. Before the weathering and after weathering for 2000 hours, the loss of UV absorber is measured with the aid of a UV/VIS spectrometer (Perkin-Elmer, Lambda 5; change in absorption at the long-wave maximum). The results are shown in Table 2 below.


Table 2: Loss of UV absorber after UVCON weathering for 2000 hours

Amount of stabilizers		Measurement wavelength	Loss
Type I	Type II	[nm]	[%]
1.5 % I/6	none	339	36.1
none	1.5 % II/21	355	43.1
0.75 % I/6	0.75 % II/21	345	29.1


It is evident from the results in Table 2 that the loss of UV absorber can be considerably reduced when the novel mixture is employed.

WHAT IS CLAIMED IS:

1. A mixture comprising a compound of the formula I



and a compound of the formula II



in which n is 1 or 2;

R₁, R'₁, R₂ and R'₂, independently of one another, are H, C₁-C₁₂alkyl; C₂-C₆alkenyl; C₁-C₁₂alkoxy; C₂-C₁₈alkenoxy; halogen; trifluoromethyl; C₇-C₁₁phenylalkyl; phenyl; phenyl which is substituted by C₁-C₁₈alkyl, C₁-C₁₈alkoxy or halogen; phenoxy; or phenoxy which is substituted by C₁-C₁₈alkyl, C₁-C₁₈alkoxy or halogen;


R₃ and R₄, independently of one another, are H, C₁-C₁₂alkyl; C₂-C₆alkenyl; C₁-C₁₂alkoxy; C₅-C₁₂cycloalkoxy; C₂-C₁₈alkenoxy; halogen; trifluoromethyl; C₇-C₁₁phenylalkyl; phenyl; phenyl which is substituted by C₁-C₁₈alkyl, C₁-C₁₈alkoxy or halogen; phenoxy; or phenoxy which is substituted by C₁-C₁₈alkyl, C₁-C₁₈alkoxy or

halogen;

R₆ is hydrogen, C₁-C₂₄alkyl, C₅-C₁₂cycloalkyl or C₇-C₁₅phenylalkyl;

R₇, in the case where n = 1, and R'₇, independently of one another, are hydrogen or C₁-C₁₈alkyl; or are C₁-C₁₂alkyl which is substituted by OH, C₁-C₁₈alkoxy, allyloxy, halogen, -COOH, -COOR₈, -CONH₂, -CONHR₉, -CON(R₉)(R₁₀), -NH₂, -NHR₉, -N(R₉)(R₁₀), -NHCOR₁₁, -CN, -OCOR₁₁, phenoxy and/or phenoxy which is substituted by C₁-C₁₈alkyl, C₁-C₁₈alkoxy or halogen; or R₇ is C₃-C₅₀alkyl which is interrupted by -O- and may be substituted by OH; or R₇ is C₃-C₆alkenyl; glycidyl; C₅-C₁₂cycloalkyl; cyclohexyl which is substituted by OH, C₁-C₄alkyl or -OCOR₁₁; C₇-C₁₁phenylalkyl which is unsubstituted or substituted by OH, Cl or CH₃; -CO-R₁₂ or -SO₂-R₁₃;

R₇, in the case where n = 2, is C₂-C₁₆alkylene, C₄-C₁₂alkenylene, xylylene, C₃-C₂₀alkylene which is interrupted by O and/or substituted by OH, or is a group of the formula -CH₂CH(OH)CH₂O-R₂₀-OCH₂CH(OH)CH₂-, -CO-R₂₁-CO-, -CO-NH-R₂₂-NH-CO- or -(CH₂)_m-COO-R₂₃-OOC-(CH₂)_m-, in which m is a number in the range from 1 to 3, or is



R₈ is C₁-C₁₈alkyl; C₂-C₁₈alkenyl; C₃-C₅₀alkyl which is interrupted by O, NH, NR₉ or S and/or is substituted by OH; C₁-C₄alkyl which is substituted by -P(O)(OR₁₄)₂, -N(R₉)(R₁₀) or -OCOR₁₁ and/or OH; glycidyl; cyclohexyl; phenyl; C₇-C₁₄alkylphenyl or C₇-C₁₁phenylalkyl;

R₉ and R₁₀, independently of one another, are C₁-C₁₂alkyl; C₃-C₁₂alkoxyalkyl; C₄-C₁₆dialkylaminoalkyl or C₅-C₁₂cycloalkyl, or R₉ and R₁₀ together are C₃-C₉alkylene or -oxaalkylene or -azaalkylene;

R₁₁ is C₁-C₁₈alkyl; C₂-C₁₈alkenyl or phenyl; or is C₃-C₅₀alkyl which is interrupted by -O- and may be substituted by OH;

R₁₂ is C₁-C₁₈alkyl; C₂-C₁₈alkenyl; phenyl; C₁-C₁₈alkoxy; C₃-C₁₈alkenylalkoxy; C₃-C₅₀alkoxy which is interrupted by O, NH, NR₉ or S and/or substituted by OH; cyclohexyloxy; C₇-C₁₄alkylphenoxy; C₇-C₁₁phenylalkoxy; phenoxy; C₁-C₁₂alkylamino; phenylamino; tolylamino or naphthylamino;

R₁₃ is C₁-C₁₂alkyl; phenyl; naphthyl or C₇-C₁₄alkylphenyl;


R₁₄ is C₁-C₁₂alkyl, methylphenyl or phenyl;

R₂₀ is C₂-C₁₀alkylene; C₄-C₅₀alkylene which is interrupted by O, phenylene or a

-phenylene-X-phenylene- group, in which X is -O-, -S-, -SO₂-, -CH₂- or -C(CH₃)₂-;

R₂₁ is C₂-C₁₀alkylene, C₂-C₁₀oxaalkylene, C₂-C₁₀thiaalkylene, C₆-C₁₂arylene or C₂-C₆alkenylene;

R₂₂ is C₂-C₁₀alkylene, phenylene, tolylene, diphenylenemethane or a



R₂₃ is C₂-C₁₀alkylene or C₄-C₂₀alkylene which is interrupted by O.

2. A mixture according to claim 1, comprising from 0.2 to 5 parts by weight of compound of the formula II per part by weight of compound of the formula I.

3. A mixture according to claim 1 or 2, in which, in the formulae I and II,

R₁, R'₁, R'₂ and R₂, independently of one another, are H, C₁-C₄alkoxy or C₁-C₄alkyl;

R₃ and R₄, independently of one another, are H, C₁-C₁₂alkyl, C₂-C₆alkenyl, C₁-C₁₂alkoxy, Cl, F, phenyl or phenoxy;

R₇, in the case where n = 1, and R'₇ are hydrogen, C₁-C₁₈alkyl, allyl, glycidyl or benzyl; or are C₁-C₁₂alkyl which is substituted by OH, C₁-C₁₈alkoxy, phenoxy, -COOR₈,

-CONHR₉, -CON(R₉)(R₁₀) and/or -OCOR₁₁; or R₇ is -(CH₂CHR₁₅-O)_i-R₁₈ or

-CH₂-CH(OH)-CH₂-O-(CH₂CHR₁₅-O)_i-R₁₈, where i is a number in the range from 1 to 12;

R₇, in the case where n = 2, is C₂-C₁₆alkylene, C₄-C₁₂alkenylene, xylylene, or

C₃-C₂₀alkylene which is interrupted by O and/or is substituted by OH;

R₈ is C₁-C₁₂alkyl; C₃-C₁₈alkenyl; C₃-C₂₀alkyl which is interrupted by O and/or is substituted by OH; or C₁-C₄alkyl which is substituted by -P(O)(OR₁₄)₂;

R₉ and R₁₀, independently of one another, are C₁-C₈alkyl or cyclohexyl; or R₉ and R₁₀ together are pentamethylene or 3-oxapentamethylene;

R₁₁ is C₁-C₈alkyl, C₂-C₅alkenyl or phenyl; or is C₃-C₂₀alkyl which is interrupted by -O- and may be substituted by OH;

R₁₄ is C₁-C₄alkyl;

R₁₅ is H or methyl; and

R₁₈ is H, C₁-C₁₈alkyl, phenyl or C₇-C₁₀alkylphenyl.

4. A mixture according to claim 1 or 2, in which, in the formulae I and II,

n is 1;

R₇ and R'₇ are hydrogen; C₁-C₁₈alkyl, C₁-C₁₂alkyl which is substituted by OH, C₁-C₁₈alkoxy, -COOR₈, -CON(R₉)(R₁₀), phenoxy and/or -OCOR₁₁; glycidyl or benzyl; or R₇ is -(CH₂CHR₁₅-O)_i-R₁₈ or -CH₂-CH(OH)-CH₂-O-(CH₂CHR₁₅-O)_i-R₁₈, where i is a number in the range from 2-12;

R₈ is C₁-C₁₂alkyl; C₃-C₁₂alkenyl; C₆-C₂₀alkyl which is interrupted by O and/or is substituted by OH; or C₁-C₄alkyl which is substituted by -P(O)(OR₁₄)₂;

R₉ and R₁₀ are C₄-C₈alkyl;

R₁₁ is C₁-C₈alkyl or C₂-C₃alkenyl; or is C₃-C₂₀alkyl which is interrupted by -O- and may be substituted by OH;

R₁₄ is C₁-C₄alkyl;

R₁₅ is hydrogen; and

R₁₈ is H, C₁-C₁₈alkyl, phenyl or C₇-C₁₀alkylphenyl.

5. A mixture according to claim 1 or 2, in which, in the formulae I and II, n is 1;

R₁ and R₂, independently of one another, are hydrogen, methyl or methoxy;

R'₁ and R'₂, independently of one another, are hydrogen or methyl;

R₃ and R₄, independently of one another, are H, Cl, C₁-C₄alkyl, allyl, C₁-C₄alkoxy or phenyl;

R₆ is hydrogen;

R₇ and R'₇ are C₁-C₁₈alkyl or benzyl; or are C₂-C₆alkyl which is substituted by OH, C₁-C₁₈alkoxy, phenoxy, -COOR₈ and/or OCOR₁₁;

R₈ is C₁-C₈alkyl or C₃-C₈alkenyl; and

R₁₁ is C₁-C₄alkyl or C₂-C₃alkenyl.

6. A mixture as claimed in claim 1 or 2, in which, in the formulae I and II, n is 1;

R₁ and R₂, independently of one another, are hydrogen, methoxy or methyl;

R'₁ and R'₂ are hydrogen;

R₃ and R₄, independently of one another, are hydrogen, phenyl, methoxy or methyl;

R₆ is hydrogen;

R₇ and R'₇, independently of one another, are C₁-C₁₈alkyl, or a -CH₂CH(OH)CH₂O-R₁₉ group; and R₁₉ is C₁-C₁₈alkyl, phenyl or C₃-C₅alkenyl.

7. A composition comprising

A) an organic material which is sensitive to damage by light, oxygen and/or heat, and

B) as stabilizer, a mixture comprising a compound of the formula I and a compound of the

formula II, as defined in any one of claims 1 and 3 to 6.

8. A composition according to claim 7, comprising from 0.01 to 15 parts by weight of component B per 100 parts by weight of component A.

9. A composition according to claim 7 or 8, comprising, in addition to components A and B, one or more other stabilizers or other additives.

10. A composition according to any one of claims 7 to 9, wherein component A is a synthetic organic polymer.

11. A composition according to any one of claims 7 to 9, wherein component A is a thermoplastic polymer, a binder for coatings or a photographic material.

12. A composition according to claim 11, comprising as component A, a binder for coatings and, as further components, one or more stabilizers selected from light stabilizers of the sterically hindered amine and/or 2-hydroxyphenyl-2H-benzotriazole type.

13. A process for stabilizing organic material against damage by light, oxygen and/or heat, which comprises adding thereto, as stabilizer, a mixture according to claim 1 comprising a compound of the formula I and a compound of the formula II.

14. The use of a mixture according to claim 1 comprising a compound of the formula I and a compound of the formula II for stabilizing organic material against damage by light, oxygen and/or heat.

15. A composition according to claim 1 substantially as hereinbefore described with reference to any one of the foregoing Examples.



Application No: GB 9600897.4

Examiner: Miss Maureen M. Kelman

Claims searched: 1 to 15

Date of search: 10 April 1996

Patents Act 1977
Search Report under Section 17

Databases searched:

UK Patent Office collections, including GB, EP, WO & US patent specifications, in:
UK CI (Ed.O): C3K KCC KCZ
Int CI (Ed.6): C08K 5/00, 5/34, 5/3467, 5/3477, 5/3492
Other: ONLINE:Chinese Patents ABS, CLAIMS, JAPIO, WPI

Documents considered to be relevant:

Table with 3 columns: Category, Identity of document and relevant passage, Relevant to claims. Rows include EP 0520938 A1 CIBA-GEIGY and EP 0434608 A1 CIBA-GEIGY.

X Document indicating lack of novelty or inventive step
Y Document indicating lack of inventive step if combined with one or more other documents of same category.
& Member of the same patent family
A Document indicating technological background and/or state of the art.
P Document published on or after the declared priority date but before the filing date of this invention.
E Patent document published on or after, but with priority date earlier than, the filing date of this application.