



(51) International Patent Classification:

*C09B 31/18* (2006.01)      *C09B 31/28* (2006.01)  
*C09B 31/20* (2006.01)      *D21H 21/28* (2006.01)

(21) International Application Number:

PCT/EP2011/071292

(22) International Filing Date:

29 November 2011 (29.11.2011)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

10193158.2      30 November 2010 (30.11.2010)      EP  
61/482,352      4 May 2011 (04.05.2011)      US

(71) Applicant (for all designated States except US): **KEMIRA OYJ** [FI/FI]; Porkkalankatu 3, FIN-00180 Helsinki (FI).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **MEIER, Helmut-Martin** [DE/DE]; Am Obersthof 3, 40883 Ratingen (DE). **HEIDE, Christof** [DE/DE]; Habichtweg 13, 51429 Bergisch Gladbach (DE). **STRUMPF, Klaus-Günter** [DE/DE]; Weiherstr. 102, 51373 Leverkusen (DE). **HÜBBE, Thomas** [DE/DE]; Hochwinkel 22, 51069 Köln (DE).

(74) Agent: **BUBLAK, Wolfgang**; Bardehle Pagenberg, Prinzregentenplatz 7, 81675 München (DE).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))



**WO 2012/072635 A1**

(54) Title: AZO DYES

(57) Abstract: The present invention relates to new azo dyes, a process for their preparation, and their use for dyeing or printing fibrous materials, to produce materials with brownish shades.

## Azo dyes

5 The invention relates to new azo dyes, a process for their preparation, and their use for dyeing or printing materials, in particular organic or fiber-containing materials, to produce materials with brownish shades.

In order to produce papers with a brown shade, it is known to dye paper  
10 with mixtures of different dyes. For example, WO-A 2007/057370 is directed to liquid formulations containing the direct dyes C.I. Direct Brown 44 and Direct Yellow 11. EP-A-1 258 562 relates to dye mixtures containing two anionic dyes each with a different, defined absorption maximum. WO-A 2004/048478 teaches the production of a low-salt  
15 liquid formulation of C.I. Direct Brown 44. The production process comprises production of vesuvine from m-phenylenediamine and direct conversion to C.I. Direct Brown 44. Vesuvine and its coupling products, such as C.I. Direct Brown 44, have been known since the beginning of dye chemistry. For instance, the Colour Index (C.I.) shows that C.I.  
20 Direct Brown 44 is obtained by formally coupling two parts of sulfanilic acid onto one part of vesuvine (Bismarck Brown C.I. 21000). However, the lightfastness of the produced brown papers is often not sufficient. From JP 2001-004833 A1 there is known a polarizing film for liquid crystal projector including an azo compound of specified structure which  
25 contains at least two azo groups linked by three aromatic groups.


In paper mills or paper processing industry, brownish papers often are stored without being prevented from the influence of light or weather, which results in change of color or color shade. Therefore, there is a need  
30 for improving the lightfastness of brownish papers.

Surprisingly, it has been found that this problem can be solved by new azo dyes containing at least three azo groups which are linked by aromatic structures, such as substituted benzene and/or naphthalene groups. These azo dyes are soluble in water and enable the production of materials, in particular of organic or fiber-containing materials, e.g. paper or board, in brownish shades and with high lightfastness. In particular, it was surprising that the brownish shade could be obtained with the use of one dye only, in contrast to the prior art, which commonly uses dye mixtures for that purpose.


10

Thus, the present invention provides compounds of the general formula


(1)



A represents




and B represents



15 or

A, B independently of each other, represent one of the following groups:




wherein








5 R1, R2, R3, R4 independently of each other, represent hydrogen, substituted or unsubstituted C<sub>1</sub>-C<sub>4</sub> alkyl, substituted or unsubstituted C<sub>1</sub>-C<sub>4</sub> alkoxy, substituted or unsubstituted aryl, substituted or unsubstituted phenyl, amino, sulfonic, carboxyl, hydroxyl, nitro, or halogen groups.

10 Surprisingly, it was found that compounds of formula (1) are soluble in water, and materials dyed with those dyes show improved lightfastness.

The invention also refers to a process for preparing the compounds of formula (1), comprising diazotizing a compound of formula (2) or formula (2a)




formula 2a




coupling the obtained product with a compound of formula (3)

10




diazotizing the obtained product and coupling with a compound of formula (4)



formula 4






diazotizing the obtained product and coupling with a compound of formula (5) or formula (5a)

5



formula 5

formula 5a



10 to obtain the compound of formula (1).

Further, the invention refers to the use of the compounds of formula (1) for dyeing or printing materials, in particular materials containing cellulose and/or polyamide, preferably paper or board. In addition, the invention relates to a process for dyeing or printing materials, in particular materials containing cellulose and/or polyamide, preferably paper or board, and to materials or paper obtained by that process. Preferred embodiments of the invention are described in the description hereinafter and the claims. In the present invention, the term paper is used to cover paper or board.

20


In formula (1), the substituents R1 to R4 each are, independently of each other, attached to the corresponding aromatic rings at any position thereof. This also includes that R2 can be attached at any position of the






naphthyl ring. In the context of the invention, the C<sub>1</sub>-C<sub>4</sub> alkyl or C<sub>1</sub>-C<sub>4</sub> alkoxy group can be linear or branched. If the alkyl, alkoxy, aryl or phenyl group is substituted, the possible substituents are amino, hydroxyl, sulfonic, or carboxylic groups, which groups can be attached at any position of the alkyl, alkoxy, aryl or phenyl group.

In the present invention, a sulfonic group means the group -SO<sub>3</sub>M, wherein M is a cation. Preferably, M is hydrogen, alkaline metal, earth alkaline metal, ammonium, or mono-, di-, tri- or tetra-substituted ammonium, in particular M is mono-C<sub>1-5</sub>-alkyl-, di-C<sub>1-5</sub>-alkyl-, tri-C<sub>1-5</sub>-alkyl-, tetra-C<sub>1-5</sub>-alkylammonium, mono-C<sub>1-5</sub>-hydroxyalkyl-, di-C<sub>1-5</sub>-hydroxyalkyl-, tri-C<sub>1-5</sub>-hydroxyalkyl-, tetra-C<sub>1-5</sub>-hydroxyalkyl-ammonium, or benzyltri-C<sub>1-5</sub>-hydroxyalkylammonium; or ammonium based on amines derived from nitrogen-containing five- or six-membered saturated heterocycles, such as pyrrolidine, piperidine, morpholine or piperazine or their N-monoalkyl- or N,N-dialkyl-substituted products. In the present invention, sulfonic and carboxyl groups are present in the form of free acids or in the form of salts, preferably alkali, earth alkali, ammonium, alkyl ammonium, or alkanol ammonium salts, in particular as alkanol ammonium salts. Preferred ammonium salts are defined above.




Preferred groups for R<sub>1</sub> to R<sub>4</sub> are sulfonic, carboxyl, hydroxyl, or amino groups, in particular sulfonic and carboxyl groups. In a preferred embodiment, R<sub>2</sub> and/or R<sub>3</sub>, in particular both R<sub>2</sub> and R<sub>3</sub>, are sulfonic and carboxyl groups, in particular sulfonic groups. In a further preferred embodiment, R<sub>2</sub> appears one time at the naphthyl moiety.

Preferred compounds of formula (1) are:










5









8





5






5 More preferred compounds of formula (1) are:






The invention also provides a process for preparing the compounds of formula (1) using known procedures, such as diazotization and coupling steps. Generally, the compounds can be prepared by diazotizing a starting primary aromatic amine, and coupling to another primary aromatic amine. The obtained reaction product is diazotized again and coupled to a third primary aromatic amine which in turn is diazotized and coupled to a fourth compound to yield the desired compound. It is also possible to start with appropriate azo compounds and react those with corresponding amino-containing compounds to yield the desired dyes.


As an example, the synthesis of the above described preferred dye having the formula



can be accomplished by starting with an appropriate azo compound, such as 4-((4-amino-2-methylphenyl)diazenyl)benzoic acid having the formula




which is diazotized and reacted with an amino containing compound, such as Cleve's acid 6 having the formula



5


then diazotized again and coupled with phenol



to yield the desired azo dye.


10

As another example, the synthesis of the above described dye having the formula




15

can be accomplished by starting with an appropriate azo compound, such as 5-amino-8-((4-amino-2-methoxy-5-sulfo-2-phenyl)diazenyl)naphthalene-2-sulfonic acid having the formula



20

which is tetra-azotized and coupled with salicylic acid



to yield the desired azo dye.

- 5 Azo dyes and their production using diazotization and coupling steps are well-known and familiar to those skilled in the art.

In a further preferred embodiment, generally first a diazonium salt is prepared followed by a coupling reaction. In a suitable embodiment, an  
10 amine compound is dissolved or suspended in aqueous hydrochloric or sulfuric acid, and a concentrated aqueous sodium nitrite solution is added. An excess of 2.5-3 equivalents of acid per equivalent of amine compound is further added at a temperature of 0-10°C, preferably of 0-5°C, to generate the diazonium salt. The obtained acidic diazonium salt is  
15 added to a, preferably aqueous, solution of the coupling component. The coupling reaction may be completed after mixing of the components.


Another suitable procedure starts with solving the amine compound in water or weak alkaline solution, and adding the calculated amount of  
20 sodium nitrite solution to this amine solution. The obtained amine-nitrite solution is stirred into an ice-cooled acid solution which is present in a vessel. It is also possible to add the acid or ice-cooled acid solution to the amine-nitrite solution at a temperature of 0-10°C, preferably of 0-5°C. Depending on the amine compound even 0-40°C may be possible.

25 Further, it is possible to dissolve water-insoluble amine compounds in organic solvents, such as ethanol, acetone, pyridine, acetic acid, or formic acid. After addition of acid, diazotizing is carried out in the usual manner by means of sodium nitrite solution. Instead of sodium nitrite,  
30 diazotization agents, such as nitrosyl sulfuric acid, nitrosyl chloride,

alkylnitrite or nitrous gases also can be used. Further, it is possible to add emulsifiers, dispersing agents or surfactants during the reaction.

5 The preparation process is not limited to the methods described above, but may be carried out by applying procedures known from the state of the art for diazotization and coupling procedures or as known from the literature (e.g. Klaus Hunger (Editor), *Industrial Dyes*, Wiley-VCH, Weinheim, 2003, pages 19, 28).


10 In a preferred process of the invention, the compounds of formula (1) are obtained by the following procedure. The process starts with an amine compound of formula (2) or (2a)




formula 2

15

formula 2a




which is diazotized and coupled to an amine compound of formula (3).




5

The product obtained is diazotized again and coupled to a compound of formula (4).




10





The product obtained is diazotized again and coupled to a compound of formula (5) or (5a)



formula 5



formula 5a






























5 to yield the compound of formula (1).








Furthermore, it is also possible to start with appropriate azo compounds with amino groups to yield the azo dyes of the invention.

10 Preferred compounds of formula (2) or formula (2a) are:






formula 2a



The substituents shown also may be located at other positions of the aromatic rings.

5


Preferred compounds of formula (3) are:



The substituents shown also may be located at other positions of the aromatic rings.


5

Preferred compounds of formula (4) are:



The substituents shown also may be located at other positions of the aromatic rings.

Preferred compounds of formula (5) or formula (5a) are:



- 5 The substituents shown also may be located at other positions of the aromatic rings.

The dyes of formula (1) can be isolated from the reaction medium by conventional processes, for example by salting out with an alkali metal salt, filtering and drying, if appropriate under reduced pressure and at elevated temperature. Depending on the reaction and/or isolation conditions, the dyes of formula (1) can be obtained as free acid, as salt or as mixed salt which contains for example one or more cations selected from alkali metals ion, for example the sodium ion, or an ammonium ion or alkyl ammonium cation, for example mono-, di- or trimethyl-, or ethyl ammonium cations, or an alkanol ammonium cation, for example

10

15

mono-, di- or tri-ethanol ammonium cations. The dyes can be converted from the free acid into a salt or into a mixed salt or vice versa or from one salt form into another one by conventional techniques. If desired, the dyes can be further purified by diafiltration, wherein undesired salts and synthesis by-products are separated from the crude anionic dye. The removal of undesired salts and synthesis by-products and a partial removal of water from the crude dye solution can be carried out by means of a semi-permeable membrane by applying a pressure whereby the dye is obtained, without the undesired salts and synthesis by-products, as a solution and if desired as a solid material in a conventional manner. Such procedures belong to the state of the art and are described for example in WO-A 2007/057370.

The compounds of formula (1) can be utilized in form of a liquid formulation, preferably an aqueous liquid formulation, a moist press cake, or in dried form. In the last two cases, when preparing a solution alkylamine is preferably added.

According to a more preferred embodiment of the invention, the compound of formula (1) is present or used in form of an aqueous liquid formulation comprising at least one alkylamine whose one, two or three alkyl radicals may each be substituted by one or two hydroxyl groups and/or amino groups and/or interrupted by one or two oxygen atoms in ether function, the alkylamine being present in an amount of 0.5-15% by weight based on the total weight of the liquid formulation. Preference is given to alkylamines whose two or three alkyl radicals may each be substituted by one or two hydroxyl groups and/or interrupted by one or two oxygen atoms in ether function. Particular preference is given to mono-, di- and trialkanolamines. Preferred alkylamines are ethanolamine, diethanolamine, triethanolamine, dimethylethanolamine, N-methyldiethanolamine, monomethylethanolamine, 2-(2-aminoethoxy)ethanol, aminoethylethanolamine. Particular preference is

given to ethanolamine, especially diethanolamine and triethanolamine and ethoxylated or propoxylated triethanolamine.

Suitable additives in the liquid formulation can be C<sub>1</sub>-C<sub>4</sub>-alkanols, for  
5 example methanol, ethanol, propanol, isopropanol, butanol, isobutanol,  
sec-butanol or tert-butanol; carboxamides, such as N,N-  
dimethylformamide or N,N-dimethylacetamide; ketones or keto alcohols,  
such as acetone, methyl ethyl ketone or 2-methyl-2-hydroxypentane-4-  
one; mono-, oligo- or polyalkylene glycols or -thioglycols which have  
10 C<sub>2</sub>-C<sub>6</sub>-alkylene units, such as ethylene glycol, 1,2- or 1,3-propylene  
glycol, 1,2- or 1,4-butylene glycol, hexane-1,6-diol, diethylene glycol,  
triethylene glycol, dipropylene glycol, thiodiglycol, polyethylene glycol  
or polypropylene glycol; other polyols, such as glycerol or hexane-1,2,6-  
triol; C<sub>1</sub>-C<sub>4</sub>-alkyl ethers of polyhydric alcohols, such as ethylene glycol  
15 monomethyl ether, ethylene glycol monoethyl ether, diethylene glycol  
monomethyl ether, diethylene glycol monoethyl ether, diethylene glycol  
monobutyl ether (butyldiglycol) or triethylene glycol monomethyl ether  
or triethylene glycol monoethyl ether; C<sub>1</sub>-C<sub>4</sub>-alkyl esters of polyhydric  
alcohols,  $\gamma$ -butyrolactone or dimethylsulfoxide. Suitable solubilizing  
20 additives are further lactams, such as  $\epsilon$ -caprolactam, pyrrolidin-2-one or  
N-methylpyrrolidin-2-one, cyclic ureas, such as 1,3-  
dimethylimidazolidin-2-one or 1,3-dimethylhexahydropyrimid-2-one,  
and also polyacrylic acids, polyacrylic acid derivatives, polyvinyl  
acetates, polyvinyl alcohols, polyvinylpyrrolidones, polysiloxanes or  
25 copolymers of the respective monomers. It is further possible to use  
oligomers of ethylene oxide or propylene oxide or derivatives of these  
oligomers.

The dyes of formula (1) and their salts are particularly suitable for dyeing  
30 or printing organic material, fibrous or fiber-containing material, in  
particular materials containing lignocellulosic material, cellulose and/or  
polyamide, preferably materials consisting of natural or synthetic  
polyamides, cellulose, lignocellulosic material, or substrates like wool,

leather, textile or paper or board. The material may be of wood and/or straw origin, mechanically and/or chemically produced, in particular by any suitable pulping or refining technique normally employed in papermaking, e.g. by thermomechanical pulping (TMP), chemi-  
5 mechanical pulping (CMP), chemithermomechanical pulping (CTMP), groundwood pulping (GW), alkaline sulphate (kraft) pulping, acid sulphite pulping and/or semichemical pulping. The material may also contain or consist of recycled fiber or pulp, especially made of waste paper. Polyamide or lignocellulosic material may be in fibrous or non-  
10 fibrous form. The fibrous material is preferably of wood and/or straw origin, mechanically and/or chemically obtained, e.g. by thermo-mechanical pulping (TMP), chemimechanical pulping (CMP), chemithermomechanical pulping (CTMP), groundwood pulping (GW), alkaline sulphate (kraft) pulping, acid sulphite pulping and/or  
15 semichemical pulping. The fibrous material or pulp may also contain or consist of recycled fiber or pulp, especially made of waste paper. The pulp used may contain, in addition to the fibrous material, e.g. fillers and/or auxiliary chemicals, before or after dyeing the pulp. In a most preferred embodiment, the material is paper or board. The obtained  
20 shades can be orange to brownish, or reddish to brownish. Further, the dyes of formula (1) and their salts are suitable for producing printing inks, especially ink-jet inks, and for using these inks for printing materials, in particular organic or fibrous material, for example materials consisting of natural or synthetic polyamides, cellulose or substrates like  
25 wool, leather, textile, paper or board. Preferably, the dyes of formula (1) and their salts are used to dye paper in orange to brownish shades, in particular in brownish shades.

The invention also relates to a process for dyeing or printing organic  
30 material, fibrous or fiber-containing material, in particular materials containing lignocellulosic material, cellulose and/or polyamide, preferably lignocellulosic- or cellulose-containing material, wherein the material is brought into contact with the compound of formula (1),



wherein that compound is contained in a liquid formulation, a moist press cake, or in dried form, as described above. Preferably the material is brought into contact with an aqueous liquid formulation containing the compound of formula (1). Suitable materials are the same as described above with respect to the use of the dye of formula (1). The material may be of wood and/or straw origin, mechanically and/or chemically produced, in particular by any suitable pulping or refining technique normally employed in papermaking, e.g. by thermomechanical pulping (TMP), chemimechanical pulping (CMP), chemithermomechanical pulping (CTMP), groundwood pulping (GW), alkaline sulphate (kraft) pulping, acid sulphite pulping and/or semichemical pulping. The material may also contain or consist of recycled fiber or pulp, especially made of waste paper. Polyamide or lignocellulosic material may be in fibrous or non-fibrous form. The fibrous material is preferably of wood and/or straw origin, mechanically and/or chemically obtained, e.g. by thermomechanical pulping (TMP), chemimechanical pulping (CMP), chemithermomechanical pulping (CTMP), groundwood pulping (GW), alkaline sulphate (kraft) pulping, acid sulphite pulping and/or semichemical pulping. The fibrous material or pulp may also contain or consist of recycled fiber or pulp, especially made of waste paper. The pulp used may contain, in addition to the fibrous material, e.g. fillers and/or auxiliary chemicals, before or after dyeing the pulp. The dyeing of paper can be carried out in the pulp.

The invention also relates to a process for dyeing paper or board, wherein a pulp or a paper sheet or web is brought into contact with an aqueous preparation or formulation as described above. Preferably, the paper sheet or web is contacted with the aqueous preparation in a size press, or in a coating application, preferably in a coating colour.

30

The following Examples illustrate the invention without limiting its scope.

## EXAMPLES

The Examples demonstrate the synthesis of dyes of formula (1) and of comparative dyes, and their use in an aqueous preparation for dyeing paper. The lightfastness of the obtained paper was determined according to the test method described below. In case that products were salted out in the examples, the term x % b.v. means x % of volume of reaction mixture in g salt.

### 10 **Dyeing process:**

7 parts by weight of chemically bleached pinewood sulfite cellulose and 3 parts by weight of chemically bleached birchwood sulfite cellulose were beaten into water in a mixer. 1 part by weight of the liquid dye preparation was added to this stuff. Paper was made from that after a mixing time of 20 minutes.

### **Lightfastness test according to EN ISO 105-B02:**

Test for color fastness - Part B02: Color fastness to artificial light: The xenon arc fading lamp test (ISO 105-B02:1994, including amendment 1:1998), which is commonly used by those skilled in the art, was used. Lightfastness is defined by the degree of decomposition of dyeing or printings on paper by sun light or artificial light. In the present test, paper having been dyed and radiated by the xenon arc fading lamp was measured against the standard blue wool scale ranging from 1 (lowest lightfastness) to 8 (highest lightfastness). The blue wool scale consists of 8 different blue dyes on wool with gradually increasing lightfastness from 1 to 8. After radiation of the dyed paper samples by the xenon arc fading lamp in a weather-o-meter (a device which simulates rain and sunshine) the lightfastness was evaluated by comparison with the blue wool scale.

### **Comparative Example 1**

Preparation of Direct Brown 44 according to WO-A 2007/057370

Stage 1:

28.12 g of m-phenylenediamine and 8.76 g of 20% by weight of hydrochloric acid were added to 344 ml of water. Ice was added in an amount of 338 g. Then, 15.04 g of sodium nitrite were introduced,  
5 followed by the dropwise addition of 78.86 g of 20% by weight of hydrochloric acid within 50 minutes at  $<3^{\circ}\text{C}$ . After 10 minutes further 1.73 g of m-phenylenediamine were added and a pH of 3 was set using 13 g of aqueous sodium hydroxide solution (25% by weight). This was followed by stirring at  $3^{\circ}\text{C}$  for 1 hour.

10 Stage 2:

To a solution of 34.6 g of sulfanilic acid in 273.46 g of water and 32.4 g of aqueous sodium hydroxide solution (25% by weight) were added 279 g of ice and 68.9 g of sodium nitrite. The mixture was admixed with 82.76 g of hydrochloric acid (20% by weight) at  $0-5^{\circ}\text{C}$  and subsequently  
15 stirred for 30 minutes. The obtained product was combined with the stage 1 product at  $20^{\circ}\text{C}$  in the course of 90 minutes. All the time, the pH was maintained at pH 5 using aqueous sodium hydroxide solution (25% by weight). After 3 hours at  $20^{\circ}\text{C}$  the obtained mixture was adjusted to pH 7.5 and then heated to  $55-60^{\circ}\text{C}$ . Hydrochloric acid (20% by weight) was  
20 used to adjust the pH to 1, and the solids were filtered off with suction and washed with water to obtain about 300 g of a moist press cake of Direct Brown 44 whose solids content was 22% by weight (sodium content:  $<0.5\%$  by weight in the dry material).

25 Production of a liquid formulation of Direct Brown 44:

80.33 g of the moist press cake (corresponding to 20.0 g dry weight) were dissolved with 5.25 g of diethanolamine, 3.44 g of aqueous ammonium hydroxide solution (25%  $\text{NH}_3$ ), 5 g of polyethylene glycol (average molecular weight: 200) and water to form 100 g of liquid dye.

30

Paper was made using the above described dyeing process. Lightfastness was measured according to EN ISO 105-B02 with the result: 1, i.e. lowest lightfastness.

**Comparative Example 2**

Preparation of Direct Yellow 11 according to WO-A 2007/057370

5 1.10 kg of 5-nitro-o-toluenesulfonic acid (83% by weight, 33.5 mol) was added to 1.5 l of water. A total of 278 g of solid lithium hydroxide (56% pure by weight) was then added continuously in small amounts. 67 g of diethanolamine were added and the mixture was stirred at 50-60°C for 20 hours and then at 58°C for 5 hours. Thereafter, 1.7 liters of water were added and a pH of 9.0 was set with glacial acetic acid. The dye was dissolved with 1.85 kg of urea and adjusted to final color strength, compared to a previously defined standard sample, with water. The product was obtained in an amount of 7.26 kg and had a dye content of about 12% by weight.

15 Direct Brown 44 (D.Br. 44) and Direct Yellow 11 (D.Y. 11) were mixed according to WO-A 2007/057370 resulting in the following composition:

9.4 % D.Br. 44 (dry)

6.6 % D.Y. 11 (dry)

3.13 % Diethanolamine

20 0.43 % NH<sub>3</sub>

2.50 % Polyethylene glycol 200 and water,

to form 100 g of liquid dye.

25 Paper was made using the above described dyeing process.

Lightfastness was measured according to EN ISO 105-B02 with the result: 1, i.e. lowest lightfastness.

**Example 1**

30 Stage 1

In a 1L beaker with stirrer, 500 mL of distilled water and 30.1 g (219.48 mmol) of p-aminobenzoic acid were mixed at room temperature at pH 3. Lithium hydroxide (12.9 g) was added resulting in pH>12. The obtained

solution was cooled using an external ice bath, followed by adding 250 g of ice into the reaction mixture, and then 35 mL (253.62 mmol) of sodium nitrite solution (500 g/L) was added. This solution then was dripped within 20 min. to 75 mL of hydrochloric acid (30 % b.w.), 100 mL of dist. water, and 100 g of ice at 0°C. The suspension of the diazonium salt was stirred for 2 hours at 5-10°C. Excess of nitrite was destroyed by addition of amidosulfonic acid.

#### Coupling:

In a 3L beaker containing 23.5 g (219.29 mmol) of m-toluidine, and 0.5 g of an emulsifier (from Tanatex Deutschland GmbH, product of 1 mol arylphenol with 11 mol ethylene oxide), in 300 mL of dist. water at room temperature, pH 10.3, the diazonium salt was added within 20 min. at a constant pH 7.5, controlled by 240 mL of sodium carbonate solution (20 % b.v.). The batch was stirred for 1.5 hours at room temperature, pH 8.2. The product was salted out using 64 mL of hydrochloric acid (30 % b.w.) during stirring for 0.5 h, and isolated by filtration to yield 223 g of press cake (217.39 mmol of stage 1 product).

#### Stage 2

In a 2L beaker with stirrer, 700 mL of distilled water and 223 g (217.39 mmol) of press cake stage 1 product, pH=2.6, were mixed with 11.6 g of LiOH resulting in pH>12. A solution of 32 mL (231.88 mmol) of sodium nitrite (500 g/L) was added. This mixture was added to a solution of 75 mL of hydrochloric acid (30 % b.w.), 100 mL of dist. water and 100 g of ice within about 15 min. The temperature was increased from 0°C at the beginning to 15°C at the end of addition, pH 1.2. The reaction mixture was stirred for 3 hours. Excess of nitrite was destroyed by addition of amidosulfonic acid.

#### Coupling:

In a 3L beaker containing 48.9 g (217.39 mmol) of Cleve's acid 6, solved with sodium carbonate solution in 200 mL of dist. water at pH 7.5, the diazonium salt was added within 25 min. at a constant pH 7.5, controlled by 372 mL of sodium carbonate solution. The batch was stirred for 1.5 hours at room temperature, pH 7.9. The product was salted out using 480


g of sodium chloride solution (20 % b.v.) and 240 g of potassium chloride solution (10 % b.v.) during stirring for 0.5 h, and isolated by filtration to yield 765 g of press cake (217.39 mmol of stage 2 product).

### Stage 3

5 In a 1L beaker with stirrer, 250 mL of distilled water and 102 g (28.99 mmol) of stage 2 product were mixed with 3.3 g of LiOH. A solution of 5 mL (14.50 mmol) of sodium nitrite (500 g/L) was added. This mixture was added to a solution of 37 mL (430 mmol) of hydrochloric acid (30%b.w.), 50 mL of dist. water and 25 g of ice within about 20 min. The  
10 temperature was increased from 0°C at the beginning to 10-15°C at the end of addition, pH 0.8. The reaction mixture was stirred for 2 hours. Excess of nitrite was destroyed by addition of amidosulfonic acid.

### Coupling:

In a 1L beaker containing 3.4 g (30.43 mmol) of resorcinol, solved with  
15 sodium carbonate solution in 150 mL of dist. water at pH 7.5, the diazonium salt was added within 15 min. at a constant pH 8, controlled by 158 mL of sodium carbonate solution. The batch was stirred for 2 hours at room temperature, pH 8.5. The product was salted out using 180 g of sodium chloride (solution 15 % b.v.) during stirring for 1 h, and  
20 isolated by filtration to yield 20.7 g of press cake (stage 3 product). The moist press cake was dried in vacuum at 60°C to yield 12.8 g of product of formula



25

Paper was made using the above described dyeing process.

Lightfastness was measured to EN ISO 105-B02 with the result: 3.

### Example 2

30

Stage 1

In a 1L beaker with stirrer, 500 mL of distilled water and 49.5 g (240.72 mmol) of p-sulfanilic acid (100g/486.3 mmol) were mixed at room temperature at pH=6.1. Cooled with an ice bath and after addition of 250 g of ice, 35 mL (253.62 mmol) of sodium nitrite solution (500 g/L) was added and afterwards 50 mL (475 mmol) of hydrochloric acid (30 % b.w.) was immediately added at 0°C. The suspension of the diazonium salt was stirred for 2.5 hours at 5-8°C. Excess of nitrite was destroyed by addition of amidosulfonic acid.

Coupling:

In a 2L beaker containing 26.0 g (240.72 mmol) of m-toluidine in 300 mL of dist. water at room temperature, pH 10.3, the diazonium salt was added within 15 min. at constant pH 7.5, controlled by 332 mL of sodium carbonate solution (20 % b.v.). The batch was stirred for 1.5 hours at room temperature, pH 7.7. The product was salted out using 340 g (5808 mmol) of sodium chloride (solution 20 % b.v.) during stirring for 0.5 h, and isolated by filtration to yield 115.0 g of press cake (240.5 mmol of stage 1 product).

Stage 2

In a 2L beaker with stirrer, 1000 mL of distilled water and 115 g (240.5 mmol) of press cake stage 1 product, pH=9.6, were mixed and warmed up to 70-75°C. A solution of 35 mL (253.62 mmol) of sodium nitrite (500 g/L) was added. This mixture was added to a solution of 85 mL (808 mmol) of hydrochloric acid (30 % b.w.), 100 mL of dist. water and 300 g of ice within about 25 min. The temperature was increased from -10°C at the beginning to 15-17°C at the end of addition, pH 0.9. The reaction mixture was stirred for 2.5 h. Excess of nitrite was destroyed by addition of amidosulfonic acid.

Coupling:

In a 3L beaker containing 55.4 g (248.15 mmol) of Cleve's acid 6, solved with sodium carbonate solution in 200 mL of dist. water at pH 7.5, the diazonium salt was added within 30 min. at constant pH 7.5, controlled by 238 mL of sodium carbonate solution. The batch was stirred for 1.5 h at room temperature, pH 7.9. The product was salted out using 360 g


(6153 mmol) of sodium chloride solution (15 % b.v.) during stirring for 0.5 h, and isolated by filtration to yield 397.7 g of press cake (217.39 mmol of stage 2 product).

#### Stage 3

5 In a 1L beaker with stirrer, 600 mL of distilled water and 106 g (57.94 mmol) of stage 2 product were mixed. A solution of 10 mL (72.46 mmol) of sodium nitrite (500 g/L) was added. This mixture was added to a solution of 50 mL (430 mmol) of hydrochloric acid (30%b.w.), 50 mL of dist. water and 200 g of ice within about 12 min. The temperature was  
10 increased from -10°C at the beginning to 10-15°C at the end of addition, pH 0.6. The reaction mixture was stirred for 2.5 hours. Excess of nitrite was destroyed by addition of amidosulfonic acid.

#### Coupling:

In a 2L beaker containing 5.4 g (57.98 mmol) of aniline, solved in 150  
15 mL of dist. water at pH 7.5, the diazonium salt was added within 40 min. at constant pH 7.5, controlled by 300 mL of sodium carbonate solution (20% b.v.). The batch was stirred for 3 hours at room temperature, pH 7.5. The product was salted out using sodium chloride (solution 10 % b.v.) during stirring for 1 h, and isolated by filtration to yield 36.4 g of  
20 press cake (stage 3 product). The moist press cake was dried in vacuum at 60°C to yield 18.6 g of product of formula



Paper was made using the above described dyeing process.

25 Lightfastness was measured to EN ISO 105-B02 with the result: 3.

### Example 3

#### Stage 1

In a 1L beaker with stirrer, 200 mL of distilled water and 14.9 g (72.46  
30 mmol) of p-sulfanilic acid (100g/486.3 mmol) were mixed at room



temperature with pH=6.1. Cooled with an ice bath and after addition of 75 g of ice, 11 mL (79.71 mmol) of sodium nitrite solution (500 g/L) was added and afterwards 18 mL (171 mmol) of hydrochloric acid (30 % b.w.) was immediately added at 0°C. The suspension of the diazonium salt was stirred for 2.5 hours at 5-8°C. Excess of nitrite was destroyed by addition of amidosulfonic acid.

Coupling:

In a 1L beaker containing 7.8 g (72.46 mmol) of m-toluidine in 100 mL of dist. water at room temperature, pH 8.2, the diazonium salt was added within 15 min. at constant pH 7.5, controlled by 70 mL of sodium carbonate solution. The batch was stirred for 1.5 h at room temperature, pH 8.4. The product was salted out using 120 g (2050 mmol) of sodium chloride (solution 20 % b.v.) during stirring for 0.5 h, and isolated by filtration to yield 41.7 g of press cake (68.84 mmol of stage 1 product).

Stage 2

In a 1L beaker with stirrer, 500 mL of distilled water and 41.7 g (68.84 mmol) of press cake stage 1 product, pH=9.6, were mixed and warmed up to 70-75°C. A solution of 50 mL (72.46 mmol) of sodium nitrite (100 g/L) was added. This mixture was added to a solution of 45 mL (430 mmol) of hydrochloric acid (30%b.w.), 100 mL of dist. water and 100 g of ice within about 25 min. The temperature was increased from -10°C at the beginning to 15-17°C at the end of addition, pH 0.9. The reaction mixture was stirred for 2.5 hours. Excess of nitrite was destroyed by addition of amidosulfonic acid.

Coupling:


In a 2L beaker containing 15.5 g (68.84 mmol) of Cleve's acid 6, solved with sodium carbonate solution in 200 mL of dist. water at pH 7.5, the diazonium salt was added within 30 min. at constant pH 7.5, controlled by 210 mL of sodium carbonate solution. The batch was stirred for 1.5 hours at room temperature, pH 7.9. The product was salted out using 187.5 g (3200 mmol) of sodium chloride (solution 20 % b.v.) during stirring for 0.5 h, and isolated by filtration to yield 53.5 g of press cake (62.32 mmol of stage 2 product).

## Stage 3

In a 1L beaker with stirrer, 600 mL of distilled water and 53.5 g (62.32 mmol) of stage 2 product were mixed. A solution of 10 mL (72.46 mmol) of sodium nitrite (500 g/L) was added. This mixture was added to a solution of 45 mL (430 mmol) of hydrochloric acid (30%b.w.), 100 mL of dist. water and 50 g of ice within about 20 min. The temperature was increased from 0°C at the beginning to 10-15°C at the end of addition, pH 0.8. After adding 60 g of ε-caprolactam, the reaction mixture was stirred for 2.5 hours. Excess of nitrite was destroyed by addition of amidosulfonic acid.

## Coupling:

In a 3L beaker containing 6.9 g (72.46 mmol) of phenol, solved with sodium carbonate solution in 200 mL of dist. water at pH 7.5, the diazonium salt was added within 40 min. at constant pH 7.5, controlled by 170 mL of sodium carbonate solution. The batch was stirred for 1.5 h at room temperature, pH 7.5. The product was salted out using 90 g (1200 mmol) of potassium chloride solution (5 % b.v.) and 270 g of sodium chloride (solution 20 % b.v.) during stirring for 1 hour, and isolated by filtration to yield 44.2 g of press cake (stage 3 product). The moist press cake was dried in vacuum at 60°C to yield 22 g of product of formula



Paper was made using the above described dyeing process. Lightfastness was measured to EN ISO 105-B02 with the result: 3.

**Example 4**

## Stage 1

In a 2L beaker with stirrer, 750 mL of distilled water and 59 g (237.77 mmol) of 5-amino-4-methoxy-2-nitrobenzenesulfonic acid were mixed at 50°C, pH=7.1. A solution of 35 mL (253.62 mmol) of sodium nitrite (500 g/L) was added. This mixture was added to a solution of 75 mL of hydrochloric acid (30 % b.w.), 75 mL of dist. water and 100 g of ice within about 20 min. The temperature was increased from -10°C at the beginning to 20-25°C at the end of addition, pH 0.7. The reaction mixture was stirred for 2.5 hours. Excess of nitrite was destroyed by addition of amidosulfonic acid.

10 Coupling:


In a 2L beaker containing 49.2 g (220.33 mmol) of Cleve's acid 6, solved with 47.2 g diluted NaOH solution (200 g/L), at pH 6, adjusted with sodium carbonate solution in 300 mL of dist. water to pH 7.5, the diazonium salt was added within 15 min. at constant pH 7.5, controlled by 262 mL of sodium carbonate solution (20 % b.v.). The batch was stirred for 1.5 hours at room temperature, pH 7.9. The coupling product was warmed up to 50°C and pH was adjusted to 11.7 using 75 mL of NaOH solution (400 g/L). Within 10 min. a solution of 63.3 g (351.2 mmol) of glucose in 300 mL of dist. water was added with slightly exothermic reaction at 55-57°C, pH<10. After adding 25 mL of NaOH solution (400 g/L), the mixture was warmed to 65°C for 20 min. The obtained product was salted out using 250 g of sodium chloride (as solid substance), and isolated by filtration to yield 161.3 g of press cake (stage 1 product).

25 Stage 2

In a 1L beaker with stirrer, 600 mL of distilled water and 48.4 g (50.22 mmol) of stage 1 product were mixed with 1.2 g of LiOH. A solution of 14 mL (101.45 mmol) of sodium nitrite (500 g/L) was added. This mixture was added to a solution of 40 mL of hydrochloric acid (30%b.w.), 50 mL of dist. water and 100 g of ice within about 20 min. The temperature was increased from -8°C at the beginning to 10-15°C at the end of addition, pH 0.8. The reaction mixture was stirred for 1 h. Excess of nitrite was destroyed by addition of amidosulfonic acid.

## Coupling:

In a 3L beaker containing 19.5 g (141.20 mmol) of salicylic acid, solved with sodium carbonate solution in 500 mL of dist. water at pH 7.5, the diazonium salt was added within 20 min. at constant pH 7.5, controlled by 240 mL of sodium carbonate solution (20 % b.v.). The batch was stirred for 1 hour at room temperature. The product was salted out using 360 g of potassium chloride (solution 10 % b.v.) and 180 g of sodium chloride (solution 10 % b.v.) during stirring for 30 min., and isolated by filtration to yield 21.3 g of press cake (stage 2 product). The moist press cake was dried in vacuum at 60°C to yield 11.1 g of product of formula



Paper was made using the above described dyeing process.

Lightfastness was measured to EN ISO 105-B02 with the result: 3

**Example 5**

## Stage 1

In a 1L beaker with stirrer, 500 mL of distilled water and 30.1 g (219.48 mmol) of p-aminobenzoic acid were mixed at room temperature at pH 3. Lithium hydroxide (12.9 g) was added resulting in pH>12. The obtained solution was cooled using an external ice bath, followed by adding 250 g of ice into the reaction mixture, and then 35 mL (253.62 mmol) of sodium nitrite solution (500 g/L) was added. This solution then was dripped within 20 min. to 75 mL of hydrochloric acid (30 % b.w.), 100 mL of dist. water, and 100 g of ice at 0°C. The suspension of the diazonium salt was stirred for 2 hours at 5-10°C. Excess of nitrite was destroyed by addition of amidosulfonic acid.

## Coupling:

In a 3L beaker containing 23.5 g (219.29 mmol) of m-toluidine, 0.5 g of emulsifier (from Tanatex Deutschland GmbH, product of 1 mol arylphenol with 11 mol ethylene oxide), in 300 mL of dist. water at room temperature, pH 10.3, the diazonium salt was added within 20 min. at a constant pH 7.5, controlled by 240 mL of sodium carbonate solution (20 % b.v.). The batch was stirred for 1.5 hours at room temperature, pH 8.2. The product was salted out using 64 mL of hydrochloric acid (30 % b.w.) during stirring for 0.5 h, and isolated by filtration to yield 223 g of press cake (217.39 mmol of stage 1 product).

10 Stage 2

In a 2L beaker with stirrer, 700 mL of distilled water and 223 g (217.39 mmol) of press cake stage 1 product, pH=2.6, were mixed with 11.6 g of LiOH resulting in pH>12. A solution of 32 mL (231.88 mmol) of sodium nitrite (500 g/L) was added. This mixture was added to a solution of 75 mL of hydrochloric acid (30 % b.w.), 100 mL of dist. water and 100 g of ice within about 15 min. The temperature was increased from 0°C at the beginning to 15°C at the end of addition, pH 1.2. The reaction mixture was stirred for 3 hours. Excess of nitrite was destroyed by addition of amidosulfonic acid.

20 Coupling:

In a 3L beaker containing 48.9 g (217.39 mmol) of Cleve's acid 6, solved with sodium carbonate solution in 200 mL of dist. water at pH 7.5, the diazonium salt was added within 25 min. at a constant pH 7.5, controlled by 372 mL of sodium carbonate solution. The batch was stirred for 1.5 hours at room temperature, pH 7.9. The product was salted out using 480 g of sodium chloride solution (20 % b.v.) and 240 g of potassium chloride solution (10 % b.v.) during stirring for 0.5 h, and isolated by filtration to yield 765 g of press cake (217.39 mmol of stage 2 product).

Stage 3


30 In a 1L beaker with stirrer, 300 mL of distilled water and 102 g (28.98 mmol) of press cake stage 2 product, pH=2.6, were mixed with 4.0 g of LiOH resulting in pH>12. A solution of 30 mL (43.47 mmol) of sodium nitrite (100 g/L) was added. This mixture was added to a solution of 40

mL of hydrochloric acid (30 % b.w.), 50 mL of dist. water and 30 g of ice within about 30 min. The temperature was increased from 0°C at the beginning to 15°C at the end of addition, pH 1.2. The reaction mixture was stirred for 2 hours. Excess of nitrite was destroyed by addition of  
5 amidosulfonic acid. The diazo suspension yields a volume of 600 mL.

Coupling:

In a 2L beaker containing 3.94 g (30.43 mmol) of barbituric acid, solved with 2.1 g of lithium hydroxide in 100 mL of dist. water at pH 12, the diazonium salt solution of stage 3 was added within 20 min. at constant  
10 pH 8, controlled by the addition of 154 mL of sodium carbonate solution (20 % b.w.). The batch was stirred for 5 h at room temperature at pH 8.3. The product was isolated by filtration to yield 33.8 g of press cake (30.43 mmol of stage 3 product). The moist press cake was dried in vacuum at 60°C to yield 12.9 g of product of formula

15



Paper was made using the above described dyeing process.

Lightfastness was measured to EN ISO 105-B02 with the result: 3.


20

All papers obtained in the Examples and Comparative Examples exhibited brownish shades.


The examples show that the dyes of the invention provide paper with  
25 higher lightfastness than paper produced with known dye mixtures.

## CLAIMS


- 5 1. A compound of formula (1)



A represents




and B represents



or

- 10 A, B independently of each other, represent one of the following groups



wherein


- 5 R1, R2, R3, R4 independently of each other, represent hydrogen, substituted or unsubstituted C<sub>1</sub>-C<sub>4</sub> alkyl, substituted or unsubstituted C<sub>1</sub>-C<sub>4</sub> alkoxy, substituted or unsubstituted aryl, substituted or unsubstituted phenyl, amino, sulfonic, carboxyl, hydroxyl, nitro or halogen groups.

10

2. The compound of claim 1, having the following structure:




40




3. The compound of claim 1, having the following structure:

5




4. The compound of claim 1, having the following structure:

10




5. The compound of claim 1, having the following structure:

15




6. The compound of claim 1, having the following structure:

20




7. The compound of claim 1, having the following structure:




5

8. The compound of any of the preceding claims, wherein in the sulfonic group with the meaning  $-\text{SO}_3\text{M}$ , M is a cation, preferably M is hydrogen, alkaline metal, earth alkaline metal, ammonium, or mono-, di-, tri- or tetra-substituted ammonium, in particular M is mono- $\text{C}_{1-5}$ -alkyl-, di- $\text{C}_{1-5}$ -alkyl-, tri- $\text{C}_{1-5}$ -alkyl-, tetra- $\text{C}_{1-5}$ -alkylammonium, mono- $\text{C}_{1-5}$ -hydroxyalkyl-, di- $\text{C}_{1-5}$ -hydroxyalkyl-, tri- $\text{C}_{1-5}$ -hydroxyalkyl-, tetra- $\text{C}_{1-5}$ -hydroxyalkyl-ammonium, or benzyltri- $\text{C}_{1-5}$ -hydroxyalkylammonium.
- 10
9. A process for preparing a compound of formula (1) according to claim 1, comprising diazotizing a compound of formula (2) or (2a)
- 15




formula 2

formula 2a




and coupling to an amine compound of formula (3)




5

diazotizing the product obtained and coupling to a compound of formula (4)




10





diazotizing the product obtained and coupling to a compound of formula (5) or (5a)



formula 5



formula 5a



to obtain the compound of formula (1).

5

10. Use of a compound of formula (1) according to any of claims 1 to 8, for dyeing or printing materials.

10 11. The use according to claim 10, wherein the materials used contain cellulose and/or polyamide, in particular cellulose.

12. The use according to claim 10 or 11, wherein the material used is paper or board.

15 13. The use according to any of claims 10 to 12, wherein the material used is a fiber-containing or fibrous material.

20 14. A process for dyeing or printing materials, wherein the material is brought into contact with a compound of formula (1) according to any of claims 1 to 8 or prepared according to claim 9.

15. A product or paper obtainable by a process according to claim 14.

**INTERNATIONAL SEARCH REPORT**

International application No  
PCT/EP2011/071292

**A. CLASSIFICATION OF SUBJECT MATTER**  
 INV. C09B31/18 C09B31/20 C09B31/28 D21H21/28  
 ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)  
 C09B D21H

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)  
 EPO-Internal, CHEM ABS Data, WPI Data, BEILSTEIN Data

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	GB 1 563 415 A (SANDOZ LTD) 26 March 1980 (1980-03-26) page 1, lines 6-8 page 5; example 5 page 23; claim 16 -----	1,10,14, 15
X	US 5 198 022 A (AULICK RODNEY O [US] ET AL) 30 March 1993 (1993-03-30) column 1, lines 11-12 column 6, lines 49-51 claim 11 -----	1,10,14, 15
X	US 5 167 703 A (EIDA TSUYOSHI [JP] ET AL) 1 December 1992 (1992-12-01) column 1, lines 7-8 columns 11-12; compounds II-(18) column 18; example 22 ----- -/--	1,10,14, 15

Further documents are listed in the continuation of Box C.

See patent family annex.

\* Special categories of cited documents :

<p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p>	<p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"&amp;" document member of the same patent family</p>
--	--

Date of the actual completion of the international search  31 January 2012	Date of mailing of the international search report  22/02/2012
Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer  Durand-Oral, Ilknur

## INTERNATIONAL SEARCH REPORT

International application No  
PCT/EP2011/071292

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2007/062409 A1 (MISTRY PRAHALAD M [GB] ET AL MISTRY PRAHALAD MANIBHAI [GB] ET AL) 22 March 2007 (2007-03-22) page 8; example 2 page 1, column 0001 page 42; example 64 -----	1,10,14, 15
X	US 2007/287830 A1 (SANO HIDEO [JP] ET AL) 13 December 2007 (2007-12-13) column 1, lines 9-10 page 6; compounds I-1 -----	1
X	US 3 028 376 A (ERMANNIO GAETANI) 3 April 1962 (1962-04-03) column 1, lines 9-10 columns 1-2; example 2 -----	1
X	US 5 883 233 A (CATLIN JOSEPH C [US] ET AL) 16 March 1999 (1999-03-16) column 1, lines 5-6 column 1, lines 57-63 column 12; claim 1 the whole document -----	1-15
A	US 5 288 294 A (KAESER ADOLF [CH]) 22 February 1994 (1994-02-22) the whole document -----	1-15
A	US 5 559 217 A (KAESER ADOLF [CH]) 24 September 1996 (1996-09-24) the whole document -----	1-15

## INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2011/071292

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
GB 1563415	A	26-03-1980	CH 617713 A5 13-06-1980 DE 2648370 A1 26-05-1977 ES 453289 A1 01-02-1978 FR 2331604 A2 10-06-1977 GB 1563415 A 26-03-1980 IT 1080522 B 16-05-1985 JP 52063222 A 25-05-1977
US 5198022	A	30-03-1993	NONE
US 5167703	A	01-12-1992	AT 167222 T 15-06-1998 DE 69129578 D1 16-07-1998 DE 69129578 T2 15-10-1998 EP 0490195 A1 17-06-1992 ES 2116990 T3 01-08-1998 US 5167703 A 01-12-1992
US 2007062409	A1	22-03-2007	EP 1697467 A1 06-09-2006 JP 4688814 B2 25-05-2011 JP 2007517082 A 28-06-2007 US 2007062409 A1 22-03-2007 WO 2005052065 A1 09-06-2005
US 2007287830	A1	13-12-2007	EP 1832628 A1 12-09-2007 JP 2006206878 A 10-08-2006 KR 20070089712 A 31-08-2007 US 2007287830 A1 13-12-2007 WO 2006070818 A1 06-07-2006
US 3028376	A	03-04-1962	NONE
US 5883233	A	16-03-1999	AT 227758 T 15-11-2002 CA 2277533 A1 24-01-2000 DE 69903889 D1 19-12-2002 DE 69903889 T2 10-04-2003 EP 0974620 A1 26-01-2000 ES 2187101 T3 16-05-2003 JP 2000053878 A 22-02-2000 TW 469288 B 21-12-2001 US 5883233 A 16-03-1999
US 5288294	A	22-02-1994	DE 59208643 D1 31-07-1997 EP 0534903 A1 31-03-1993 ES 2104881 T3 16-10-1997 JP 3157305 B2 16-04-2001 JP 5263396 A 12-10-1993 US 5288294 A 22-02-1994
US 5559217	A	24-09-1996	NONE