

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
20 April 2006 (20.04.2006)

PCT

(10) International Publication Number
WO 2006/041736 A1

- (51) International Patent Classification:
C08L 57/00 (2006.01) C08L 91/00 (2006.01)
- (21) International Application Number:
PCT/US2005/035327
- (22) International Filing Date:
30 September 2005 (30.09.2005)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
60/617,594 8 October 2004 (08.10.2004) US
- (71) Applicant (for all designated States except US): **EXXON-MOBIL CHEMICAL PATENTS INC.** [US/US]; 5200 Bayway Drive, Baytown, TX 77520 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **KAPPES, Nicolas** [FR/BE]; Rue Sainte Anne, 8, B-1000 Bruxelles (BE). **LECHAT, Jacques, B.** [FR/BE]; Avenue de l'Oree, 24, B-1420 Braine l'Alleud (BE). **LACOSTE, Olivier, H., V.** [FR/FR]; 41 Rue Molière, F-92500 Rueil-Malmaison (FR). **DICTUS, Martine** [BE/BE]; Stampmolen 16, B-2830 Willebroek (BE).
- (74) Agent: **WELCH, Jeremy, P.**; ExxonMobil Chemical Company, PO Box 2149, Baytown, TX 77522-2149 (US).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM,

AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii))

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 2006/041736 A1

(54) Title: COMBINATIONS OF TACKIFIER AND POLYALPHAOLEFIN OIL

(57) Abstract: The use of a polyalphaolefin oil or combinations of polyalphaolefin oils to modify the softening point characteristics of a tackifier and compositions containing a tackifier and polyalphaolefin oil are disclosed herein.

COMBINATIONS OF TACKIFIER AND POLYALPHAOLEFIN OIL

RELATED APPLICATIONS

[0001] This application is related to and claims priority from USSN 60/617,594, incorporated herein by reference.

BACKGROUND

[0002] The present invention relates to combinations of polyalphaolefin oils and tackifiers.

[0003] Tackifiers may be commonly used in adhesive systems in combination with one or more natural or synthetic elastomers, and/or other ingredients, such as plasticizers, waxes, fillers, and/or antioxidants. Tackifiers are generally either solid or liquid at room temperature and generally have corresponding high or low softening points. The performance of these tackifiers may also vary according to softening point.

[0004] High softening point tackifiers increase the softening point of the adhesive formulation and are easily handled. These tackifiers may also have softening points greater than about 80°C and are solid at or near room temperature (around 20°C - 25°C). Lower softening point tackifiers are liquid at room temperature, with softening points generally less than about 25°C. Because they are liquid they may be more difficult to handle, but they may also provide the benefits of decreasing the softening point and the glass transition temperature (T_g) of the adhesive.

[0005] Medium softening point (MSP) tackifiers may generally be semi-solid materials at room temperature. Although they appear solid, they will flow over time. Such resins have softening points ranging from about 25-80°C, more likely 35-65°C, and more likely within the range of 50-60°C.

[0006] Adhesive formulations incorporating MSP tackifiers have lower volatilities than those formulated with a liquid resin and/or plasticizing oil, and can be applied over a broader range of temperatures than similar systems formulated with normally liquid and/or normally solid resins and/or processing oils. In addition, aging studies indicate that the adhesives incorporating MSP tackifiers bleed less and stain less than adhesive formulated with conventional tackifiers and conventional plasticizers.

[0007] Control of the softening point is important in the production of tackifiers. The softening point of the tackifying resin is generally determined by the stripping conditions. Targeting a specific softening point while maintaining the resin properties may be difficult. It would be beneficial to find an alternate and less difficult method to target and control the softening point of the tackifier, without losing any of the tackifier properties.

[0008] Alternatively, other routes to manufacture MSP resins have been considered and disclosed herein are combinations of one or more conventional tackifiers and one or more polyalphaolefin oils (PAO(s)). The use of certain PAOs lowers the softening point characteristics of the tackifier, which can be controlled by varying the amount or type of PAO selected. This allows tackifier manufacturers and adhesive formulators to target a specific softening point without the difficulties normally encountered during manufacturing or the drawbacks associated with using conventional plasticizers or processing oils.

SUMMARY

[0009] The embodiments disclosed herein include a composition comprising at least one tackifier and a polyalphaolefin oil (PAO) or combination of one or more PAOs, wherein the PAO or combination of PAOs has (i) a Kinematic viscosity \leq about 10.5 mm²/s at 100°C and/or (ii) a pour point \leq about -38°C. A process is also disclosed which comprises mixing at least one tackifier and at least one PAO having one or more of the properties described herein. Also disclosed is the use of one or more PAOs to lower the softening point characteristics of a tackifier or combination of tackifiers.

DETAILED DESCRIPTION

[0010] The compositions disclosed herein generally comprise a tackifier and a

polyalphaolefin oil (PAO). In certain embodiments the compositions may consist or consist essentially of at least one tackifier and at least one PAO. Additional embodiments disclosed herein include adhesives comprising the aforementioned combinations, masterbatches useful in producing adhesives, and processes for making suitable mixtures, masterbatches and adhesives containing the tackifier and PAO.

[0011] The compositions described herein preferably comprise from about 99.99 to 20 wt% tackifier(s) and about 80 to 0.01 wt% PAO(s) based on the weight of the tackifier(s) and PAO(s). When referring to compositional amounts of the tackifier and PAO, the amounts refer to the total amount of tackifier(s) and PAO(s) if the composition comprises more than one of either component. The final compositional amounts will depend on the desired softening point or other characteristic(s) desired by the end user.

[0012] The term "about" as used herein with respect to numerical ranges applies to both the upper and lower end of the range.

[0013] The amount of PAO(s) (based on the weight of tackifier and PAO) preferably ranges from about 0.01-80% wt, more preferably about 1-75 wt%, more preferably about 2-50 wt%, more preferably about 2-40 wt%, more preferably about 3-30 wt%, more preferably about 4-30 wt%, more preferably about 4-25 wt%, more preferably about 5-20 wt%. Other suitable ranges include from about 5-15 wt%, about 10-15 wt%, about 5-12 wt%, about 12-20 wt%, and about 12-25 wt%.

[0014] Corresponding amounts of tackifier (based on the weight of tackifier and PAO) preferably range from about 20-99.99 wt%, more preferably about 25-99 wt%, more preferably about 50-98 wt%, more preferably about 60-98 wt%, more preferably about 70-97 wt%, more preferably about 70-96 wt%, more preferably about 75-96 wt%, more preferably about 80-95 wt%. Other corresponding ranges of tackifier include about 85-95 wt%, about 85-90 wt%, about 88-95 wt%, about 80-88 wt%, and about 75-88 wt%.

[0015] Exemplary tackifiers include aliphatic hydrocarbon resins, hydrogenated aliphatic hydrocarbon resins, aromatic modified aliphatic hydrocarbon resins, hydrogenated aromatic modified aliphatic hydrocarbon resins,

polycyclopentadiene resins, hydrogenated polycyclopentadiene resins, cycloaliphatic hydrocarbon resins, hydrogenated cycloaliphatic resins, cycloaliphatic/aromatic hydrocarbon resins, hydrogenated cycloaliphatic/aromatic hydrocarbon resins, hydrogenated aromatic hydrocarbon resins, maleic acid/anhydride modified tackifier, terpene modified aromatic and/or aliphatic hydrocarbon resin, hydrogenated terpene modified aromatic and/or aliphatic hydrocarbon resin, polyterpene resins, hydrogenated polyterpene resins, aromatic modified polyterpene resins, hydrogenated aromatic modified polyterpene resins, terpene-phenol resins, hydrogenated terpene-phenol resins, gum rosin resins, hydrogenated gum rosin resin, gum rosin ester resins, hydrogenated gum rosin ester resins, wood rosin resin, hydrogenated wood rosin resins, wood rosin ester resins, hydrogenated wood rosin ester resins, tall oil rosin resins, hydrogenated tall oil rosin resins, tall oil rosin ester resins, hydrogenated tall oil rosin ester resins, rosin acid resins, hydrogenated rosin acid resins, and mixtures of two or more thereof. These materials are preferably low molecular weight materials having a weight-average molecular weight (Mw) below 10,000, more preferably below 5,000, more preferably below 2500, more preferably below 2000, with suitable ranges falling in between 1 and 1000, more preferably 500-2000, and more preferably 500-1000.

[0016] Suitable commercially available tackifiers include ESCOREZ[®] 1000, 2000 and 5000 series hydrocarbon resins, ECR-373, Oppera[™] PR 100, 101, 102, 103, 104, 105, 106, 111, 112, 115, and 120, available from ExxonMobil Chemical Company, ARKON[™] M series, Arkon P series and SUPER ESTER[™] rosin esters available from Arakawa Chemical Company of Japan, SYLVAREST[™] phenol modified styrene- α methyl styrene resins, styrenated terpene resins, ZONATAC terpene-aromatic resins, and terpene phenolic resins available from Arizona Chemical Company of Jacksonville, Florida, SYLVATACT[™] and SYLVALITE[™] rosin esters available from Arizona Chemical Company, NORSOLENE[™] aliphatic aromatic resins available from Cray Valley of France, DERTOPHENE[™] terpene phenolic resins available from DRT Chemical Company of Landes, France, EASTOTACT[™] resins, PICCOTACT[™] C₅/C₉ resins, REGALITE[™] and REGALREZ[™] aromatic and REGALITE[™]

cycloaliphatic/aromatic resins available from Eastman Chemical Company of Kingsport, TN, WINGTACK™ resins available from Goodyear Chemical Company of Akron, Ohio, FORAL™, PENTALYN™, AND PERMALYN™ rosins and rosin esters available from Eastman Chemical Company, QUINTONE™ acid modified C₅ resins, C₅/C₉ resins, and acid modified C₅/C₉ resins available from Nippon Zeon of Japan, and LX™ mixed aromatic/cycloaliphatic resins available from Neville Chemical Company of Pittsburgh, Pennsylvania, CLEARON hydrogenated terpene aromatic resins available from Yasuhara Chemical of Japan. The preceding examples are illustrative only and by no means limiting.

[0017] These tackifiers before combination with the PAO generally have a Ring and Ball softening point (measured according to ASTM E-28) of about 10-200°C, more preferably about 10-160°C, more preferably about 25-140°C, more preferably about 60-130°C, more preferably about 70-130°C, more preferably about 80-120°C, more preferably about 85-115°C, and more preferably about 90-110°C, wherein any upper limit and any lower limit of softening point may be combined for a preferred softening point range. As used herein, softening point (°C) is the Ring & Ball softening point, unless otherwise indicated as Mettler softening point, which is measured according to ASTM D 6090-99.

[0018] Tackifiers are well known and are produced, for example, by Friedel-Crafts polymerisation of various feeds, which may be pure monomer feeds or refinery streams containing mixtures of various unsaturated materials. Generally speaking, the purer the feed the easier to polymerise. For example pure styrene, pure α -methyl styrene and mixtures thereof are easier to polymerise than a C₈/C₉ refinery stream. Similarly, pure or concentrated piperylene is easier to polymerise than C₄-C₆ refinery streams. These pure monomers are, however, more expensive to produce than the refinery streams which may be by-products of large volume refinery processes.

[0019] Aliphatic hydrocarbon resins can be prepared by cationic polymerisation of a cracked petroleum feed containing C₄, C₅, and C₆ paraffins, olefins, and conjugated diolefins referred to herein as C₅ monomers. As used

herein, C₅ monomers preferably excludes DCPD monomers removed by thermal soaking as described below. These C₅ monomer streams comprise cationically and thermally polymerisable monomers such as butadiene, isobutylene, 1,3-pentadiene (piperylene) along with 1,4-pentadiene, cyclopentene, 1-pentene, 2-pentene, 2-methyl-1-pentene, 2-methyl-2-butene, 2-methyl-2-pentene, isoprene, cyclohexene, 1-3-hexadiene, 1-4-hexadiene, cyclopentadiene, and dicyclopentadiene. To obtain these feeds the refinery streams are preferably purified usually by both fractionation and treatment to remove impurities. In some embodiments, the C₅ feed stream may include at least some (preferably less than 2 wt%) cyclopentadiene (CPD) and substituted cyclopentadiene (e.g., methylcyclopentadiene) components. These components are optionally separated from the C₅ monomer streams by thermal soaking wherein the feed stream is heated to a temperature between 100°C and 160°C, preferably between 100°C and 150°C, for 0.5 to 6 hours, followed by separation of the DCPD monomers to reduce the level of cyclopentadiene and/or dicyclopentadiene in the C₅ monomer stream to preferably below 2 wt%. Low temperature heat soaking is preferred in order to limit the cyclic diene (cyclopentadiene and methylcyclopentadiene) co-dimerisation with C₅ linear conjugated dienes (isoprene and pentadienes 1,3 cis- and trans-). The thermal soaking step preferably dimerizes the cyclopentadiene and substituted cyclopentadiene, making separation from the C₅ monomer stream easier. After fractionation and, if carried out, thermal soaking, the feedstock is preferably subjected to distillation to remove cyclic conjugated diolefins which are gel precursors (cyclopentadiene and methylcyclopentadiene being removed as dimers, trimers, etc.).

[0020] One example of a C₅ monomer stream is a steam cracked petroleum stream boiling in the range of -10°C to 100°C. Examples of commercial samples of C₅ monomer feedstocks include Naphtha Petroleum 3 Piperylenes from Lyondell Petrochemical Company of Houston, Tex., regular Piperylene Concentrate or Super Piperylene Concentrate both from Shell Nederland Chemie B.V. of Hoogvilet, the Netherlands.

[0021] The resin polymerization feed may also comprise C₈-C₁₀ aromatic monomers (referred to herein as C₉ monomers) such as styrene, indene,

derivatives of styrene, derivatives of indene, and combinations thereof. Particularly preferred aromatic olefins include styrene, α -methylstyrene, β -methylstyrene, indene, methylindenes and vinyl toluenes. One example of a C₉ monomer stream is a steam cracked petroleum stream boiling in the range of -10°C to 210°C (135°C to 210°C if the C₅ monomers and DCPD components are not present). Examples of commercial C₉ monomer feedstocks include LRO-90 from Lyondell Petrochemical Company, Houston, Tex., DSM C₉ Resinfeed Classic from DSM, Geleen, the Netherlands, RO-60 and RO-80 from Dow Chemical Company of Midland, Mich., and Dow Resin Oil 60-L from the Dow Chemical Company of Terneuzen, the Netherlands.

[0022] In addition to the reactive components, non-polymerisable components in the feed may include saturated hydrocarbons such as pentane, cyclopentane, or 2-methyl pentane that can be co-distilled with the unsaturated components. This monomer feed can be co-polymerised with other C₄ or C₅ olefins or dimers. Preferably, however, the feeds are purified to remove unsaturated materials that adversely affect the polymerisation reaction or cause undesirable colors in the final resin (e.g., isoprene). This is generally accomplished by fractionation. In one embodiment, polymerization is conducted using Friedel-Crafts polymerisation catalysts such as supported or unsupported Lewis acids (e.g., boron trifluoride (BF₃), complexes of boron trifluoride, aluminium trichloride (AlCl₃), complexes of aluminium trichloride or alkyl aluminium halides, particularly chlorides). Suitable reaction conditions for Friedel-Crafts polymerization include temperatures of -20°C to 100°C, pressures of 100-2000 kPa. In one embodiment, C₅ and C₉ monomers are polymerized by such a process.

[0023] Typically, the feed stream includes between 20-80 wt% monomers and 20-80 wt% solvent. Preferably, the feed stream includes 30-70 wt% monomers and 30-70 wt% of solvent. More preferably, the feed stream includes 50-70 wt% monomers and 30-50 wt% of solvent. The solvent may include an aromatic solvent, which may be toluenes, xylenes, other aromatic solvents, aliphatic solvents and/or mixtures of two or more thereof. The solvent is preferably recycled. The solvent may comprise the unpolymerisable component of the feed. The solvents generally contain less than 250 ppm water, preferably less than 100

ppm water, and most preferably less than 50 ppm water.

[0024] In another embodiment, the feed stream includes 30-95 wt% of C₅ monomers, as described above and 5-70 wt% of a co-feed including at least one member selected from the group consisting of pure monomer, C₉ monomers, and terpenes. Preferably, the feed stream includes about 50-85 wt% of C₅ monomers and about 15-50 wt% of a co-feed, including at least one member selected from the group consisting of pure monomer, C₉ monomers, and terpenes.

[0025] The monomer feed can be co-polymerised with C₄ or C₅ olefins or their olefinic dimers as chain transfer agents. Up to 40 wt%, preferably up to 20 wt%, of chain transfer agents may be added to obtain resins with lower and narrower molecular weight distributions than can be prepared from using the monomer feed alone. Chain transfer agents stop the propagation of a growing polymer chain by terminating the chain in a way, which regenerates a polymer initiation site. Components, which behave as chain transfer agents in these reactions include but are not limited to, 2-methyl-1-butene, 2-methyl-2-butene or dimers or oligomers of these species. The chain transfer agent can be added to the reaction in pure form or diluted in a solvent.

[0026] Another type of tackifier resin are DCPD resins which may be obtained by or derived from thermal polymerisation of a feed comprising unsaturated monomers of DCPD and/or substituted DCPD. In one embodiment, the feed also comprises aromatic monomers as previously described. In such embodiments, a mixture of (a) DCPD stream, preferably a steam cracked petroleum distillate boiling in the range 80-200°C, more preferably 140°C to 200°C, containing dimers and codimers of cyclopentadiene and its methyl derivatives together with (b) C₉ monomers, preferably a steam cracked distillate boiling in the range 150-200°C comprising α -methyl styrene, vinyl toluenes, indene and methyl indene with other C₉ and C₁₀ aromatics.

[0027] In one embodiment, the resin is preferably obtained by or derived from thermal polymerisation of a feed comprising C₅ monomers and C₉ monomers as previously described. In such embodiments, a mixture of (a) C₅ monomers, preferably, a steam cracked petroleum distillate boiling in the range 80-200°C containing C₅ monomers together with (b) C₉ monomers, preferably a steam

cracked distillate boiling in the range 150-200°C comprising α -methyl styrene, vinyl toluenes, indene and methyl indene with other C₈-C₁₀ aromatics, in the weight ratio (a:b) between 90:10 to 50:50 is heated in a batch polymerization reactor to 160-320°C at a pressure of 9.8×10^5 - 20×10^5 Pa, more preferably 9.8×10^5 - 11.7×10^5 Pa for 1.2 to 4 hrs, more preferably 1.5 to 4 hrs.

[0028] The resin material can also be hydrogenated to reduce coloration and improve color stability. Any of the known processes for catalytically hydrogenating resin material can be used. In particular the processes disclosed in US 5171793, US 4629766, US 5502104 and US 4328090 and WO 95/12623 are suitable. Generic hydrogenation treating conditions include reactions in the temperature range of about 100-350°C and pressures of between five atmospheres (506 kPa) and 300 atm (30390 kPa) (and up to 400 atm) hydrogen, for example, 10-275 atm (1013-27579 kPa). In one embodiment the temperature is in the range including 180-330°C and the pressure is in the range including 15195-20260 kPa hydrogen. The hydrogen to feed volume ratio to the reactor under standard conditions (25°C, 1 atm (101 kPa) pressure) typically can range from 20:1-200:1; for water-white resins 100:1-200:1 is preferred. The hydrogenated product may be stripped to remove low molecular weight by-products and any solvent.

[0029] The hydrogenation of the resin material may be carried out via molten or solution based processes by either a batch wise or, more commonly, a continuous process. Catalysts employed for the hydrogenation of tackifiers are typically supported monometallic and bimetallic catalyst systems based on group 6, 8, 9, 10 or 11 elements. Catalysts such as nickel on a support (for example, nickel on alumina, nickel on charcoal, nickel on silica, nickel on kieselguhr, etc), palladium on a support (for example, palladium on silica, palladium on charcoal, palladium on magnesium oxide, etc) and copper and/or zinc on a support (for example copper chromite on copper and/or manganese oxide, copper and zinc on alumina, etc) are good hydrogenation catalysts. The support material is typically comprised of such porous inorganic refractory oxides as silica, magnesia, silica-magnesia, zirconia, silica-zirconia, titania, silica-titania, alumina, silica-alumina, alumina-silicate, etc, with supports containing γ -alumina being highly preferred. Preferably, the supports are essentially free of crystalline molecular sieve

materials. Mixtures of the foregoing oxides are also contemplated, especially when prepared as homogeneously as possible. Useful support materials include those disclosed in the US Patents 4686030, 4846961, 4500424, and 4849093, which are incorporated by reference. Suitable supports include alumina, silica, carbon, MgO, TiO₂, ZrO₂, Fe₂O₃ or mixtures thereof. Other suitable processes for hydrogenating tackifiers are disclosed in US Patents 5820749 and 4629766 and EP 0082726, which are incorporated by reference.

[0030] In some embodiments, the tackifier is preferably hydrogenated so that its initial Yellowness Index (YI) color is less than 20, more preferably less than 15, more preferably less than 10, more preferably less than 5 and more preferably less than 1. When color is measured according to the Gardner color scale, the color is preferably less than 2.6, more preferably less than 1.9, and more preferably less than 1.

[0031] Hydrogenated tackifiers preferably contain less than 50% aromatic protons, more preferably less than 40% aromatic protons, more preferably less than 25% aromatic protons, more preferably less than 15% aromatic protons, more preferably less than 10% aromatic protons, more preferably less than 5% aromatic protons, more preferably less than 4% aromatic protons, more preferably less than 3% aromatic protons, more preferably less than 2% aromatic protons, more preferably less than 1% aromatic protons.

[0032] As used herein aromatic content and olefin content are measured by ¹H-NMR as measured directly from the ¹H NMR spectrum from a spectrometer with a field strength greater than 300 MHz, most preferably 400 MHz (frequency equivalent). Aromatic content is the integration of aromatic protons versus the total number of protons. Olefin proton or olefinic proton content is the integration of olefinic protons versus the total number of protons.

[0033] The resulting tackifier may have a number-average molecular weight (M_n) of 400-3000, a weight-average molecular weight (M_w) of 500-6000, a z-average molecular weight (M_z) of 700-15,000 and a polydispersity (PD) as measured by M_w/M_n between 1 and 45. As used herein, molecular weights (number average molecular weight (M_n), weight average molecular weight (M_w), and z-average molecular weight (M_z)) are measured by Size Exclusion

Chromatography using a Waters 150 Gel Permeation Chromatograph equipped with a differential refractive index detector and calibrated using polystyrene standards. Samples are run in tetrahydrofuran (THF) (45°C). Molecular weights are reported as polystyrene-equivalent molecular weights and are generally measured in g/mol.

PAOs

[0034] The PAO may comprise oligomers of linear olefins having 5 to 14 carbon atoms, more preferably 6 to 12 carbon atoms, more preferably 8 to 10 carbon atoms. Preferred PAOs have the properties described herein. Preferred PAOs are hydrogenated to yield substantially (> 99 wt%) paraffinic materials.

[0035] When a combination of more than one PAOs is employed, it is preferred that the combination of PAOs have a pour point less than or equal to -38°C and/or a Kinematic viscosity less than or equal to $10.5\text{ mm}^2/\text{s}$ at 100°C . Such formulations may include a PAO having one or more of the properties described herein and another PAO with properties that may or may not have one or more of the properties described herein as long as the combination of PAOs have a pour point less than or equal to -38°C and/or a Kinematic viscosity less than or equal to $10.5\text{ mm}^2/\text{s}$ at 100°C .

[0036] The PAO(s) preferably have a viscosity index ("VI"), as determined by ASTM D-2270 of 100 or more, preferably 110 or more, and more preferably 120 or more. Preferred ranges for VI include from 100-180, more preferably 100-170, more preferably 100-160, more preferably 100-150, more preferably 110-150, more preferably 110-140, and more preferably 120-140.

[0037] Preferably, the PAO has a pour point \leq about -38°C (as determined by ASTM D 97), more preferably \leq about -39°C , more preferably \leq about -40°C , more preferably \leq about -41°C , more preferably \leq about -42°C , more preferably \leq about -43°C , more preferably \leq about -44°C , more preferably \leq about -45°C , more preferably \leq about -50°C , more preferably \leq about -55°C , more preferably \leq about -60°C . Preferred ranges for the pour point include from about -38°C to -75°C , more preferably from about -38° to -70°C , more preferably from about

-40°C to -75°C, more preferably from about -40°C to -70°C, more preferably from about -40°C to -65°C, more preferably from about -42°C to -65°C, more preferably from about -45°C to -65°C.

[0038] The PAO may comprise C₂₀ to C₁₅₀₀ paraffins, preferably C₄₀ to C₁₀₀₀ paraffins, preferably C₅₀ to C₇₅₀ paraffins, preferably C₅₀ to C₅₀₀ paraffins. The PAOs are preferably oligomers (are dimers, trimers, tetramers, pentamers, etc.) of C₅ to C₁₄ α-olefins, C₆ to C₁₂ α-olefins and/or C₈ to C₁₂ α-olefins. Suitable olefins include 1-pentene, 1-hexene, 1-heptene, 1-octene, 1-nonene, 1-decene, 1-undecene and 1-dodecene. In one embodiment, the olefin is 1-decene, and the PAO is a mixture of dimers, trimers, tetramers and pentamers (and higher) of 1-decene. Preferred PAO's are described more particularly in, for example, U.S. Patents 5,171,908, and 5,783,531 and in SYNTHETIC LUBRICANTS AND HIGH-PERFORMANCE FUNCTIONAL FLUIDS 1-52 (Leslie R. Rudnick & Ronald L. Shubkin, ed. Marcel Dekker, Inc. 1999). For example, the methods disclosed by U.S. Pat. Nos. 4, 149,178 or 3,382,291 may be conveniently used to produce PAOs. Other descriptions of PAO synthesis are found in the following U.S. Patents: 3,742,082, 3,769,363, 3,876,720, 4,239,930, 4,367,352, 4,413,156, 4,434,408, 4,910,355, 4,956,122, and 5,068,487. Preferred PAOs are hydrogenated.

[0039] PAOs useful in the present invention typically possess a number average molecular weight (Mn) of from 100-21,000, more preferably 200-10,000, more preferably 200-7,000, more preferably 200-2,000, and more preferably from 200-500.

[0040] Preferred PAOs have Kinematic viscosities (mm²/s (cSt)) (as measured by ASTM 445 at 100°C) ≤ about 10.5, more preferably ≤ about 10.4, more preferably ≤ about 10.3, more preferably ≤ about 10.25, more preferably ≤ about 10.2, more preferably ≤ about 10.1, more preferably 10.0. Suitable ranges of Kinematic viscosity @ 100°C include about 0.1-10.5, more preferably about 0.5-10.5, more preferably about 0.5-10.4, more preferably about 1.0-10.25, more preferably about 1.5-10.0 and more preferably about 2.0 to 10.0. Other preferred ranges may include about 0.1-10, more preferably about 1.8-10, more preferably

about 1.8-8, more preferably about 2-6, more preferably about 3-6 and more preferably about 4-6. Other suitable ranges include about 2, about 2.25, about 2.5, about 3, or about 4 as a lower limit and include any upper limit of about 10, about 9.5, about 9.25, about 9, about 8, about 7.5, about 7, or about 6.5.

[0041] Preferred PAOs have Kinematic viscosities (mm^2/s (cSt))(as measured by ASTM 445 at 40°C) \leq about 120, more preferably \leq about 110, more preferably \leq about 100, more preferably \leq about 80, more preferably \leq about 75, more preferably \leq about 70. Suitable ranges of Kinematic viscosity @ 40°C include about 5-120, more preferably about 5-100, more preferably about 5-75, more preferably about 5-65, more preferably about 5-60, more preferably about 5-50, more preferably about 10-50, and more preferably about 15-50.

[0042] Preferred PAOs have a flash point measured the open cup method (ASTM- D92) of \geq about 140°C , more preferably \geq about 150°C , more preferably \geq about 160°C , more preferably \geq about 175°C , more preferably \geq about 200°C , with suitable ranges of flash point falling from about $140^\circ\text{-}300^\circ\text{C}$, more preferably about $160^\circ\text{-}300^\circ\text{C}$, more preferably about $175^\circ\text{C-}300^\circ\text{C}$, more preferably about $200^\circ\text{C-}275^\circ\text{C}$, more preferably about $210^\circ\text{-}275^\circ\text{C}$, and more preferably about $210^\circ\text{C-}250^\circ\text{C}$.

[0043] Useful PAO's include those sold under the tradenames SYNFLUID™ available from ChevronPhillips Chemical Co. in Pasadena, Texas, DURASYN™ available from BP Amoco Chemicals in London England, NEXBASE™ available from Fortum Oil and Gas in Finland, SYNTON™ available from Crompton Corporation in Middlebury, Connecticut, USA, EMERY™ available from Cognis Corporation in Ohio, USA. Exemplary preferred polyalphaolefin oils include DURASYN™ 162, 164, 166 and 168 available from BP Chemicals, SYNFLUID™ 2, 2.5, 4, 5, 6, 7 and 8 available from ChevronPhillips Chemical Company, EMERY™ 3004, 3006, and 3008 available from Cognis, and NEXBASE™ 2002, 2004, 2004FG, 2006, 2006FG, 2008 and 2008FG available from Fortum Oil and Gas of Finland, SYNTON™ 40 and 100 available from Crompton Corporation in Connecticut, USA. Suitable PAOs available from ExxonMobil Chemical Company in Houston, TX, USA include:

Grade	Specific Gravity @ 15.6°C	Kinematic viscosity @ 100°C	Kinematic viscosity @ 40°C	Pour Point (°C)	Flash Point (°C)	Color ASTM
SPECTRASYN 2	0.798	1.68	5.30	- 60	155	< 0.5
SPECTRASYN 2B	0.802	1.80	5.80	- 54	150	< 0.5
SPECTRASYN 4	0.818	4.00	18.0	- 57	218	< 0.5
SPECTRASYN 5	0.824	5.10	25.0	- 57	240	< 0.5
SPECTRASYN 6	0.826	5.80	30.0	- 57	240	< 0.5
SPECTRASYN 8	0.833	7.90	47.0	- 54	250	< 0.5
SPECTRASYN 10	0.835	10.0	68.0	- 54	265	< 0.5

[0044] Other exemplary PAOs include mixtures of any two or more of the above or mixtures of any one or more of the above with one or more any other PAO.

[0045] As illustrated below in the Examples, the softening point of the tackifier/PAO (relative to the softening point of the tackifier) is generally lower, depending on the concentration of PAO. This allows combining of PAOs and tackifiers to target the softening point of the tackifier for particular end uses on an as needed basis. The softening point of the tackifier PAO combinations is preferably below about 120°C, more preferably below about 110°C, more preferably below about 100°C, more preferably below about 90°C, and more preferably below about 80°C. Suitable ranges for softening point of the tackifier/PAO combination include about 25-80°C, more preferably about 30-70°C, more preferably about 35-65°C, more preferably about 40-60°C, and more preferably about 50-60°C.

Blending into Adhesive Components and Compositions

[0046] Any of the previously described embodiments may be combined with other adhesive components and formulated into adhesives, hot melt adhesives (HMAs), pressure sensitive adhesives (PSAs), and/or hot melt pressure sensitive adhesive (HMPSAs). Adhesive applications include, but are not limited to, woodworking, packaging, bookbinding, tapes, labels, non-wovens or disposables.

The embodiments described herein can also be formulated into compositions for sealants, rubber compounds, pipe wrapping, carpet backing, contact adhesives, road-marking, tires and/or inks. These compositions may be used without further dilution as in the case of HMAs or HMPSAs they may be diluted in appropriate solvents to form solvent-based adhesives (SBAs) or dispersed in water to form resin emulsions for water-based adhesives (WBAs). In general, any of the adhesive compositions described herein comprise (based on the total weight of the adhesive formulation) 0.5-80 wt% tackifier-PAO combinations as described herein, up to 80 wt% base polymer, with the remainder comprising other additives such as a filler or wax or other materials as described below. Other preferred ranges for the tackifier-PAO combination in the adhesive includes about 1-75 wt%, about 5-70 wt%, about 10-70 wt%, about 15-70 wt%, and about 15-65 wt%.

[0047] Any of the previously described embodiments may be combined or combined with a polyolefin (base polymer) to form an adhesive. Typical base polymers include polyethylene, ethylene copolymerized with one or more C₃ to C₂₀ linear, branched, or cyclic α -olefins, polypropylene, propylene copolymerized with one or more of ethylene and/ or C₄ to C₂₀ linear, branched, or cyclic α -olefins, polybutylene, polybutylene copolymerized with one or more of C₅ to C₂₀ linear, branched, or cyclic α -olefins, low density polyethylene (LDPE) (density 0.915 to less than 0.935 g/cm³) linear low density polyethylene (LLDPE), ultra low density polyethylene (density 0.86 to less than 0.90 g/cm³), very low density polyethylene (density 0.90 to less than 0.915 g/cm³), medium density polyethylene (density 0.935 to less than 0.945 g/cm³), high density polyethylene (HDPE) (density 0.945 to 0.98 g/cm³). Other hydrocarbon polymers (or copolymers of) include: polybutene-1, polyisobutylene, polybutene, polyisoprene, polybutadiene, butyl rubber, amorphous polypropylene, ethylene propylene diene monomer rubber, natural rubber, styrene butadiene rubber, copolymers and halogenated copolymers of isobutylene and para-alkylstyrene, elastomers such as ethylene-propylene rubber (EPR), vulcanized EPR, EPDM, nylons, polycarbonates, PET resins, polymers of aromatic monomers such as polystyrene, copolymers of isobutylene and para-alkyl styrene, high molecular weight HDPE, low molecular weight HDPE, graft copolymers generally, polyacrylonitrile

homopolymer or copolymers, thermoplastic polyamides, polyacetal, polyvinylidene fluoride and other fluorinated elastomers, polyethylene glycols, polyisobutylene, or blends thereof. Preferred α -olefins include propylene, butene, pentene, hexene, heptene, octene, nonene, dodecene, cyclopentene, 3,5,5-trimethylhexene-1, 3-methylpentene-1, 4-methyl pentene-1 and terpolymers of the above monomers. In another embodiment, the copolymer comprises a terpolymer of (i) ethylene and/or (ii) a C_3 to C_{20} comonomer, and (iii) a diene. Preferred dienes include butadiene, pentadiene, hexadiene, norbornene, ethylidene norbornene, vinyl norbornene, dicyclopentadiene, and substituted versions thereof. The architecture of such polymers may be linear, substantially linear, short-chain branched, long-chain branched, star branched or any other combination thereof. The branches or arms may be the same as the main backbone or different such as branch-block polymers or multi-armed stars.

[0048] Suitable polymers also include polyisoprene, block copolymers of styrene and one or more conjugated dienes such as SI (Styrene-Isoprene), SBS (Styrene-Butadiene-Styrene), SB (Styrene-Butadiene), SIS (Styrene-Isoprene-Styrene), SEP (Styrene-Ethylene/Propylene), SEB (Styrene-Ethylene/Butylene), SEBS (Styrene-Ethylene/Butylene-Styrene), SEPS (Styrene-Ethylene/Propylene-Styrene), where the architecture of the block copolymers includes linear, radial or multi-arm star, multi-branched and may include various combinations of styrene (S), isoprene (I), or butadiene (B), which may or may not be hydrogenated, and mixtures of two or more thereof. The styrene block copolymers may comprise tetrablock or pentablock copolymers selected from SISI, SISB, SBSB, SBSI, SIBS, ISISI, ISISB, BSISB, ISBSI, BSBSB, BSBSI, SIBSB, BSIBS, SIBSI, ISIBS, SIBSB, ISIBS. The block copolymers may be used on their own or mixed with other polymers or styrene block copolymers.

[0049] Any of the previously described embodiments may be combined with or formulated into adhesives comprising polar polymers. As used herein, polar polymers include homopolymers, copolymers, and terpolymers containing polar groups such as esters, ethers, ketones, amides, imides, alcohols, phenols, halides, acids, anhydrides, sulfides, nitriles, isocyanates, aromatic and heteroaromatic groups. These polar substituents may be found in the polymer backbone, pendant

to the polymer backbone or attached to an aromatic group that may be either incorporated in the polymer backbone or pendant to the polymer backbone. Suitable examples include copolymers of a C₂ to C₂₀ olefin, such as ethylene and/or propylene and/or butene with one or more polar monomers such as vinyl esters or alcohols, acids, anhydrides, acrylic or methacrylic acids or esters. Polar polymers also include any thermoplastic copolymer comprising a functional group capable of interacting with the unsaturated acid or anhydride group present with the resin material. Examples include, but are not limited to, polymers (or copolymers of) such as polyesters, polyamides, polyureas, polycarbonates, polyacrylonitriles, polyacrylates, polymethylacrylates, ethylene vinyl esters, halogenated polymers, polyvinyl chloride, polyethylene terephthalate, polybutylene terephthalate (PBT), polyacetal, acrylic or methacrylic acids, alkyl acrylates, or methacrylates, ethylene methyl acrylate, ethylene butyl acrylate, and the like. Accordingly, in one embodiment, the tackifier-PAO combination(s) may be formulated with a polar polymer, such as EVA. It may optionally comprise other components such as one or more waxes or oils.

[0050] Any of the previously described embodiments may be blended with grafted polymers or blends of grafted polymers and/or non-grafted polymers. Examples of polymers and of such blends include, but are not limited to, those described in US 5,936,058.

[0051] Any of the previously described embodiments may be blended with elastomers to form adhesive sealants. Preferred elastomers include natural rubber, polyisoprene, polybutadiene, copolymers of butadiene with styrene, copolymers of butadiene with acrylonitrile, butyl rubber, polychloroprene, ethylene/propylene rubber and elastomeric copolymers of ethylene, propylene and a non-conjugated diene, styrenic block copolymers such as block copolymers of styrene and or α -methyl styrene with an alkadiene (such as isoprene or butadiene) in linear, radial, and/or tapered form.

[0052] In one embodiment, the base polymer may be a polymer produced using a metallocene catalyst system. Typically, the metallocene homopolymers or copolymers are produced using mono- or bis-cyclopentadienyl transition metal catalysts in combination with an activator of alumoxane and/or a non-coordinating

anion in solution, slurry, high-pressure or gas phase. The catalyst system may be supported or unsupported and the cyclopentadienyl rings may be substituted or unsubstituted. Titanium, zirconium and hafnium are preferred transition metals. Several commercial products produced with such catalyst/activator combinations are commercially available from ExxonMobil Chemical Company in Baytown, Texas under the tradenames EXCEED[®] and EXACT[®] or from Dow Chemical Company under the tradenames ENGAGE[™] and AFFINITY[™].

[0053] The metallocene produced copolymers described above preferably have a polydispersity less than 4 and a composition distribution breadth index (CDBI) of 50 % or more, preferably above 60%, even more preferably above 70%. In one embodiment, the CDBI is above 80%, even more preferably above 90%, even more preferably above 95%. In one embodiment, the polyethylene copolymer has a CDBI between 60-85%, even more preferably between 65-85%. Composition Distribution Breadth Index (CDBI) is a measure of the composition distribution of monomer within the polymer chains and is measured by the procedure described in PCT publication WO 93/03093, published February 18, 1993 including that fractions having a weight average molecular weight (Mw) below 15000 are ignored when determining CDBI.

[0054] Any of the previously described embodiments may be admixed with additives well known in the art in adhesive applications. In some embodiments, suitable adhesive applications may include additives in an amount of \leq about 30 wt%, more preferably \leq about 25 wt%, more preferably \leq about 20 wt%, more preferably \leq about 15 wt%, more preferably \leq about 10 wt%, and more preferably \leq about 5 wt%.

[0055] In adhesive applications where additional processing oils (such as naphthenic, paraffinic, aromatic oils, mineral oils, white oils, hydrogenated mineral oils and the like) are present, it is preferred that such materials is present in amounts (based on the weight of the adhesive formulation) \leq about 17 wt%, more preferably \leq about 15 wt%, more preferably \leq about 12 wt%, more preferably \leq about 10 wt%, more preferably \leq about 7 wt%, more preferably \leq about 5 wt%, and more preferably \leq about 2 wt%. In adhesives applications, suitable oils

include FLEXON[®] or PRIMOL[®] grades available from ExxonMobil Chemical Company, KAYDOL oil available from Crompton-Witco, NYFLEX grades available from Nynas of Sweden, EDELEX, GRAVEX and SHELLFLEX grades available from Shell Chemicals of Houston, TX.

[0056] Exemplary additives include, but are not limited to performance oils, plasticizers, defoamers, rheology modifiers, humectants, surfactants, flame retardants, fluorescing agents, compatibilizers, anti-microbial agents, anti-block, anti-static, antioxidants, cross-linking agents, silica, carbon black, talc, pigments, fillers, processing aids, UV stabilizers, neutralizers, lubricants, anti-slip agents, slip agents, surfactants and/or nucleating agents. Examples of common additives include: antioxidants such as Irganox[®] 1010, silicon dioxide, titanium dioxide, polydimethylsiloxane, talc, dyes, wax, calcium stearate, carbon black and glass beads. In adhesive applications, suitable synthetic waxes include paraffin waxes, microcrystalline waxes having melting points within a range from about 55°C to about 130°C and low molecular weight polyethylene and Fischer-Tropsch waxes, maleinized waxes. The wax content is preferably from about 1 to about 35 wt.% of the total blend composition.

[0057] Optional components in an HMA embodiment are plasticizers or other additives such as oils, tackifiers, surfactants, fillers, color masterbatches, and the like. Preferred plasticizers include mineral oils, polybutenes, phthalates, and the like. Particularly preferred plasticizers include phthalates such as diisodecyl phthalate (DIOP), diisononylphthalate (DINP), dioctylphthalates (DOP). Particularly preferred oils include aliphatic naphthenic oils.

[0058] Another optional component of an HMA composition is a low molecular weight product such as wax, oil, or low number-average molecular weight (Mn) polymer, (low meaning below number-average molecular weight (Mn) of 5000, preferably below 4000, more preferably below 3000, even more preferably below 2500). Preferred oils include aliphatic naphthenic oils, white oils, or the like. Preferred low number-average molecular weight (Mn) polymers include polymers of lower α olefins such as propylene, butene, pentene, and hexene. A particularly preferred polymer includes polybutene having a number-average molecular weight (Mn) of less than 1000. An example of such a polymer

is available under the trade name PARAPOL® 950 from ExxonMobil Chemical Company. PARAPOL® 950 is a liquid polybutene polymer having a number-average molecular weight (Mn) of 950 and a kinematic viscosity of 220 mm²/s (cSt) at 100 °C, as measured by ASTM D 445. Suitable embodiments of HMAs generally comprise 20-70 wt% tackifier-PAO combinations as described herein, 30-80 wt% base polymer, and 0-35 wt% wax.

[0059] HMAs embodiments can be used for disposable diaper and napkin chassis construction, elastic attachment in disposable goods, converting, packaging, labeling, bookbinding, woodworking, and other assembly applications. Particular examples include: baby diaper leg elastic, diaper frontal tape, diaper standing leg cuff, diaper chassis construction, diaper core stabilization, diaper liquid transfer layer, diaper outer cover lamination, diaper elastic cuff lamination, feminine napkin core stabilization, feminine napkins adhesive strip, industrial filtration bonding, industrial filter material lamination, filter mask lamination, surgical gown lamination, surgical drape lamination, and perishable products packaging. Suitable embodiments of woodworking applications comprise 30-50 wt% base polymers, preferably an EVA, 15-35 wt% tackifier-PAO combinations as described herein, 20-50 wt% fillers, such as calcium carbonate, barium sulfate, silica or titanium dioxide. Suitable embodiments of bookbinding applications include 35-45 wt% base polymer, preferably an EVA, 35-45 wt% tackifier-PAO combinations as described herein, and 10-25 wt% wax.

Pressure Sensitive Adhesives

[0060] Suitable pressure sensitive adhesives can be formulated using tackifier-PAO combinations described herein. Any of the previously described embodiments may be formulated into pressure sensitive adhesives that may be applied to any conventional backing layer such as paper, recycled paper, kraft paper, vellum paper, calendered paper, clayed paper, foil, polymeric film, release liners, woven or non-woven backing material to make for example, packaging tapes, masking tapes and labels.

[0061] An embodiment of a hot melt pressure sensitive adhesive is a pressure sensitive adhesive for tapes applications comprising 100 parts by weight of a base polymer, preferably a styrenic block copolymer, from 50 to 180 phr (parts per 100

parts by weight base polymer) of tackifier-PAO combination as described herein, and optionally an extender oil, and 0-5 phr of anti-oxidant.

[0062] Another embodiment is a pressure sensitive adhesive for label applications. These adhesives generally comprise or consist essentially of (based on the weight of the adhesive) from 40 to 90 wt% of tackifier-PAO combination as described herein, from 10 to 60 wt% of polymer, preferably any of the block copolymers previously described herein and/or mixture thereof, and the remainder comprising additives well known in the art such as anti-block, anti-static, antioxidants, UV stabilizers, neutralisers, lubricants, surfactants, antinucleating agents and/or fillers. Preferred additives include silica, titanium dioxide, polydimethylsiloxane, talc, dyes, wax, calcium stearate, calcium carbonate, carbon black, barium sulphate and magnesium silicate. Other preferred ranges for the tackifier-PAO blend in a Pressure Sensitive Adhesive include from 50 to 80 wt%, from 50 to 75 wt%, from 55 to 75 wt%, from 50 to 70 wt%, from 60 to 80 wt%, and from 60 to 75 wt%, depending on the application. Other preferred ranges for the polymer include from 20 to 50 wt%, from 20 to 45 wt%, from 25 to 50 wt%, from 25 to 45 wt%, from 30 to 50 wt%, and from 30 to 45 wt%, depending on the application.

[0063] A suitable application for such PSAs, particularly, HMPSAs is in the production of labels wherein the adhesive is applied to a release liner and subsequently laminated to a face stock. The laminate is then converted into a label stock. During label manufacture, a laminate of a face stock, pressure-sensitive adhesive layer, and a release liner, such as silicone-coated paper, which is passed through an apparatus that converts the laminate into commercially useful labels and label stock. The converting operation processes involve printing, die-cutting, and matrix stripping to leave labels on a release liner, marginal hole punching, perforating, fan folding, guillotining and the like. Such adhesives are suitable for applications requiring a typical die-cutting process, which involves cutting the laminate through to the release liner face. Other procedures involve cutting completely through the label laminate and include hole punching, perforating, and guillotining, particularly on flat sheets. Such PSAs and HMPSAs are also suitable for applications including direct coating or liner less products.

[0064] The PSA formulations described herein exhibit excellent performance at low temperatures and ambient temperatures. Enhanced performance at elevated temperatures may be accomplished by cross-linking techniques such as the electron beam (EB) radiation and ultraviolet (UV) radiation and chemical cross-linking. If employed, tackifying additives should be substantially saturated so that all of the energy of cure goes into cross-linking of the adhesives elastomeric components.

Additives for Road Marking

[0065] The embodiments disclosed herein may be formulated into thermoplastic road-marking (TRM) compositions. Such formulation comprises a resin, plasticizer or an oil, pigment, fillers, glass beads, and/or adhesion promoters. The tackifier-PAO combinations described herein may be used as the primary resin of the road-marking composition or as an additional additive to the road-marking composition. The road-marking compositions containing tackifier-PAO combinations can additionally comprise EVA, polyisobutylene, block copolymers as described herein, polyethylene waxes, hydrocarbon resins, rosin esters, rosin derivatives, maleic acid/anhydride modified tackifier and hydrogenated version of such resins.

[0066] One embodiment of a TRM application comprises 2-40 wt% tackifier-PAO combinations as described herein, 2-20 wt% pigment, such as TiO₂, 1-10 wt% oil, 0-7 wt% base polymers, and the remainder comprising a filler such as glass beads, calcium carbonate, sand, silica or others described herein.

Process

[0067] The combinations of PAO(s) and tackifier(s) may be blended or combined by any suitable means. For example, they may be combined in a static mixer, batch mixer, extruder, or a combination thereof, that is sufficient to achieve an adequate dispersion of the PAO in the tackifier. The mixing step may involve first dry blending using, for example, a tumble blender. Dispersion may take place as part of a processing method used to fabricate articles, such as in the extruder on an injection molding machine or fiber line. The PAO may be injected into the extruder barrel or introduced at the feed throat of the extruder to save the step of pre-blending. In another embodiment, tackifier pellets could dry blended to

achieve a homogeneous mixture at the desired concentrations. In yet another embodiment, tackifier pellets could be added to a pre-existing PAO-tackifier combination to blend down the PAO concentration.

[0068] In some embodiments, it is preferred that the operating temperature during the mixing/blending step be above the softening point of the tackifier but below the flash point of the PAO. It may also be preferred to admix the PAO slowly to prevent pooling of the PAO in the tackifier. In some embodiments, the combination may be cooled and allowed to "solidify" or it may be kept in molten form.

[0069] Alternatively, in making an adhesive composition, one could combine one or more of the adhesive components described herein with the tackifier and subsequently admix the PAOs. Or, one could combine one or more of the adhesive components described herein with the PAO and subsequently admix the tackifier. The selection of the method is at the discretion of the end user.

[0070] In yet another embodiment, a masterbatch approach could be employed, wherein the combination of PAO and tackifier is mixed and additionally admixed with one or more of additives and/or carrier polymers, which may include any of the polymeric materials described herein (and depending on the ultimate end use of the masterbatch). For example, in an adhesive application, the carrier polymer may comprise one of the previously described block copolymers, ethylene-vinyl acetate copolymers, or a C₂-, C₃-, or C₄- based homo-, co- or terpolymer. In a film application, the carrier polymer may include any previously described polymer, and may preferably comprise polyamide, PET, ethylene-vinyl acetate copolymer, or a C₂-, C₃-, or C₄- based homo-, co- or terpolymer.

Examples

Table 1
Materials used in the Examples

Material	Description	Source
ESCOREZ [®] 5690	Hydrogenated aromatic cycloaliphatic hydrocarbon resin having a Ring and Ball softening point of 89°C	ExxonMobil Chemical Company
ESCOREZ [®] 5600	Hydrogenated aromatic cycloaliphatic hydrocarbon resin having a Ring and	ExxonMobil Chemical Company

	Ball softening point of 103°C	
ESCOREZ[®] 1310	Aliphatic Hydrocarbon Resin having a Ring and Ball softening point of 93°C	ExxonMobil Chemical Company
SYLVALITE[™] RE100S	Rosin Ester	Arizona Chemical Company
WINGTACK[™] 10	Liquid aliphatic C ₅ hydrocarbon resin having a softening point of 10°C	Goodyear Chemical Company
VECTOR[®] 4114	(SIS/SI) linear block copolymer containing 42 wt% SI diblock	Dexco Polymers, LP
VECTOR[®] DPX-565	(SIS/SI) linear block copolymer containing 56 wt% SI diblock	Dexco Polymers, LP
VECTOR[®] DPX-586	Styrene-Isoprene (SI) _n /SIradial block copolymer	Dexco Polymers, LP
IRGANOX[™] 1076	Phenolic antioxidant	Ciba-Geigy

Table 2
PAOs used in the Examples

PAO*	Specific gravity (15.6/15.6°C)	Kinematic Viscosity @ 100°C (mm ² /s)	VI	Pour Point, (°C)
SHF-41	0.818	4.00	123	-57
PURESYN[™] 6	0.827	5.7	134	-54
SHF-101	0.835	10.0	136	-54
SUPERSYN[™] 2300	0.852	300	235	-30

*polyalphaolefin oligomeric oils available from ExxonMobil Chemical Company

Examples 1-22

[0071] The components listed in the tables were mixed together in the amounts listed in the tables using a Z-blade mixer or a coaxial stirrer, at a temperature between 155 and 185°C. The Mettler softening point of the resulting mixture was then measured.

Table 3
Examples 1-11

Example	1	2	3	4	5	6	7	8	9	10	11
Component (parts by weight)											
ESCOREZ[®] 5690	95	90	85	80	75	92	84	76	92	84	76
PURESYN[™] 6	5	10	15	20	25						
SHF-101						8	16	24			

SUPERSYN™ 2300									8	16	24
Softening Point – Mettler (°C)	77	65	54	43	35	71	56	41	84	81	78

Table 4
Examples 12-22

Example	12	13	14	15	16	17	18	19	20	21	22
Component (parts by weight)											
ESCOREZ® 5690	92.2	87.5	82.7	76	91.5	75.5	95	90	85	80	75
PURESYN™ 6	7.8	12.5	17.3	24							
SHF-101					8.5	24.5	5	10	15	20	25
Softening Point - Mettler (°C)	70	59	49	42	71	38	75	62	50	39	33

[0072] From the data in Tables 3 and 4, a skilled person could conduct a linear regression of these data to determine the amount of PAO needed to reach a particular softening point. Based on the data and regression, the following hypothetical amounts of each PAO (based on the weight of the tackifier alone) combined with the tackifier of Examples 1-22 would be needed to reach a targeted softening point. Such an analysis could easily be conducted for any tackifier-PAO combination in an effort to efficiently tailor the softening point of the combination.

Table 5
Hypothetical Softening Points of an
Escorez® 5690 Hydrocarbon Resin
based on PAO content

Targeted Softening Point (°C)	SHF-41 (wt% added)	Puresyn 6 (wt% added)	SHF 101 (wt% added)	Supersyn 2300 (wt% added)
80	1.82	3.1	3.2	18.7
70	6.50	7.83	8.53	45.3
60	11.17	12.6	13.9	72.0
50	15.84	17.3	19.2	98.7
40	20.51	22.0	24.5	125.3
30	25.19	26.7	29.9	152

Examples 23-25

[0073] The components listed in Examples 14-15 and 17 were mixed as described above the resulting materials were tested for color measurement and heat stability. The color was evaluated with a Hunterlab spectrophotometer.

Table 6
Examples 23-25

Example	23	24	25
Components (%)			
Escorez [®] 5690	82.7	76	75.5
Puresyn [™] 6	17.3	24	
SHF-101			25
Softening Point (Mettler / °C)	49	42	38
Brookfield Viscosity (mPa.s @ 175°C)	89	81	92
Initial Color			
YI (ASTM-D1925)	8.4	7.0	7.3
Heat Stability (@ 175°C, 5 hrs)			
YI (ASTM-D1925)	35.8	37.5	44.3
Gardner (ASTM D-6166)	4.1	4.2	4.8

Examples 26-29

[0074] In the examples 26-29, HMPSAs were prepared by mixing the block copolymers with the tackifier PAO combinations in a laboratory Z-blade mixer of 300 ml capacity, at a temperature of about 145°C. A small amount of phenolic antioxidant was added to the blend to prevent its degradation during the blending process. The total mixing time was about 70 minutes.

[0075] Final blend viscosity was evaluated with a Brookfield viscosimeter according to a procedure based on ASTM D 3236-88.

[0076] The pressure sensitive adhesives were applied as hot melt adhesives to a silicone coated paper at a coating weight of about 20 g/m², using an Acumeter laboratory coater with a slot die for extrusion of the molten adhesive at a temperature of 165°C. The lamination was done according to industry practice, by transfer coating from the silicone coated paper release substrate onto a 80 g/m² vellum paper frontal substrate.

[0077] The adhesive performances were evaluated according to test methods published by Finat, Postbus 85612, NL-2508-CH, The Hague, e.g., FTM 1 for the peel adhesion at 180°, FTM 8 for the shear resistance and FTM 9 for the loop tack measurements. In the examples, adhesive failure (af), cohesive failure (cf), paper tear (pt), and jerking (j) are indicated where necessary. The results are shown in Table 7.

Table 7
Examples 26-29

Example	Comparative example 1	26	27	28	29
Component (%)					
Tackifier/PAO Mixture of Example 17		69			
Tackifier/PAO Mixture of Example 19			69		
Tackifier/PAO Mixture of Example 21				42.1	
Tackifier/PAO Mixture of Example 22					31
VECTOR [®] DPX-586	31	31	31	31	31
ESCOREZ [®] 1310	42			26.9	38
WINGTACK [®] 10	27				
IRGANOX [®] 1076	0.3	0.3	0.3	0.3	0.3
Brookfield Viscosity (@175°C, mPa.s)	5840	5860	5910	4130	5640
180° Peel strength (N/25 mm) @ 23°C/50% humidity - glass	32.6 cf + pt	32.3 pt	33.1 Pt	32.0 cf + pt	32.8 pt
180° Peel strength (N/25 mm) @ 23°C/50% humidity - PE	28.9 cf + pt	22.0 af + pt	23.4 af+pt	24.0 af	25.3 af + pt
Loop Tack (N) @ 23°C/50% humidity - glass	27.7 af	18.0 pt	19.1 Af	21.1 af	29.2 pt
Loop Tack (N) @ 23°C/50% humidity - PE	19.1 af	17.6 pt	18.7 Af	14.6 af	18.5 pt
Shear (hrs) at room temperature	120	>150	>150	78.0 cf	> 150

Examples 30-32

[0078] The components listed in Table 8 were mixed together in the amounts listed using the same process as for Examples 1-22. The resulting softening point of the combinations was measured.

Table 8
Examples 30-32

Example	30	31	32
Component (%)			
ESCOREZ [®] 5600	90	80	75
SHF-41	10	20	25
Softening Point - Mettler (°C)	75	54	37

[0079] The components of examples 30-32 were used in a hot-melt formulation in the amounts indicated in Table 9 and made according to the procedure previously described in Examples 26-29. Comparative Examples 1 and

2 were prepared by the same methods. The results are illustrated in Table 9.

Example 36

[0080] In example 36, a HMPSA was prepared by mixing the block copolymers with the tackifiers and the PAO in a laboratory z-blade mixer of 300 ml capacity. The adhesive was made and tested according to the procedures described previously for Examples 26-29. The results are illustrated in Table 9.

Table 9
Examples 33-36

Example	Comp. Ex. 1	Comp. Ex. 2	33	34	35	36
Component (%)						
Tackifier/PAO Mixture of Example 32			57			
Tackifier/PAO Mixture of Example 33				42	42	
VECTOR [®] DPX-586	31		31	31		
VECTOR [®] DPX-565		31			31	
VECTOR [®] 4114						35
SCOREZ [®] 1310	42	42	12	27	27	
WINGTACK [®] 10	27	27				20
SHF-41						13
SYLVALITE [™] RE100S						32
IRGANOX [®] 1076	0.3	0.3	0.3	0.3	0.3	0.3
Brookfield Viscosity (@175°C, mPa.s)	5840	12900	4005	3710	5910	8540
180° Peel strength (N/25 mm) @ 23°C/50% humidity - glass	32.6 cf + pt	36 cf + pt	34.4 cf + pt	34.9 cf + pt	34.6 cf + pt	19.7 af
180° Peel strength (N/25 mm) @ 3°C - glass		24.3 pt	34.6 pt	36.7 pt	34.8 pt	25.8 af + pt
180° Peel strength (N/25 mm) @ 23°C/50% humidity - PE	28.9 cf + pt	24.6 af	24.8 af	27.5 af	24.2 af	5.5 af
180° Peel strength (N/25 mm) @ 3°C - PE		23 pt	24.8 af + pt	27.5 af + pt	26.6 af + pt	22.8 af
Loop Tack (N) @ room temperature - glass	27.7 af	26.9 af	27.0 af	25.4 af	21.3 af	11.7 af
Loop Tack (N) @ 3°C - glass		12 pt	13.6 pt	11.7 pt	10.4 pt	14.2 af + pt
Loop Tack (N) @ 23°C/50% humidity - PE	19.1 cf	20.7 af	18.4 af	18.6 af	15.8 af	9.1 af
Loop Tack (N) @ 3°C - PE		7 af	11.0 af + j + pt	11.8 af + j + pt	17.9 af + j + pt	16.2 af + pt
Shear (hrs) at room temperature	120	152	>200 cf	123 cf	65.5 cf	>150

Example 37

[0081] Linear alpha olefins may also be strong depressants of softening points, with longer the chains having a stronger effect. Such resins can be

produced with severe stripping giving a medium softening point tackifier having high flash points and low volatility and therefore more acceptable in the hot melt industry. This route could be considered for production of LAO-spiked aliphatic resins, aromatic modified aliphatic resins, DCPD resins, as well as hydrogenated derivative versions of such grades. The LAO-spiked resin polymerization feed could be a cracked petroleum feed containing C₄, C₅ and C₆ paraffins, olefins and conjugated diolefins referred herein as C₅ monomers, leading to an aliphatic resin. The LAO-spiked resin polymerization feed may also comprise C₈-C₁₀ aromatic monomers leading to such aromatic modified aliphatic resins.

[0082] In the example 37, HMPSA was prepared by mixing the block copolymers with the LAO modified tackifier (*e.g.*, ESCOREZ 5000 grade) and other tackifiers according to the procedure previously described in Examples 26-29. As used herein "linear alpha olefins" are oligomers of n-C₅ to n-C₅₀, preferably n-C₅ to n-C₃₀, preferably n-C₅ to n-C₂₀. Comparative Examples 1 was prepared by the same methods. The results are illustrated in Table 10.

Table 10
Examples 37

Example	Comp. Ex. 1	37
Component (%)		
LAO modified ESCOREZ 5000 grade		39.8
VECTOR [®] DPX-586	31	31
ESCOREZ [®] 1310	42	29.2
WINGTACK [®] 10	27	
IRGANOX [®] 1076	0.3	0.3
Brookfield Viscosity (@175°C, mPa.s)	5840	3915
180° Peel strength (N/25 mm) @ 23°C/50% humidity - glass	32.6 cf + pt	35.4 cf + pt
180° Peel strength (N/25 mm) @ 3°C - glass		36.1 pt
180° Peel strength (N/25 mm) @ 23°C/50% humidity - PE	28.9 cf + pt	26.9 af
180° Peel strength (N/25 mm) @ 3°C - PE		27.9 af + pt
Loop Tack (N) @ room temperature - glass	27.7 af	29 af
Loop Tack (N) @ 3°C - glass		12.8 pt
Loop Tack (N) @ 23°C/50% humidity - PE	19.1 cf	20.8 af
Loop Tack (N) @ 3°C - PE		6.9 af
Shear (hrs) at room temperature	120	106

Claims:

1. A composition comprising:
 - (a) at least one tackifier; and
 - (b) at least one polyalphaolefin oil (PAO), wherein the collective at least one PAO has at least one property chosen from the group consisting of:
 - (i) a Kinematic viscosity $\leq 10.5 \text{ mm}^2/\text{s}$ at 100°C ; and
 - (ii) a pour point $\leq -38^\circ\text{C}$.
2. The composition according to claim 1, wherein the composition does not comprise a thermally conductive filler comprising zinc oxide, boron nitride, aluminum nitride, silicon carbide, silicon nitride, or mixtures thereof.
3. The composition according to claim 1 or claim 2 consisting essentially of at least one tackifier and at least one polyalphaolefin oil (PAO).
4. The composition according to any of the previous claims wherein the collective at least one PAO has a Kinematic viscosity $\leq 10.4 \text{ mm}^2/\text{s}$ at 100°C .
5. The composition according to claim 4 wherein the collective at least one PAO has a Kinematic viscosity $\leq 10.25 \text{ mm}^2/\text{s}$ at 100°C .
6. The composition according to any of the previous claims wherein the collective at least one PAO has a Kinematic viscosity $\geq 0.5 \text{ mm}^2/\text{s}$ at 100°C .
7. The composition according to claim 6 wherein the collective at least one PAO has a Kinematic viscosity $\geq 1.0 \text{ mm}^2/\text{s}$ at 100°C .
8. The composition according to any of the previous claims wherein the collective at least one PAO has a Kinematic viscosity from $1.5\text{-}10.0 \text{ mm}^2/\text{s}$ at 100°C .

9. The composition according to any of the previous claims wherein the collective at least one PAO has a Kinematic viscosity from 2.0-10.0 mm²/s at 100°C.
10. The composition according to any of the previous claims wherein the collective at least one PAO has a Kinematic viscosity \leq 120 mm²/s at 40°C.
11. The composition according to any of the previous claims wherein the collective at least one PAO has a Kinematic viscosity \leq 100 mm²/s at 40°C.
12. The composition according to any of the previous claims wherein the collective at least one PAO has a Kinematic viscosity \leq 80 mm²/s at 40°C.
13. The composition according to any of the previous claims wherein the collective at least one PAO has a pour point \leq -40°C.
14. The composition according to any of the previous claims wherein the collective at least one PAO has a pour point \leq -45°C.
15. The composition according to any of the previous claims wherein the collective at least one PAO has a pour point \leq -50°C.
16. The composition according to any of the previous claims wherein the collective at least one PAO has a pour point \leq -55°C.
17. The composition according to any of the previous claims comprising from 20-99.99 wt % tackifier and from 0.01-80 wt% PAO based on the weight of the tackifier and PAO(s).
18. The composition according to claim 17 comprising from 50-99 wt% tackifier and from 1-50 wt% PAO based on the weight of the tackifier and

PAO(s).

19. The composition according to claim 17 comprising from 75-95 wt% tackifier and from 5-25 wt% PAO based on the weight of the tackifier and PAO(s).

20. The composition of claims 15 - 19 further comprising at least one wax.

21. The composition of claims 15 - 19 further comprising at least one processing oil.

22. The composition according to any of the previous claims wherein the at least one tackifier is selected from aliphatic hydrocarbon resins, hydrogenated aliphatic hydrocarbon resins, aromatic modified aliphatic hydrocarbon resins, hydrogenated aromatic modified aliphatic hydrocarbon resins, polycyclopentadiene resins, hydrogenated polycyclopentadiene resins, cycloaliphatic hydrocarbon resins, hydrogenated cycloaliphatic resins, cycloaliphatic/aromatic hydrocarbon resins, hydrogenated cycloaliphatic/aromatic hydrocarbon resins, hydrogenated aromatic hydrocarbon resins, maleic acid/anhydride modified tackifier, terpene modified aromatic and/or aliphatic hydrocarbon resin, hydrogenated terpene modified aromatic and/or aliphatic hydrocarbon resin, polyterpene resins, hydrogenated polyterpene resins, aromatic modified polyterpene resins, hydrogenated aromatic modified polyterpene resins, terpene-phenol resins, hydrogenated terpene-phenol resins, gum rosin resins, hydrogenated gum rosin resin, gum rosin ester resins, hydrogenated gum rosin ester resins, wood rosin resin, hydrogenated wood rosin resins, wood rosin ester resins, hydrogenated wood rosin ester resins, tall oil rosin resins, hydrogenated tall oil rosin resins, tall oil rosin ester resins, hydrogenated tall oil rosin ester resins, rosin acid resins, hydrogenated rosin acid resins, and mixtures of two or more thereof.

23. An adhesive comprising a composition of any of the previous claims.

24. The adhesive according to claim 23 further comprising a base polymer.
25. The adhesive of claim 24 wherein the base polymer is selected from the group consisting of: polyethylene, an ethylene α -olefin (C₃-C₂₀) co- or terpolymer, polypropylene, a propylene α -olefin (C₄-C₂₀) co- or terpolymer, polybutylene, a butylene α -olefin (C₅-C₂₀) co- or terpolymer, a polyisobutylene polymer, α -olefin diene copolymers, block copolymers comprising styrene and one or more conjugated dienes, and mixtures of two or more thereof.
26. The adhesive of claim 23 wherein the base polymer is selected from the group of SI (Styrene-Isoprene), SBS (Styrene-Butadiene-Styrene), SB (Styrene-Butadiene), SIS (Styrene-Isoprene-Styrene), SEP (Styrene-Ethylene/Propylene), SEB (Styrene-Ethylene/Butylene), SEBS (Styrene-Ethylene/Butylene-Styrene), SEPS (Styrene-Ethylene/Propylene-Styrene), where the architecture of the block copolymers includes linear, radial or multi-arm star, and multi-branched.
27. The adhesive of claim 23 wherein the base polymer comprises styrene block copolymers comprising tetrablock or pentablock copolymers selected from SISI, SISB, SBSB, SBSI, SIBS, ISISI, ISISB, BSISB, ISBSI, BSBSB, BSBSI, SIBSB, BSIBS, SIBSI, ISIBS, SIBSB, ISIBS.
28. The adhesive of claim 23 wherein the base polymer is selected from the group consisting of polyesters, polyamides, polyureas, polycarbonates, polyacrylonitriles, polyacrylates, polymethylacrylates, ethylene vinyl acetate copolymers, polyvinyl chloride, polyethylene terephthalate, polybutylene terephthalate, polyacetals, ethylene methyl acrylate, ethylene butyl acrylate, and mixtures of two or more thereof.
29. An article comprising a substrate selected from the group of: polyethylene terephthalate, paper, recycled paper, kraft paper, vellum paper, calendered paper, clayed paper, a film comprising one or more polyolefins, cardboard, recycled cardboard, substrates having acrylic varnishes thereon, wood, glass, ceramic,

asphalt, concrete, and metal, the substrate having an adhesive composition according to claim 23 adhered thereto.

30. A tape or label comprising a composition according to any of claims 1-22 or an adhesive according to any of claims 23-29.

31. A tape or label according to claim 30 further comprising a backing element.

32. A tape or label according to claim 31 wherein the backing element is selected from polymeric films, polyester films, polyolefin-based films, polyurethane films, polyvinylchloride foam, polyethylene foam, nonwoven polyurethane, nonwoven polyester, knitted fabric, face stock, paper, recycled paper, kraft paper, vellum paper, calendered paper, clayed paper, synthetic polymeric material, plastic, polyolefins, such as polyethylene and polypropylene, polyester, polyethylene terephthalate, polyvinyl chloride, kraft paper, polymers, laminates, latex saturated paper, foil, litho stock, lightweight stock, styrene foam, laminated foam, expanded polystyrene foam, woven fabric, non-woven fabric, cloth, creped paper, thermoplastic, and mixtures thereof.

33. A label according to any of claims 30-32 further comprising a release liner.

34. A package or disposable article comprising an adhesive according to claims 23 – 29.

35. A road marking composition comprising a composition according to any of claims 1-22 or an adhesive according to any of claims 23-29.

36. An adhesive masterbatch comprising a composition according to any of claims 1-22 and a carrier polymer.

37. The adhesive masterbatch according to claim 36 wherein the carrier polymer is selected from a C₂-C₂₀ homopolymer, a C₂-C₂₀ copolymer, or a C₂-C₂₀ terpolymer.
38. A process comprising combining a masterbatch of any of claims 36-37 with a base polymer.
39. A process comprising:
- (a) combining at least one tackifier and at least one PAO, wherein the PAO has at least one property chosen from the group consisting of:
 - (i) a Kinematic viscosity $\leq 10.5 \text{ mm}^2/\text{s}$ at 100°C; and
 - (ii) a pour point $\leq -38^\circ\text{C}$.
40. A process according to claim 39 further comprising combining at least one base polymer.
41. The process according to any of claims 39-40 wherein the base polymer is selected from the group consisting of: polyethylene, an ethylene α -olefin (C₃-C₂₀) copolymer, or an ethylene α -olefin (C₃-C₂₀) terpolymer, polypropylene, a propylene α -olefin (C₄-C₂₀) copolymer or a propylene α -olefin (C₄-C₂₀) terpolymer, polybutylene, a butylene α -olefin (C₅-C₂₀) copolymer or butylene α -olefin (C₅-C₂₀) terpolymer, a polyisobutylene polymer, α -olefin diene copolymers, block copolymers comprising styrene and one or more conjugated dienes, and mixtures of two or more thereof.
42. The process according to claim 40 wherein the base polymer is selected from the group of SI (Styrene-Isoprene), SBS (Styrene-Butadiene-Styrene), SB (Styrene-Butadiene), SIS (Styrene-Isoprene-Styrene), SEP (Styrene-Ethylene/Propylene), SEB (Styrene-Ethylene/Butylene), SEBS (Styrene-Ethylene/Butylene-Styrene), SEPS (Styrene-Ethylene/Propylene-Styrene), where the architecture of the block copolymers includes linear, radial or multi-arm star,

and multi-branched.

43. The composition according to claim 40 wherein the base polymer comprises styrene block copolymers comprising tetrablock or pentablock copolymers selected from SISI, SISB, SBSB, SBSI, SIBS, ISISI, ISISB, BSISB, ISBSI, BSBSB, BSBSI, SIBSB, BSIBS, SIBSI, ISIBS, SIBSB, ISIBS.

44. The process of any of claims 39-43 further comprising combining at least one wax.

45. A process comprising:

applying a composition to a substrate, the composition produced by combining at least one tackifier and at least one PAO, wherein the at least one PAO has at least one property chosen from the group consisting of:

- (i) a Kinematic viscosity $\leq 10.5 \text{ mm}^2/\text{s}$ at 100°C ; and
- (ii) a pour point $\leq -38^\circ\text{C}$.

46. A process comprising:

using at least one polyalphaolefin oil (PAO) to lower the softening point properties of a tackifier, wherein the at least one PAO has at least one property chosen from the group consisting of:

- (i) a Kinematic viscosity $\leq 10.5 \text{ mm}^2/\text{s}$ at 100°C ; and
- (ii) a pour point $\leq -38^\circ\text{C}$.

47. A tackifier composition comprising an LAO-spiked tackifier resin.

48. The tackifier composition of claim 47 where the LAO-spiked tackifier is an aliphatic hydrocarbon resins.

49. A tackifier composition according to claim 47 where the LAO-spiked tackifier is an aliphatic hydrocarbon resins.

50. A tackifier composition according to claim 47 where the LAO-spiked tackifier is an aliphatic hydrocarbon resins.
51. A tackifier composition according to claim 47 where the LAO-spiked tackifier is a hydrogenated aromatic modified aliphatic hydrocarbon resin.
52. A tackifier composition according to claim 47 where the LAO-spiked tackifier is a polycyclopentadiene resin.
53. A tackifier composition according to claim 47 where the LAO-spiked tackifier is a hydrogenated polycyclopentadiene resin.
54. A tackifier composition according to claim 47 where the LAO-spiked tackifier is a cycloaliphatic hydrocarbon resins.
55. A tackifier composition according to claim 47 where the LAO-spiked tackifier is a hydrogenated cycloaliphatic resin.
56. A tackifier composition according to claim 47 where the LAO-spiked tackifier is selected from the group consisting of cycloaliphatic hydrocarbon resins and aromatic hydrocarbon resins.
57. A tackifier composition according to claim 47 where the LAO-spiked tackifier is selected from the group consisting of hydrogenated cycloaliphatic hydrocarbon resins and hydrogenated aromatic hydrocarbon resins.
58. A tackifier composition according to claim 47 where the LAO-spiked tackifier is a hydrogenated aromatic hydrocarbon resins.
59. An adhesive comprising the composition of any of claims 47-58.
60. A tape or label comprising the adhesive of claim 59.

61. An adhesive masterbatch comprising the composition of any of claims 47-58 and a carrier polymer.

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2005/035327

A. CLASSIFICATION OF SUBJECT MATTER
C08L57/00 C08L91/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, PAJ, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2004/106723 A1 (OURIEVA GALINA ET AL) 3 June 2004 (2004-06-03) abstract; claims 1-16 page 6; table 2 page 9, paragraph 111 page 20, paragraph 216 page 20, paragraph 222	1-35, 39-46
X	US 5 151 205 A (CULPON JR DOUGLAS H) 29 September 1992 (1992-09-29) abstract; claims 1-17	1-16, 21, 22
X	WO-96/03470 A (EXXON-CHEMICAL-PATENTS INC) 8 February 1996 (1996-02-08) abstract; claims 1-10 page 5, line 23	47-61
	----- -/--	

Further documents are listed in the continuation of Box C.

See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

14 March 2006

Date of mailing of the international search report

22 MAR 2006

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Bergmans, K

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2005/035327

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 6 221 448 B1 (BAETZOLD JOHN P ET AL) 24 April 2001 (2001-04-24) abstract; claims 1-19 column 8, line 64 column 9, line 2	47-61
X	EP 0 451 920 A (SHELL INTERNATIONALE RESEARCH MAATSCHAPPIJ B.V) 16 October 1991 (1991-10-16) abstract; claims 1-4 page 5, line 22	47-61
A	US 4 284 542 A (BOYCE ET AL) 18 August 1981 (1981-08-18) abstract; claims 1-9	36,37

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US2005/035327

Box II Observations where certain claims were found unsearchable (Continuation of item 2 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:

2. Claims Nos.:
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:

3. Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box III Observations where unity of invention is lacking (Continuation of item 3 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

see additional sheet

1. As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
2. As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
4. No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

The additional search fees were accompanied by the applicant's protest.

No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

This International Searching Authority found multiple (groups of) inventions in this international application, as follows:

1. claims: 1-35,39-46

~~A composition and the preparation and article thereof made from a tackifier and a PAO oil characterised by kinematic viscosity and pour point.~~

2. claims: 36-38

An adhesive master-batch and the proeparation thereof wherein the master-batch comprises a tackifier and a PAO oil characterised by kinematic viscosity and pour point.

3. claims: 47-60

A tackifier composition, an adhesive or article made therefrom comprising a LAO-spiked tackifier resin.

4. claim: 61

An adhesive master-batch comprising a LAO-spiked tackifier resin and a carrier polymer.

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No PCT/US2005/035327

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2004106723	A1	03-06-2004	NONE
US 5151205	A	29-09-1992	NONE
WO 9603470	A	08-02-1996	DE 69508403 D1 22-04-1999 DE 69508403 T2 02-09-1999 EP 0772657 A1 14-05-1997
US 6221448	B1	24-04-2001	NONE
EP 0451920	A	16-10-1991	AU 634875 B2 04-03-1993 AU 7424691 A 17-10-1991 BR 9101416 A 26-11-1991 CA 2040113 A1 12-10-1991 DE 69131433 D1 19-08-1999 DE 69131433 T2 13-01-2000 DK 451920 T3 29-11-1999 ES 2133277 T3 16-09-1999 JP 5078637 A 30-03-1993 KR 204814 B1 15-06-1999 US 5118762 A 02-06-1992
US 4284542	A	18-08-1981	CA 1130029 A1 17-08-1982