



(51) International Patent Classification:

B01J 23/881 (2006.01) **B01J 23/888** (2006.01)
B01J 23/882 (2006.01) **B01J 35/10** (2006.01)
B01J 23/883 (2006.01) **B01J 37/02** (2006.01)
B01J 23/887 (2006.01)

(21) International Application Number:

PCT/US2014/033714

(22) International Filing Date:

11 April 2014 (11.04.2014)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

10 2013 006 251.9

11 April 2013 (11.04.2013)

DE

(61) Related by addition to earlier application or grant:

DE

10 2013 006 251.9 (POA)

Filed on

11 April 2013 (11.04.2013)

(71) Applicants: **CLARIANT CORPORATION** [US/US]; IP Department, 1600 West Hill Street, Louisville, Kentucky 40210 (US). **CLARIANT INTERNATIONAL LTD.** [CH/CH]; Rothausstr. 61, 4132 Muttenz, Switzerland, CH-4132 Muttenz (CH).

(72) Inventors; and

(71) Applicants : **SOKOLOVSKII, Valery** [US/US]; 1845 Palm View Place, #111, Santa Clara, CA 95050, Santa Clara, California 95050 (US). **LOWE, David Michael** [US/US]; 992 Belmont Terrace Unit #8, Sunnyvale, California 94086 (US). **MACHIRAJU, Deepti** [IN/US]; 801 Church St., Apt. 1127, Mountain View, CA 94041, Mountain View, California 94041 (US). **HOU, Hongyi C.** [CN/US]; 1168 De Altura Commons, San Jose, CA 95126, San Jose, California 95126 (US). **MESTL, Gerhard** [DE/DE]; Ebereschenstr. 71, 80935 Munich, Germany, 80935 Munich (DE). **LUGMAIR, Claus G.** [US/US]; 977

Walglenn Ct., San Jose, CA 95136, San Jose, California 95136 (US). **MILLER, Aaron B.** [US/US]; 2536 Promontory Circle, San Ramon, CA 94583, San Ramon, California 94583 (US). **VOLPE, JR., Anthony F.** [US/US]; 2582 Tartan Drive, Santa Clara, CA 95051, Santa Clara, California 95051 (US).

(81) Designated States (unless otherwise indicated, for every

kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every

kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii))

Published:

- with international search report (Art. 21(3))

(54) Title: METHOD FOR PRODUCING A CATALYST FOR THE PARTIAL OXIDATION/AMMOXIDATION OF OLEFINS

(57) Abstract: The present invention relates to a method for producing a supported catalyst, a catalyst which is obtainable using the method, and use thereof for the partial oxidation or ammoxidation of olefins, in particular for the oxidation of propene to acrolein, of isobutene to methacrolein, and/or the ammoxidation of propene to acrylonitrile. The method according to the invention includes the following steps: a) providing a solution in which precursor compounds of the catalytically active component are essentially completely dissolved in a suitable solvent; b) bringing the solution obtained in step a) into contact with a (chemically) inert, porous support having a specific surface of 1 to 500 m²/g; c) heat treatment of the material obtained in step b), in which the precursor compounds of the catalytically active component are converted to their oxides.



**METHOD FOR PRODUCING A CATALYST FOR THE PARTIAL
OXIDATION/AMMOXIDATION OF OLEFINS**

The present invention relates to a simple method for producing a supported catalyst, a
5 catalyst which is obtainable using the method, and use thereof for the partial oxidation or
ammoxidation of olefins, in particular for the oxidation of propene to acrolein, of isobutene to
methacrolein, and/or the ammoxidation of propene to acrylonitrile.

The partial oxidation of propene to acrolein, of isobutene to methacrolein, and the
10 ammoxidation of propene to acrylonitrile are widely used industrially as the first step in the
production of acrylic acid, acrylic esters, and acrylamide or methacrylic acid, which in turn
are important intermediate products in the production of acrylic polymers such as
poly(meth)acrylic acids and poly(meth)acrylates.

15 The partial oxidation of propene to acrolein, of isobutene to methacrolein, and the
ammoxidation of propene to acrylonitrile are usually carried out by gas phase oxidation in the
presence of oxygen and a suitable heterogeneous catalyst. For this purpose, a catalyst based
on molybdenum, bismuth, and iron as well as various additives such as nickel, cobalt,
tungsten, magnesium, manganese, boron, silicon, and alkali metals, is typically used. Various
20 variations of the catalyst composition are known from the prior art.

These catalysts are customarily produced using relatively complicated processes as described,
for example, in US 5,856,259, US 6,383,973, US 6,632,965, US 6,781,013, US 6,946,422,
US 7,341,974, US 7,544,633, US 7,632,777, US 7,851,397, US 2010/0323881, and WO
25 2005/035115 A1, using a slurry of the catalytically active components. The conventional
production processes for catalysts typically comprise the following steps: 1. preparation of at
least two solutions, 2. production of a slurry by slow mixing of these solutions, 3. drying of
the slurry, resulting in a catalyst cake, 4. crushing of the solid material, 5. addition of pore-
forming agents, 6. addition of additives for enhancing the mechanical properties, 7. shaping,
30 and 8. calcination.

In addition, these catalysts may be produced by a Pechini process, or a sol-gel process as described, for example, by Bu Young Jo et al. in *Appl Catal A:Gen*, 358 (2009) 180-185 and Duc Truong Duc et al. in *Res Chem Intermed*, 37 (2011) 605-616. In these processes, the catalytically active components are dissolved, optionally using a complexing agent, and
5 subsequently gelled under the influence of heat, for example. The customary further steps correspond to steps 3 through 8 mentioned above.

A key feature of all conventional production process is the formation of loose catalytically active material, which must be brought into a certain form or applied to a substrate. It is
10 important to note that the conventional production processes provide loose catalytically active material having a large pore volume, which is detrimental to the mechanical strength of the material. For this reason, in the conventional production processes, additives such as glass fibers for enhancing the mechanical properties must be added to the loose catalytically active material before it is shaped.

The conventional production processes for catalysts for the partial oxidation of olefins also share the common feature that they include precipitation or gelling of the catalytically active components to form a slurry or a gel. It is disadvantageous that a uniform catalyst material is difficult to achieve, since the catalytically active components situated within the solid
20 particles are not able to react with other components that are present in the solution. In addition, the catalytically active components situated within the solid particles are not available for the oxidation reaction to be catalyzed, so that only a small portion of the catalytically active components is in contact with the reaction mixture and thus actually catalyzes the oxidation reaction, which of course not only impairs the efficiency of the
25 catalytically active components that are used, but also decreases the conversion rate of the oxidation reaction to be catalyzed and thus reduces the yield of the desired product.

The object of the present invention, therefore, is to provide a simple and cost-saving method by means of which a highly efficient catalyst may be produced for the partial oxidation of
30 olefins, in particular for the partial oxidation of propene to acrolein, of isobutene to methacrolein, and/or the ammoxidation of propene to acrylonitrile. At the same time, the aim is to overcome the mechanical problems in the shaping on account of the large pore volume

of the catalyst which is advantageous for the catalytic effectiveness, without the use of additives for enhancing the mechanical properties, or binders.

This object is achieved by a method for producing a catalyst which includes as the

5 catalytically active component a compound having the general formula

$\text{Mo}_x\text{Bi}_y\text{Fe}_z\text{A}_a\text{B}_b\text{C}_c\text{D}_d\text{O}_v$, where A stands for Ni and/or Co, B stands for one or more metals selected from Mg, Cr, Mn, Zn, Ce, and Ca and combinations thereof, C stands for W, and D

10 stands for one or more alkali metals, where x stands for a number from 10 to 14, y stands for a number from 0.1 to 5, z stands for a number from 0.5 to 5, a stands for a number from 1 to 10, b stands for a number from 0.1 to 6, c stands for a number from ≥ 0 to 2, d stands for a number from 0.02 to 2, and v is determined by the oxidation state of the elements, the method including the following steps:

- 15 a) Providing a solution in which the precursor compounds of the catalytically active component are essentially completely dissolved in a suitable solvent;
- b) Bringing the solution obtained in step a) into contact with a (chemically) inert, porous support having a specific surface of 1 to 500 m^2/g ;
- 20 c) Heat treatment of the material obtained in step b), in which the precursor compounds of the catalytically active components are converted to their oxides (i.e. the catalytically active component according to the above formula).

It has surprisingly been found that by bringing a solution containing the precursor compounds of the catalytically active components into contact with a (chemically) inert, porous support without forming a slurry or a gel, a uniform distribution of the catalytically active component in the form of a thin layer on the surface of the support is achieved, so that a supported
25 catalyst is obtained in which essentially all constituents of the catalytically active component are actually available for the oxidation reaction to be catalyzed.

In addition, the problems in the shaping and forming of the required pore structure may be
30 solved by selecting a support which already has a suitable predefined shape and pore structure. At the same time, by selecting a support having high mechanical strength, the

problems of mechanical strength are solved without the need for additives for enhancing the mechanical properties, or binders.

The catalyst produced by the method according to the invention comprises as the catalytically active component a compound having the general formula $Mo_xBi_yFe_zA_aB_bC_cD_dO_v$, where A stands for Ni and/or Co, B stands for one or more metals selected from Mg, Cr, Mn, Zn, Ce, and Ca, preferably selected from Mg, Cr, Mn, Zn, and Ca, C stands for W, and D stands for one or more alkali metals Li, Na, K, Cs, Fe, preferably K and/or Cs, where x stands for a number from 10 to 14, in refinements of the invention preferably 12, y stands for a number from 0.1 to 5, z stands for a number from 0.5 to 5, preferably 0.6 to 4, a stands for a number from 1 to 10, b stands for a number from 0.1 to 6, c stands for a number from 0 to 2, d stands for a number from 0.02 to 2, and v is determined by the oxidation state of the other elements. Preferably the catalyst produced according to the invention has the before-mentioned general formula, i.e. consists of the compound of the before-mentioned general formula.

Under the term “compound having the general formula $Mo_xBi_yFe_zA_aB_bC_cD_dO_v$ ” does not only fall a single compound of the mixed oxide comprising the metals Mo, Bi, Fe, A, B, C, and D, but does also fall a mixture of different oxides comprising 1, 2, 3, 4, 5, 6, or 7 metals selected from the metals of the before-mentioned formula, as long as the ratio of the metals Mo, Bi, Fe, A, B, C, and D is within range of the parameters x, y, z, a, b, c, and d as defined.

In one refinement of the invention, B stands for Mg.

In another refinement of the invention, D stands for K and/or Cs, preferably K.

In another refinement of the invention, y stands for a number from 0.2 to 3, preferably a number from 0.5 to 2 or a number from 0.7 to 1.5, and in another embodiment preferably stands for a number from 0.8 to 1.4, more preferably a number from 0.9 to 1.3, in particular a number from 1.0 to 1.2.

In another refinement of the invention, z stands for a number from 0.6 to 4, preferably a number from 0.7 to 3 or a number from 0.75 to 2.5, in particular a number from 0.8 to 2.2.

In yet another refinement of the invention, a stands for a number from 2 to 9, preferably a number from 3 to 8 or a number from 4 to 7, in particular a number from 5.5 to 6.5.

5 According to the invention, the molar ratio of Mo to Bi is 140 to 2, preferably 120 to 2.4, and in preferred embodiments of the invention, 15.5 to 7.7 or 13.3 to 9.3. According to the invention, the molar ratio of Bi to Fe is 0.002 to 1, preferably 0.46 to 1.5, and in further embodiments, 1.0 to 1.2 or 0.8 to 2.2.

10 In another embodiment of the invention, the catalyst produced by the method according to the invention contains Ni as well as Co, the molar fractions e for Ni and f for Co resulting in the sum a, i.e., $a = e + f$. It is advantageous when e stands for a number from 1.5 to 3.5, preferably a number from 1.8 to 3.2 or a number from 2.0 to 3.0, in particular a number from 2.4 to 2.7, and when f stands for a number from 2.5 to 5.5, preferably a number from 2.8 to 4.5 or a number from 3.0 to 4.0, in particular a number from 3.3 to 3.6.

In another refinement of the invention, b stands for a number from 0.15 to 5, preferably a number from 0.2 to 3 or a number from 0.22 to 2.5, in particular a number from 0.25 to 2.0. For the case that B stands for multiple metals from the group Mg, Cr, Mn, Zn, Ce, and Ca, 20 the molar fractions thereof result in the sum b.

In another refinement of the invention, c stands for a number from 0.02 to 1.5, preferably a number from 0.05 to 1.0 or a number from 0.1 to 0.6, in particular a number from 0.15 to 0.4.

25 In another refinement of the invention, d stands for a number from 0.03 to 1.0, preferably a number from 0.04 to 0.5 or a number from 0.05 to 0.1, in particular a number from 0.06 to 0.09.

The above-described catalysts produced by the method according to the invention have 30 proven to be particularly suitable for the partial oxidation/ammoxidation of olefins, in particular for the partial oxidation of propene to acrolein, of isobutene to methacrolein, and/or the ammoxidation of propene to acrylonitrile, in particular with regard to a high conversion

rate of the starting product and a high yield of the desired products, and at the same time with high selectivity.

In the method according to the invention, a solution in which the precursor compounds of the catalytically active component are essentially completely dissolved in a suitable solvent is provided in a step a). Step a) of the method according to the invention could also be formulated as that the precursor compounds are dissolved in a solvent. The individual precursor compounds of the catalytically active component may be dissolved in a suitable solvent, and/or commercially available, ready-to-use solutions of the individual precursor compounds of the catalytically active component may be used. It is further preferred that all precursor compounds necessary for producing the catalytically active component are already applied in step a) of the method according to the invention.

Within the meaning of the present invention, "precursor compounds of the catalytically active component" mean chemical compounds comprising metals and/or metalloids, which produce an effect in the reaction to be catalyzed. Since the effective forms of the catalytically active component, generally metal oxides and/or metalloid oxides as well as elemental metals and/or metalloids, frequently are sparingly soluble, soluble forms of the corresponding metals and/or metalloids, in particular slightly soluble metal salts and/or metalloid salts, are used as the precursor compounds of the catalytically active component.

Thus, in step a) of the method according to the invention, slightly soluble salts of the precursor compounds of the catalytically active component are preferably used which may be essentially completely dissolved in a suitable solvent.

Within the meaning of the present invention, "essentially completely dissolved" means that at least 95% by weight, preferably at least 98% by weight and particularly preferably at least 99% by weight, of the precursor compounds of the catalytically active component used are dissolved in the solution provided in step a). In other words, the solution provided in step a) of the method according to the invention should be free of residues, apart from technically unavoidable impurities, and thus should represent a clear solution. In order to not compromise the advantages that are achievable using the method according to the invention,

the solution provided in step a) of the method according to the invention should not be a slurry, gel, suspension, or other type of dispersion.

The salts which are preferably used as the precursor compounds of the catalytically active component in the method according to the invention are not subject to any special limitations as long as they are soluble in a suitable solvent and include common metal salts or metalloids salts of the corresponding metals or metalloids.

Examples of precursor compounds of the catalytically active component are as follows:

10 Examples of suitable molybdenum compounds include molybdates, in particular ammonium molybdates, preferably ammonium heptamolybdate. Examples of suitable bismuth compounds include inorganic or organic salts of bismuth, in particular bismuth nitrate, bismuth subsalicylate, or bismuth citrate, preferably bismuth nitrate. Examples of suitable iron compounds include inorganic or organic salts of iron(III), in particular iron(III) nitrate, 15 iron(III) salicylate, or iron(III) citrate, preferably iron(III) nitrate. Examples of suitable nickel compounds include nickel acetate, nickel nitrate, nickel salicylate, or nickel citrate, preferably nickel acetate. Examples of suitable cobalt compounds include cobalt acetate, cobalt nitrate, cobalt salicylate, or cobalt citrate, preferably cobalt acetate. Examples of suitable magnesium compounds include magnesium acetate, magnesium nitrate, magnesium 20 salicylate, or magnesium citrate, preferably magnesium acetate. Examples of suitable tungsten compounds include tungstates, in particular ammonium tungstates, preferably ammonium metatungstate. Examples of suitable potassium compounds include potassium acetate, potassium nitrate, potassium salicylate, or potassium citrate, preferably potassium acetate. Examples of suitable cesium compounds include cesium acetate, cesium nitrate, 25 cesium salicylate, or cesium citrate, preferably cesium acetate. According to the so-called Pearson hard and soft acids and bases (HSAB) concept, cesium (Cs^+) is a so-called "soft" cation, and according to the invention is better suited than a "hard" cation such as Li^+ or Na^+ . Other suitable salts of the above-mentioned metals as well as salts of other metals, for example chromium, manganese, zinc, cerium, and/or calcium, and/or of metalloids may be 30 easily selected by those skilled in the art. Mixtures of various salts of the same metal may also be used.

It is advantageous when the counterion of the salts of the precursor compounds of the catalytically active component which are preferably used in the method according to the invention, i.e., generally the anion, or in the case of metal acids such as tungstate or molybdate, the cation, may be removed with essentially no residues in the heat treatment in
5 step c) of the method according to the invention.

In another embodiment of the present invention, an aqueous solvent is used as the suitable solvent in step a) of the method according to the invention, i.e., a solvent composed of water, or a solvent mixture which in addition to water contains one or more further solvents that are
10 miscible with water, such as polar organic solvents, in particular alcohols. The use of an aqueous solvent in step a) of the method according to the invention is advantageous from an environmental and economic standpoint.

It is also preferred for the aqueous solvent to include an acidic aqueous solvent, by means of
15 which the complete dissolution of the precursor compounds of the catalytically active component is facilitated in many cases. This is specifically advantageous in that Bi precursor compounds and Mo precursor compounds are usually not soluble in one solution under the same conditions. However, the means for acidifying the aqueous solvent is not subject to any special limitations as long as it is suitable for solving all precursor compounds in one
20 solution, and as long as it does not impair the catalytic activity of the finished catalyst. In this regard, in particular acids are preferred which may be removed with essentially no residues in the heat treatment in step c) of the method according to the invention. By using an acid for ensuring that all of the precursor compounds can be solved has the technical effect that the particle growth is very low resulting in a relatively high BET-surface area. Another
25 advantage of a homogeneous solution of the precursor compounds is that all of the metals of the catalytically active component are evenly distributed over the entire catalyst. The latter advantage cannot be reached when no acid is added. The other advantages can only partly be compensated in that the precipitated powder is spray-calcined in a pulsation reactor instead of a simple calcination in an oven.

30

The before-mentioned acids may be inorganic or organic acids. Organic acids are more preferred in the method according to the invention. It is even more preferred that the organic

acid is a weak organic acid such as glycolic acid, acetic acid, lactic acid, citric acid, oxalic acid, malonic acid, succinic acid, adipic acid, maleic acid, tartaric acid, or mixtures thereof, in particular glycolic acid, acetic acid, and/or lactic acid. It is further preferred that the organic acid is a chelating organic acid, i.e. be capable to stabilize the metals of the precursor compounds of the catalytically active component by means of more than one coordinative bond. These chelating organic acids are preferably α -hydroxycarboxylic acids, dicarboxylic acids. Preferred examples of such chelating organic acids are glycolic acid, lactic acid, citric acid, oxalic acid, malonic acid, succinic acid, adipic acid, maleic acid, tartaric acid, or mixtures thereof, in particular glycolic acid, and/or lactic acid. The latter allows better solubilization of the metals and metal bonds. An advantageous pH of the acidic aqueous solvent is in the range of pH 0 to 6, preferably pH 0.5 to 4, taking into account the fact that some metallic precursor compounds of the catalytically active component are only sparingly or slowly soluble in a neutral or weakly basic environment, while other metallic precursor compounds of the catalytically active component may precipitate in an excessively acidic environment. A suitable pH may be easily selected by those skilled in the art, taking into account the particular precursor compounds of the catalytically active component to be used.

In the method according to the invention, the solution obtained in step a) is brought into contact with a chemically inert, porous support having a specific surface of 1 to 500 m²/g (measured according to the BET method of DIN ISO 9277:2010 or DIN 66134) in a step b).

In one preferred embodiment, step b) includes impregnation of the (chemically) inert, porous support with the solution obtained in step a). The impregnation is particularly preferably carried out using a so-called incipient wetness method (pore-filling method) in which the porous support is combined with a volume of the solution obtained in step a) which corresponds to its pore volume. It is advantageous for the porous support to contain no water residues prior to the impregnation, so that the support material is preferably dried prior to the impregnation in order to remove any water from the pores and thus increase the free pore volume. In this method, the catalytically active component and the precursor compounds thereof are distributed very uniformly on the surface of the support.

In another embodiment, step b) includes coating of the surface of the chemically inert, porous support with the solution obtained in step a). Examples of coating methods preferred according to the invention include spraying the solution obtained in step a) onto the support (spray coating) and dipping the support into the solution obtained in step a) (dip coating).

5 In another embodiment, the support is heated during the bringing into contact according to step b) of the method according to the invention and/or directly thereafter in order to rapidly evaporate the solvent. This is advantageous in particular when runoff of the solution is to be avoided. On the other hand, it may also be advantageous to delay the evaporation of the solvent, for example by cooling the support, when a uniform distribution of the catalytically
10 active component or the precursor compounds of the catalytically active component cannot be ensured.

It is important for the method according to the invention that the porous support has a certain specific surface in order to ensure a high conversion rate of the oxidation reaction to be
15 catalyzed, and thus, a high yield of the desired product. This is because the pore structure of the support, among other factors, primarily determines the pore structure of the finished catalyst. According to the invention, the specific surface of the support is 1 to 500 m²/g, preferably 1 to 250 m²/g, preferably 1 to 100 m²/g, more preferably 2 to 90 m²/g, even more preferably 5 to 85 m²/g, most preferably 10 to 80 m²/g. The specific surface is determined
20 using the BET method according to DIN ISO 9277:2010.

In one preferred embodiment, the inert, porous support, preferably chemically inert support, is formed as a molded body. In principle, the support formed as a molded body may have any shape known by those skilled in the art to be suitable for the purpose according to the
25 invention. As the result of forming the support into the shape desired for the subsequent use in the reaction to be catalyzed prior to bringing it into contact with the precursor compounds of the catalytically active component, shaping the catalyst before the calcination, as is known from the prior art, is no longer necessary, so that the mechanical problems of the catalysts from the prior art do not occur in the shaping in the method according to the invention, also
30 without the need for using additives for enhancing the mechanical properties, or binders.

The support material is not subject to any special limitations as long as it is (chemically) inert and has the required specific surface. Within the meaning of the present invention, "inert" or "chemically inert" means that during the reaction to be catalyzed, the support material does not take part in a chemical reaction, in particular with substances participating in the reaction
5 to be catalyzed.

In one preferred embodiment, the support material according to the invention is an inorganic support material. Suitable examples include silicon carbide, silicon dioxide, zirconium dioxide, titanium dioxide, aluminum oxide, porous ceramics, sheet silicates, bentonites, and
10 mixtures thereof. Supports that are not inorganic, in particular carbon-based supports, may also be used.

According to another embodiment of the method according to the invention, it may be provided that a drying step takes place between step b) and step c) of the method according to
15 the invention. This optional drying step is used to remove the solvent, so that, in contrast to the heat treatment according to step c) of the method according to the invention, the precursor compounds of the catalytically active component are not appreciably decomposed into their oxides. The drying temperature is preferably in the range of 25 to 250°C, preferably in the range of 50 to 200°C, more preferably in the range of 80 to 180°C, and particularly preferably
20 in the range of 100 to 150°C. The drying period is preferably in the range of 5 min to 10 h, preferably in the range of 30 min to 8 h, more preferably in the range of 1 to 5 h.

In the method according to the invention, the material obtained in step b) which is optionally subjected to a drying step undergoes heat treatment in a step c), so that the precursor
25 compounds of the catalytically active component are decomposed into their oxides (i.e. the catalytically active component).

In one preferred embodiment, step c) of the method according to the invention includes calcination of the material obtained in step b) which is optionally subjected to a drying step.
30 The term "calcination" is generally understood to mean heating to high temperatures with the objective of changing, in particular materially or structurally, the treated material or a component thereof. As the result of calcination, for example thermal decomposition, a phase

transition, or the removal of volatile substances may be achieved. In step c) of the method according to the invention, in particular the precursor compounds of the catalytically active component, which have been used in soluble form in step a) of the method according to the invention as stated above, are decomposed into their respective oxides, i.e., converted to their catalytically effective form.

In one particularly preferred embodiment, the heat treatment according to step c) of the method according to the invention includes heating of the material obtained in step b), which is optionally subjected to a drying step, to a temperature in the range of 400 to 700°C, preferably in the range of 450 to 650°C, more preferably in the range of 480 to 620°C, and particularly preferably in the range of 500 to 610°C. The duration of the heat treatment according to step c) of the method according to the invention is preferably in the range of 30 min to 20 h, preferably in the range of 45 min to 15 h, more preferably in the range of 1 to 8 h.

The present invention further relates to a catalyst which is obtainable using the method according to the invention. The catalyst according to the invention not only has a high efficiency of the catalytically active components used, since essentially all catalytically active components used are actually available for the reaction to be catalyzed, but also has a high conversion rate of the reaction to be catalyzed and thus a high yield of the desired product, since, due to the targeted selection of the catalyst support, the pore structure of the product may be optimally adjusted to the needs of the reaction to be catalyzed. The catalyst according to the invention is very well suited in particular for the partial oxidation/ammoxidation of olefins, in particular for the partial oxidation of propene to acrolein, of isobutene to methacrolein, and/or the ammoxidation of propene to acrylonitrile.

The catalyst according to the invention includes a compound having the general formula $\text{Mo}_x\text{Bi}_y\text{Fe}_z\text{A}_a\text{B}_b\text{C}_c\text{D}_d\text{O}_v$, as the catalytically active component, where A stands for Ni and/or Co, B stands for one or more metals selected from Mg, Cr, Mn, Zn, Ce, and Ca and combinations thereof, C stands for W, and D stands for one or more alkali metals, where x stands for a number from 10 to 14, and in preferred refinements x is 12, y stands for a number from 0.1 to 5, z stands for a number from 0.5 to 5, a stands for a number from 1 to 10, b

stands for a number from 0.1 to 6, c stands for a number from ≥ 0 to 2, d stands for a number from 0.02 to 2, and v is determined by the oxidation state of the other elements.

In one refinement of the invention, B stands for Mg.

5

In another refinement of the invention, D stands for K and/or Cs, preferably K.

In another refinement of the invention, y stands for a number from 0.2 to 3, preferably a number from 0.5 to 2 or a number from 0.7 to 1.5, more preferably a number from 0.8 to 1.4, even more preferably a number from 0.9 to 1.3, in particular a number from 1.0 to 1.2.

10

In another refinement of the invention, z stands for a number from 0.6 to 4, preferably a number from 0.7 to 3 or a number from 0.75 to 2.5, in particular a number from 0.8 to 2.2.

15

In yet another refinement of the invention, a stands for a number from 2 to 9, preferably a number from 3 to 8 or a number from 4 to 7, in particular a number from 5.5 to 6.5.

In another embodiment, the catalyst according to the invention contains Ni as well as Co, the molar fractions e for Ni and f for Co resulting in the sum a, i.e., $a = e + f$. It is advantageous when e stands for a number from 1.5 to 3.5, preferably a number from 1.8 to 3.2, more preferably a number from 2.0 to 3.0, in particular a number from 2.4 to 2.7, and when f stands for a number from 2.5 to 5.5, preferably a number from 2.8 to 4.5 or a number from 3.0 to 4.0, in particular a number from 3.3 to 3.6.

20

25

In another refinement of the invention, b stands for a number from 0.15 to 5, preferably a number from 0.2 to 3 or a number from 0.22 to 2.5, in particular a number from 0.25 to 2.0. For the case that B stands for multiple metals from the group Mg, Cr, Mn, Zn, Ce, and Ca, the molar fractions thereof result in the sum b.

30

In another refinement of the invention, c stands for a number from 0.02 to 1.5, preferably a number from 0.05 to 1.0 or a number from 0.1 to 0.6, in particular a number from 0.15 to 0.4.

In another refinement of the invention, d stands for a number from 0.03 to 1.0, preferably a number from 0.04 to 0.5 or a number from 0.05 to 0.1, in particular a number from 0.06 to 0.09.

5 The above-described catalysts according to the invention have proven to be particularly suitable for the partial oxidation/ammoxidation of olefins, in particular for the partial oxidation of propene to acrolein, of isobutene to methacrolein, and/or the ammoxidation of propene to acrylonitrile, in particular with regard to a high conversion rate of the starting product and a high yield of the desired products, and at the same time with high selectivity.

10

Accordingly, the present invention further relates to the use of a catalyst according to the invention for the partial oxidation or ammoxidation of olefins, in particular for the oxidation of propene to acrolein or of isobutene to methacrolein, and/or for the ammoxidation of propene to acrylonitrile.

15

Furthermore, the present invention also relates to a method for the partial oxidation or ammoxidation of olefins, in particular the oxidation of propene to acrolein or of isobutene to methacrolein, and/or ammoxidation of propene to acrylonitrile, wherein in a first step a catalyst is produced according to the method of the present invention and in a second step the

20 partial oxidation or ammoxidation of olefins is applied with that catalyst.

The present invention further relates to the following embodiments:

In an embodiment (i) the present invention relates to a method for producing a catalyst which

25 includes as the catalytically active component a compound having the general formula $\text{Mo}_x\text{Bi}_y\text{Fe}_z\text{A}_a\text{B}_b\text{C}_c\text{D}_d\text{O}_v$, where A stands for Ni and/or Co, B stands for one or more metals selected from Mg, Cr, Mn, Zn, Ce, and Ca and combinations thereof, C stands for W, and D stands for one or more alkali metals, where x stands for a number from 10 to 14, y stands for a number from 0.1 to 5, z stands for a number from 0.5 to 5, a stands for a number from 1 to

30 10, b stands for a number from 0.1 to 6, c stands for a number from ≥ 0 to 2, d stands for a number from 0.02 to 2, and v is determined by the oxidation state of the elements, the method including the following steps:

- 5
- a) Providing a solution in which the catalytically active components are essentially completely dissolved in a suitable solvent;
 - b) Bringing the solution obtained in step a) into contact with a chemically inert, porous support having a specific surface of 1 to 500 m²/g;
 - c) Heat treatment of the material obtained in step b), in which the catalytically active components are converted to their oxides.

10 In another embodiment (ii) the present invention relates to a method according to embodiment (i), wherein step b) includes impregnation of the chemically inert, porous support with the solution obtained in step a).

15 In another embodiment (iii) the present invention relates to a method according to embodiment (i), wherein step b) includes coating of the surface of the chemically inert, porous support with the solution obtained in step a).

20 In another embodiment (iv) the present invention relates to a method according to one of the preceding embodiments (i) to (iii), wherein the chemically inert, porous support has a specific surface of 1 to 100 m²/g.

In another embodiment (v) the present invention relates to a method according to one of the preceding embodiments (i) to (iv), wherein the chemically inert, porous support is formed as a molded body.

25 In another embodiment (vi) the present invention relates to a method according to one of the preceding embodiments (i) to (v), wherein the chemically inert, porous support is an inorganic support.

30 In another embodiment (vii) the present invention relates to a method according to one of the preceding embodiments (i) to (vi), wherein step c) includes calcination of the material obtained in step b).

In another embodiment (viii) the present invention relates to a method according to one of the preceding embodiments (i) to (vii), wherein the heat treatment in step c) includes heating the material obtained in step b) to a temperature of 450 to 650°C over a period of 1 to 8 hours.

- 5 In another embodiment (ix) the present invention relates to a method according to one of the preceding embodiments (i) to (viii), wherein the suitable solvent in step a) is an aqueous solvent, in particular an acidic aqueous solvent.

In another embodiment (x) the present invention relates to a catalyst which includes a
10 compound having the general formula $\text{Mo}_x\text{Bi}_y\text{Fe}_z\text{A}_a\text{B}_b\text{C}_c\text{D}_d\text{O}_v$ as the catalytically active component, where A stands for Ni and/or Co, B stands for one or more metals selected from Mg, Cr, Mn, Zn, Ce, and Ca and combinations thereof, C stands for W, and D stands for one or more alkali metals, where x stands for a number from 10 to 14, and in preferred
refinements x is 12, y stands for a number from 0.1 to 5, z stands for a number from 0.5 to 5,
15 a stands for a number from 1 to 10, b stands for a number from 0.1 to 6, c stands for a number from ≥ 0 to 2, d stands for a number from 0.02 to 2, and v is determined by the oxidation state of the other elements, the catalyst being obtainable by a method according to one of the preceding embodiments (i) to (ix).

- 20 In another embodiment (xi) the present invention relates to the catalyst according to embodiment (x), where x is 12.

In another embodiment (xii) the present invention relates to the use of a catalyst according to
embodiments (x) and (xi) for the partial oxidation or ammoxidation of olefins, in particular
25 for the oxidation of propene to acrolein and/or of isobutene to methacrolein, and/or for the ammoxidation of propene to acrylonitrile.

The term “catalytically active components” in steps a) to c) of the method according to
embodiment (i) is to be understood as precursor compounds of the catalytically active
30 component in the meaning as defined above.

The invention is explained in greater detail below with reference to several exemplary embodiments, which are not to be construed as limiting to the scope of the invention.

Examples:

5

Example 1

0.512 g bismuth nitrate, 2.118 g ammonium heptamolybdate, 0.610 g nickel acetate, 0.82 g cobalt acetate, 0.483 g iron(III) nitrate, and 0.43 g magnesium acetate were dissolved in 3 mL of an aqueous glycolic acid solution (70% by weight in water). After dissolution was complete, 0.111 mL of an ammonium metatungstate solution (2.35 M tungsten) and 0.062 mL of a potassium acetate solution (1.13 M) were added. This solution was mixed with 6 g SiC (BET = 27 m²/g, pore volume: 0.9 mL/g). The material obtained was calcined for 4 hours at 500°C, resulting in catalyst 1.

15

Example 2

0.512 g bismuth nitrate, 2.118 g ammonium heptamolybdate, 0.610 g nickel acetate, 0.82 g cobalt acetate, 0.322 g iron(III) nitrate, and 0.43 g magnesium acetate were dissolved in 3 mL of an aqueous glycolic acid solution (70% by weight in water). After dissolution was complete, 0.128 mL of an ammonium metatungstate solution (2.35 M tungsten) and 0.062 mL of a potassium acetate solution (1.13 M) were added. This solution was mixed with 6 g SiC (BET = 27 m²/g, pore volume: 0.9 mL/g). The material obtained was calcined for 4 hours at 500°C, resulting in catalyst 2.

25

Example 3

0.256 g bismuth nitrate, 1.059 g ammonium heptamolybdate, 0.305 g nickel acetate, 0.41 g cobalt acetate, 0.402 g iron(III) nitrate, and 0.215 g magnesium acetate were dissolved in 3 mL of an aqueous glycolic acid solution (70% by weight in water). After dissolution was complete, 0.085 mL of an ammonium metatungstate solution (2.35 M tungsten) and 0.031 mL of a potassium acetate solution (1.13 M) were added. This solution was mixed with 3 g

30

SiC (BET = 27 m²/g, pore volume: 0.9 mL/g). The material obtained was calcined for 4 hours at 500°C, resulting in catalyst 3.

Example 4

5

0.256 g bismuth nitrate, 1.059 g ammonium heptamolybdate, 0.305 g nickel acetate, 0.41 g cobalt acetate, 0.402 g iron(III) nitrate, and 0.108 g magnesium acetate were dissolved in 1.5 mL of an aqueous glycolic acid solution (70% by weight in water). After dissolution was complete, 0.043 mL of an ammonium metatungstate solution (2.35 M tungsten) and 0.031 mL of a potassium acetate solution (1.13 M) were added. This solution was mixed with 3 g SiC (BET = 27 m²/g, pore volume: 0.9 mL/g). The material obtained was calcined for 4 hours at 500°C, resulting in catalyst 4.

Example 5

15

0.256 g bismuth nitrate, 1.0593 g ammonium heptamolybdate, 0.305 g nickel acetate, 0.41 g cobalt acetate, 0.402 g iron(III) nitrate, and 0.215 g magnesium acetate were dissolved in 1.5 mL of an aqueous glycolic acid solution (70% by weight in water). After dissolution was complete, 0.043 mL of an ammonium metatungstate solution (2.35 M tungsten) and 0.031 mL of a potassium acetate solution (1.13 M) were added. This solution was mixed with 3 g SiC (BET = 27 m²/g, pore volume: 0.9 mL/g). The material obtained was calcined for 4 hours at 500°C, resulting in catalyst 5.

Example 6

25

0.261 g bismuth nitrate, 1.0593 g ammonium heptamolybdate, 0.311 g nickel acetate, 0.418 g cobalt acetate, 0.41 g iron(III) nitrate, and 0.110 g magnesium acetate were dissolved in 1.5 mL of an aqueous glycolic acid solution (70% by weight in water). After dissolution was complete, 0.043 mL of an ammonium metatungstate solution (2.35 M tungsten) and 0.032 mL of a potassium acetate solution (1.13 M) were added. This solution was mixed with 2.2 g SiO₂ (BET = 68 m²/g, pore volume: 1.2 mL/g). The material obtained was calcined for 4 hours at 500°C, resulting in catalyst 6.

Example 7

0.261 g bismuth nitrate, 1.0593 g ammonium heptamolybdate, 0.311 g nickel acetate, 0.418 g cobalt acetate, 0.41 g iron(III) nitrate, and 0.110 g magnesium acetate were dissolved in 1.5
5 mL of an aqueous glycolic acid solution (70% by weight in water). After dissolution was complete, 0.043 mL of an ammonium metatungstate solution (2.35 M tungsten) and 0.032 mL of a potassium acetate solution (1.13 M) were added. This solution was mixed with 2.2 g SiO₂ (BET = 68 m²/g, pore volume: 1.2 mL/g). The material obtained was calcined for 3 hours at 550°C, resulting in catalyst 7.

10

Example 8

0.279 g bismuth nitrate, 1.0593 g ammonium heptamolybdate, 0.332 g nickel acetate, 0.447 g cobalt acetate, 0.439 g iron(III) nitrate, and 0.030 g magnesium acetate were dissolved in 1.5
15 mL of an aqueous glycolic acid solution (70% by weight in water). After dissolution was complete, 0.039 mL of an ammonium metatungstate solution (2.35 M tungsten) and 0.034 mL of a potassium acetate solution (1.13 M) were added. This solution was mixed with 2.2 g SiO₂ (BET = 68 m²/g, pore volume: 1.2 mL/g). The material obtained was calcined for 1 hour at 550°C, resulting in catalyst 8.

20

Example 9

0.261 g bismuth nitrate, 1.0593 g ammonium heptamolybdate, 0.311 g nickel acetate, 0.418 g cobalt acetate, 0.41 g iron(III) nitrate, and 0.110 g magnesium acetate were dissolved in 1.5
25 mL of an aqueous glycolic acid solution (70% by weight in water). After dissolution was complete, 0.043 mL of an ammonium metatungstate solution (2.35 M tungsten) and 0.032 mL of a potassium acetate solution (1.13 M) were added. This solution was mixed with 3 g SiC (BET = 27 m²/g, pore volume: 0.9 mL/g). The material obtained was calcined for 1 hour at 590°C, resulting in catalyst 9.

30

Example 10

0.279 g bismuth nitrate, 1.0593 g ammonium heptamolybdate, 0.332 g nickel acetate, 0.447 g cobalt, 0.439 g iron(III) nitrate, and 0.030 g magnesium acetate were dissolved in 1.5 mL of
5 an aqueous glycolic acid solution (70% by weight in water). After dissolution was complete, 0.039 mL of an ammonium metatungstate solution (2.35 M tungsten) and 0.034 mL of a potassium acetate solution (1.13 M) were added. This solution was mixed with 3 g SiC (BET = 27 m²/g, pore volume: 0.9 mL/g). The material obtained was calcined for 1 hour at 590°C, resulting in catalyst 10.

10

Example 11

0.256 g bismuth nitrate, 1.059 g ammonium heptamolybdate, 0.305 g nickel acetate, 0.41 g cobalt acetate, 0.402 g iron(III) nitrate, and 0.108 g magnesium acetate were dissolved in 1.5
15 mL of an aqueous lactic acid solution (70% by weight in water). After dissolution was complete, 0.043 mL of an ammonium metatungstate solution (2.35 M tungsten) and 0.031 mL of a potassium acetate solution (1.13 M) were added. This solution was mixed with 3 g SiC (BET = 27 m²/g). The material obtained was calcined for 4 hours at 500°C, resulting in catalyst 11.

20

Comparative examples:Comparative example 1

25 0.256 g bismuth nitrate, 1.059 g ammonium heptamolybdate, 0.305 g nickel acetate, 0.41 g cobalt acetate, 0.402 g iron(III) nitrate, and 0.108 g magnesium acetate were dissolved in 1.5 mL of an aqueous glycolic acid solution (70% by weight in water). After dissolution was complete, 0.043 mL of an ammonium metatungstate solution (2.35 M tungsten) and 0.031 mL of a potassium acetate solution (1.13 M) were added. This solution was mixed with 3 g
30 SiC (BET = 0.001 m²/g). The material obtained was calcined for 4 hours at 500°C, resulting in catalyst 12.


Comparative example 2

0.256 g bismuth nitrate, 1.059 g ammonium heptamolybdate, 0.305 g nickel acetate, 0.41 g cobalt acetate, 0.402 g iron(III) nitrate, and 0.108 g magnesium acetate were dissolved in 1.5 mL of an aqueous glycolic acid solution (70% by weight in water). After dissolution was complete, 0.043 mL of an ammonium metatungstate solution (2.35 M tungsten) and 0.031 mL of a potassium acetate solution (1.13 M) were added. This solution was mixed with 3 g α -Al₂O₃ (BET = 0.1 m²/g). The material obtained was calcined for 4 hours at 500°C, resulting in catalyst 13.

Comparative Example 3

A first solution was prepared by dissolving 0.44 g ammonium heptamolybdate and 0.018 g ammonium metatungstate in 0.89 mL water and adding 0.065 g colloidal SiO₂ (BET = 129-155 m²/g; Ludox AS-40). A second solution was prepared by dissolving 0.0149 g bismuth nitrate, 0.312 g nickel nitrate, 0.089 g cobalt nitrate, 0.185 g ferric nitrate, 0.118 g magnesium nitrate, 0.00032 g potassium nitrate, and 0.00061 g cesium nitrate in 0.62 mL water. The two aqueous solutions were combined to form a slurry. To the slurry was added 0.046 g of Coconit 300. The slurry was dried on a hot plate and the solid was further dried at 110 °C. The solid was calcined in air at 580 °C for 1 h to produce catalyst 14.


The elemental composition of the obtained material was as follows:

Comparative Example 4

A first solution was prepared by dissolving 0.44 g ammonium heptamolybdate in 0.89 mL water and adding 0.065 g colloidal SiO₂ (BET = 129-155 m²/g; Ludox AS-40). A second solution was prepared by dissolving 0.0286 g bismuth nitrate, 0.24 g nickel nitrate, 0.137 g cobalt nitrate, 0.143 g ferric nitrate, 0.090 g magnesium nitrate, 0.030 g manganese nitrate, 0.030 g cerium nitrate, 0.00023 g potassium nitrate, and 0.00093 g cesium nitrate in 0.83 mL water. The two aqueous solutions were combined to form a slurry. To the slurry was added

0.046 g of Coconit 300. The slurry was dried on a hot plate and the solid was further dried at 110 °C. The solid was calcined in air at 580 °C for 1 h to produce catalyst 15.

The elemental composition of the obtained material was as follows:



The elemental composition of the obtained catalysts is summarized in Table 1 below.

Comparative Example 5

10

A first solution is produced in that 1.02 kg iron nitrate nonahydrate (Honeywell; Lot: B1960) is added to 0.727 kg deionized water at 60°C. Without further heating the solution 2.37 kg nickel nitrate hexahydrate (ALFA Aesar; Lot: 61101000) and 0.62 kg magnesium nitrate hexahydrate (Honeywell; Lot: 90140) are subsequently added, and the compounds are solved
15 under stirring. Then, 0.039 kg 1 M KOH (Merck; Lot: HC111978) is added. After the addition of KOH a brown precipitate is formed, which is then again quickly solved. Subsequently, 0.3 kg bismuth nitrate pentahydrate (ALFA Aesar; Lot: 42060004) is added.

20

A second solution is produced by adding 2.62 kg ammoniumheptamolybdat tetrahydrat (HC Starck; Lot: 1163/048) into 8.3 kg deionized water and is solved under stirring.

25

After that, the first and the second solution are combined and 0.19 kg Syloid C809 (Grace Davison; Lot: 1000214955; colloidal SiO_2) is added. Thereby, a precipitate is formed which forms a suspension with the resulting solution.

30

The so obtained suspension is spray-calcined in a pulsation reactor of the company IBU-tec (Typ: PR-4). The temperature in the pulsation reactor is 500°C and the residence time was in the range of 200 ms to 2 s. The obtained material is formed to catalyst 16.

Table 1

Catalyst	Mo	Bi	Fe	Ni	Co	Mg	W	K
Catalyst 1	12	1.05	1.2	2.45	3.3	2.0	0.26	0.07
Catalyst 2	12	1.05	0.8	2.45	3.3	2.0	0.3	0.07
Catalyst 3	12	1.05	2.0	2.45	3.3	2.0	0.4	0.07
Catalyst 4	12	1.05	2.0	2.45	3.3	1.0	0.2	0.07
Catalyst 5	12	1.05	2.0	2.45	3.3	2.0	0.2	0.07
Catalyst 6	12	1.07	2.04	2.5	3.37	1.02	0.2	0.07
Catalyst 7	12	1.07	2.04	2.5	3.37	1.02	0.2	0.07
Catalyst 8	12	1.145	2.18	2.67	3.6	0.28	0.185	0.08
Catalyst 9	12	1.07	2.04	2.5	3.37	1.02	0.2	0.07
Catalyst 10	12	1.145	2.18	2.67	3.6	0.28	0.185	0.08
Catalyst 11	12	1.05	2.0	2.45	3.3	1.0	0.2	0.07
Catalyst 12	12	1.05	2.0	2.45	3.3	1.0	0.2	0.07
Catalyst 13	12	1.05	2.0	2.45	3.3	1.0	0.2	0.07

Test results:

5
 Catalysts 1 through 16 were tested with regard to their catalytic properties in the partial
 oxidation of propene. For this purpose, they were added to a multi-channel fixed-bed reactor
 and exposed to a reaction mixture composed of 8% by volume propene, 14.4% by volume
 oxygen, 8% by volume water vapor, 10% by volume neon, and the remainder helium at
 10 360°C for a contact period of 0.5 to 2.5 sec. The results obtained are shown in Table 2 below.

Table 2

Catalyst	Propylene conversion rate [%]	Yield (acrolein and acrylic acid) [%]
Catalyst 1	99.0	95.6
Catalyst 2	99.1	95.8
Catalyst 3	99.1	94.6
Catalyst 4	99.5	96.1
Catalyst 5	99.2	93.9
Catalyst 6	99.0	96.3
Catalyst 7	99.1	96.2
Catalyst 8	99.0	96.2
Catalyst 9	98.4	95.9
Catalyst 10	98.0	95.8
Catalyst 11	98.6	95.9
Catalyst 12 *	2.8	2.75
Catalyst 13 *	13.8	13.3
Catalyst 14 *	91.8	96.0
Catalyst 15 *	87.8	94.1
Catalyst 16 *	99.5	88.6

* Comparative examples

- 5 These results clearly show that the catalysts produced by the method according to the invention are highly effective, selective catalysts for the oxidation of olefins. The catalysts of the comparative examples, in which the same solution was used as for catalyst 4 according to the invention but in which a support not according to the invention, having a low specific

surface, was used, are clearly inferior to the catalysts according to the invention, and can by no means be used to achieve the underlying object of the present invention. Catalyst 16 is prepared according to the invention with the only difference that no chelating acid is used in the solution comprising all metal precursor compounds. The use of the pulsating temperature
5 treatment, however, ensures that the disadvantage of the absence of a chelating acid is partly compensated in the catalytic performance. However, when preparing a catalyst according to comparative example 5 but calcining the material at about 550°C for 1 h in a usual calcining oven instead of the pulsating treatment, the inventors of the present invention observed that the catalytic performance is significantly lower than for catalyst 16.

Claims

1. Method for producing a catalyst which includes as the catalytically active component a compound having the general formula $Mo_xBi_yFe_zA_aB_bC_cD_dO_v$, where A stands for
5 Ni and/or Co, B stands for one or more metals selected from Mg, Cr, Mn, Zn, Ce, and Ca and combinations thereof, C stands for W, and D stands for one or more alkali metals, where x stands for a number from 10 to 14, y stands for a number from 0.1 to 5, z stands for a number from 0.5 to 5, a stands for a number from 1 to 10, b stands for a number from 0.1 to 6, c stands for a number from ≥ 0 to 2, d stands for a number
10 from 0.02 to 2, and v is determined by the oxidation state of the elements, the method including the following steps:
- a) Providing a solution in which precursor compounds of the catalytically active component are essentially completely dissolved in a suitable solvent;
 - 15 b) Bringing the solution obtained in step a) into contact with a chemically inert, porous support having a specific surface of 1 to 500 m^2/g ;
 - c) Heat treatment of the material obtained in step b), in which the precursor compounds of the catalytically active component are converted to their oxides.
- 20 2. Method according to Claim 1, wherein step b) includes impregnation of the chemically inert, porous support with the solution obtained in step a).
3. Method according to Claim 1, wherein step b) includes coating of the surface of the chemically inert, porous support with the solution obtained in step a).
- 25 4. Method according to one of the preceding claims, wherein the chemically inert, porous support has a specific surface of 1 to 100 m^2/g .
5. Method according to one of the preceding claims, wherein the chemically inert,
30 porous support is formed as a molded body.

6. Method according to one of the preceding claims, wherein the chemically inert, porous support is an inorganic support.
7. Method according to one of the preceding claims, wherein step c) includes calcination
5 of the material obtained in step b).
8. Method according to one of the preceding claims, wherein the heat treatment in step c) includes heating the material obtained in step b) to a temperature of 450 to 650°C over a period of 1 to 8 hours.
- 10
9. Method according to one of the preceding claims, wherein the suitable solvent in step a) is an aqueous solvent, in particular an acidic aqueous solvent.
10. Catalyst which includes a compound having the general formula
15 $\text{Mo}_x\text{Bi}_y\text{Fe}_z\text{A}_a\text{B}_b\text{C}_c\text{D}_d\text{O}_v$ as the catalytically active component, where A stands for Ni and/or Co, B stands for one or more metals selected from Mg, Cr, Mn, Zn, Ce, and Ca and combinations thereof, C stands for W, and D stands for one or more alkali metals, where x stands for a number from 10 to 14, and in preferred refinements x is 12, y stands for a number from 0.1 to 5, z stands for a number from 0.5 to 5, a stands for a
20 number from 1 to 10, b stands for a number from 0.1 to 6, c stands for a number from ≥ 0 to 2, d stands for a number from 0.02 to 2, and v is determined by the oxidation state of the other elements, the catalyst being obtainable by a method according to one of the preceding claims.
- 25
11. Catalyst according to Claim 10, where x is 12.
12. Use of a catalyst according to Claim 10 or 11 for the partial oxidation or ammoxidation of olefins, in particular for the oxidation of propene to acrolein and/or of isobutene to methacrolein, and/or for the ammoxidation of propene to acrylonitrile.
- 30

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2014/033714

A. CLASSIFICATION OF SUBJECT MATTER
 INV. B01J23/881 B01J23/882 B01J23/883 B01J23/887 B01J23/888
 B01J35/10 B01J37/02
 ADD.
 According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED
 Minimum documentation searched (classification system followed by classification symbols)
 B01J C07C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)
 EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DE 10 2007 009981 A1 (EVONIK DEGUSSA GMBH [DE]) 4 September 2008 (2008-09-04) abstract paragraphs [0038] - [0042] example 1	1-12
X	EP 0 239 071 A2 (MITSUBISHI PETROCHEMICAL CO [JP]) 30 September 1987 (1987-09-30) abstract page 7, lines 41-51 examples B-6 claim 1	1-12
	----- -/--	

Further documents are listed in the continuation of Box C.

See patent family annex.

* Special categories of cited documents :

<p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier application or patent but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p>	<p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</p> <p>"&" document member of the same patent family</p>
---	---

Date of the actual completion of the international search 7 July 2014	Date of mailing of the international search report 16/07/2014
--	--

Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer Fischbach, Malaika
--	--

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2014/033714

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2004/110978 A1 (PAPARIZOS CHRISTOS [US] ET AL) 10 June 2004 (2004-06-10) abstract paragraph [0042] example 3 claims 1,8 -----	1-12
X	US 5 834 394 A (CHEN XIN [CN] ET AL) 10 November 1998 (1998-11-10) abstract column 4, lines 34-49 examples 2,7,11 claims 1,13,14 -----	1-12
X	MY 141 945 A (ASAHI KASEI CHEMICALS CORP [JP]) 30 July 2010 (2010-07-30) abstract page 12, line 6 - page 16, line 7 page 31, lines 8-21 examples 1,2 table 1 claim 1 -----	1-12

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No
PCT/US2014/033714

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
DE 102007009981 A1	04-09-2008	BR PI0808026 A2	17-06-2014
		CN 101631615 A	20-01-2010
		DE 102007009981 A1	04-09-2008
		EP 2125213 A1	02-12-2009
		JP 2010520040 A	10-06-2010
		RU 2009135860 A	27-05-2011
		SG 170046 A1	29-04-2011
		US 2010324331 A1	23-12-2010
		US 2012283088 A1	08-11-2012
		WO 2008104432 A1	04-09-2008

EP 0239071 A2	30-09-1987	CN 87103192 A	08-06-1988
		DE 3775587 D1	13-02-1992
		EP 0239071 A2	30-09-1987
		SU 1665870 A3	23-07-1991
		US 4732884 A	22-03-1988

US 2004110978 A1	10-06-2004	AU 2003295643 A1	23-06-2004
		BR 0316852 A	18-10-2005
		CA 2507182 A1	17-06-2004
		EP 1567263 A1	31-08-2005
		JP 4688499 B2	25-05-2011
		JP 2006507936 A	09-03-2006
		JP 2011062692 A	31-03-2011
		KR 20050085259 A	29-08-2005
		MX PA05005760 A	08-09-2005
		RU 2349379 C2	20-03-2009
		US 2004110978 A1	10-06-2004
		WO 2004050240 A1	17-06-2004

US 5834394 A	10-11-1998	JP 3896194 B2	22-03-2007
		JP H10156185 A	16-06-1998
		US 5834394 A	10-11-1998

MY 141945 A	30-07-2010	NONE	
