



(86) Date de dépôt PCT/PCT Filing Date: 2004/05/14
 (87) Date publication PCT/PCT Publication Date: 2004/12/02
 (85) Entrée phase nationale/National Entry: 2005/10/24
 (86) N° demande PCT/PCT Application No.: US 2004/015526
 (87) N° publication PCT/PCT Publication No.: 2004/104100
 (30) Priorités/Priorities: 2003/05/15 (60/470,756) US;
 2003/05/15 (60/470,592) US; 2003/06/03 (60/475,396) US

(51) Cl.Int.⁷/Int.Cl.⁷ C08L 67/02
 (71) Demandeur/Applicant:
 E.I. DU PONT DE NEMOURS AND COMPANY, US
 (72) Inventeurs/Inventors:
 ALMS, GREGORY R., US;
 CROFT, NEIL J., US;
 GRUNER, CHRISTIAN, DE;
 KOBAYASHI, TOSHIKAZU, US;
 MOLITOR, MICHAEL J., US;
 BRISSOT, CLAIRE, FR;
 STEGEN, HELGA, DE
 (74) Agent: BENNETT JONES LLP

(54) Titre : COMPOSITIONS DE POLYESTER A CRISTALLISATION RAPIDE
 (54) Title: FAST CRYSTALLIZING POLYESTER COMPOSITIONS

(57) **Abrégé/Abstract:**

Fast crystallizing polyester compositions comprise a semicrystalline isotropic polyester, and specified amount of a liquid crystalline polymer, a solid particulate material, and a plasticizer for the isotropic polyester. These compositions generally crystallize faster and/or more extensively and/or at lower temperatures than the corresponding compositions without these ingredients present. The compositions are especially useful for molded and extruded parts.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
2 December 2004 (02.12.2004)

PCT

(10) International Publication Number
WO 2004/104100 A1

- (51) International Patent Classification⁷: **C08L 67/02**
- (21) International Application Number:
PCT/US2004/015526
- (22) International Filing Date: 14 May 2004 (14.05.2004)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
60/470,592 15 May 2003 (15.05.2003) US
60/470,756 15 May 2003 (15.05.2003) US
60/475,396 3 June 2003 (03.06.2003) US
- (71) Applicant (for all designated States except US): **E.I. DUPONT DE NEMOURS AND COMPANY** [US/US]; 1007 Market Street, Wilmington, DE 19898 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **ALMS, Gregory, R.** [US/US]; 1 Ashleaf Court, Hockessin, DE 19707 (US). **CROFT, Neil, J.** [US/US]; 9 Forest Gate Lane, Wilmington, DE 19810 (US). **GRUNER, Christian** [DE/DE]; Am Benden 16, 50345 Huerth (DE). **KOBAYASHI, Toshikazu** [JP/US]; 116 Millbrook drive, Chadds Ford, PA 19317 (US). **MOLITOR, Michael, J.** [US/US]; 107 Mathes Places, Wilmington, DE 19804 (US). **BRISSOT, Claire** [FR/FR]; Villa "la fontaine", Apartment 1.2-598, Route de Fenieres, F-01710 Thiory (FR). **STEGEN, Helga** [DE/DE]; Berliner Strasse 144, 42277 Wuppertal (DE).
- (74) Agent: **JARNHOLM, Arne, R.**; E. I. Du Pont De Nemours And Company, Legal Patent Records Center, 4417 Lancaster Pike, Wilmington, DE 19805 (US).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:**
— with international search report
— before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: FAST CRYSTALLIZING POLYESTER COMPOSITIONS

(57) Abstract: Fast crystallizing polyester compositions comprise a semicrystalline isotropic polyester, and specified amount of a liquid crystalline polymer, a solid particulate material, and a plasticizer for the isotropic polyester. These compositions generally crystallize faster and/or more extensively and/or at lower temperatures than the corresponding compositions without these ingredients present. The compositions are especially useful for molded and extruded parts.

WO 2004/104100 A1

FAST CRYSTALLIZING POLYESTER COMPOSITIONS

FIELD OF THE INVENTION

5 Fast crystallizing polyester compositions comprise an isotropic polyester, a liquid crystalline polymer, optionally a solid particulate material, and a plasticizer for the isotropic polyester.

TECHNICAL BACKGROUND

10 Thermoplastic isotropic polyesters (IPEs) are important items of commerce, being used for fibers, molded and extruded parts, foams, and other uses. Many of these IPEs are semicrystalline, that is part of the IPE is in a crystalline form in the end use part. In semicrystalline polymers in general part of the polymer is present in an amorphous (often glassy) form, and part of the polymer is present as crystallites, usually distributed throughout the polymer. In most instances, it is preferred that IPEs which can crystallize be used in the semicrystalline form, and often it is helpful or necessary that the IPE crystallize relatively rapidly for the purpose of forming the final part.

25 For example, in injection molding of thermoplastics, the molten polymer is injected into a mold and rapidly cooled until it is solid. The mold is then opened and solid part is ejected from the mold. If the part is not solid and/or deforms easily upon ejection from the mold it may be deformed and thereby rendered useless. An important facet in have obtaining a relatively strong part from semicrystalline IPEs is that they be (at least partially) crystallized when they are removed from the mold. However some semicrystalline IPEs crystallize very

30

slowly, so they would have to be in the mold a long time to allow them to be demolded without significant deformation. This would lead to long molding cycles, which is highly undesirable and uneconomic.

5 To solve this slow crystallization of some IPEs, so-called "crystallization packages" or "crystallization initiator systems" have been developed for slow crystallizing polyesters. These packages provide much faster crystallization initiation and/or faster
10 crystallization itself and/or lower the crystallization temperature. For example poly(ethylene terephthalate) (PET) is a slow crystallizing IPE, and by itself is usually unsuitable for injection molding because of the very long molding cycles and/or high mold temperatures
15 needed. However crystallization packages have been developed for this IPE, making it suitable for injection molding and other forming processes. A typical crystallization package for PET is a sodium ion source such as a sodium or a sodium salt of a carboxylate
20 containing polymer and a small amount of plasticizer for the PET, see for instance U.S. Patent Re32,334. While not all IPEs are slow crystallizing, faster crystallization may lead to shorter melt processing cycle times which are more desirable.

25 U.S. Patent 6,221,962 describes compositions containing an LCP, a toughening agent with reactive functional groups, and a thermoplastic. The presence of specific compositions containing plasticizers is not mentioned.

30 U.S. Patent 4,753,980 describes polyester compositions containing certain toughening agents. The use of LCPs is not mentioned in the patent.

U.S. Patents 4,438,236 and 4,433,083 describe blends of LCPs with various thermoplastics. No specific mention

is made of compositions containing polyesters and plasticizers.

S. H. Kim, et al., J. Appl. Polym. Sci., vol. 67, p. 1383-1392 (1998) reports that "... liquid crystalline polymer reinforcements with 10 wt % added accelerated the rate of crystallization of PET". No mention is made of the use of plasticizers in these compositions.

SUMMARY OF THE INVENTION

This invention concerns a composition, comprising,

10 (a) at least 35 weight percent of a semicrystalline isotropic polyester (IPE) with a melting point of about 100°C or higher;

(b) about 0.1 to about 40 weight percent of a liquid crystalline polymer (LCP) whose melting point is at least 50°C higher than a cold crystallization point (CCP) of said isotropic polyester, or if said isotropic polyester has no cold crystallization point, said melting point of said liquid crystalline polymer is about 150°C or higher;

20 (c) 0.0 to about 60 weight percent of a solid particulate material; and

(d) about 0.2 to about 15 weight percent of a plasticizer for said isotropic polyester;

wherein the weight percentages of (a) and (c) are based on the weight of total composition, and the weight percentages of (b) and (d) are based on the weight of (a) in said composition.

This invention also concerns a process for the formation of a shaped part from an isotropic polyester, comprising, cooling a composition from a temperature above a melting point of said isotropic polyester to a temperature below said melting point, wherein said composition comprises:

(a) at least 35 weight percent of a semicrystalline isotropic polyester with a melting point of about 100°C or higher;

(b) about 0.1 to about 40 weight percent of a liquid crystalline polymer whose melting point is at least 50°C higher than a cold crystallization point of said isotropic polyester, or if said isotropic polyester has no cold crystallization point, said melting point of said liquid crystalline polymer is about 150°C or higher;

(c) 0.0 to about 60 weight percent of a solid particulate material; and

(d) about 0.2 to about 15 weight percent of a plasticizer for said isotropic polyester;

wherein the weight percentages of (a) and (c) are based on the weight of total composition, and the weight percentages of (b) and (d) are based on the weight of (a) in said composition.

Preferred composition for this process are also preferred for the composition (itself) described above.

DETAILS OF THE INVENTION

Herein certain terms are used, and some of them are defined below.

By a "liquid crystalline polymer" is meant a polymer that is anisotropic when tested using the TOT test or any reasonable variation thereof, as described in U.S. Patent 4,118,372, which is hereby included by reference. Useful LCPs include polyesters, poly(ester-amides), and poly(ester-imides). One preferred form of LCP is "all aromatic", that is all of the groups in the polymer main chain are aromatic (except for the linking groups such as ester groups), but side groups which are not aromatic may be present.

By "isotropic" herein is meant a polymer which is isotropic when tested by the TOT test, described above.

LCPs and isotropic polymers are mutually exclusive species. Preferably the IPE is a continuous phase in the composition. This can be determined by an appropriate form of microscopy.

5 By an "IPE" is meant a condensation polymer which is isotropic and in which more than 50 percent of the groups connecting repeat units are ester groups. Thus IPEs may include polyesters, poly(ester-amides) and poly(ester-imides), so long as more than half of the connecting
10 groups are ester groups. Preferably at least 70% of the connecting groups are esters, more preferably at least 90% of the connecting groups are ester, and especially preferably essentially all of the connecting groups are esters. The proportion of ester connecting groups can be
15 estimated to a first approximation by the molar ratios of monomers used to make the IPE.

Unless otherwise noted, melting points are measured by ASTM Method D3418, using a heating rate of 10 °C/min. Melting points are taken as the maximum of the melting
20 endotherm, and are measured on the first heat. If more than one melting point is present the melting point of the polymer is taken as the highest of the melting points. Except for LCPs, a melting point preferably has a heat of fusion of at least 3 J/g associated with that
25 melting point. Melting points of LCPs are taken on the second heat.

Herein for the ingredients in the composition, including (a), b), (c) and (d) the use of the singular such as "an IPE" or "a particulate solid" also means the
30 plural, that more than one of each these things which meets the limitations set forth herein may be present.

By a "particulate solid" is meant any solid (infusible at temperatures to which the composition is normally exposed) which is finely divided enough to be

dispersed under melt mixing conditions (see below) into the composition. Typically the particulate solid will be a material which may already be used in thermoplastic compositions, such as pigments, reinforcing agents, and fillers. The particulate solid may or may not have a coating on it, for example a sizing and/or to improve adhesion of the particulate solid to the polymers of the composition. The particulate solid may be organic or inorganic. Useful particulate solids include minerals such as clay, talc, wollastonite, mica, and calcium carbonate; glass in various forms such as fibers, milled glass, solid or hollow spheres; carbon as black or fiber; titanium dioxide; aramid in the form of short fibers, fibrils or fibrids; and flame retardants such as antimony oxide, sodium antimonate, and appropriate infusible organic compounds. Preferred particulate solids are wollastonite, mica, talc, glass especially glass fiber, and calcium carbonate.

By a "CCP" is meant a value determined as follows. The "pure" (no other ingredients in the composition except small amounts of materials such as an antioxidant which may be needed to stabilize the IPE in the injection molding process) IPE or a composition containing the IPE is injection molded into a 1.59 mm (1/16") thick plaque using a mold whose temperature is 50°C. An appropriate sized sample (for the instrument) from the plaque is placed in a Differential Scanning Calorimeter (DSC) and heated from ambient temperature (approximately 20-35°C) at a rate of 10°C/min. The peak of the exotherm from crystallization of the IPE while it is being heated is taken as the CCP. The IPE has no CCP if there is no crystallization exotherm below the melting point of the IPE.

The "CCP" can also be determined by the "Quick Quench Method". In this method, the pure IPE or a composition containing the IPE is molded into a specimen bar. A sample from the specimen bar is placed in a DSC pan and heated quickly to above the melt point of the material (usually about 270°C for PET) then quickly quenched in a dry ice/acetone mixture or liquid nitrogen. The material is then placed in a DSC and equilibrated to 0°C. Then the temperature is increased at 10.0°C/min to 290.0°C. The peak of the exotherm from crystallization of the IPE while it is being heated is taken as the CCP. The IPE has no CCP if there is no crystallization exotherm below the melting point of the IPE.

It is generally believed by those skilled in the art that, not only for a polyester which is difficult to crystallize, but for all semicrystalline polyesters, a lowering of the CCP from the CCP of the pure polymer indicates that a crystallization initiator system is present. For a given amount of crystallization initiator system, the more the CCP is lowered, the more efficient is that crystallization initiator system. Responses to the amount of crystallization initiator system are generally limited, with higher and higher amounts giving lesser or no advantage (little or no effect on lowering CCP).

By a "plasticizer" is typically meant a compound or mixture of compounds with a melting point of about 50°C or less with a(n) (average) molecular weight of 2000 or less. The plasticizer may be oligomeric, in which case its number average molecular weight (measured by Size Exclusion Chromatography using appropriate standards) is 2000 or less. These are typical properties of a plasticizer. For a further description of plasticizers see C. E. Carraher, Jr., Seymour/Carraher's Polymer

Chemistry, 5th Ed., Marcel Dekker Inc., New York, 2000, p. 60 and p. 463-465, which is hereby included by reference.

By "all percents by weight are based on the total of all ingredients in the composition" is meant that these
5 percents are based on the total amount of (a), (b), (c) and (d) present plus any other ingredients present in the composition.

The IPE used may be any IPE with the requisite melting point. Preferably the melting point of the IPE
10 is about 150°C or higher, and more preferably about 200°C or higher. Polyesters (which have mostly or all ester linking groups) are normally derived from one or more dicarboxylic acids and one or more diols. In one preferred type of IPE the dicarboxylic acids comprise one
15 or more of terephthalic acid, isophthalic acid and 2,6-naphthalene dicarboxylic acid, and the diol component comprises one or more of HO(CH₂)_nOH (I), 1,4-cyclohexanedimethanol, HO(CH₂CH₂O)_mCH₂CH₂OH (II), and HO(CH₂CH₂CH₂CH₂O)_zCH₂CH₂CH₂CH₂OH (III), wherein n is an
20 integer of 2 to 10, m on average is 1 to 4, and is z an average of about 7 to about 40. Note that (II) and (III) may be a mixture of compounds in which m and z, respectively, may vary and hence since m and z are averages, they do not have to be integers. In preferred
25 polyesters, n is 2, 3 or 4, and/or m is 1.

Specific preferred IPEs include poly(ethylene terephthalate) (PET), poly(1,3-propylene terephthalate) (PPT), poly(1,4-butylene terephthalate) (PBT), a thermoplastic elastomeric polyester having poly(1,4-
30 butylene terephthalate) and poly(tetramethyleneether)glycol blocks (available as Hytrel® from E. I. DuPont de Nemours & Co., Inc., Wilmington, DE 19898 USA), and poly(1,4-cyclohexyldimethylene terephthalate) (PCT), and PET, is

especially preferred. By "PET" herein is meant a polyester in which at least 80, more preferably at least 90, mole percent of the diol repeat units are from ethylene glycol and at least 80, more preferably at least 90, mole percent of the dicarboxylic acid repeat units are from terephthalic acid. If more than one IPE (with the proper melting points) is present, the total of such polymers in the composition is taken as component (a).

Preferably the solid particulate material is 0.2 to 60 weight percent of the total composition, more preferably about 5 to about 50 weight percent of the total composition.

Preferably the IPE is at least about 40 weight percent of the total composition, more preferably at least about 50 weight percent of the total composition.

Preferably the LCP is about 0.5 to about 20, more preferably about 1.0 to about 10, percent by weight of (a). Also preferably the LCP is in a discontinuous phase (as measured by an appropriate form of microscopy - if the particle size of the LCP is so small it can't be found by electron microscopy, it is assumed to be in a dispersed phase).

Preferably the plasticizer is about 0.5 to about 12 weight percent of the IPE [(a)], more preferably about 3.0 to about 10 percent of the IPE. One preferred type of plasticizer is a diester of a diol of the formula $R^1CO_2R^2O_2CR^1$ wherein each R^1 is independently hydrocarbyl containing 1 to 20 carbon atoms, more preferably alkyl, and each R^2 (by this is meant R^2 in each molecule may vary somewhat) is alkylene optionally substituted with ether groups, containing 2 to 30 carbon atoms. By alkylene is meant is a divalent hydrocarbyl radical (containing on carbon and hydrogen) in which the free valencies are to two different alkyl (saturated) carbon atoms. Specific

useful plasticizers include poly(ethylene glycol 400) di-
2-ethylhexanoate and poly(ethylene glycol) dilaurate with
a number average molecular weight of approximately 946.
Other useful plasticizers will be found in U.S. Patents
5 Re32,334 and 4,548,978, which are hereby included by
reference. Not all plasticizers useful for one
particular IPE will necessarily be useful for another
IPE, but often this will be the case.

Other ingredients, particularly those commonly used
10 in thermoplastics, may also be added to the present
composition in amounts commonly used in thermoplastics.
Such materials include antioxidants, lubricant, mold
release, flame retardants, (paint) adhesion promoters,
other types of polymers (to form polymer blends), etc.
15 Preferably the total of all these ingredients is less
than about 60 weight percent, more preferably less than
about 40, and especially preferably less than about 25
weight percent of the composition.

A preferred optional ingredient is a polymeric
20 toughening agent. This is a polymer, typically which is
an elastomer or has a relatively low melting point,
generally $<200^{\circ}\text{C}$, preferably $<150^{\circ}\text{C}$, which has attached to
it functional groups which can react with the IPE (and
optionally other polymers present). Since IPEs usually
25 have carboxyl and hydroxyl groups present, these
functional groups usually can react with carboxyl and/or
hydroxyl groups. Examples of such functional groups
include epoxy, carboxylic anhydride, hydroxyl (alcohol),
carboxyl, and isocyanato. Preferred functional groups
30 are epoxy, and carboxylic anhydride, and epoxy is
especially preferred. Such functional groups are usually
"attached" to the polymeric toughening agent by grafting
small molecules onto an already existing polymer or by
copolymerizing a monomer containing the desired

functional group when the polymeric toughener molecules are made by copolymerization. As an example of grafting, maleic anhydride may be grafted onto a hydrocarbon rubber using free radical grafting techniques. The resulting
5 grafted polymer has carboxylic anhydride and/or carboxyl groups attached to it. An example of a polymeric toughening agent wherein the functional groups are copolymerized into the polymer is a copolymer of ethylene and a (meth)acrylate monomer containing the appropriate
10 functional group. By (meth)acrylate herein is meant the compound may be either an acrylate, a methacrylate, or a mixture of the two. Useful (meth)acrylate functional compounds include (meth)acrylic acid, 2-hydroxyethyl(meth)acrylate, glycidyl(meth)acrylate, and
15 2-isocyanatoethyl (meth)acrylate. In addition to ethylene and a functional (meth)acrylate monomer, other monomers may be copolymerized into such a polymer, such as vinyl acetate, unfunctionalized (meth)acrylate esters such as ethyl (meth)acrylate, n-butyl (meth)acrylate, and
20 cyclohexyl (meth)acrylate. Preferably the amount of polymeric toughening agent containing functional groups present is about 2 to about 40 percent by weight of (a), the IPE. Preferred tougheners include those listed in U.S. Patent 4,753,980, which is hereby included by
25 reference. Especially preferred tougheners are copolymers of ethylene, ethyl acrylate or n-butyl acrylate, and glycidyl methacrylate.

It is preferred that the polymeric toughener contain about 0.5 to about 20 weight percent of monomers
30 containing functional groups, preferably about 1.0 to about 15 weight percent, more preferably about 7 to about 13 weight percent of monomers containing functional groups. There may be more than one type of functional monomer present in the polymeric toughener. It has been

found that toughness of the composition is increased by increasing the amount of polymeric toughener and/or the amount of functional groups. However, these amounts should preferably not be increased to the point that the composition may crosslink, especially before the final part shape is attained. Preferably there is about 2 to about 30 weight percent of the polymeric toughener in the composition, more preferably 5 to about 25 weight percent, and especially preferably about 10 to about 20 weight percent, of the total composition.

When a polymeric toughener, such as those described above, is added, it has been found that in many instances the particle size of the LCP in the composition is much reduced. For instance, in one composition the particle size of the LCP was about 2-5 μm , while in the same composition but containing a polymeric toughener the LCP particle size was about 0.2-0.5 μm .

Another preferred type of other ingredient is an epoxy compounds or resin. Preferably such a compound or resin has an average molecular weight of less than about 1000 (the polymeric toughening agent as described above, even if it does contain epoxy groups, is not considered herein part of this epoxy compound or resin). This epoxy material is preferably present at a level of 0.1 to about 1.0 weight percent of the entire composition. Useful epoxy compounds or resins include Epon® 1002F, 1009F or 1031, or Araldite® GT7099 or GT6099. It is believed that in some instance the epoxy compound or resin stabilizes melt viscosity and/or improves color stability of the composition. The latter is particularly important when an appearance part is not coated a paint or other coating.

It is to be understood that any preferred ingredient an/or ingredient amount may be combined with any other preferred ingredient and/or ingredient amount herein.

In one preferred type of composition less than 25 ppm, preferably less than 10 ppm of "free" metal cations such as alkali metal or alkaline earth metal cations are added to the composition. By "free" metal cations are meant cations which may readily react with functional groups which are present in the composition, such as carboxyl groups to form carboxylate salts. Free metal cations may be added as carboxylate salts such as acetates of 4-hydroxybenzoates, as other metal salts such as metal halides, and as metal salts of polymeric carboxylates. Not included in added free metal cations are normal impurities in the other ingredients or metal cations which are part of minerals or other compound, wherein the metal cations are tightly bound to that ingredient or mineral. As mentioned above some of the crystallization initiation systems for polyesters contain alkali or other metal cations. These are sometimes deleterious to the use of these compositions for electrical or electronic uses, where the metal ions can change the electrical properties of the composition. Similarly the presence of metal cations may lead to poorer hydrolysis or other chemical resistance problems. Such disadvantages are not evident in the present compositions. Also, it is believed that at least some polymeric tougheners are more effective or effective at lower amounts when metal cations are not present or present in only low amounts, especially when the counterion to the metal cation may be able to react with a functional group which is part of the polymeric toughener. Therefore the combination of low metal ion

content and the presence of polymeric tougheners is preferred.

The compositions described herein can be made by typical melt mixing techniques. For instance the ingredients may be added to a single or twin screw extruder or a kneader and mixed in the normal manner, Preferably the temperature of the ingredients in at least part of the mixing apparatus is at or above the melting point of the LCP present (the measured or set temperature in any zone of the mixing apparatus may be below the actual material temperature because of mechanical heating). After the materials are mixed they may be formed (cut) into pellets or other particles suitable for feeding to a melt forming machine. Melt forming can be carried out by the usual methods for thermoplastics, such as injection molding, thermoforming, or extrusion, or any combination of these methods. Some of the ingredients such as fillers, plasticizers, and lubricants (mold release) may be added at one or more downstream points in the extruder, so as to decrease attrition of solids such as fillers, and/or improve dispersion, and/or decrease the thermal history of relatively thermally unstable ingredients, and/or decrease losses by evaporation of volatile ingredients.

As mentioned above parts of the present composition may be made by heating the composition above the melting point of the IPE (and hence melting the IPE), and then cooling them below the melting point to solidify the composition and formed a shaped part. Preferably the part is cooled at least 50°C below the melting point, more preferably at least 100°C below the melting point, or preferably below the CCP. Most commonly ultimately the composition will be cooled to ambient temperature, most typically 15-45°C.

The compositions described herein (often when having additional optional ingredients present) are particularly useful as "appearance parts", that is parts in which the surface appearance is important. This is applicable
5 whether the composition's surface is viewed directly, or whether it is coated with paint or another material such as a metal. Such parts include automotive body panels such as fenders, fascia, hoods, tank flaps and other exterior parts; interior automotive panels; appliance
10 parts such as handles, control panels, chassises (cases), washing machine tubs and exterior parts, interior or exterior refrigerator panels, and dishwasher front or interior panels; power tool housings such as drills and saws; electronic cabinets and housings such as personal
15 computer housings, printer housings, peripheral housings, server housings; exterior and interior panels for vehicles such as trains, tractors, lawn mower decks, trucks, snowmobiles, aircraft, and ships; decorative interior panels for buildings; furniture such as office
20 and/or home chairs and tables; and telephones and other telephone equipment. As mentioned above these parts may be painted or they may be left unpainted in the color of the composition.

The composition may be colored with pigments and/or
25 dyes, so many color variations are possible. This type of coloration of parts made from the composition is particularly attractive economically, since such parts need not be subsequently coated (painted) in one or more additional steps. If extremely high gloss and/or
30 distinctness of image are not needed, this is often a better overall alternative to coating. Alternatively of course parts made from this composition may also be coated (painted).

Another method of coloring the surface of parts made from these compositions (or variation thereof) is a dye sublimation (printing) process.

As mentioned above the present compositions or variations thereof may be used for automobile parts, especially automobile (car) bodies. Currently, there are three different approaches to the production of coated car bodies assembled from metal and plastic parts in a mixed construction:

10 1. The method known as the off-line process, in which the metal car body and the plastic parts are coated separately and then assembled.

The drawback of the off-line process is its susceptibility to lack of visual harmonization of the coated metal and plastic surfaces, at least in cases where coated plastic parts and coated metal parts are subjected to direct visual comparison for reasons of construction, for example, owing to the virtually seamless proximity of the coated parts and/or arrangement of the coated parts in one plane.

A further drawback is the necessity of operating two coating lines.

25 2. The method known as the in-line process in which the metal body already provided with an electrodeposition coating as a primer and the uncoated plastic parts or the plastic parts optionally only provided with a plastic primer are assembled and provided with one or more further coating layers in a subsequent common coating process.

30 The drawback of the in-line process is the assembly step inserted into the coating process as an interruptive intermediate step which also involves the risk of introducing dirt into the further coating process.

3. The method known as the on-line process, in which the uncoated body parts made of metal and the uncoated plastic parts or the plastic parts optionally only provided with a plastic primer are assembled into a body
5 constructed in a mixed construction and then passed through a common coating process including electrodeposition coating, wherein naturally only the electrically conductive metal parts are provided with an electrodeposition coating, while all the coating layers
10 to be applied subsequently are applied both to the electrodeposition coated metal parts and to the plastic parts.

The on-line process is particularly preferred as it clearly separates the body base shell construction and
15 the coating process and allows an undisturbed coating sequence.

Basically only adequately heat-resistant and simultaneously heat deformation-resistant plastics materials are suitable for the particularly preferred on-
20 line process, since high temperatures are used in drying the electrodeposition coating.

Coating substrates car bodies assembled from metal parts and at least one plastic part (the composition described herein), with visible metal and plastic
25 surfaces, comprising the successive steps:

(1) electrodeposition coating the substrates, removing non-deposited electrodeposition coating agent from the substrate and thermally cross-linking the deposited electrodeposition coating and thereby forming
30 an electrodeposition coating primer on the metal surfaces,

(2) application and curing of at least one additional coating at least on all the visible metal and plastic surfaces, at least one of the plastic parts

making up the visible plastic surfaces of the substrate having the composition described herein.

When they will be coated the plastic parts (of the composition described herein) may be pretreated in a conventional manner, for example, by UV irradiation, flame treatment or plasma treatment or be coated with a conventional plastic primer known to the person skilled in the art, in particular a conductive primer providing the plastic part with adequate electrical conductivity for electrostatically-assisted coatability, before they are assembled with the metal parts.

The metal parts and the at least one plastic part optionally provided with a plastic primer are assembled in the conventional manner known to the person skilled in the art, for example by screwing, clipping and/or adhesion, to form the substrate to be coated by the process according to the invention.

At least that (those) plastic part(s) of a substrate with the smallest possible joint width and in particular also in the same plane as the adjacent metal parts is (are) assembled with the metal parts.

Optionally, further plastic parts that are still missing from the body, if any, which in general will differ in composition from the at least one plastic part and which in general are less resistant to heat deformation can be fitted on after completion of step (1) of the process according to the invention and can also be subjected to the further coating process of step (2) (compare the in-line process described above) and/or be fitted on after completion of the process according to the invention in finished coated form (compare the off-line process described above).

In view of the application of at least one further coating layer, taking place in step (2) of the process

according to the invention, preferably by electrostatically-assisted spray coating, it is expedient if the metal and plastic part(s) are assembled such that that they are not electrically insulated from one another; for example, a direct electric contact between the conductive primer and metal can be ensured by direct contact or via electrically conductive connecting elements, for example, metal screws.

To produce an anti-corrosive primer layer on the metal parts, the substrates assembled from metal parts and at least one plastic part in step (1) of the process according to the invention are coated in an electrodeposition coating bath in the conventional manner known to the person skilled in the art.

Suitable electrodeposition coating agents include conventional waterborne coating compositions with a solids content from, for example, 10 to 30 wt. percent.

The electrodeposition coating compositions may be conventional anodic electrodeposition coating agents known to the skilled person. The binder basis of the anodic electrodeposition coating compositions may be chosen at will. Examples of anodic electrodeposition binders are polyesters, epoxy resin esters, (meth)acrylic copolymer resins, Melanite oils or polybutadiene oils with a weight average molecular mass (Mw) of, for example, 300-10,000 and a carboxyl group content, for example, corresponding to an acid value of 35 to 300 mg OH/g. At least a part of the carboxyl groups is converted to carboxylate groups by neutralization with bases. These binders may be self cross-linking or cross-linked with separate cross-linking agents.

Preferably conventional cathodic electrodeposition coating agents known to the skilled person are used in the process according to the invention for the

application of the electrodeposition coating layer. Cathodic electrodeposition coating compositions contain binders with cationic groups or groups which can be converted to cationic groups, for example, basic groups. Examples include amino, ammonium, e.g., quaternary ammonium, phosphonium and/or sulfonium groups. Nitrogen-containing basic groups are preferred; said groups may be present in the quaternized form or they are converted to cationic groups with a conventional neutralizing agent, e.g., an organic monocarboxylic acid such as, e.g., formic acid, lactic acid, methane sulfonic acid or acetic acid. Examples of basic resins are those with primary, secondary and/or tertiary amino groups corresponding to an amine value from, for example, 20 to 200 mg KOH/g. The weight average molecular mass (Mw) of the binders is preferably 300 to 10,000. Examples of such binders are amino(meth)acrylic resins, aminoepoxy resins, aminoepoxy resins with terminal double bonds, aminoepoxy resins with primary OH groups, aminopolyurethane resins, amino group-containing polybutadiene resins or modified epoxy resin-carbon dioxide-amine reaction products. These binders may be self-cross-linking or they may be used with known cross-linking agents in the mixture. Examples of such cross-linking agents include aminoplastic resins, blocked polyisocyanates, cross-linking agents with terminal double bonds, polyepoxy compounds or cross-linking agents containing groups capable of transesterification.

Apart from binders and any separate cross-linking agents, the electrodeposition coating compositions may contain pigments, fillers and/or conventional coating additives. Examples of suitable pigments include conventional inorganic and/or organic colored pigments and/or fillers, such as carbon black, titanium dioxide, iron oxide pigments, phthalocyanine pigments,

quinacridone pigments, kaolin, talc or silicon dioxide. Examples of additives include, in particular, wetting agents, neutralizing agents, leveling agents, catalysts, corrosion inhibitors, anti-cratering agents, anti-foaming agents, solvents.

Electrodeposition coating takes place in a conventional manner known to the skilled person, for example, at deposition voltages from 200 to 500 V. After deposition of the electrodeposition coating, the substrate is cleaned from excess and adhering but non-deposited electrodeposition coating in a conventional manner known to the skilled person, for example, by rinsing with water. Thereafter the substrate is baked at oven temperatures of, for example, up to 220°C according to object temperatures of, for example, up to 200°C in order to crosslink the electrodeposition coating.

In the subsequent step (2) of the process according to the invention, at least one further coating layer is applied, preferably by spray application, in particular, electrostatically-assisted spray application, at least to all the visible metal and plastic surfaces on the substrates thus obtained and only provided with a baked electrodeposition coating layer on the metal surfaces.

If only one further coating layer is applied, this is generally a pigmented top coat. However, it is preferred to apply more than one further coating layer. Examples of conventional multicoat constructions formed from a plurality of coating layers are:

- primer surfacer/top coat.
- primer surfacer/base coat/clear coat,
- base coat/clear coat,
- primer surfacer substitute layer/base coat/clear coat.

Primer surfacers or primer surfacer substitute coatings are mainly used for stone-chip protection and surface leveling and prepare the surface for the subsequent decorative top coat which provides protection
5 against environmental influences and is made of pigmented top coat or of color- and/or effect-producing base coat and protective clear coat.

The multicoat constructions mentioned by way of example may also be provided over the entire surface or
10 part of the surface with a transparent sealing coat, in particular, providing high scratch-resistance.

All these coating layers following the electrodeposition coating layer may be applied from conventional coating agents well known to the person
15 skilled in the art for applying the relevant coating layer. This can be a respective liquid coating agent containing, for example, water and/or organic solvents as diluents or a powder coating agent. The coating agents may be a single-component or multi-component coating
20 agent; they may be physically drying or by oxidation or be chemically crosslinkable. In particular, primer surfacers, top coats, clear coats and sealing coats these are generally chemically cross-linking systems which can be cured thermally (by convection and/or by infrared
25 irradiation) and/or by the action of energy-rich radiation, in particular ultraviolet radiation.

If more than one coating layer is applied in step (2) of the process according to the invention, the coating layers do not basically have to be cured
30 separately prior to application of the respective subsequent coating layer. Rather, the coating layer can be applied according to the wet-on-wet principle known to the person skilled in the art, wherein at least two coating layers are cured together. In particular, for

example, in the case of base coat and clear coat, following the application of the base coat, optionally followed by a short flash-off phase, the clear coat is applied and cured together with the base coat.

5 The on-line process according to the invention allows substrates assembled in a mixed construction from metal parts and plastic parts which are based on thermoplastics and are adequately resistant to heat deformation to be coated with excellent harmonization of
10 the visual impression of the coated plastic and metal surfaces.

Nonappearance parts may also be made with these compositions. These are parts whose surface appearance is not critical. Such parts include those now made with
15 so-called engineering thermoplastics, especially those which are filled with materials which are designed to enhance the composition's physical properties, such as stiffness, toughness and tensile strength.

CCP Done by one of two methods, Method A, injection
20 molding into a 50°C mold as described above, or Method B, the Quick Quench method, also described above.

Melting point Determined by ASTM D3418-82, at a heating rate of 10°C/min. The peak of the melting endotherm is taken as the melting point.

25 Freeze Time Freeze time (sometimes called crystallization time) is defined as the inflection point in cavity pressure curve. A transducer placed behind an ejector pin located near the gate of the part is used to measure cavity pressure over time during the molding
30 cycle. A time of zero seconds occurs when the screw begins to move forward at the start of injection cycle. A peak pressure occurs when the part been completely filled and the pressure remains essentially constant for the initial portion of the packing phase of the molding

cycle. As the resin begins to crystallize, shrinkage occurs. Once the resin at the gate is fully crystallized, crystallization of resin in the cavity causes enough shrinkage that a reduction in the cavity pressure is seen. The cavity pressure continues to drop over time. The point at which the curve transitions from a concave to a convex shape is the inflection point and is defined as the freeze point.

Crystallization half life (CHL). This was done by a differential scanning calorimetry (DSC) method. In one sample preparation method the sample was simply used as was. In another method the sample was heated to 290°C, quenched and quenched in liquid nitrogen. With either preparation method the sample was then heated at a rate of 200°C/min to the desired temperature and the crystallization exotherm followed at that temperature in the DSC. From the exotherm curve generated with time, the crystallization half life at that temperature was then calculated.

20 Compounding and Molding Method

All polymeric compositions were prepared by compounding in 30 mm Werner and Pfleiderer twin screw extruder. All ingredients were blended together and added to the rear (barrel 1) of the extruder except that Nyglos and other minerals were side-fed into barrel 5 (of 10 barrels) and the plasticizer was added using a liquid injection pump. Any exceptions to this method are noted in the examples. Barrel temperatures were set at 280-310°C resulting in melt temperatures 290-350°C depending on the composition and extruder rate and rpm of the screw.

Resins were molded into ASTM test specimens on a 3 or 6 oz injection molding machine. Melt temperature were 280-300°C, mold temperatures were 110-130°C.

In the Examples certain ingredients are used, and they are defined below:

CaCO₃ - particulate calcium carbonate, Super-Pflex® 200, available from Mineral Technologies, Inc.,
5 New York, NY 10174 USA).

Crystar® 3934 - PET homopolymer, IV = 0.67, available from E. I. DuPont de Nemours & Co., Inc.,
Wilmington, DE 19898 USA

glass fiber - PPG 3563 available from PPG
10 Industries, Pittsburgh, PA 15272 USA.

Irganox® 1010 - antioxidant available from Ciba Specialty Chemicals, Tarrytown, NY 10591, USA.

LCP1 - 50/50/70/30/320 (molar parts)
hydroquinone/4,4'-biphenol/terephthalic acid/2,6-
15 naphthalene dicarboxylic acid/4-hydroxybenzoic acid
copolymer, melting point 334°C.

Licowax® PED521 - an oxidized polyethylene wax used as a mold lubricant available from Clariant Corp. D-65840 Sulzbach am Taunns, Germany.

20 Nyad® 1250 - wollastonite fibers with no sizing available from Nyco Minerals, Calgary, AB, Canada.

Nyglos® 4 - average approximately 9 µm length wollastonite fibers with no sizing available from Nyco Minerals, Calgary, AB, Canada.

25 Nyglos® 4W 20544 - average approximately 10 µm length sized wollastonite fibers, available from Nyco Minerals, Calgary, AB, Canada.

Plasthall® 809 - polyethylene glycol 400 di-2-ethylhexanoate.

30 Polymer A - ethylene/n-butyl acrylate/glycidyl methacrylate (66.75/28/5.25 wt. %) copolymer, melt index 12 g/10 min.

Polymer B - ethylene/n-butyl acrylate/glycidyl methacrylate (66/22/12 wt. %) copolymer, melt index 8 g/10 min.

RCL4 - Tiona® RCL4 titanium dioxide, a chloride process rutile-type TiO₂ surface treated with alumina and an organic substance, available from SMC Corp. of Baltimore, MD, U.S.A.

talc - Jetfil® 575C available from Luzenac America, Englewood, CO 80112 USA.

10 In the Examples, all compositional amounts shown are parts by weight. All compositions containing PET also contain 0.3 wt. % Irganox® 1010, and 0.5 wt. % PED521.

Example 1

Compositions were made using the standard method.
15 The CCP was determined using Method A. Compositions and CCPs are given in Table 1.

Table 1

State	Crystar® 3934	LCP1	Nyglos® 4W	Plasthall® 809	CCP, °C
A	100.0				127.9
B	97.0			3.0	119.5
C	92.0	5.0		3.0	114.4
D	95.0	5.0			122.2
E	82.0		15.0	3.0	121.3
F	80.0	5.0	15.0		122.8

Example 2

20 Compositions were made using the standard method. The CCP was determined using Method A. Compositions and CCPs are given in Table 2.

Table 2

State	Crystar® 3934	LCP1	Nyglos® 4W	Plasthall® 809	CCP, °C
A	87.0	0.0	10.0	3.0	117.3
B	87.0	1.0	9.0	3.0	115.5
C	87.0	3.0	7.0	3.0	112.9
D	87.0	7.0	3.0	3.0	109.9
E	87.0	9.0	1.0	3.0	111.4
F	87.0	10.0	0.0	3.0	110.1

Example 3

Compositions were made using the standard method. Each fillers was present in the amount of 15 parts by weight. The CCP was determined using Method A, except for states C and D which used Method B. Compositions and CCPs are given in Table 3.

Table 3

State	Crystar® 3934	LCP1	Filler	Plasthall® 809	CCP, °C
A	77.0	5.0	glass fiber	3.0	109.3
B	77.0	5.0	Nyad® 1250	3.0	112.0
C	77.0	5.0	CaCO ₃	3.0	105.7
D	77.0	5.0	RCL4	3.0	118.1
E	77.0	5.0	talc	3.0	116.3
F	77.0	5.0	Nylgos® 4	3.0	110.8

10

Example 4

Compositions were made using the standard method. The polymer compositions were molded with a melt temperature of 284-286°C, a mold temperature of 109-100°C, a cycle time of 39-40 sec, a hold/pack pressure of 80 MPa, and a fill speed of 19.1 mm/sec. Physical property testing was done according to standard ISO methods. The freeze times shown are comparative times with a commercial PET injection molding resin, Rynite® 530 BK503 (available from E. I. DuPont de Nemours & Co., Inc., Wilmington, DE 19898 USA), which contains 30 weight percent glass fibers and a crystallization package which includes a sodium source and Plasthall® 809, but no

20

polymers similar to Polymers A and B. A positive number indicates that the freezing time was longer than Rynite® 530, while a negative number indicates the freezing time was shorter than Rynite® 530. Compositions and results are shown in Table 4.

Table 4

State	A	B	C	D	E	F	G
Crystar® 3934	81.2	61.2	71.2	71.2	75.2	65.2	56.2
LCP1		5	5	5	1	1	10
Polymer B		15		5	5	15	15
Polymer A			5				
Irganox® 1010	0.3	0.3	0.3	0.3	0.3	0.3	0.3
PED521	0.5	0.5	0.5	0.5	0.5	0.5	0.5
Nyglos® 4W 20544	15	15	15	15	15	15	15
Plasthall® 809	3	3	3	3	3	3	3
Tensile Strength, MPa	72.2	39.4	51.1	53.2	55.2	39.0	39.0
Tensile Elongation, %	2.9	27	7	10	12	35	25
Tensile Modulus, GPa	5.8	3.65	4.62	4.52	4.67	3.44	3.39
Flexural Strength, MPa	130	76.6	102	103	106	76.6	73.7
Flexural Modulus, GPa	5.64	3.80	4.82	4.75	4.84	3.72	3.65
Approx. Freeze Time, sec	2	-3	0	-0.5	0	-1.5	-3.5

Example 5

Compositions containing Crystar® 3934, Plasthall® 809 and LCP1 were made by melt mixing using a twin screw extruder, and these compositions ("States") together with their constituents are shown in Table 5. The CCP and CHL (at 110°C) of these states were measured, and the results are also shown in Table 5. These show that a combination of an LCP and a plasticizer is very effective in nucleating and accelerating the crystallization of the Crystar® 3934.

Table 5

State	Crystar® 3934	LCP1	Plasthall® 809	CCP, °C	CHL, min
A	100.0			131.5°	4.87min
B	99.0	1.0		124.5°	3.28min
C	97.0	3.0		124.1°	2.98min
D	95.0	5.0		124.5°	2.28min
E	99.0		1.0	128.8°	5.08min
F	97.0		3.0	122.0°	1.68min
G	95.0		5.0	117.9°	0.98min
H	98.0	1.0	1.0	123.2°	2.48min
I	96.0	3.0	1.0	121.3°	1.77min
J	94.0	5.0	1.0	119.8°	1.62min
K	96.0	1.0	3.0	114.9°	1.22min
L	94.0	3.0	3.0	114.8°	0.88min
M	92.0	5.0	3.0	113.6°	0.75min
N	94.0	1.0	5.0	110.1°	0.67min
O	92.0	3.0	5.0	109.0°	0.55min
P	90.0	5.0	5.0	108.1°	0.40min

Example 6

Production of a steel/plastics substrate: A 13 cm x 13 cm plastics panel made from the composition of State B of Example 4 was stuck using double-sided adhesive tape onto a 30 cm x 60 cm panel of bodywork steel in such a manner that two common edges were formed. Before being adhered, the plastics panel was provided with a
 5
 10
 15
 20
 25
 30
 35
 40
 45
 50
 55
 60
 65
 70
 75
 80
 85
 90
 95
 100
 105
 110
 115
 120
 125
 130
 135
 140
 145
 150
 155
 160
 165
 170
 175
 180
 185
 190
 195
 200
 205
 210
 215
 220
 225
 230
 235
 240
 245
 250
 255
 260
 265
 270
 275
 280
 285
 290
 295
 300
 305
 310
 315
 320
 325
 330
 335
 340
 345
 350
 355
 360
 365
 370
 375
 380
 385
 390
 395
 400
 405
 410
 415
 420
 425
 430
 435
 440
 445
 450
 455
 460
 465
 470
 475
 480
 485
 490
 495
 500
 505
 510
 515
 520
 525
 530
 535
 540
 545
 550
 555
 560
 565
 570
 575
 580
 585
 590
 595
 600
 605
 610
 615
 620
 625
 630
 635
 640
 645
 650
 655
 660
 665
 670
 675
 680
 685
 690
 695
 700
 705
 710
 715
 720
 725
 730
 735
 740
 745
 750
 755
 760
 765
 770
 775
 780
 785
 790
 795
 800
 805
 810
 815
 820
 825
 830
 835
 840
 845
 850
 855
 860
 865
 870
 875
 880
 885
 890
 895
 900
 905
 910
 915
 920
 925
 930
 935
 940
 945
 950
 955
 960
 965
 970
 975
 980
 985
 990
 995

Preparation of a cathodic electrodeposition coating bath: A cathodic electrodeposition coating bath with a solids content of 18 wt. percent was prepared by mixing 4356 g of an aqueous cathodic electrodeposition binder dispersion (Herberts AQUA EC 2000, R 39660 from DuPont Performance Coatings GmbH & Co. KG, Wuppertal) with 1408 g of a cathodic electrodeposition pigment paste (Herberts AQUA EC 2000, R 39661 from DuPont Performance Coatings GmbH & Co. KG, Wuppertal) and dilution with 5236 g of deionized water.

Production of the multilayer coating: The steel/plastics substrate was coated to a dry film thickness of 20 μm in the cathodic electrodeposition (CED) coating bath according to Example (coating conditions: two minutes at 30°C with a deposition voltage of 320 V; baking conditions: 20 minutes at 175°C object temperature). The steel/plastics substrate provided in this manner with a CED coating layer only on the metal surface was then coated to a dry film thickness of 35 μm with a white aqueous filler (Herberts Aqua-Fill R 63520 from DuPont Performance Coatings GmbH & Co. KG, Wuppertal) and, after 10 min flashing off at 80°C, was baked for 25 min at 160°C (object temperature). The steel/plastics substrate now coated over its entire surface with the white aqueous filler layer was then coated to a dry film thickness of 12 μm with a black metallic water-borne base coat (Herberts Aqua-Base R 65949 from DuPont Performance Coatings GmbH & Co. KG, Wuppertal) and, after 10 min flashing off at 80°C, was coated to a dry film thickness of 35 μm with a two-component polyurethane clear coat (2K-Clear R 40491 from DuPont Performance Coatings GmbH & Co. KG, Wuppertal) and, after 5 min flashing off at 23°C, was baked for 20 min at 135°C (object temperature). All the spray coatings were applied in each case with the steel/plastics substrate in a vertical position. All flashing-off, drying and baking operations were performed in the horizontal position.

Evaluation simply with the naked eye revealed virtually no visible differences in appearance (gloss, roughness) between the coated plastics and steel surfaces. Using a BYK Wavescan instrument [for the optical surface characterization of painted surfaces the "Wave Scan" (Byk-Gardner GmbH, D-82538 Geretsried, Germany) can

be used. The Wave Scan is an orange peel meter, simulates the visual evaluation of surface smoothness.], a short-wave value of 21 was measured for the coated plastics surface, while the value for the coated steel surface was 5 6. This shows the excellent coated surface obtained on both the steel and plastic substrates.

CLAIMS

1. A composition, comprising,
- (a) at least 35 weight percent of a
5 semicrystalline isotropic polyester with a melting point
of about 100°C or higher;
- (b) about 0.1 to about 40 weight percent of a
liquid crystalline polymer whose melting point is at
least 50°C higher than a cold crystallization point of
10 said isotropic polyester, or if said isotropic polyester
has no cold crystallization point, said melting point of
said liquid crystalline polymer is about 150°C or higher;
- (c) 0.0 to about 60 weight percent of a solid
particulate material; and
- 15 (d) about 0.2 to about 15 weight percent of a
plasticizer for said isotropic polyester;
- wherein the weight percentages of (a) and (c) are
based on the weight of total composition, and the weight
percentages of (b) and (d) are based on the weight of (a)
20 in said composition.
2. The composition as recited in claim 1 wherein
said isotropic polyester has a melting point of about 200°
or more.
3. The composition as recited in claim 1 or 2
25 wherein said isotropic polyester consists essentially of
repeat units derived from one or more of terephthalic
acid, isophthalic acid and 2,6-naphthalene dicarboxylic
acid, and repeat units derived from one or more of
HO(CH₂)_nOH, 1,4-cyclohexanedimethanol, HO(CH₂CH₂O)_mCH₂CH₂OH,
30 and HO(CH₂CH₂CH₂CH₂O)_zCH₂CH₂CH₂CH₂OH, wherein n is an
integer of 2 to 10, m is an average of 1 to 4, and z is
an average of about 7 to about 40.
4. The composition as recited in any one of the
preceding claims wherein said isotropic polyester is

poly(ethylene terephthalate), poly(1,3-propylene terephthalate), poly(1,4-butylene terephthalate), or poly(1,4-cyclohexyldimethylene terephthalate).

5 5. The composition as recited in any one of the preceding claims wherein said plasticizer is about 3.0 to about 10 weight percent of said isotropic polyester.

6. The composition as recited in any one of the preceding claims wherein said plasticizer has the formula $R^1CO_2R^2O_wCR^1$ wherein each R^1 is hydrocarbyl and each R^2 is
10 alkylene optionally substituted with one or more ether groups and containing 2 to 30 carbon atoms.

7. The composition as recited in any one of the preceding claims wherein said liquid crystalline polymer is about 1.0 to about 10 weight percent of said isotropic
15 polyester.

8. The composition as recited in any one of the preceding claims wherein said solid particulate material is about 5 to about 50 weight percent of said total composition.

20 9. The composition as recited in any one of the preceding claims additionally comprising a polymeric toughening agent containing one or more types of functional groups.

10. The composition as recited in claim 9 wherein
25 said functional group is epoxy or carboxylic anhydride.

11. The composition as recited in claim 9 wherein said functional group is epoxy.

12. The composition as recited in claim 11 wherein
30 said polymeric toughening agent comprises repeat units derived from an epoxy containing (meth)acrylate and ethylene.

13. The composition as recited in any one of the preceding claims which additionally comprises an epoxy compound or resin.

14. The composition as recited in any one of the preceding claims which contains less than 25 ppm free metal cation.

15. An appearance part comprising the composition of
5 claim 1.

16. The appearance part as recited in claim 15 which is pigmented.

17. The appearance part as recited in claim 15 which is coated.

10 18. The appearance part as recited in any one of claims 15-17 which is an automotive body panel, appliance part, power tool housing, electronic cabinet or housing, exterior or interior panel for a vehicle, decorative interior panel for a building, furniture, or telephones
15 or telephone equipment comprising the composition of claim 1.

19. A process for the formation of a shaped part from an isotropic polyester, comprising, cooling a composition from a temperature above a melting point of
20 said isotropic polyester to a temperature below said melting point, wherein said composition comprises:

(a) at least 35 weight percent of a semicrystalline isotropic polyester with a melting point of about 100°C or higher;

25 (b) about 0.1 to about 40 weight percent of a liquid crystalline polymer whose melting point is at least 50°C higher than a cold crystallization point of said isotropic polyester, or if said isotropic polyester has no cold crystallization point, said melting point of
30 said liquid crystalline polymer is about 150°C or higher;

(c) 0.0 to about 60 weight percent of a solid particulate material; and

(d) about 0.2 to about 15 weight percent of a plasticizer for said isotropic polyester;

wherein the weight percentages of (a) and (c) are based on the weight of total composition, and the weight percentages of (b) and (d) are based on the weight of (a) in said composition.

5 20. The process as recited in claim 19 wherein said isotropic polyester has a melting point of about 200° or more.

21. The process as recited in claim 19 or 20 wherein said isotropic polyester consists essentially of repeat
10 units derived from one or more of terephthalic acid, isophthalic acid and 2,6-naphthalene dicarboxylic acid, and repeat units derived from one or more of HO(CH₂)_nOH, 1,4-cyclohexanedimethanol, HO(CH₂CH₂O)_mCH₂CH₂OH, and HO(CH₂CH₂CH₂CH₂O)_zCH₂CH₂CH₂CH₂OH, wherein n is an integer of
15 2 to 10, m is an average of 1 to 4, and z is an average of about 7 to about 40.

22. The process as recited in any one of claims 19-21 wherein said isotropic polyester is poly(ethylene terephthalate), poly(1,3-propylene terephthalate),
20 poly(1,4-butylene terephthalate), or poly(1,4-cyclohexyldimethylene terephthalate).

23. The process as recited in any one of claims 19-22 wherein said plasticizer is about 3.0 to about 10 weight percent of said isotropic polyester.

24. The process as recited in any one of claims 19-23 wherein said liquid crystalline polymer is about 1.0 to about 10 weight percent of said isotropic polyester.

25. The process as recited in any one of claims 19-24 wherein said solid particulate material is about 5 to
30 about 50 weight percent of said total composition.

26. The process as recited in any one of claims 19-25 additionally comprising a polymeric toughening agent containing one or more types of functional groups.

27. The process as recited in claim 26 wherein said functional group is epoxy.

28. The process as recited in claim 27 wherein said polymeric toughening agent comprises repeat units derived
5 from an epoxy containing (meth)acrylate and ethylene.

29. The process as recited in any one of claims 19-28 wherein said composition contains less than 25 ppm free metal cation.

10