

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
11 June 2009 (11.06.2009)

PCT

(10) International Publication Number  
**WO 2009/073437 A1**

(51) International Patent Classification:

A61K 8/60 (2006.01) A61K 9/10 (2006.01)  
A61K 8/73 (2006.01) A61K 31/738 (2006.01)  
A61K 8/04 (2006.01) C08B 37/00 (2006.01)  
A61Q 19/00 (2006.01) A61K 9/00 (2006.01)  
A61Q 19/08 (2006.01)

(74) Agents: FOX, Linda, A et al.; Allergan, Inc., 2525 Dupont Drive, Irvine, CA 92612 (US).

(21) International Application Number:

PCT/US2008/084515

(22) International Filing Date:

24 November 2008 (24.11.2008)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

60/991,473 30 November 2007 (30.11.2007) US  
12/276,167 21 November 2008 (21.11.2008) US

(71) Applicant (for all designated States except US): ALLERGAN, INC. [US/US]; 2525 Dupont Drive, Irvine, CA 92612 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): STROUMPOULIS, Dimitrios [GR/US]; 6616 Abrego Road, #4, Goleta, CA 93117 (US). MUDD, Christopher, S. [US/US]; 451 Whitman Street, #B, Goleta, CA 93117 (US). TEZEL, Ahmet [US/US]; 112 Gerard Drive, Goleta, CA 93117 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, NO, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

(54) Title: POLYSACCHARIDE GEL FORMULATION

(57) Abstract: Described herein are polysaccharide gel formulations including at least one inhibitor of polysaccharide degradation and methods of making the same. The methods described herein involve the steps of providing at least one polysaccharide and incorporating at least one inhibitor of degradation into the polysaccharide. In some embodiments, the incorporating step comprises 1) mixing the at least one inhibitor with the at least one polysaccharide at a highly hydrated state thereby encapsulating the at least one inhibitor in a polysaccharide network, and 2) dehydrating the polysaccharide network thereby controlling release kinetics or final swell ratio. In another embodiment, the incorporating step comprises 1) encapsulating at least one inhibitor into a biocompatible or biodegradable vessel and 2) combining the polysaccharide and the vessel into a gel formulation. The polysaccharide gel formulations described herein can be used for a variety of cosmetic applications.



WO 2009/073437 A1

## POLYSACCHARIDE GEL FORMULATION

By Inventors

5 Dimitrios Stroumpoulis, Christopher S. Mudd, and Ahmet Tezel

### CROSS REFERENCE TO RELATED APPLICATIONS

This application claims the benefit of U.S. provisional patent application number 60/991,473, filed November 30, 2007, the entire disclosure of which is incorporated herein by reference.

### FIELD OF THE INVENTION

Disclosed generally are formulations useful for increasing polysaccharide gel longevity for cosmetic or medical applications, and related methods of making and using same.

### BACKGROUND

Polysaccharides are relatively complex carbohydrates. They are polymers made up of many monosaccharides joined together by glycosidic bonds. They are therefore large, often branched, macromolecules. Polysaccharides, especially hyaluronic acid (HA), have been useful in cosmetic and medical applications. These polymers have been used, for example, as fillers in soft tissue augmentation.

Residing in the extracellular space, HA functions as a space-filling, structure stabilizing, and cell protective molecule with uniquely malleable physical properties and superb biocompatibility. HA matrices are extremely viscoelastic while preserving a high level of hydration. A strong correlation exists between the water content in the skin and levels of HA in dermal tissue. As human skin ages, there are known alterations in HA content and metabolism. With these changes, there is a significant deterioration in the mechanical properties of the skin. There appears to be a relationship between

Docket: 18340 PCT (FAC)

youthful skin and the presence of a strong HA network in the intercellular matrix.

Unfortunately, non-cross-linked as well as cross-linked polysaccharide chains such as HA are subject to degradation through different pathways; (e.g. enzymatic, free radical) thus limiting the polymer's longevity *in vivo*. It is, therefore, important to develop methods and compositions that decrease the rate of natural decomposition and increase the product's persistence *in vivo*. There remains an unmet need for having a polysaccharide formulation which has increased longevity by being resistant to degradation.

### SUMMARY

Described herein are polysaccharide gel (e.g. hyaluronic acid, HA) formulations with increased longevity, or increased degradation time, *in vivo*. This increase in degradation time is provided by the incorporation of molecules that act as inhibitors to degradation. Further, the present disclosure provides methods for encapsulating these formulations to sustain a prolonged longevity or degradation time *in vivo*. The present disclosure also relates to the preparation of gels that can have pharmaceutical or cosmetic applications.

In one embodiment described herein is a polysaccharide gel formulation comprising at least one polysaccharide selected from the group consisting of hyaluronic acid, cellulose, chitosan, *o*-sulfated HA, dextran, dextran sulfate, chondroitin sulfate, dermatan sulfate, keratin sulfate, heparin, heparin sulfate, and alginate, and at least one inhibitor of polysaccharide degradation selected from the group consisting of a glycosaminoglycan, an antioxidant, a flavonoid, a protein, a fatty acid, and combinations thereof. In one embodiment, the polysaccharide is cross-linked. In one embodiment, the at least one polysaccharide is hyaluronic acid.

In one embodiment, the glycosaminoglycan is selected from the group consisting of heparin, heparin sulfate, dermatan sulfate, chondroitin

Docket: 18340 PCT (FAC)

sulfate, o-sulfated hyaluronic acid, linamarin and amygdalin. In another embodiment, the glycosaminoglycan is chondroitin sulfate and is present at a concentration of about 1% to about 40% by weight.

In one embodiment, antioxidant is selected from the group consisting of ascorbic acid, melatonin, vitamin C, vitamin E and combinations thereof.

In one embodiment, the flavonoid is selected from the group consisting of luteolin, apigenin, tangeritin, quercetin, kaempferol, myricetin, fisetin, isorhamnetin, pachypodol, rhamnazin, hesperetin, naringenin, eriodictyol, homoeriodictyol, taxifolin, dihydroquercetin, dihydrokaempferol, tannic acid, tannis, condensed tannis, hydrolysable tannis and combinations thereof. In another embodiment, the flavonoid is tannic acid and is present at a concentration of about 0.0001 to about 1% by weight.

In one embodiment, the protein is a serum hyaluronidase inhibitor. In another embodiment, the fatty acid is a saturated C<sub>10-22</sub> fatty acid.

In one embodiment, the formulation further comprises a biocompatible or biodegradable vessel wherein the inhibitor is inside or part of said vessel, wherein the vessel is a liposome, micelle, or polymerized vesicle. In another embodiment, the inhibitor provides the formulation with improved rheological properties resulting in less extrusion force required for administration of the formulation compared to a cross-linked polysaccharide gel formulation.

In one embodiment described herein is a method of producing a polysaccharide gel formulation comprising having an increased degradation time comprising the step of: providing at least one polysaccharide selected from the group consisting of hyaluronic acid, cellulose, chitosan, o-sulfated HA, dextran, dextran sulfate, chondroitin sulfate, dermatan sulfate, keratin sulfate, heparin, heparin sulfate, and alginate and incorporating in the polysaccharide at least one inhibitor of polysaccharide degradation selected

Docket: 18340 PCT (FAC)

from the group consisting of a glycosaminoglycan, antioxidant, flavonoid, protein and fatty acid.

In one embodiment of the method, the incorporating step comprises 1) mixing the inhibitor with the polysaccharide at a highly hydrated state thereby encapsulating the inhibitor in a polysaccharide network, and 2) dehydrating the polysaccharide network thereby controlling release kinetics or final swell ratio.

In another embodiment of the method, the at least one polysaccharide is cross-linked before incorporation of the at least one inhibitor of polysaccharide degradation using a cross-linker selected from the group consisting of 1,4-butanediol diglycidyl ether (BDDE), 1,2-bis(2,3-epoxypropoxy)ethylene, 1-(2,3-epoxypropyl)-2,3-epoxycyclohexane and combinations thereof.

In one embodiment of the method, the incorporating step comprises 1) encapsulating an inhibitor into a biocompatible or biodegradable vessel and 2) combining the at least one polysaccharide and the vessel into a gel formulation.

In one embodiment described herein is a polysaccharide gel formulation with an increased degradation time comprising cross-linked hyaluronic acid and tannic acid, wherein the tannic acid is present at a concentration of about 0.0001% to about 1%.

In one embodiment described herein is a polysaccharide gel formulation with an increased degradation time comprising cross-linked hyaluronic acid and chondroitin sulfate, wherein the chondroitin sulfate is present at a concentration of about 1% to about 40%.

Further described herein are pharmaceutical compositions comprising a polysaccharide gel formulation, a pharmaceutically acceptable carrier, and an active ingredient. In one embodiment, the active ingredient is selected from the group consisting of anti-itch, anti-cellulite, anti-scarring, anti-

Docket: 18340 PCT (FAC)

inflammatory agents, antioxidants, vitamins, moisturizers and combinations thereof.

### **BRIEF DESCRIPTION OF THE DRAWINGS**

Figure 1 graphically illustrates the extent of enzymatic degradation of polysaccharide gels including chondroitin sulfate A (CSA) using a colorimetric assay.

Figure 2 graphically illustrates the extent of enzymatic degradation of polysaccharide gels including tannic acid (TA) using a colorimetric assay.

Figure 3 graphically illustrates the extent of enzymatic degradation of polysaccharide gels both with and without CSA using a soluble HA assay.

Figure 4 graphically illustrates the extent of enzymatic degradation of polysaccharide gels both with and without TA using a soluble HA assay.

Figure 5 graphically illustrates effects of CSA on the extrusion force of a polysaccharide gel.

### **DETAILED DESCRIPTION**

Described herein are polysaccharide gel (e.g. hyaluronic acid, HA) formulations with increased longevity, or increased degradation time, *in vivo* provided by incorporating molecules that act as inhibitors to degradation. In some embodiments, the polysaccharide gels are cross-linked. Further, the present disclosure also relates to methods for encapsulating these formulations to sustain a prolonged longevity or degradation time *in vivo*. The present disclosure also relates to the preparation of gels that can have pharmaceutical or cosmetic applications.

One aspect of the present disclosure relates to polysaccharide gel formulations comprising at least one polysaccharide and at least one inhibitor of polysaccharide degradation. The present disclosure further relates to increasing the degradation time of polysaccharide gels by incorporating inhibitors to degradation. "Polysaccharide" refers to a polymer of more than two monosaccharide molecules, of which the monosaccharides can be

Docket: 18340 PCT (FAC)

identical or different. The polysaccharide of the present disclosure can be cross-linked or not cross-linked. The polysaccharides used herein can be, but are not limited to, HA, cellulose, chitosan, *o*-sulfated HA, dextran, dextran sulfate, chondroitin sulfate, dermatan sulfate, keratin sulfate, heparin, heparin sulfate, and alginate.

Inhibitors are molecules that act by targeting and neutralizing specific degradation mechanisms such as enzymatic and free radical degradation. Molecules that display inhibitory activity include but are not limited to glycosaminoglycans (GAGs), (e.g. heparin, heparan sulfate, dermatan sulfate, chondroitin sulfate, *o*-sulfated HA, linamarin and amygdalin), antioxidants (e.g. ascorbic acid, melatonin, vitamin C and vitamin E), proteins (e.g. serum hyaluronidase inhibitor) and fatty acids (e.g. saturated C<sub>10</sub> to C<sub>22</sub> fatty acids).

Inhibitors are typically molecules orders of magnitude smaller than cross-linked polysaccharide polymers. Due to their small size and higher diffusivity, they are prone to fast adsorption *in vivo* that could potentially limit their performance. One method of increasing the local half-life of such molecules *in vivo* is to chemically graft them to the polysaccharide polymer network and deliver them simultaneously. One disadvantage of this method is that the bound molecule may display significantly lower activity compared to the unbound one. In the present polysaccharide gel formulation, the inhibitor concentration can be in the range of about 0.0001% to about 99% by wt, about 0.001% to about 75% by weight, about 0.01% to about 60% by weight, about 1% to about 50% by weight, about 1% to about 40% by weight, about 1% to about 30% by weight, about 1% to about 20% by weight, about 10% to about 20% by weight, about 20% to about 30% by weight 0.0001% to about 0.01% by weight, about 0.0001% to about 0.1% by weight, about 0.0001% to about 1% by weight, about 0.001% to about 1% by weight, about 0.01% to about 1% by weight, or about 1% to about 10% by weight.

Docket: 18340 PCT (FAC)

Another aspect of the present disclosure relates to a method of producing a polysaccharide gel formulation having reduced degradation comprising providing a polysaccharide and encapsulating an inhibitor of degradation in the polysaccharide.

5 Non-cross-linked as well as cross-linked polysaccharide chains are subject to degradation through different pathways (e.g. enzymatic, free radical) that often limits the polymer's longevity *in vivo*. It is therefore important to develop ways that decrease the rate of this natural decomposition process and increase the product's persistence in tissues.

10 One method for achieving increased polysaccharide persistence is to encapsulate inhibitor molecules within the polysaccharide polymer network itself or into large vessels within the network that would enable local (injection site), sustained and controlled release of degradation inhibitors. This would also allow avoidance of the natural degradation mechanisms. The present  
15 encapsulation method provides a constant supply of degradation inhibitors to the polysaccharide polymer network over a period of weeks. In other embodiments, a constant supply of degradation inhibitors is provided over a period of months. One method of encapsulation is to incorporate the degradation inhibitors within the polysaccharide polymer network either by  
20 adsorption or by an encapsulation process. In the latter case, the inhibitors are allowed to mix with the polysaccharide network at a highly hydrated state, followed by dehydration of the network to control the release kinetics (e.g. final swelling ratio of the polymer). A highly hydrated state corresponds to an HA concentration that is less than about 20 mg/ml.

25 The final swelling ratio can be controlled by adjusting the pH or partially dehydrating the polysaccharide network. The contracted network can be sized into particles, mixed with the polysaccharide gel and delivered at the site of the injection. The slow re-hydration of the inhibitor-loaded polysaccharide particles can provide a sustained and controlled delivery of  
30 their active content.



Docket: 18340 PCT (FAC)

Another aspect of the present disclosure relates to a polysaccharide gel formulation comprising a polysaccharide and an inhibitor of polysaccharide degradation, and further comprising a biocompatible or biodegradable vessel wherein the inhibitor is inside or part of the vessel.

5 Such vessels can be composed of non-covalently or covalently linked self-assembled molecules such as liposomes, micelles, and polymerized vesicles.

A liposome is a vesicle composed of one or more bilayer membranes formed of naturally-derived phospholipids with mixed lipid chains (such as egg phosphatidylethanolamine), or of pure surfactant components  
10 like dioleoylphosphatidylethanolamine (DOPE). Liposomes, usually but not by definition, contain a core of aqueous solution; lipid structures that contain no aqueous material are called micelles. A micelle is an aggregate of surfactant molecules dispersed in a liquid colloid. A typical micelle in aqueous solution forms an aggregate with the hydrophilic "head" regions in contact with  
15 surrounding solvent, sequestering the hydrophobic "tail" regions in the micelle center. This type of micelle is known as a normal phase micelle (oil-in-water micelle). Inverse micelles have the headgroups at the centre with the tails extending out (water-in-oil micelle). Micelles are often approximately spherical in shape, however, other forms, including shapes such as ellipsoids,  
20 cylinders, and bilayers are also possible. The shape and size of a micelle is a function of the molecular geometry of its surfactant molecules and solution conditions such as surfactant concentration, temperature, pH, and ionic strength. The process of forming micelles is known as micellisation and forms part of the phase behavior of many lipids according to their polymorphism.

25 Another aspect of the present disclosure relates to a method for producing a polysaccharide gel formulation having reduced degradation comprising the steps of 1) providing a polysaccharide, 2) incorporating an inhibitor into a biocompatible or biodegradable vessel and 3) combining said polysaccharide and vessel into a gel formulation. This method of  
30 encapsulation thus incorporates the inhibitors into biocompatible and biodegradable vessels that could be delivered at the same time with the

Docket: 18340 PCT (FAC)

polysaccharide. Such vessels can be composed of non-covalently or covalently linked self-assembled molecules (e.g. micelles, liposomes, and polymerized vesicles). Self-assembly is a term used herein to describe processes in which a disordered system of pre-existing components forms an organized structure or pattern as a consequence of specific, local interactions among the components themselves, without external direction.

An additional advantage of the proposed formulation is the increased tune-ability of the final product's rheological properties. Cross-linked polysaccharide gels typically have high viscosity and require considerable force to extrude through a fine needle. Uncross-linked polysaccharides are often used as lubricants to facilitate this extrusion process. However, especially in HA dermal fillers, uncross-linked HA does not contribute to the persistence of the final product *in vivo*. In fact, the more cross-linked HA is replaced by uncross-linked HA to tune the rheological properties of the dermal filler (for a fixed total HA concentration), the lower the degradation resistance of the product will be. Instead, according to the proposed formulation, uncross-linked GAGs that are also inhibitors to degradation (e.g. chondroitin sulfate, *o*-sulfated hyaluronic acid) can be used both to extend the longevity and improve the rheological properties of the final product.

The polysaccharides described herein can be cross-linked or uncross-linked. A cross-linking agent can be used to cross-link the polysaccharides according to the present description. The cross-linking agent may be any agent known to be suitable for cross-linking polysaccharides and their derivatives via their hydroxyl groups. Suitable cross-linking agents include but are not limited to, for example, 1,4-butanediol diglycidyl ether (or 1,4-bis(2,3-epoxypropoxy)butane or 1,4-bisglycidylloxybutane, all of which are commonly known as BDDE), 1,2-bis(2,3-epoxypropoxy)ethylene and 1-(2,3-epoxypropyl)-2,3-epoxycyclohexane. The use of more than one cross-linking agent or a different cross-linking agent is not excluded from the scope of the

Docket: 18340 PCT (FAC)

present disclosure. In one embodiment, the cross-linking agent comprises or consists of BDDE.

5 Dermal fillers can be used to treat moderate to severe facial wrinkles and folds such as nasolabial folds (those lines that extend from the nose to the corners of the mouth). Dermal fillers can be a gel implant that includes HA, a natural complex sugar that bolsters skin elasticity, providing a smooth and supple appearance. It is biocompatible and can supplement the body's natural HA, which aging can deplete.

10 A dermal gel can be injected with a syringe into the mid to deep dermis of the face. The dermis is the subsurface skin layer that contains connective tissue, nerve endings, sweat and oil glands, and blood vessels. Dermal fillers can improve the skins appearance by lifting and adding volume to the wrinkles and folds in the treatment area.

15 Another aspect of the present disclosure relates to a cosmetic composition comprising the present polysaccharide gel formulation, a cosmetic carrier, and an active ingredient. The cosmetic active ingredients may include but are not limited to antioxidants, vitamins, and moisturizers.

20 As used herein, "cosmetic" is an adjective referring to improving the appearance of a surface or covering defects. Typically, cosmetic compositions can be used to improve aesthetic rather than functional aspects of a surface. Most commonly, cosmetic compositions are formulated for application as a health and beauty treatment or for affecting personal appearance of the body, for example, keratinous surfaces such as skin, hair, nails, and the like.

25 As used herein, "cosmetically acceptable carrier" refers to a material which is suitable for application to keratinous surfaces or other areas of the body. Upon application, cosmetically acceptable carriers are substantially free of adverse reactions with skin and other keratinous surfaces. For example, the cosmetic carriers may take the form of fatty or  
30 non-fatty creams, milky suspensions or emulsion-in-oil or oil-in-water types,

Docket: 18340 PCT (FAC)

lotions, gels or jellies, colloidal or non-colloidal aqueous or oily solutions, pastes, aerosols, soluble tablets or sticks.

As used herein, "formulation" and "composition" may be used interchangeably and refer to a combination of elements that is presented together for a given purpose. Such terms are well known to those of ordinary skill in the art.

As used herein, "carrier," "inert carrier," and "acceptable carrier" may be used interchangeably and refer to a carrier which may be combined with the presently disclosed polysaccharide gel in order to provide a desired composition. Those of ordinary skill in the art will recognize a number of carriers that are well known for making specific remedial pharmaceutical and/or cosmetic compositions.

Another aspect of the present disclosure relates to a pharmaceutical composition comprising the polysaccharide gel formulation, a pharmaceutical carrier and an active ingredient. As used herein, an active ingredient includes but is not limited to a drug. A drug can generally be defined as a chemical substance used in the treatment, cure, prevention, or diagnosis of disease or used to otherwise enhance physical or mental well-being.

Examples of active ingredients which can be included in the present pharmaceutical composition are anti-itch, anti-cellulite, anti-scarring, and anti-inflammatory agents. Anti-itch agents can include methyl sulphonyl methane, sodium bicarbonate, calamine, allantoin, kaolin, peppermint, tea tree oil and combinations thereof. Anti-cellulite agents can include forskolin, xanthine compounds such as, but not limited to, caffeine, theophylline, theobromine, and aminophylline, and combinations thereof. Anti-scarring agents can include IFN- $\gamma$ , fluorouracil, poly(lactic-co-glycolic acid), methylated polyethylene glycol, polylactic acid, polyethylene glycol and combinations thereof. Anti-inflammatory agents can include dexamethasone, prednisolone,

Docket: 18340 PCT (FAC)

corticosterone, budesonide, estrogen, sulfasalazine, mesalamine and combinations thereof.

A polysaccharide such as HA is found naturally in many tissues of the body, such as, but not limited to, skin, cartilage, and the vitreous humor. It is therefore well suited to biomedical applications targeting these tissues. HA can be used in eye surgery (i.e., corneal transplantation, cataract surgery, glaucoma surgery and surgery to repair retinal detachment). HA is also used to treat osteoarthritis of the knee. Such treatments, called visco-supplementation, are administered as a course of injections into the knee joint and are believed to supplement the viscosity of the joint fluid, thereby lubricating the joint, cushioning the joint, and producing an analgesic effect. It has also been suggested that HA has positive biochemical effects on cartilage cells. Oral use of HA has been lately suggested, although its effectiveness needs to be demonstrated. At present, there are some preliminary clinical studies that suggest that oral administration of HA has a positive effect on osteoarthritis.

Due to its high biocompatibility and its common presence in the extracellular matrix of tissues, HA can be used as a biomaterial scaffold in tissue engineering research. In some cancers, HA levels correlate well with malignancy and poor prognosis. HA is thus often used as a tumor marker for prostate and breast cancer. It may also be used to monitor the progression of the disease. HA may also be used postoperatively to induce tissue healing, notably after cataract surgery. Current models of wound healing propose that larger polymers of HA appear in the early stages of healing to physically make room for white blood cells, which mediate the immune response.

A pharmaceutical composition can optionally include one or more agents such as, without limitation, emulsifying agents, wetting agents, sweetening or flavoring agents, tonicity adjusters, preservatives, buffers antioxidants and flavonoids. Tonicity adjustors useful in a pharmaceutical composition of the present disclosure include, but are not limited to, salts such

Docket: 18340 PCT (FAC)

as sodium acetate, sodium chloride, potassium chloride, mannitol or glycerin and other pharmaceutically acceptable tonicity adjusters. Preservatives useful in the pharmaceutical compositions described herein include, without limitation, benzalkonium chloride, chlorobutanol, thimerosal, phenyl mercuric acetate, and phenyl mercuric nitrate. Various buffers and means for adjusting pH can be used to prepare a pharmaceutical composition, including but not limited to, acetate buffers, citrate buffers, phosphate buffers and borate buffers. Similarly, antioxidants useful in pharmaceutical compositions are well known in the art and includes for example, sodium metabisulfite, sodium thiosulfate, acetylcysteine, butylated hydroxyanisole and butylated hydroxytoluene. Flavonoids are compounds found in plants that are well known to have diverse beneficial biochemical and antioxidant effects. Subcategories of flavonoids include: flavones, flavonols, flavanone and flavanonols. Examples of flavonoids include: luteolin, apigenin, tangeritin, quercetin, kaempferol, myricetin, fisetin, isorhamnetin, pachypodol, rhamnazin, hesperetin, naringenin, eriodictyol, homoeriodictyol, taxifolin, dihydroquercetin, dihydrokaempferol, tannic acid, tannis, condensed tannis, and hydrolysable tannis. It is understood that these and other substances known in the art of pharmacology can be included in a pharmaceutical composition of the invention. See for example, Remington's *Pharmaceutical Sciences* Mac Publishing Company, Easton, PA 16<sup>th</sup> Edition 1980.

Some of the advantages of the invention are illustrated below using examples which describe the preparation of an HA filling gel according to the methods described herein, the preparation of an HA filling gel according to the prior art and the degradation tests performed on those samples.

Molecular weight ( $M_w$ ) as used herein refers to the sum of the atomic weights of the atoms in a molecule. For example, that of methane ( $CH_4$ ) is 16.043 g/mol, the atomic weights being carbon = 12.011 g/mol, hydrogen = 1.008 g/mol. A Dalton (Da) is a unit of mass equal to 1/12 the mass of  $^{12}O$  and one million Da can be notated as 1 MDa.

Docket: 18340 PCT (FAC)

**EXAMPLE 1**

## Preparation of a HA Filling Gel According to the Present Disclosure

One to five grams of polysaccharide filler with a HA concentration of 24 mg/mL, about a 6% degree of cross-linking and a G' of about 180 (JUVÉDERM® 24HV, (Allergan Inc., Irvine, California)) are mixed with 1000 µl of a phosphate buffered saline (PBS) solution (pH~7) that is supplemented with 10-200 mg of chondroitin sulfate A (CSA -  $M_w = 5,000-120,000$  Da). The mixture is mechanically homogenized.

**EXAMPLE 2**

## 10 Preparation of a HA Filling Gel by the Process of the Prior Art

One to five grams of polysaccharide filler with a HA concentration of 24 mg/mL, about a 6% degree of cross-linking and a G' of about 180 (JUVÉDERM® 24HV) are mixed with 1000 µl of PBS such that the final HA concentration is the same as in Example 1. The mixture is mechanically homogenized.

**EXAMPLE 3**

## An Alternative Preparation of a Hyaluronic Acid Filling Gel According to the Present Disclosure

One to five grams of a HA based polysaccharide filler with a HA concentration of 24 mg/mL, about a 6% degree of cross-linking and a G' of about 170 (JUVÉDERM® 30) are mixed with 50 µl of PBS solution (pH~7) that is supplemented with 1-20 mg of tannic acid (TA -  $M_w = 800-4,000$  Da). The mixture is mechanically homogenized.

**EXAMPLE 4**

## 25 An Alternative Preparation of a Hyaluronic Acid Filling Gel by the Process of the Prior Art

One to five grams of a HA based polysaccharide filler with a HA concentration of 24 mg/mL, about a 6% degree of cross-linking and a G' of about 170 (JUVÉDERM® 30) are mixed with 50 µl of PBS such that the final

Docket: 18340 PCT (FAC)

HA concentration is the same as in Example 3. The mixture is mechanically homogenized.

### **EXAMPLE 5**

#### Preparation of a Hyaluronic Acid Filling Gel According to the Present Disclosure

One gram of sodium hyaluronate fibers (NaHA,  $M_w = 0.5 - 3$  MDa) is mixed with 5-10 g of 1% sodium hydroxide solution and the mixture is left to hydrate for 1-5 hrs.

Fifty to two hundred milligrams of 1,4-butanediol diglycidyl ether (BDDE) are added to the NaHA gel and the mixture is mechanically homogenized.

The mixture is then placed in a 40-70°C oven for 1-4 hrs.

The resulting cross-linked hydrogel is neutralized with an equimolar amount of hydrochloric acid (HCl) and swelled in PBS (pH≈7).

Ten to two hundred milligrams of CSA ( $M_w = 5,000-120,000$  Da) are added and the hydrogel is mechanically homogenized.

### **EXAMPLE 6**

#### Preparation of an Hyaluronic Acid (HA) Filling Gel by the Process of the Prior Art

One gram of NaHA ( $M_w = 0.5 - 3$  MDa) is mixed with 5-10 g of 1% sodium hydroxide solution and the mixture is left to hydrate for 1-5 hrs.

Fifty to two hundred milligrams of BDDE (same HA: cross-linker molar ratio as in Example 5) are added to the NaHA gel and the mixture is mechanically homogenized.

The mixture is then placed in a 40-70°C oven for 1-4 hrs.

The resulting cross-linked hydrogel is neutralized with an equimolar amount of hydrochloric acid (HCl) and swelled in PBS (pH≈7) such



Docket: 18340 PCT (FAC)

that the final HA concentration is the same as in Example 5. The obtained hydrogel is mechanically homogenized.

### **EXAMPLE 7**

#### Enzymatic Degradation Study (Colorimetric Test)

5 Resistance to enzymatic degradation of the HA filling gels prepared in Examples 1 and 2, was evaluated using the Morgan-Elson colorimetric assay. This assay is used to estimate the average molecular weight of the HA chains before and after enzymatic degradation.

10 Hyaluronidase (0.1-10 mg) was added to the HA samples for 10-250 mins at 37°C followed by 0.1 ml of a 0.8 M potassium tetraborate solution and heating at 100°C for 10 mins. The samples were supplemented with 3 ml of a 10% (wt) p-dimethylaminobenzaldehyde solution in acetic acid and incubated at 37°C for 10-120 mins. The change in the optical density (OD) at 585 nm post and pre-degradation was used to quantify the extent of  
15 degradation in each sample.

The results of the measurements made on the filling gels prepared according to the methods of the present disclosure and according to the prior art shown in Figure 1 (Enzymatic Degradation Test Results (Colorimetric Assay)) indicate that the OD values of the gel prepared by the methods of the present disclosure (*Example 1*: 0.774-25.184 mg/ml CSA) are lower than that  
20 of the gel prepared by the process of the prior art (*Example 2*: 0 mg/ml CSA). Furthermore, the decrease in the OD values is proportional to the concentration of CSA. Since the OD value represents the extent of degradation, the results suggest that the gels prepared according to the present methods display a 3-75% higher enzymatic degradation resistance  
25 than the gel prepared according to the prior art.

Similarly to the case of the CSA supplemented gels, the OD values of the TA supplemented gels prepared by the methods of the present disclosure, as shown in Figure 2, (*Example 3*: 0.063-1.000 mg/mL TA) are

Docket: 18340 PCT (FAC)

lower than that of the gel prepared by the method of the prior art (*Example 4*: 0 mg/mL TA). Furthermore, the decrease in the OD values is proportional to the concentration of TA. Since the OD value represents the extent of degradation, the results suggest that the gels prepared according to the present description display a 15-90% higher enzymatic degradation resistance than the gel prepared according to the prior art. It can further be seen that TA has a higher inhibitory activity than CSA since it generally takes an order of magnitude less amount of TA to obtain the same inhibition as with CSA.

### **EXAMPLE 8**

#### Enzymatic Degradation Study (Soluble HA Assay)

To further evaluate the enzymatic degradation resistance of the HA filling gels prepared in Examples 1 and 2, a SEC-MALS (Size Exclusion Multi-Angle Light Scattering) based soluble HA assay was used. This assay can be used to quantify degradation by evaluating the percentage of soluble HA (defined as the portion of the gel that can pass through a 0.2-1.0  $\mu\text{m}$  filter) contained in each sample. The change in the amount of soluble HA, pre and post-degradation, can be used to quantify the extent of degradation in each sample.

The SEC-MALS tests were performed using an Agilent size exclusion chromatography system equipped with Wyatt light scattering and refractive index units. Hyaluronidase (0.1-10 mg) was added to the HA samples for 10-250 mins at 37°C followed by 0.1 ml of a 0.8 M potassium tetraborate solution and heating at 100°C for 10 mins. The samples were diluted in PBS, filtered through a 0.2-1.0  $\mu\text{m}$  filter and injected into the SEC-MALS system. The soluble HA content before and after the enzymatic degradation as well as their difference are shown in Figure 3.

The results shown in Figure 3 (Enzymatic Degradation Test Results (SEC-MALS Assay)) indicate that the increase in the soluble HA

Docket: 18340 PCT (FAC)

content post enzymatic degradation is significantly greater for the non-CSA containing sample. This difference in the soluble HA increase between the CSA and the non-CSA samples is consistent with the results obtained in the colorimetric degradation assay and suggests that the gel prepared according to the methods of the present disclosure shows a higher degradation resistance than the gel prepared according to the prior art.

Similarly to the case of the CSA supplemented gels, the post degradation increase in the soluble HA content of the TA supplemented gels prepared by the methods of the present description (*Example 3*: 0.063-1.000 mg/mL TA) is lower than that of the gel prepared by the process of the prior art (*Example 4*: 0 mg/mL TA). These results are in agreement with the colorimetric method summarized in Figure 4. Furthermore, it can be seen again that the inhibitory activity of TA is an order of magnitude higher than that of CSA.

### **EXAMPLE 9**

#### Continuous Extrusion Force Test

To evaluate the rheological properties of the hyaluronic acid filling gels prepared in Examples 5 and 6 continuous extrusion force tests were performed on each sample. The extrusion force test can be used to determine whether CSA can facilitate the extrusion process, by acting as a lubricant.

The extrusion force tests were performed on an Instron instrument using a 5 ml syringe with a 30G needle. 0.5 ml of each sample was extruded at a constant rate of 50 mm/min. The peak force recorded quantifies the ease of extrusion. The compressive force as a function of the compressive extension for the two samples is plotted in Figure 5.

The results in Figure 5 show that the extrusion force recorded for the gel prepared by the methods described herein is lower than that of the gel prepared by the process of the prior art. This difference in the extrusion force

Docket: 18340 PCT (FAC)

is characteristic of the difference in gel hardness under flow and suggests that the CSA contained in the gel prepared by the methods described herein acts as a lubricant that facilitates flow.

Unless otherwise indicated, all numbers expressing quantities of ingredients, properties such as molecular weight, reaction conditions, and so forth used in the specification and claims are to be understood as being modified in all instances by the term "about." Accordingly, unless indicated to the contrary, the numerical parameters set forth in the specification and attached claims are approximations that may vary depending upon the desired properties sought to be obtained by the present invention. At the very least, and not as an attempt to limit the application of the doctrine of equivalents to the scope of the claims, each numerical parameter should at least be construed in light of the number of reported significant digits and by applying ordinary rounding techniques. Notwithstanding that the numerical ranges and parameters setting forth the broad scope of the invention are approximations, the numerical values set forth in the specific examples are reported as precisely as possible. Any numerical value, however, inherently contains certain errors necessarily resulting from the standard deviation found in their respective testing measurements.

The terms "a," "an," "the" and similar referents used in the context of describing the invention (especially in the context of the following claims) are to be construed to cover both the singular and the plural, unless otherwise indicated herein or clearly contradicted by context. Recitation of ranges of values herein is merely intended to serve as a shorthand method of referring individually to each separate value falling within the range. Unless otherwise indicated herein, each individual value is incorporated into the specification as if it were individually recited herein. All methods described herein can be performed in any suitable order unless otherwise indicated herein or otherwise clearly contradicted by context. The use of any and all examples, or exemplary language (e.g., "such as") provided herein is intended merely to better illuminate the invention and does not pose a limitation on the scope of

Docket: 18340 PCT (FAC)

the invention otherwise claimed. No language in the specification should be construed as indicating any non-claimed element essential to the practice of the invention.

5 Groupings of alternative elements or embodiments of the invention disclosed herein are not to be construed as limitations. Each group member may be referred to and claimed individually or in any combination with other members of the group or other elements found herein. It is anticipated that one or more members of a group may be included in, or deleted from, a group for reasons of convenience and/or patentability. When any such inclusion or  
10 deletion occurs, the specification is deemed to contain the group as modified thus fulfilling the written description of all Markush groups used in the appended claims.

Certain embodiments of this invention are described herein, including the best mode known to the inventors for carrying out the invention.  
15 Of course, variations on these described embodiments will become apparent to those of ordinary skill in the art upon reading the foregoing description. The inventor expects skilled artisans to employ such variations as appropriate, and the inventors intend for the invention to be practiced otherwise than specifically described herein. Accordingly, this invention includes all  
20 modifications and equivalents of the subject matter recited in the claims appended hereto as permitted by applicable law. Moreover, any combination of the above-described elements in all possible variations thereof is encompassed by the invention unless otherwise indicated herein or otherwise clearly contradicted by context.

25 Furthermore, numerous references have been made to patents and printed publications throughout this specification. Each of the above-cited references and printed publications are individually incorporated herein by reference in their entirety.

In closing, it is to be understood that the embodiments of the  
30 invention disclosed herein are illustrative of the principles of the present

Docket: 18340 PCT (FAC)

invention. Other modifications that may be employed are within the scope of the invention. Thus, by way of example, but not of limitation, alternative configurations of the present invention may be utilized in accordance with the teachings herein. Accordingly, the present invention is not limited to that  
5 precisely as shown and described.

Specific embodiments disclosed herein may be further limited in the claims using consisting of or and consisting essentially of language. When used in the claims, whether as filed or added per amendment, the transition term "consisting of" excludes any element, step, or ingredient not  
10 specified in the claims. The transition term "consisting essentially of" limits the scope of a claim to the specified materials or steps and those that do not materially affect the basic and novel characteristic(s). Embodiments of the invention so claimed are inherently or expressly described and enabled  
herein.

15 .

Docket: 18340 PCT (FAC)

We claim:

1. A polysaccharide gel formulation comprising at least one polysaccharide selected from the group consisting of hyaluronic acid, cellulose, chitosan, *o*-sulfated HA, dextran, dextran sulfate, chondroitin sulfate, dermatan sulfate, keratin sulfate, heparin, heparin sulfate, and alginate, and at least one inhibitor of polysaccharide degradation selected from the group consisting of a glycosaminoglycan, an antioxidant, a flavonoid, a protein, a fatty acid, and combinations thereof.
2. The formulation of claim 1, wherein said polysaccharide is cross-linked.
3. The formulation of claim 1, wherein said at least one polysaccharide is hyaluronic acid.
4. The formulation of claim 1, wherein said glycosaminoglycan is selected from the group consisting of heparin, heparin sulfate, dermatan sulfate, chondroitin sulfate, *o*-sulfated hyaluronic acid, linamarin and amygdalin.
5. The formulation of claim 4, wherein said glycosaminoglycan is chondroitin sulfate.
6. The formulation of claim 5, wherein said chondroitin sulfate is present at a concentration of about 1% to about 40% by weight.
7. The formulation of claim 1, wherein said antioxidant is selected from the group consisting of ascorbic acid, melatonin, vitamin C, vitamin E and combinations thereof.
8. The formulation of claim 1, wherein said flavonoid is selected from the group consisting of luteolin, apigenin, tangeritin, quercetin, kaempferol, myricetin, fisetin, isorhamnetin, pachypodol, rhamnazin, hesperetin, naringenin, eriodictyol, homoeriodictyol, taxifolin, dihydroquercetin,

Docket: 18340 PCT (FAC)

dihydrokaempferol, tannic acid, tannis, condensed tannis, hydrolysable tannis and combinations thereof.

9. The formulation of claim 8, wherein said flavonoid is tannic acid.
10. The formulation of claim 9, wherein said tannic acid is present at a concentration of about 0.0001 to about 1% by weight.
11. The formulation of claim 1, wherein said protein is a serum hyaluronidase inhibitor.
12. The formulation of claim 1, wherein said fatty acid is a saturated C<sub>10-22</sub> fatty acid.
13. The formulation of claim 1, further comprising a biocompatible or biodegradable vessel wherein said inhibitor is inside or part of said vessel, wherein said vessel is a liposome, micelle, or polymerized vesicle.
14. The formulation of claim 1, wherein said inhibitor provides said formulation with improved rheological properties resulting in less extrusion force required for administration of said formulation compared to a cross-linked polysaccharide gel formulation.
15. A method of producing a polysaccharide gel formulation comprising having an increased degradation time comprising the step of:  
  
providing at least one polysaccharide selected from the group consisting of hyaluronic acid, cellulose, chitosan, *o*-sulfated HA, dextran, dextran sulfate, chondroitin sulfate, dermatan sulfate, keratin sulfate, heparin, heparin sulfate, and alginate and incorporating in said polysaccharide at least one inhibitor of polysaccharide degradation selected from the group consisting of a glycosaminoglycan, antioxidant, flavonoid, protein and fatty acid.
16. The method of claim 15, wherein said incorporating step comprises 1) mixing said at least one inhibitor with said at least one polysaccharide at a



Docket: 18340 PCT (FAC)

highly hydrated state thereby encapsulating said at least one inhibitor in a polysaccharide network, and 2) dehydrating said polysaccharide network thereby controlling release kinetics or final swell ratio.

17. The method of claim 15, wherein said at least one polysaccharide is cross-linked before incorporation of said at least one inhibitor of polysaccharide degradation using a cross-linker selected from the group consisting of 1,4-butanediol diglycidyl ether (BDDE), 1,2-bis(2,3-epoxypropoxy)ethylene, 1-(2,3-epoxypropyl)-2,3-epoxycyclohexane and combinations thereof.

18. The method of claim 15, wherein said incorporating step comprises 1) encapsulating said at least one inhibitor into a biocompatible or biodegradable vessel and 2) combining said at least one polysaccharide and said vessel into a gel formulation.

19. A polysaccharide gel formulation with an increased degradation time comprising cross-linked hyaluronic acid and tannic acid, wherein said tannic acid is present at a concentration of about 0.0001% to about 1%.

20. A polysaccharide gel formulation with an increased degradation time comprising cross-linked hyaluronic acid and chondroitin sulfate, wherein said chondroitin sulfate is present at a concentration of about 1% to about 40%.






FIG. 1



**FIG. 2**



**FIG. 4**




FIG. 3




FIG. 5

# INTERNATIONAL SEARCH REPORT

International application No  
PCT/US2008/084515

**A. CLASSIFICATION OF SUBJECT MATTER**

INV.	A61K8/60	A61K8/73	A61K8/04	A61Q19/00	A61Q19/08
	A61K9/10	A61K31/738	C08B37/00	A61K9/00	

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)  
A61K A61Q C08B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 92/00105 A (GENZYME CORP [US]) 9 January 1992 (1992-01-09) page 3, line 28 - page 6, line 34; claims -----	1-20
E	WO 2009/028764 A (UNIV SOGANG IND UNIV COOP FOUN [KR]; KIM YONG-HEE [KR]; JIN KWANG-MI [ ]) 5 March 2009 (2009-03-05) claims -----	1-20
P,X	WO 2008/072230 A (MOR RESEARCH APPLIC LTD [IL]; BEN-SHALOM NOAH [IL]; NEVO ZVI [IL]; PAT) 19 June 2008 (2008-06-19) claims 1,10,13,14 -----	1-20
X	US 4 605 691 A (BALAZS ENDRE A [US] ET AL) 12 August 1986 (1986-08-12) example 16 -----	1-20
	-/--	

Further documents are listed in the continuation of Box C.

See patent family annex.

\* Special categories of cited documents :

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*Z\* document member of the same patent family

Date of the actual completion of the international search

30 March 2009

Date of mailing of the international search report

08/04/2009

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040,  
Fax: (+31-70) 340-3016

Authorized officer

Mitchell, Gemma

## INTERNATIONAL SEARCH REPORT

International application No

PCT/US2008/084515

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, A	WO 2008/034176 A (ULTRACEUTICALS R & D PTY LTD [AU]; UNIV SYDNEY [AU]; HEBER GEOFFREY KE) 27 March 2008 (2008-03-27) the whole document -----	1-20
A	US 2004/265389 A1 (YUI NOBUHIKO [JP] ET AL) 30 December 2004 (2004-12-30) paragraphs [0003], [0004], [0010] - [0028] -----	1-20
A	US 2003/031638 A1 (JOSHI VIJAY KUMAR [US] ET AL) 13 February 2003 (2003-02-13) paragraphs [0005], [0006], [0025], [0026], [0034], [0047], [0048] -----	1-20
A	EP 0 273 823 A (MERO ROUSSELOT SATIA SA [FR]) 6 July 1988 (1988-07-06) example 5 -----	1-20

## INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2008/084515

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9200105	A	09-01-1992	AT 151294 T	15-04-1997
			AU 660282 B2	22-06-1995
			AU 8392491 A	23-01-1992
			DE 69125609 D1	15-05-1997
			DE 69125609 T2	17-07-1997
			DK 537292 T3	04-08-1997
			EP 0537292 A1	21-04-1993
			ES 2100954 T3	01-07-1997
			FI 925802 A	21-12-1992
			GR 3023436 T3	29-08-1997
			JP 3399526 B2	21-04-2003
			JP 5508161 T	18-11-1993
			NO 924875 A	16-12-1992
			US 5017229 A	21-05-1991
WO 2009028764	A	05-03-2009	KR 100813224 B1	13-03-2008
WO 2008072230	A	19-06-2008	US 2009004276 A1	01-01-2009
US 4605691	A	12-08-1986	NONE	
WO 2008034176	A	27-03-2008	NONE	
US 2004265389	A1	30-12-2004	JP 2004323453 A	18-11-2004
US 2003031638	A1	13-02-2003	AU 5064902 A	30-01-2003
			CA 2390824 A1	26-01-2003
			GB 2378653 A	19-02-2003
			US 2004202630 A1	14-10-2004
			ZA 200205749 A	25-07-2003
EP 0273823	A	06-07-1988	CA 1323307 C	19-10-1993
			FR 2608456 A1	24-06-1988
			JP 63197540 A	16-08-1988
			PT 86390 A	01-01-1988
			US 5051304 A	24-09-1991