



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B05D 1/32, 3/02, B32B 17/06	A1	(11) International Publication Number: WO 99/00197 (43) International Publication Date: 7 January 1999 (07.01.99)
(21) International Application Number: PCT/US98/13428 (22) International Filing Date: 29 June 1998 (29.06.98) (30) Priority Data: 08/884,713 30 June 1997 (30.06.97) US (71) Applicant: AVERY DENNISON CORPORATION [US/US]; 150 North Orange Grove Boulevard, Pasadena, CA 91103 (US). (72) Inventors: MAKAR, Onsy, Y.; 26 Parker Road, Framingham, MA 01702 (US). CARUSO, Paul, J.; 5 Dewey Road, Bedford, MA 01730 (US). (74) Agents: KRIEGSMAN, Irving, M. et al.; Kriegsman & Kriegsman, 883 Edgell Road, Framingham, MA 01701 (US).	(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>	
(54) Title: METHOD FOR SCREEN PRINTING GLASS ARTICLES		
(57) Abstract A method for decorating and/or labelling glass articles and like ceramic ware by screen printing. The present method comprises the steps of: (a) treating a glass article or the like with a silane adhesion promoter; and (b) applying a non-ceramic screen ink directly onto the silane-treated glass article by screen printing. The non-ceramic screen ink is preferably a heat-set ink which includes an organic resinous binder, a non-heavy metal colorant and a vaporizable solvent system. Examples of the binder include, but are not limited to, one or more of polyamide, polyester, polyester-vinyl, acrylic, vinyl and acrylic-vinyl resins. Examples of the non-heavy metal colorant include titanium dioxide and organic colorants (e.g., insoluble derivatives of organic dyes). The non-ceramic screen ink may additionally comprise one or more rheology-adjusting agents for making the ink well-suited for screen printing and may additionally include other additives of the type commonly found in screen or other printing inks. Once the ink has been applied to the glass article by screen printing, the printed article is preferably heated, causing the solvent system to be driven off and causing the binder, colorant and other non-volatile components of the ink to be set on the article.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakistan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

METHOD FOR SCREEN PRINTING GLASS ARTICLES**BACKGROUND OF THE INVENTION**

The present invention relates generally to techniques for decorating and/or labelling articles and more particularly to a novel method for screen printing glass articles and like ceramic ware.

The decorating and/or labelling of commercial articles, such as, and without limitation to, containers, clothing materials, construction materials, artwork and the like, is widespread and well-known. One established technique for decorating and/or labelling articles is screen printing. Screen printing typically uses a porous screen of fine silk, stainless steel or a similarly suitable synthetic fiber that is mounted on a frame. A stencil is produced on the screen, either manually or photomechanically, in which the non-printing areas are protected by the stencil. Printing is done on a substrate under the screen by applying ink with a paint-like consistency to the screen, and then spreading and forcing the ink through the openings of the screen with a rubber squeegee onto the underlying substrate.

One of the desirable aspects of screen printing is that a thick layer of ink can be deposited onto a desired substrate. Another desirable aspect of screen printing is that a variety of different types of materials can be decorated by screen printing; however, heretofore, the type of material being printed upon has, to some extent, limited the type of screen ink that could be used in printing thereon. For example, ceramic materials, including glass articles, have heretofore required the use of ceramic screen inks. Ceramic screen inks typically include a ceramic material, such as silicon dioxide, which is doped with an inorganic pigment (which is often a derivative of a heavy metal). Such inks typically further include a liquid vehicle, said vehicle often comprising a dispersant and a suitable solvent. If necessary, additives for adjusting the rheology of the ink for screen printing, or other desirable additives, are also included. After a glass or other ceramic article has been screen printed with a ceramic screen ink of the foregoing type, the printed article is typically fired to a very high temperature, causing the liquid vehicle to be burned-off and causing the doped ceramic material to become fused to the article.

Examples of ceramics inks suitable for screen printing are disclosed in the following U.S. patents, all of which are herein incorporated by reference: U.S. Patent No. 4,043,824, inventor Wagar, issued August 23, 1977; U.S. Patent No. 4,416,974, inventor Scheve, issued November 22, 1983; U.S. Patent No. 5,275,649, inventors Linke et al., issued January 4, 1994; and U.S. Patent No. 5,238,881, inventor Norris, issued August 24, 1993.

One problem with ceramic screen inks is that the colorant/dopant must be an inorganic pigment in order to withstand the high firing temperatures mentioned above. Many inorganic pigments, however, are derivatives of heavy metals (titanium dioxide being a notable exception) and, therefore, pose health and/or environmental risks. Additionally, as can readily be appreciated, the range of different colors afforded by the class of inorganic pigments is limited, due to the constraints of nature, as compared to that afforded by the class of organic colorants.

Still another problem with ceramic screen inks is that one must possess equipment capable of obtaining the very high firing temperatures discussed above in order to cure the ink once printed on the substrate. As can readily be appreciated, the expense of such equipment will, in many instances, preclude all but glass manufacturers from being able to screen print ceramic inks onto glass and the like.

Screen printing is not the only technique presently used to decorate or to label glass articles. One such alternative technique involves the use of heat-transfer labels. One well-known type of heat-transfer label is described in U.S. Patent No. 3,616,015, inventor Kingston, which issued October, 1971, and which is incorporated herein by reference. In the aforementioned patent, there is disclosed a heat-transfer label comprising a paper sheet or web, a wax release layer affixed to the paper sheet, and an ink design layer printed on the wax release layer. In the heat-transfer labelling process, the label-carrying web is subjected to heat, and the label is pressed onto an article with the ink design layer making direct contact with the article. As the paper sheet is subjected to heat, the wax layer begins to melt so that the paper sheet can be released from the ink design layer,

a portion of the wax layer being transferred with the ink design layer and a portion of the wax layer remaining with the paper sheet. After transfer of the design to the article, the paper sheet is immediately removed, leaving the design firmly affixed to the article and the wax transferred therewith exposed to the environment. The wax layer is thus intended to serve two purposes: (1) to provide release of the ink design from the web upon application of heat to the web and (2) to form a protective layer over the transferred ink design. After transfer of the label to the article, the transferred wax release layer is typically subjected to a post-flaming technique which enhances the optical clarity of the wax protective layer (thereby enabling the ink design layer therebeneath to be better observed) and which enhances the protective properties of the transferred wax release.

In some heat-transfer labels, an adhesive layer (e.g., solvent-soluble polyamide, acrylic or polyester) is deposited over the ink design to facilitate adhesion of the label onto a receiving article. An example of a heat-transfer label having an adhesive layer is disclosed in U.S. Patent No. 4,548,857, inventor Galante, which issued October 22, 1985, and which is incorporated herein by reference. Additionally, in some heat-transfer labels, a protective lacquer layer is interposed between the wax release layer and the ink layer. An example of such a label is disclosed in U.S. Patent No. 4,426,422, inventor Daniels, which issued January 17, 1984, and which is incorporated herein by reference.

Another type of heat-transfer label (i.e., a wax-less, heat-transfer label) is disclosed in U.S. Patent No. 4,935,300, inventors Parker et al., which issued June 19, 1990, and which is incorporated herein by reference. In the aforementioned patent, the label, which is said to be particularly well-suited for use on high density polyethylene, polypropylene, polystyrene, polyvinylchloride and polyethylene terephthalate surfaces or containers, comprises a paper carrier web which is overcoated with a layer of polyethylene. A protective lacquer layer comprising a polyester resin and a relatively small amount of a nondrying oil is printed onto the polyethylene layer. An ink design layer comprising a resinous binder base selected from the group consisting of polyvinylchloride, acrylics, polyamides and nitrocellulose is printed onto the protective lacquer layer. A heat-activatable

adhesive layer comprising a thermoplastic polyamide adhesive is printed onto the ink design layer.

In general, the ink design layer of the above-described heat-transfer labels is formed by gravure printing onto the protective lacquer layer (or onto whichever
5 layer it is desired to put the ink design layer) a design using an ink formulation comprising an organic resinous binder, a colorant and a vaporizable solvent system. The printed article is then heated, causing the solvent system to evaporate and causing the remaining non-volatile components to be set on the substrate. The resinous binder is typically selected from the group including
10 polyamide, polyester, polyester-vinyl, acrylic, vinyl and acrylic-vinyl resins. The colorant is typically selected from the group including titanium dioxide and organic colorants (e.g., insoluble derivatives of organic dyes).

In those instances in which a heat-transfer label of the type described above is used to decorate a glass container, the glass container is typically pre-treated
15 with a silane adhesion promoter of the type described in U.S. Patent No. 3,907,974, inventor Smith, which issued September 23, 1975, and which is incorporated herein by reference. The reason for silane-treatment is to make the glass container more receptive to the adhesive layer of the heat-transfer label. Glass containers are typically not receptive to heat-transfer labels because they are usually
20 manufactured with a coating of stearate applied to the outside surface thereof, the stearate-coating impairing adhesion between the heat-transfer label and the glass container. The reason why stearate is typically applied to glass containers is to act as a lubricant to reduce scratching of adjacent glass containers following their manufacture. By silane-treating a stearate-coated glass container, it has been
25 found that one can improve the adhesion between the glass container and a heat-transfer label.

SUMMARY OF THE INVENTION

It is an object of the present invention to provide a novel method for decorating and/or labelling glass articles and like ceramic ware.

5 It is another object of the present invention to provide a method as described above that involves screen printing.

It is still another object of the present invention to provide a method as described above that overcomes at least some of the problems discussed above in connection with the screen printing of glass articles and like ceramic ware.

10 Additional objects, as well as features, advantages and aspects of the present invention, will be set forth in part in the description which follows, and in part will be obvious from the description or may be learned by practice of the invention. In the description, reference is made to specific embodiments for practicing the invention. These embodiments will be described in sufficient detail to enable those skilled in the art to practice the invention, and it is to be understood
15 that other embodiments may be utilized and that changes may be made without departing from the scope of the invention. The following detailed description is, therefore, not to be taken in a limiting sense, and the scope of the present invention is best defined by the appended claims.

20 In furtherance of the above and other objects that are herein disclosed or are apparent from the present specification, there is hereinafter provided a method for decorating and/or labelling a glass article or like ceramic ware, said method comprising the steps of: (a) treating the glass article with a silane adhesion promoter; and (b) applying a non-ceramic screen ink directly onto the silane-treated glass article by screen printing.

25 Preferably, said non-ceramic screen ink comprises an organic resinous binder, a non-heavy metal colorant and a solvent system. Examples of the binder include, but are not limited to, one or more of polyamide, polyester, polyester-vinyl, acrylic, vinyl and acrylic-vinyl resins. Examples of the non-heavy metal colorant include titanium dioxide and organic colorants (e.g., insoluble derivatives of organic
30 dyes). Said non-ceramic screen ink may additionally comprise one or more rheology-adjusting agents for making the ink well-suited for screen printing and may

additionally include other additives of the type commonly found in screen or other printing inks.

5 Preferably, said non-ceramic screen ink is a heat-set ink. Accordingly, once the ink has been applied to the glass article by screen printing, the printed article is heated, causing the solvent system to evaporate and causing the binder, colorant and other non-volatile components of the ink to be set on the article.

In addition to being directed to the above-described method, the present invention is also directed to glass articles decorated by the above-described method.

10

DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS

As indicated above, the present invention is directed to a novel method for decorating and/or labelling glass and related ceramic articles by screen printing. One important aspect of the present method is that ceramic screen inks are not used. One advantage of not using ceramic screen inks in the present method is that the firing temperatures discussed above that are needed to fuse a ceramic ink to a glass article are no longer needed nor is the equipment for generating such firing temperatures needed. Moreover, because ceramic inks require the use of certain colorants that are stable even when subjected to the aforementioned types of firing temperatures, such as heavy-metal inorganic pigments (many of which pose health and/or environmental risks), the elimination of ceramic inks in the present method makes possible the use of colorants that do not have the disadvantages associated with heavy-metal inorganic pigments.

Simply stated, the present method comprises the steps of (a) treating a glass article or the like with a silane adhesion promoter; and (b) applying a non-ceramic screen ink directly onto the silane-treated glass article by screen printing.

The treatment of glass and like articles with silane adhesion promoters in accordance with the present invention is done in the conventional manner, as evidenced by U.S. Patent No. 3,907,974. Typically, silane-treatment comprises spraying or spreading (using a belt) a silane solution onto a glass article at room temperature. The treated article is then heated prior to decoration, typically to about 200-250°F, thereby driving off the volatile components (e.g., water) of the silane solution and leaving behind the nonvolatile components (e.g., silane) of the solution on the glass article. Examples of silane solutions include, but are not limited to, HYDROSIL HS 3202 (Huls America Inc., Piscataway, NJ), T-185995 (Seagrave), SILANE Z-6020 (Dow) and A-1100 (Union Carbide).

The non-ceramic screen ink of the present invention preferably comprises an organic resinous binder, a non-heavy metal colorant and a suitable solvent system. Examples of the organic resinous binder include, but are not limited to, one or more of polyamide, polyester, polyester-vinyl, acrylic, vinyl and acrylic-vinyl resins.

Examples of the non-heavy metal colorant include titanium dioxide and the class of organic colorants, including insoluble derivatives of organic dyes. Examples of organic colorants include, but are not limited to, carbon black, phthalocyanine blue and green, naphthol red and diarylide yellow. Additional
5 examples of organic colorants are disclosed in U.S. Patent No. 4,321,185, inventor Benitez, issued March 23, 1982 and U.S. Patent No. 5,389,717, inventors Santini et al., issued February 14, 1995, both of which are incorporated herein by reference.

The non-ceramic screen ink of the present invention may additionally
10 comprise one or more rheology-adjusting agents for making the ink well-suited for screen printing. Examples of said rheology-adjusting agents include, but are not limited to, silicas, clays and gums. Specific rheology-adjusting agents are disclosed in U.S. Patent No. 5,217,255, inventors Lin et al., issued June 8, 1993, which is incorporated herein by reference, as well as the aforementioned U.S. Patent No.
15 5,389,717.

The non-ceramic screen ink of the present invention may further include other additives of the type commonly found in screen or other printing inks. Examples of such additives include preservatives, anti-corrosion agents and the like.

20 Preferably, the non-ceramic screen ink of the present invention is a heat-set ink, the solvent system therein being vaporizable. Accordingly, once the ink has been applied to the glass article by screen printing, the printed article is heated, causing the solvent system to evaporate and causing the binder, colorant and other non-volatile components of the ink to be set on the article.

25 The non-ceramic screen ink of the present invention may be made by adding one or more rheology-adjusting agents, if necessary, to any one of the inks used to make the ink design layer of the heat-transfer labels described in, for example, U.S. Patent No. 4,935,300, inventors Parker et al., issued June 19, 1990; U.S. Patent No. 4,548,857, inventor Galante, issued October 22, 1985; U.S. Patent No.
30 4,426,422, inventor Daniels, issued January 17, 1984; U.S. Patent No. 3,907,974,

inventor Smith, issued September 23, 1975, all of which are incorporated herein by reference.

The following Examples illustrate certain aspects of the present invention and, in no way, should be limiting:

5

EXAMPLE I

<u>Ingredient</u>	<u>Percentage by weight</u>
VITEL [®] 2700 [†]	18.0
phthalocyanine (blue pigment)	7.0
toluene	45.0
10 n-propyl acetate	27.0
SYLOID 244 [*]	3.0

[†] VITEL[®] 2700 is a copolyester resin having a high tensile strength (7000 psi) and a low elongation (4% elongation) commercially available from Shell Chemical Company, Akron, OH.

^{*} SYLOID 244 is a synthetic amorphous silica commercially available from W.R. Grace & Co.

15

The above-described screen ink was applied to a silane-treated glass container by screen printing. The decorated glass container was then heated in an oven until the glass container reached a temperature of 400°F (which took about 5-15 minutes) to cure the printed ink.

20

EXAMPLE II

<u>Ingredient</u>	<u>Percentage by weight</u>
ELVACITE [®] 2045 [‡]	21.0
phthalocyanine (blue pigment)	7.0
toluene	36.0
25 methyl ethyl ketone	33.0
SYLOID 244	3.0

[‡] ELVACITE[®] 2045 is a high molecular weight isobutyl methacrylate resin having an inherent viscosity of 0.64 (as measured in a solution containing 0.25 g of polymer in 50 ml methylene chloride, measured at 20°C using a No. 50 Cannon-Fenske Viscometer) commercially available from ICI Acrylics, Inc., Wilmington, DE.

30

The above-described screen ink was applied to a silane-treated glass container. The decorated glass container was then heated in an oven until the

glass container reached a temperature of 400°F (which took approximately 5-15 minutes) to cure the printed ink.

5 The embodiments of the present invention recited herein are intended to be merely exemplary and those skilled in the art will be able to make numerous variations and modifications to it without departing from the spirit of the present invention. Certain variations and modifications, while producing less than optimal results, may still produce satisfactory results. All such variations and modifications are intended to be within the scope of the present invention as defined by the claims appended hereto.

WHAT IS CLAIMED IS:

1. A method for decorating and/or labelling a glass article or like ceramic ware, said method comprising the steps of:

- (a) treating the glass article with a silane adhesion promoter; and
5 (b) applying a non-ceramic screen ink directly onto the silane-

treated glass article by screen printing.

2. The method as claimed in claim 1 wherein said non-ceramic screen ink comprises an organic resinous binder, a non-heavy metal colorant and a solvent system.

10 3. The method as claimed in claim 2 wherein said organic resinous binder is selected from the group consisting of one or more of polyamide, polyester, polyester-vinyl, acrylic, vinyl and acrylic-vinyl binders.

4. The method as claimed in claim 3 wherein said organic resinous binder is a polyamide binder.

15 5. The method as claimed in claim 3 wherein said organic resinous binder is a polyester binder.

6. The method as claimed in claim 3 wherein said organic resinous binder is an acrylic binder.

20 7. The method as claimed in claim 2 wherein said non-heavy metal colorant is selected from the group consisting of titanium dioxide and organic colorants.

8. The method as claimed in claim 7 wherein said non-heavy metal colorant is titanium dioxide.

9. The method as claimed in claim 7 wherein said non-heavy metal colorant is an organic colorant.

25 10. The method as claimed in claim 9 wherein said organic colorant is an insoluble derivative of an organic dye.

11. The method as claimed in claim 2 wherein said non-ceramic screen ink further includes a rheology-adjusting agent.

30 12. The method as claimed in claim 11 wherein said rheology-adjusting agent is a silica.

13. The method as claimed in claim 2 wherein said non-ceramic screen ink is a heat-set ink, said method further comprising, after said applying step, the step of heating the printed glass article so as to cause the solvent system to evaporate and so as to cause the organic resinous binder and the non-heavy metal colorant to be set on the glass article.

14. A printed glass article made by the method of claim 13.

15. The method as claimed in claim 1 wherein said non-ceramic screen ink comprises 18.0%, by weight, of a copolyester resin having a tensile strength of 7000 psi and 4% elongation; 7.0%, by weight, of phthalocyanine; 45.0%, by weight, of toluene; 27.0%, by weight, of n-propyl acetate; and 3.0%, by weight, of a synthetic amorphous silica.

16. The method as claimed in claim 1 wherein said non-ceramic screen ink comprises 21.0%, by weight, of an isobutyl methacrylate resin having an inherent viscosity of 0.64 as measured in a solution containing 0.25 g of polymer in 50 ml methylene chloride, measured at 20°C using a No. 50 Cannon-Fenske Viscometer; 7.0%, by weight, of phthalocyanine; 36.0%, by weight, of toluene; 33.0%, by weight, of methyl ethyl ketone; and 3.0%, by weight, of a synthetic amorphous silica.

17. The method as claimed in claim 1 wherein said non-ceramic screen ink comprises an organic resinous binder.

18. The method as claimed in claim 17 is selected from the group consisting of one or more of polyamide, polyester, polyester-vinyl, acrylic, vinyl and acrylic-vinyl binders.

19. The method as claimed in claim 1 wherein said non-ceramic screen ink comprises a non-heavy metal colorant.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US98/13428

A. CLASSIFICATION OF SUBJECT MATTER		
IPC(6) : BO5D 1/32, 3/02; B32B 17/06 US CL : 427/ 282, 372.2; 428/426 According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED		
Minimum documentation searched (classification system followed by classification symbols) U.S. : 427/ 282, 372.2; 428/426; 101/129; 106/31.05, 31.49, 31.58, 31.78, 31.86; 524/88, 560, 601, 847		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched Hawley's Condensed Chemical Dictionary		
Electronic data base consulted during the international search (name of data base and, where practicable, search terms used) Please See Extra Sheet.		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 3,872,044 A (HERVEY et al) 18 March 1975, columns 3-4.	1-19
Y	US 5,549,929 A (SCHEIBELHOFFER et al) 27 August 1996, columns 1-3.	3-6,18
Y	US 3,920,469 A (KIENZLE et al) 18 November 1975, col. 1, lines 21-41.	7-10,15
Y	US 3,961,965 A (ZWAHLEN) 08 June 1976, columns 6-9.	15
Y	US 4,057,436 A (DAVIES et al) 08 November 1977, col. 3, lines 25-42 and col. 9, lines 19-51, table 2.	16
Y	LEWIS, R.J., Sr. "Hawley's Condensed Chemical Dictionary", 13th Edition, pages 995-996.	16
<input checked="" type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.		
* Special categories of cited documents:	*T	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
A document defining the general state of the art which is not considered to be of particular relevance	*X*	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
E earlier document published on or after the international filing date	*Y*	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*&*	document member of the same patent family
O document referring to an oral disclosure, use, exhibition or other means		
P document published prior to the international filing date but later than the priority date claimed		
Date of the actual completion of the international search 22 JULY 1998	Date of mailing of the international search report 14 OCT 1998	
Name and mailing address of the ISA/US Commissioner of Patents and Trademarks Box PCT Washington, D.C. 20231 Facsimile No. (703) 305-3230	Authorized officer <i>Fred J. Parker</i> FRED J. PARKER Telephone No. (703) 308-0661	

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US98/13428

B. FIELDS SEARCHED

Electronic data bases consulted (Name of data base and where practicable terms used):

APS

search terms: glass, ceramic, screen print###, resin binder#, polyamide, (co)polyester, titanium dioxide, phthalocyanine, n-propyl acetate