



US00RE40787E

(19) **United States**
(12) **Reissued Patent**
Martin et al.

(10) **Patent Number:** **US RE40,787 E**
(45) **Date of Reissued Patent:** **Jun. 23, 2009**

(54) **MULTILAYER PLASTIC SUBSTRATES**

FOREIGN PATENT DOCUMENTS

(75) Inventors: **Peter M. Martin**, Kennewick, WA (US);
Gordon L. Graff, West Richland, WA
(US); **Mark E. Gross**, Pasco, WA (US);
Michael G. Hall, West Richland, WA
(US); **Eric S. Mast**, Richland, WA (US)

BE	704297	2/1968
CA	2353506 A1	5/2000
DE	196 03 746 A1	4/1997
DE	696 15 510 T2	5/2002
EP	0 147 696 B1	7/1985
EP	0 299 753 A2	1/1989
EP	0 299 753	1/1989
EP	0 340 935	11/1989
EP	0 340 935 A2	11/1989
EP	0 390 540 B1	3/1990

(73) Assignee: **Battelle Memorial Institute**, Columbus,
OH (US)

(21) Appl. No.: **10/889,640**

(Continued)

(22) Filed: **Jul. 12, 2004**

OTHER PUBLICATIONS

Related U.S. Patent Documents

Reissue of:

(64) Patent No.: **6,623,861**
Issued: **Sep. 23, 2003**
Appl. No.: **09/835,768**
Filed: **Apr. 16, 2001**

U.S. Applications:

(63) Continuation-in-part of application No. 09/427,138, filed on
Oct. 25, 1999, now Pat. No. 6,522,067.

(51) **Int. Cl.**
B32B 27/36 (2006.01)

(52) **U.S. Cl.** **428/412**; 428/411.1; 428/480;
428/473.5; 428/474.4; 428/421; 430/58

(58) **Field of Classification Search** 428/412,
428/411.1, 480, 473.5, 474.4, 421; 430/58
See application file for complete search history.

Clark I. Bright, et al., Transparent Barrier Coatings Based on
ITO for Flexible Plastic Displays, Oct. 17-19, 1999, pp.
247-264, Tucson, Arizona.

Akedo et al., "LP-5: Lake-News Poster: Plasma-CVD
SiNx/Plasma-Polymerized CNx:H Multi-layer Passivation
Films for Organic Light Emmitting Diodes", SID 03 Digest.*
Chwang et al., "Thin Film encapsulated flexible organic
electroluminescent displays", American Institute of Physics,
2003.*

Notification of Transmittal of the International Search
Report Or The Declaration, Mar. 3, 2000, PCT/US99/29853.
Graupner, W. et al.; "High Resolution Color Organic Light
Emitting Diode Microdisplay Fabrication Method", SPIE
Proceedings 4207; 11-19 (2000); pp. 1-9.

(Continued)

Primary Examiner—Milton I. Cano
Assistant Examiner—Tamra L. Dicus
(74) *Attorney, Agent, or Firm*—Dinsmore & Shohl LLP

(56) **References Cited**

(57) **ABSTRACT**

U.S. PATENT DOCUMENTS


2,382,432 A	8/1945	McManus et al.
2,384,500 A	9/1945	Stoll
3,475,307 A	10/1969	Karl-Heinz et al.
3,607,365 A	9/1971	Lindlof
3,941,630 A	3/1976	Larrabee
4,061,835 A	12/1977	Pope et al.

A multilayer plastic substrate. The substrate comprises a
plurality of thin film layers of at least one polymer, the plu-
rality of thin film layers being adjacent to one another and
having sufficient strength to be self-supporting, wherein the
multilayer plastic substrate has an average visible light trans-
mittance of greater than about 80%.

(Continued)

23 Claims, 1 Drawing Sheet

100



U.S. PATENT DOCUMENTS					
4,098,965 A	7/1978	Kinsman	5,731,661 A	3/1998	So et al.
4,266,223 A	5/1981	Frame	5,736,207 A	4/1998	Walther et al.
4,283,482 A	8/1981	Hattori et al.	5,747,182 A	5/1998	Friend et al.
4,313,254 A	2/1982	Feldman et al.	5,757,126 A	5/1998	Harvey, et al.
4,426,275 A	1/1984	Meckel et al.	5,759,329 A	6/1998	Krause et al.
4,521,458 A	6/1985	Nelson	5,771,177 A	6/1998	Tada et al.
4,537,814 A	8/1985	Itoh et al.	5,771,562 A	6/1998	Harvey, III et al.
4,555,274 A	11/1985	Kitajima et al.	5,782,355 A	7/1998	Katagiri et al.
4,557,978 A	12/1985	Mason	5,792,550 A	8/1998	Phillips et al.
4,572,845 A	2/1986	Christen	5,795,399 A	8/1998	Hasegawa et al.
4,581,337 A	4/1986	Frey et al.	5,811,177 A	9/1998	Shi et al.
4,624,867 A	11/1986	Iijima et al.	5,811,183 A	9/1998	Shaw et al.
4,695,618 A	9/1987	Mowrer	5,821,138 A	10/1998	Yamazaki et al.
4,710,426 A	12/1987	Stephens	5,821,692 A	10/1998	Rogers et al.
4,722,515 A	2/1988	Ham	5,844,363 A	12/1998	Gu et al.
4,768,666 A	9/1988	Kessler	5,869,791 A	2/1999	Young
4,842,893 A	6/1989	Yializis et al.	5,872,355 A	2/1999	Hueschen
4,843,036 A	6/1989	Schmidt et al.	5,891,554 A	4/1999	Hosokawa et al.
4,854,186 A	8/1989	Grolig et al.	5,895,228 A	4/1999	Biebuyck et al.
4,855,186 A	8/1989	Grolig et al.	5,902,641 A	5/1999	Affinito et al.
4,889,609 A	12/1989	Cannella	5,902,688 A	5/1999	Antoniadis et al.
4,913,090 A	4/1990	Harada et al.	5,904,958 A	5/1999	Dick et al.
4,931,158 A	6/1990	Bunshah et al.	5,912,069 A	6/1999	Yializis et al.
4,934,315 A	6/1990	Linnebach et al.	5,919,328 A	7/1999	Tropsha et al.
4,954,371 A	9/1990	Yializis	5,920,080 A	7/1999	Jones
4,977,013 A	12/1990	Ritchie et al.	5,922,161 A	7/1999	Wu et al.
5,032,461 A	7/1991	Shaw et al.	5,929,562 A	7/1999	Pichler
5,036,249 A	7/1991	Pike-Bieganski et al.	5,934,856 A	8/1999	Asakawa et al.
5,047,131 A	9/1991	Wolfe et al.	5,945,174 A	8/1999	Shaw et al.
5,059,861 A	10/1991	Littman et al.	5,948,552 A	9/1999	Antoniadis et al.
5,124,204 A	6/1992	Yamashita et al.	5,952,778 A	9/1999	Haskal et al.
5,189,405 A	2/1993	Yamashita et al.	5,955,161 A	9/1999	Tropsha
5,203,898 A	4/1993	Carpenter et al.	5,965,907 A	10/1999	Huang et al.
5,204,314 A	4/1993	Kirlin et al.	5,968,620 A	10/1999	Harvey et al.
5,237,439 A	8/1993	Misono et al.	5,994,174 A	11/1999	Carey et al.
5,260,095 A	11/1993	Affinito	5,996,498 A	12/1999	Lewis
5,336,324 A	8/1994	Stall et al.	6,013,337 A	1/2000	Knors
5,354,497 A	10/1994	Fukuchi et al.	6,040,017 A	3/2000	Mikhael et al.
5,356,947 A	10/1994	Ali et al.	6,045,864 A	4/2000	Lyons et al.
5,376,467 A	12/1994	Abe et al.	6,066,826 A	5/2000	Yializis
5,393,607 A	2/1995	Kawasaki et al.	6,083,313 A	7/2000	Venkatraman et al.
5,395,644 A	3/1995	Affinito	6,083,628 A	7/2000	Yializis
5,402,314 A	3/1995	Amago et al.	6,084,702 A	7/2000	Byker et al.
5,427,638 A	6/1995	Goetz et al.	6,087,007 A	7/2000	Fujii et al.
5,440,446 A	8/1995	Shaw et al.	6,092,269 A	7/2000	Yializis et al.
5,451,449 A	9/1995	Shetty et al.	6,106,627 A	8/2000	Yializis
5,461,545 A	10/1995	Leroy et al.	6,117,266 A	9/2000	Horzel et al.
5,464,667 A	11/1995	Kohler et al.	6,118,218 A	9/2000	Yializis et al.
5,510,173 A	4/1996	Pass et al.	6,146,225 A	11/2000	Sheats et al.
5,512,320 A	4/1996	Turner et al.	6,146,462 A	11/2000	Yializis et al.
5,536,323 A	7/1996	Kirlin et al.	6,150,187 A	11/2000	Zyung et al.
5,547,508 A	8/1996	Affinito	6,165,566 A	12/2000	Tropsha
5,554,220 A	9/1996	Forrest et al.	6,178,082 B1	1/2001	Farooq et al.
5,576,101 A	11/1996	Saitoh et al.	6,195,142 B1	2/2001	Gyotoku et al.
5,578,141 A	11/1996	Mori et al.	6,198,217 B1	3/2001	Suzuki et al.
5,607,789 A	3/1997	Treger et al.	6,198,220 B1	3/2001	Jones et al.
5,620,524 A	4/1997	Fan et al.	6,203,898 B1	3/2001	Kohler et al.
5,629,389 A	5/1997	Roitman et al.	6,207,238 B1	3/2001	Affinito
5,652,192 A	7/1997	Matson et al.	6,207,239 B1	3/2001	Affinito
5,654,084 A	8/1997	Egert	6,214,422 B1	4/2001	Yializis
5,660,961 A	8/1997	Yu	6,217,947 B1	4/2001	Affinito
5,665,280 A	9/1997	Tropsha	6,224,948 B1	5/2001	Affinito
5,681,615 A	10/1997	Affinito et al.	6,228,434 B1	5/2001	Affinito
5,681,666 A	10/1997	Treger et al.	6,228,436 B1	5/2001	Affinito
5,684,084 A	11/1997	Lewin et al.	6,231,939 B1	5/2001	Shaw et al.
5,686,360 A	11/1997	Harvey, III et al.	6,264,747 B1	7/2001	Shaw et al.
5,693,956 A	12/1997	Shi et al.	6,268,695 B1	7/2001	Affinito
5,695,564 A	12/1997	Imahashi	6,274,204 B1	8/2001	Affinito
5,711,816 A	1/1998	Kirlin et al.	6,322,860 B1	11/2001	Stein et al.
5,725,909 A	3/1998	Shaw et al.	6,333,065 B1	12/2001	Arai et al.
			6,348,237 B2	2/2002	Kohler et al.

US RE40,787 E

Page 3

6,350,034	B1	2/2002	Fleming et al.	7,015,640	B2	3/2006	Schaepkens et al.
6,352,777	B1	3/2002	Bulovic et al.	7,018,713	B2	3/2006	Padiyath et al.
6,358,570	B1	3/2002	Affinito	7,029,765	B2	4/2006	Kwong et al.
6,361,885	B1	3/2002	Chou	7,033,850	B2	4/2006	Tyan et al.
6,397,776	B1	6/2002	Yang et al.	7,056,584	B2	6/2006	Iacovangelo
6,413,645	B1	7/2002	Graff et al.	7,086,918	B2	8/2006	Hsiao et al.
6,416,872	B1	7/2002	Maschwitz	7,122,418	B2	10/2006	Su et al.
6,420,003	B2	7/2002	Shaw et al.	7,156,942	B2	1/2007	McCormick et al.
6,436,544	B1	8/2002	Veyrat et al.	7,166,007	B2	1/2007	Auch et al.
6,460,369	B2	10/2002	Hosokawa	7,183,197	B2	2/2007	Won et al.
6,465,953	B1	10/2002	Duggal	7,186,465	B2	3/2007	Bright
6,468,595	B1	10/2002	Mikhael et al.	7,221,093	B2	5/2007	Auch et al.
6,469,437	B1	10/2002	Parthasarathy et al.	7,255,823	B1	8/2007	Guenther et al.
6,492,026	B1	12/2002	Graff et al.	2001/0015074	A1	8/2001	Hosokawa
6,497,598	B2	12/2002	Affinito	2001/0015620	A1	8/2001	Affinito
6,497,924	B2	12/2002	Affinito et al.	2002/0022156	A1	2/2002	Bright
6,509,065	B2	1/2003	Affinito	2002/0025444	A1	2/2002	Hebgrink et al.
6,512,561	B1	1/2003	Terashiat et al.	2002/0068143	A1	6/2002	Silvernail et al.
6,522,067	B1	2/2003	Graff et al.	2002/0069826	A1	6/2002	Hunt et al.
6,537,688	B2	3/2003	Silvernail et al.	2002/0102363	A1	8/2002	Affinitio et al.
6,544,600	B2	4/2003	Affinito et al.	2002/0102818	A1	8/2002	Sandhu et al.
6,548,912	B1	4/2003	Graff et al.	2002/0125822	A1	9/2002	Graff et al.
6,569,515	B2	5/2003	Hebrink et al.	2002/0139303	A1	10/2002	Yamazaki et al.
6,570,325	B2	5/2003	Graff et al.	2002/0140347	A1	10/2002	Weaver
6,573,652	B1	6/2003	Graff et al.	2003/0038590	A1	2/2003	Silvernail et al.
6,576,351	B2	6/2003	Silvernail	2003/0045021	A1	3/2003	Akai
6,592,969	B1	7/2003	Burroughes et al.	2003/0085652	A1	5/2003	Weaver
6,597,111	B2	7/2003	Silvernail et al.	2003/0098647	A1	5/2003	Silvernail
6,613,395	B2	9/2003	Affinito et al.	2003/0117068	A1	6/2003	Forrest et al.
6,614,057	B2	9/2003	Silvernail et al.	2003/0124392	A1	7/2003	Bright
6,624,568	B2	9/2003	Silvernail et al.	2003/0127973	A1	7/2003	Weaver et al.
6,627,267	B2	9/2003	Affinito	2003/0134487	A1	7/2003	Breen et al.
6,628,071	B1	9/2003	Su	2003/0184222	A1	10/2003	Nilsson et al.
6,653,780	B2	11/2003	Sugimoto et al.	2003/0197197	A1	10/2003	Brown et al.
6,656,537	B2	12/2003	Affinito et al.	2003/0218422	A1	11/2003	Park et al.
6,660,409	B1	12/2003	Komatsu et al.	2003/0235648	A1	12/2003	Affinito et al.
6,664,137	B2	12/2003	Weaver	2004/0029334	A1	2/2004	Bijker et al.
6,681,716	B2	1/2004	Schaepkens	2004/0046497	A1	3/2004	Schaepkens et al.
6,720,203	B2	4/2004	Carcia et al.	2004/0071971	A1	4/2004	Iacovangelo
6,734,625	B2	5/2004	Vong et al.	2004/0113542	A1	6/2004	Hslao et al.
6,737,753	B2	5/2004	Kumar et al.	2004/0115402	A1	6/2004	Schaepkens
6,743,524	B2	6/2004	Schaepkens	2004/0115859	A1	6/2004	Murayama et al.
6,749,940	B1	6/2004	Terasaki et al.	2004/0119028	A1	6/2004	McCormick et al.
6,765,351	B2	7/2004	Forrest et al.	2004/0175512	A1	9/2004	Schaepkens
6,803,245	B2	10/2004	Auch et al.	2004/0175580	A1	9/2004	Schaepkens
6,811,829	B2	11/2004	Affinito et al.	2004/0209090	A1	10/2004	Iwanaga
6,815,887	B2	11/2004	Lee et al.	2004/0219380	A1	11/2004	Naruse et al.
6,818,291	B2	11/2004	Funkenbusch et al.	2004/0229051	A1	11/2004	Schaepkens et al.
6,835,950	B2	12/2004	Brown et al.	2004/0241454	A1	12/2004	Shaw et al.
6,836,070	B2	12/2004	Chung et al.	2004/0263038	A1	12/2004	Ribotzi et al.
6,837,950	B1	1/2005	Berard	2005/0003098	A1	1/2005	Kohler et al.
6,864,629	B2	3/2005	Miyaguchi et al.	2005/0006786	A1	1/2005	Sawada
6,866,901	B2	3/2005	Burrows et al.	2005/0051094	A1	3/2005	Schaepkens et al.
6,867,539	B1	3/2005	McCormick et al.	2005/0079295	A1	4/2005	Schaepkens
6,872,114	B2	3/2005	Chung et al.	2005/0079380	A1	4/2005	Iwanaga
6,872,248	B2	3/2005	Mizutani et al.	2005/0093001	A1	5/2005	Liu et al.
6,872,428	B2	3/2005	Yang et al.	2005/0093437	A1	5/2005	Ouyang
6,878,467	B2	4/2005	Chung et al.	2005/0094394	A1	5/2005	Padiyath et al.
6,888,305	B2	5/2005	Weaver	2005/0095422	A1	5/2005	Sager et al.
6,888,307	B2	5/2005	Silvernail et al.	2005/0095736	A1	5/2005	Padiyath et al.
6,891,330	B2	5/2005	Duggal et al.	2005/0112378	A1	5/2005	Naruse et al.
6,897,474	B2	5/2005	Brown et al.	2005/0115603	A1	6/2005	Yoshida et al.
6,897,607	B2	5/2005	Sugimoto et al.	2005/0122039	A1	6/2005	Satani
6,905,769	B2	6/2005	Komada	2005/0129841	A1	6/2005	McCormick et al.
6,923,702	B2	8/2005	Graff et al.	2005/0133781	A1	6/2005	Yan et al.
6,936,131	B2	8/2005	McCormick et al.	2005/0140291	A1	6/2005	Hirakata et al.
6,975,067	B2	12/2005	McCormick et al.	2005/0146267	A1	7/2005	Lee et al.
6,994,933	B1	2/2006	Bates	2005/0174045	A1	8/2005	Lee et al.
6,998,648	B2	2/2006	Silvernail	2005/0202646	A1	9/2005	Burrows et al.
7,002,294	B2	2/2006	Forrest et al.	2005/0212419	A1	9/2005	Vazan et al.
7,012,363	B2	3/2006	Weaver et al.	2005/0224935	A1	10/2005	Schaepkens et al.

2005/0238846	A1	10/2005	Arakatsu et al.	JP	09-161967	6/1997
2006/0001040	A1	1/2006	Kim et al.	JP	9-161967	6/1997
2006/0003474	A1	1/2006	Tyan et al.	JP	9-201897	8/1997
2006/0028128	A1	2/2006	Ohkubo	JP	09-232553	9/1997
2006/0061272	A1	3/2006	McCormick et al.	JP	10-725	1/1998
2006/0062937	A1	3/2006	Padiyath et al.	JP	10-013083	1/1998
2006/0063015	A1	3/2006	McCormick et al.	JP	10-016150	1/1998
2006/0132461	A1	6/2006	Furukawa et al.	JP	H10-41067	2/1998
2006/0246811	A1	11/2006	Winters et al.	JP	10-334744	12/1998
2006/0250084	A1	11/2006	Cok et al.	JP	11-017106	1/1999
2006/0291034	A1	12/2006	Patry et al.	JP	11-040344	2/1999
2007/0009674	A1	1/2007	Okubo et al.	JP	11-149826	6/1999
2007/0281089	A1	12/2007	Heller et al.	JP	11-255923	9/1999

FOREIGN PATENT DOCUMENTS

EP	0 390 540	10/1990		JP	2000-058258	2/2000
EP	0 468 440	A2	1/1992	JP	2002/505969	2/2002
EP	0 547 550		6/1993	JP	10312883	3/2002
EP	0 547 550	A1	6/1993	JP	2003/282239	10/2003
EP	0 590 467		4/1994	JP	3579556	B2 10/2004
EP	0 590 467	A1	4/1994	JP	2006-294780	10/2006
EP	0 722 787		7/1996	WO	WO 87/07848	12/1987
EP	0 722 787	A2	7/1996	WO	WO 89/00337	1/1989
EP	0 777 280	B1	6/1997	WO	WO 95/10117	5/1995
EP	0 777 280	A2	6/1997	WO	WO 96/23217	8/1996
EP	0 777 281	A2	6/1997	WO	WO 97/04885	2/1997
EP	0 787 824	A2	8/1997	WO	WO 97/16053	5/1997
EP	0 787 826	A1	8/1997	WO	WO 97/22631	6/1997
EP	0 787 826		8/1997	WO	WO 98/10116	3/1998
EP	0 915 105	A1	5/1999	WO	WO 98/18852	5/1998
EP	0 916 394	A2	5/1999	WO	WO 99/16557	4/1999
EP	0 916 394		5/1999	WO	WO 99/16931	4/1999
EP	0 931 850	A1	7/1999	WO	WO 99/46120	9/1999
EP	0 931 850		7/1999	WO	WO 00/26973	5/2000
EP	0 977 469		2/2000	WO	WO 00/35603	6/2000
EP	0 977 469	A2	2/2000	WO	WO 00/35604	6/2000
EP	1 021 070	A1	7/2000	WO	WO 00/35993	6/2000
EP	1 127 381	A1	8/2001	WO	WO 00/36661	6/2000
EP	1 130 420	A2	9/2001	WO	WO 00/36665	6/2000
EP	1 278 244	A2	1/2003	WO	WO 00/53423	A1 9/2000
EP	1 426 813	A2	6/2004	WO	WO 01 68360	A 9/2001
EP	1 514 317	A1	3/2005	WO	WO 01/68360	A1 9/2001
GB	2 210 826	A	6/1989	WO	WO 01/81649	A1 11/2001
JP	S63-96895		4/1988	WO	WO 01/82336	A2 11/2001
JP	63136316		8/1988	WO	WO 01/82389	A1 11/2001
JP	64-18441		1/1989	WO	WO 01/87825	A1 11/2001
JP	S64-41192		2/1989	WO	WO 01/89006	A1 11/2001
JP	2-183230		7/1990	WO	WO 02/26973	A1 4/2002
JP	3-183759		8/1991	WO	WO 03/016589	A1 2/2003
JP	3-290375		12/1991	WO	WO 03/098716	A1 11/2003
JP	4-14440		1/1992	WO	WO 2004/006199	A2 1/2004
JP	4-48515		2/1992	WO	WO 2004/016992	A1 2/2004
JP	4-1440		4/1992	WO	WO 2004/070840	A1 8/2004
JP	H4-267097		9/1992	WO	WO 2004/089620	A2 10/2004
JP	05-217158		1/1993	WO	WO 2004/112165	A1 12/2004
JP	5-147678		6/1993	WO	WO 2005/015655	A1 2/2005
JP	H5-182759		7/1993	WO	WO 2005/045947	A2 5/2005
JP	61-36159		5/1994	WO	WO 2005/048368	A1 5/2005
JP	06158305		6/1994	WO	WO 2005/050754	A1 6/2005
JP	61-79644		6/1994	WO	WO 2006/036492	A1 4/2006
JP	6-234186		8/1994	WO	WO 2008/140313	11/2008
JP	07-074378		3/1995	WO	WO 2008/142645	11/2008
JP	H07-147189		6/1995			
JP	H7-192868		7/1995			
JP	8-72188		3/1996			
JP	H8-171988		7/1996			
JP	8-179292		7/1996			
JP	08325713		10/1996			
JP	8-318590		12/1996			
JP	09059763		4/1997			
JP	H9-132774		5/1997			

OTHER PUBLICATIONS

Norenberg, H. et al.; Comparative Study of Oxygen Permeation Through Polymers and Gas Barrier Films; Denver, Apr. 15–20, 2000; pp. 347–351; Society of Vacuum Coaters.
 Yializis, A. et al.; Ultra High Barrier Films; Denver, Apr. 15–20, 2000; pp. 404–407; Society of Vacuum Coaters.
 Mahon, J.K. et al.; Requirements of Flexible Substrates for Organic Light Emitting Devices in Flat Panel Display Applications; Society of Vacuum Coaters; 42nd Annual Technical Conference Proceedings; Apr. 1999; pp. 456–459.

- Henry, B.M. et al.; Microstructural and Gas Barrier Properties of Transparent Aluminum Oxide and Indium Tin Oxide Films; Denver, Apr. 15–20, 2000; pp. 373–378; Society of Vacuum Coaters.
- Affinito, J.D. et al.; Vacuum Deposited Polymer/metal Multilayer Films for Optical Applications; Paper No. C1.13; International Conference on Metallurgical Coatings; Apr. 15–21, 1995; pp. 1–14.
- Affinito, J.D. et al.; Vacuum Deposition of Polymer Electrolytes On Flexible Substrates; The Ninth International Conference on Vacuum Web Coating; 1995; pp. 20–37.
- Affinito, J.D. et al.; Vacuum Deposition of Polymer Electrolytes On Flexible Substrates; The Ninth International Conference on Vacuum Web Coating; 1995; pp. 0–16.
- Affinito, J.D. et al.; Molecularly Doped Polymer Composite Films for Light Emitting Polymer Application Fabricated by the PML Process; 41st Technical Conference of the Society of Vacuum Coaters; Apr. 1998; pp. 220–225.
- Affinito, J.D. et al., PML/Oxide/PML Barrier Layer Performance Differences Arising From Use Of UV Or Electron Beam Polymerization Of The PML Layers, SVC 40th Annual Technical Conference, Apr. 12–17, 1997, pp. 19–25.
- Affinito, J.D. et al.; Polymer/Polymer, Polymer/Oxide, and Polymer/Metal Vacuum Deposited Interference Filters; Tenth International Vacuum Web Coating Conference; Nov. 1996; pp. 0–14.
- Felts, J.T.; Transparent Barrier Coatings Update: Flexible Substrates; Society of Vacuum Coaters; 36th Annual Technical Conference Proceedings; Apr. 25–30, 1993; pp. 324–331.
- Affinito, J.D. et al.; Ultra High Rate, Wide Area, Plasma Polymerized Films from High Molecular Weight/Low Vapor Pressure Liquid or Solid Monomer Precursors; 45th International Symposium of the American Vacuum Society; Nov. 2–6, 1998; pp. 0–26.
- Tropsha et al.; Combinatorial Barrier Effect of the Multilayer SiOx Coatings on Polymer Substrates; 1997 Society of Vacuum Coaters; 40th Annual Technical Conference Proceedings; Apr. 12–17, 1997; pp. 64–69.
- Tropsha et al., Activated Rate Theory Treatment of Oxygen and Water Transport through Silicon Oxide/Poly(ethylene terephthalate) Composite Barrier Structures; J. Phys. Chem B Mar. 1997; pp. 2259–2266.
- Affinito, J.D. et al.; Vacuum Deposited Conductive Polymer Films; The Eleventh International Conference on Vacuum Web Coating; Nov. 9–11, 1997; pp. 0–12.
- De Gryse, R. et al.; Sputtered Transparent Barrier Layers, Tenth International Conference on Vacuum Web Coating, Nov. 1996, pp. 190–198.
- Hibino, N. et al.; Transparent Barrier Al₂O₃ Coating By Activated Reactive Evaporation; Thirteenth International Conference on Vacuum Web Coating; Oct. 17–19, 1999; pp. 234–245.
- Kukla, R. et al.; Transparent Barrier Coatings with EB-Evaporation, an Update; Section Five; Transparent Barrier Coating Papers; Thirteenth International Conference on Vacuum Web Coating; Oct. 17–19, 1999; pp. 222–233.
- Bright, Clark I.; Transparent Barrier Coatings Based on ITO for Flexible Plastic Displays; Thirteenth International Conference on Vacuum Web Coating; Oct. 17–19, 1999; pp. 247–255.
- Henry, B.M. et al.; Microstructural Studies of Transparent Gas Barrier Coatings on Polymer Substrates; Thirteenth International Conference on Vacuum Web Coating; Oct. 17–19, 1999; pp. 265–273.
- Affinito, J.D. et al.; Ultra High Rate, Wide Area, Plasma Polymerized Films from High Molecular Weight/Low Vapor Pressure Liquid or Liquid/Solid Suspension Monomer Precursors; MRS Conference; Nov. 29–Dec. 3, 1998; Paper No. Y12.1
- Affinito, J.D. et al., “Molecularly Doped Polymer Composite Films for Light Emitting Polymer Applications Fabricated by the PML Process” 41st Technical Conference of Society of Vacuum Coaters, Apr. 1998, pp. 1–6.
- Affinito, J.D. et al., “Vacuum Deposition of Polymer Electrolytes on Flexible Substrates” The Ninth International Conference on Vacuum Web Coating, pp. 0–16.
- Bunshah, R.F. et al., “Deposition Technologies for Films and Coatings” Noyes Publications, Park Ridge, New Jersey, 1982, p. 339.
- Affinito, J.D., Energy Res. Abstr. 18(6), #17171, 1993.
- Graupner, W. et al.; “High Resolution Color Organic Light Emitting Diode Microdisplay Fabrication Method”, SPIE Proceedings, Nov. 6, 2000; pp. 11–19.
- Czeremuszkin, G. et al.; Permeation Through Defects in Transparent Barrier Coated Plastic Films; 43rd Annual Technical Conference Proceedings; Apr. 15, 2000; pp. 408–413.
- Affinito, J.D. et al.; Vacuum Deposited Conductive Polymer Films; The Eleventh International Conference on Vacuum Web Coatings, pp. 1–12.
- Vossen, J.L. et al.; Thin Film Processes; Academic Press, 1978, Part II, Chapter II–1, Glow Discharge Sputter Deposition, pp. 12–63; Part IV, Chapter IV–1 Plasma Deposition of Inorganic Compounds and Chapter IV–2 Glow Discharge Polymerization, pp. 335–397.
- Affinito, J.D. et al.; Ultra High Rate, Wide Area, Plasma Polymerized Films from High Molecular Weight/Low Vapor Pressure Liquid or Solid Monomer Precursors; 45th International Symposium of the American Vacuum Society; pp. 0–26.
- G. Gustafson, et al.; Flexible light-emitting diodes made from soluble conducting polymers; Letters to Nature; vol. 357; Jun. 11, 1992; pp. 477–479.
- Tropsha et al.; Combinatorial Barrier Effect of the Multilayer SiOx Coatings on Polymer Substrates; 1997 Society of Vacuum Coaters, 40th Annual Technical Conferences Proceedings; pp. 64–69.
- Tropsha et al.; Activated Rate Theory Treatment of Oxygen and Water Transport through Silicon Oxide/Poly(ethylene terephthalate) Composite Barrier Structures; J. Phys. Chem B 1997 pp. 2259–2266.
- F.M. Penning; Electrical Discharges in Gases; 1965; pp. 1–51; Gordon and Breach, Science Publishers, New York–London–Paris.
- Affinito, J.D. et al.; High Rate Vacuum Deposition of Polymer Electrolytes; Journal Vacuum Science Technology A 14(3), May/June 1996.
- Affinito, J.D. et al.; Vacuum Deposited Polymer/metal Multilayer Films for Optical Applications; Paper No. C1.13; pp. 1–14.
- Shi, M.K. et al.; Plasma treatment of PET and acrylic coating surfaces—I. In situ XPS measurements; Journal of Adhesion Science and Technology; Mar. 2000 14(12); pp. 1–8.

- Affinito, J.D. et al.; Vacuum Deposition of Polymer Electrolytes On Flexible Substrates, The Ninth International Conference on Vacuum Web Coating; pp. 20–37.
- Affinito, J.D. et al.; Ultrahigh Rate, Wide Area, Plasma Polymerized Films from High Molecular Weight/Low Vapor Pressure Liquid or Solid Monomer Precursors; *Journal Vacuum Science Technology A* 17(4); Jul./Aug. 1999; pp. 1974–1981; American Vacuum Society.
- Shi, M.K. et al.; In situ and real-time monitoring of plasma-induced etching PET and acrylic films, *Plasmas and Polymers*; Dec. 1999, 494); pp. 1–25.
- Affinito, J.D. et al.; Vacuum Deposited Conductive Polymer Films; The Eleventh International Conference on Vacuum Web Coating; pp. 0–12.
- Affinito, J.D. et al.; Molecularly Doped Polymer Composite Films for Light Emitting Polymer Application Fabricated by the PML Process; 41st Technical Conference of the Society of Vacuum Coaters; 1998; pp. 220–225.
- Affinito, J.D. et al.; Polymer/polymer, Polymer/Oxide, and Polymer/Metal Vacuum Deposited Interference Filters; Tenth International Vacuum Web Coating Conference; pp. 0–14.
- Affinito, J.D. et al.; Vacuum Deposited Polymer/Metal Multilayer Films for Optical Application; *Thin Solid Films* 270, 1995; pp. 43–48.
- Felts, J.T.; Transparent Barrier Coatings Update: Flexible Substrates; pp. 324–331.
- Mahon, J.K., et al.; Requirements of Flexible Substrates for Organic Light Emitting Devices in Flat Panel Display Applications, Society of Vacuum Coaters, 42nd Annual Technical Conference Proceedings, 1999, pp. 456–459.
- Henry, B.M. et al.; Microstructural and Gas Barrier Properties of Transparent Aluminium Oxide and Indium Tin Oxide Films; 2000; pp. 373–378; Society of Vacuum Coaters.
- Phillips, R.W.; Evaporated Dielectric Colorless Films on PET and Opp Exhibiting High Barriers Toward Moisture and Oxygen; Society of Vacuum Coaters; 36th Annual Technical Conference Proceedings; 1993; pp. 293–300.
- Yamada, Y. et al.; The Properties of a New Transparent and Colorless Barrier Film; 1995; pp. 28–31; Society of Vacuum Coaters.
- Chahroudi, D.; Transparent Glass Barrier Coatings for Flexible Film Packaging; 1991; pp. 130–133; Society of Vacuum Coaters.
- Bright, Clark, I.; Transparent Barrier Coatings Based on ITO for Flexible Plastic Displays; pp. 247–255.
- Henry, B.M. et al.; Microstructural Studies of Transparent Gas Barrier Coatings on Polymer Substrates; pp. 265–273.
- Hibino, N. et al.; Transparent Barrier Al₂O₃ Coating By Activated Reactive Evaporation; pp. 234–245.
- Kukla, R. et al.; Transparent Barrier Coatings with EB-Evaporation, an Update; Section Five; Transparent Barrier Coating Papers; pp. 222–233.
- Krug, T. et al.; New Developments in Transparent Barrier Coatings; 1993; pp. 302–305; Society Vacuum Coaters.
- Affinito, J.D. et al.; PML/Oxide/PML Barrier Layer Performance Differences Arising From Use Of UV or Electron Beam Polymerization of the PML Layers; *Thin Solid Films*; Elsevier Science S.A.; vol. 308–309; Oct. 31, 1997; pp. 19–25.
- Affinito, J.D. et al.; A new method for fabricating transparent barrier layers, *Thin Solid Films* 290–291; 1996; pp. 63–67.
- Affinito, J.D. et al.; Polymer–Oxide Transparent Barrier Layers; SVC 39th Annual Technical Conference; Vacuum Web Coating Session; 1996; pp. 392–397.
- Hoffmann, G. et al.; Transparent Barrier Coatings by Reactive Evaporation; 1994; pp. 155–160; Society of Vacuum Coaters.
- Norenberg, H. et al.; Comparative Study of Oxygen Permeation Through Polymers and Gas Barrier Films; 2000; pp. 347–351; Society of Vacuum Coaters.
- Yializis, A. et al.; Ultra High Barrier Films; 2000; pp. 404–407; Society Vacuum Coaters.
- Klemberg–Sapieha, J.E. et al.; Transparent Gas Barrier Coatings Produced by Dual–Frequency PECVD; 1993; pp. 445–449; Society of Vacuum Coaters.
- Finson, E. et al.; Transparent SiO₂ Barrier Coatings: Conversion and Production Status; 1994; pp. 139–143; Society of Vacuum Coaters.
- Yializis, A. et al.; High Oxygen Barrier Polypropylene Films Using Transparent Acrylate–Al₂O₃ and Opaque Al–Acrylate Coatings; 1995; pp. 95–102; Society of Vacuum Coaters.
- Shaw, D.G. et al.; Use of Vapor Deposited Acrylate Coatings to Improve the Barrier Properties of Metalized Film; 1994; pp. 240–244; Society of Vacuum Coaters.
- Wong, F.L., et al., “Long–lifetime thin–film encapsulated organic light–emitting diodes,” *Journal of Applied Physics* 104, pp. 014509–1–4 (2008).

* cited by examiner




FIG. 1

MULTILAYER PLASTIC SUBSTRATES

Matter enclosed in heavy brackets [] appears in the original patent but forms no part of this reissue specification; matter printed in italics indicates the additions made by reissue.

This application is a continuation-in-part of U.S. patent application Ser. No. 09/427,138, filed Oct. 25, 1999, entitled "Environmental Barrier Material For Organic Light Emitting Device and Method Of Making," now U.S. Pat. No. 6,522,067, issued Feb. 18, 2003.

BACKGROUND OF THE INVENTION

The present invention relates generally to plastic substrates which may be useful in products including, but not limited to, visual display devices, and more particularly to multilayer plastic substrates having improved light transmittance.

As used herein, the term "(meth)acrylic" is defined as "acrylic or methacrylic." Also, (meth)acrylate is defined as "acrylate or methacrylate."

As used herein, the term "average visible light transmittance" means the average light transmittance over the visible range from 400 to 800 nm.

As used herein, the term "peak visible light transmittance" means the peak light transmittance over the visible range from 400 to 800 nm.

As used herein, the term "polymer precursor" includes monomers, oligomers, and resins, and combinations thereof. As used herein, the term "monomer" is defined as a molecule of simple structure and low molecular weight that is capable of combining with a number of like or unlike molecules to form a polymer. Examples include, but are not limited to, simple acrylate molecules, for example, hexanedioldiacrylate, or tetraethyleneglycoldiacrylate, styrene, methyl styrene, and combinations thereof. The molecular weight of monomers is generally less than 1000, while for fluorinated monomers, it is generally less than 2000. Monomers may be combined to form oligomers and resins but do not combine to form other monomers.

As used herein, the term "oligomer" is defined as a compound molecule of at least two monomers that maybe cured by radiation, such as ultraviolet, electron beam, or x-ray, glow discharge ionization, and spontaneous thermally induced curing. Oligomers include low molecular weight resins. Low molecular weight is defined herein as about 1000 to about 20,000 exclusive of fluorinated monomers. Oligomers are usually liquid or easily liquifiable. Oligomers do not combine to form monomers.

As used herein, the term "resin" is defined as a compound having a higher molecular weight (generally greater than 20,000) which is generally solid with no definite melting point. Examples include, but are not limited to, polystyrene resins, epoxy polyamine resins, phenolic resins, and acrylic resins (for example, polymethylmethacrylate), and combinations thereof.

There is a need for versatile visual display devices for electronic products of many different types. Although many current displays use glass substrates, manufacturers have attempted to produce commercial products, primarily liquid crystal display devices, using unbreakable plastic substrates. These attempts have not been completely successful to date because of the quality, temperature, and permeation limitations of polymeric materials. Flexible plastic substrates,

such as polyethylene terephthalate (PET), polyethylene naphthalate (PEN), and polyether sulfone (PES), have been used in thicknesses from about 0.004 inches to 0.007 inches. However, the surface quality of these substrates is often poor, with the surface having large numbers of scratches, digs, pits, and other defects.

In addition, many polymers exhibit poor oxygen and water vapor permeation resistance, often several orders of magnitude below what is required for product performance. For example, the oxygen transmission rates for materials such polyethylene terephthalate (PET) are as high as 1550 cc/m²/day/micron of thickness (or 8.7 cc/m²/day for 7 mil thickness PET), and the water vapor transmission rates are also in this range. Certain display applications, such as those using organic light emitting devices (OLEDs), require encapsulation that has a maximum oxygen transmission rate of 10⁻⁴ to 10⁻² cc/m²/day, and a maximum water vapor transmission rate of 10⁻⁵ to 10⁻⁶ g/m²/day.

Barrier coatings have been applied to plastic substrates to decrease their gas and liquid permeability. Barrier coatings typically consist of single layer thin film inorganic materials, such as Al, SiO_x, AlO_x, and Si₃N₄ vacuum deposited on polymeric substrates. A single layer coating on PET reduces oxygen permeability to levels of about 0.1 to 1.0 cc/m²/day, and water vapor permeability of about 0.1 to 1.0 g/m²/day. However, those levels are still insufficient for many display devices.

Additionally, many processes used in the manufacture of displays require relatively high temperatures that most polymer substrates cannot tolerate. For example, the recrystallization of amorphous Si to poly-Si in thin film transistors requires substrate temperatures of at least 160°–250° C., even with pulsed excimer laser anneals. The conductivity of a transparent electrode, which is typically made of indium tin oxide (ITO), is greatly improved if deposition occurs above 220° C. Polyimide curing generally requires temperatures of 250° C. In addition, many of the photolithographic process steps for patterning electrodes are operated in excess of 120° C. to enhance processing speeds in the fabrication. These processes are used extensively in the manufacture of display devices, and they have been optimized on glass and silicon substrates. The high temperatures needed for such processes can deform and damage a plastic substrate, and subsequently destroy the display. If displays are to be manufactured on flexible plastic materials, the plastic must be able to withstand the necessary processing conditions, including high temperatures over 100° C., harsh chemicals, and mechanical damage.

Thus, there is a need for an improved plastic substrate for visual display devices, and for a method of making such a substrate.

SUMMARY OF THE INVENTION

The present invention meets this need by providing a multilayer plastic substrate. The substrate consists essentially of a plurality of thin film layers of at least one polymer, the plurality of thin films layers being adjacent to one another and having sufficient strength to be self-supporting, wherein the multilayer plastic substrate has an average visible light transmittance of greater than about 80%. The average visible light transmittance is typically greater than about 85%, and it can be greater than about 90%. The peak visible transmittance is typically greater than about 85% and it can be greater than about 90%.

There are typically at least about 50 thin film layers. The number of layers depends on the thickness of the thin film

layers and the desired overall thickness of the multilayer plastic substrate. The multilayer plastic substrate is typically at least about 0.001 inches thick, and generally at least about 0.004 inches thick. Each thin film layer is typically less than about 50 μm thick.

Polymers include, but are not limited to (meth)acrylate-containing polymers, styrene containing polymers, methyl styrene containing polymers, and fluorinated polymers, and combinations thereof. The glass transition temperature of the at least one polymer is generally greater than about 150° C., and it may be greater than about 200° C.

The surface roughness of the multilayer plastic substrate is generally less than about 10 nm, and it may be less than about 5 nm, or less than about 2 nm.

The multilayer plastic substrate can have a refractive index of greater than about 1.4 or greater than about 1.5.

The multilayer plastic substrate can include additional layers, including, but not limited to, scratch resistant layers, antireflective coatings, antifingerprint coatings, antistatic coatings, conductive coatings, transparent conductive coatings, and barrier coatings, to provide functionality to the substrate if desired.

Another aspect of the invention involves a method of making the multilayer plastic substrate. The method includes providing a support, depositing a plurality of thin film layers of at least one polymer on the support so that the plurality of thin film layers have sufficient strength to be self-supporting to form the multilayer substrate, and removing the support from the multilayer substrate, wherein the multilayer plastic substrate has an average visible light transmittance of greater than about 80%.

The thin film layers can be deposited in a vacuum. One example of a vacuum deposition process is flash evaporation. In this method, depositing the plurality of thin film layers includes flash evaporating a polymer precursor, condensing the polymer precursor as a liquid film, and cross-linking the polymer precursor to form the polymer. The polymer precursor can be cross-linked by any suitable method, including, but not limited to, radiation curing, such as ultraviolet, electron beam, or x-ray, glow discharge ionization, and spontaneous thermally induced curing.

Alternatively, the plurality of thin film layers can be deposited by extruding or casting a layer of polymer precursor, and cross-linking the polymer precursor to form the polymer using any suitable cross-linking method.

Accordingly, it is an object of the present invention to provide an improved, multilayer plastic substrate and to provide a method of making such a substrate.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a cross-section of one embodiment of the substrate of the present invention.

DESCRIPTION OF THE INVENTION

FIG. 1 shows one embodiment of a multilayer plastic substrate of the present invention. The multilayer plastic substrate **100** is formed on a support **110**. After the multilayer plastic substrate is formed, the support **110** is removed.

The multilayer plastic substrate of the present invention consists essentially of a plurality of thin film layers **120** of at least one polymer adjacent to one another. By adjacent, we mean next to, but not necessarily directly next to. In most of the multilayer plastic substrate, the polymer thin film layers will be directly next to one another. However, there can be additional layers intervening between some adjacent layers

in order to provide additional functionality to the multilayer plastic substrate, as shown in FIG. 1 and described below.

The plurality of thin film layers have sufficient strength to be self-supporting after they are formed. The exact number of thin film layers is not critical. It depends on the thickness of each of the individual thin film layers and the desired overall thickness of the multilayer plastic substrate. There must be enough thin film layers so that the plurality of thin film layers have sufficient strength to be self-supporting. As used herein, the term self-supporting means the substrate can be handled and processed without the need for an underlying support once the plurality of thin film layers have been deposited. There are typically at least about 50 thin film layers, more typically at least about 100 thin film layers. There are generally in the range of about 500 thin film layers to about 1000 thin film layers or more. Each thin film layer is typically between about 0.05 to about 2 μm thick, generally between about 0.2 to about 0.3 μm . If the thin film layers are extruded, they are usually thicker, typically up to about 50 μm thick, in that case. The multilayer plastic substrate is typically at least about 0.001 inches thick, and generally at least about 0.004 inches thick. A 0.007 inch thick substrate would require about 90 to 350 passes of the web past the polymer precursor sources. The multilayer plastic substrate can be flexible or rigid.

The average visible light transmittance of the multilayer plastic substrate is greater than about 80%, generally greater than 85%, and it may be greater than 90%. The peak visible light transmittance is generally greater than 85%, and it may be greater than 90%.

The at least one polymer can be any suitable polymer, including, but not limited to, polymers made from styrene polymer precursors, polymers made from methyl styrene polymer precursors, polymers made from (meth)acrylate polymer precursors, for example, polymers made from hexanedioldiacrylate or tetraethyleneglycoldiacrylate polymer precursors, and fluorinated polymers, and combinations thereof. Polymers made from (meth)acrylate polymer precursors work well.

The multilayer plastic substrate can be flexible or rigid. Multilayer plastic substrates made from polymers including, but not limited to, (meth)acrylate polymer precursors will be flexible. One advantage of multilayer laminated materials is that they typically have greater strength and flexibility than comparable single layer substrates. A multilayer plastic substrate of the present invention generally has hundreds of cross-linked layers that provide mechanical strength and sufficient rigidity to support the circuitry and devices on the display.

A multilayer plastic substrate made from (meth)acrylate polymer precursors will have excellent transmission at visible wavelengths. Because polymers made from (meth)acrylate polymer precursors have very low optical absorption, a multilayer plastic substrate made entirely from such polymers will have high optical transparency, typically an average visible light transmittance of greater than about 90%. Multilayer substrates made entirely from fluorinated polymers will also have an average visible light transmittance of greater than 90%. Substrates made from styrene and methyl styrene polymers would have an average visible light transmittance of about 89%.

The birefringence present in many flexible substrates can be reduced or eliminated with the present invention because the multilayer plastic substrate is not mechanically stressed during deposition.

Fully cured layers of polymers made from (meth)acrylate polymer precursors generally have a refractive index of

greater than about 1.5, while fully cured fluorinated polymers generally have a refractive index of greater than about 1.4. Styrene containing polymers would have a refractive index of about 1.6.

Many optical applications, such as mirrors and reflectors, and display applications, such as organic light emitting devices, require substrates with a surface roughness of less than 2 nm. Surface roughness is the root mean square of peak-to-valley measurement over a specified distance, usually 1 nm. It can be measured using an atomic force microscope or back reflection distribution function. Many substrates do not have the necessary surface smoothness. For example, the surface roughness of PET is about 20–50 nm with 100 nm spikes. In contrast, flash evaporated polymer coatings have a very low surface roughness, generally less than about 10 nm, and it may be less than 5 nm, or less than about 2 nm. Surface roughness on the order of 1 nm has been demonstrated. The surface of the multilayer plastic substrate is specular because of the exceptional smoothness of the polymer layers.

Because the polymer material is highly cross-linked, the multilayer plastic substrate can have a high glass transition temperature and excellent chemical resistance. The glass transition temperature of the at least one polymer is generally greater than about 150° C., and may be greater than about 200° C.

Polymers including, but not limited to, (meth)acrylates, polycarbonates, polysulfones, polyethersulfones, polyimides, polyamides, and polyether naphtheates have demonstrated excellent resistance to solvents. This provides protection from processing chemicals, ultraviolet light exposure, and photoresists during lithography processes used to manufacture flat panel displays and their devices.

The thin film layers that form the multilayer substrate can be deposited by any suitable method, including vacuum flash evaporation, extrusion, or casting. With vacuum flash evaporation, deposition can be performed using a rotating drum or strap configuration. The polymer precursor is degassed and metered into a hot tube where it flash evaporates and exits through a nozzle as a polymer precursor gas.

The flash evaporating may be performed by supplying a continuous liquid flow of the polymer precursor into a vacuum environment at a temperature below both the decomposition temperature and the polymerization temperature of the polymer precursor, continuously atomizing the polymer precursor into a continuous flow of droplets, and continuously vaporizing the droplets by continuously contacting the droplets on a heated surface having a temperature at or above a boiling point of the liquid polymer precursor, but below a pyrolysis temperature, forming the evaporate. The droplets typically range in size from about 1 micrometer to about 50 micrometers, by they could be smaller or larger.

Alternatively, the flash evaporating may be performed by supplying a continuous liquid flow of the polymer precursor into a vacuum environment at a temperature below both the decomposition temperature and the polymerization temperature of the polymer precursor, and continuously directly vaporizing the liquid flow of the polymer precursor by continuously contacting the liquid polymer precursor on a heated surface having a temperature at or above the boiling point of the liquid polymer precursor, but below the pyrolysis temperature, forming the evaporate. This may be done using the vaporizer disclosed in U.S. Pat. Nos. 5,402,314, 5,536,323, and 5,711,816, which are incorporated herein by reference.

The polymer precursor then condenses on the support as a liquid film which is subsequently cross-linked to form a

polymer by any suitable method, including, but not limited to, radiation, such as ultraviolet, electron beam, or x-ray, glow discharge ionization, and spontaneous thermally induced curing. This process is capable of depositing thousands of polymer layers at web speeds up to 100 m/min.

Alternatively, after degassing, the polymer precursor can be deposited by extruding, spraying, or casting layers of polymer precursor on the support. The polymer precursor is then cross-linked using any suitable method, such as those described above.

The functionality of the multilayer plastic substrate can be increased by the incorporation of functional layers **130**, **140**, and **150** during the deposition process. These functional layers **130**, **140**, and **150** can be deposited at any time during the deposition process. They can be deposited below, **130**, in between, **140**, or on top of, **150**, the plurality of thin film layers **120** of the multilayer plastic substrate, as shown in FIG. 1. As used herein, depositing a coating adjacent to the multilayer plastic substrate includes: depositing the coating on the top layer of the multilayer plastic coating; depositing the coating on the multilayer plastic substrate and then depositing additional layers of the multilayer plastic substrate over the coating so that the coating is between the layers of the multilayer plastic substrate; and depositing the coating first and then depositing the layers of the multilayer plastic substrate, and combinations thereof. Functional layers **130**, **140**, and **150** include, but are not limited to, scratch resistant coatings, antireflective coatings, antifingerprint coatings, antistatic coatings, conductive coatings, transparent conductive coatings, and barrier coatings, and other functional layers. Depositing these additional layers allows the multilayer plastic substrate to be specifically tailored to different applications. Little or no surface modification is necessary for deposition of other layers because of the very smooth surface of the multilayer plastic substrate. Interfaces can be graded to bond all integrated functional layers firmly during the same coating run and pumpdown.

For some applications, it may be important that the presence of functional layers not reduce the average visible light transmittance below 80%, for others, not below 85%, and still others, not below 90%. In others, it may be important that the peak visible light transmittance not drop below 85%, and for others, not below 90%. In others, it may be important that the functional layers not increase the surface roughness to greater than about 10 nm, for others, not greater than about 5 nm, and for others, not greater than 2 nm.

One type of functional layer that can be included is a barrier coating. One example of a barrier coating is described in application Ser. No. 09/427,138, filed Oct. 25, 1999, entitled "Environmental Barrier Material for Organic Light Emitting Device and Method of Making," which is incorporated herein by reference. The barrier coating can be a barrier stack having one or more barrier layers and one or more polymer layers. There could be one polymer layer and one barrier layer, there could be one or more polymer layers on one side of one or more barrier layers, or there could be one or more polymer layers on both sides of one or more barrier layers. The important feature is that the barrier stack have at least one polymer layer and at least one barrier layer. The barrier layers and polymer layers in the barrier stack can be made of the same material or of a different material. The barrier layers are typically in the range of about 100–400 Å thick, and the polymer layers are typically in the range of about 1000–10,000 Å thick.

The number of barrier stacks is not limited. The number of barrier stacks needed depends on the material used for the

polymer of the substrate and the level of permeation resistance needed for the particular application. One or two barrier stacks should provide sufficient barrier properties for some applications. The most stringent applications may require five or more barrier stacks.

The barrier layers should be transparent. Transparent barrier materials include, but are not limited to, metal oxides, metal nitrides, metal carbides, metal oxynitrides, metal oxyborides, and combinations thereof. The metal oxides include, but are not limited to, silicon oxide, aluminum oxide, titanium oxide, indium oxide, tin oxide, indium tin oxide, tantalum oxide, zirconium oxide, niobium oxide, and combinations thereof. The metal carbides include, but are not limited to, boron carbide, tungsten carbide, silicon carbide, and combinations thereof. The metal nitrides include, but are not limited to, aluminum nitride, silicon nitride, boron nitride, and combinations thereof. The metal oxynitrides include, but are not limited to, aluminum oxynitride, silicon oxynitride, boron oxynitride, and combinations thereof. The metal oxyborides include, but are not limited to, zirconium oxyboride, titanium oxyboride, and combinations thereof.

The polymer layers of the barrier stacks can be made from (meth)acrylate polymer precursors. The polymer layers in the barrier stacks can be the same or different.

The barrier stacks can be made by vacuum deposition. The barrier layer can be vacuum deposited onto, or into, the multilayer plastic substrate, or another functional layer. The polymer layer is then deposited on the barrier layer, preferably by flash evaporating (meth)acrylate polymer precursors, condensing on the barrier layer, and polymerizing in situ in a vacuum chamber. U.S. Pat. Nos. 5,440,446 and 5,725,909, which are incorporated herein by reference, describe methods of depositing thin film, barrier stacks.

Vacuum deposition includes flash evaporation of (meth)acrylate polymer precursors with in situ polymerization under vacuum, plasma deposition and polymerization of (meth)acrylate polymer precursors, as well as vacuum deposition of the barrier layers by sputtering, chemical vapor deposition, plasma enhanced chemical vapor deposition, evaporation, sublimation, electron cyclotron resonance-plasma enhanced vapor deposition (ECR-PECVD), and combinations thereof.

In order to protect the integrity of the barrier layer, the formation of defects and/or microcracks in the deposited layer subsequent to deposition and prior to downstream processing should be avoided. The multilayer plastic substrate is preferably manufactured so that the barrier layers are not directly contacted by any equipment, such as rollers in a web coating system, to avoid defects that may be caused by abrasion over a roll or roller. This can be accomplished by designing the deposition system such that the barrier layers are always covered by polymer layers prior to contacting or touching any handling equipment.

While certain representative embodiments and details have been shown for purposes of illustrating the invention, it will be apparent to those skilled in the art that various changes in the compositions and methods disclosed herein may be made without departing from the scope of the invention, which is defined in the appended claims.

What is claimed is:

1. A multilayer plastic substrate consisting essentially of: a plurality of flash evaporated thin film layers of at least one polymer, the plurality of thin film layers being adjacent to one another and having sufficient strength to be self-supporting, wherein the multilayer plastic substrate has an average visible light transmittance of

greater than about 80%, wherein the multilayer plastic substrate comprises at least about 50 thin film layers, and wherein the multilayer plastic substrate has a surface roughness of less than about 10 nm.

2. The multilayer plastic substrate of claim 1 wherein the average visible light transmittance is greater than about 85%.

3. The multilayer plastic substrate of claim 1 wherein the average visible light transmittance is greater than about 90%.

4. The multi layer plastic substrate of claim 1 wherein the peak visible light transmittance is greater than about 85%.

5. The multilayer plastic substrate of claim 1 wherein the peak visible light transmittance is greater than about 90%.

6. The multilayer plastic substrate of claim 1, wherein the multilayer plastic substrate comprises at least about 100 thin film layers.

7. The multilayer plastic substrate of claim 6, wherein the multilayer plastic substrate comprises at least about 500 thin film layers.

8. The multilayer plastic substrate of claim 7, wherein the multilayer plastic substrate comprises at least about 1000 thin film layers.

9. The multilayer plastic substrate of claim 1, wherein the multilayer plastic substrate is at least about 0.001 inches thick.

10. The multilayer plastic substrate of claim 1, wherein the multilayer plastic substrate is at least about 0.004 inches thick.

11. The multilayer plastic substrate of claim 1, wherein each thin film layer is less than about 50 μm thick.

12. The multilayer plastic substrate of claim 1, wherein each thin film layer is less than about 5 μm thick.

13. The multilayer plastic substrate of claim 1, wherein each thin film layer is in the range of about 0.05 to about 2 μm thick.

14. The multilayer plastic substrate of claim 1, wherein each thin film layer is in the range of about 0.2 to about 0.3 μm .

15. The multilayer plastic substrate of claim 1, wherein the at least one polymer is selected from (meth)acrylates, polystyrenes, methyl styrene-containing polymers, fluorinated polymers, polycarbonates, polysulfones, polyethersulfones, polyimides, polyamides, and polyether naphthalenes, and combinations thereof.

16. The multilayer plastic substrate of claim 1, wherein the glass transition temperature of the at least one polymer is greater than about 150° C.

17. The multilayer plastic substrate of claim 1, wherein the glass transition temperature of the at least one polymer is greater than about 200° C.

18. The multilayer plastic substrate of claim 1, wherein the multilayer plastic substrate has a surface roughness of less than about 2 nm.

19. The multilayer plastic substrate of claim 1, wherein the multilayer plastic substrate has a refractive index of greater than about 1.5.

20. The multilayer plastic substrate of claim 1, wherein the multilayer plastic substrate has a refractive index of greater than about 1.4.

21. The multilayer plastic substrate of claim 1, wherein the multilayer plastic substrate is flexible.

22. The multilayer plastic substrate of claim 1, wherein the multilayer plastic substrate is rigid.

23. The multilayer plastic substrate of claim 1, wherein the multilayer plastic substrate has a surface roughness of less than about 5 nm.