

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
11 May 2006 (11.05.2006)

PCT

(10) International Publication Number
WO 2006/050100 A2

- (51) International Patent Classification:
H01M 4/38 (2006.01) *H01M 4/48* (2006.01)
- (21) International Application Number:
PCT/US2005/038944
- (22) International Filing Date: 27 October 2005 (27.10.2005)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
10/979,041 29 October 2004 (29.10.2004) US
10/978,681 29 October 2004 (29.10.2004) US
- (71) Applicant (for all designated States except US):
MEDTRONIC, INC. [US/US]; 710 Medtronic Park-
way NE, Minneapolis, Minnesota 55432 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **HOWARD, William, G.** [US/US]; 2550 North Fisk Street, Roseville, MN 55113 (US). **SCHMIDT, Craig, L.** [US/US]; 831 Hidden Meadow Trail, Eagan, Minnesota 55311 (US). **SCOTT, Erik, R.** [US/US]; 7781 Shenandoah Lane N., Maple Grove, Minnesota 55311 (US).
- (74) Agent: **MCKENNA, Richard, J.**; FOLEY & LARDNER LLP, 777 East Wisconsin Avenue, Milwaukee, Wisconsin 53202 (US).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM,

AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:


- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii))

Published:

- without international search report and to be republished upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: LITHIUM-ION BATTERY



(57) Abstract: A lithium-ion battery includes a positive electrode that includes a positive current collector, a first active material, and a second active material. The lithium-ion battery also includes a negative electrode comprising a negative current collector, a third active material, and a quantity of lithium in electrical contact with the negative current collector. The first active material, second active material, and third active materials are configured to allow doping and undoping of lithium ions, and the second active material exhibits charging and discharging capacity below a corrosion potential of the negative current collector and above a decomposition potential of the first active material.

WO 2006/050100 A2

LITHIUM-ION BATTERY

BACKGROUND

[0001] The present invention relates generally to the field of lithium batteries. Specifically, the present invention relates to lithium-ion batteries that are relatively tolerant to over-discharge conditions.

[0002] Lithium-ion batteries include a positive current collector (e.g., aluminum such as an aluminum foil) having an active material provided thereon (e.g., LiCoO_2) and a negative current collector (e.g., copper such as a copper foil) having an active material (e.g., a carbonaceous material such as graphite) provided thereon. Together the positive current collector and the active material provided thereon are referred to as a positive electrode, while the negative current collector and the active material provided thereon are referred to as a negative electrode.

[0003] FIGURE 1 shows a schematic representation of a portion of a lithium-ion battery 10 such as that described above. The battery 10 includes a positive electrode 20 that includes a positive current collector 22 and a positive active material 24, a negative electrode 30 that includes a negative current collector 32 and a negative active material 34, an electrolyte material 40, and a separator (e.g., a polymeric microporous separator, not shown) provided intermediate or between the positive electrode 20 and the negative electrode 30. The electrodes 20, 30 may be provided as relatively flat or planar plates or may be wrapped or wound in a spiral or other configuration (e.g., an oval configuration). The electrode may also be provided in a folded configuration.

[0004] During charging and discharging of the battery 10, lithium ions move between the positive electrode 20 and the negative electrode 30. For example, when the battery 10 is discharged, lithium ions flow from the negative electrode 30 to the positive electrode 20. In contrast, when the battery 10 is charged, lithium ions flow from the positive electrode 20 to the negative electrode 30.

[0005] FIGURE 2 is a graph 100 illustrating the theoretical charging and discharging behavior for a conventional lithium-ion battery. Curve 110 represents the electrode potential versus a lithium reference electrode for a positive electrode that includes an

aluminum current collector having a LiCoO_2 active material provided thereon, while curve 120 represents the electrode potential versus a lithium reference electrode for a negative electrode that includes a copper current collector having a carbonaceous active material provided thereon. The difference between curves 110 and 120 is representative of the overall cell voltage.

[0006] As shown in FIGURE 2, upon initial charging to full capacity, the potential of the positive electrode, as shown by curve 110, increases from approximately 3.0 volts to a point above the corrosion potential of copper used to form the negative electrode (designated by dashed line 122). The potential of the negative electrode decreases from approximately 3.0 volts to a point below the decomposition potential of the LiCoO_2 active material provided on the aluminum current collector (designated by dashed line 112). Upon initial charging, the battery experiences an irreversible loss of capacity due to the formation of a passive layer on the negative current collector, which may be referred to as a solid-electrolyte interface ("SEI"). The irreversible loss of capacity is shown as a ledge or shelf 124 in curve 120.

[0007] One difficulty with conventional lithium-ion batteries is that when such a battery is discharged to a point near zero volts, it may exhibit a loss of deliverable capacity and corrosion of the negative electrode current collector (copper) and possibly of the battery case, depending on the material used and the polarity of the case. As shown in FIGURE 2, after initial charging of the battery, a subsequent discharge of the battery in which the voltage of the battery approaches zero volts (i.e., zero percent capacity) results in a negative electrode potential that follows a path designated by dashed line 126. As shown in FIGURE 2, the negative electrode potential levels off or plateaus at the copper corrosion potential of the negative current collector (approximately 3.5 volts for copper and designated by dashed line 122 in FIGURE 2).

[0008] The point at which the curves 110 and 120 cross is sometimes referred to as the zero voltage crossing potential, and corresponds to a cell voltage that is equal to zero (i.e., the difference between the two curves equals zero at this point). Because of the degradation of the copper current collector which occurs at the copper corrosion potential, the copper material used for the negative current collector corrodes before the cell reaches a zero voltage condition, resulting in a battery that exhibits a dramatic loss of deliverable capacity.

[0009] While FIGURE 2 shows the theoretical charging and discharging behavior of a battery that may experience corrosion of the negative current collector when the battery approaches a zero voltage configuration, it should be noted that there may also be cases in which the active material on the positive current collector may degrade in near-zero-voltage conditions. In such cases, the theoretical charging and discharging potential of the positive electrode versus a lithium reference electrode would decrease to the decomposition potential of the positive active material (shown as line 112 in FIGURE 2), at which point the positive active material would decompose, resulting in potentially decreased protection against future over-discharge conditions.

[0010] Because damage to the lithium-ion battery may occur in the event of a low voltage condition, conventional lithium-ion batteries may include protection circuitry and/or may be utilized in devices that include protection circuitry which substantially reduces the current drain from the battery (e.g., by disconnecting the battery).

[0011] The medical device industry produces a wide variety of electronic and mechanical devices for treating patient medical conditions. Depending upon the medical condition, medical devices can be surgically implanted or connected externally to the patient receiving treatment. Clinicians use medical devices alone or in combination with drug therapies and surgery to treat patient medical conditions. For some medical conditions, medical devices provide the best, and sometimes the only, therapy to restore an individual to a more healthful condition and a fuller life.

[0012] It may be desirable to provide a source of battery power for such medical devices, including implantable medical devices. In such cases, it may be advantageous to provide a battery that may be recharged. It may also be advantageous to provide a battery that may be discharged to a near zero voltage condition without substantial risk that the battery may be damaged (e.g., without corroding one of the electrodes or the battery case, decomposing the positive active material, etc.) such that the performance of the battery is degraded in subsequent charging and discharging operations.

[0013] It would be advantageous to provide a battery (e.g., a lithium-ion battery) that may be discharged to near zero volts without producing a subsequent decrease in the amount of deliverable capacity or producing a corroded negative electrode or battery case. It would also be advantageous to provide a battery that compensates for the irreversible loss of

capacity resulting from initial charging of the battery to allow the battery to be used in near zero voltage conditions without significant degradation to battery performance. It would also be advantageous to provide a medical device (e.g., an implantable medical device) that utilizes a battery that includes any one or more of these or other advantageous features.

SUMMARY

[0014] An exemplary embodiment relates to a lithium-ion battery that includes a positive electrode that includes a positive current collector, a first active material, and a second active material. The lithium-ion battery also includes a negative electrode comprising a negative current collector, a third active material, and a quantity of lithium in electrical contact with the negative current collector. The first active material, second active material, and third active materials are configured to allow doping and undoping of lithium ions, and the second active material exhibits charging and discharging capacity below a corrosion potential of the negative current collector and above a decomposition potential of the first active material.

BRIEF DESCRIPTION OF THE DRAWINGS

[0015] FIGURE 1 is a schematic cross-sectional view of a conventional lithium-ion battery.

[0016] FIGURE 2 is a graph illustrating the theoretical charging and discharging behavior for a conventional lithium-ion battery such as that shown schematically in FIGURE 1.

[0017] FIGURE 3 is a schematic cross-sectional view of a portion of a lithium-ion battery according to an exemplary embodiment.

[0018] FIGURE 4 is a schematic cross-sectional view of a portion of a lithium-ion battery according to another exemplary embodiment.

[0019] FIGURE 5 is a graph illustrating the theoretical charging and discharging behavior for a lithium-ion battery such as that shown in FIGURE 3.

[0020] FIGURE 6 is a schematic view of a system in the form of an implantable medical device implanted within a body or torso of a patient.

[0021] FIGURE 7 is schematic view of another system in the form of an implantable medical device.

DETAILED DESCRIPTION OF EXEMPLARY EMBODIMENTS

[0022] With reference to FIGURE 3, a schematic cross-sectional view of a portion of a lithium-ion battery 200 is shown according to an exemplary embodiment. According to an exemplary embodiment, the battery 200 has a rating of between approximately 10 and 1000 milliampere hours (mAh). According to another exemplary embodiment, the battery has a rating of between approximately 100 and 400 mAh. According to another exemplary embodiment, the battery is an approximately 300 mAh battery. According to another exemplary embodiment, the battery is an approximately 75 mAh battery.

[0023] The battery 200 includes at least one positive electrode 210 and at least one negative electrode 220. The electrodes may be provided as flat or planar components of the battery 200, may be wound in a spiral or other configuration, or may be provided in a folded configuration. For example, the electrodes may be wrapped around a relatively rectangular mandrel such that they form an oval wound coil for insertion into a relatively prismatic battery case. According to other exemplary embodiments, the battery may be provided as a button cell battery, a thin film solid state battery, or as another lithium-ion battery configuration.

[0024] The battery case (not shown) may be made of stainless steel or another metal. According to an exemplary embodiment, the battery case may be made of titanium, aluminum, or alloys thereof. According to another exemplary embodiment, the battery case may be made of a plastic material or a plastic-foil laminate material (e.g., an aluminum foil provided intermediate a polyolefin layer and a polyester layer).

[0025] According to an exemplary embodiment, the negative electrode is coupled to a stainless steel case by a member or tab comprising nickel or a nickel alloy. An aluminum or aluminum alloy member or tab may be coupled or attached to the positive electrode. The nickel and aluminum tabs may serve as terminals for the battery according to an exemplary embodiment.

[0026] The dimensions of the battery 200 may differ according to a variety of exemplary embodiments. For example, according to one exemplary embodiment in which the electrodes are wound such that they may be provided in a relatively prismatic battery case, the battery has dimensions of between approximately 30-40 mm by between approximately 20-30 mm by between approximately 5-7 mm. According to another exemplary embodiment, the dimensions of the battery are approximately 20 mm by 20 mm by 3 mm. According to another exemplary embodiment, a battery may be provided in the form of a button cell type battery having a diameter of approximately 30 mm and a thickness of approximately 3 mm. It will be appreciated by those of skill in the art that such dimensions and configurations as are described herein are illustrative only, and that batteries in a wide variety of sizes, shapes, and configurations may be produced in accordance with the novel concepts described herein.

[0027] An electrolyte 230 is provided intermediate or between the positive and negative electrodes to provide a medium through which lithium ions may travel. According to an exemplary embodiment, the electrolyte may be a liquid (e.g., a lithium salt dissolved in one or more non-aqueous solvents). According to another exemplary embodiment, the electrolyte may be a lithium salt dissolved in a polymeric material such as poly(ethylene oxide) or silicone. According to another exemplary embodiment, the electrolyte may be an ionic liquid such as N-methyl-N-alkylpyrrolidinium bis(trifluoromethanesulfonyl)imide salts. According to another exemplary embodiment, the electrolyte may be a solid state electrolyte such as a lithium-ion conducting glass such as lithium phosphorous oxynitride (LiPON).

[0028] Various other electrolytes may be used according to other exemplary embodiments. For example, according to an exemplary embodiment, the electrolyte may be a 1:1 mixture of ethylene carbonate to diethylene carbonate (EC:DEC) in a 1.0 M salt of LiPF_6 . According to another exemplary embodiment, the electrolyte may include a polypropylene carbonate solvent and a lithium bis-oxalatoborate salt (sometimes referred to as LiBOB). According to other exemplary embodiments, the electrolyte may comprise one or more of a PVDF copolymer, a PVDF-polyimide material, and organosilicon polymer, a thermal polymerization gel, a radiation cured acrylate, a particulate with polymer gel, an inorganic gel polymer electrolyte, an inorganic gel-polymer electrolyte, a PVDF gel, polyethylene oxide (PEO), a glass ceramic electrolyte, phosphate glasses, lithium

conducting glasses, lithium conducting ceramics, and an inorganic ionic liquid or gel, among others.

[0029] A separator 250 is provided intermediate or between the positive electrode 210 and the negative electrode 220. According to an exemplary embodiment, the separator 250 is a polymeric material such as a polypropylene/polyethelene copolymer or another polyolefin multilayer laminate that includes micropores formed therein to allow electrolyte and lithium ions to flow from one side of the separator to the other. The thickness of the separator 250 is between approximately 10 micrometers (μm) and 50 μm according to an exemplary embodiment. According to a particular exemplary embodiment, the thickness of the separator is approximately 25 μm and the average pore size of the separator is between approximately 0.02 μm and 0.1 μm .

[0030] The positive electrode 210 includes a current collector 212 made of a conductive material such as a metal. According to an exemplary embodiment, the current collector 212 comprises aluminum or an aluminum alloy. According to an exemplary embodiment, the thickness of the current collector 212 is between approximately 5 μm and 75 μm . According to a particular exemplary embodiment, the thickness of the current collector 212 is approximately 20 μm . It should also be noted that while the positive current collector 212 has been illustrated and described as being a thin foil material, the positive current collector may have any of a variety of other configurations according to various exemplary embodiments. For example, the positive current collector may be a grid such as a mesh grid, an expanded metal grid, a photochemically etched grid, or the like.

[0031] The current collector 212 has a layer of active material 214 provided thereon (e.g., coated on the current collector). While FIGURE 3 shows that the layer of active material 214 is provided on only one side of the current collector 212, it should be understood that a layer of active material similar or identical to that shown as layer 214 may be provided or coated on both sides of the current collector 212.

[0032] As shown in FIGURE 3, layer 214 includes a primary active material 216 and a secondary or auxiliary active material 218. While the primary active material 216 and the secondary active material 218 are shown as being provided as separate individual layers according to an exemplary embodiment, it will be appreciated that the primary active material 216 and the secondary active material 218 may be provided as a single active

material layer in which the primary and secondary active materials are intermixed (see, e.g., the exemplary embodiment shown in FIGURE 4, in which layer 214 includes both the primary active material 216 and the secondary active material 218). A binder material may also be utilized in conjunction with the layer of active material 214 to bond or hold the various electrode components together. For example, according to an exemplary embodiment, the layer of active material may include a conductive additive such as carbon black and a binder such as polyvinylidene fluoride (PVDF) or an elastomeric polymer.

[0033] According to an exemplary embodiment, the primary active material 216 is a material or compound that includes lithium. The lithium included in the primary active material 216 may be doped and undoped during discharging and charging of the battery, respectively. According to an exemplary embodiment, the primary active material 216 is lithium cobalt oxide (LiCoO_2). According to another exemplary embodiment, the positive active material is of the form $\text{LiCo}_x\text{Ni}_{(1-x)}\text{O}_2$, where x is between approximately 0.05 and 0.8. According to another exemplary embodiment, the primary active material is of the form $\text{LiAl}_x\text{Co}_y\text{Ni}_{(1-x-y)}\text{O}_2$, where x is between approximately 0.05 and 0.3 and y is between approximately 0.1 and 0.3. According to other exemplary embodiments, the primary active material may include LiMn_2O_4 .

[0034] According to various other exemplary embodiments, the primary active material may include a material such as a material of the form $\text{Li}_{1-x}\text{MO}_2$ where M is a metal (e.g., LiCoO_2 , LiNiO_2 , and LiMnO_2), a material of the form $\text{Li}_{1-w}(\text{M}'_x\text{M}''_y)\text{O}_2$ where M' and M'' are different metals (e.g., $\text{Li}(\text{Ni}_x\text{Mn}_y)\text{O}_2$, $\text{Li}(\text{Ni}_{1/2}\text{Mn}_{1/2})\text{O}_2$, $\text{Li}(\text{Cr}_x\text{Mn}_{1-x})\text{O}_2$, $\text{Li}(\text{Al}_x\text{Mn}_{1-x})\text{O}_2$, $\text{Li}(\text{Co}_x\text{M}_{1-x})\text{O}_2$ where M is a metal, $\text{Li}(\text{Co}_x\text{Ni}_{1-x})\text{O}_2$, and $\text{Li}(\text{Co}_x\text{Fe}_{1-x})\text{O}_2$), a material of the form $\text{Li}_{1-w}(\text{Mn}_x\text{Ni}_y\text{Co}_z)\text{O}_2$ (e.g., $\text{LiCo}_x\text{Mn}_y\text{Ni}_{(1-x-y)}\text{O}_2$, $\text{Li}(\text{Mn}_{1/4}\text{Ni}_{1/4}\text{Co}_{1/2})\text{O}_2$, $\text{Li}(\text{Mn}_{1/4}\text{Ni}_{1/4}\text{Co}_{1/2-x}\text{Mg}_x)\text{O}_2$, $\text{Li}(\text{Mn}_{0.4}\text{Ni}_{0.4}\text{Co}_{0.2})\text{O}_2$, and $\text{Li}(\text{Mn}_{0.1}\text{Ni}_{0.1}\text{Co}_{0.8})\text{O}_2$), a material of the form $\text{Li}_{1-w}(\text{Mn}_x\text{Ni}_y\text{Co}_z\text{Al}_w)\text{O}_2$, a material of the form $\text{Li}_{1-w}(\text{Ni}_x\text{Co}_y\text{Al}_z)\text{O}_2$ (e.g., $\text{Li}(\text{Ni}_{0.8}\text{Co}_{0.15}\text{Al}_{0.05})\text{O}_2$), a material of the form $\text{Li}_{1-w}(\text{Ni}_x\text{Co}_y\text{M}_z)\text{O}_2$ where M is a metal, a material of the form $\text{Li}_{1-w}(\text{Ni}_x\text{Mn}_y\text{M}_z)\text{O}_2$ where M is a metal, a material of the form $\text{Li}(\text{Ni}_{x-y}\text{Mn}_y\text{Cr}_{2-x})\text{O}_4$, LiMn_2O_4 , a material of the form $\text{LiM}'\text{M}''_2\text{O}_4$ where M' and M'' are different metals (e.g., $\text{LiMn}_{2-y-z}\text{Ni}_y$, Li_2O_4 , $\text{LiMn}_{1.5}\text{Ni}_{0.5}\text{O}_4$, LiNiCuO_4 , $\text{LiMn}_{1-x}\text{Al}_x\text{O}_4$, $\text{LiNi}_{0.5}\text{Ti}_{0.5}\text{O}_4$, and $\text{Li}_{1.05}\text{Al}_{0.1}\text{Mn}_{1.85}\text{O}_{4-z}\text{F}_z$), Li_2MnO_3 , a material of the form $\text{Li}_x\text{V}_y\text{O}_z$ (e.g., LiV_3O_8 , LiV_2O_5 , and $\text{LiV}_6\text{O}_{13}$), a material of the form LiMPO_4 where M is a metal or $\text{LiM}_x\text{'M}''_{1-x}\text{PO}_4$ where M' and M'' are different metals (e.g.,

LiFePO_4 , $\text{LiFe}_x\text{M}_{1-x}\text{PO}_4$ where M is a metal, LiVOPO_4 , and $\text{Li}_3\text{V}_2(\text{PO}_4)_3$, LiMPO_{4x} where M is a metal such as iron or vanadium and X is a halogen such as fluorine, and combinations thereof.

[0035] The secondary active material 218 is a material that is selected to have relatively significant cyclable charge and discharge capacity (i.e., cyclable capacity) below the corrosion potential of the material used for a negative current collector 222 provided as part of the negative electrode 220 (and/or any other material to which the negative current collector is electrically attached or in electrical communication with, for example, a case or housing for the battery) and above the decomposition potential of the primary active material 216. For example, according to an exemplary embodiment in which the negative current collector 222 comprises copper, for which the corrosion potential is approximately 3.5 volts, the secondary active material 218 includes significant charge and discharge capacity below 3.5 volts.

[0036] The secondary active material 218 may or may not contain lithium. According to an exemplary embodiment in which the secondary active material does not include lithium, the secondary active material is V_6O_{13} . According to another exemplary embodiment in which the secondary active material includes lithium, the secondary active material is LiMn_2O_4 . According to various other exemplary embodiments, the secondary active material may be selected from the following materials and combinations thereof: V_2O_5 , V_6O_{13} , LiMn_2O_4 (spinel), $\text{LiM}_x\text{Mn}_{(2-x)}\text{O}_4$ (spinel) where M is metal (including Li) and where x is between approximately 0.05 and 0.4, $\text{Li}_5\text{Ti}_4\text{O}_{12}$, Li_xVO_2 (where x is between approximately 0 and 1), V_3O_8 , MoO_3 , TiS_2 , WO_2 , MoO_2 , and RuO_2 .

[0037] According to an exemplary embodiment, electrochemically active or cyclable lithium may be added as finely divided or powdered lithium. Such powdered lithium may include a passive coating (e.g., a thin layer or film of lithium carbonate) provided thereon to reduce the reactivity of the powdered lithium with air and moisture. Such material may be mixed with the secondary active material prior to application of the secondary active material to fabrication of the cells or may be added as another separate active material layer.

[0038] The lithium added to the secondary active material 218 of the positive electrode 210 has significant charge/discharge capacity that lies below the corrosion potential of the negative current collector and/or any battery components to which it is electrically

connected (e.g., the case) and above the decomposition potential of the positive electrode active material. The lithium becomes significantly doped at a potential below the corrosion potential for the negative current collector 222. In so doing, this material lowers the final potential of the positive electrode in the discharge state, so that the zero voltage crossing potential remains below the corrosion potential of the negative current collector and the battery case. The secondary active material may be capable of releasing the lithium when the battery is charged.

[0039] It should be noted that while a variety of materials have been described above as being useful for secondary active material 218, a variety of additional materials may be utilized in addition to or in place of such materials. For example, the secondary active material may comprise an oxide material such as one or more of Li_xMoO_3 ($0 < x \leq 2$), Li_xMoO_2 ($0 < x \leq 1$), $\text{Li}_x\text{Mo}_2\text{O}_4$ ($0 < x \leq 2$), Li_xMnO_2 ($0 < x \leq 1$), $\text{Li}_x\text{Mn}_2\text{O}_4$ ($0 < x \leq 2$), $\text{Li}_x\text{V}_2\text{O}_5$ ($0 < x \leq 2.5$), $\text{Li}_x\text{V}_3\text{O}_8$ ($0 < x \leq 3.5$), $\text{Li}_x\text{V}_6\text{O}_{13}$ ($0 < x \leq 6$ for $\text{Li}_x\text{VO}_{2.19}$ and $0 < x \leq 3.6$ for $\text{Li}_x\text{VO}_{2.17}$), Li_xVO_2 ($0 < x \leq 1$), Li_xWO_3 ($0 < x \leq 1$), Li_xWO_2 ($0 < x \leq 1$), Li_xTiO_2 (anatase) ($0 < x \leq 1$), $\text{Li}_x\text{Ti}_2\text{O}_4$ ($0 < x \leq 2$), Li_xRuO_2 ($0 < x \leq 1$), $\text{Li}_x\text{Fe}_2\text{O}_3$ ($0 < x \leq 2$), $\text{Li}_x\text{Fe}_3\text{O}_4$ ($0 < x \leq 2$), $\text{Li}_x\text{Cr}_2\text{O}$ ($0 < x \leq 3$), Li_xCr ($0 < x \leq 3.8$), and $\text{Li}_x\text{Ni}_y\text{Co}_{1-y}\text{O}_2$ ($0 < x \leq 1$, $0.90 < y \leq 1.00$), where x is selected such that these materials have little or no lithium that becomes undoped below the corrosion potential of the negative current collector during the first charge of the battery.

[0040] According to another exemplary embodiment, the secondary active material may comprise a sulfide material such as one or more of $\text{Li}_x\text{V}_2\text{S}_5$ ($0 < x \leq 4.8$), Li_xTaS_2 ($0 < x \leq 1$), Li_xFeS ($0 < x \leq 1$), Li_xFeS_2 ($0 < x \leq 1$), Li_xNbS_3 ($0 < x \leq 2.4$), Li_xMoS_3 ($0 < x \leq 3$), Li_xMoS_2 ($0 < x \leq 1$), Li_xTiS_2 ($0 < x \leq 1$), Li_xZrS_2 ($0 < x \leq 1$), $\text{Li}_x\text{Fe}_{0.25}\text{V}_{0.75}\text{S}_2$ ($0 < x \leq 1$), $\text{Li}_x\text{Cr}_{0.75}\text{V}_{0.25}\text{S}_2$ ($0 < x \leq 0.65$), and $\text{Li}_x\text{Cr}_{0.5}\text{V}_{0.5}\text{S}_2$ ($0 < x \leq 1$), where x is selected such that these materials have little or no lithium that becomes undoped below corrosion potential of the negative current collector during the first charge of the battery.

[0041] According to another exemplary embodiment, the secondary active material may comprise a selenide material such as one or more of Li_xNbSe_3 ($0 < x \leq 3$), Li_xVSe_2 ($0 < x \leq 1$). Various other materials may also be used, for example, Li_xNiPS_3 ($0 < x \leq 1.5$) and Li_xFePS_3 ($0 < x \leq 1.5$), where x is selected such that these materials have little or no lithium that becomes undoped below corrosion potential of the negative current collector during the first charge of the battery.

[0042] According to an exemplary embodiment, the thickness of the layer of active material 214 is between approximately 0.1 μm and 3 mm. According to another exemplary embodiment, the thickness of the layer of active material 214 is between approximately 25 μm and 300 μm . According to a particular exemplary embodiment, the thickness of the layer of active material 214 is approximately 75 μm . In embodiments in which the primary active material 216 and the secondary active material 218 are provided as separate layers of active material, the thickness of the primary active material 216 is between approximately 25 μm and 300 μm (and approximately 75 μm according to a particular exemplary embodiment), while the thickness of the secondary active material 218 is between approximately 5 μm and 60 μm (and approximately 10 μm according to a particular exemplary embodiment). The amount of the secondary active material 218 to be added is determined by the electrochemical equivalents (i.e., capacity) of lithium that can be cycled from that material. According to an exemplary embodiment, the amount is as small as practical, because this minimizes the amount to which the battery's average operating voltage (and therefore energy density) is reduced. According to another exemplary embodiment, the amount is at a minimum equal to the difference between the irreversible capacity of the negative electrode active material and that of the positive active material.

[0043] The negative current collector 222 included as part of the negative electrode 220 is made of a conductive material such as a metal. According to an exemplary embodiment, the current collector 222 is copper or a copper alloy. According to another exemplary embodiment, the current collector 222 is titanium or a titanium alloy. According to another exemplary embodiment, the current collector 222 is nickel or a nickel alloy. According to another exemplary embodiment in which the negative active material 224 is not carbon, the current collector 222 is aluminum or an aluminum alloy. It should also be noted that while the negative current collector 222 has been illustrated and described as being a thin foil material, the positive current collector may have any of a variety of other configurations according to various exemplary embodiments. For example, the positive current collector may be a grid such as a mesh grid, an expanded metal grid, a photochemically etched grid, or the like.

[0044] According to an exemplary embodiment, the thickness of the current collector 222 is between approximately 100 nm and 100 μm . According to another exemplary embodiment, the thickness of the current collector 222 is between approximately 5 μm and

25 μm . According to a particular exemplary embodiment, the thickness of the current collector 222 is approximately 10 μm .

[0045] The negative current collector 222 has a negative active material 224 provided thereon. While FIGURE 3 shows that the active material 224 is provided on only one side of the current collector 222, it should be understood that a layer of active material similar or identical to that shown may be provided or coated on both sides of the current collector 222.

[0046] According to exemplary embodiment, the negative active material 224 is a carbonaceous material (e.g., carbon such as graphite). According to exemplary embodiment, the negative active material 224 is a lithium titanate material such as $\text{Li}_4\text{Ti}_5\text{O}_{12}$. Other lithium titanate materials which may be suitable for use as the negative active material may include one or more of include the following lithium titanate spinel materials: $\text{H}_x\text{Li}_{y-x}\text{TiO}_x\text{O}_4$, $\text{H}_x\text{Li}_{y-x}\text{TiO}_x\text{O}_4$, $\text{Li}_4\text{M}_x\text{Ti}_{5-x}\text{O}_{12}$, $\text{Li}_x\text{Ti}_y\text{O}_4$, $\text{Li}_x\text{Ti}_y\text{O}_4$, $\text{Li}_4[\text{Ti}_{1.67}\text{Li}_{0.33-y}\text{M}_y]\text{O}_4$, Li_2TiO_3 , $\text{Li}_4\text{Ti}_{4.75}\text{V}_{0.25}\text{O}_{12}$, $\text{Li}_4\text{Ti}_{4.75}\text{Fe}_{0.25}\text{O}_{11.88}$, and $\text{Li}_4\text{Ti}_{4.5}\text{Mn}_{0.5}\text{O}_{12}$, and $\text{LiM}'\text{M}''\text{XO}_4$ (where M' is a metal such as nickel, cobalt, iron, manganese, vanadium, copper, chromium, molybdenum, niobium, or combinations thereof, M'' is an optional three valent non-transition metal, and X is zirconium, titanium, or a combination of these two). Note that such lithium titanate spinel materials may be used in any state of lithiation (e.g., $\text{Li}_{4+x}\text{Ti}_5\text{O}_{12}$, where $0 \leq x \leq 3$).

[0047] One advantage of using a lithium titanate material instead of a carbonaceous material is that it is believed that the use of a lithium titanate material allows for charging and discharging of the battery at higher rates than is capable using carbonaceous materials. Lithium titanate materials are also believed to offer superior cycle life because they are so called "zero-strain" materials. Zero strain materials have crystal lattices which do not experience shrinkage or contraction with lithium doping/de-doping, making them free from strain-related degradation mechanisms. According to other exemplary embodiments, the negative active material 224 may be carbon, Li_xAl , Li_xSn , Li_xSi , Li_xSnO , metal nanoparticle composites (e.g., including Li_xAl , Li_xSn , Li_xSi , or Li_xSnO), or carbon-coated lithium titanate.

[0048] Another advantageous feature of using a lithium titanate material is that it is believed that when used in a negative electrode of a lithium-ion battery, such materials will cycle lithium at a potential plateau of about 1.5 V versus a lithium reference electrode. This

is substantially higher than graphitic carbon, which is traditionally used in lithium ion batteries, and cycles lithium down to about 0.1 V in the fully charged state. As a result, the battery using lithium titanate is believed to be less likely to result in plating of lithium (which occurs at 0 V versus a lithium reference) while being charged. Lithium plating is a well-known phenomenon that can lead to loss in performance of lithium ion batteries. Being free from the risk of lithium plating, cells with lithium titanate negative electrodes may also be charged at rates that exceed those with carbon negative electrodes. For example, a common upper limit for the rate of charge in lithium ion batteries is about 1C (meaning that the battery can be fully charged from the discharged state in one hour). Conversely, it has been reported in literature that lithium titanate may be charged at rates up to 10C (i.e., attaining full charge in 1/10 hour, or six minutes). Being able to recharge a battery more quickly substantially increases the functionality of devices that employ such a battery. A further advantage of the higher potential of the lithium titanate material is that it avoids decomposition of organic solvents (such as propylene carbonate) commonly used in lithium ion batteries. In so doing, it may reduce negative consequences such as formation of gas, cell swelling, reduction of reversible battery capacity, and buildup of resistive films which reduce battery power.

[0049] A binder material may also be utilized in conjunction with the layer of active material 224. For example, according to an exemplary embodiment, the layer of active material may include a conductive additive such as carbon black and a binder such as polyvinylidene fluoride (PVDF) or an elastomeric polymer.

[0050] According to various exemplary embodiments, the thickness of the active material 224 is between approximately 0.1 μm and 3 mm. According to other exemplary embodiments, the thickness of the active material 224 may be between approximately 25 μm and 300 μm . According to another exemplary embodiment, the thickness of the active material 224 may be between approximately 20 μm and 90 μm , and according to a particular exemplary embodiment, may be approximately 75 μm .

[0051] As shown in FIGURE 3, a mass or quantity of electrochemically active lithium (shown as a piece of lithium in the form of a lithium patch or member 240) is shown as being coupled or attached to (e.g., in electrical contact with) the negative current collector 222. Such a configuration corresponds to a situation in which the secondary active material 228 is provided without including electrochemically active lithium (e.g., the secondary

active material 228 does not include lithium as it is coated on the positive current collector). One such exemplary embodiment involves the use of V_6O_{13} for the secondary active material. It should also be noted that electrochemically cyclable lithium may be added by adding lithium-containing compounds such as a lithium intermetallic compound such as a lithium-aluminum compound, a lithium-tin compound, a lithium-silicon compound, or any other similar compound that irreversibly donates lithium at a potential below that of the corrosion potential of the negative current collector (and any material to which it is electrically connected).

[0052] The electrochemically active lithium may be provided in other locations in the negative electrode 220 and/or may have a different size or shape than that shown schematically in FIGURE 3. For example, the electrochemically active lithium may be provided as a disc or as a rectangular piece of material coupled to the negative current collector. While the electrochemically active lithium is shown as being provided on a single side of the current collector 222 in FIGURE 3 (e.g., as a lithium patch), separate lithium patches may be provided on opposite sides of the current collector 222. Further, multiple lithium patches may be provided on one or more of the sides of the current collector 222. In another example, the lithium may be provided elsewhere within the battery and connected (e.g., by a wire) to the current collector 222.

[0053] According to another exemplary embodiment, the electrochemically active or cyclable lithium may be added as finely divided or powdered lithium. Such powdered lithium may include a passive coating (e.g., a thin layer or film of lithium carbonate) provided thereon to reduce the reactivity of the powdered lithium with air and moisture. Such material may be mixed with the negative electrode active material prior to application of the negative electrode active material to fabrication of the cells or may be added as another separate active material layer. According to an exemplary embodiment, the finely divided or powdered lithium particles have a diameter of between approximately 1 μm and 100 μm , and according to a particular embodiment, between approximately 5 μm and 30 μm .

[0054] One advantage of providing electrochemically active lithium at the negative electrode (e.g., in the form of one or more lithium patches) is that the secondary active material 228 may be partially or completely lithiated by the lithium to compensate for the irreversible loss of capacity which occurs upon the first charging of the battery 200. For

example, when the battery cell is filled with electrolyte, lithium from the lithium patch 240 is oxidized and inserted into the negative active material (i.e., the lithium in the electrochemically active lithium is effectively “shorted” to the negative active material).

[0055] The electrochemically active lithium may also provide a number of additional advantages. For example, it may act to maintain the potential of the negative current collector below its corrosion potential prior to initial charging (“formation”) of the battery. The electrochemically active lithium may also aid in the formation of the solid-electrolyte interface (“SEI”) at the negative electrode. Further, the electrochemically active lithium may provide the “formation” of the active material on the negative electrode without a corresponding reduction in battery capacity as would occur when the source of lithium for formation is the active material from the positive electrode.

[0056] The amount of electrochemically active lithium is selected such the amount of electrochemical equivalents provided by the electrochemically active lithium at minimum corresponds to the irreversible capacity of the negative electrode active material and at maximum corresponds to the sum of the irreversible capacity of the negative electrode active material and the capacity of the secondary active material 228. In this manner, the electrochemically active lithium at least compensates for the irreversible loss of capacity which occurs on initial charging of the battery 200 and most preferably corresponds to the sum of the irreversible capacity of the negative electrode active material and the capacity of the secondary active material 228.

[0057] According to an exemplary embodiment in which a lithium patch 240 is utilized, the size the lithium patch 240 is between approximately 1.4 cm x 1.4 cm x 0.11 cm, which corresponds to approximately 0.013 grams (e.g., approximately 50 mAh). The specific size of the lithium patch may vary according to other exemplary embodiments (e.g., approximately 5-25 percent of the capacity of either the negative or positive electrode).

[0058] FIGURE 5 is a graph 300 illustrating the theoretical charging and discharging behavior for a lithium-ion battery constructed in accordance with an exemplary embodiment such as that shown and described with regard to FIGURE 3. Curve 310 represents the electrode potential versus a lithium reference electrode for a positive electrode (e.g., positive electrode 210) that includes an aluminum current collector having a LiCoO_2 primary active material and a secondary active material provided thereon.

[0059] The secondary active material is selected to provide significant charging/discharging capacity below the corrosion potential (shown as dashed line 322) of the negative current collector and above the decomposition potential (shown as dashed line 312) of the LiCoO_2 primary active material. According to an exemplary embodiment, the secondary active material is V_6O_{13} or LiMn_2O_4 . According to various other exemplary embodiments, the secondary active material may be selected from the following materials and combinations thereof: V_2O_5 , LiMn_2O_4 , V_6O_{13} , $\text{LiM}_x\text{Mn}_{(2-x)}\text{O}_4$ (spinel) where M is metal (including Li), $\text{Li}_5\text{Ti}_4\text{O}_{12}$, Li_xVO_2 , V_3O_8 , MoO_3 , TiS_2 , WO_2 , MoO_2 , and RuO_2 .

[0060] Curve 320 represents the electrode potential versus a lithium reference electrode for a negative electrode that includes a copper current collector having a carbonaceous active material (i.e., carbon) and a lithium patch provided thereon. The difference between curves 310 and 320 is representative of the overall cell voltage of the battery.

[0061] It should be noted that the theoretical charging and discharge behavior for the negative electrode is believed to be qualitatively similar to that shown in FIGURE 5 for a copper current collector having a $\text{Li}_4\text{Ti}_5\text{O}_{12}$ active material provided thereon (as opposed to a carbon active material), with the relatively flat portion of the curve 320 being shifted upward to a level of approximately 1.57 volts (in contrast to the approximately 0.1 volts for the carbon active material).

[0062] Upon initial charging, the battery experiences an irreversible loss of capacity due to the formation of a passive layer on the negative electrode, which may be referred to as a solid-electrolyte interface ("SEI"). The irreversible loss of capacity is shown as a ledge or shelf 324 in curve 320. The lithium patch is provided so as to compensate for the irreversible loss of capacity and to provide lithium to the second active material in the event of discharge to a voltage approaching zero. For example, as shown in FIGURE 5, the relative capacity provided by the lithium patch is shown by arrow 328.

[0063] As shown in FIGURE 5, the initial state of the cell, after it is filled with electrolyte and allowed to equilibrate, is indicated by dashed line XXX. The potential of the positive electrode, as shown by curve 310, is approximately 3 volts (shown as point 311). The potential of the negative electrode, as shown by curve 320, is approximately 0.1 volts (shown as point YYY). When the cell is charged, the potentials of the positive and negative electrodes progress to the right along curves 310 and 320, respectively. When the cell is

discharged, the potentials of the positive and negative electrode potentials progress toward the left.

[0064] The charging/discharging behavior of the primary and secondary active materials (e.g., primary active material 216 and secondary active material 218) provided on the positive current collector are shown in FIGURE 5 as two portions 314, 316 of curve 310. Portion 314 of curve 310 represents the charging/discharging behavior of the positive electrode due to the doping and undoping of the primary active material (i.e., LiCoO_2), while portion 316 of curve 310 represents the charging/discharging behavior of the positive electrode due to the doping and undoping of the secondary active material (i.e., V_6O_{13} , LiMn_2O_4 , etc.).

[0065] Upon discharging the battery to a point approaching zero volts, the negative electrode potential follows a path designated by line 326. However, because the secondary active material is chosen to have significant charging/discharging capacity below the corrosion potential of the negative current collector and above the decomposition potential of the LiCoO_2 primary active material, the zero voltage crossing potential (shown as point 330) is below the corrosion potential of the negative current collector and above the decomposition potential of the LiCoO_2 primary active material, thus avoiding corrosion of the negative current collector (and potentially of the battery case) and any associated loss of battery charging capacity.

[0066] It is intended that a lithium-ion battery such as that described herein may be fully discharged while the materials for both electrodes, including their corresponding current collectors, are stable (e.g., corrosion of the current collectors and/or the decomposition of active material may be avoided, etc.). One potential advantageous feature of such an arrangement is that the occurrence of reduced device functionality (i.e., the need to recharge more frequently) and corrosion of the current collectors and battery case (with the incumbent possibility of leaking potentially corrosive and toxic battery contents) may be reduced or avoided. Another advantageous feature of such an arrangement is that the battery may be repeatedly cycled (i.e., charged and discharged) to near-zero-voltage conditions without significant decline in battery performance.

[0067] Various advantageous features may be obtained by utilizing batteries such as those shown and described herein. For example, use of such batteries may eliminate the need to

utilize circuitry to disconnect batteries approaching near-zero voltage conditions. By not utilizing circuitry for this function, volume and cost reductions may be obtained.

[0068] According to an exemplary embodiment, lithium-ion batteries such as those described above may be used in conjunction with medical devices such as medical devices that may be implanted in the human body (referred to as “implantable medical devices” or “TMD’s”).

[0069] FIGURE 6 illustrates a schematic view of a system 400 (e.g., an implantable medical device) implanted within a body or torso 432 of a patient 430. The system 400 includes a device 410 in the form of an implantable medical device that for purposes of illustration is shown as a defibrillator configured to provide a therapeutic high voltage (e.g., 700 volt) treatment for the patient 430.

[0070] The device 410 includes a container or housing 414 that is hermetically sealed and biologically inert according to an exemplary embodiment. The container may be made of a conductive material. One or more leads 416 electrically connect the device 410 and to the patient’s heart 420 via a vein 422. Electrodes 417 are provided to sense cardiac activity and/or provide an electrical potential to the heart 420. At least a portion of the leads 416 (e.g., an end portion of the leads shown as exposed electrodes 417) may be provided adjacent or in contact with one or more of a ventricle and an atrium of the heart 420.

[0071] The device 410 includes a battery 440 provided therein to provide power for the device 410. According to another exemplary embodiment, the battery 440 may be provided external to the device or external to the patient 430 (e.g., to allow for removal and replacement and/or charging of the battery). The size and capacity of the battery 440 may be chosen based on a number of factors, including the amount of charge required for a given patient’s physical or medical characteristics, the size or configuration of the device, and any of a variety of other factors. According to an exemplary embodiment, the battery is a 5 mAh battery. According to another exemplary embodiment, the battery is a 300 mAh battery. According to various other exemplary embodiments, the battery may have a capacity of between approximately 10 and 1000 mAh.

[0072] According to other exemplary embodiments, more than one battery may be provided to power the device 410. In such exemplary embodiments, the batteries may have the same capacity or one or more of the batteries may have a higher or lower capacity than

the other battery or batteries. For example, according to an exemplary embodiment, one of the batteries may have a capacity of approximately 500 mAh while another of the batteries may have a capacity of approximately 75 mAh.

[0073] According to another exemplary embodiment shown in FIGURE 7, an implantable neurological stimulation device 500 (an implantable neuro stimulator or INS) may include a battery 502 such as those described above with respect to the various exemplary embodiments. Examples of some neuro stimulation products and related components are shown and described in a brochure titled "Implantable Neurostimulation Systems" available from Medtronic, Inc.

[0074] An INS generates one or more electrical stimulation signals that are used to influence the human nervous system or organs. Electrical contacts carried on the distal end of a lead are placed at the desired stimulation site such as the spine or brain and the proximal end of the lead is connected to the INS. The INS is then surgically implanted into an individual such as into a subcutaneous pocket in the abdomen, pectoral region, or upper buttocks area. A clinician programs the INS with a therapy using a programmer. The therapy configures parameters of the stimulation signal for the specific patient's therapy. An INS can be used to treat conditions such as pain, incontinence, movement disorders such as epilepsy and Parkinson's disease, and sleep apnea. Additional therapies appear promising to treat a variety of physiological, psychological, and emotional conditions. Before an INS is implanted to deliver a therapy, an external screener that replicates some or all of the INS functions is typically connected to the patient to evaluate the efficacy of the proposed therapy.

[0075] The INS 500 includes a lead extension 522 and a stimulation lead 524. The stimulation lead 524 is one or more insulated electrical conductors with a connector 532 on the proximal end and electrical contacts (not shown) on the distal end. Some stimulation leads are designed to be inserted into a patient percutaneously, such as the Model 3487A Pisces-Quad[®] lead available from Medtronic, Inc. of Minneapolis Minn., and stimulation some leads are designed to be surgically implanted, such as the Model 3998 Specify[®] lead also available from Medtronic.

[0076] Although the lead connector 532 can be connected directly to the INS 500 (e.g., at a point 536), typically the lead connector 532 is connected to a lead extension 522. The

lead extension 522, such as a Model 7495 available from Medtronic, is then connected to the INS 500.

[0077] Implantation of an INS 520 typically begins with implantation of at least one stimulation lead 524, usually while the patient is under a local anesthetic. The stimulation lead 524 can either be percutaneously or surgically implanted. Once the stimulation lead 524 has been implanted and positioned, the stimulation lead's 524 distal end is typically anchored into position to minimize movement of the stimulation lead 524 after implantation. The stimulation lead's 524 proximal end can be configured to connect to a lead extension 522.

[0078] The INS 500 is programmed with a therapy and the therapy is often modified to optimize the therapy for the patient (i.e., the INS may be programmed with a plurality of programs or therapies such that an appropriate therapy may be administered in a given situation). In the event that the battery 502 requires recharging, an external lead (not shown) may be used to electrically couple the battery to a charging device or apparatus.

[0079] A physician programmer and a patient programmer (not shown) may also be provided to allow a physician or a patient to control the administration of various therapies. A physician programmer, also known as a console programmer, uses telemetry to communicate with the implanted INS 500, so a clinician can program and manage a patient's therapy stored in the INS 500, troubleshoot the patient's INS 500 system, and/or collect data. An example of a physician programmer is a Model 7432 Console Programmer available from Medtronic. A patient programmer also uses telemetry to communicate with the INS 500, so the patient can manage some aspects of her therapy as defined by the clinician. An example of a patient programmer is a Model 7434 Itrel[®] 3 EZ Patient Programmer available from Medtronic.

[0080] While the medical devices described herein (e.g., systems 400 and 500) are shown and described as a defibrillator and a neurological stimulation device, it should be appreciated that other types of implantable medical devices may be utilized according to other exemplary embodiments, such as pacemakers, cardioverters, cardiac contractility modulators, drug administering devices, diagnostic recorders, cochlear implants, and the like for alleviating the adverse effects of various health ailments. According to still other

embodiments, non-implantable medical devices or other types of devices may utilize batteries as are shown and described in this disclosure.

[0081] It is also contemplated that the medical devices described herein may be charged or recharged when the medical device is implanted within a patient. That is, according to an exemplary embodiment, there is no need to disconnect or remove the medical device from the patient in order to charge or recharge the medical device. For example, transcutaneous energy transfer (TET) may be used, in which magnetic induction is used to deliver energy from outside the body to the implanted battery, without the need to make direct physical contact to the implanted battery, and without the need for any portion of the implant to protrude from the patient's skin. According to another exemplary embodiment, a connector may be provided external to the patient's body that may be electrically coupled to a charging device in order to charge or recharge the battery. According to other exemplary embodiments, medical devices may be provided that may require removal or detachment from the patient in order to charge or recharge the battery.

[0082] It is also important to note that the construction and arrangement of the lithium-ion battery as shown and described with respect to the various exemplary embodiments is illustrative only. Although only a few embodiments of the present inventions have been described in detail in this disclosure, those skilled in the art who review this disclosure will readily appreciate that many modifications are possible (e.g., variations in sizes, dimensions, structures, shapes and proportions of the various elements, values of parameters, mounting arrangements, use of materials, colors, orientations, etc.) without materially departing from the novel teachings and advantages of the subject matter recited in the claims. Accordingly, all such modifications are intended to be included within the scope of the present invention as defined in the appended claims. Other substitutions, modifications, changes and omissions may be made in the design, operating conditions and arrangement of the preferred and other exemplary embodiments without departing from the scope of the present invention as expressed in the appended claims.

WHAT IS CLAIMED IS:

- 1 1. A lithium-ion battery comprising:
2 a positive electrode comprising a positive current collector, a first active
3 material, and a second active material; and
4 a negative electrode comprising a negative current collector, a third active
5 material, and a quantity of lithium in electrical contact with the negative current collector;
6 wherein the first active material, second active material, and third active
7 materials are configured to allow doping and undoping of lithium ions; and
8 wherein the second active material exhibits charging and discharging
9 capacity below a corrosion potential of the negative current collector and above a
10 decomposition potential of the first active material.
- 1 2. The lithium-ion battery as claimed in Claim 1, wherein the second active
2 material does not include lithium.
- 1 3. The lithium-ion battery as claimed in any of the preceding Claims, wherein
2 the positive electrode and the negative electrode have a zero voltage potential below the
3 corrosion potential of the negative current collector and above the decomposition potential
4 of the first active material.
- 1 4. The lithium-ion battery as claimed in any of the preceding Claims, wherein
2 the quantity of lithium is provided as finely divided lithium or in the form of a lithium patch
3 coupled to the negative current collector.
- 1 5. The lithium-ion battery as claimed in any of the preceding Claims, wherein
2 the negative current collector comprises a material selected from the group consisting of
3 copper, nickel, nickel alloys, aluminum, aluminum alloys, titanium, titanium alloys, and
4 combinations thereof.
- 1 6. The lithium-ion battery as claimed in any of the preceding Claims, wherein
2 the first active material comprises lithium.
- 1 7. The lithium-ion battery as claimed in Claim 6, wherein the first active
2 material comprises at least one of LiCoO_2 , $\text{LiCo}_x\text{Mn}_y\text{Ni}_{(1-x-y)}\text{O}_2$, $\text{LiNi}_x\text{Co}_y\text{Al}_z\text{O}_2$, and
3 $\text{LiCo}_x\text{Ni}_{(1-x)}\text{O}_2$.

- 1 8. The lithium-ion battery as claimed in Claim 2, wherein the second active
2 material comprises V_6O_{13} .
- 1 9. The lithium-ion battery as claimed in Claim 1, wherein the second active
2 material comprises $LiMn_2O_4$.
- 1 10. The lithium-ion battery as claimed in Claim 1, wherein the second active
2 material comprises a material selected from the group consisting of V_2O_5 , V_6O_{13} , $LiMn_2O_4$,
3 $Li_5Ti_4O_{12}$, Li_xVO_2 , $LiM_xMn_{(2-x)}O_4$, V_3O_8 , MoO_3 , TiS_2 , WO_2 , MoO_2 , RuO_2 , and
4 combinations thereof.
- 1 11. The lithium-ion battery as claimed in Claim 1 or 2, wherein the third active
2 material comprises a carbonaceous material or a lithium titanate material.
- 1 12. The lithium-ion battery as claimed in Claim 1 or 2, wherein the first active
2 material is selected from the group consisting of $LiCoO_2$, $LiCo_{1/3}Mn_{1/3}Ni_{1/3}O_2$,
3 $LiNi_xCo_yAl_zO_2$, $LiCo_xNi_{(1-x)}O_2$, and combinations thereof.
- 1 13. The lithium-ion battery as claimed in Claim 1, wherein the second active
2 material comprises $LiMn_2O_4$.
- 1 14. The lithium-ion battery as claimed in Claim 1 or 2, wherein the second active
2 material comprises a material selected from the group consisting of V_2O_5 , V_3O_8 , MoO_3 ,
3 TiS_2 , WO_2 , MoO_2 , RuO_2 , and combinations thereof.
- 1 15. The lithium-ion battery as claimed in any of the preceding Claims, wherein
2 the battery has a capacity between approximately 10 mAh and 1000 mAh.
- 1 16. The lithium-ion battery as claimed in any of the preceding Claims, wherein
2 the corrosion potential of the negative current collector is approximately 3.5 volts.
- 1 17. The lithium battery as claimed in any of the preceding Claims provided in a
2 medical device.
- 1 18. The lithium-ion battery as claimed in Claim 17, wherein at least a portion of
2 the medical device or system is configured for implantation into a body of a patient.

1 19. The lithium-ion battery as claimed in Claim 17 or 18, wherein the medical
2 device or system is selected from the group consisting of a neurological stimulation device,
3 a cardiac defibrillator, a cardiac pacemaker, a cardiac contractility modulator, a
4 cardioverter, a drug administration device, a cochlear implant, a hearing aid, a sensor, a
5 telemetry device, and a diagnostic recorder.




FIGURE 1




FIGURE 2




FIGURE 3





FIGURE 4



Capacity

FIGURE 5




FIGURE 6




FIGURE 7