




(86) Date de dépôt PCT/PCT Filing Date: 2006/05/01
 (87) Date publication PCT/PCT Publication Date: 2006/11/09
 (85) Entrée phase nationale/National Entry: 2007/11/02
 (86) N° demande PCT/PCT Application No.: US 2006/016538
 (87) N° publication PCT/PCT Publication No.: 2006/119153
 (30) Priorité/Priority: 2005/05/02 (US11/120,139)


(51) Cl.Int./Int.Cl. *A61K 9/50* (2006.01)
 (71) Demandeur/Applicant:
EURAND, INC., US
 (72) Inventeur/Inventor:
VENKATESH, GOPI, US
 (74) Agent: DEETH WILLIAMS WALL LLP

(54) Titre : SYSTEMES DE LIBERATION CHRONOCONTROLEE PAR IMPULSIONS
 (54) Title: TIMED, PULSATILE RELEASE SYSTEMS

Timed, Pulsatile-Release Profiles of Nizatidine of Ex. 1C
 (No Barrier Coating / Lag-time Coating)



Timed, Pulsatile Release Profiles of Propranolol HCl and Nizatidine
 (No Barrier Coating / BC/HPMCP (Lag-time) Coating)



(57) Abrégé/Abstract:

A unit multiparticulate dosage form for delivering one or more basic, active pharmaceutical ingredients into the body in need of such medications to achieve target PK (pharmacokinetics) profiles is described. The dosage form comprises one or more

(57) **Abrégé(suite)/Abstract(continued):**

multicoated drug particles (beads, pellets, mini-/micro-tablets) having a barrier coating and a lag-time coating. Each Timed Pulsatile Release (TPR) bead population exhibits predetermined lag-time followed by differing release characteristics. The composition and thickness of the barrier coating, composition and thickness of the lag-time coating, ratio of IR beads to one or more TPR bead populations and total dose may be varied depending on the alkalinity, pH-dependent solubility and elimination half-life of the active ingredients to achieve target PK profiles (suitable for a once or twice daily dosing regimen) in patients in need of such medications.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
9 November 2006 (09.11.2006)

PCT

(10) International Publication Number
WO 2006/119153 A3



- (51) International Patent Classification:
A61K 9/50 (2006.01)
- (21) International Application Number:
PCT/US2006/016538
- (22) International Filing Date: 1 May 2006 (01.05.2006)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
11/120,139 2 May 2005 (02.05.2005) US
- (71) Applicant (for all designated States except US): **EU-RAND, INC.** [US/US]; 845 Center Drive, Vandalia, Ohio 45377 (US).
- (72) Inventor; and
- (75) Inventor/Applicant (for US only): **VENKATESH, Gopi** [US/US]; 780 Waldsmith Way, Vandalia, Ohio 45377 (US).
- (74) Agents: **LEVY, Mark et al.; THOMPSON HINE LLP**, Post Office Box 8801, Dayton, Ohio 45401-8801 (US).

- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:
— with international search report

[Continued on next page]

(54) Title: TIMED, PULSATILE RELEASE SYSTEMS



(57) Abstract: A unit multiparticulate dosage form for delivering one or more basic, active pharmaceutical ingredients into the body in need of such medications to achieve target PK (pharmacokinetics) profiles is described. The dosage form comprises one or more multicoated drug particles (beads, pellets, mini-/micro-tablets) having a barrier coating and a lag-time coating. Each Timed Pulsatile Release (TPR) bead population exhibits predetermined lag-time followed by differing release characteristics. The composition and thickness of the barrier coating, composition and thickness of the lag-time coating, ratio of IR beads to one or more TPR bead populations and total dose may be varied depending on the alkalinity, pH-dependent solubility and elimination half-life of the active ingredients to achieve target PK profiles (suitable for a once or twice daily dosing regimen) in patients in need of such medications.

WO 2006/119153 A3

WO 2006/119153 A3



(88) Date of publication of the international search report:
31 May 2007

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

TIMED, PULSATILE RELEASE SYSTEMS**TECHNICAL FIELD**

[0001] The present invention relates to the development of timed, pulsatile release bead populations comprising one or more alkaline pharmaceutical actives exhibiting release of the drug after a predetermined delay (lag time) of more than about 5 hours and to the production of oral drug delivery systems to target PK (pharmacokinetics, i.e., plasma concentration-time) profiles suitable for a twice- or once-daily dosing regimen, thereby minimizing potential risks of adverse side effects, enhancing patient compliance and therapeutic efficacy, and reducing cost of treatment.

BACKGROUND OF THE INVENTION

[0002] Many therapeutic agents are most effective when made available at constant rates at or near the absorption sites. The absorption of therapeutic agents thus made available generally results in desired plasma concentrations leading to maximum efficacy, and minimum toxic side effects. Much effort has been devoted to developing sophisticated drug delivery systems such as osmotic devices for oral application. However, there are instances where maintaining a constant blood level of a drug is not desirable. For example, a major objective of chronotherapy for cardiovascular diseases is to deliver the drug in higher concentrations during the time of greatest need, e.g., the early morning hours, and in lesser concentrations when the need is less, e.g., during the late evening and early sleep hours. In addition to a properly designed drug delivery system, the time of administration is equally important. The unique pharmacokinetic profile needed can be calculated from a simulated modeling developed using the pharmacokinetic parameters, knowledge of drug solubility, absorption along the gastrointestinal tract and elimination half-life.

[0003] A timed, pulsatile delivery system capable of providing one or more immediate release pulses at predetermined lag times or at specific sites result in better absorption of the active and more effective plasma profile. However, there are only a few such orally applicable pulsatile release systems due to potential limitations of the dosage form size, and/or polymeric materials and their compositions used for producing dosage forms. Ishino et

al. disclose a dry-coated tablet form in Chemical Pharm. Bull. Vol. 40 (11), p3036-3041 (1992). U.S. Pat. No. 4,871,549 assigned to Fujisawa Pharmaceutical Company discloses the preparation of a time-controlled explosion system in which rapid-release pulses at predetermined time intervals are caused by explosion of the membrane surrounding the drug cores comprising swelling agents such as disintegrants (e.g., low-substituted hydroxypropylcellulose, crospovidone, crosslinked carboxymethylcellulose, sodium starch glycolate). These systems are rather difficult to manufacture and do not consistently perform.

[0004] U.S. Pat. No. 6,531,152 discloses an explosion-controlled drug delivery system comprising a core containing a drug in combination with a core material (such as a polysaccharide or a crosslinked protein and a disintegrant that swell on exposure to body fluids or water) having a rigid membrane comprising hydrophobic and hydrophilic polymers that bursts rapidly releasing the active when the core swells. The '152 patent discloses specific tablet formulations having lag-times of up to about 12 hours. U.S. Pat. No. 6,287,599 to Burnside et al. discloses a pharmaceutical composition (a tablet formulation) comprising at least one pharmaceutically active agent that has a pH dependent solubility, at least one non-pH dependent sustained release agent and at least one pH-dependent agent that increases the dissolution rate of the active at a pH in excess of 5.5. Such a system exhibits approximately pH independent drug release profile.

[0005] However, monolithic drug delivery systems exhibit variable gastrointestinal transit times, and multiparticulate dosage forms containing coated drug particles (beads, pellets or micro-tablets) exhibiting consistent GI transit times are preferred.

[0006] The pulsatile burst release times in the above-described delivery systems are controlled by choosing appropriate core material, and by varying the membrane composition and/or thickness. However, it is difficult to consistently manufacture quality products based on such drug delivery systems wherein the drug-release is controlled by a swelling agent, a hydrophobic excipient, an osmotic agent alone or mixtures thereof.

[0007] U.S. Pat. No. 6,627,223, assigned to Eurand Pharmaceutical Limited, which is incorporated herein by reference, discloses a pulsatile release system consisting of a combination of one or more bead populations, each with a well-defined release profile. A timed, sustained-release profile (i.e., a sustained-release profile over a 12 to 24 hours after a lag-time of about 4 hours (i.e., a period of little or no release) following oral administration is

disclosed in U.S. Pat. No. 6,500,454, and a biphasic release profile (i.e., an immediate-release pulse and a rapid burst after a lag-time of about 3 hours) is disclosed in U.S. Pat. No. 6,663,888. Although, a lag-time of greater than 3 hours could be achieved by applying a membrane comprising a water-insoluble polymer such as ethylcellulose (Ethocel Standard Premium 10 cps available from Dow Chemical Company) and an enteric polymer such as hydroxypropyl methylcellulose phthalate (HP-55 available from Shin-Etsu Chemical Corporation, Tokyo, Japan) on drug-layered beads containing propranolol hydrochloride (56% drug-load coated on 25-30 mesh sugar spheres) at 10-15% weight gain, the same coating composition applied on drug-layered beads containing nizatidine (56% drug-load coated on 25-30 mesh sugar spheres) even at 35-39% by weight resulted in a lag-time of less than 3 hours. It was considered in the prior art that the solubility of therapeutic agent in the dissolution medium and/or the molecular weight of the agent determined the drug dissolution within the coated bead and its diffusion out of the membrane. After extensive investigations, it was surprisingly discovered that apart from pH-dependent solubility of the therapeutic agent, its acidity/alkalinity has a significant effect on the lag-time that could be achieved. Additionally, the impact of a barrier coating (i.e., an intermediate coating applied in between the inner protective seal coat and the outer lag time coating, hereafter referred to as the barrier coat) and/or its composition on lag-time that could be achieved can vary depending on the acidity/alkalinity of the actives.

SUMMARY OF THE INVENTION

[0008] The present invention provides a pulsatile delivery system suitable for a twice-daily or once-daily dosing regimen by oral administration of a specific therapeutic agent depending on its acidity/alkalinity, solubility in gastrointestinal fluids, and its elimination half-life. The pulsatile delivery system comprises one or more bead populations, such as immediate release (IR) Beads and timed, pulsatile-release (TPR) bead populations. Each TPR bead population releases the drug as a rapid burst or as a sustained-release profile after a pre-determined lag-time (for example, 10 hours or longer is achievable) upon oral administration. The IR Beads may be simply drug cores coated with a protective membrane (for example, a coating with Opadry Clear). These IR Beads with a barrier coating are coated with a functional membrane of a mixture of water insoluble and enteric polymers, a plasticized polymeric system being applied from aqueous or solvent based composition. The finished dosage form may be a

modified-release (MR) capsule, a standard (conventional) tablet or an orally disintegrating tablet (ODT) comprising a coated spherical bead population containing the active substance alone or a combination of two or more coated bead populations to provide target plasma concentrations suitable for a once or twice-daily dosing regimen. For example, a once-daily dosage form of an active with an elimination half-life of about 7 hours may contain a mixture of an IR bead population which allows immediate release, a second, TPR bead population with a shorter lag-time (about 3-4 hours), which allows a delayed "burst" release and a third, TPR bead population with a longer lag-time (about 6-9 hours), which allows a delayed, typically sustained-release profile of an active with an elimination half-life of about 7 hours, thus enhancing safety, therapeutic efficacy and patient compliance while reducing cost of treatment. The achievable lag time depends on the composition and thickness of the barrier coating, the composition and thickness of the lag-time coating, as well as the nature of the therapeutic agent. Specific factors that can affect the lag-time include, but are not limited to, the therapeutic agent's alkalinity/acidity, solubility, elimination half-life, and dosing (twice-daily or once-daily) regimen.

BRIEF DESCRIPTION OF THE FIGURES

[0009] The invention will be described in further detail with reference to the accompanying Figures wherein:

Figure 1 shows drug release profiles of nizatidine IR beads (without a barrier coating) coated with EC/HPMCP at 20, 25 and 30% by weight of Example 1C.

Figure 2 shows drug-release profiles of propranolol hydrochloride IR beads (without a barrier coating) coated with EC/HPMCP at 20, 30 and 40% by weight of Example 2C.

Figure 3 shows drug release profiles of IR beads (without a barrier coating) coated with EC/HPMCP at 20% by weight (a) propranolol hydrochloride and (b) nizatidine and at 30% by weight (c) propranolol hydrochloride and (d) nizatidine.

Figure 4 shows drug release profiles of nizatidine IR beads coated first with a barrier coating of HPMCP and then coated with a lag-time coating at 20, 30 and 40% by weight of Example 1D.

Figure 5 shows drug release profiles of nizatidine IR beads coated first with a barrier coating of EC/HPC and then coated with a lag-time coating at 20, 30 and 40% by weight of Example 1E.

Figure 6 shows the effect of the barrier coating applied on nizatidine IR beads on the lag time achieved at a lag-time coating of 30% by weight: (A) None, (B) 10% HPMCP and (C) 5% 70/30 EC/HPC.

DETAILED DESCRIPTION OF THE INVENTION

[0010] Active pharmaceutical ingredients (API) typically are either slightly acidic or basic when suspended in purified water (see Table 1). The extent of acidity or alkalinity varies significantly. For example, the pH can range from as low as 5.7-6.5 for propranolol hydrochloride to a pH of 6.5-8.7 for nizatidine to as high as a pH of 7.9-11.0 for atenolol. An active pharmaceutical ingredient exhibiting a pH of 7.0, or less, when suspended in water at a solid content of 2 g/mL is designated as an acidic drug in this invention disclosure while an API exhibiting a pH of 7.0, or greater, is designated as an alkaline drug.

Table 1: pH of representative drugs suspended in water

Drug	Acidity/Alkalinity	PH of Solution/Suspension		
		0.2 g/mL	2.0 g/mL	20 g/mL
Propranolol Hydrochloride	Acidic	pH=6.5	pH=6.0	PH=6.5

Nizatidine	Alkaline	pH=5.7	pH=7.4	PH=8.7
Drug concentration (solid content)		0.1 g/mL	1.0 g/mL	10 g/mL
Cyclobenzaprine Hydrochloride	Acidic	pH=6.1	pH=6.5	pH=6.7
Atenolol	Alkaline	pH=7.9	pH=10.9	pH=11.0

[0011] Since the polymer blend system typically utilized to delay the onset of drug-release by several hours upon oral administration is a mixture of water-insoluble and enteric polymers, the extent of delayed onset depends on the acidity/alkalinity of the API. The present invention provides a method for manufacturing a pharmaceutically elegant multi-particulate dosage form having timed, pulsatile release profiles, i.e., a well time-controlled single pulse or a series of pulses occurring several hours after oral administration. The present invention also provides a multicoated, multiparticulate dosage form having an active core, an intermediate barrier-coating and an outer membrane of a mixture of water-insoluble polymer and an enteric polymer. A barrier coating applied on IR beads may comprise an enteric polymer, a water-insoluble polymer or a mixture of water-insoluble and water-soluble polymers. The polymers used in forming the barrier coating and the outer membrane may be plasticized.

[0012] In accordance with one aspect of the present invention, the active core of the dosage form may comprise an inert particle, which is coated with a drug-containing film-forming formulation and, in accordance with certain embodiments, an inert particle is coated with a water-soluble film forming composition to form a water-soluble/dispersible particle. The amount of drug in the core will depend on the drug and the dose that is desired. Generally, the core in accordance with this aspect of the invention will contain about 5 to 60% by weight of the drug based on the total weight of the core. Those skilled in the art will be able to select an appropriate amount of drug for coating or incorporation into the core to achieve the desired dosage form.

[0013] The active core of the dosage form of certain embodiments of the present invention may comprise an inert particle such as a sugar sphere with a desired mean particle size. In

one embodiment, the inactive core may be a sugar sphere, a cellulose sphere, a spheroidal silicon dioxide bead, a buffer crystal or an encapsulated buffer crystal, such as calcium carbonate, sodium bicarbonate, fumaric acid, tartaric acid, etc. Buffer crystals are useful to alter the microenvironment. Alternatively in accordance with other embodiments, drug-containing microgranules or pellets may be prepared by roto granulation, high-shear granulation and extrusion-spheronization or compression (as mini-/micro-tablets (about one/two mm in diameter)) of the drug, a polymeric binder and optionally fillers/diluents.

[0014] Active cores comprising an inert particle coated with a drug-containing film forming binder can be prepared in accordance with the following process. An aqueous or a pharmaceutically acceptable solvent medium may be used for preparing core particles based on coated inert particles. The type of inert binder that is used to bind the water-soluble drug to the inert particle is not critical but usually water soluble or alcohol soluble binders, such as polyvinylpyrrolidone (PVP or povidone) or hydroxypropylcellulose may be used. The binder may be used at any concentration capable of being applied to the inert particle. Typically, the binder is used at a concentration of about 0.5 to 10% by weight. The drug substance may be present in this coating formulation in solution form or may be suspended. The drug concentration may vary depending on the application but typically will be used at concentrations from about 10 to 30% by weight depending on the viscosity of the coating formulation.

[0015] In accordance with other embodiments, the active core may be prepared by roto granulation, or by granulation followed by extrusion-spheronization or tableting into micro-/mini-tablets. The drug substance, a binder, an optional dissolution rate controlling polymer, and optionally other pharmaceutically acceptable excipients (e.g., diluents/fillers) may be blended together in a high-shear granulator, such as Fielder granulator, or a fluid bed granulator, such as Glatt GPCG granulator, and granulated to form agglomerates by adding/spraying a granulating fluid such as water or alcohol and dried. The wet mass can be extruded and spheronized to produce spherical particles (pellets) using an extruder/marumerizer. The blend comprising drug particles, a binder and optionally a filler/diluent or drug-containing granules can also be compressed into mini-tablets (about 2 mm in diameter) or micro-tablets (about 1 mm in diameter) to produce IR pellets. In these embodiments, the drug load could be as high as 95% by weight based on the total weight of the extruded or granulated core.

[0016] Generally, the individual polymeric coatings on the active core will vary from about 1.5 to 60% by weight depending on the nature of the active, composition of the barrier coat, and required lag-time. In one embodiment, the core with a high drug-load may be provided with a barrier-coat of a plasticized water-insoluble polymer, such as ethylcellulose (EC), at about 1.5–15% by weight to sustain the drug-release over about 5-20 hours. In certain other embodiments, the core with a high drug-load may be provided with a barrier-coat of a plasticized enteric polymer, such as hydroxypropyl methylcellulose phthalate (HPMCP), at about 5–20% by weight. In yet another embodiment of the present invention, the active core may be provided with an outer lag-time coating of EC/HPMCP/plasticizer at about 45.5/40/14.5 for a weight gain of about 30-60% by weight to lengthen the lag-time up to about 10 hours or longer.

[0017] Both the barrier and outer (hereafter referred to as lag-time) membrane coatings on water-soluble/dispersible drug containing particles (IR beads) may comprise a plasticizer. The intermediate or barrier membrane may comprise an enteric polymer such as hydroxypropyl methylcellulose phthalate (HPMCP) or a water-insoluble polymer (e.g., ethylcellulose) alone or in combination with one or more water-soluble/pore-forming polymer such as HPMC, methyl cellulose, hydroxypropyl cellulose (HPC), polyethylene glycol (PEG) or polyvinylpyrrolidone (PVP). When the barrier coating comprises a water-insoluble polymer in combination with a water-soluble/pore-forming polymer, the polymers are typically present at a ratio from about 9:1 to 5:5, water-insoluble polymer to water-soluble polymer. The barrier coating is typically applied for a weight gain of from about 1.5 to 15% by weight.

[0018] The outer lag-time membrane may comprise a plasticized mixture of a water-insoluble polymer and an enteric polymer wherein the water-insoluble polymer and the enteric polymer may be present at a weight ratio of about 10:1 to 1:2 and typically about 3:1 to 1:1. The total weight of the lag coating varies from about 30 to 60% and more particularly from about 40 to 55% by weight based on the weight of the coated bead.

[0019] Cores comprising a slightly basic drug, such as nizatidine, may be provided with only the lag-time coating (no barrier coating) of EC/HPMCP/plasticizer at about 45.5/40/14.5 for a weight gain of about 40% by weight, which may result in a lag-time of about 3 hours or less. In contrast, cores comprising a slightly acidic drug, such as propranolol hydrochloride, may be provided with only the lag-time coating of EC/HPMCP/plasticizer at about

45.5/40/14.5 for a weight gain of about 40% by weight, which could result in a lag-time of about 6 hours or longer. Those skilled in the art will be able to select an appropriate amount of active for coating onto or incorporating into the core to achieve the desired dosage.

[0020] In accordance with one particular embodiment of the present invention, the water soluble/dispersible drug-containing particle is coated with a mixture of a water insoluble polymer and an enteric polymer. The water insoluble polymer and enteric polymer may be present at a weight ratio of from about 10:1 to 1:2, more particularly from about 2:1 to 1:1, and the total weight of the coatings is about 30 to 60% by weight based on the total weight of the coated beads. The polymeric coatings typically contain plasticizers and may be applied from aqueous and/or solvent-based systems.

[0021] The composition of the membrane layer and the individual weights of the polymers are important factors to be considered for achieving a desired lag time prior to appreciable drug release. The coated beads may optionally have a barrier layer of pharmaceutical glaze (shellac) under the lag-time coating, which basically dictates the lag time.

[0022] The invention also provides a method of making timed, pulsatile release beads comprising the steps of:

1. preparing drug-containing cores by coating inert particles, such as sugar spheres or cellulose spheres, with one or more active pharmaceutical ingredients from a polymeric binder solution/suspension and applying a protective seal-coat to form immediate release (IR) beads;
2. coating the IR beads with a plasticized a) water-insoluble polymer alone or in combination with a water-soluble polymer or b) enteric polymer to form barrier-coated beads with a membrane thickness of from about 1.5% to 20% by weight;
3. coating the barrier-coated beads with a plasticized mixture of a water-insoluble polymer and an enteric polymer with a membrane thickness of from about 40% to 60% by weight to form TPR (Timed Pulsatile Release) beads exhibiting a lag-time of up to about 10 hours or longer; and
4. filling two or more bead populations – IR beads and one or more TPR bead populations, wherein each TPR bead population may exhibit different lag-times

into hard gelatin capsules, or compressing into conventional tablets or orally disintegrating tablets, to produce a once-daily or twice-daily capsule formulation.

[0023] The release profiles for IR, barrier-coated and TPR beads may be determined according to the following procedure:

[0024] Dissolution testing of IR beads and enteric coated beads (for acid resistance testing) is conducted with a USP Apparatus 1 (baskets at 100 rpm) or Apparatus 2 (paddles at 50 rpm) in 900 mL of 0.1N HCl at 37°C while the dissolution testing of TPR beads is conducted in a USP apparatus using a two-stage dissolution medium (first 2 hours in 700 mL of 0.1N HCl at 37°C followed by dissolution testing at pH = 6.8 obtained by the addition of 200 mL of pH modifier). Drug release with time is determined by HPLC on samples pulled at selected intervals.

[0025] The TPR Beads prepared in accordance with present invention may be designed to provide a target drug-release profile, such as a rapid pulse or a sustained-release profile following a pre-determined lag-time. Even in the absence of the barrier coating, thicker lag-time coatings typically provide moderately sustained rather than rapid pulses (see Figure 3 for details). The multiparticulate dosage form may be provided as a single TPR bead population alone or a TPR bead population combined with an IR bead population and/or one or more additional TPR bead populations providing different release profiles. In accordance with one embodiment, a multiparticulate dosage form is provided with at least an IR bead population, a first TPR population and a second TPR population wherein the ratio of IR bead to the first and second TPR bead population varies from about 10/20/70 to about 30/60/10, respectively, depending on factors such as alkalinity, pH-dependent solubility, and/or elimination half-life of the active ingredient.

[0026] There are instances wherein the onset of drug release should begin several hours following oral administration to provide adequate plasma concentration to be suitable for a once-daily dosing regimen, depending on the elimination half-life of the active. In accordance with particular aspects of the invention, drug release may be delayed for up to about 10-15 hours after oral administration.

[0027] A single targeted sustained-release profile over several hours after oral administration, with or without an immediate release pulse, is provided in accordance with certain of the timed pulsatile release drug delivery systems of the present invention.

[0028] In accordance with one aspect of the invention, one or more active ingredients, a binder such as hydroxypropylcellulose (Klucel LF), a dissolution rate controlling polymer (if used), and optionally other pharmaceutically acceptable excipients are blended together in a high shear granulator such as Fielder or a fluid bed granulator such as Glatt GPCG 5 and granulated to form agglomerates by adding/spraying a granulating fluid such as water or alcohol and dried. The wet mass can be extruded and spheronized to produce spherical particles (beads) using an extruder/marumerizer. In accordance with another embodiment of the invention, dried granules may be compressed into pellets (i.e., mini or micro-tablets) with a diameter of about 1 mm to 2 mm. In these embodiments, the drug load could be as high as 95% by weight based on the total weight of the extruded/spheronized or mini-/micro-tablet core.

[0029] In accordance with a specific embodiment, the active containing cores (beads, pellets, mini-/micro-tablets or granular particles) thus obtained are coated with a lag-time coating comprising a water-insoluble polymer and an enteric polymer, such as ethylcellulose and hypromellose phthalate (i.e., hydroxypropyl methylcellulose phthalate or HPMCP) at a thickness from about 10 to 60%, more particularly from about 30% to 60%, by weight based on the total weight of the coated beads. The ratio of water insoluble polymer to enteric polymer may vary from about 10:1 to 1:2, more particularly from about 2:1 to 1:1.

[0030] An aqueous or a pharmaceutically acceptable solvent medium may be used for preparing core particles. The type of inert binder that is used to bind the water-soluble drug to the inert particle is not critical but usually water-soluble or alcohol soluble binders are used. Representative examples of binders include, but are not limited to, polyvinylpyrrolidone (PVP), hydroxypropyl methylcellulose (HPMC), hydroxypropylcellulose, carboxyalkylcelluloses, polyethylene oxide, polysaccharides such as dextran, corn starch, which may be dissolved or dispersed in water, alcohol, acetone or mixtures thereof. The binders are typically used at a concentration of from about 0.5 to 10% by weight.

[0031] Representative examples of enteric polymers useful in the invention include esters of cellulose and its derivatives (cellulose acetate phthalate, hydroxypropyl methylcellulose phthalate, hydroxypropyl methylcellulose acetate succinate), polyvinyl acetate phthalate, pH-sensitive methacrylic acid-methamethacrylate copolymers and shellac. These polymers may be used as a dry powder or an aqueous dispersion. Some commercially available materials that may be used are methacrylic acid copolymers sold under the trademark Eudragit (L100, S100, L30D) manufactured by Rohm Pharma, Cellacefate (cellulose acetate phthalate) from Eastman Chemical Co., Aquateric (cellulose acetate phthalate aqueous dispersion) from FMC Corp. and Aqoat (hydroxypropyl methylcellulose acetate succinate aqueous dispersion) from Shin Etsu K.K.

[0032] Representative examples of water-insoluble polymers useful in the invention include ethylcellulose, polyvinyl acetate (for example, Kollicoat SR#30D from BASF), cellulose acetate, cellulose acetate butyrate, neutral copolymers based on ethyl acrylate and methylmethacrylate, copolymers of acrylic and methacrylic acid esters with quaternary ammonium groups such as Eudragit NE, RS and RS30D, RL or RL30D and the like.

[0033] Dissolution rate controlling polymers suitable for incorporating in the formulation for producing granules by high shear or fluid bed granulation or by dry granulation include high molecular weight hydroxypropyl methylcellulose, hydroxypropyl cellulose, ethyl cellulose, sodium carboxymethyl cellulose, alginic acid, polymethylmethacrylate copolymers and polyvinyl acetate/crotonic acid copolymer or combinations thereof.

[0034] Both enteric and water-insoluble polymers used in forming the membranes are usually plasticized. Representative examples of plasticizers that may be used to plasticize the membranes include triacetin, tributyl citrate, triethyl citrate, acetyl tri-n-butyl citrate, diethyl phthalate, castor oil, dibutyl sebacate, acetylated monoglycerides, acetylated diglycerides and the like or mixtures thereof. The plasticizer, when used, may comprise about 3 to 30 wt.% and more typically about 10 to 25 wt.% based on the polymer. The type of plasticizer and its content depends on the polymer or polymers and nature of the coating system (e.g., aqueous or solvent based, solution or dispersion based and the total solids).

[0035] In general, it is desirable to prime the surface of the particle before applying the membrane coatings or to separate the different membrane layers by applying a thin

hydroxypropyl methylcellulose (HPMC) (Opadry Clear) film. While HPMC is typically used, other primers such as hydroxypropylcellulose (HPC) can also be used.

[0036] The active pharmaceutical ingredients suitable for incorporation into these time-controlled pulsatile release systems include basic bioactive molecules or their salts. The drug substance can be selected from the group of pharmaceutically acceptable chemical entities with proven pharmacological activity in humans. Representative examples include analgesics, anticonvulsants, antidiabetic agents, anti-infective agents, antineoplastics, antiParkinsonian agents, antirheumatic stimulants, cardio vascular agents, CNS (central nervous system) stimulants, dopamine receptor agonists, gastrointestinal agents, psychetherapeutic agents, opioid agonists, opioid antagonists, urinary tract agents, antiemetics, anti-epileptic drugs, histamine H₂ antagonists, skeletal muscle relaxants, and antiasthmatic agents.

[0037] The membrane coatings can be applied to the core using any of the coating techniques commonly used in the pharmaceutical industry, but fluid bed coating is particularly useful. The present invention is directed to multi-dose forms, i.e., drug products in the form of multi-particulate dosage forms (hard gelatin capsules, conventional tablets or ODTs (orally disintegrating tablets)) comprising one or more bead populations for oral administration to provide target PK profiles in patients in need of treatment. The conventional tablets rapidly disperse on entry into the stomach while ODTs rapidly disintegrate in the oral cavity forming a suspension of coated beads for easy swallowing. One or more coated bead populations may be compressed together with appropriate excipients into tablets (for example, a binder, a diluent/filler, and a disintegrant for conventional tablets while a rapidly dispersing granulation may replace the binder-diluent/filler combination in ODTs).

[0038] The following non-limiting examples illustrate the capsule dosage forms comprising one or more pulses, each with a predetermined delayed-onset and the totality of the *in vitro* drug-release profile or the ensuing *in vivo* plasma concentration profile upon oral administration of the dosage form should mimic the desired profile to achieve maximum therapeutic efficacy to enhance patient compliance and quality of life. Such dosage forms, when administered at the 'right time', would enable maintaining drug plasma concentration at a level potentially beneficial in minimizing the occurrence of side-effects associated with C_{max} or C_{min}.

Example 1 (Inventive):A. IR Beads of Nizatidine

[0039] Nizatidine (168 kg) was slowly added to an aqueous solution of hydroxypropylcellulose such as Klucel LF (18.6 kg) and mixed well. # 25-30 mesh sugar spheres (107.4 kg) were coated with the drug suspension in a Glatt fluid bed coater, equipped with a 32" bottom spray Wurster insert. The drug containing particles were dried, and a seal coat of Opadry Clear (2% w/w) was first applied and dried in the Glatt fluid bed unit as a precautionary measure to drive off excessive surface moisture. The drug load was 56% w/w.

B. Nizatidine Beads with a Barrier-coating of HPMCP:

[0040] IR beads produced above were coated in Glatt GPCG 5 equipped with a bottom spray Wurster insert with HPMCP (e.g., hypromellose phthalate, HP-55 commercially available from Shin Etsu) and triethyl citrate (TEC) as a plasticizer at a ratio of 90/10 dissolved in 98/2 acetone/water for a weight gain of 10% based on the weight of the coated beads.

C. Nizatidine TPR Beads without a Barrier-coating of HPMCP:

[0041] Drug containing IR Beads from Step A above were provided with an outer membrane by spraying a solution of 45.5/40/14.5 EC/HPMCP/TEC (ethylcellulose / HPMCP / triethylcitrate) in 98/2 acetone/water in a fluid bed coater for a weight gain of approximately 20%, 25% and 30%. The coated particles were unit cured at 60°C for 10 minutes to produce TPR Beads (batch size: 4 kg).

D. Nizatidine TPR Beads with a Barrier-coating of HPMCP:

[0042] The enteric-coated beads from Step B above were provided with an outer membrane by spraying a solution of 45.5/40/14.5 EC/HPMCP/TEC in 98/2 acetone/water in a fluid bed coater for a weight gain of approximately 20%, 30%, and 40%. The coated particles were unit cured at 60°C for 10 minutes to produce TPR Beads (batch size: 4 kg).

E. Nizatidine TPR Beads with a Barrier-coating of EC/HPC:

[0043] IR beads produced above (Step A) were coated in Glatt GPCG 5 equipped with a bottom spray Wurster insert with ethylcellulose and hydroxypropylcellulose (e.g., Klucel LF commercially available from Aqualon) at a ratio of 70/30 dissolved in acetone/water plasticized with TEC for a weight gain of 5% based on the weight of the coated beads. These barrier-coated beads were provided with an outer membrane by spraying a solution of 45.5/40/14.5 EC/HPMCP/TEC in 98/2 acetone/water in a fluid bed coater for a weight gain of approximately 20%, 30% and 40%. The coated particles were unit cured at 60°C for 10 minutes to produce TPR Beads (batch size: 4 kg).

Example 2 (Comparative):**A. IR Beads of Propranolol HCl:**

[0044] Propranolol HCl (168 kg) was slowly added to an aqueous solution of polyvinylpyrrolidone (8.8 kg Povidone K-30) and mixed well. 25-30 mesh sugar spheres (117.2 kg) were coated with the drug solution in a Glatt fluid bed granulator equipped with 32" bottom spray Wurster insert. The drug containing pellets were dried, and a seal coat of Opadry Clear (6.0 kg) was first applied and dried in the Glatt fluid-bed unit as a precautionary measure to drive off excessive surface moisture. The drug load was 56% w/w.

B. Propranolol HCl Beads with a Barrier-coating of HPMCP:

[0045] IR beads produced above were coated in Glatt GPCG 5 equipped with a bottom spray Wurster insert with HPMCP and TEC at a ratio of 90/10 dissolved in 98/2 acetone/water for a weight gain of 10% based on the weight of the coated beads.

C. Propranolol HCl TPR Beads (without barrier-coating):

[0046] IR beads produced in Step A above were coated in Glatt GPCG 5 with ethylcellulose, HPMCP and triethyl citrate at a ratio of 45.5/40/14.5 dissolved in 98/2

acetone/water for a weight gain of 20%, 30% and 40% based on the weight of the coated beads.

D. Propranolol HCl TPR Beads (with a barrier-coat of EC):

[0047] IR beads produced in Step Aabove were coated in fluid-bed equipment (Fluid Air FA0300 equipped with a 32" bottom spray Wurster insert) with ethylcellulose and diethyl phthalate (DEP) as a plasticizer at a ratio of 90/10 for a weight gain of 1.8% by weight. This coating was followed by a lag-time coating of EC/HPMCP/DEP at a ratio of 45.5/40/14.5 dissolved in 98/2 acetone/water for a weight gain of 15%, based on the weight of the coated beads.

[0048] Drug Release Testing: The drug release profiles were generated by dissolution testing per US Pharmacopoeia method (Apparatus 1 with baskets at 100 rpm or Apparatus 2 with paddles at 50 rpm) using 700 mL of p H 1.2 buffer for 2 hours followed by testing in 900 mL of pH 6.8 for the remaining time-points). The IR and enteric-coated beads were tested in 900 mL of 0.1N HCl for 1 and 1.5 hrs, respectively. The samples pulled at different time-points were quantified by HPLC.

Example 3

Stability of Coated Beads:

[0049] Nizatidine TPR beads of Example 1D coated with EC/HPMCP at 40% were packaged in induction-sealed HDPE bottles, placed on stability at 40°C/75%RH and samples were pulled at 1, 2, 3 and 6-month time points. Dissolution tests were performed using the procedures detailed above. The TPR beads stored at accelerated stability conditions exhibited acceptable stability for at least 6 months.

Drug Release Profile:

[0050] Finished capsules may comprise one or more TPR bead populations with desired lag-times or in combination with IR beads at a desired ratio and in sufficient quantities to provide target *in vitro* drug-release profiles and hence target pharmacokinetics (PK) profiles suitable for a twice-daily or once-daily dosing regimen. When tested under *in vitro*

conditions following the dissolution test procedure listed above, the IR beads which are designed to provide a loading dose typically release substantially all of the drug within the first hour, preferably within the first 30 minutes. The Timed Pulsatile Release (TPR) Beads are designed to begin releasing the drug after a lag-time of up to several hours (a period of minimal drug-release (less than about 10% of the dose) following oral administration). The pulse may be a rapid burst or spread over a period ranging from about 2 hours to about 20 hours depending on the thickness of the lag-time coating and/or the barrier-coat.

Acid-resistance of Nizatidine and Propranolol Beads Coated with HPMCP

[0051] The enteric polymer coating applied on nizatidine IR beads of Example 1B more or less disintegrated within an hour releasing most of the dose in the acidic buffer although the enteric polymer was not supposed to dissolve. In contrast, the enteric-coated beads of propranolol hydrochloride of Example 2B exhibited the expected acid-resistant property by releasing not more than 1% of the dose in 1.5 hours of dissolution testing at pH 1.2.

Although not wishing to be bound by theory, it appears the water imbibed into the core of coated nizatidine beads dissolves some nizatidine creating an alkaline pH environment, which tends to destroy the enteric polymer membrane on the enteric coated IR beads, even though the dissolution medium is acidic.

Effect of Barrier-coat on Lag-time:

[0052] From a comparison of Figures 1 and 2, which depict the drug-release profiles of TPR beads without a barrier coat, it is clear that the TPR beads of nizatidine, a slightly alkaline drug, coated with EC/HPMCP at 30% by weight exhibits a lag-time of less than 3 hours. In contrast, the TPR beads of propranolol HCl, a slightly acidic drug, coated with the same polymer blend at the same coating thickness exhibits a lag-time of about 5 hours. From a comparison of the lag-times observed from Nizatidine and propranolol HCl TPR beads at identical coating conditions and compositions, it is evident that the acidity/alkalinity plays a major role in providing the lag time (Fig. 3).

[0053] Figs. 4 and 5 demonstrate the effect of a barrier coating on the lag time that can be achieved for nizatidine beads. For example, at the coating of 40% by weight, an enteric-

polymer barrier provides a lag time of about 5 hours while a more hydrophobic barrier of EC/HPC enables achieving a lag time of about 8 hours. These differences become clearer from Fig. 6, which shows the drug-release profiles from TPR beads at 30% coating: i) with no barrier coating; ii) with a barrier coating of an enteric polymer; or iii) a hydrophobic polymer blend. It is evident that a barrier coating with a hydrophobic water-insoluble polymer such as ethylcellulose provides longer lag times as compared to a barrier coating of an enteric polymer from TPR beads of alkaline drugs.

[0054] From these demonstrations, it is apparent that the alkalinity/acidity of the active pharmaceutical ingredient has a significant impact on the lag time that can be achieved at given coating conditions. Another active such as atenolol which is more alkaline than nizatidine would be expected to show shorter lag time than nizatidine. Of course, the lag time can be increased by providing a barrier coating comprising an appropriate polymer alone or in combination with a membrane modifier (for example, hydrophobic ethylcellulose alone or together with water-soluble hydroxypropylcellulose). The membrane thickness can be varied to further fine-tune the lag time.

[0055] While the invention has been described in detail and with respect to specific embodiments thereof, it will be apparent that numerous modifications and variations are possible without departing from the scope of the invention as defined by the following claims.

What is claimed is:

1. A pharmaceutical multiparticulate dosage form comprising a mixture of immediate release (IR) beads and timed, pulsatile release (TPR) beads, wherein said TPR beads comprise:
 - a) a core particle comprising one or more basic, active pharmaceutical ingredients or pharmaceutically acceptable salts thereof;
 - b) an inner barrier coating surrounding said core particle, said barrier coating comprising: i) an enteric polymer, or ii) a water-insoluble polymer alone or in combination with a water-soluble pore-forming polymer; and
 - c) an outer lag-time coating comprising a water-insoluble polymer in combination with an enteric polymer, said outer membrane providing a lag time of at least about 5 hours before onset of drug release.
2. A pharmaceutical multiparticulate dosage form claim 1 wherein the active pharmaceutical ingredient is selected from the group consisting of analgesics, anticonvulsants, antidiabetic agents, anti-infective agents, antineoplastics, antiParkinsonian agents, antirheumatic agents, cardiovascular agents, CNS (central nervous system) stimulants, dopamine receptor agonists, anti-emetics, gastrointestinal agents, psychotherapeutic agents, opioid agonists, opioid antagonists, anti-epileptic drugs, histamine H₂ antagonists, anti-asthmatic agents, and skeletal muscle relaxants.
3. A pharmaceutical multiparticulate dosage form in accordance with claim 1 comprising two or more bead populations to provide target pharmacokinetic profiles suitable for a once or twice-daily dosing regimen, wherein each population exhibits a predetermined (target) drug-release profile when dissolution tested using USP Apparatus 1 or 2 and a two-stage dissolution media (first two hours in 700 mL of 0.1N HCl and thereafter in 900 mL at pH 6.8).
4. A pharmaceutical multiparticulate dosage form in accordance with claim 1 comprising at least an IR bead population, a first TPR bead population and a second TPR bead population wherein the ratio of IR bead to the first and second TPR bead populations varies from about 10/20/70 to about 30/60/10, respectively, depending on

the alkalinity, pH-dependent solubility and/or elimination half-life of the active ingredient.

5. A pharmaceutical multiparticulate dosage form in accordance with claim 1, wherein said core particle comprises:
 - i) an inert particle coated with an active ingredient and a polymeric binder; or
 - ii) a pellet or mini- or micro-tablet containing the active ingredient, a polymeric binder and a diluent/filler, prepared by rotogranulation, granulation-extrusion-spheronization or granulation-tableting.
6. A pharmaceutical multiparticulate dosage form in accordance with claim 5 wherein said polymeric binder is selected from the group consisting of polyvinylpyrrolidone, methylcellulose, hydroxypropylcellulose, hydroxypropyl methylcellulose, corn starch, pregelatinized starch and mixtures thereof.
7. A pharmaceutical multiparticulate dosage form in accordance with claim 1 wherein said particle barrier coating comprises an enteric polymer selected from the group consisting of cellulose acetate phthalate, hydroxypropyl methylcellulose phthalate, hydroxypropyl methylcellulose succinate, polyvinyl acetate phthalate, pH-sensitive methacrylic acid-methylmethacrylate copolymers, shellac, derivatives thereof, and mixtures thereof.
8. A pharmaceutical multiparticulate dosage form in accordance with claim 7 wherein the barrier coating comprises from about 5 to 20% by weight of the barrier coated bead.
9. A pharmaceutical multiparticulate dosage form in accordance with claim 1 wherein particle core is provided with a barrier coating comprising a water-insoluble polymer alone or in combination with a water soluble polymer at a ratio of from about 9:1 to 5:5 wherein said barrier coating is applied for a weight gain of from about 1.5% to 15% by weight based on the weight of the coated bead.

10. A pharmaceutical dosage form in accordance with claim 9 wherein said water-soluble polymer is selected from the group consisting of such as methylcellulose, hydroxypropyl methylcellulose, hydroxypropylcellulose, polyvinyl pyrrolidone and polyethylene glycol and mixtures thereof.
11. A pharmaceutical dosage form in accordance with claim 1 wherein the outer lag-time coating comprises the water-insoluble polymer and the enteric polymer at a ratio of from about 10:1 to 1:2, respectively, for a weight gain of from about 30% to 60% by weight based on the weight of the TPR bead.
12. A pharmaceutical dosage form in accordance with claim 11 wherein said water-insoluble polymer is selected from the group consisting of ethylcellulose, cellulose acetate, polyvinyl acetate, methylmethacrylate ester polymers and mixtures thereof.
13. A pharmaceutical dosage form in accordance with claim 1 wherein at least one of the inner barrier coating and the outer lag-time coating comprises a plasticizer selected from the group consisting of triacetin, tributyl citrate, tri-ethyl citrate, acetyl tri-n-butyl citrate, diethyl phthalate, dibutyl sebacate, polyethylene glycol, polypropylene glycol, castor oil, acetylated mono- and di-glycerides and mixtures thereof.
14. A pharmaceutical dosage form in accordance with claim 1 wherein said lag-time coating comprises water insoluble and enteric polymers at a ratio varying from approximately 3:1 to approximately 1:1, respectively.
15. A pharmaceutical dosage form in accordance with claim 1 wherein said dosage form further comprises immediate release (IR) beads, which provide a loading dose by releasing not less than about 90% of the active contained in said IR beads within the first hour after oral administration of the dosage form.
16. A pharmaceutical dosage form in accordance with claim 1 wherein said dosage form comprises at least two timed, pulsatile release (TPR) bead populations, wherein each TPR bead population exhibits upon oral administration of the dosage form a pre-determined lag-time followed by differing release characteristics.

17. A pharmaceutical dosage form in accordance with claim 1 wherein said lag-time coating comprises ethylcellulose and hydroxypropyl methylcellulose phthalate.
18. A method for the preparation of a multiparticulate dosage form comprising:
- a) preparing IR (immediate-release) beads comprising one or more basic active pharmaceutical ingredients or pharmaceutically acceptable salts thereof;
 - b) applying a barrier coating on said IR beads, said barrier coating comprising an enteric polymer or a water-insoluble polymer for a weight gain of from about 1.5% to 20% by dry weight of the coated bead;
 - c) applying an outer lag-time coating comprising a water-insoluble polymer in combination with an enteric polymer at a ratio of from about 10:1 to 1:2, respectively, for a weight gain of from about 30% to 60% by dry weight of the coated bead to form a Timed, Pulsatile Release (TPR) bead; and
 - d) filling into gelatin capsules or compressing into conventional tablets or ODTs (orally disintegrating tablets) one or more TPR bead populations at appropriate amounts to achieve target PK (pharmacokinetics) profiles (suitable for a once- or twice daily dosing regimen) in patients in need of such active pharmaceutical ingredients.
19. A method in accordance with claim 18, wherein said outer lag-time coating is applied from a solution in a pharmaceutically acceptable solvent system or from an aqueous dispersion.
20. A method in accordance with claim 18 wherein said pharmaceutical dosage form is in the form of a hard gelatin capsule, a conventional tablet rapidly disintegrating into coated beads upon entry into the stomach, or an orally disintegrating tablet rapidly disintegrating in the oral (buccal) cavity forming easy-to-swallow suspensions.
21. A method in accordance with claim 18 wherein said pharmaceutical dosage form further comprises IR beads to provide target PK release profiles in patients in need of such a treatment.

22. A method comprising orally administering to a patient a dosage form in accordance with claim 1 containing therapeutically effective amounts of one or more active pharmaceutical ingredients.

23. A method comprising orally administering to a patient a dosage form in accordance with claim 1 wherein the dosage form comprises therapeutically effective amounts of IR and one or more multicoated TPR bead populations of one or more active pharmaceutical ingredients, each multicoated TPR bead population exhibiting a lag-time of at least 5 hours, followed by differing release characteristics.

1/3

Timed, Pulsatile-Release Profiles of Nizatidine of Ex. 1C
(No Barrier Coating / Lag-time Coating)




FIG. 1

Timed, Pulsatile Release Profiles for Propranolol HCl of Ex. 2C
(No Barrier Coating / EC/HPMCP (Lag-time) Coating)




FIG. 2

2/3

Timed, Pulsatile Release Profiles of Propranolol HCl and Nizatidine
(No Barrier Coating / EC/HPMCP (Lag-time) Coating)




FIG. 3

Timed, Pulsatile-Release Profiles of Nizatidine of Ex. 1D
(HPMCP Coating at 10% / EC/HPMCP (Lag-time) Coating)




FIG. 4

3/3

Timed, Pulsatile Release Profiles of Nizatidine of Ex. 1E
(EC/HPC (Klucel) at 5% / EC/HPMCP (Lag-time) Coating)




FIG. 5

Timed, Pulsatile Release Profiles of Nizatidine
(Barrier Coating / EC/HPMCP (Lag-time Coating at 30%))





FIG. 6

Timed, Pulsatile-Release Profiles of Nizatidine of Ex. 1C
(No Barrier Coating / Lag-time Coating)



Timed, Pulsatile Release Profiles of Propranolol HCl and Nizatidine
(No Barrier Coating / EC/HPMCP (Lag-time) Coating)

