



- (51) **International Patent Classification:**
H01L 51/00 (2006.01) *C08G 77/04* (2006.01)
- (21) **International Application Number:**
PCT/EP2016/000392
- (22) **International Filing Date:**
4 March 2016 (04.03.2016)
- (25) **Filing Language:** English
- (26) **Publication Language:** English
- (30) **Priority Data:**
15000920.7 30 March 2015 (30.03.2015) EP
- (71) **Applicant:** MERCK PATENT GMBH [DE/DE]; Frankfurter Strasse 250, 64293 Darmstadt (DE).
- (72) **Inventors:** BÉALLE, Gaëlle; Werderstrasse 20, 69120 Heidelberg (DE). LEONHARD, Christoph; Die Halde 14, 64853 Otzberg (DE). TSENG, Hsin-Rong; Walter-Leiske-Strasse 37, 60320 Frankfurt am main (DE). MARTYN-OVA, Irina; Pfungstaedter Strasse 7A, 64347 Griesheim (DE). LUDEMANN, Aurélie; Lersnerstrasse 24, 60322 Frankfurt am Main (DE).

- (81) **Designated States** (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.
- (84) **Designated States** (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))



WO 2016/155866 A1

(54) **Title:** FORMULATION OF AN ORGANIC FUNCTIONAL MATERIAL COMPRISING A SILOXANE SOLVENT

(57) **Abstract:** The present invention relates to a formulation for manufacturing organic semiconducting devices containing at least one organic functional material and at least a first and a second solvent, characterized in that the first solvent is a siloxane. Preferably, the siloxane is a cyclic siloxane selected from octamethylcyclotetrasiloxane, decamethylcyclopentasiloxane, dodecamethylcyclohexasiloxane, tetradecamethylcycloheptasiloxane, hexaethylcyclotrisiloxane, octaethylcyclotetrasiloxane, 2,4,6,8,10-pentaethyl-2,4,6,8,10-pentamethylcyclopentasiloxane and 2,4,6-triethyl-2,4,6-trimethylcyclotrisiloxane.

FORMULATION OF AN ORGANIC FUNCTIONAL MATERIAL COMPRISING A SILOXANE SOLVENT

Technical Field

5 The present invention relates to formulations containing at least one organic functional material and at least a first and a second solvent, characterized in that the first solvent is a siloxane, as well as to electroluminescent devices prepared by using these formulations.

Background Art

10 Organic Light Emitting Devices (OLEDs) have been fabricated for a long time by vacuum deposition processes. Other techniques such as inkjet printing have been recently thoroughly investigated because of their advantages such as cost savings and scale-up possibilities. One of the main challenges in multi-layer printing is to identify the relevant parameters
15 to obtain a homogeneous deposition of inks on the substrate. To trigger these parameters, such as surface tension, viscosity or boiling point, some additives can be added to the formulation. As an example, (cyclic)siloxanes added in very small quantities (ratio additive to solvent : 0.0001 to 0.5 % m/v, WO 03/019693) are remarkably efficient in promoting the wetting and
20 the leveling of various surfaces. They can also be used as a solvent for inorganic semiconductors for inkjet printing (WO 200946148).

Technical Problem and Object of the Invention

25 Many solvents have been proposed in organic electronic devices for inkjet printing. However, the number of important parameters playing a role during deposition and the drying process makes the choice of the solvent very challenging. Thus, the formulations containing organic semiconductors used for deposition by inkjet printing still need to be improved. One object of the present invention is to provide a formulation of an organic
30 semiconductor which allows a controlled deposition to form organic semiconductor layers having good layer properties and efficiency performance. A further object of the present invention is to provide a

formulation of an organic semiconductor which allows an uniform application of ink droplets on a substrate when used in an inkjet printing method thereby giving good layer properties and efficiency performance. It is also a further object of the present invention to improve the wetting properties of the inks on substrates and underlying layers which results in a higher homogeneity of light emission.

Solution to Problem

The above objects of the present invention are solved by providing a formulation comprising an organic functional material and a mixture of at least a first and a second solvent, wherein the first solvent is a siloxane, preferably a cyclosiloxane.

Advantageous Effects of Invention

The inventors have surprisingly found that the addition of a siloxane as first solvent allows a complete control of the surface tension and induces an effective ink deposition to form uniform and well-defined organic layers of functional materials which have good layer properties and performance.

Brief Description of Drawings

Figure 1 shows a typical layer structure of a device containing a substrate, an ITO anode, a hole-injection layer (HIL), a hole-transport layer (HTL), a green-emissive layer (G-EML), a blue-emissive layer (B-EML), an electron-transport layer (ETL) and an Al cathode.

Figure 2 shows the layer structure of a device which is used in Examples 3 and 4 and the Reference. The device contains a substrate, an ITO anode, a hole-injection layer (HIL), a hole-transport layer (HTL), a green-emissive layer (G-EML), a hole-blocking layer (HBL), an electron-transport layer (ETL) and an Al cathode.

30


Description of Embodiments

The present invention relates to a formulation containing at least one organic functional material and at least a first and a second solvent, characterized in that the first solvent is a siloxane.

5 Preferred Embodiments

In a first preferred embodiment, the first solvent is a cyclosiloxane. The cyclosiloxane is preferably a cyclosiloxane according to general formula (I)

10



wherein

15

R^1 and R^2 are identical or different at each occurrence, and are H, D, F, Cl, Br, I, NO_2 , CN, a straight-chain alkyl or alkoxy group having from 1 to 20 carbon atoms or a branched or cyclic alkyl or alkoxy group having from 3 to 20 carbon atoms, in which one or more nonadjacent CH_2 groups may be replaced by $-\text{O}-$, $-\text{S}-$, $-\text{NR}^5-$, $-\text{CONR}^5-$, $-\text{CO}-\text{O}-$, $-\text{C}=\text{O}-$, $-\text{CH}=\text{CH}-$ or $-\text{C}\equiv\text{C}-$, and in which one or more hydrogen atoms may be replaced by F, or an aryl or heteroaryl group which has from 4 to 14 carbon atoms and may be substituted by one or more nonaromatic R^5 radicals, and a plurality of substituents R^5 , either on the same ring or on the two different rings, may together in turn form a mono- or polycyclic, aliphatic or aromatic ring system;


25

R^5 are identical or different at each instance, and are a straight-chain alkyl or alkoxy group having from 1 to 20 carbon atoms or a branched or cyclic alkyl or alkoxy group having from 3 to 20 carbon atoms, in which one or more nonadjacent CH_2 groups may be replaced by $-\text{O}-$, $-\text{S}-$, $-\text{CO}-\text{O}-$, $-\text{C}=\text{O}-$, $-\text{CH}=\text{CH}-$ or $-\text{C}\equiv\text{C}-$, and in which one or more hydrogen atoms may be replaced by F, or an aryl or heteroaryl group which has from 4 to 14 carbon atoms and may be substituted by one or more nonaromatic R^5 radicals; and

30

n is in the range from 3 to 9, preferably 4, 5, 6 or 7 and more preferably 5 or 6.

In a second preferred embodiment, the first solvent is a siloxane according to general formula (II)











wherein

R¹, R², R³ and R⁴ are identical or different at each occurrence, and are H, D, F, Cl, Br, I, NO₂, CN, a straight-chain alkyl or alkoxy group having from 1 to 20 carbon atoms or a branched or cyclic alkyl or alkoxy group having from 3 to 20 carbon atoms, in which one or more nonadjacent CH₂ groups may be replaced by -O-, -S-, -NR⁵-, CONR⁵-, -CO-O-, -C=O-, -CH=CH- or -C≡C-, and in which one or more hydrogen atoms may be replaced by F, or an aryl or heteroaryl group which has from 4 to 14 carbon atoms and may be substituted by one or more nonaromatic R⁵ radicals, and a plurality of substituents R⁵, either on the same ring or on two different rings, may together in turn form a mono- or polycyclic, aliphatic or aromatic ring system;

R⁵ are identical or different at each instance, and are a straight-chain alkyl or alkoxy group having from 1 to 20 carbon atoms or a branched or cyclic alkyl or alkoxy group having from 3 to 20 carbon atoms, in which one or more nonadjacent CH₂ groups may be replaced by -O-, -S-, -CO-O-, -C=O-, -CH=CH- or -C≡C-, and in which one or more hydrogen atoms may be replaced by F, or an aryl or heteroaryl group which has from 4 to 14 carbon atoms and may be substituted by one or more nonaromatic R⁵ radicals; and n is in the range from 3 to 9, preferably 4, 5, 6 or 7 and more preferably 5 or 6.

Examples of the most preferred cyclosiloxanes and their boiling points (BP) are shown in Table 1.

5	Substance	BP (°C)
10	 <p data-bbox="347 797 890 819">Octamethylcyclotetrasiloxane, CAS: 556-67-2</p>	175
15	 <p data-bbox="347 1032 911 1061">Decamethylcyclopentasiloxane, CAS: 541-02-6</p>	210
20	 <p data-bbox="347 1290 935 1319">Dodecamethylcyclohexasiloxane, CAS: 540-97-6</p>	245
25	 <p data-bbox="347 1599 970 1628">Tetradecamethylcycloheptasiloxane, CAS: 107-50-6</p>	336
30	 <p data-bbox="347 1928 863 1957">Hexaethylcyclotrisiloxane, CAS: 2031-79-0</p>	252

5	 <p>Octaethylcyclotetrasiloxane, CAS: 1451-99-6</p>	295
10	 <p>2,4,6,8,10-pentaethyl-2,4,6,8,10-pentamethylcyclopentasiloxane, CAS: 17940-63-5</p>	287
15	 <p>2,4,6-triethyl-2,4,6-trimethylcyclotrisiloxane, CAS: 15901-49-2</p>	198

20 Table 1: Most preferred cyclosiloxanes and their boiling points (BP)

Preferably, the first solvent has a surface tension of ≤ 25 mN/m. More preferably, the surface tension of the first solvent is in the range from 10 to 25 mN/m and most preferably in the range from 15 to 25 mN/m.

25

The content of the first solvent is preferably in the range from 1 to 50 vol.-%, more preferably in the range from 1 to 25 vol.-% and most preferably in the range from 1 to 10 vol.-%, based on the total amount of solvents in the formulation.

30

Consequently, the content of the second solvent is in the range from 50 to 99 vol.-%, preferably in the range from 75 to 99 vol.-% and more preferably

in the range from 90 to 99 vol.-%, based on the total amount of solvents in the formulation.

5 Preferably, the first solvent has a boiling point in the range from 100 to 400°C, more preferably in the range from 150 to 350°C.

The formulations according to the present invention comprise at least one second solvent which is different from the first solvent. The second solvent is employed together with the first solvent.

10

Suitable second solvents are preferably organic solvents which include inter alia, alcohols, aldehydes, ketones, ethers, esters, amides such as di-C₁₋₂-alkylformamides, sulfur compounds, nitro compounds, hydrocarbons, halogenated hydrocarbons (e.g. chlorinated hydrocarbons), aromatic or
15 heteroaromatic hydrocarbons and halogenated aromatic or heteroaromatic hydrocarbons.

Preferably, the second solvent can be chosen from one of the following groups: substituted and non-substituted aromatic or linear esters such as
20 ethyl benzoate, butyl benzoate; substituted and non-substituted aromatic or linear ethers such as 3-phenoxytoluene or anisole; substituted or non-substituted arene derivatives such as xylene; indane derivatives such as hexamethylindane; substituted and non-substituted aromatic or linear
25 ketones; substituted and non-substituted heterocycles such as pyrrolidinones, pyridines, pyrazines; other fluorinated or chlorinated aromatic hydrocarbons.

Particularly preferred second organic solvents are, for example, 1,2,3,4-tetramethylbenzene, 1,2,3,5-tetramethylbenzene, 1,2,3-trimethylbenzene,
30 1,2,4,5-tetramethylbenzene, 1,2,4-trichlorobenzene, 1,2,4-trimethylbenzene, 1,2-dihydronaphthalene, 1,2-dimethylnaphthalene, 1,3-benzo-

dioxolane, 1,3-diisopropylbenzene, 1,3-dimethylnaphthalene, 1,4-benzodioxane, 1,4-diisopropylbenzene, 1,4-dimethylnaphthalene, 1,5-dimethyltetralin, 1-benzothiophene, thianaphthalene, 1-bromonaphthalene, 1-chloromethylnaphthalene, 1-ethylnaphthalene, 1-methoxynaphthalene,
5 1-methylnaphthalene, 1-methylindole, 2,3-benzofuran, 2,3-dihydrobenzofuran, 2,3-dimethylanisole, 2,4-dimethylanisole, 2,5-dimethylanisole, 2,6-dimethylanisole, 2,6-dimethylnaphthalene, 2-bromo-3-bromomethylnaphthalene, 2-bromomethylnaphthalene, 2-bromonaphthalene, 2-ethoxynaphthalene, 2-ethylnaphthalene, 2-isopropylanisole, 2-methylanisole, 2-methyl-
10 indole, 3,4-dimethylanisole, 3,5-dimethylanisole, 3-bromoquinoline, 3-methylanisole, 4-methylanisole, 5-decanolide, 5-methoxyindane, 5-methoxyindole, 5-tert-butyl-m-xylene, 6-methylquinoline, 8-methylquinoline, acetophenone, anisole, benzonitrile, benzothiazole, benzyl acetate, bromobenzene, butyl benzoate, butyl phenyl ether, cyclohexylbenzene,
15 decahydronaphthol, dimethoxytoluene, 3-phenoxytoluene, diphenyl ether, propiophenone, ethylbenzene, ethyl benzoate, γ -terpine, hexylbenzene, indane, hexamethylindane, indene, isochroman, cumene, m-cymene, mesitylene, methyl benzoate, o-, m-, p-xylene, propyl benzoate, propylbenzene, o-dichlorobenzene, pentylbenzene, phenetol,
20 ethoxybenzene, phenyl acetate, p-cymene, propiophenone, sec-butylbenzene, t-butylbenzene, thiophene, toluene, veratrol, monochlorobenzene, o-dichlorobenzene, pyridine, pyrazine, pyrimidine, pyrrolidinone, morpholine, dimethylacetamide, dimethyl sulfoxide, decalin and/or mixtures of these compounds.

25

These solvents can be employed individually or as a mixture of two, three or more solvents forming the second solvent.

30

Preferably, the second solvent has a boiling point in the range from 100 to 400°C, more preferably in the range from 150 to 350°C.

The at least one organic functional material has a solubility in the second solvent which is preferably in the range from 1 to 250 g/l.

5 The content of the at least one organic functional material in the formulation is in the range from 0.001 to 20 weight-%, preferably in the range from 0.01 to 10 weight-% and more preferably in the range from 0.1 to 5 weight-% and most preferably in the range from 0.3 to 5 weight-%, based on the total weight of the formulation.

10 The formulation according to the present invention has a surface tension preferably in the range from 1 to 70 mN/m, more preferably in the range from 10 to 50 mN/m and most preferably in the range from 15 to 40 mN/m.

15 Furthermore, the formulation according to the present invention has a viscosity in the range from 1 to 50 mPas, preferably in the range from 2 to 40 mPas, and more preferably in the range from 2 to 20 mPas.

The surface tension of the formulations and solvents is measured by pendant drop characterization which is an optical method. This measurement technique dispenses a drop from a needle in a bulk gaseous phase. The shape of the drop results from the relationship between the surface tension, gravity and density differences. Using the pendant drop method, the surface tension is calculated from the shadow image of a pendant drop using drop shape analysis. A commonly used and commercially available high precision drop shape analysis tool, namely the DSA100 from Krüss GmbH, was used to perform all surface tension measurements. The surface tension is determined by the software "DSA4" in accordance with DIN 55660-1. All measurements were performed at room temperature which is in the range between 22°C and 24°C. The standard operating procedure includes the determination of the surface tension of each formulation using a fresh disposable drop dispensing system (syringe and needle). Each drop is measured over the duration of

20

25

30

one minute with sixty measurements which are later on averaged. For each formulation three drops are measured. The final value is averaged over said measurements. The tool is regularly cross-checked against various liquids having well known surface tension.

5

The viscosity of the formulations and solvents according to the present invention is measured with a 1° cone-plate rotational rheometer of the type Haake MARS III Rheometer (Thermo Scientific). The equipment allows a precise control of the temperature and sheer rate. The measurement of the
10 viscosity is carried out at a temperature of 23.4°C (+/- 0.2°C) and a sheer rate of 500s⁻¹. Each sample is measured three times and the obtained measured values are averaged. The measurement and processing of data is carried out using the software "Haake RheoWin Job Manager" according to DIN 1342-2. The Haake MARS III Rheometer is regularly calibrated by
15 Thermo Scientific and the tool received a certified standard factory calibration before first use.

The formulation according to the invention comprises at least one organic functional material which can be employed for the production of functional
20 layers of electronic devices. Functional materials are generally the organic materials which are introduced between the anode and the cathode of an electronic device.

The term organic functional material denotes, inter alia, organic conductors,
25 organic semiconductors, organic fluorescent compounds, organic phosphorescent compounds, organic light-absorbent compounds, organic light-sensitive compounds, organic photosensitisation agents and other organic photoactive compounds. The term organic functional material furthermore encompasses organometallic complexes of transition metals, rare
30 earths, lanthanides and actinides.

The organic functional material is selected from the group consisting of fluorescent emitters, phosphorescent emitters, host materials, matrix materials, exciton-blocking materials, electron-transport materials, electron-injection materials, hole-conductor materials, hole-injection materials, n-dopants, p-dopants, wide-band-gap materials, electron-blocking materials and hole-blocking materials.

Preferred embodiments of organic functional materials are disclosed in detail in WO 2011/076314 A1, where this document is incorporated into the present application by way of reference.

In a preferred embodiment, the organic functional material is an organic semiconductor selected from the group consisting of hole-injecting, hole-transporting, emitting, electron-transporting and electron-injecting materials.

More preferably, the organic functional material is an organic semiconductor selected from the group consisting of hole-injecting and hole-transporting materials.

The organic functional material can be a compound having a low molecular weight, a polymer, an oligomer or a dendrimer, where the organic functional material may also be in the form of a mixture. Thus, the formulations according to the invention may comprise two different compounds having a low molecular weight, one compound having a low molecular weight and one polymer or two polymers (blend).

Organic functional materials are frequently described via the properties of the frontier orbitals, which are described in greater detail below. Molecular orbitals, in particular also the highest occupied molecular orbital (HOMO) and the lowest unoccupied molecular orbital (LUMO), their energy levels and the energy of the lowest triplet state T_1 or of the lowest excited singlet state S_1 of the materials are determined via quantum-chemical calculations.

In order to calculate organic substances without metals, firstly a geometry optimisation is carried out using the "Ground State/Semi-empirical/Default Spin/AM1/Charge 0/Spin Singlet" method. An energy calculation is subsequently carried out on the basis of the optimised geometry. The "TD-SCF/
5 DFT/Default Spin/B3PW91" method with the "6-31G(d)" base set (charge 0, spin singlet) is used here. For metal-containing compounds, the geometry is optimised via the "Ground State/ Hartree-Fock/Default Spin/LanL2MB/ Charge 0/Spin Singlet" method. The energy calculation is carried out analogously to the above-described method for the organic substances,
10 with the difference that the "LanL2DZ" base set is used for the metal atom and the "6-31G(d)" base set is used for the ligands. The energy calculation gives the HOMO energy level HEh or LUMO energy level LEh in hartree units. The HOMO and LUMO energy levels in electron volts calibrated with reference to cyclic voltammetry measurements are determined therefrom
15 as follows:

$$\text{HOMO(eV)} = ((\text{HEh} * 27.212) - 0.9899) / 1.1206$$

$$\text{LUMO(eV)} = ((\text{LEh} * 27.212) - 2.0041) / 1.385$$

20 For the purposes of this application, these values are to be regarded as HOMO and LUMO energy levels respectively of the materials.

The lowest triplet state T_1 is defined as the energy of the triplet state having the lowest energy which arises from the quantum-chemical calculation
25 described.

The lowest excited singlet state S_1 is defined as the energy of the excited singlet state having the lowest energy which arises from the quantum-chemical calculation described.
30

The method described herein is independent of the software package used and always gives the same results. Examples of frequently used programs

for this purpose are "Gaussian09W" (Gaussian Inc.) and Q-Chem 4.1 (Q-Chem, Inc.).

5 Compounds having hole-injection properties, also called hole-injection materials herein, simplify or facilitate the transfer of holes, i.e. positive charges, from the anode into an organic layer. In general, a hole-injection material has an HOMO level which is in the region of or above the level of the anode, i.e. in general is at least -5.3 eV.

10 Compounds having hole-transport properties, also called hole-transport materials herein, are capable of transporting holes, i.e. positive charges, which are generally injected from the anode or an adjacent layer, for example a hole-injection layer. A hole-transport material generally has a high HOMO level of preferably at least -5.4 eV. Depending on the structure of an
15 electronic device, it may also be possible to employ a hole-transport material as hole-injection material.

The preferred compounds which have hole-injection and/or hole-transport properties include, for example, triarylamine, benzidine, tetraaryl-para-
20 phenylenediamine, triarylphosphine, phenothiazine, phenoxazine, dihydrophenazine, thianthrene, dibenzo-para-dioxin, phenoxathiylene, carbazole, azulene, thiophene, pyrrole and furan derivatives and further O-, S- or N-containing heterocycles having a high HOMO (HOMO = highest occupied molecular orbital).



25 As compounds which have hole-injection and/or hole-transport properties, particular mention may be made of phenylenediamine derivatives (US 3615404), arylamine derivatives (US 3567450), amino-substituted chalcone derivatives (US 3526501), styrylanthracene derivatives (JP-A-56-
30 46234), polycyclic aromatic compounds (EP 1009041), polyaryllkane derivatives (US 3615402), fluorenone derivatives (JP-A-54-110837), hydrazone derivatives (US 3717462), acylhydrazones, stilbene derivatives (JP-A-

61-210363), silazane derivatives (US 4950950), polysilanes (JP-A-2-204996), aniline copolymers (JP-A-2-282263), thiophene oligomers (JP Heisei 1 (1989) 211399), polythiophenes, poly(N-vinylcarbazole) (PVK), polypyrroles, polyanilines and other electrically conducting macromolecules, porphyrin compounds (JP-A-63-2956965, US 4720432), aromatic dimethylidene-type compounds, carbazole compounds, such as, for example, CDBP, CBP, mCP, aromatic tertiary amine and styrylamine compounds (US 4127412), such as, for example, triphenylamines of the benzidine type, triphenylamines of the styrylamine type and triphenylamines of the diamine type. It is also possible to use arylamine dendrimers (JP Heisei 8 (1996) 193191), monomeric triarylamine (US 3180730), triarylamine containing one or more vinyl radicals and/or at least one functional group containing active hydrogen (US 3567450 and US 3658520), or tetraaryldiamines (the two tertiary amine units are connected via an aryl group). More triarylamine groups may also be present in the molecule. Phthalocyanine derivatives, naphthalocyanine derivatives, butadiene derivatives and quinoline derivatives, such as, for example, dipyrzino[2,3-f:2',3'-h]-quinoxalinehexacarbonitrile, are also suitable.


Preference is given to aromatic tertiary amines containing at least two tertiary amine units (US 2008/0102311 A1, US 4720432 and US 5061569), such as, for example, NPD (α -NPD = 4,4'-bis[N-(1-naphthyl)-N-phenylamino]biphenyl) (US 5061569), TPD 232 (= N,N'-bis-(N,N'-diphenyl-4-aminophenyl)-N,N-diphenyl-4,4'-diamino-1,1'-biphenyl) or MTDATA (MTDATA or m-MTDATA = 4,4',4''-tris[3-methylphenyl]phenylamino]triphenylamine) (JP-A-4-308688), TBDB (= N,N,N',N'-tetra(4-biphenyl)-diaminobiphenylene), TAPC (= 1,1-bis(4-di-*p*-tolylaminophenyl)cyclohexane), TAPPP (= 1,1-bis(4-di-*p*-tolylaminophenyl)-3-phenylpropane), BDTAPVB (= 1,4-bis[2-[4-[N,N-di(*p*-tolyl)amino]phenyl]vinyl]benzene), TTB (= N,N,N',N'-tetra-*p*-tolyl-4,4'-diaminobiphenyl), TPD (= 4,4'-bis[N-3-methylphenyl]-N-phenylamino)biphenyl), N,N,N',N'-tetraphenyl-4,4''-diamino-

1,1',4',1'',4'',1'''-quaterphenyl, likewise tertiary amines containing carbazole units, such as, for example, TCTA (= 4-(9H-carbazol-9-yl)-N,N-bis[4-(9H-carbazol-9-yl)phenyl]benzenamine). Preference is likewise given to hexa-
5 azatriphenylene compounds in accordance with US 2007/0092755 A1 and phthalocyanine derivatives (for example H₂Pc, CuPc (= copper phthalocyanine), CoPc, NiPc, ZnPc, PdPc, FePc, MnPc, ClAlPc, ClGaPc, ClInPc, ClSnPc, Cl₂SiPc, (HO)AlPc, (HO)GaPc, VOPc, TiOPc, MoOPc, GaPc-O-GaPc).


10 Particular preference is given to the following triarylamine compounds of the formulae (TA-1) to (TA-12), which are disclosed in the documents EP 1162193 B1, EP 650 955 B1, *Synth. Metals* **1997**, 91(1-3), 209, DE 19646119 A1, WO 2006/122630 A1, EP 1 860 097 A1, EP 1834945 A1, JP 08053397 A, US 6251531 B1, US 2005/0221124, JP 08292586 A, US
15 7399537 B2, US 2006/0061265 A1, EP 1 661 888 and WO 2009/041635. The said compounds of the formulae (TA-1) to (TA-12) may also be substituted:



5




formula TA-3




formula TA-4

10




formula TA-5




formula TA-6

15




formula TA-7




formula TA-8

20

25




formula TA-9




formula TA-10

30

5



formula TA-11



formula TA-12

10

Further compounds which can be employed as hole-injection materials are described in EP 0891121 A1 and EP 1029909 A1, injection layers in general in US 2004/0174116 A1.

15

These arylamines and heterocycles which are generally employed as hole-injection and/or hole-transport materials preferably result in an HOMO in the polymer of greater than -5.8 eV (vs. vacuum level), particularly preferably greater than -5.5 eV.

20

Compounds which have electron-injection and/or electron-transport properties are, for example, pyridine, pyrimidine, pyridazine, pyrazine, oxadiazole, quinoline, quinoxaline, anthracene, benzanthracene, pyrene, perylene, benzimidazole, triazine, ketone, phosphine oxide and phenazine derivatives, but also triarylboranes and further O-, S- or N-containing heterocycles having a low LUMO (LUMO = lowest unoccupied molecular orbital).

25


Particularly suitable compounds for electron-transporting and electron-injecting layers are metal chelates of 8-hydroxyquinoline (for example LiQ, AlQ₃, GaQ₃, MgQ₂, ZnQ₂, InQ₃, ZrQ₄), BAlQ, Ga oxinoid complexes, 4-azaphenanthren-5-ol-Be complexes (US 5529853 A, cf. formula ET-1), butadiene derivatives (US 4356429), heterocyclic optical brighteners (US 4539507), benzimidazole derivatives (US 2007/0273272 A1), such as, for example, TPBI (US 5766779, cf. formula ET-2), 1,3,5-triazines, for example spirobifluorenyltriazine derivatives (for example in accordance with DE 102008064200), pyrenes, anthracenes, tetracenes, fluorenes, spirofluorenes, dendrimers, tetracenes (for example rubrene derivatives), 1,10-

30


phenanthroline derivatives (JP 2003-115387, JP 2004-311184, JP-2001-267080, WO 02/043449), silacyclopentadiene derivatives (EP 1480280, EP 1478032, EP 1469533), borane derivatives, such as, for example, tri-arylborane derivatives containing Si (US 2007/0087219 A1, cf. formula ET-3), pyridine derivatives (JP 2004-200162), phenanthrolines, especially 1,10-phenanthroline derivatives, such as, for example, BCP and Bphen, also several phenanthrolines connected via biphenyl or other aromatic groups (US-2007-0252517 A1) or phenanthrolines connected to anthracene (US 2007-0122656 A1, cf. formulae ET-4 and ET-5).

10

15



formula ET-1




TPBI

2,2,2'-(1,3,5-benzenetriyl)tris(1-phenyl-1H-benzimidazole)


formula ET-2

20




formula ET-3

25




formula ET-4

30




formula ET-5


Likewise suitable are heterocyclic organic compounds, such as, for example, thiopyran dioxides, oxazoles, triazoles, imidazoles or oxadiazoles. Examples of the use of five-membered rings containing N, such as, for example, oxazoles, preferably 1,3,4-oxadiazoles, for example compounds
5 of the formulae ET-6, ET-7, ET-8 and ET-9, which are disclose, inter alia, in US 2007/0273272 A1; thiazoles, oxadiazoles, thiadiazoles, triazoles, inter alia, see US 2008/0102311 A1 and Y.A. Levin, M.S. Skorobogatova, Khimiya Geterotsiklicheskikh Soedinenii 1967 (2), 339-341, preferably
10 compounds of the formula ET-10, silacyclopentadiene derivatives. Preferred compounds are the following of the formulae (ET-6) to (ET-10):




formula ET-6




formula ET-7



formula ET-8




formula ET-9



5 formula ET-10


It is also possible to employ organic compounds, such as derivatives of fluorenone, fluorenylidene methane, perylenetetracarboxylic acid, anthraquinonedimethane, diphenoquinone, anthrone and anthraquinone-
10 diethylenediamine.

Preference is given to 2,9,10-substituted anthracenes (with 1- or 2-naphthyl and 4- or 3-biphenyl) or molecules which contain two anthracene units (US2008/0193796 A1, cf. formula ET-11). Also very advantageous is the connection of 9,10-substituted anthracene units to benzimidazole derivatives (US 2006 147747 A and EP 1551206 A1, cf. formulae ET-12 and ET-13).




20

25 formula ET-11



30

formula ET-12



formula ET-13

The compounds which are able to generate electron-injection and/or electron-transport properties preferably result in an LUMO of less than -2.5 eV (vs. vacuum level), particularly preferably less than -2.7 eV.

5

The present formulations may comprise emitters. The term emitter denotes a material which, after excitation, which can take place by transfer of any type of energy, allows a radiative transition into a ground state with emission of light. In general, two classes of emitter are known, namely fluorescent and phosphorescent emitters. The term fluorescent emitter denotes materials or compounds in which a radiative transition from an excited singlet state into the ground state takes place. The term phosphorescent emitter preferably denotes luminescent materials or compounds which contain transition metals.

10

15

Emitters are frequently also called dopants if the dopants cause the properties described above in a system. A dopant in a system comprising a matrix material and a dopant is taken to mean the component whose proportion in the mixture is the smaller. Correspondingly, a matrix material in a system comprising a matrix material and a dopant is taken to mean the component whose proportion in the mixture is the greater. Accordingly, the term phosphorescent emitter can also be taken to mean, for example, phosphorescent dopants.

20

25

Compounds which are able to emit light include, inter alia, fluorescent emitters and phosphorescent emitters. These include, inter alia, compounds containing stilbene, stilbenamine, styrylamine, coumarine, rubrene, rhodamine, thiazole, thiadiazole, cyanine, thiophene, paraphenylene, perylene, phtalocyanine, porphyrin, ketone, quinoline, imine, anthracene and/or pyrene structures. Particular preference is given to compounds which are able to emit light from the triplet state with high efficiency, even at

30

room temperature, i.e. exhibit electrophosphorescence instead of electrofluorescence, which frequently causes an increase in the energy efficiency. Suitable for this purpose are firstly compounds which contain heavy atoms having an atomic number of greater than 36. Preference is given to
5 compounds which contain d- or f-transition metals which satisfy the above-mentioned condition. Particular preference is given here to corresponding compounds which contain elements from group 8 to 10 (Ru, Os, Rh, Ir, Pd, Pt). Suitable functional compounds here are, for example, various complexes, as described, for example, in WO 02/068435 A1,
10 WO 02/081488 A1, EP 1239526 A2 and WO 2004/026886 A2.

Preferred compounds which can serve as fluorescent emitters are described by way of example below. Preferred fluorescent emitters are selected from the class of the monostyrylamines, the distyrylamines, the
15 tristyrylamines, the tetrastyrylamines, the styrylphosphines, the styryl ethers and the arylamines.

A monostyrylamine is taken to mean a compound which contains one substituted or unsubstituted styryl group and at least one, preferably aromatic,
20 amine. A distyrylamine is taken to mean a compound which contains two substituted or unsubstituted styryl groups and at least one, preferably aromatic, amine. A tristyrylamine is taken to mean a compound which contains three substituted or unsubstituted styryl groups and at least one, preferably aromatic, amine. A tetrastyrylamine is taken to mean a compound which
25 contains four substituted or unsubstituted styryl groups and at least one, preferably aromatic, amine. The styryl groups are particularly preferably stilbenes, which may also be further substituted. Corresponding phosphines and ethers are defined analogously to the amines. An arylamine or an aromatic amine in the sense of the present invention is taken to mean a
30 compound which contains three substituted or unsubstituted aromatic or heteroaromatic ring systems bonded directly to the nitrogen. At least one of these aromatic or heteroaromatic ring systems is preferably a condensed


ring system, preferably having at least 14 aromatic ring atoms. Preferred examples thereof are aromatic anthracenamines, aromatic anthracenediamines, aromatic pyrenamines, aromatic pyrenediamines, aromatic chrysenamines or aromatic chrysenediamines. An aromatic anthracenamine is taken to mean a compound in which one diarylamino group is bonded directly to an anthracene group, preferably in the 9-position. An aromatic anthracenediamine is taken to mean a compound in which two diarylamino groups are bonded directly to an anthracene group, preferably in the 2,6- or 9,10-position. Aromatic pyrenamines, pyrenediamines, chrysenamines and chrysenediamines are defined analogously thereto, where the diarylamino groups are preferably bonded to the pyrene in the 1-position or in the 1,6-position.

Further preferred fluorescent emitters are selected from indenofluorenamines or indenofluorenediamines, which are described, inter alia, in WO 2006/122630; benzoindenofluorenamines or benzoindenofluorenediamines, which are described, inter alia, in WO 2008/006449; and dibenzoindenofluorenamines or dibenzoindenofluorenediamines, which are described, inter alia, in WO 2007/140847.


Examples of compounds from the class of the styrylamines which can be employed as fluorescent emitters are substituted or unsubstituted tristilbenamines or the dopants described in WO 2006/000388, WO 2006/058737, WO 2006/000389, WO 2007/065549 and WO 2007/115610. Distyrylbenzene and distyrylbiphenyl derivatives are described in US 5121029. Further styrylamines can be found in US 2007/0122656 A1.

Particularly preferred styrylamine compounds are the compounds of the formula EM-1 described in US 7250532 B2 and the compounds of the formula EM-2 described in DE 10 2005 058557 A1:

5



formula EM-1




formula EM-2


10

Particularly preferred triarylamine compounds are compounds of the formulae EM-3 to EM-15 disclosed in CN 1583691 A, JP 08/053397 A and US 6251531 B1, EP 1957606 A1, US 2008/0113101 A1, US 2006/210830 A, WO 2008/006449 and DE 102008035413 and derivatives thereof:

15




formula EM-3




formula EM-4

20



formula EM-5




formula EM-6


25

30

5




formula EM-7




formula EM-8

10




formula EM-9




formula EM-10

15




formula EM-11




formula EM-12

20




formula EM-13



formula EM-14

25

30



formula EM-15

Further preferred compounds which can be employed as fluorescent emitters are selected from derivatives of naphthalene, anthracene, tetracene, 5 benzanthracene, benzophenanthrene (DE 10 2009 005746), fluorene, fluoranthene, periflanthene, indenoperylene, phenanthrene, perylene (US 2007/0252517 A1), pyrene, chrysene, decacyclene, coronene, tetraphenylcyclopentadiene, pentaphenylcyclopentadiene, fluorene, spirofluorene, rubrene, coumarine (US 4769292, US 6020078, US 2007/10 0252517 A1), pyran, oxazole, benzoxazole, benzothiazole, benzimidazole, pyrazine, cinnamic acid esters, diketopyrrolopyrrole, acridone and quinacridone (US 2007/0252517 A1).

Of the anthracene compounds, particular preference is given to 9,10-15 substituted anthracenes, such as, for example, 9,10-diphenylanthracene and 9,10-bis(phenylethynyl)anthracene. 1,4-Bis(9'-ethynylanthracenyl)-benzene is also a preferred dopant.

Preference is likewise given to derivatives of rubrene, coumarine, rhodamine, 20 quinacridone, such as, for example, DMQA (= N,N'-dimethylquinacridone), dicyanomethylenepyran, such as, for example, DCM (= 4-(dicyanoethylene)-6-(4-dimethylaminostyryl-2-methyl)-4H-pyran), thiopyran, polymethine, pyrylium and thiapyrylium salts, periflanthene and indenoperylene.

25 Blue fluorescent emitters are preferably polyaromatic compounds, such as, for example, 9,10-di(2-naphthylanthracene) and other anthracene derivatives, derivatives of tetracene, xanthene, perylene, such as, for example, 2,5,8,11-tetra-*t*-butylperylene, phenylene, for example 4,4'-bis(9-ethyl-3-carbazovinylene)-1,1'-biphenyl, fluorene, fluoranthene, arylpyrenes 30 (US 2006/0222886 A1), arylenevinylenes (US 5121029, US 5130603), bis(azinyl)imine-boron compounds (US 2007/0092753 A1), bis(azinyl)methene compounds and carbostyryl compounds.

Further preferred blue fluorescent emitters are described in C.H. Chen et al.: "Recent developments in organic electroluminescent materials" Macromol. Symp. 125, (1997) 1-48 and "Recent progress of molecular organic electroluminescent materials and devices" Mat. Sci. and Eng. R, 39 (2002), 143-222.

Further preferred blue-fluorescent emitters are the hydrocarbons disclosed in DE 102008035413.

10

Preferred compounds which can serve as phosphorescent emitters are described below by way of example.

Examples of phosphorescent emitters are revealed by WO 00/70655, WO 01/41512, WO 02/02714, WO 02/15645, EP 1191613, EP 1191612, EP 1191614 and WO 2005/033244. In general, all phosphorescent complexes as are used in accordance with the prior art for phosphorescent OLEDs and as are known to the person skilled in the art in the area of organic electroluminescence are suitable, and the person skilled in the art will be able to use further phosphorescent complexes without inventive step.

20

Phosphorescent metal complexes preferably contain Ir, Ru, Pd, Pt, Os or Re.

25


Preferred ligands are 2-phenylpyridine derivatives, 7,8-benzoquinoline derivatives, 2-(2-thienyl)pyridine derivatives, 2-(1-naphthyl)pyridine derivatives, 1-phenylisoquinoline derivatives, 3-phenylisoquinoline derivatives or 2-phenylquinoline derivatives. All these compounds may be substituted, for example by fluoro, cyano and/or trifluoromethyl substituents for blue. Auxiliary ligands are preferably acetylacetonate or picolinic acid.

30

In particular, complexes of Pt or Pd with tetradentate ligands of the formula EM-16 are suitable

5

10



15

20

25

30

The compounds of the formula EM-16 are described in greater detail in US 2007/0087219 A1, where, for an explanation of the substituents and indices in the above formula, reference is made to this specification for disclosure purposes. Furthermore, Pt-porphyrin complexes having an enlarged ring system (US 2009/0061681 A1) and Ir complexes, for example 2,3,7,8,12,13,17,18-octaethyl-21H, 23H-porphyrin-Pt(II), tetraphenyl-Pt(II) tetrabenzoporphyrin (US 2009/0061681 A1), *cis*-bis(2-phenylpyridinato-N,C^{2'})Pt(II), *cis*-bis(2-(2'-thienyl)pyridinato-N,C^{3'})Pt(II), *cis*-bis(2-(2'-thienyl)quinolinato-N,C^{5'})Pt(II), (2-(4,6-difluorophenyl)pyridinato-N,C^{2'})Pt(II) (acetylacetonate), or tris(2-phenylpyridinato-N,C^{2'})Ir(III) (= Ir(ppy)₃, green), bis(2-phenylpyridinato-N,C^{2'})Ir(III) (acetylacetonate) (= Ir(ppy)₂ acetylacetonate, green, US 2001/0053462 A1, Baldo, Thompson et al. *Nature* 403, (2000), 750-753), bis(1-phenylisoquinolinato-N,C^{2'})(2-phenylpyridinato-N,C^{2'})-iridium(III), bis(2-phenylpyridinato-N,C^{2'})(1-phenylisoquinolinato-N,C^{2'})-iridium(III), bis(2-(2'-benzothienyl)pyridinato-N,C^{3'})iridium(III) (acetylacetonate), bis(2-(4',6'-difluorophenyl)pyridinato-N,C^{2'})iridium(III) (piccolinate) (Flpic, blue), bis(2-(4',6'-difluorophenyl)pyridinato-N,C^{2'})Ir(III) (tetrakis(1-pyrazolyl)borate), tris(2-(biphenyl-3-yl)-4-tert-butylpyridine)-


iridium(III), (ppz)₂Ir(5phdpym) (US 2009/0061681 A1), (45ooppz)₂-
 Ir(5phdpym) (US 2009/0061681 A1), derivatives of 2-phenylpyridine-Ir com-
 plexes, such as, for example, PQIr (= iridium(III) bis(2-phenylquinolyl-
 N,C^{2'})acetylacetonate), tris(2-phenylisoquinolino-N,C)Ir(III) (red), bis(2-
 5 (2'-benzo[4,5-a]thienyl)pyridinato-N,C^{3'})Ir (acetylacetonate) ([Btp₂Ir(acac)],
 red, Adachi et al. *Appl. Phys. Lett.* 78 (2001), 1622-1624).

Likewise suitable are complexes of trivalent lanthanides, such as, for
 example, Tb³⁺ and Eu³⁺ (J. Kido et al. *Appl. Phys. Lett.* 65 (1994), 2124,
 10 Kido et al. *Chem. Lett.* 657, 1990, US 2007/0252517 A1), or phosphores-
 cent complexes of Pt(II), Ir(I), Rh(I) with maleonitrile dithiolate (Johnson et
 al., *JACS* 105, 1983, 1795), Re(I) tricarbonyl-diimine complexes (Wrighton,
JACS 96, 1974, 998, inter alia), Os(II) complexes with cyano ligands and
 bipyridyl or phenanthroline ligands (Ma et al., *Synth. Metals* 94, 1998, 245).

15 Further phosphorescent emitters having tridentate ligands are described in
 US 6824895 and US 10/729238. Red-emitting phosphorescent complexes
 are found in US 6835469 and US 6830828.

20 Particularly preferred compounds which are used as phosphorescent
 dopants are, inter alia, the compounds of the formula EM-17 described,
 inter alia, in US 2001/0053462 A1 and *Inorg. Chem.* 2001, 40(7), 1704-
 1711, *JACS* 2001, 123(18), 4304-4312, and derivatives thereof.

25




30

formula EM-17


Derivatives are described in US 7378162 B2, US 6835469 B2 and JP 2003/253145 A.

Furthermore, the compounds of the formulae EM-18 to EM-21 described in
 5 US 7238437 B2, US 2009/008607 A1 and EP 1348711, and derivatives thereof, can be employed as emitters.

10




formula EM-18




formula EM-19

15



formula EM-20

20



formula EM-21

Quantum dots can likewise be employed as emitters, these materials being disclosed in detail in WO 2011/076314 A1.

25

Compounds which are employed as host materials, in particular together with emitting compounds, include materials from various classes of substance.

30

Host materials generally have larger band gaps between HOMO and LUMO than the emitter materials employed. In addition, preferred host materials

exhibit properties of either a hole- or electron-transport material. Furthermore, host materials can have both electron- and hole-transport properties.

5 Host materials are in some cases also called matrix material, in particular if the host material is employed in combination with a phosphorescent emitter in an OLED.

Preferred host materials or co-host materials, which are employed, in particular, together with fluorescent dopants, are selected from the classes of
10 the oligoarylenes (for example 2,2',7,7'-tetraphenylspirobifluorene in accordance with EP 676461 or dinaphthylanthracene), in particular the oligoarylenes containing condensed aromatic groups, such as, for example, anthracene, benzanthracene, benzophenanthrene (DE 10 2009 005746, WO 2009/069566), phenanthrene, tetracene, coronene, chrysene, fluorene,
15 spirofluorene, perylene, phthaloperylene, naphthaloperylene, decacyclene, rubrene, the oligoarylenevinylens (for example DPVBi = 4,4'-bis(2,2-diphenylethenyl)-1,1'-biphenyl or spiro-DPVBi in accordance with EP 676461), the polyodal metal complexes (for example in accordance with WO 04/081017), in particular metal complexes of 8-hydroxyquinoline, for
20 example AlQ₃ (= aluminium(III) tris(8-hydroxyquinoline)) or bis(2-methyl-8-quinolinolato)-4-(phenylphenolinolato)aluminium, also with imidazole chelate (US 2007/0092753 A1) and the quinoline-metal complexes, aminoquinoline-metal complexes, benzoquinoline-metal complexes, the hole-conducting compounds (for example in accordance with WO 2004/058911),
25 the electron-conducting compounds, in particular ketones, phosphine oxides, sulfoxides, etc. (for example in accordance with WO 2005/084081 and WO 2005/084082), the atropisomers (for example in accordance with WO 2006/048268), the boronic acid derivatives (for example in accordance with WO 2006/117052) or the benzanthracenes (for example in accordance
30 with WO 2008/145239).

Particularly preferred compounds which can serve as host materials or co-host materials are selected from the classes of the oligoarylenes, comprising anthracene, benzanthracene and/or pyrene, or atropisomers of these compounds. An oligoarylene in the sense of the present invention is
5 intended to be taken to mean a compound in which at least three aryl or arylene groups are bonded to one another.

Preferred host materials are selected, in particular, from compounds of the formula (H-1),

10



where Ar^4 , Ar^5 , Ar^6 are on each occurrence, identically or differently, an aryl or heteroaryl group having 5 to 30 aromatic ring atoms, which may optionally be substituted, and p represents an integer in the range from 1 to 5; the
15 sum of the π electrons in Ar^4 , Ar^5 and Ar^6 is at least 30 if $p = 1$ and at least 36 if $p = 2$ and at least 42 if $p = 3$.


In the compounds of the formula (H-1), the group Ar^5 particularly preferably stands for anthracene, and the groups Ar^4 and Ar^6 are bonded in the 9- and
20 10-position, where these groups may optionally be substituted. Very particularly preferably, at least one of the groups Ar^4 and/or Ar^6 is a condensed aryl group selected from 1- or 2-naphthyl, 2-, 3- or 9-phenanthrenyl or 2-, 3-, 4-, 5-, 6- or 7-benzanthracenyl. Anthracene-based compounds are
25 described in US 2007/0092753 A1 and US 2007/0252517 A1, for example 2-(4-methylphenyl)-9,10-di-(2-naphthyl)anthracene, 9-(2-naphthyl)-10-(1,1'-biphenyl)anthracene and 9,10-bis[4-(2,2-diphenylethenyl)phenyl]anthracene, 9,10-diphenylanthracene, 9,10-bis(phenylethynyl)anthracene and
1,4-bis(9'-ethynylanthracenyl)benzene. Preference is also given to compounds containing two anthracene units (US 2008/0193796 A1), for example
30 10,10'-bis[1,1',4',1'']terphenyl-2-yl-9,9'-bisanthracenyl:

Further preferred compounds are derivatives of arylamine, styrylamine, fluorescein, diphenylbutadiene, tetraphenylbutadiene, cyclopentadiene, tetraphenylcyclopentadiene, pentaphenylcyclopentadiene, coumarine, oxadiazole, bisbenzoxazoline, oxazole, pyridine, pyrazine, imine, benzo-
5 thiazole, benzoxazole, benzimidazole (US 2007/0092753 A1), for example 2,2',2''-(1,3,5-phenylene)tris[1-phenyl-1H-benzimidazole], aldazine, stilbene, styrylarylene derivatives, for example 9,10-bis[4-(2,2-diphenyl-ethenyl)phenyl]anthracene, and distyrylarylene derivatives (US 5121029),
10 diphenylethylene, vinylanthracene, diaminocarbazole, pyran, thiopyran, diketopyrrolopyrrole, polymethine, cinnamic acid esters and fluorescent dyes.

Particular preference is given to derivatives of arylamine and styrylamine, for example TNB (= 4,4'-bis[N-(1-naphthyl)-N-(2-naphthyl)amino]biphenyl).
15 Metal-oxinoid complexes, such as LiQ or AlQ₃, can be used as co-hosts.


Preferred compounds with oligoarylene as matrix are disclosed in US 2003/0027016 A1, US 7326371 B2, US 2006/043858 A, WO 2007/114358, WO 2008/145239, JP 3148176 B2, EP 1009044, US 2004/018383,
20 WO 2005/061656 A1, EP 0681019B1, WO 2004/013073A1, US 5077142, WO 2007/065678 and DE 102009005746, where particularly preferred compounds are described by the formulae H-2 to H-8.

25




30

formula H-2




formula H-3

5




formula H-4




formula H-5

10




formula H-6



formula H-7

15



formula H-8

20

Furthermore, compounds which can be employed as host or matrix include materials which are employed together with phosphorescent emitters.

25


These compounds, which can also be employed as structural elements in polymers, include CBP (N,N-biscarbazolylbiphenyl), carbazole derivatives (for example in accordance with WO 2005/039246, US 2005/0069729, JP 2004/288381, EP 1205527 or WO 2008/086851), azacarbazoles (for example in accordance with EP 1617710, EP 1617711, EP 1731584 or JP 2005/347160), ketones (for example in accordance with WO 2004/

30


093207 or in accordance with DE 102008033943), phosphine oxides, sulfoxides and sulfones (for example in accordance with WO 2005/003253), oligophenylenes, aromatic amines (for example in accordance with US 2005/0069729), bipolar matrix materials (for example in accordance with WO 2007/137725), silanes (for example in accordance with WO 2005/111172), 9,9-diarylfuorene derivatives (for example in accordance with DE 102008017591), azaboroles or boronic esters (for example in accordance with WO 2006/117052), triazine derivatives (for example in accordance with DE 102008036982), indolocarbazole derivatives (for example in accordance with WO 2007/063754 or WO 2008/056746), indenocarbazole derivatives (for example in accordance with DE 102009023155 and DE 102009031021), diazaphosphole derivatives (for example in accordance with DE 102009022858), triazole derivatives, oxazoles and oxazole derivatives, imidazole derivatives, polyarylalkane derivatives, pyrazoline derivatives, pyrazolone derivatives, distyrylpyrazine derivatives, thiopyran dioxide derivatives, phenylenediamine derivatives, tertiary aromatic amines, styrylamines, amino-substituted chalcone derivatives, indoles, hydrazone derivatives, stilbene derivatives, silazane derivatives, aromatic dimethylidene compounds, carbodiimide derivatives, metal complexes of 8-hydroxyquinoline derivatives, such as, for example, AlQ₃, which may also contain triarylaminophenol ligands (US 2007/0134514 A1), metal complex/poly-silane compounds, and thiophene, benzothiophene and dibenzothiophene derivatives.

Examples of preferred carbazole derivatives are mCP (= 1,3-N,N-dicarbazolylbenzene (= 9,9'-(1,3-phenylene)bis-9H-carbazole)) (formula H-9), CDBP (= 9,9'-(2,2'-dimethyl[1,1'-biphenyl]-4,4'-diyl)bis-9H-carbazole), 1,3-bis(N,N'-dicarbazolyl)benzene (= 1,3-bis(carbazol-9-yl)benzene), PVK (polyvinylcarbazole), 3,5-di(9H-carbazol-9-yl)biphenyl and CMTTP (formula H-10). Particularly referred compounds are disclosed in US 2007/0128467 A1 and US 2005/0249976 A1 (formulae H-11 and H-13).

5




formula H-9




formula H-10

10




formula H-11



formula H-12

15



formula H-13


20

Preferred tetraaryl-Si compounds are disclosed, for example, in US 2004/
 25 0209115, US 2004/0209116, US 2007/0087219 A1 and in H. Gilman, E.A.
 Zuech, Chemistry & Industry (London, United Kingdom), 1960, 120.

Particularly preferred tetraaryl-Si compounds are described by the formulae
 H-14 to H-20.


30

5



UGH1


formula H-14



UGH2


formula H-15

10



UGH4

formula H-16




TPSi-F

Triphenyl-[4-(9-phenyl-9H-fluoren-9-yl)phenyl]silane


formula H-17

15




SimCP

formula H-18




formula H-19

25



formula H-20




formula H-21

30

Particularly preferred compounds from group 4 for the preparation of the matrix for phosphorescent dopants are disclosed, inter alia, in DE 102009022858, DE 102009023155, EP 652273 B1, WO 2007/063754 and WO 2008/056746, where particularly preferred compounds are


5




10

15

formula H-22




formula H-23



20

formula H-24



formula H-25

25

With respect to the functional compounds which can be employed in accordance with the invention and which can serve as host material, especial preference is given to substances which contain at least one nitrogen atom. These preferably include aromatic amines, triazine derivatives and carbazole derivatives. Thus, carbazole derivatives in particular exhibit surprisingly high efficiency. Triazine derivatives result in unexpectedly long

30

lifetimes of the electronic devices.

It may also be preferred to employ a plurality of different matrix materials as a mixture, in particular at least one electron-conducting matrix material and at least one hole-conducting matrix material. Preference is likewise given to the use of a mixture of a charge-transporting matrix material and an
5 electrically inert matrix material which is not involved in the charge transport to a significant extent, if at all, as described, for example, in WO 2010/108579.

It is furthermore possible to employ compounds which improve the transi-
10 tion from the singlet state to the triplet state and which, employed in support of the functional compounds having emitter properties, improve the phosphorescence properties of these compounds. Suitable for this purpose are, in particular, carbazole and bridged carbazole dimer units, as described, for example, in WO 2004/070772 A2 and WO 2004/113468 A1.
15 Also suitable for this purpose are ketones, phosphine oxides, sulfoxides, sulfones, silane derivatives and similar compounds, as described, for example, in WO 2005/040302 A1.

n-Dopants herein are taken to mean reducing agents, i.e. electron donors.
20 Preferred examples of n-dopants are $W(hpp)_4$ and other electron-rich metal complexes in accordance with WO 2005/086251 A2, P=N compounds (for example WO 2012/175535 A1, WO 2012/175219 A1), naphthylencarbo- diimides (for example WO 2012/168358 A1), fluorenes (for example
25 WO 2012/031735 A1), free radicals and diradicals (for example EP 1837926 A1, WO 2007/107306 A1), pyridines (for example EP 2452946 A1, EP 2463927 A1), N-heterocyclic compounds (for example WO 2009/000237 A1) and acridines as well as phenazines (for example US 2007/145355 A1).

30 Furthermore, the formulations may comprise a wide-band-gap material as functional material. Wide-band-gap material is taken to mean a material in

the sense of the disclosure content of US 7,294,849. These systems exhibit particularly advantageous performance data in electroluminescent devices.

5 The compound employed as wide-band-gap material can preferably have a band gap of 2.5 eV or more, preferably 3.0 eV or more, particularly preferably 3.5 eV or more. The band gap can be calculated, inter alia, by means of the energy levels of the highest occupied molecular orbital (HOMO) and the lowest unoccupied molecular orbital (LUMO).

10 Furthermore, the formulations may comprise a hole-blocking material (HBM) as functional material. A hole-blocking material denotes a material which prevents or minimises the transmission of holes (positive charges) in a multilayer system, in particular if this material is arranged in the form of a layer adjacent to an emission layer or a hole-conducting layer. In general, a
15 hole-blocking material has a lower HOMO level than the hole-transport material in the adjacent layer. Hole-blocking layers are frequently arranged between the light-emitting layer and the electron-transport layer in OLEDs.

It is basically possible to employ any known hole-blocking material. In addition to other hole-blocking materials described elsewhere in the present
20 application, advantageous hole-blocking materials are metal complexes (US 2003/0068528), such as, for example, bis(2-methyl-8-quinolinolato)(4-phenylphenolato)aluminium(III) (BAIQ). Fac-tris(1-phenylpyrazolato-N,C2)-iridium(III) (Ir(ppz)₃) is likewise employed for this purpose (US 2003/
25 0175553 A1). Phenanthroline derivatives, such as, for example, BCP, or phthalimides, such as, for example, TMPP, can likewise be employed.

Furthermore, advantageous hole-blocking materials are described in WO 00/70655 A2, WO 01/41512 and WO 01/93642 A1.

30

Furthermore, the formulations may comprise an electron-blocking material (EBM) as functional material. An electron-blocking material denotes a

material which prevents or minimises the transmission of electrons in a multilayer system, in particular if this material is arranged in the form of a layer adjacent to an emission layer or an electron-conducting layer. In general, an electron-blocking material has a higher LUMO level than the
5 electron-transport material in the adjacent layer.

It is basically possible to employ any known electron-blocking material. In addition to other electron-blocking materials described elsewhere in the present application, advantageous electron-blocking materials are
10 transition-metal complexes, such as, for example, Ir(ppz)₃ (US 2003/0175553).

The electron-blocking material can preferably be selected from amines, tri-arylamines and derivatives thereof.

15 Furthermore, the functional compounds which can be employed as organic functional materials in the formulations preferably have, if they are low-molecular-weight compounds, a molecular weight of $\leq 3,000$ g/mol, particularly preferably $\leq 2,000$ g/mol and especially preferably $\leq 1,000$ g/mol.

20 Of particular interest are furthermore functional compounds which are distinguished by a high glass-transition temperature. In this connection, particularly preferred functional compounds which can be employed as organic functional material in the formulations are those which have a glass-
25 transition temperature of $\geq 70^\circ\text{C}$, preferably $\geq 100^\circ\text{C}$, particularly preferably $\geq 125^\circ\text{C}$ and especially preferably $\geq 150^\circ\text{C}$, determined in accordance with DIN 51005.

The formulations may also comprise polymers as organic functional materi-
30 als. The compounds described above as organic functional materials, which frequently have a relatively low molecular weight, can also be mixed with a polymer. It is likewise possible to incorporate these compounds covalently

into a polymer. This is possible, in particular, with compounds which are substituted by reactive leaving groups, such as bromine, iodine, chlorine, boronic acid or boronic acid ester, or by reactive, polymerisable groups, such as olefins or oxetanes. These can be used as monomers for the production of corresponding oligomers, dendrimers or polymers. The oligomerisation or polymerisation here preferably takes place via the halogen functionality or the boronic acid functionality or via the polymerisable group. It is furthermore possible to crosslink the polymers via groups of this type. The compounds and polymers according to the invention can be employed as crosslinked or uncrosslinked layer.

Polymers which can be employed as organic functional materials frequently contain units or structural elements which have been described in the context of the compounds described above, inter alia those as disclosed and extensively listed in WO 02/077060 A1, in WO 2005/014689 A2 and in WO 2011/076314 A1. These are incorporated into the present application by way of reference. The functional materials can originate, for example, from the following classes:

- Group 1: structural elements which are able to generate hole-injection and/or hole-transport properties;
- Group 2: structural elements which are able to generate electron-injection and/or electron-transport properties;
- Group 3: structural elements which combine the properties described in relation to groups 1 and 2;
- Group 4: structural elements which have light-emitting properties, in particular phosphorescent groups;

Group 5: structural elements which improve the transition from the so-called singlet state to the triplet state;

5 Group 6: structural elements which influence the morphology or also the emission colour of the resultant polymers;


Group 7: structural elements which are typically used as backbone.

10 The structural elements here may also have various functions, so that a clear assignment need not be advantageous. For example, a structural element of group 1 may likewise serve as backbone.

15 The polymer having hole-transport or hole-injection properties employed as organic functional material, containing structural elements from group 1, may preferably contain units which correspond to the hole-transport or hole-injection materials described above.

20 Further preferred structural elements of group 1 are, for example, triarylamine, benzidine, tetraaryl-para-phenylenediamine, carbazole, azulene, thiophene, pyrrole and furan derivatives and further O-, S- or N-containing heterocycles having a high HOMO. These arylamines and heterocycles preferably have an HOMO of above -5.8 eV (against vacuum level), particularly preferably above -5.5 eV.

25 Preference is given, inter alia, to polymers having hole-transport or hole-injection properties, containing at least one of the following recurring units of the formula HTP-1:



HTP-1

in which the symbols have the following meaning:


5 Ar¹ is, in each case identically or differently for different recurring units, a single bond or a monocyclic or polycyclic aryl group, which may optionally be substituted;

10 Ar² is, in each case identically or differently for different recurring units, a monocyclic or polycyclic aryl group, which may optionally be substituted;

15 Ar³ is, in each case identically or differently for different recurring units, a monocyclic or polycyclic aryl group, which may optionally be substituted;


m is 1, 2 or 3.

20 Particular preference is given to recurring units of the formula HTP-1 which are selected from the group consisting of units of the formulae HTP-1A to HTP-1C:




HTP-1A

30



HTP-1B



HTP-1C

15

in which the symbols have the following meaning:


20 R^a is on each occurrence, identically or differently, H, a substituted or unsubstituted aromatic or heteroaromatic group, an alkyl, cycloalkyl, alkoxy, aralkyl, aryloxy, arylthio, alkoxy carbonyl, silyl or carboxyl group, a halogen atom, a cyano group, a nitro group or a hydroxyl group;

25 r is 0, 1, 2, 3 or 4, and

s is 0, 1, 2, 3, 4 or 5.

30

Preference is given, inter alia, to polymers having hole-transport or hole-injection properties, containing at least one of the following recurring units of the formula HTP-2:



HTP-2

in which the symbols have the following meaning:

5 T¹ and T² are selected independently from thiophene, selenophene, thieno-
[2,3-b]thiophene, thieno[3,2-b]thiophene, dithienothiophene, pyrrole and
aniline, where these groups may be substituted by one or more radicals R^b;

10 R^b is selected independently on each occurrence from halogen, -CN, -
NC, -NCO, -NCS, -OCN, -SCN, -C(=O)NR⁰R⁰⁰, -C(=O)X, -C(=O)R⁰, -
NH₂, -NR⁰R⁰⁰, -SH, -SR⁰, -SO₃H, -SO₂R⁰, -OH, -NO₂, -CF₃, -SF₅, an
optionally substituted silyl, carbyl or hydrocarbyl group having 1 to 40
carbon atoms, which may optionally be substituted and may optionally
contain one or more heteroatoms;

15 R⁰ and R⁰⁰ are each independently H or an optionally substituted carbyl or
hydrocarbyl group having 1 to 40 carbon atoms, which may optionally be
substituted and may optionally contain one or more heteroatoms;

20 Ar⁷ and Ar⁸ represent, independently of one another, a monocyclic or poly-
cyclic aryl or heteroaryl group, which may optionally be substituted and may
optionally be bonded to the 2,3-position of one or both adjacent thiophene
or selenophene groups;

25 c and e are, independently of one another, 0, 1, 2, 3 or 4, where
 $1 < c + e \leq 6$;

d and f are, independently of one another, 0, 1, 2, 3 or 4.

30 Preferred examples of polymers having hole-transport or hole-injection
properties are described, inter alia, in WO 2007/131582 A1 and WO 2008/
009343A1.

The polymer having electron-injection and/or electron-transport properties employed as organic functional material, containing structural elements from group 2, may preferably contain units which correspond to the electron-injection and/or electron-transport materials described above.

5

Further preferred structural elements of group 2 which have electron-injection and/or electron-transport properties are derived, for example, from pyridine, pyrimidine, pyridazine, pyrazine, oxadiazole, quinoline, quinoxaline and phenazine groups, but also triarylborane groups or further O-, S- or N-containing heterocycles having a low LUMO level. These structural elements of group 2 preferably have an LUMO of below -2.7 eV (against vacuum level), particularly preferably below -2.8 eV.

10

The organic functional material can preferably be a polymer which contains structural elements from group 3, where structural elements which improve the hole and electron mobility (i.e. structural elements from groups 1 and 2) are connected directly to one another. Some of these structural elements can serve as emitters here, where the emission colours may be shifted, for example, into the green, red or yellow. Their use is therefore advantageous, for example, for the generation of other emission colours or a broad-band emission by polymers which originally emit in blue.

15

20

The polymer having light-emitting properties employed as organic functional material, containing structural elements from group 4, may preferably contain units which correspond to the emitter materials described above. Preference is given here to polymers containing phosphorescent groups, in particular the emitting metal complexes described above which contain corresponding units containing elements from groups 8 to 10 (Ru, Os, Rh, Ir, Pd, Pt).

25

30

The polymer employed as organic functional material containing units of group 5 which improve the transition from the so-called singlet state to the

triplet state can preferably be employed in support of phosphorescent compounds, preferably the polymers containing structural elements of group 4 described above. A polymeric triplet matrix can be used here.

5 Suitable for this purpose are, in particular, carbazole and connected carbazole dimer units, as described, for example, in DE 10304819 A1 and DE 10328627 A1. Also suitable for this purpose are ketone, phosphine oxide, sulfoxide, sulfone and silane derivatives and similar compounds, as described, for example, in DE 10349033 A1. Furthermore, preferred structural units can be derived from compounds which have been described
10 above in connection with the matrix materials employed together with phosphorescent compounds.

The further organic functional material is preferably a polymer containing
15 units of group 6 which influence the morphology and/or the emission colour of the polymers. Besides the polymers mentioned above, these are those which have at least one further aromatic or another conjugated structure which do not count amongst the above-mentioned groups. These groups accordingly have only little or no effect on the charge-carrier mobilities, the
20 non-organometallic complexes or the singlet-triplet transition.

Structural units of this type are able to influence the morphology and/or the emission colour of the resultant polymers. Depending on the structural unit, these polymers can therefore also be used as emitters.

25 In the case of fluorescent OLEDs, preference is therefore given to aromatic structural elements having 6 to 40 C atoms or also tolan, stilbene or bis-styrylarylene derivative units, each of which may be substituted by one or more radicals. Particular preference is given here to the use of groups
30 derived from 1,4-phenylene, 1,4-naphthylene, 1,4- or 9,10-anthrylene, 1,6-, 2,7- or 4,9-pyrenylene, 3,9- or 3,10-perylenylene, 4,4'-biphenylene, 4,4''-


terphenylene, 4,4'-bi-1,1'-naphthylene, 4,4'-tolanylene, 4,4'-stilbenylene or 4,4''-bisstyrylarylene derivatives.

5 The polymer employed as organic functional material preferably contains units of group 7, which preferably contain aromatic structures having 6 to 40 C atoms which are frequently used as backbone.

These include, inter alia, 4,5-dihdropyrene derivatives, 4,5,9,10-tetra-
10 hydrodropyrene derivatives, fluorene derivatives, which are disclosed, for example, in US 5962631, WO 2006/052457 A2 and WO 2006/118345A1, 9,9-spirobifluorene derivatives, which are disclosed, for example, in WO 2003/020790 A1, 9,10-phenanthrene derivatives, which are disclosed, for example, in WO 2005/104264 A1, 9,10-dihydrophenanthrene deriva-
15 tives, which are disclosed, for example, in WO 2005/014689 A2, 5,7-dihydrodibenzoxepine derivatives and cis- and trans-indenofluorene derivatives, which are disclosed, for example, in WO 2004/041901 A1 and WO 2004/113412 A2, and binaphthylene derivatives, which are disclosed, for example, in WO 2006/063852 A1, and further units which are disclosed, for example, in WO 2005/056633A1, EP 1344788A1, WO 2007/043495A1,
20 WO 2005/033174 A1, WO 2003/099901 A1 and DE 102006003710.

Particular preference is given to structural units of group 7 which are selected from fluorene derivatives, which are disclosed, for example, in
25 US 5,962,631, WO 2006/052457 A2 and WO 2006/118345 A1, spiro-bifluorene derivatives, which are disclosed, for example, in WO 2003/020790 A1, benzofluorene, dibenzofluorene, benzothiophene and dibenzofluorene groups and derivatives thereof, which are disclosed, for example, in WO 2005/056633 A1, EP 1344788 A1 and WO 2007/043495 A1.

30 Especially preferred structural elements of group 7 are represented by the general formula PB-1:



5

formula PB-1

in which the symbols and indices have the following meanings:


- 10 A, B and B' are each, also for different recurring units, identically or differently, a divalent group, which is preferably selected from $-\text{CR}^c\text{R}^d-$, $-\text{NR}^c-$, $-\text{PR}^c-$, $-\text{O}-$, $-\text{S}-$, $-\text{SO}-$, $-\text{SO}_2-$, $-\text{CO}-$, $-\text{CS}-$, $-\text{CSe}-$, $-\text{P}(=\text{O})\text{R}^c-$, $-\text{P}(=\text{S})\text{R}^c-$ and $-\text{SiR}^c\text{R}^d-$;
- 15 R^c and R^d are selected on each occurrence, independently, from H, halogen, $-\text{CN}$, $-\text{NC}$, $-\text{NCO}$, $-\text{NCS}$, $-\text{OCN}$, $-\text{SCN}$, $-\text{C}(=\text{O})\text{NR}^0\text{R}^{00}$, $-\text{C}(=\text{O})\text{X}$, $-\text{C}(=\text{O})\text{R}^0$, $-\text{NH}_2$, $-\text{NR}^0\text{R}^{00}$, $-\text{SH}$, $-\text{SR}^0$, $-\text{SO}_3\text{H}$, $-\text{SO}_2\text{R}^0$, $-\text{OH}$, $-\text{NO}_2$, $-\text{CF}_3$, $-\text{SF}_5$, an optionally substituted silyl, carbyl or hydrocarbyl group having 1 to 40 carbon atoms, which may optionally be substituted and may
- 20 optionally contain one or more heteroatoms, where the groups R^c and R^d may optionally form a spiro group with a fluorene radical to which they are bonded;
- X is halogen;
- 25 R^0 and R^{00} are each, independently, H or an optionally substituted carbyl or hydrocarbyl group having 1 to 40 carbon atoms, which may optionally be substituted and may optionally contain one or more heteroatoms;
- 30 g is in each case, independently, 0 or 1 and h is in each case, independently, 0 or 1, where the sum of g and h in a sub-unit is preferably 1;
- m is an integer ≥ 1 ;

Ar¹ and Ar² represent, independently of one another, a monocyclic or polycyclic aryl or heteroaryl group, which may optionally be substituted and may optionally be bonded to the 7,8-position or the 8,9-position of an indeno-
5 fluorene group;

a and b are, independently of one another, 0 or 1.


If the groups R^c and R^d form a spiro group with the fluorene group to which these groups are bonded, this group preferably represents a spiro-
10 bifluorene.

Particular preference is given to recurring units of the formula PB-1 which are selected from the group consisting of units of the formulae PB-1A to
15 PB-1E:



20

formula PB-1A




25

formula PB-1B


30

5



formula PB-1C


10



15

formula PB-1D

20



formula PB-1E

25

where R^c has the meaning described above for formula PB-1, r is 0, 1, 2, 3 or 4, and R^e has the same meaning as the radical R^c .


30

R^e is preferably -F, -Cl, -Br, -I, -CN, -NO₂, -NCO, -NCS, -OCN, -SCN, -C(=O)NR⁰R⁰⁰, -C(=O)X, -C(=O)R⁰, -NR⁰R⁰⁰, an optionally substituted silyl, aryl or heteroaryl group having 4 to 40, preferably 6 to 20, C atoms, or a straight-chain, branched or cyclic alkyl, alkoxy, alkylcarbonyl, alkoxy-carbonyl, alkylcarbonyloxy or alkoxy-carbonyloxy group having 1 to 20, preferably 1 to 12, C atoms, where one or more hydrogen atoms may optionally

be substituted by F or Cl, and the groups R⁰, R⁰⁰ and X have the meaning described above for formula PB-1.


Particular preference is given to recurring units of the formula PB-1 which
 5 are selected from the group consisting of units of the formulae PB-1F to PB-1I:

10




formula PB-1F

15




formula PB-1G

20



formula PB-1H

30



5

formula PB-11

in which the symbols have the following meaning:

10

L is H, halogen or an optionally fluorinated, linear or branched alkyl or alkoxy group having 1 to 12 C atoms and preferably stands for H, F, methyl, i-propyl, t-butyl, n-pentoxy or trifluoromethyl; and

15

L' is an optionally fluorinated, linear or branched alkyl or alkoxy group having 1 to 12 C atoms and preferably stands for n-octyl or n-octyloxy.

20

For carrying out the present invention, preference is given to polymers which contain more than one of the structural elements of groups 1 to 7 described above. It may furthermore be provided that the polymers preferably contain more than one of the structural elements from one group described above, i.e. comprise mixtures of structural elements selected from one group.

25

Particular preference is given, in particular, to polymers which, besides at least one structural element which has light-emitting properties (group 4), preferably at least one phosphorescent group, additionally contain at least one further structural element of groups 1 to 3, 5 or 6 described above, where these are preferably selected from groups 1 to 3.

30

The proportion of the various classes of groups, if present in the polymer, can be in broad ranges, where these are known to the person skilled in the art. Surprising advantages can be achieved if the proportion of one class

present in a polymer, which is in each case selected from the structural elements of groups 1 to 7 described above, is preferably in each case ≥ 5 mol%, particularly preferably in each case ≥ 10 mol%.

- 5 The preparation of white-emitting copolymers is described in detail, inter alia, in DE 10343606 A1.

In order to improve the solubility, the polymers may contain corresponding groups. It may preferably be provided that the polymers contain substitu-
10 ents, so that on average at least 2 non-aromatic carbon atoms, particularly preferably at least 4 and especially preferably at least 8 non-aromatic carbon atoms are present per recurring unit, where the average relates to the number average. Individual carbon atoms here may be replaced, for exam-
15 ple, by O or S. However, it is possible for a certain proportion, optionally all recurring units, to contain no substituents which contain non-aromatic carbon atoms. Short-chain substituents are preferred here, since long-chain substituents can have adverse effects on layers which can be obtained using organic functional materials. The substituents preferably contain at
20 most 12 carbon atoms, preferably at most 8 carbon atoms and particularly preferably at most 6 carbon atoms in a linear chain.

The polymer employed in accordance with the invention as organic functional material can be a random, alternating or regioregular copolymer, a block copolymer or a combination of these copolymer forms.
25

In a further embodiment, the polymer employed as organic functional material can be a non-conjugated polymer having side chains, where this embodiment is particularly important for phosphorescent OLEDs based on polymers. In general, phosphorescent polymers can be obtained by free-
30 radical copolymerisation of vinyl compounds, where these vinyl compounds contain at least one unit having a phosphorescent emitter and/or at least one charge-transport unit, as is disclosed, inter alia, in US 7250226 B2.

Further phosphorescent polymers are described, inter alia, in JP 2007/211243 A2, JP 2007/197574 A2, US 7250226 B2 and JP 2007/059939 A.

5 In a further preferred embodiment, the non-conjugated polymers contain backbone units, which are connected to one another by spacer units. Examples of such triplet emitters which are based on non-conjugated polymers based on backbone units are disclosed, for example, in DE 102009023154.

10 In a further preferred embodiment, the non-conjugated polymer can be designed as fluorescent emitter. Preferred fluorescent emitters which are based on non-conjugated polymers having side chains contain anthracene or benzanthracene groups or derivatives of these groups in the side chain, where these polymers are disclosed, for example, in JP 2005/108556,
15 JP 2005/285661 and JP 2003/338375.

These polymers can frequently be employed as electron- or hole-transport materials, where these polymers are preferably designed as non-conjugated polymers.

20 Furthermore, the functional compounds employed as organic functional materials in the formulations preferably have, in the case of polymeric compounds, a molecular weight M_w of $\geq 10,000$ g/mol, particularly preferably $\geq 20,000$ g/mol and especially preferably $\geq 50,000$ g/mol.

25 The molecular weight M_w of the polymers here is preferably in the range from 10,000 to 2,000,000 g/mol, particularly preferably in the range from 20,000 to 1,000,000 g/mol and very particularly preferably in the range from 50,000 to 300,000 g/mol. The molecular weight M_w is determined by means
30 of GPC (= gel permeation chromatography) against an internal polystyrene standard.

The publications cited above for description of the functional compounds are incorporated into the present application by way of reference for disclosure purposes.

5 The formulations according to the invention may comprise all organic functional materials which are necessary for the production of the respective functional layer of the electronic device. If, for example, a hole-transport, hole-injection, electron-transport or electron-injection layer is built up precisely from one functional compound, the formulation comprises precisely this compound as organic functional material. If an emission layer
10 comprises, for example, an emitter in combination with a matrix or host material, the formulation comprises, as organic functional material, precisely the mixture of emitter and matrix or host material, as described in greater detail elsewhere in the present application.

15

Besides the said components, the formulation according to the invention may comprise further additives and processing assistants. These include, inter alia, surface-active substances (surfactants), lubricants and greases,
20 additives which modify the viscosity, additives which increase the conductivity, dispersants, hydrophobising agents, adhesion promoters, flow improvers, antifoams, deaerating agents, diluents, which may be reactive or unreactive, fillers, assistants, processing assistants, dyes, pigments, stabilisers, sensitisers, nanoparticles and inhibitors.

25

The present invention furthermore relates to a process for the preparation of a formulation according to the invention, wherein the at least first and second solvent and the at least one organic functional material, which can be employed for the production of functional layers of electronic devices,
30 are mixed.

A formulation in accordance with the present invention can be employed for the production of a layer or multilayered structure in which the organic functional materials are present in layers, as are required for the production of preferred electronic or opto-electronic components, such as OLEDs.

5

The formulation of the present invention can preferably be employed for the formation of functional layers on a substrate or one of the layers applied to the substrate.

10 The present invention likewise relates to a process for the production of an electronic device in which a formulation according to the invention is applied to a substrate and dried.

15 The functional layers can be produced, for example, by flood coating, dip coating, spray coating, spin coating, screen printing, relief printing, gravure printing, rotary printing, roller coating, flexographic printing, offset printing or nozzle printing, preferably ink-jet printing on a substrate or one of the layers applied to the substrate.

20 After the application of a formulation according to the invention to a substrate or a functional layer already applied, a drying step can be carried out in order to remove the solvent from the continuous phase described above. The drying can preferably be carried out at relatively low temperature and over a relatively long period in order to avoid bubble formation and to obtain
25 a uniform coating. The drying can preferably be carried out at a temperature in the range from 80 to 300°C, particularly preferably 150 to 250°C and especially preferably 160 to 200°C. The drying here can preferably be carried out at a pressure in the range from 10^{-6} mbar to 2 bar, particularly preferably in the range from 10^{-2} mbar to 1 bar and especially
30 preferably in the range from 10^{-1} mbar to 100 mbar. The duration of the drying depends on the degree of drying to be achieved, where small

amounts of water can optionally be removed at relatively high temperature and in combination with sintering, which is preferably to be carried out.

5 It may furthermore be provided that the process is repeated a number of times, with formation of different or identical functional layers. Crosslinking of the functional layer formed can take place here in order to prevent dissolution thereof, as is disclosed, for example, in EP 0 637 899 A1.

10 The present invention also relates to an electronic device obtainable by a process for the production of an electronic device.

The present invention furthermore relates to an electronic device having at least one functional layer comprising at least one organic functional material which is obtainable by the above-mentioned process for the
15 production of an electronic device.

An electronic device is taken to mean a device which comprises anode, cathode and at least one functional layer in between, where this functional layer comprises at least one organic or organometallic compound.
20

The organic, electronic device is preferably an organic electroluminescent device (OLED), a polymeric electroluminescent device (PLED), an organic integrated circuit (O-IC), an organic field-effect transistor (O-FET), an organic thin-film transistor (O-TFT), an organic, light-emitting transistor
25 (O-LET), an organic solar cell (O-SC), an organic, optical detector, an organic photoreceptor, an organic field-quench device (O-FQD), an organic electrical sensor, a light-emitting electrochemical cell (LEC) or an organic laser diode (O-laser).

30 Active components are generally the organic or inorganic materials which are introduced between the anode and the cathode, where these active components effect, maintain and/or improve the properties of the electronic

device, for example its performance and/or its lifetime, for example charge-injection, charge-transport or charge-blocking materials, but in particular emission materials and matrix materials. The organic functional material which can be employed for the production of functional layers of electronic devices accordingly preferably comprises an active component of the electronic device.

Organic electroluminescent devices are a preferred embodiment of the present invention. The organic electroluminescent device comprises a cathode, an anode and at least one emitting layer.

It is furthermore preferred to employ a mixture of two or more triplet emitters together with a matrix. The triplet emitter having the shorter-wave emission spectrum serves as co-matrix here for the triplet emitter having the longer-wave emission spectrum.

The proportion of the matrix material in the emitting layer in this case is preferably between 50 and 99.9% by vol., particularly preferably between 80 and 99.5% by vol. and especially preferably between 92 and 99.5% by vol. for fluorescent emitting layers and between 85 and 97% by vol. for phosphorescent emitting layers.

Correspondingly, the proportion of the dopant is preferably between 0.1 and 50% by vol., particularly preferably between 0.5 and 20% by vol. and especially preferably between 0.5 and 8% by vol. for fluorescent emitting layers and between 3 and 15% by vol. for phosphorescent emitting layers.

An emitting layer of an organic electroluminescent device may also encompass systems which comprise a plurality of matrix materials (mixed-matrix systems) and/or a plurality of dopants. In this case too, the dopants are generally the materials whose proportion in the system is the smaller and the matrix materials are the materials whose proportion in the system is the

greater. In individual cases, however, the proportion of an individual matrix material in the system may be smaller than the proportion of an individual dopant.

5 The mixed-matrix systems preferably comprise two or three different matrix materials, particularly preferably two different matrix materials. One of the two materials here is preferably a material having hole-transporting properties and the other material is a material having electron-transporting properties. However, the desired electron-transporting and hole-transporting
10 properties of the mixed-matrix components may also be combined principally or completely in a single mixed-matrix component, where the further mixed-matrix component(s) fulfil(s) other functions. The two different matrix materials may be present here in a ratio of 1:50 to 1:1, preferably 1:20 to 1:1, particularly preferably 1:10 to 1:1 and especially preferably 1:4 to 1:1.
15 Mixed-matrix systems are preferably employed in phosphorescent organic electroluminescent devices. Further details on mixed-matrix systems can be found, for example, in WO 2010/108579.

Apart from these layers, an organic electroluminescent device may also
20 comprise further layers, for example in each case one or more hole-injection layers, hole-transport layers, hole-blocking layers, electron-transport layers, electron-injection layers, exciton-blocking layers, electron-blocking layers, charge-generation layers (IDMC 2003, Taiwan; Session 21 OLED (5), T. Matsumoto, T. Nakada, J. Endo, K. Mori, N. Kawamura, A.
25 Yokoi, J. Kido, *Multiphoton Organic EL Device Having Charge Generation Layer*) and/or organic or inorganic p/n junctions. It is possible here for one or more hole-transport layers to be p-doped, for example with metal oxides, such as MoO₃ or WO₃, or with (per)fluorinated electron-deficient aromatic compounds, and/or for one or more electron-transport layers to be n-doped.
30 It is likewise possible for interlayers, which have, for example, an exciton-blocking function and/or control the charge balance in the electro-

luminescent device, to be introduced between two emitting layers. However, it should be pointed out that each of these layers does not necessarily have to be present. These layers may likewise be present on use of the formulations according to the invention, as defined above.

5

The present invention thus also relates to a layer, in particular an organic layer, comprising one or more surface-active polymers, as defined above.

10

In a further embodiment of the present invention, the device comprises a plurality of layers. The formulation according to the invention can preferably be employed here for the production of a hole-transport, hole-injection, electron-transport, electron-injection and/or emission layer.

15

The present invention accordingly also relates to an electronic device which comprises at least three layers, but in a preferred embodiment all said layers, from hole-injection, hole-transport, emission, electron-transport, electron-injection, charge-blocking and/or charge-generation layer and in which at least one layer has been obtained by means of a formulation to be employed in accordance with the invention. The thickness of the layers, for example the hole-transport and/or hole-injection layer, can preferably be in the range from 1 to 500 nm, particularly preferably in the range from 2 to 200 nm.

20

25

The device may furthermore comprise layers built up from further low-molecular-weight compounds or polymers which have not been applied by the use of formulations according to the invention. These can also be produced by evaporation of low-molecular-weight compounds in a high vacuum.

30

It may additionally be preferred to use the compounds to be employed not as the pure substance, but instead as a mixture (blend) together with further polymeric, oligomeric, dendritic or low-molecular-weight substances of

any desired type. These may, for example, improve the electronic properties or themselves emit.

5 In a preferred embodiment of the present invention, the formulations according to the invention comprise organic functional materials which are employed as host materials or matrix materials in an emitting layer. The formulation here may comprise the emitters described above in addition to the host materials or matrix materials. The organic electroluminescent device here may comprise one or more emitting layers. If a plurality of
10 emission layers are present, these preferably have a plurality of emission maxima between 380 nm and 750 nm, resulting overall in white emission, i.e. various emitting compounds which are able to fluoresce or phosphoresce are used in the emitting layers. Very particular preference is given to three-layer systems, where the three layers exhibit blue, green and orange
15 or red emission (for the basic structure see, for example, WO 2005/011013). White-emitting devices are suitable, for example, as backlighting of LCD displays or for general lighting applications.

It is also possible for a plurality of OLEDs to be arranged one above the
20 other, enabling a further increase in efficiency with respect to the light yield to be achieved.

In order to improve the coupling-out of light, the final organic layer on the light-exit side in OLEDs can, for example, also be in the form of a nano-
25 foam, resulting in a reduction in the proportion of total reflection.

Preference is furthermore given to an organic electroluminescent device in which one or more layers are applied by means of a sublimation process, in which the materials are applied by vapour deposition in vacuum sublimation
30 units at a pressure below 10^{-5} mbar, preferably below 10^{-6} mbar, particularly preferably below 10^{-7} mbar.

It may furthermore be provided that one or more layers of an electronic device according to the invention are applied by means of the OVPD (organic vapour phase deposition) process or with the aid of carrier-gas sublimation, in which the materials are applied at a pressure between
5 10⁻⁵ mbar and 1 bar.

It may furthermore be provided that one or more layers of an electronic device according to the invention are produced from solution, such as, for example, by spin coating, or by means of any desired printing process,
10 such as, for example, screen printing, flexographic printing or offset printing, but particularly preferably LITI (light induced thermal imaging, thermal transfer printing) or ink-jet printing.

These layers may also be applied by a process in which no compound of
15 the formula (I) or (II) is employed. An orthogonal solvent can preferably be used here, which, although dissolving the functional material of a layer to be applied, does not dissolve the layer to which the functional material is applied.

20 The device usually comprises a cathode and an anode (electrodes). The electrodes (cathode, anode) are selected for the purposes of the present invention in such a way that their band energies correspond as closely as possible to those of the adjacent, organic layers in order to ensure highly efficient electron or hole injection.

25 The cathode preferably comprises metal complexes, metals having a low work function, metal alloys or multilayered structures comprising various metals, such as, for example, alkaline-earth metals, alkali metals, main-group metals or lanthanoids (for example Ca, Ba, Mg, Al, In, Mg, Yb, Sm,
30 etc.). In the case of multilayered structures, further metals which have a relatively high work function, such as, for example, Ag, can also be used in addition to the said metals, in which case combinations of the metals, such

as, for example, Ca/Ag or Ba/Ag, are generally used. It may also be preferred to introduce a thin interlayer of a material having a high dielectric constant between a metallic cathode and the organic semiconductor. Suitable for this purpose are, for example, alkali-metal or alkaline-earth metal fluorides, but also the corresponding oxides (for example LiF, Li₂O, BaF₂, MgO, NaF, etc.). The layer thickness of this layer is preferably between 0.1 and 10 nm, particularly preferably between 0.2 and 8 nm, especially preferably between 0.5 and 5 nm.

The anode preferably comprises materials having a high work function. The anode preferably has a potential greater than 4.5 eV vs. vacuum. Suitable for this purpose are on the one hand metals having a high redox potential, such as, for example, Ag, Pt or Au. On the other hand, metal/metal oxide electrodes (for example Al/Ni/NiO_x, Al/PtO_x) may also be preferred. For some applications, at least one of the electrodes must be transparent in order to facilitate either irradiation of the organic material (O-SCs) or the coupling-out of light (OLEDs/PLEDs, O-lasers). A preferred structure uses a transparent anode. Preferred anode materials here are conductive, mixed metal oxides. Particular preference is given to indium tin oxide (ITO) or indium zinc oxide (IZO). Preference is furthermore given to conductive, doped organic materials, in particular conductive, doped polymers, such as, for example, poly(ethylenedioxythiophene) (PEDOT) and polyaniline (PANI) or derivatives of these polymers. It is furthermore preferred for a p-doped hole-transport material to be applied as hole-injection layer to the anode, where suitable p-dopants are metal oxides, for example MoO₃ or WO₃, or (per)fluorinated electron-deficient aromatic compounds. Further suitable p-dopants are HAT-CN (hexacyanohexaazatriphenylene) or the compound NPD9 from Novaled. A layer of this type simplifies hole injection in materials having a low HOMO, i.e. an HOMO with a large value.

In general, all materials as are used for the layers in accordance with the prior art can be used in the further layers, and the person skilled in the art

will be able to combine each of these materials with the materials according to the invention in an electronic device without inventive step.

5 The device is correspondingly structured in a manner known per se, depending on the application, provided with contacts and finally hermetically sealed, since the lifetime of such devices is drastically shortened in the presence of water and/or air.

10 The formulations according to the invention and the electronic devices, in particular organic electroluminescent devices, obtainable therefrom are distinguished over the prior art by one or more of the following surprising advantages:

- 15 1. The electronic devices obtainable using the formulations according to the invention exhibit very high stability and a very long lifetime compared with electronic devices obtained using conventional methods.
- 20 2. The formulations according to the invention can be processed using conventional methods, so that cost advantages can also be achieved thereby.
- 25 3. The organic functional materials employed in the formulations according to the invention are not subject to any particular restrictions, enabling the process of the present invention to be employed comprehensively.
- 30 4. The coatings obtainable using the formulations of the present invention exhibit excellent quality, in particular with respect to the uniformity of the coating.

These above-mentioned advantages are not accompanied by an impairment of the other electronic properties.

It should be pointed out that variations of the embodiments described in the present invention fall within the scope of this invention. Each feature disclosed in the present invention can, unless this is explicitly excluded, be replaced by alternative features which serve the same, an equivalent or a similar purpose. Thus, each feature disclosed in the present invention is, unless stated otherwise, to be regarded as an example of a generic series or as an equivalent or similar feature.

All features of the present invention can be combined with one another in any way, unless certain features and/or steps are mutually exclusive. This applies, in particular, to preferred features of the present invention. Equally, features of non-essential combinations can be used separately (and not in combination).

It should furthermore be pointed out that many of the features, and in particular those of the preferred embodiments of the present invention, are themselves inventive and are not to be regarded merely as part of the embodiments of the present invention. For these features, independent protection can be sought in addition or as an alternative to each invention presently claimed.

The teaching on technical action disclosed with the present invention can be abstracted and combined with other examples.

The invention is explained in greater detail below with reference to working examples, but without being restricted thereby.

The person skilled in the art will be able to use the descriptions to produce further electronic devices according to the invention without the need to employ inventive skill and thus can carry out the invention throughout the range claimed.


Working Examples

Two devices were made, using the device structure shown in Figure 1. The hole-injection layers (HIL) are Example 1 and Example 2. The solvents for HIL are a mixture of 3-phenoxytoluene and decamethylcyclopentasiloxane having a ratio by volume of 97:3 (Example 1), and a mixture of 3-phenoxytoluene and dodecamethylcyclohexasiloxane having a ratio by volume of 97:3 (Example 2). Table 2 summarizes concentration, viscosity and surface tension of the inks used in these examples as hole-injection layer material.

Layer	Ink Code	Conc. (g/L)	Viscosity (mPas)	Surface Tension (mN/m)
HIL	Example 1	13	4.2	29.6
HIL	Example 2	13	4.1	28.1

Table 2. Concentration, viscosity and surface tension of the inks for HIL.

Table 3 shows the boiling point, surface tension and viscosity of the solvents used in the examples.

Solvents	Boiling point (°C)	Viscosity (mPas) @25°C	Surface tension (mN/m)
 3-phenoxytoluene, CAS: 3586-14-9	272	4.4	37.8



5	 <p>Decamethylcyclopentasiloxane, CAS: 541-02-6</p>	211	4.04	17.9
10	 <p>Dodecamethylcyclohexasiloxane, CAS: 540-97-6</p>	245	6.84	18.2

Table 3: Solvents used in the examples.

15 The viscosity of the formulations and solvents was measured using a 1°
cone-plate rotational rheometer (type: Haake MARS III Rheometer from
Thermo Scientific), where the temperature and sheer rate are exactly
controlled. The viscosities given in Table 2 are the viscosities of each
20 formulation measured at a temperature of 23.4°C (+/- 0.2°C) and a sheer
rate of 500s⁻¹. The measurements were carried out with the following setup:
Haake MARS III Rheometer with bottom plate TMP60 and cone C60/1° Ti
L.; N₂ supply with a back-pressure of ~ 1.8 bar; sample volume of 1.3 mL.
Each formulation is measured three times. The stated viscosity value is
25 averaged over said measurements. The data processing is performed with
the software "Haake RheoWin Job Manager" in accordance with DIN 1342-
2. The equipment (Haake MARS III from Thermo Scientific) is regularly
calibrated by Thermo Scientific and received a certified standard factory
calibration before its first use.

30 The Surface tension measurements were performed using the high
precision drop shape analysis tool DSA100 from Krüss GmbH. The surface

tension is determined by the software "DSA4" in accordance with DIN 55660-1. All measurements were performed at room temperature being in the range between 22°C and 24°C. The standard operating procedure includes the determination of the surface tension of each formulation
5 (sample volume of 0.3 mL) using a fresh disposable drop dispensing system (syringe and needle). Each drop is measured over the duration of one minute with sixty measurements which are later on averaged. For each formulation three drops are measured. The final value is averaged over said measurements. The tool is regularly cross-checked against various
10 liquids having well known surface tension.

Description of Fabrication Process

Glass substrates covered with pre-structured ITO and bank material were cleaned using ultrasonication in de-ionized water, then dried using an air-
15 gun and a subsequent annealing on a hot-plate at 180°C for 5 minutes. Then a plasma treatment (first 5 seconds of O₂ plasma followed by 80 seconds of CF₄ plasma) was conducted. A hole-injection layer (HIL) was inkjet-printed onto the substrate and dried in vacuum. The HIL was then annealed at 180°C for 30 minutes. On top of the HIL, a hole-transport
20 layer (HTL) was inkjet-printed, dried in vacuum and annealed at 230°C for 30 minutes. The green emissive layer (G-EML) was also inkjet-printed, vacuum dried and annealed at 160°C for 10 minutes. All the inkjet printing processes were done under yellow light, in air and under ambient
25 conditions. HIL annealing process was done in air; HTL and G-EML were annealed in nitrogen atmosphere. The devices were then transferred into the vacuum deposition chamber where the deposition of a blue emissive layer (B-EML), an electron-transport layer (ETL), and a cathode (Al) was done using thermal evaporation. The devices were then encapsulated in a
30 glove box and physical characterization was performed in ambient air. The device is driven with constant voltage provided by a Keithley 230 voltage source. The voltage over the LEP device as well as the current through the LEP device are measured with two Keithley 199 DMM

multimeters. The brightness of the device is detected with a SPL-025Y brightness sensor, a combination of a photodiode with a photonic filter. The photo current is measured with a Keithley 617 electrometer. For the spectra, the brightness sensor is replaced by a glass fiber which is
5 connected to the spectrometer input. The device lifetime is measured under a given current with an initial luminance. The luminance is then measured over time by a calibrated photodiode.

Results and Discussion

10 The luminance efficiency at 1000 cd/m^2 is 48.7 and 49.2 cd/A for Example 1 and Example 2, respectively. The external quantum efficiency (EQE) at 1000 cd/m^2 is 13.8 and 13.8% for Example 1 and Example 2, respectively. The power efficiency at 1000 cd/m^2 is 23.4 and 23.2 lm/W for Example 1 and Example 2, respectively. The measured values are summarized in
15 Table 4.

The efficiencies of the examples in this invention show very good values. This is due to the fact that the HIL layer, when deposited using for example here mentioned solvent blends of 3-phenoxytoluene and
20 dodecamethylcyclopentasiloxane as well as 3-phenoxytoluene and dodecamethylcyclohexasiloxane are showing a better film formation during the drying process. There is no difference between our examples, which clearly shows that there is no damage or bad effect of the new solvent system on the device performance if the chainlength of the cyclosiloxane is
25 varied. Furthermore, the co-solvent system provides a much wider tunable range of viscosities and surface tensions. This allows a greater variability of the process to meet the different requirements of various ink-jet printing machines using different printing heads.

30

5

	Luminance efficiency at 1000 cd/m ²	External quantum efficiency at 1000 cd/m ²	Power efficiency at 1000 cd/m ²
Example 1	48.7 cd/A	13.8%	23.4 lm/W
Example 2	49.2 cd/A	13.8%	23.2 lm/W

10

Table 4: Luminance efficiency, external quantum efficiency and power efficiency of Examples 1 and 2.

Additional Working Examples 3 and 4 and Reference

15

Description of the Fabrication Process

20

All following working examples were made using the device structure as shown in Figure 2. The hole-injection layer (HIL) and hole transport layer (HTL) of all examples were prepared by an inkjet printing process to achieve the desired thickness. For the green emissive layer, the individual solvents used in the Reference and Examples 3 and 4 are listed in Table 3 above showing the boiling point, viscosity and surface tension of the solvents used in these working examples. The specific physical chemical characterization properties of the EML ink formulations are as follows:

25

EML1's surface tension was measured under room temperature and gave 17.9 mN/m and EML2's surface tension resulted in 18.3 mN/m. Also the viscosity of both formulations was characterized using the above described viscosity measurement set-up. Under the standard temperature the characteristic curve of a Newtonian fluid could be verified. EML1 gave 3.86 mPas under a sheer-rate of 489.5 per second, whereas EML2 resulted in a 29.824% lower viscosity than solvent 2 under 400 per second sheer rate.

30


The concentration of the EML inks is shown in Table 5 below.

Glass substrates covered with pre-structured ITO and bank material were cleaned using ultrasonication in isopropanol followed by de-ionized water, then dried using an air-gun and a subsequent annealing on a hot-plate at
 5 230°C for 2 hours.

A hole-injection layer (HIL) using PEDOT-PSS (Clevios Al4083, Heraeus) was inkjet-printed onto the substrate and dried in vacuum. The HIL was then annealed at 185°C for 30 minutes in air.

10 On top of the HIL, a hole-transport layer (HTL) was inkjet-printed, dried in vacuum and annealed at 210°C for 30 minutes in nitrogen atmosphere. As material for the hole-transport layer polymer HTM-1 was used. The structure of the polymer HTM-1 is the following:

15




25

The green emissive layer (G-EML) was also inkjet-printed, vacuum dried and annealed at 160°C for 10 minutes in nitrogen atmosphere. The ink for the green emissive layer contained in all working examples two host materials (*i.e.* HM-1 and HM-2) as well as one triplet emitter (EM-1). The materials were used in the following ratio: HM-1 : HM-2 : EM-1 = 40 : 40 :
 30 20. Only the solvent differ from example to example, as can be seen from

Table 5 below which shows the composition and concentration of the inks used in Examples 3 and 4 and the Reference.

The structures of the materials are the following:


5



HM-1

10


15



HM-2

20

25




30

EM-1

All the inkjet printing processes were performed under yellow light and under ambient conditions.

5 The devices were then transferred into the vacuum deposition chamber where the deposition of a common hole blocking layer (HBL), an electron-transport layer (ETL), and a cathode (Al) was done using thermal evaporation (see Figure 2). The devices were then characterized in the glovebox.

10 In the hole blocking layer (HBL) ETM-1 was used as a hole-blocking material. The material has the following structure:



20 In the electron transport layer (ETL) a 50:50 mixture of ETM-1 and LiQ was used. LiQ is lithium 8-hydroxyquinolate.

25 Finally, the Al electrode is vapor-deposited. The devices were then encapsulated in a glove box and physical characterization was performed in ambient air.

30

Working Example	Layer	Ink Code	Solvent 1	Volume % of Solvent 1	Solvent 2	Volume % of Solvent 2	Total solid concentration (weight%)
5 Reference	G-EML	Reference	CAS: 3586-14-9	100	-	0	1.332
Example 3	G-EML	EML1	CAS: 3586-14-9	99.5	CAS: 541-02-6	0.5	1.333
Example 4	G-EML	EML2	CAS: 3586-14-9	97	CAS: 541-02-6	3	1.336

10 Table 5: Composition and concentration of the inks for Examples 3 and 4 and the Reference (assuming ideal behavior for solvent mixtures).

Measurement methods for Examples 3 and 4 and the Reference

15 The devices are driven with constant voltage provided by a Keithley 230 voltage source. The voltage over the device as well as the current through the device are measured with two Keithley 199 DMM multimeters. The brightness of the device is detected with a SPL-025Y brightness sensor, a combination of a photodiode with a photonic filter. The photo current is measured with a Keithley 617 electrometer. For the spectra, the brightness

20 sensor is replaced by a glass fiber which is connected to the spectrometer input. The device lifetime is measured under a given current with an initial luminance. The luminance is then measured over time by a calibrated photodiode.

25 Table 6 summarizes the luminance efficiency and quantum efficiency at 1500 cd/m², as well as device lifetime LT90 at initial brightness 6000 cd/m². The efficiencies of all the examples in this invention show comparable or slightly better values as reference. This is due to the fact that using decamethylcyclopentasiloxane and dodecamethylcyclohexasiloxane in G-

30 EML layer improves wetting properties and results in a better film formation during the drying process. There is a slight improvement of the device parameters of examples 3 and 4, which shows that there is no negative


effect of the new solvent system on the device performance. Furthermore, the co-solvent system provides a much wider tunable range of viscosities and surface tensions. This allows a greater variability of the process to meet the different requirements of various ink-jet printing machines using different printing heads. Additionally, the wetting of the inks on substrates and underlying layers is improved which increases the homogeneity of the resulting emission.

	Luminance efficiency @ 1500 cd/m ² (cd/A)	External quantum efficiency @ 1500 cd/m ² (%)	Device Lifetime LT90 @ initial luminance of 6000 cd/m ² (hours)
Reference	56.2	15.2	32
Example 3	56.9	15.4	35
Example 4	57.5	15.5	36

Table 6: Luminance efficiency, external quantum efficiency and device lifetime for Reference and Examples 3 and 4.

Patent Claims

1. Formulation containing at least one organic functional material and at least a first and a second solvent, characterized in that the first solvent is a siloxane.
- 5
2. Formulation according to claim 1, characterized in that the first solvent is a cyclosiloxane.
- 10
3. Formulation according to claim 2, characterized in that the cyclosiloxane is a cyclosiloxane according to general formula (I)



wherein

R¹ and R² are identical or different at each occurrence, and are H, D, F, Cl, Br, I, NO₂, CN, a straight-chain alkyl or alkoxy group having from 1 to 20 carbon atoms or a branched or cyclic alkyl or alkoxy group having from 3 to 20 carbon atoms, in which one or more nonadjacent CH₂ groups may be replaced by -O-, -S-, -NR⁵-, -CONR⁵-, -CO-O-, -C=O-, -CH=CH- or -C≡C-, and in which one or more hydrogen atoms may be replaced by F, or an aryl or heteroaryl group which has from 4 to 14 carbon atoms and may be substituted by one or more nonaromatic R⁵ radicals, and a plurality of substituents R⁵, either on the same ring or on the two different rings, may together in turn form a mono- or polycyclic, aliphatic or aromatic ring system; R⁵ are identical or different at each instance, and are a straight-chain alkyl or alkoxy group having from 1 to 20 carbon atoms or a branched or cyclic alkyl or alkoxy group having from 3 to 20 carbon atoms, in


20

25

30

which one or more nonadjacent CH₂ groups may be replaced by -O-,
 -S-, -CO-O-, -C=O-, -CH=CH- or -C≡C-, and in which one or more
 hydrogen atoms may be replaced by F, or an aryl or heteroaryl group
 which has from 4 to 14 carbon atoms and may be substituted by one
 5 or more nonaromatic R⁵ radicals; and
 n is in the range from 3 to 9, preferably 4, 5, 6 or 7 and more
 preferably 5 or 6.

4. Formulation according to claim 1, characterized in that the siloxane is
 10 a siloxane according to general formula (II)



15 wherein R¹, R², R³ and R⁴ are identical or different at each
 occurrence, and are H, D, F, Cl, Br, I, NO₂, CN, a straight-chain alkyl
 or alkoxy group having from 1 to 20 carbon atoms or a branched or
 cyclic alkyl or alkoxy group having from 3 to 20 carbon atoms, in which
 20 one or more nonadjacent CH₂ groups may be replaced by -O-, -S-, -
 NR⁵-,
 -CONR⁵-, -CO-O-, -C=O-, -CH=CH- or -C≡C-, and in which one or
 more hydrogen atoms may be replaced by F, or an aryl or heteroaryl
 group which has from 4 to 14 carbon atoms and may be substituted
 25 by one or more nonaromatic R⁵ radicals, and a plurality of substituents
 R⁵, either on the same ring or on the two different rings, may together
 in turn form a mono- or polycyclic, aliphatic or aromatic ring system;
 R⁵ are identical or different at each instance, and are a straight-chain
 alkyl or alkoxy group having from 1 to 20 carbon atoms or a branched
 30 or cyclic alkyl or alkoxy group having from 3 to 20 carbon atoms, in
 which one or more nonadjacent CH₂ groups may be replaced by -O-,
 -S-, -CO-O-, -C=O-, -CH=CH- or -C≡C-, and in which one or more

hydrogen atoms may be replaced by F, or an aryl or heteroaryl group which has from 4 to 14 carbon atoms and may be substituted by one or more nonaromatic R⁵ radicals; and

n is in the range from 3 to 9, preferably 4, 5, 6 or 7 and more preferably 5 or 6.

5

5. Formulation according to one or more of the preceding claims 1 to 4, characterized in that the content of the first solvent is in the range from 1 to 50 vol.-%, preferably in the range from 1 to 25 vol.-% and more preferably in the range from 1 to 10 vol.-%, based on the total amount of solvents in the formulation.

10

6. Formulation according to one or more of the preceding claims 1 to 5, characterized in that the content of the second solvent is in the range from 50 to 99 vol.-%, preferably in the range from 75 to 99 vol.-% and more preferably in the range from 90 to 99 vol.-%, based on the total amount of solvents in the formulation.

15

7. Formulation according to one or more of the preceding claims 1 to 6, characterized in that the first solvent has a boiling point in the range from 100 to 400°C, preferably 150 to 350°C.

20

8. Formulation according to one or more of the preceding claims 1 to 7, characterized in that the second solvent has a boiling point in the range from 100 to 400°C, preferably 150 to 350°C.

25

9. Formulation according to one or more of the preceding claims 1 to 8, characterized in that the at least one organic functional material has a solubility in the second solvent in the range from 1 to 250 g/l.

30

10. Formulation according to one or more of the preceding claims 1 to 9, characterized in that the formulation has a surface tension in the

range from 1 to 70 mN/m, preferably in the range from 10 to 50 mN/m and more preferably in the range from 15 to 40 mN/m.

- 5
11. Formulation according to one or more of the preceding claims 1 to 10, characterized in that the formulation has a viscosity in the range from 1 to 50 mPas, preferably in the range from 2 to 40 mPas, and more preferably in the range from 2 to 20 mPas.
- 10
12. Formulation according to one or more of the preceding claims 1 to 11, characterized in that the content of the at least one organic functional material in the formulation is in the range from 0.001 to 20 weight-%, preferably in the range from 0.01 to 10 weight-% and more preferably in the range from 0.1 to 5 weight-%, based on the total weight of the formulation.
- 15
13. Formulation according to one or more of the preceding claims 1 to 12, characterized in that the at least one organic functional material is selected from the group consisting of organic conductors, organic semiconductors, organic fluorescent compounds, organic phosphorescent compounds, organic light-absorbent compounds,
- 20
- organic light-sensitive compounds, organic photosensitisation agents and other organic photoactive compounds such as organometallic complexes of transition metals, rare earths, lanthanides and actinides.
- 25
14. Formulation according to claim 13, characterized in that the at least one organic functional material is selected from the group consisting of fluorescent emitters, phosphorescent emitters, host materials, matrix materials, exciton-blocking materials, electron-transport materials, electron-injection materials, hole-conductor materials, hole-injection materials, n-dopants, p-dopants, wide-band-gap materials,
- 30
- electron-blocking materials and hole-blocking materials.

- 5
15. Formulation according to claim 13, characterized in that the at least one organic functional material is an organic semiconductor selected from the group consisting of hole-injecting, hole-transporting, emitting, electron-transporting and electron-injecting materials.
- 10
16. Formulation according to claim 15, characterized in that the at least one organic semiconductor is selected from the group consisting of hole-injecting and hole-transporting materials.
17. Formulation according to claim 16, characterized in that the hole-injecting and hole-transporting material is a polymeric compound or a blend of a polymeric compound and a non-polymeric compound.
- 15
18. Process for the preparation of a formulation according to one or more of the preceding claims 1 to 17, wherein the at least first and second solvent and the at least one organic functional material are mixed.
- 20
19. Process for the preparation of an electroluminescent device, characterized in that at least one layer of the electroluminescent device is prepared in that a formulation according to one of more of claims 1 to 17 is deposited, preferably printed, on a surface and subsequently dried.
- 25
20. Electroluminescent device, characterized in that it contains at least one layer, which is prepared in that a formulation according to one or more of claims 1 to 17 is deposited, preferably printed, on a surface and subsequently dried.
- 30

Figure 1:

5	100 nm	Al Cathode
	20 nm	ETL
	20 nm	B-EML
	60 nm	G-EML
	20 nm	HTL
10	40 nm	HIL (Reference, Examples 1 & 2)
	50 nm	ITO Anode
		Substrate

Figure 2:

15	100 nm	Al Cathode
	40 nm	ETL
	10 nm	HBL
	60 nm	G-EML (Reference, Examples 3 & 4)
20	20 nm	HTL
	20 nm	HIL
	50 nm	ITO Anode
		Substrate

25

30

INTERNATIONAL SEARCH REPORT

International application No PCT/EP2016/000392

A. CLASSIFICATION OF SUBJECT MATTER
 INV. H01L51/00 C08G77/04
 ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
 H01L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2009/085095 A1 (KAMATH ARVIND [US] ET AL) 2 April 2009 (2009-04-02) cited in the application paragraphs [0057], [0045] -----	1-20
X	US 2012/256137 A1 (JAMES MARK [GB] ET AL) 11 October 2012 (2012-10-11) examples 1,6-12 -----	1-20
X	US 6 063 135 A (BERNDT DIETER R [US] ET AL) 16 May 2000 (2000-05-16) the whole document -----	1-12

Further documents are listed in the continuation of Box C.

See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance
 "E" earlier application or patent but published on or after the international filing date
 "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
 "O" document referring to an oral disclosure, use, exhibition or other means
 "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

3 May 2016

Date of mailing of the international search report

17/05/2016

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040,
 Fax: (+31-70) 340-3016

Authorized officer

Wolfbauer, Georg

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No PCT/EP2016/000392

Patent document cited in search report		Publication date		Patent family member(s)	Publication date
US 2009085095	A1	02-04-2009	CA	2701412 A1	09-04-2009
			CN	101821839 A	01-09-2010
			EP	2195829 A1	16-06-2010
			JP	2010541255 A	24-12-2010
			KR	20100081983 A	15-07-2010
			KR	20160040319 A	12-04-2016
			SG	2012070850 A	28-04-2014
			US	2009085095 A1	02-04-2009
			US	2013189823 A1	25-07-2013
			WO	2009046148 A1	09-04-2009

US 2012256137	A1	11-10-2012	CN	102668151 A	12-09-2012
			EP	2517273 A1	31-10-2012
			JP	5840621 B2	06-01-2016
			JP	2013516052 A	09-05-2013
			KR	20120123361 A	08-11-2012
			TW	201144367 A	16-12-2011
			US	2012256137 A1	11-10-2012
			WO	2011076324 A1	30-06-2011

US 6063135	A	16-05-2000	NONE		
