



- (51) **International Patent Classification:**
C08K 5/51 (2006.01) *C08L 23/04* (2006.01)
- (21) **International Application Number:**
PCT/IB2016/056758
- (22) **International Filing Date:**
9 November 2016 (09.11.2016)
- (25) **Filing Language:** English
- (26) **Publication Language:** English
- (30) **Priority Data:**
2913280 25 November 2015 (25.11.2015) CA
- (71) **Applicant: NOVA CHEMICALS (INTERNATIONAL) S.A.** [CH/CH]; Avenue de la Gare 14, 1700 Fribourg (CH).
- (72) **Inventors: WALDIE, Fraser;** 826 Radford Road NE, Calgary, Alberta T2E 5G2 (CA). **LIGHTBODY, Owen;** #302, 354 - 2nd Avenue NE, Calgary, Alberta T2E 0E4 (CA). **TIKUISIS, Tony;** 2205 - 1st Street NW, Calgary, Alberta T2M 2T7 (CA). **CHISHOLM, P. Scott;** 4927 Batchelor Crescent NW, Calgary, Alberta T2L 1S8 (CA).
- (81) **Designated States** (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR,

KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

- (84) **Designated States** (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

- *as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))*
- *as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii))*
- *of inventorship (Rule 4.17(iv))*

Published:

- *with international search report (Art. 21(3))*



WO 2017/089920 A1

(54) **Title:** PHENOL FREE STABILIZATION OF POLYETHYLENE

(57) **Abstract:** This invention provides a process for the stabilization of thermoplastic polyolefins during melt processing operations. The stabilizer package of this invention is "phenol free" and must contain at least two selected phosphite stabilizers. The process of this invention is especially suitable for the manufacture of polyethylene film.

PHENOL FREE STABILIZATION OF POLYETHYLENE

TECHNICAL FIELD

This invention relates to the melt processing of polyolefins using a stabilizer which is essentially free of any phenolic antioxidant.

BACKGROUND ART

Polyolefins are conventionally stabilized with a phenolic antioxidant and a phosphite. A hindered amine light stabilizer (or "HALS") may also be included if long term stabilization is desired. These formulations generally provide adequate stabilization performance during the melt processing operations which are used to produce finished plastic parts from the thermoplastic polyolefin resin and during the normal lifetime of the parts.

A general overview of phenol/phosphite stabilizer systems is provided in Polyolefins 2001--The International Conference on Polyolefins, "Impact of Stabilization Additives on the Controlled Degradation of Polypropylene", p. 521, presented by Urs Stadler of Ciba Specialty Chemicals Corporation. For convenience, a summary of the teachings of this paper is provided below. It is generally accepted that:

1. Carbon centered radicals (or "CCRs") are formed when polyolefins are subjected to heat and shear during melt processing;
2. CCRs react with oxygen to form peroxy radicals (or "PRs"); and
3. PR's react with the polyolefin to form hydroperoxides (or "HPs") and more CCRs.

In a conventional phenol/phosphite stabilizer system, it is generally accepted that:

1. the phenolic (which is also referred to as the "primary" antioxidant) decomposes the carbon centered radicals and peroxy radicals; and
2. the phosphite (which is also referred to as the "secondary" antioxidant) decomposes the hydroperoxides.

In addition, it is generally accepted that (a) the phenolic antioxidant provides a synergistic effect at the temperatures which are encountered during melt processing by reducing the rate at which the phosphite is depleted or consumed; and (b) if/when the phosphite is depleted (to below the concentration which is

required for the decomposition of the hydroperoxides) then the structure of the polyolefin is altered by the action of the free radicals. In polypropylene, this generally results in "chain scission" (a reduction in the molecular weight of the polypropylene) whereas "crosslinking" is generally believed to predominate in polyethylene (which results in an increase in apparent molecular weight).

Stabilizer packages which comprise a combination of a phenolic antioxidant and a phosphite are in wide spread commercial use and generally provide efficient and cost effective results.

However, the use of phenolics is associated with color development in the finished plastic parts, especially in polyethylene or polypropylene which is produced with a transition metal catalyst (such as titanium, vanadium, zirconium or chromium). For example, "yellowing" and "pinking" have been observed in plastic parts which are stabilized with a phenolic antioxidant.

Thus, as noted in United States Patent ("USP") U.S. Pat. No. 5,596,033: "there is a long-felt need in the market place for a stabilizer system which can prevent color formation associated with the use of phenolic antioxidants".

Several "phenol free" stabilization systems have been proposed and brief overviews of several of these systems follow:

1. Phosphites plus hindered amines (HALS): these phenol free systems are reported to lack adequate process stabilization (see U.S. Pat. No. 5,596,033).
2. N,N-dialkylhydroxylamine plus HALS: these phenol free systems are expensive (due to the high cost of the hydroxylamine) and may have restricted use in certain food contact applications due to FDA regulations (again, due to the presence of the hydroxylamine) (U.S. Pat. No. 5,596,033).
3. HALS, plus hydroxylamine (or nitron) plus phosphite: as above, these phenol free systems are expensive and may have restrictions upon their use (U.S. Pat. No. 6,664,317).
4. HALS plus hydroxylamine plus a mixture of two hydrolytically resistant phosphites: as above, these phenol free systems are expensive and may have restrictions upon their use (U.S. Pat. No. 6,077,890).
5. Lactones (such as benzofuranone) plus HALS: these phenol free systems are also expensive (due to the high cost of the lactone) and may have restricted use due to FDA regulations concerning the use of lactones (U.S. Pat. No. 5,883,165).

6. Combination of aryl monophosphite with a diphosphite: these dual phosphite systems are subject to solubility limitations that restrict the use of the systems in some cast film applications (U.S. Patent No. 7,361,703).

We have now discovered an effective low cost, phenol free stabilization package for the melt processing of polyolefins.

DISCLOSURE OF INVENTION

The present invention provides a process for stabilizing a thermoplastic polyolefin during melt processing conditions, said process comprising the step of incorporating into said thermoplastic polyolefin a stabilizer package comprising:

- i. a first phosphite: tris(2-4-di-tert-butylphenyl)phosphite; and
- ii. a second phosphite composition consisting essentially of:

phosphorous acid, mixed 2,4-bis(1,1-dimethylpropyl)phenyl and 4-(1,1-dimethylpropyl) phenyl triesters,

and subjecting said thermoplastic polyolefin to sufficient temperature to melt said polyolefin;

with the proviso that said stabilizer package is essentially free of any additive selected from the group consisting of hindered phenolic antioxidants, lactone stabilizers and hydroxylamine stabilizers.

BEST MODE FOR CARRYING OUT THE INVENTION

This invention generally relates to the melt processing of polyolefins using a stabilizer system which is essentially free of phenolic antioxidant.

The "phenol free" melt processing operation of this invention is generally suitable for any thermoplastic polyolefin, though thermoplastic polypropylene and polyethylene are preferred. The preferred thermoplastic polyolefins for use in this invention are prepared with a transition metal catalyst such as titanium, vanadium, zirconium or chromium and the present invention is particularly suitable for polyolefins which contain from about 0.5 parts per million by weight ("ppm") to about 10 parts per million by weight of transition metal residue. (The process of this invention may not provide complete process stabilization if the polyolefin contains more than 10 parts per million transition metal and the process of this invention may not be required if the polyolefin contains less than 0.5 ppm of transition metal). In addition, the polyolefin may contain magnesium residues (in amounts up to 500 ppm); aluminum residues (in amounts up to 150 ppm); and chlorine residues (in amounts up to 200 ppm).

It is preferred that the thermoplastic polyolefin is a linear polyethylene having:

- (i) a density of from 0.880 grams per cubic centimeter (g/cc) to 0.960 grams per cubic centimeter (g/cc) -- especially from 0.910 to 0.945 g/cc; and
- (ii) a melt index, I₂, as determined by ASTM D 1238 of from 0.3 (grams per 10 minutes) to 150, especially from 1 to 100 and most preferably from 1.5 to 5.

The most preferred linear polyethylene are copolymers of ethylene with at least one other olefin selected from the group consisting of butene, pentene, hexene, and octene. These thermoplastic polyethylenes may be produced in any of the known polymerization processes (such as a gas phase process, a slurry process or a solution process) using any known polymerization catalyst (such as a chromium catalyst, a Ziegler Natta catalyst or a single site catalyst such as a metallocene catalyst or a so-called "constrained geometry catalyst").

The melt processing process of this invention is characterized by:

- (1) the required use of a first phosphite (described in part A below);
 - (2) the required use of a second phosphite (described in part B below);
- and
- (3) that the melt processing is essentially free of a phenolic antioxidant or hydroxylamine or lactone stabilizer (described in part D below).

In addition to the two require phosphites, the stabilizer package used in the present invention preferably contains an acid neutralizer (described in Part C.1 below). If the finished part which is made in accordance with the present invention is intended for long term use, then the use of additional stabilizers (especially HALS) is preferred as described in C.2 below. Other conventional additives may also be included.

PART A

First Phosphite

The first phosphite is tris(2-4-di-tert-butylphenyl)phosphite (CAS Reg. No. 31570-04-4). This phosphite is commercially available under the trademark IRGAFOS® I-168.

PART B

Second Phosphite

The second phosphite is not a discrete molecule. It is a mixture of molecules that is defined as: phosphorous acid, mixed 2,4-bis(1,1-dimethylpropyl)phenyl and 4-(1,1-dimethylpropyl) phenyl triesters.

The CAS registry number for the second phosphite is 9390402-02-5. The second phosphite is commercially available under the trademark WESTON® 705.

In an embodiment, each of the first phosphites and the second phosphite composition is used in amounts of from 200 ppm to 2,000 ppm, preferably from 300 to 1,500 ppm and most preferably from 400 to 1,000 ppm.

PART C.1 - Acid Neutralizers

Many commercially available polyolefins contain chloride residues. These chloride residues may generate hydrochloric acid, particularly during melt processing operations. Accordingly, an "acid neutralizer" is conventionally included in a polyolefin stabilization package and is preferably included in the process of this invention.

These acid neutralizers may be divided into "Inorganic" -- such as zinc oxide, synthetic hydrotalcites and Li, Na, Ca or Al (hydroxy) carbonates; and "Organic" -- such as salts of fatty acids or their derivatives including calcium stearate, zinc stearate, calcium lactate and calcium stearoyl lactylate.

When employed, these conventional acid neutralizers are used in conventional amounts. It is preferred to use a synthetic hydrotalcite (in an amount of from 100 to 1,000 ppm), zinc stearate (in an amount of from 200 to 700 ppm) or calcium stearoyl lactylate (in an amount of from 200 to 700 ppm). A combination of a hydrotalcite with an "organic" acid neutralizer is highly preferred.

Part C.2 - Long Term Stabilizers

Plastic parts which are intended for long term use preferably contain at least one HALS (C.2.1).

Part C.2.1 - HALS

A hindered amine light stabilizer (HALS) is preferably included in the stabilizer package used in the present invention if the plastic part is intended for more than single/short term use.

HALS are well known to those skilled in the art.

When employed, the HALS is preferably a commercially available material and is used in a conventional manner and amount.

Commercially available HALS include those sold under the trademarks CHIMASSORB® 119; CHIMASSORB 944; CHIMASSORB 2020; TINUVIN® 622 and TINUVIN 770 from Ciba Specialty Chemicals Corporation, and CYASORB® UV 3346, CYASORB UV 3529, CYASORB UV 4801, and CYASORB UV 4802 from Cytec Industries. TINUVIN 622 is preferred. Mixtures of more than one HALS are also contemplated.

Suitable HALS include: bis (2,2,6,6-tetramethylpiperidyl)-sebacate; bis-5 (1,2,2,6,6-pentamethylpiperidyl)-sebacate; n-butyl-3,5-di-tert-butyl-4-hydroxybenzyl malonic acid bis(1,2,2,6,6,-pentamethylpiperidyl)ester; condensation product of 1-hydroxyethyl-2,2,6,6-tetramethyl-4-hydroxy-piperidine and succinic acid; condensation product of N,N'-(2,2,6,6-tetramethylpiperidyl)-hexamethyldiamine and 4-tert-octylamino-2,6-dichloro-1,3,5-s-triazine; tris-(2,2,6,6-tetramethylpiperidyl)-nitrilotriacetate, tetrakis-(2,2,6,6-tetramethyl-4-piperidyl)-1,2,3,4butane-tetra-arbonic acid; and 1,1'(1,2-ethanediyl)-bis-(3,3,5,5-tetramethylpiperazinone).

Part C.2.2 - Other Optional Additives

C.2.2.1 2-(2'-hydroxyphenyl)-benzotriazoles

For example, the 5'-methyl-,3'5'-di-tert-butyl-,5'-tert-butyl-,5'(1,1,3,3-tetramethylbutyl-),-5-chloro-3',5'-di-tert-butyl-,5-chloro-3'-tert-butyl-5'-methyl-3'-sec-butyl-5'-tert-butyl-,4'-octoxy,3',5'-ditert-amyl-3',5'-bis-(alpha, alpha-dimethylbenzyl)-derivatives.

C.2.2.2 Hydroxy-Benzophenones

For example, the 4-hydroxy-4-methoxy-,4-octoxy,4-decyloxy-,4-dodecyloxy-,4-benzyloxy,4,2',- 4'-trihydroxy-and 2'-hydroxy-4,4'-dimethoxy derivative.

C.2.2.3 Esters of Substituted and Unsubstituted Benzoic Acids

For example, phenyl salicylate; 4-tertbutylphenyl-salicylate; octylphenyl salicylate; dibenzoylresorcinol; bis-(4-tert-butylbenzoyl)-resorcinol; benzoylresorcinol; 2,4-di-tert-butyl-phenyl-3,5-di-tert-butyl-4-hydroxybenzoate; and hexadecyl-3,5-di-tert-butyl-4-hydroxybenzoate.

C.2.2.4 Acrylates

For example, alpha-cyano-.beta.,.beta.-diphenylacrylic acid-ethyl ester or isoctyl ester; alpha-carbomethoxy-cinnamic acid methyl ester; alpha-cyano-.beta.-

methyl-p-methoxy-cinnamic acid methyl ester or butyl ester; alpha-carbomethoxy-p-methoxy-cinnamic acid methyl ester; and N-(beta-carbomethoxy-beta-cyano-vinyl)-2-methyl-indoline.

C.2.2.5 Nickel Compounds

For example, nickel complexes of 2,2'-thio-bis(4-(1,1,1,3-tetramethylbutyl)phenol), such as the 1:1 or 1:2 complex, optionally with additional ligands such as n-butylamine, triethanolamine or N-cyclohexyl-diethanolamine; nickel dibutyldithiocarbamate; nickel salts of 4-hydroxy-3,5-di-tert-butylbenzylphosphonic acid monoalkyl esters, such as of the methyl, ethyl, or butyl ester; nickel complexes of ketoximes such as of 2-hydroxy-4-methyl-phenyl undecyl ketoxime; and nickel complexes of 1-phenyl-4-lauroyl-5-hydroxy-pyrazole, optionally with additional ligands.

C.2.2.6 Oxalic Acid Diamides

For example, 4,4'-di-octyloxy-oxanilide; 2,2'-di-octyloxy-5',5'-di-tert-butyl-oxanilide; 2,2'-di-dodecyloxy-5',5'-di-tert-butyl-oxanilide; 2-ethoxy-2'-ethyl-oxanilide; N,N'-bis(3-dimethylaminopropyl)-oxalamide; 2-ethoxy-5-tert-butyl-2'-ethyloxanilide and its mixture with 2-ethoxy-2'-ethyl-5,4-di-tert-butyl-oxanilide; and mixtures of ortho-and para-methoxy as well as of o- and p-ethoxy-disubstituted oxanilides.

C.2.2.7 Hydroxyphenyl-s-triazines

For example, 2,6-bis-(2,4-dimethylphenyl)-4-(2-hydroxy-4-octyloxyphenyl)-s-triazine; 2,6-bis(2,4-dimethylphenyl)-4-(2,4-dihydroxyphenyl)-s-triazine; 5,2,4-bis(2,4-dihydroxyphenyl)-6-(4-chlorophenyl)-s-triazine; 2,4-bis(2-hydroxy-4-(2-hydroxyethoxy)phenyl)-6-(4-chlorophenyl)-s-triazine; 2,4-bis(2-hydroxy-4-(2-hydroxyethoxy)phenyl)-6-phenyl-s-triazine; 2,4-bis(2-hydroxy-4-(2-hydroxyethoxy)phenyl)-6-(2,4-dimethylphenyl)-s-triazine; 2,4-bis(2-hydroxy-4-(2-hydroxyethoxy)phenyl)-6-(4-bromo-phenyl)-s-triazine; 2,4-bis(2-hydroxy-4-(2-acetoxyethoxy)phenyl)-6-(4-chlorophenyl)-s-triazine; and 2,4-bis(2,4-dihydroxyphenyl)-6-(2,4-dimethylphenyl)-1-s-triazine.

C.2.2.8 Metal Deactivators

For example, N,N'-diphenyloxalic acid diamide; N-salicylal-N'-salicyloylhydrazine; N,N'-bis-salicyloylhydrazine; N,N'-bis-(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)-2-hydrazine; salicyloylarnino-1,2,4-triazole; and bis-benzyliden-oxalic acid dihydrazide.

C.2.2.9 Peroxide Scavengers

For example, esters of betathiodipropionic acid, for example the lauryl, stearyl, myristyl or tridecyl esters; mercaptobenzimidazole or the zinc salt of 2-mercaptobenzimidazole; zinc-dibutyldithiocarbamate; dioctadecyldisulfide; and pentaerythritotetrakis-(beta-dodecylmercapto)-propionate.

C.2.2.10 Polyamide Stabilizers

For example, copper salts in combination with iodides and/or phosphorus compounds and salts of divalent manganese.

C.2.2.11 Nucleating Agents

For example, 4-tert-butylbenzoic acid; adipic acid; diphenylacetic acid; sodium salt of methylene bis-2,4-dibutylphenyl; cyclic phosphate esters; sorbitol tris-benzaldehyde acetal; and sodium salt of bis(2,4-di-t-butylphenyl) phosphate or Na salt of ethylidene bis(2,4-di-t-butyl phenyl)phosphate.

C.2.2.12 Fillers and Reinforcing Agents

For example, calcium carbonate; silicates; glass fibers; asbestos; talc; kaolin; mica; barium sulfate; metal oxides and hydroxides; carbon black and graphite.

C.2.2.13 Miscellaneous Additives

For example, plasticizers; epoxidized vegetable oils, such as epoxidized soybean oils; lubricants; emulsifiers; polymer process additives (e.g. fluoroelastomers); pigments; optical brighteners; flameproofing agents; anti-static agents; blowing agents and thiosynergists, such as dilaurythiodipropionate or distearylthiodipropionate.

The term "phenol free" has been used herein to refer to a stabilizer package which is "essentially free" of any "primary" antioxidant such as a phenolic, lactone or hydroxylamine. The phrase "essentially free" is meant to convey a plain meaning, namely that none of the phenolic (or lactone or hydroxylamine) is deliberately added to the polyolefin in order to achieve the melt stabilization of this invention. The "excluded" stabilizers (i.e. the stabilizers which are not deliberately added to the polyolefin according to this invention) are described in Part D below.

PART D - Excluded Stabilizers

The process of this invention utilizes a stabilizer package which is essentially free of phenolic antioxidants, hydroxyl amines (and amine oxides) and lactones.

Part D.1 - Phenolic Antioxidants

D.1.1 Alkylated Mono-Phenols

For example, 2,6-di-tert-butyl-4-methylphenol; 2-tert-butyl-4,6-dimethylphenol; 2,6-di-tert-butyl-4-ethylphenol; 2,6-di-tert-butyl-4-n-butylphenol; 2,6-di-tert-butyl-4-isobutylphenol; 2,6-dicyclopentyl-4-methylphenol; 2-(.alpha.-methylcyclohexyl)-4,6 dimethylphenol; 2,6-di-octadecyl-4-methylphenol; 2,4,6,-tricyclohexylphenol; and 2,6-di-tert-butyl-4-methoxymethylphenol.

D.1.2 Alkylated Hydroquinones

For example, 2,6-di-tert-butyl-4-methoxyphenol; 2,5-di-tert-butylhydroquinone; 2,5-di-tert-amyl-hydroquinone; and 2,6-diphenyl-4-octadecyloxyphenol.

D.1.3 Hydroxylated Thiodiphenyl Ethers

For example, 2,2'-thio-bis-(6-tert-butyl-4-methylphenol); 2,2'-thio-bis-(4-octylphenol); 4,4'-thio-bis-(6-tert-butyl-3-methylphenol); and 4,4'-thio-bis-(6-tert-butyl-2-methylphenol).

D. 1.4 Alkylidene-Bisphenols

For example, 2,2'-methylene-bis-(6-tert-butyl-4-methylphenol); 2,2'-methylene-bis-(6-tert-butyl-4-ethylphenol); 2,2'-methylene-bis-(4-methyl-6-(alpha-methylcyclohexyl)phenol); 2,2'-methylene-bis-(4-methyl-6-cyclohexylphenol); 2,2'-methylene-bis-(6-nonyl-4-methylphenol); 2,2'-methylene-bis-(6-nonyl-4-methylphenol); 2,2'-methylene-bis-(6-(alpha-methylbenzyl)-4-nonylphenol); 2,2'-methylene-bis-(6-(alpha, alpha-dimethylbenzyl)-4-nonyl-phenol); 2,2'-methylene-bis-(4,6-di-tert-butylphenol); 2,2'-ethylidene-bis-(6-tert-butyl-4-isobutylphenol); 4,4'-methylene-bis-(2,6-di-tert-butylphenol); 4,4'-methylene-bis-(6-tert-butyl-2-methylphenol); 1,1-bis-(5-tert-butyl-4-hydroxy-2-methylphenol)butane 2,6-di-(3-tert-butyl-5-methyl-2-hydroxybenzyl)-4-methylphenol; 1,1,3-tris-(5-tert-butyl-4-hydroxy-2-methylphenyl)butane; 1,1-bis-(5-tert-butyl-4-hydroxy-2-methylphenyl)-3-dodecylmercaptobutane; ethyleneglycol-bis-(3,3-bis-(3'-tert-butyl-4'-hydroxyphenyl)-butyrate)-d i-(3-tert-butyl-4-hydroxy-5-methylphenyl)-dicyclopentadiene; di-(2-(3'-tert-butyl-2'-hydroxy-5'-methylbenzyl)-6-tert-butyl-4-methylphenyl)-terephthalate; and other phenolics such as monoacrylate esters of bisphenols such as ethylidene bis-2,4-di-t-butylphenol monoacrylate ester.

D.1.5 Benzyl Compounds

For example, 1,3,5-tris-(3,5-di-tert-butyl-4-hydroxybenzyl)-2,4,6-trimethylbenzene; bis-(3,5-di-tert-butyl-4-hydroxybenzyl)sulfide; isooctyl 3,5-di-tert-butyl-4-hydroxybenzyl-mercaptoacetate; bis-(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl)dithiol-terephthalate; 1,3,5-tris-(3,5-di-tert-butyl-4,10-hydroxybenzyl)isocyanurate; 1,3,5-tris-(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl)isocyanurate; dioctadecyl 3,5-di-tert-butyl-4-hydroxybenzylphosphonate; calcium salt of monoethyl 3,5-di-tert-butyl-4-hydroxybenzylphosphonate; and 1,3,5-tris-(3,5-dicyclohexyl-4-hydroxybenzyl)isocyanurate.

D.1.6 Acylaminophenols

For example, 4-hydroxy-lauric acid anilide; 4-hydroxy-stearic acid anilide; 2,4-bis-octylmercapto-6-(3,5-tert-butyl-4-hydroxyanilino)-s-triazine; and octyl-N-(3,5-di-tert-butyl-4-hydroxyphenyl)-carbamate.

D.1.7 Esters of beta-(5-tert-butyl-4-hydroxy-3-methylphenyl)-propionic acid with Monohydric or Polyhydric Alcohols

For example, methanol; diethyleneglycol; octadecanol; triethyleneglycol; 1,6-hexanediol; pentaerythritol; neopentylglycol; tris-hydroxyethyl isocyanurate; thidiethyleneglycol; and dihydroxyethyl oxalic acid diamide.

D.1.8 Amides of beta-(3,5-di-tert-butyl-4-hydroxyphenyl)-propionic acid

For example, N,N'-di-(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)-hexamethylenediamine; N,N'-di-(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)trimethylenediamine; and N,N'-di(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)-hydrazine.

Part D.2 - Hydroxylamines and Amine Oxides

The process of this invention is essentially free of hydroxylamine stabilizers. For example, N,N-dibenzylhydroxylamine; N,N-diethylhydroxylamine; N,N-dioctylhydroxylamine; N,N-dilaurylhydroxylamine; N,N-ditetradecylhydroxylamine; N,N-dihexadecylhydroxylamine; N,N-dioctadecylhydroxylamine; N-hexadecyl-N-octadecylhydroxylamine; N-heptadecyl-N-octadecylhydroxylamine; and N,N-dialkylhydroxylamine derived from hydrogenated tallow amine. The analogous amine oxides (as disclosed in U.S. Pat. No. 5,844,029, Prachu et al.) are also meant to be included by the definition of hydroxylamine (and thus are not used in the process of this invention).

Part D.3 - Lactones

The process of this invention is essentially free of lactone stabilizers.

The use of lactones such as benzofuranone (and derivatives thereof) or indolinone (and derivatives thereof) as stabilizers is described in U.S. Pat. No. 4,611,016.

Melt Processing Operations

In general, the process of this invention is suitable for processing molten thermoplastic polyolefins. The melt processing operations are conducted at temperatures from above the melting point of the thermoplastic polyolefin to as high as 400°C.

The present process is particularly suitable for extrusion operations, injection molding operations and rotomolding operations.

The extrusion of polyethylene film is particularly preferred. Examples of polyethylene film extrusion process include the blown film process and cast film process which are briefly described below.

In a blown film process, the polyethylene is melted in a screw extruder (preferably at a temperature of from 200 to 320°C, especially from 210 to 250°C) and then forced through an annular die to form a tube of molten polyethylene. The tube is inflated with air from the interior of the tube, then cooled and finally flattened by nip rolls. It is also known to co-extrude multi layers of film by this process.

In a cast film process, the polyethylene is also melted in a screw extruder (preferably at temperatures of from 450°F (232°C) to 600°F (316°C) especially from 500°F (260°C) to 550°F (288°C) and then forced through a flat die. The molten polyethylene web is then cooled (typically, through the use of a water bath or, alternatively, temperature controlled casting rolls).

In an injection molding process, the polyethylene is typically melted in a screw extruder and then rammed under very high pressures into a hollow mold.

In a rotomolding process, the polyethylene resin is ground into a fine powder, then charged into a hollow mold. The mold is then placed in a furnace and heated to temperatures of from 250°C to 325°C (especially from 520°F (271°C) to 600°F (316°C) while the mold is rotated. The molten plastic flows through the mold under the gentle (low shear) forces from the rotation.

The cast film process is especially challenging for stabilization systems because it combines high temperatures and high shear rates.

EXAMPLES

Example 1

A series of small scale experiments was completed to investigate the performance of various stabilizers. The experiments were undertaken in a fusion-head mixer (manufactured by C.W. Brabender Instruments, Inc.) equipped with roller mixing blades in a mixing bowl having a 40 cc capacity. The stabilizer formulations (shown in Table 1) were mixed with a thermoplastic polyethylene in the fusion-head mixer for a period of 10 minutes at 160°C.

The thermoplastic polyethylene used in all experiments of example 1 was an ethylene-octene copolymer having a density of about 0.920 g/cc and a melt index, I2 (as determined by ASTM D 1238) of about 1.0 grams per 10 minutes. This copolymer was produced in a solution phase polymerization process using a Zeigler-Natta type catalyst and contained about 8 parts per million by weight of residual titanium.

Two control experiments (C1 and C2) were conducted using a conventional stabilizer package (C1 contained 500 ppm of a phenolic ("AO1") and 500 ppm of a phosphite ("P1") sold under the trademarks IRGANOX® 1076 and IRGAFOS® 168, respectively, by Ciba Specialty Chemicals); while C2 contained 500 ppm of the IRGANOX 1076 phenolic ("AO2") and 500 ppm of tris (nonylphenyl) phosphite ("P2").

Inventive experiment IE1 was completed using a blend of two phosphite stabilizers at a loading level of 500 ppm each (IE1 contained 500 ppm P1 and 500 ppm P2 under the trademarks IRGAFOS 168 by BASF and WESTON 705 by Addivant, respectively).

It should be noted P1 was used as received in the form of a powder and that P2 was used as received in the form of a viscous liquid. A small experiment was conducted in which some of the P1 powder was added to the P2 liquid (in an amount of about 10% P1/90% P2). The P1 powder did not completely dissolve in the P2 liquid. However, the resulting liquid admixture was considered to be potentially suitable for use as a liquid suspension.

The resin was removed from the fusion-head mixer after the ten minute test and pressed into plaques. Color measurements were performed on the plaques in accordance with ASTM standards (yellow index or "YI" was determined according

to ASTM D 1925 and whiteness index or "WI" was determined according to ASTM E313).

Low YI values and high WI values are desirable. Color data are also provided in Tables 1 and 2.

TABLE 1**Color data for various additive formulations**

Formulation	AO1	AO2	P1	P2	Color (YI)	Color (WI)
C1	500		500		-1.8	67
C2		500	500		-0.6	64
IE1			500	500	-3.1	70

TABLE 2**Color stability data for various additive formulations after multiple extrusion pass experiment (225°C)**

Extrusion Pass #	C1	C2	IE1
0	-1.8	-0.6	-3.1
1	3.2	5.2	-1.9
3	8.2	9.8	-0.3
5	11.1	12.6	0.9

TABLE 3**Change in color data (YI) for various additive formulations after exposure to atmospheric fume chamber**

Days Exposed	C1	C2	IE1
0	11.00	1.50	1.53
1	11.00	3.72	1.61
3	12.52	6.43	1.36
4	13.32	7.10	1.10
8	13.78	10.19	0.88
14	15.60	13.27	0.75
21	17.77	15.72	0.93
28	20.35	18.40	0.56

The color data shown in Table 1 clearly indicate that the comparative stabilizer packages generate undesirable color under the conditions of this experiment. The YI and WI of the resin of experiment C1 were -1.8 and 67, respectively, while the color levels produced in C2 were marginally worse.

The longer term color stability of the test plaques was also tested in a "gas fading" test. The gas fading test is based on Test Method 23-1999 of the American Association of Textile Chemists and Colorists. The test is conducted in a test chamber (sold by Instrument Marking Service as model # 8727ES) which is equipped with a bunsen burner. Natural gas at a pressure of about 0.14 pounds per square inch gauge (1 KPa gauge) is burned in the chamber so as to expose the test plaques to combustion gasses. The temperature of the chamber is controlled to 140°F (60°C) by using an exhaust fan which expels hot air and draws fresh air into the combustion zone. Color testing on the plaques is recorded over a period of 28 days. This test is used to simulate the effect of exposing polyethylene films to warehouse storage conditions (where combustion fumes from propane powered fork lifts are known to cause color formation in plastic films). "Gas fading" data are reported in Table 3.

Example 2

The desirable "color" performance illustrated in Example 1 is of little practical value unless the stabilizer package also provides "melt flow stability". As previously noted, a useful stabilizer package must provide some protection against chain scission reactions in polypropylene (leading to an increase in melt index) and crosslinking reactions in polyethylene. The problems caused by crosslinking of polyethylene are manifested in changes in the physical properties of the finished polyethylene good. For example, a crosslinking reaction in polyethylene used to prepare film may cause a loss of elongation, impact strength and machine direction (MD) tear strength.

The experiments of this example were performed on a twin screw extruder. For the purpose of this evaluation the temperature profile was set to obtain a melt temperatures 225°C. Melt index (I_{21}) was measured after passes 0, 1, and 3 in accordance with ASTM standard D1238 A at 190°C using a 21.6 kg weight. A summary of melt flow stability for each additive package is provided in Table 4 where the smallest deviation from pass 0 is desirable. I_{21} data are reported in units of grams per 10 minutes.

TABLE 4

Melt index (I_{21}), g/10 minutes, for various additive formulations after multiple extrusion pass experiment (225°C)

Extrusion Pass #	C1	C2	IE1
0	24.9	25.2	24.8
1	23.3	23.8	23.0
3	20.8	21.1	19.1

For clarity, the I_{21} value of comparative composition C1 decreased from 24.5 to 20.8 g/10 minutes after three passes.

INDUSTRIAL APPLICABILITY

A process for the stabilization of polyolefins (especially polyethylene and most especially linear low density polyethylene) during melt processing. The process employs two selected phosphite stabilizers and helps to reduce the level of color bodies that are formed during melt processing. The process is particularly useful for the extrusion of films and the resulting films may be used for a wide variety of packaging applications.

CLAIMS

1. A process for stabilizing a thermoplastic polyolefin during melt processing conditions said process comprising the step of incorporating into said thermoplastic polyolefin a stabilizer package comprising:
 - (i) a first phosphite:tris(2-4-di-tert-butylphenyl)phosphite; and
 - (ii) a second phosphite composition consisting essentially of phosphorous acid, mixed 2,4-bis(1,1-dimethylpropyl)phenyl and 4-(1,1-dimethylpropyl) phenyl triesters,and subjecting said thermoplastic polyolefin to sufficient temperature to melt said polyolefin;
with the proviso that said stabilizer package is essentially free of any additive selected from the group consisting of hindered phenolic antioxidants, lactone stabilizers and hydroxylamine stabilizers.
2. The process according to claim 1 wherein said stabilizer formulation contains an acid neutralizer.
3. The process according to claim 1 wherein said stabilizer formulation contains a hindered amine light stabilizer.
4. The process according to claim 1 wherein said thermoplastic polyolefin is a linear polyethylene which contains from 0.5 to 10 ppm of at least one transition metal selected from the group consisting of titanium, vanadium, zirconium and chromium.
5. The process according to claim 4 wherein said linear polyethylene is a copolymer of ethylene and at least one olefin selected from the group consisting of butene, pentene, hexene and octene.
6. The process according to claim 5 wherein said linear polyethylene has a density of from 0.880 to 0.960 g/cc and a melt index, I₂, as determined by ASTM D1238 of from 0.3 to 150 g/10 minutes.
7. The process according to claim 6 wherein said melt processing conditions comprise a film extrusion at a temperature of from 200°C to 320°C.

INTERNATIONAL SEARCH REPORT

International application No
PCT/IB2016/056758

A. CLASSIFICATION OF SUBJECT MATTER
INV. C08K5/51 C08L23/04
ADD.
According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED
Minimum documentation searched (classification system followed by classification symbols)
C08K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)
EPO-Internal, WPI Data, CHEM ABS Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 2005/261403 A1 (TIKUISIS TONY [CA] ET AL) 24 November 2005 (2005-11-24) table 1	1-7
A	----- US 2015/027516 A1 (RUMMENS FRANCOIS [BE]) 29 January 2015 (2015-01-29) example 3.1 paragraph [0535]	1-7
A	----- PETER MAPLESTON: "Anti-aging solutions: new antioxidants and UV stabilizers", COMPOUNDING WORLD (SEPTEMBER 2014), September 2014 (2014-09), pages 1-88, XP055334517, ISSN: 2053-7174 page 49 - page 58 ----- -/--	1-7

Further documents are listed in the continuation of Box C.

See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"E" earlier application or patent but published on or after the international filing date	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"O" document referring to an oral disclosure, use, exhibition or other means	"&" document member of the same patent family
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search 12 January 2017	Date of mailing of the international search report 30/01/2017
--	--

Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer Russell, Graham
--	---

INTERNATIONAL SEARCH REPORT

International application No
PCT/IB2016/056758

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>EFSA PANEL: "Scientific Opinion on the safety evaluation of the substance, phosphorous acid, mixed 2,4-bis(1,1-dimethylpropyl)phenyl and 4-(1,1-dimethylpropyl)phenyl triesters, CAS No. 939402-02-5, for use in food contact materials", THE EFSA JOURNAL, vol. 9, no. 7, 2305, July 2011 (2011-07), pages 1-14, XP055334337, Parma, IT ISSN: 1831-4732, DOI: 10.2903/j.efsa.2011.2305 page 6, paragraph 4. - page 7 -----</p>	1-7

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/IB2016/056758

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2005261403 A1	24-11-2005	CA 2464551 A1	18-11-2005
		US 2005261403 A1	24-11-2005
		WO 2005111139 A1	24-11-2005

US 2015027516 A1	29-01-2015	CN 104272467 A	07-01-2015
		EP 2826074 A1	21-01-2015
		US 2015027516 A1	29-01-2015
		WO 2013135349 A1	19-09-2013
