



(51) International Patent Classification:

*C08L 23/08* (2006.01)      *C08K 5/14* (2006.01)  
*C08L 31/04* (2006.01)      *C08J 3/24* (2006.01)

(21) International Application Number:

PCT/CN2015/074871

(22) International Filing Date:

23 March 2015 (23.03.2015)

(25) Filing Language:

English

(26) Publication Language:

English

(71) Applicant: **ARKEMA (CHANGSHU) FLUORO-CHEMICAL CO., LTD.** [CN/CN]; No. 18 Hai Ning Road, Fluorochemical Industrial Park of Changshu Economic Development Zone, Changshu, Jiangsu 215522 (CN).

(72) Inventor: **LU, Chao**; No. 18 Hai Ning Road, Fluorochemical Industrial Park of Changshu Economic Development Zone, Changshu, Jiangsu 215522 (CN).

(74) Agent: **LIU, SHEN & ASSOCIATES**; 10th Floor, Building 1, 10 Caihefang Road, Haidian District, Beijing 100080 (CN).

(81) Designated States (unless otherwise indicated, for every

kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every

kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))



(54) Title: CURABLE COMPOSITION COMPRISING AN ETHYLENE POLYMER, A MONOPEROXYCARBONATE AND A t-ALKYL HYDROPEROXIDE

(57) Abstract: The present invention pertains to a curable composition comprising (a) at least one ethylene polymer, (b) at least one monoperoxycarbonate, and (c) from 0.05 to less than 0.4 part by weight of at least one t-alkyl hydroperoxide for 100 parts by weight of constituent (b). It is also directed to a method for preventing scorching of a curable composition comprising an ethylene polymer by adding a specific amount of t-alkyl hydroperoxide thereto.

## **CURABLE COMPOSITION COMPRISING AN ETHYLENE POLYMER, A MONOPEROXYCARBONATE AND A t-ALKYL HYDROPEROXIDE**

### TECHNICAL FIELD

5 The present invention pertains to a curable composition comprising an ethylene polymer, such as an ethylene / vinyl acetate copolymer. It is also directed to a method for preventing scorching of a curable composition comprising such an ethylene polymer.

### BACKGROUND

10 Ethylene / vinyl acetate (EVA) is a copolymer widely used, *inter alia*, in solar panels, as an encapsulating material to protect solar cells (and especially the semiconductors contained therein) from outdoor environmental elements, especially moisture and UV radiation, and to provide electrical insulation. EVA indeed provides a good transparency and adhesion to the substrates of the photovoltaic (PV) module, together with a high  
15 resistivity and good moisture-barrier effect. These properties may alternatively be used in the manufacture of laminated glass.

It is common practice to crosslink these EVA copolymers in order to improve their thermal stability, especially their creep strength, their adhesion to the substrates and their  
20 weathering degradation resistance. For this purpose, various crosslinking agents have been used to date in the EVA formulation, which are typically peroxides such as dicumyl peroxide (DCP), peroxyesters, peroxyketals, peroxycarbonates and mixtures thereof. An example of monoperoxy carbonate used for this purpose is OO-t-butyl-O-2-ethylhexyl-monoperoxy carbonate (TBEC). This peroxide has proven to require a lower operating  
25 temperature than DCP, without providing the resulting product with a yellowish colour. It is thus used in the manufacture of photovoltaic modules (see for instance K. Thaworn et al., *Open Journal of Polymer Chemistry*, 2012, 2, 77-85). The Applicant has further shown that the addition of OO-t-amyl-O-2-ethylhexyl-monoperoxy carbonate (TAEC) to TBEC shortened the reaction time and improved the crosslinking density of EVA, which  
30 resulted in an increased tensile strength and a high modulus of the products made from

the crosslinked EVA (WO 2010/007315).

During the laminating process of the PV module, the EVA composition is first deposited onto the frontsheet, then covered by the solar cells and deposited again thereon, before  
5 applying the backsheet, so as to obtain a PV module which is then heated at a certain high temperature for some time and pressed into place, whereby the EVA composition is cured.

It has been found that the EVA composition was susceptible to premature crosslinking in the barrel or die head of the extruder in which it is processed, prior to the formation of the  
10 above laminate. This phenomenon, which is called "scorching", results in irregularities in the EVA sheet thus formed, which in turn impairs the appearance and properties of the PV module. In some cases, pressure may also build up in the extruder, which requires discontinuing the extrusion process. This has especially been observed in the case of  
15 EVA having a relatively low melt-flow index and/or a relatively narrow molecular weight distribution (*source* : US-4,015,058). However, on the other hand, in order to achieve commercially feasible process speeds, it is necessary that once the EVA sheets have been shaped and then heated above the thermal decomposition temperature of the peroxides, crosslinking proceeds as rapidly as possible in order to increase the economics of the process and also minimize possible side reactions.

20

Various solutions have been proposed to date to prevent scorching of EVA compositions. For instance, it has been suggested to add polymerization inhibitors to the EVA composition. However, unwanted yellowing has been noted. Alternatively, it has been proposed in US-4,015,058 to add at least 1 wt. % of cumene hydroperoxide and/or  
25 tertiary butyl hydroperoxide to dicumyl peroxide (DCP). However, the crosslinking rate obtained with this system is not high enough for industrial applications, in particular in the manufacture of PV modules, due to the presence of DCP. Because of the aromatic structure of DCP, the yellowing problems also still remain.

30 Another solution has been provided in JP2011-140588, which is said to be appropriate for

the manufacture of PV modules. It consists in adding from 4 to 50 parts by weight of a hydroperoxide, such as t-butyl hydroperoxide, to 100 parts by weight of an organic peroxide selected from a monoperoxy carbonate, a dialkyl peroxide, a peroxyketal and a peroxyester. Although this solution allows overcoming the drawbacks associated with the use of DCP, it has been found in JP2011-140588 that the above amounts of hydroperoxide negatively affected EVA crosslinking density. In this respect, it was suggested in this document to increase the total amount of monoperoxy carbonate and hydroperoxide while keeping the ratio of hydroperoxide to monoperoxy carbonate constant, i.e. around 20% (see Table 1).

10

#### SUMMARY

Surprisingly, the present inventors have found that the crosslinking density of EVA can be improved by lowering the weight ratio of hydroperoxide to monoperoxy carbonate to less than 0.4%. Moreover, they found a marked increase in the scorch preventing effect of the hydroperoxide at these low weight ratios, contrary to what was expected in JP2011-140588, without impairing the rate of the crosslinking reaction. Further, it was observed that the film homogeneity was satisfactory with substantially no bubbles. In this respect, it should be noted that bubbles formed by the evaporation of water entrapped within the film at extrusion temperatures above 100°C are responsible for surface defects which negatively affect the resistivity of the film. This is particularly damaging in the case where the film is to be used as an encapsulating material in PV modules.

15

20

25

The compositions comprising an ethylene polymer such as EVA and the above peroxides may thus be processed in extruding devices at fast throughput rates without experiencing scorching.

30

It should be noted that monoperoxy carbonates are also useful for crosslinking other ethylene polymers such as polydiene elastomers, including ethylene-propylene-diene (EPDM) elastomers and also polyethylene, including low density and high-density polyethylene, which are used, *inter alia*, in the manufacture of wire and cable insulation,

pipes and hoses (including pipes for automobile radiators, drinkable water and under-floor heating, for instance), roller coverings, rotational moldings and foamed articles. The composition of this invention is thus also useful in these applications, e.g. to prevent scorching while extruding the composition as an insulation sheath onto an electrical conductor.

More specifically, this invention is directed to a curable composition comprising:

- (a) at least one ethylene polymer,
- (b) at least one monoperoxycarbonate,
- 10 (c) from 0.05 to less than 0.4 part by weight of at least one t-alkyl hydroperoxide for 100 parts by weight of constituent (b).

Some further features of the present invention are listed below :

- advantageously, the ethylene copolymer is an ethylene / vinyl acetate copolymer.
- 15 - preferably, the monoperoxycarbonate is selected from the group consisting of OO-t-alkyl-O-alkyl monoperoxycarbonates such as OO-t-butyl-O-2-ethylhexyl-monoperoxycarbonate (TBEC), OO-t-butyl-O-2-isopropyl-monoperoxycarbonate (TBIC), OO-t-amyl-O-2-ethylhexyl-monoperoxycarbonate (TAEC), OO-t-amyl-O-2-isopropyl-monoperoxycarbonate (TAIC) and mixtures thereof, and more preferably TAEC and/or
- 20 TBEC.
- preferably, the composition according to the invention comprises from 0.1 to 0.2 part by weight of at least one t-alkyl hydroperoxide for 100 parts by weight of constituent (b).

It also pertains to the use of a t-alkyl hydroperoxide to prevent scorching of a curable composition comprising (a) at least one ethylene polymer, and (b) at least one monoperoxycarbonate, wherein the t-alkyl hydroperoxide represents from 0.05 to less than 0.4 part by weight for 100 parts by weight of constituent (b).

This invention is further directed to a method for preventing scorching of a curable composition comprising (a) at least one ethylene polymer, and (b) at least one

monoperoxy carbonate, comprising the step of adding at least one t-alkyl hydroperoxide into the composition, in an amount of from 0.05 to less than 0.4 part by weight for 100 parts by weight of constituent (b).

- 5 It is also directed to a method for manufacturing a solar cell encapsulating material or sealant, comprising the step of extruding the above composition at a temperature between 80 and 150°C.

#### DETAILED DESCRIPTION

- 10 The ethylene polymer used as constituent (a) in this invention may be an ethylene homopolymer or preferably an ethylene copolymer. Examples of ethylene copolymers are those made from both ethylene monomers and at least one other monomer selected from hydrocarbons having at least one unsaturation such as propylene, butadiene, isoprene and styrene; acryl monomers such as acrylic acid, methacrylic acid, alkyl methacrylate and  
15 alkyl acrylate, wherein the alkyl group may be selected from methyl, ethyl, propyl or butyl, for instance; and vinyl monomers such as vinyl acetate. Usually, these copolymers comprise at 30 weight percent of ethylene and at most 70 weight percent of the other monomer(s).
- 20 According to a preferred embodiment, the ethylene copolymer is an ethylene / vinyl acetate (EVA) copolymer. The EVA copolymer may comprise from 15 to 60 wt.%, and preferably from 25 to 45 wt. %, of VA monomer. Examples of such EVA copolymers are available under the trade name "Evatane<sup>®</sup> 18-150" and "Evatane<sup>®</sup> 40-55" from ARKEMA.
- 25 Other ethylene polymers that may be used in this invention have been provided, e.g., in EP 2 242 647. They comprise a functionalized polyolefin, such as a homopolymer of ethylene or a copolymer of ethylene with an alkyl(meth)acrylate or vinyl acetate, which may be functionalized either by grafting or by copolymerization with maleic anhydride or glycidyl methacrylate. This functionalized polyolefin may optionally be mixed with a  
30 copolymer of ethylene / carboxylic acid vinyl ester such as EVA.

The ethylene polymer is mixed with a specific peroxide used as constituent (b), which is at least one monoperoxycarbonate. This peroxide compound may be selected from the group consisting of OO-t-alkyl-O-alkyl monoperoxycarbonates such as OO-t-butyl-O-2-ethylhexyl-monoperoxycarbonate (TBEC), OO-t-butyl-O-2-isopropyl-monoperoxycarbonate (TBIC), OO-t-amyl-O-2-ethylhexyl-monoperoxycarbonate (TAEC), OO-t-amyl-O-2-isopropyl-monoperoxycarbonate (TAIC) and mixtures thereof. Preferred monoperoxycarbonates are TAEC and TBEC. According to an embodiment of this invention, a mixture of TBEC and TAEC is used as constituent (b), wherein TAEC represents from 0.001 to 99.9 wt %, relative to the total weight of the mixture. These monoperoxycarbonates are available under the trade name Luperox<sup>®</sup> or Lupersol<sup>®</sup> supplied by ARKEMA.

The amount of constituent (b) in the composition of this invention may range from 0.1 to 5 parts by weight, and preferably from 0.3 to 3 parts by weight, for 100 parts by weight of constituent (a).

The third component of the composition according to this invention is a t-alkyl hydroperoxide, which may be selected from the group consisting of t-butyl hydroperoxide (TBHP), t-amyl hydroperoxide (TAHP), t-hexyl hydroperoxide (THHP), 1,1,3,3-tetramethylbutyl hydroperoxide (TOHP), paramenthane hydroperoxide (PMHP), 2,5-dimethyl-2,5-di-hydroperoxide (2,5-2,5) and their mixtures, for instance. Preferably, the t-alkyl hydroperoxide is TAHP.

The amount of constituent (c) in the composition of this invention ranges from 0.05 to less than 0.4 part by weight, and preferably from 0.1 to 0.2 part by weight, for 100 parts by weight of constituent (b).

The composition of this invention may further include additives such as coupling agents, UV stabilizers, UV absorbers, fillers, plasticizers, flame retardants, anti-oxidants, dyes

and their mixtures. Examples of coupling agents are monoalkyl titanates, (vinyl)trichlorosilanes and (vinyl)trialkoxysilanes. They may represent from 0.01 to 5 wt. % relative to the weight of ethylene polymer. UV stabilizers may be chosen among hindered amine light stabilizers (HALS), whereas UV absorbers may be selected, for instance, from benzophenones, triazines and benzotriazoles. These compounds may represent from 0.01 to 3 wt. % relative to the weight of ethylene polymer. Inorganic fillers such as silicon dioxide, alumina, talc, calcium carbonate may be added to increase mechanical strength, although nanometric clays are preferred because of the transparency they provide. Examples of plasticizers are paraffinic or aromatic mineral oils, phthalates, azelates, adipates and the like. Antioxidants may be phenolic, phosphate or sulfur antioxidants. Alternatively, quinolines such as 1,2-dihydro-2,2,4-trimethylquinoline, may be used as an antioxidant.

According to a preferred embodiment, the composition of this invention does not include any aromatic peroxide such as dicumyl peroxide. Still preferably, this composition consists of constituents (a), (b) and (c) above and optionally at least one of the following additives: a coupling agent, a UV stabilizer, a UV absorber, a filler, a plasticizer, a flame retardant, an anti-oxidant, a dye and mixtures thereof.

The composition according to this invention may be prepared by mixing the above constituents (a) to (c) in conventional devices such as continuous mixers and compound extruders, below the degradation temperature of the peroxides.

It may then be used for the manufacture of various articles and more specifically in a method for manufacturing a solar cell encapsulating material or a solar panel sealant, comprising the step of extruding said composition at a temperature between 80 and 150°C, preferably from 90 to 120°C. The extrusion step may be performed in such a way as to obtain a sheet having a thickness of from 50 to 2000 µm, preferably from 100 to 1000 µm, for instance. It is thus possible to use a T-die extruder or alternatively a twin-screw extruder coupled with a two-roll mill. Preferably, a photovoltaic module will be



built, comprising successively: a front sheet (such as a glass sheet or PMMA sheet), an encapsulating material sheet, solar cells (made from crystalline silicon or organic photovoltaics), another encapsulating material sheet, and a backsheet (such as a multilayer PVDF/PET film or a glass sheet or a PMMA sheet). This laminate may then  
5 be pressed by conventional techniques while heating and/or under vacuum, for instance at a temperature of from 130 to 180°C, more preferably from 140 to 155°C under vacuum, for a curing time that may range from 1 to 20 minutes, for instance from 3 to 10 minutes. The encapsulating material sheet may be crosslinked during this pressing step of afterwards. Preferably, the process includes a single step of pressing and curing.

10

### EXAMPLES

This invention will be better understood in light of the following examples which are given for illustrative purposes only and do not intend to limit the scope of the invention, which is defined by the attached claims.

15

#### **Example 1 : Scorch protection effect**

Compositions according to this invention were prepared by mixing an ethylene / vinyl acetate (EVA) copolymer (Cosmothene<sup>®</sup> EVA KA-40 containing 28% VA, supplied by SUMITOMO) with OO-t-amyl-O-2-ethylhexyl-monoperoxy carbonate (Luperox<sup>®</sup> TAEC  
20 available from Arkema) and t-amyl hydroperoxide (Luperox<sup>®</sup> TAHP available from Arkema) in a Haake internal mixer at 35°C for 12 minutes, using a stirring rate of 50 rpm/min. The polymeric mixture was then passed through an open mill set at 60°C to produce sheets of about 2 mm thickness.

25 Samples of about 2 to 3 g of the above compositions were deposited in plate on a moving die rheometer (MDR) supplied by GOTECH, which is able to measure the cure properties of the samples and includes a DFT software for analyzing the results. Each of the samples is placed in a temperature-controlled cavity between two dies, the lower of which oscillates to apply a cyclic stress or strain to the sample while the upper die is connected  
30 to a torque sensor to measure the torque response of the sample at the deformation. The

stiffness is recorded continuously as a function of time. The stiffness of the sample increases as vulcanization proceeds.

This apparatus is able to provide, *inter alia*, calculated values of ML (minimum torque), MH (maximum torque), tc10 (time to 10% state of cure) and tc90 (time to 90% state of cure) as defined by International Standards (ASTM D5289 and ISO 6502).

The MDR was operated at 105°C with an oscillation amplitude (deformation degree) of 0.5° applied to the sample for 30 min. The scorch time was defined as the time necessary to reach 10% of the total cure, i.e. tc10.

This experiment was conducted on the following samples, wherein the amounts of TAEC and TAHP are indicated as parts per hundred parts of EVA resin (phr):

	TAHP / TAEC (wt/wt)	MH-ML (dN-m)	tc10 (m:s)	tc90 (m:s)
2phr TAEC + 0.0004phr TAHP	0.02%	1.19	08:02	27:14:00
2phr TAEC + 0.002phr TAHP	0.09%	1.17	08:16	27:26:00
2phr TAEC + 0.0025phr TAHP	0.12%	1.11	08:36	27:22:00
2phr TAEC + 0.003phr TAHP	0.16%	1.05	08:46	27:39:00
2phr TAEC + 0.004phr TAHP	0.20%	0.78	09:14	28:18:00
2phr TAEC + 0.015phr TAHP	0.75%	0.24	05:27	28:04:00
2phr TAEC + 0.025phr TAHP	1.25%	0.11	05:27	27:15:00

From this table, it can be seen that TAHP acts as a scorch-protection agent since scorch time (tc10) increases with the amount of TAHP. However, there is a dramatic decrease in scorch time, and thus a lower scorch protection effect of TAHP, when the latter reaches 0.75 wt% relative to TAEC. At lower values of TAHP, scorch is effectively prevented while maintaining a high crosslinking rate (tc90) and a good crosslinking density (MH-ML).

## CLAIMS

1. A curable composition comprising:
  - (a) at least one ethylene polymer,
  - 5 (b) at least one monoperoxycarbonate,
  - (c) from 0.05 to less than 0.4 part by weight of at least one t-alkyl hydroperoxide for 100 parts by weight of constituent (b).
  
2. The composition of claim 1, wherein the ethylene copolymer is an ethylene / vinyl  
10 acetate copolymer.
  
3. The composition according to Claim 1 or 2, wherein the monoperoxycarbonate is selected from the group consisting of OO-t-alkyl-O-alkyl monoperoxycarbonates such as  
15 OO-t-butyl-O-2-ethylhexyl-monoperoxycarbonate (TBEC), OO-t-butyl-O-2-isopropyl-monoperoxycarbonate (TBIC), OO-t-amyl-O-2-ethylhexyl-monoperoxycarbonate (TAEC), OO-t-amyl-O-2-isopropyl-monoperoxycarbonate (TAIC) and mixtures thereof, preferably TAEC and/or TBEC.
  
4. The composition according to any of Claims 1 to 3, wherein the t-alkyl hydroperoxide  
20 is selected from the group consisting of t-butyl hydroperoxide (TBHP), t-amyl hydroperoxide (TAHP), t-hexyl hydroperoxide (THHP), 1,1,3,3-tetramethylbutyl hydroperoxide (TOHP), paramenthane hydroperoxide (PMHP), 2,5-dimethyl-2,5-dihydroperoxide (2,5-2,5) and their mixtures, preferably TAHP.
  
- 25 5. The composition according to any of Claims 1 to 4, which comprises from 0.1 to 0.2 part by weight of at least one t-alkyl hydroperoxide for 100 parts by weight of constituent (b).
  
6. Use of a t-alkyl hydroperoxide to prevent scorching of a curable composition  
30 comprising (a) at least one ethylene polymer, and (b) at least one monoperoxycarbonate,

wherein the t-alkyl hydroperoxide represents from 0.05 to less than 0.4 part by weight for 100 parts by weight of constituent (b).

7. A method for preventing scorching of a curable composition comprising (a) at least  
5 one ethylene polymer, and (b) at least one monoperoxy carbonate, comprising the step of  
adding at least one t-alkyl hydroperoxide into the composition, in an amount of from 0.05  
to less than 0.4 part by weight for 100 parts by weight of constituent (b).

8. A method for manufacturing a solar cell encapsulating material or sealant, comprising  
10 the step of extruding a composition according to any of Claims 1 to 5 at a temperature  
between 80 and 150°C.

## INTERNATIONAL SEARCH REPORT

International application No.

PCT/CN2015/074871

**A. CLASSIFICATION OF SUBJECT MATTER**

C08L 23/08(2006.01)i; C08L 31/04(2006.01)i; C08K 5/14(2006.01)i; C08J 3/24(2006.01)i

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)

C08L, C08J, C08K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

VEN, CPRS, CNKI, ethylene, vinyl acetate, mono, carbonate

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	JP 2011140588 A (NOF CORP) 21 July 2011 (2011-07-21) the whole document	1-8
A	KR 20120040359 A (SAMSUNG TOTAL PETROCHEMICALS) 27 April 2012 (2012-04-27) the whole document	1-8
A	WO 2012104298 A1 (UNITED INITIATORS GMBH & CO KG ET AL.) 09 August 2012 (2012-08-09) the whole document	1-8
A	WO 2011132560 A1 (BRIDGESTONE CORP ET AL.) 27 October 2011 (2011-10-27) the whole document	1-8

 Further documents are listed in the continuation of Box C. See patent family annex.

\* Special categories of cited documents:

“A” document defining the general state of the art which is not considered to be of particular relevance

“E” earlier application or patent but published on or after the international filing date

“L” document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

“O” document referring to an oral disclosure, use, exhibition or other means

“P” document published prior to the international filing date but later than the priority date claimed

“T” later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

“X” document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

“Y” document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

“&amp;” document member of the same patent family

Date of the actual completion of the international search

13 October 2015

Date of mailing of the international search report

23 October 2015

Name and mailing address of the ISA/CN

STATE INTELLECTUAL PROPERTY OFFICE OF THE  
P.R.CHINA  
6, Xitucheng Rd., Jimen Bridge, Haidian District, Beijing  
100088, China

Authorized officer

XIAO,Gang

Facsimile No. (86-10)62019451

Telephone No. (86-10)62084458

**INTERNATIONAL SEARCH REPORT**  
**Information on patent family members**

International application No.

**PCT/CN2015/074871**

Patent document cited in search report			Publication date (day/month/year)	Patent family member(s)			Publication date (day/month/year)
JP	2011140588	A	21 July 2011	JP	5407877	B2	05 February 2014
KR	20120040359	A	27 April 2012	KR	101202573	B1	20 November 2012
WO	2012104298	A1	09 August 2012	ES	2534814	T3	28 April 2015
				EP	2670797	A1	11 December 2013
				US	2013309800	A1	21 November 2013
				DE	102011003382	A1	02 August 2012
				EP	2670797	B1	18 March 2015
				JP	2014505148	A	27 February 2014
				TW	201237020	A	16 September 2012
				KR	20130113492	A	15 October 2013
				CN	103298872	A	11 September 2013
WO	2011132560	A1	27 October 2011	JP	5587659	B2	10 September 2014
				JP	2011228509	A	10 November 2011