



(12) Patent specification

(10) SE 542 579 C2

(21) Patent application number:	1751595-8	(51) Int.Cl.:	
(45) Grant of patent:	2020-06-09	B32B 27/08	(2006.01)
(41) Available to the public:	2019-06-22	B29C 65/02	(2006.01)
(22) Filing date:	2017-12-21	B32B 27/12	(2006.01)
(24) Effective date:	2017-12-21	B32B 27/32	(2006.01)
(30) Priority data:	---	B82Y 30/00	(2011.01)
		C08J 5/18	(2006.01)
		D21H 11/18	(2006.01)

- (73) Patentee: Stora Enso OYJ, P.O. Box 309, 00101 Helsinki FI
(72) Inventor: Kaj BACKFOLK, Villmanstrand FI
Isto HEISKANEN, Imatra FI
Esa SAUKKONEN, Lappeenranta FI
Jukka KANKKUNEN, Imatra FI
(74) Agent: Henrik STEINRUD, Stora Enso ABGroup IP Box 9090, 650 09, Karlstad SE
(54) Title: Heat-sealable packaging material
(56) Cited documents: US 2012251818 A1 · WO 2017046754 A1 · WO 2017163167 A1 · US 2011167763 A1 · US 3445324 A · EP 0898466 A1
(57) Abstract:

The present invention is directed to a packaging material free from aluminium in the form of a continuous foil or film, comprising a layer of microfibrillated cellulose (MFC), wherein the layer comprising MFC has been laminated or coated on at least one side with a heat-sealable material. The MFC layer contains at least 60% by weight of microfibrillated cellulose. The present invention is also directed to a method for induction sealing, wherein a packaging material to be heat-sealed by induction is placed against an induction heating surface.

ABSTRACT

The present invention is directed to a packaging material free from aluminium in the form of a continuous foil or film, comprising a layer of microfibrillated cellulose (MFC), wherein the layer comprising MFC has been laminated or
5 coated on at least one side with a heat-sealable material. The MFC layer contains at least 60% by weight of microfibrillated cellulose. The present invention is also directed to a method for induction sealing, wherein a packaging material to be heat-sealed by induction is placed against an
10 induction heating surface.

HEAT-SEALABLE PACKAGING MATERIAL

Technical field

The present invention is directed to a heat-sealable packaging material free
5 from aluminium in the form of a continuous foil or film, comprising a layer of
microfibrillated cellulose (MFC), wherein the layer comprising MFC has been
laminated or coated on at least one side with a heat-sealable material. The
MFC layer contains at least 60% by weight of microfibrillated cellulose. The
present invention is also directed to a method for induction sealing, wherein a
10 packaging material to be heat-sealed by induction is placed against an
induction heating surface.

Background

15

Packages used for sensitive objects such as liquid beverages need to have
sufficient barrier properties. Typically, aluminium is used for these purposes
and generally provides sufficient properties with regard to penetration of gas,
such as oxygen. The aluminium layer is also an aroma barrier and plays an
20 important function in heat sealing.

Heat sealing is used in packaging primarily for producing or closing wraps,
bags, pouches, cartons, tubes, blister packs, thin wall containers, kits and
various components.

25

There are several methods useful for heat sealing, including impulse sealing,
dielectric heat sealing and thermal heat sealing.

Induction is commonly used as a means to heat seal packages. This is traditionally based on the presence of a sufficient amount of conductive material to generate heat and thereby enable heat sealing.

- 5 One issue with the use of aluminium is that it poses an environmental challenge, is a problem in the recycling process and is not compostable. It would therefore be desirable to replace aluminium with renewable materials. However, it is essential to maintain the barrier properties of the packaging material to the extent it is to be used in packages for e.g. liquids and it is also
- 10 important that the packaging material is sufficiently crack-resistant. Many packaging lines and units are equipped with induction sealers. This means also that the packaging materials must contain an aluminium layer or a foil (or similar materials) in order to be induction sealable.
- 15 The use of an aluminum layer provides good barrier properties, but is leading to problems in respect of sustainability value, recycling, and costs.

Embedding substances that enable induction sealability of a polymer film or coating or biofilm is an option, but can also lead to problems in performance,

20 recyclability and costs. Addition of functional chemicals or particles to, for example, wet end or coating process might be an option but this might increase the risks of negatively influencing barrier properties or laminate or barrier manufacturing process.

- 25 Therefore, an aluminium free coating or a film without embedded inductive substances which can still be used in induction sealing without being damaged due to the heat sealing process is needed.

30

Summary of the invention

- It has surprisingly been found that by using a layer of microfibrillated cellulose (MFC) wherein the layer comprising MFC has been laminated or extrusion
- 5 coated on at least one side with a heat-sealable material, it is possible to achieve a packaging material suitable for heat sealing using methods such as, but not limited to, induction sealing, even when the packaging material is free from aluminium in the form of a continuous foil or film.
- 10 The present invention is thus directed to a packaging material that is free from aluminium in the form of a continuous foil or film, comprising a layer of MFC, wherein the layer comprising MFC has been laminated or coated on at least one side with a heat-sealable material. The heat-sealable material may be provided on one or both sides of the MFC layer.
- 15 To facilitate the induction sealing, one side of the packaging material is provided with a coating that does not adhere to or stick to surfaces, specifically metal surfaces such as aluminum surfaces when heated. Thus, that coating prevents the coated surface from adhering to a heated metal
- 20 surface. The coating is selected from starch, a wax, a mineral or pigment coating. The coating that does not adhere to or stick to surfaces is preferably provided in an amount of up to 20 g/m², such as from 0.1 g/m² to 20 g/m², preferably 0.5 g/m² to 15 g/m² or 0.5 g/m² to 5 g/m². Alternatively, the packaging material does not adhere to a heated metal surface.
- 25 The packaging material according to the present invention has a thickness of less than 70 µm, such as less than 45 µm, less than 40 µm, or less than 35 µm.
- 30 The layer of MFC is preferably in the range of from 5 to 50 gsm, such as from 5-30 gsm or from 10-30 gsm. The MFC may be native or modified and may be a mix of native and modified MFC as well as a mix of native MFC and

different types of modified MFC. If the MFC is modified it may be phosphorylated or PCC coated MFC. The MFC may be produced from pulp, such as from dissolving pulp.

- 5 The layer of MFC has an OTR (oxygen transmission rate) value of less than $500 \text{ cm}^3/\text{m}^2\cdot\text{day}$ at $23^\circ\text{C}/50\%\text{RH}$ for a 20-30 gsm MFC layer. Preferably, the OTR value is less than $450 \text{ cm}^3/\text{m}^2\cdot\text{day}$ at $23^\circ\text{C}/50\%\text{RH}$. More preferably, the OTR value is less than $400 \text{ cm}^3/\text{m}^2\cdot\text{day}$ at $23^\circ\text{C}/50\%\text{RH}$, less than $200 \text{ cm}^3/\text{m}^2\cdot\text{day}$ at $23^\circ\text{C}/50\%\text{RH}$ or less than $100 \text{ cm}^3/\text{m}^2\cdot\text{day}$ at $23^\circ\text{C}/50\%\text{RH}$.
- 10 The OTR can be determined using methods known in the art.

- The layer of MFC in combination with the heat-sealable material according to the present invention has an OTR (oxygen transmission rate) value of less than $400 \text{ cm}^3/\text{m}^2\cdot\text{day}$ at $23^\circ\text{C}/50\%\text{RH}$. Preferably, the OTR value is less than
- 15 $300 \text{ cm}^3/\text{m}^2\cdot\text{day}$ at $23^\circ\text{C}/50\%\text{RH}$. More preferably, the OTR value is less than $100 \text{ cm}^3/\text{m}^2\cdot\text{day}$ at $23^\circ\text{C}/50\%\text{RH}$. The OTR can be determined using methods known in the art.

- The packaging material according to the present invention can be subjected
- 20 to printing through a reel to reel or reel to sheet or sheet fed printing process, but can also be subjected to off-line surface treatment with other technologies such as flexogravure, rotogravure, reverse rotogravure, silk screen printing, inkjet printing, offset printing (lithography), spray, curtain, foam or other printing or surface treatment techniques.

25

- The packaging material according to the present invention may be biodegradable and/or compostable. In this context, compostability is defined in accordance with ISO 18606, i.e. constituents in the whole material which are present at concentrations of less than 1% do not need to demonstrate
- 30 biodegradability. However, the sum of such constituents shall not exceed 5%. Biodegradability is defined as follows: the ultimate aerobic biodegradability shall be determined for the whole material or for each organic constituent

which is present in the material at a concentration of more than 1% (by dry mass). Constituents present at levels between 1 to 10% shall be tested individually.

- 5 The packaging material according to the present invention can be subjected to induction sealing, even though the packaging material is free from aluminium in the form of a continuous foil or film. In this method for induction sealing, the packaging material according to the present invention is brought into close proximity or brought into contact with a surface that can be heated
10 by induction, such as a metal surface, such as an aluminium surface, which is arranged in such a way that it can be heated by induction and used to heat and thereby seal a packaging material, under applied pressure, according to the present invention. Thus, according to this method, existing equipment for induction heat sealing can readily be adapted for use in accordance with the
15 present method for induction sealing of a packaging material according to the present invention. The heated surface may be an aluminium substrate or counterpiece.

When carrying out the induction sealing, the packaging material is arranged
20 such that at least one of the two surfaces to be sealed together is provided with a heat-sealable material. The heat from the heated surface is conducted through the packaging material and heats the heat-sealable material so that it softens or melts sufficiently to obtain the desired sealing. If one side of the packaging material is coated with a material that does not stick to surfaces,
25 then the side of the packaging material provided with the material that does not stick to surfaces is brought into close proximity or contact with the surface heated by induction. However, the packaging material according to the present invention may also be heat sealed to a surface which is not a packaging material according to the present invention.

30

The packaging material according to the present invention can be used for any type of final packaging product where induction heat sealability is

desirable. In particular, the packaging product according to the present invention can be used as a closure, lid, liquid packaging product or pouch.

5 Detailed description

The microfibrillated cellulose used according to the present invention can be prepared using methods known in the art.

10 The term “free from aluminium in the form of a continuous foil or film” as used herein in the context of a packaging material, means a packaging material that does not comprise aluminium in the form of a continuous foil or film. In this context, foil or film has a thickness of at least 250 nm and is continuous, i.e. essentially free from pin holes. Thus, the packaging material typically
15 comprises less than 2% by weight of aluminium, such as less than 1% by weight of aluminium or less than 0.5% by weight of aluminium.

The MFC layer may be plasma treated or corona treated prior to adding the heat-sealable material. The heat-sealable material may be provided directly
20 on the MFC layer. Alternatively, one or more layers can be provided between the MFC layer and the heat-sealable material. Such layers provided between the MFC layer and the heat-sealable material may for example provide additional barrier properties and/or improve the adhesion between the MFC layer and the heat-sealable material.

25 The heat-sealable material is a material which can be provided as a layer and which has a melting point and/or a glass transition temperature such that it is suitable for use in heat-sealing. Examples of such heat-sealable materials include thermoplastic polymers such as polypropylene or polyethylene.
30 Further examples are waxes and hot melts. Additional examples include vinylic polymers (PVC and PVDC based), acrylate and styrene acrylate based polymers, acrylate/polyolefin copolymers, styrene copolymers, polyesters, polypropylene dispersions, ethylene copolymers (EAA and EMAA), ethylene

terpolymer (EVA) or styrene acrylic latex or styrene butadiene latex. Thus, the heat-sealable material can be applied as a coating, for example by dispersion coating, extrusion coating or emulsion coating. The heat-sealable material can also be applied by printing.

5

The layer comprising the heat-sealable material may also contain additives such as waxes / slip agents: Polyethylene wax, AKD, Carnauba wax, PTFE, Fatty acid ester; inorganic pigments / filler: silica, talc; antioxidants / UV-stabilizer / optical brighteners and antifoaming agents.

10

In one embodiment of the present invention, the MFC layer is formed in a paper making machine or according to a wet laid production method, by providing a suspension onto a wire and dewatering the web to form an intermediate thin substrate or said film. A suspension comprising

15 microfibrillated cellulose is provided to form said film.

In one embodiment of the present invention, the MFC layer used in accordance with the present invention can be made according to any known processes described in the art such as wet laid methods, coating, printing, extrusion, lamination etc.

20

Microfibrillated cellulose (MFC) shall in the context of the patent application mean a nano scale cellulose particle fiber or fibril with at least one dimension less than 100 nm. MFC comprises partly or totally fibrillated cellulose or lignocellulose fibers. The liberated fibrils have a diameter less than 100 nm, whereas the actual fibril diameter or particle size distribution and/or aspect ratio (length/width) depends on the source and the manufacturing methods.

25

The smallest fibril is called elementary fibril and has a diameter of approximately 2-4 nm (see *e.g. Chinga-Carrasco, G., Cellulose fibres, nanofibrils and microfibrils, The morphological sequence of MFC components from a plant physiology and fibre technology point of view,*

30

Nanoscale research letters 2011, 6:417), while it is common that the aggregated form of the elementary fibrils, also defined as microfibril (Fengel, D., *Ultrastructural behavior of cell wall polysaccharides*, Tappi J., March 1970, Vol 53, No. 3.), is the main product that is obtained when making MFC e.g. by using an extended refining process or pressure-drop disintegration process. Depending on the source and the manufacturing process, the length of the fibrils can vary from around 1 to more than 10 micrometers. A coarse MFC grade might contain a substantial fraction of fibrillated fibers, i.e. protruding fibrils from the tracheid (cellulose fiber), and with a certain amount of fibrils liberated from the tracheid (cellulose fiber).

There are different acronyms for MFC such as cellulose microfibrils, fibrillated cellulose, nanofibrillated cellulose, fibril aggregates, nanoscale cellulose fibrils, cellulose nanofibers, cellulose nanofibrils, cellulose microfibers, cellulose fibrils, microfibrillar cellulose, microfibril aggregates and cellulose microfibril aggregates. MFC can also be characterized by various physical or physical-chemical properties such as large surface area or its ability to form a gel-like material at low solids (1-5 wt%) when dispersed in water. The cellulose fiber is preferably fibrillated to such an extent that the final specific surface area of the formed MFC is from about 1 to about 300 m²/g, such as from 1 to 200 m²/g or more preferably 50-200 m²/g when determined for a freeze-dried material with the BET method.

Various methods exist to make MFC, such as single or multiple pass refining, pre-hydrolysis followed by refining or high shear disintegration or liberation of fibrils. One or several pre-treatment step is usually required in order to make MFC manufacturing both energy efficient and sustainable. The cellulose fibers of the pulp to be supplied may thus be pre-treated enzymatically or chemically, for example to reduce the quantity of hemicellulose or lignin. The cellulose fibers may be chemically modified before fibrillation, wherein the cellulose molecules contain functional groups other (or more) than found in the original cellulose. Such groups include, among others, carboxymethyl

(CM), aldehyde and/or carboxyl groups (cellulose obtained by N-oxyl mediated oxydation, for example "TEMPO"), or quaternary ammonium (cationic cellulose). After being modified or oxidized in one of the above-described methods, it is easier to disintegrate the fibers into MFC or
5 nanofibrillar size fibrils.

The nanofibrillar cellulose may contain some hemicelluloses; the amount is dependent on the plant source. Mechanical disintegration of the pre-treated fibers, e.g. hydrolysed, pre-swelled, or oxidized cellulose raw material is
10 carried out with suitable equipment such as a refiner, grinder, homogenizer, colloidier, friction grinder, ultrasound sonicator, fluidizer such as microfluidizer, macrofluidizer or fluidizer-type homogenizer. Depending on the MFC manufacturing method, the product might also contain fines, or nanocrystalline cellulose or e.g. other chemicals present in wood fibers or in
15 papermaking process. The product might also contain various amounts of micron size fiber particles that have not been efficiently fibrillated.

MFC is produced from wood cellulose fibers, both from hardwood or softwood fibers. It can also be made from microbial sources, agricultural fibers such as wheat straw pulp, bamboo, bagasse, or other non-wood fiber sources. It is
20 preferably made from pulp including pulp from virgin fiber, e.g. mechanical, chemical and/or thermomechanical pulps. It can also be made from broke or recycled paper.

The above described definition of MFC includes, but is not limited to, the new
25 proposed TAPPI standard W13021 on cellulose nanofibril (CMF) defining a cellulose nanofiber material containing multiple elementary fibrils with both crystalline and amorphous regions.

According to another embodiment, the suspension may comprise a mixture of
30 different types of fibers, such as microfibrillated cellulose, and an amount of other types of fiber, such as kraft fibers, fines, reinforcement fibers, synthetic fibers, dissolving pulp, TMP or CTMP, PGW, etc.

The suspension may also comprise other process or functional additives, such as fillers, pigments, wet strength chemicals, dry strength chemicals, retention chemicals, cross-linkers, softeners or plasticizers, adhesion primers, wetting agents, biocides, optical dyes, fluorescent whitening agents, de-foaming chemicals, hydrophobizing chemicals such as AKD, ASA, waxes, resins etc. Additives can also be added using a size press.

There are several methods for preparing a film of MFC, including wire forming and cast forming. In wire forming, a suspension, comprising microfibrillated cellulose, is dewatered on a porous surface to form a fibrous web. A suitable porous surface is e.g. wire in a paper machine. The fibrous web is then dried in a drying section in a paper machine to form the MFC film, wherein the film has a first side and a second side. The papermaking machine that may be used in the process according to the present invention may be any type of machine known to the skilled person used for the production of paper, paperboard, tissue or similar products, alternatively for example a modified or non-conventional papermaking machine.

The furnish is placed onto the wire and then a web is formed, which may be dewatered to form an intermediate thin substrate or film. In cast forming, the suspension, comprising MFC, is for example applied on a supporting medium with a non-porous surface. The non-porous surface is e.g. a plastic or metal belt on which the suspension is evenly spread and the MFC film is formed during drying. The MFC film is then peeled off from the supporting medium in order to form a stand-alone film, wherein the film has a first side and a second side.

Preferably, the MFC layer is laminated or extrusion coated or dispersion coated with a thermoplastic polymer which may be a bio-based and/or biodegradable thermoplastic polymer. The thermoplastic film typically has a melting point of from 60°C to 220°C. In one embodiment of the present

invention, the thermoplastic polymer is selected from thermoplastic cellulose, thermoplastic starch (modified starch), polyethylene (PE), polypropylene (PP), high-density polyethylene (HDPE), low-density polyethylene (LDPE), linear-low density polyethylene (LLDPE), polylactic acid (PLA), polycaprolactone, 5 polyglycolide (PGA), ethylene vinyl acetate (EVA), ethylene vinyl alcohol (EVOH), polyamide (PA), ionomers (e.g. Surlyn) or combinations thereof. The thermoplastic film is typically present at at least 5 g/m², such as at least 15 g/m², such as at least 20 g/m² or at least 30 g/m².

10 In one embodiment of the present invention, the MFC layer is laminated with the thermoplastic polymer. The lamination can be carried out using methods known in the art.

A final packaging product, such as a final liquid packaging board comprising 15 the packaging material according to the present invention may comprise several layers, i.e. be a multilayer structure. The heat-sealable packaging material according to the present invention is useful for example in packages for wrapping objects, bags, pouches, cartons, tubes, blister packs, thin wall containers etc. The packaging material according to the present invention 20 may also be used as a seal or lid for a container, i.e. the packaging material may applied to seal the package, wherein the package may be manufactured from any material on which the packaging material according to the present invention may provided as seal. In one embodiment, the container to be sealed with a packaging material according to the present invention may 25 contain a sufficient of aluminium in the area on which the seal is to provided, to allow heat sealing by induction.

30 In view of the above detailed description of the present invention, other modifications and variations will become apparent to those skilled in the art.

However, it should be apparent that such other modifications and variations may be effected without departing from the spirit and scope of the invention.

CLAIMS

- 5 1. A heat-sealable packaging material that is free from aluminium in the form of a continuous foil or film, characterized in comprising a layer that comprises at least 60% by weight of microfibrillated cellulose, wherein the layer comprising microfibrillated cellulose is laminated or coated with a heat-sealable material and wherein at least one side of the packaging material is provided with a coating selected from starch,
10 a wax, a mineral or pigment coating that prevents the coated surface from adhering to a heated metal surface, wherein the thickness of the packaging material is less than 70 μm .
- 15 2. The heat-sealable packaging material according to claim 1, wherein the heat-sealable material is selected from polyethylene, polypropylene, polylactic acid, styrene acrylic latex, styrene butadiene latex or a mixture thereof.
- 20 3. The heat-sealable packaging material according to claim 1 or 2, wherein said layer comprising microfibrillated cellulose has been extrusion coated or dispersion coated with a thermoplastic polymer.
- 25 4. The heat-sealable packaging material according to claim 3, wherein said thermoplastic polymer is polyethylene.
- 30 5. The heat-sealable packaging material according to claim 1 or 2, wherein the microfibrillated cellulose is native or modified or a mixture thereof and wherein the modified microfibrillated cellulose is phosphorylated microfibrillated cellulose or PCC coated microfibrillated cellulose.

6. A method of manufacturing a heat-sealable packaging material, according to any one of claims 1-5, characterized in comprising the steps of
- 5 a) preparing a layer of microfibrillated cellulose;
- b) laminating or coating the layer of step a) with a heat-sealable material on at least one side of the microfibrillated cellulose layer and wherein at least one side of the material is provided with a coating selected from starch, a wax, a mineral or pigment coating that prevents the coated surface from adhering to a heated metal
- 10 surface.
7. Use of a heat-sealable packaging material according to any one of claims 1-5 in induction sealing, wherein the packaging material is brought into close proximity or brought into contact with a surface
- 15 heated by induction.

I följande bilaga finns en översättning av patentkraven till svenska. Observera att det är patentkravens lydelse på engelska som gäller.

A Swedish translation of the patent claims is enclosed. Please note that only the English claims have legal effect.

PATENTKRAV

1. Ett värmeförseglingsbart förpackningsmaterial som är fritt från
5 aluminium i form av en kontinuerlig folie eller film, kännetecknat av att det innefattar ett lager som innefattar minst 60 vikts-% mikrofibrillerad cellulosa, där lagret innefattande mikrofibrillerad cellulosa är laminerat eller belagt med ett värmeförseglingsbart material och där minst en
10 sida av förpackningsmaterialet är försett med en beläggning vald från stärkelse, ett vax, en mineral- eller pigmentbeläggning som förhindrar den belagda ytan från att vidhäfta vid en uppvärmd metallyta, där tjockleken för förpackningsmaterialet är mindre än 70 µm.
2. Det värmeförseglingsbara förpackningsmaterialet enligt patentkrav 1,
15 där det värmeförseglingsbara materialet är valt från polyeten, polypropen, polymjölksyra, styren-akryl-latex, styren-butadien-latex eller en blandning därav.
3. Det värmeförseglingsbara förpackningsmaterialet enligt patentkrav 1
20 eller 2, där nämnda lager innefattande mikrofibrillerad cellulosa har extrusionsbelagts eller dispersionsbelagts med en a termoplastisk polymer.
4. Det värmeförseglingsbara förpackningsmaterialet enligt patentkrav 3,
25 där nämnda termoplastiska polymer är polyeten.
5. Det värmeförseglingsbara förpackningsmaterialet enligt patentkrav 1
30 eller 2, där den mikrofibrillerade cellulosan är nativ eller modifierad eller en blandning därav och där den modifierade mikrofibrillerade cellulosan är fosforylerad mikrofibrillerad cellulosa eller PCC-belagd mikrofibrillerad cellulosa.

6. En metod för framställning av ett värmeförseglingsbart förpackningsmaterial, enligt något av patentkraven 1-5, kännetecknad av att den innefattar stegen att
- 5 a) framställa ett lager av mikrofibrillerad cellulosa;
- b) laminera eller belägga lagret från steg a) med ett värmeförseglingsbart material på minst en sida av mikrofibrillerad cellulosa-lagret och där minst en sida av materialet är försett med en beläggning vald från stärkelse, ett vax, en mineral- eller pigmentbeläggning som förhindrar den belagda ytan från att
- 10 vidhäfta vid en uppvärmd metallyta.
7. Användning av ett värmeförseglingsbart förpackningsmaterial enligt något av patentkraven 1-5 vid induktionsförsegling, där förpackningsmaterialet bringas i närheten eller i kontakt med en yta
- 15 uppvärmd genom induktion.