



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁶ : C08F 4/64, 10/00</p>	<p>A1</p>	<p>(11) International Publication Number: WO 98/51716</p> <p>(43) International Publication Date: 19 November 1998 (19.11.98)</p>
<p>(21) International Application Number: PCT/EP98/02741</p> <p>(22) International Filing Date: 11 May 1998 (11.05.98)</p> <p>(30) Priority Data: 08/855,057 13 May 1997 (13.05.97) US</p> <p>(71) Applicant: MONTELL TECHNOLOGY COMPANY B.V. [NL/NL]; Hoeksteen 66, NL-2132 MS Hoofddorp (NL).</p> <p>(72) Inventor: EWEN, John, A.; 14311 Golf View Trail, Houston, TX 77059 (US).</p> <p>(74) Agent: ZANOLI, Enrico; Montell Italia S.p.A., Via Pergolesi, 25, I-20124 Milano (IT).</p>		<p>(81) Designated States: JP, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>
<p>(54) Title: PROCESS FOR PREPARING TACTIOSELECTIVE POLYOLEFINS IN CONDENSED PHASE USING HAFNOCENES</p>		
<p>(57) Abstract</p> <p>A process for polymerizing addition polymerizable monomers using hafnocenes catalysts/catalyst precursors having a selected symmetry condition under condensed polymerization conditions where the symmetry condition is such that the resulting polymer has varying degrees of tacticity or copolymers having regions of varying degrees of tacticity. Preferred classes of the hafnocenes are capable of generating near pure isospecific polymers in solution or in bulk polymerization conditions.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

“PROCESS FOR POLYMERIZING TACTIOSELECTIVE POLYOLEFINS IN CONDENSED PHASE USING HAFNOCENES”

Field of the Invention

This invention relates to a method for making tactioselective polyolefin homopolymers and copolymers using hafnocenes with selected symmetry conditions.

More particularly, this invention relates to a method for making tactioselective polyolefin homopolymers and copolymers using hafnocenes with selected symmetry conditions in condensed phases at temperature above 50 °C.

Brief Description of Related Art

Polymerization of vinyl monomer, both mono-olefins and conjugated dienes, has focused on transition metal catalysts since the work of Ziegler and Natta. These catalysts are based on a central transition metal ion or atom surrounded by a set of coordinating ligands and modified by various co-catalysts. These polymerization systems when brought in contact with addition polymerizable monomers polymerize the monomers into polymers.

By controlling the nature of the ligand system, the central transition metal ion or atom, and the co-catalyst, highly active catalytic agents can be made. In addition, catalysts can be made that yield polymers with high degrees of addition regularity and in the case of non-ethylene type monomers, stereoregular or tactioselective and/or tactiospecific polymers can be made.

Atactic polymers exhibit no regular order of repeat unit orientation in the polymer chain, *i.e.*, the substituents are not regularly ordered relative to a hypothetical plane containing the polymer backbone (the plane is oriented such that the substituents on the pseudo-asymmetric carbon atoms are either above or below the plane). Instead, atactic polymers exhibit a random distribution of substituent orientations.

Besides metallocene catalyst that produce polyethylene and atactic polyolefins, certain metallocenes are also known to produce polymers with varying degrees of stereoregularity or tacticity, such as isotactic, syndiotactic, and hemi-isotactic polymers which have unique and regularly repeating stereochemistries or substituent orientations relative to the plane containing the polymer backbone.

Isotactic polymers are typically described as having the substituents attached to the - asymmetric carbon atoms, oriented on the same side relative to the polymer backbone, *i.e.*, the substituents are all either configured above or below the plane containing the polymer backbone. Isotacticity can be determined through the use of NMR. In Bovey's NMR nomenclature, an isotactic pentad is represented by "mmmm" with each "m" representing a "meso" dyad or successive monomer units oriented with the substituents oriented on the same side relative to the polymer backbone. As is well known in the art, any deviation, disruption, or inversion about a pseudo-asymmetric carbon in the chain will lower the degree of isotacticity and crystallinity of the polymer.

In contrast, the syndiotactic structure is typically described as having the substituents, that are attached to the pseudo-asymmetric carbon atoms, pseudo-enantiomorphically disposed, *i.e.*, the substituents are oriented alternately and regularly above and below the plane containing the polymer chain. Syndiotacticity can also be determined through the use of NMR. In NMR nomenclature, a syndiotactic pentad is represented by "rrrr" in which each "r" represents a "racemic" dyad, *i.e.*, successive substituents on alternate sides of the plane. The percentage of "r" dyads in the chain determines the degree of syndiotacticity of the polymer.

There are other variations in polymer structures as well. One such variant is the so-called hemi-isotactic polymers. Hemi-isotactic polymers are ones in which every other pseudo-asymmetric carbon atom has its substituent oriented on the same side relative to the plane containing the polymer backbone. While, the other pseudo-asymmetric carbon atoms can have their substituents oriented randomly either above or below the plane. Since only every other pseudo-asymmetric carbon is in an isotactic configuration, the term hemi is applied.

Isotactic and syndiotactic polymers are crystalline polymers and are insoluble in cold xylene. Crystallinity distinguishes both syndiotactic and isotactic polymers from hemi-isotactic or atactic polymers that are soluble in cold xylene and are non-crystalline. While it is possible for a catalyst to produce all four types of polymers (atactic, hemi-isotactic, isotactic and syndiotactic), it is desirable for a catalyst to produce predominantly or essentially exclusively isotactic or syndiotactic polymer with very little atactic polymer and few stereochemical defects.

In recent years, numerous patents and applications have been filed relating to the use of metallocene and constrained geometry catalyst for the efficient production of polyolefins and for the efficient formation of tactioselective polyolefins including iso, hemiso and syndio tactic polypropylene.

Several catalysts that produce isotactic polyolefins are disclosed in U.S. Pat. Nos. 4,794,096 and 4,975,403, as well as European Pat. Appl. 0,537,130. Several catalysts that produce syndiotactic polyolefins are disclosed in U.S. Pat. Nos. 5,155,080, 5,225,500, and 5,459,117.

Besides neutral metallocenes, cationic metallocenes are known to result in polymers with varying degrees of tactiospecificity. Cationic metallocene catalysts are disclosed in

European Patent Applications 277,003 and 277,004. Catalysts that produce hemi-isotactic polyolefins are disclosed in U.S. Pat. Nos. 5,036,034.

In addition to polymers of mono-olefins homopolymers, polymerization catalysts for preparing copolymers of mono-olefins or polymers of di-functional olefins or copolymers of di-functional olefins and mono-olefins can be prepared using coordinated metal catalysts including metallocene catalysts.

Although these catalysts are efficient for the production of polyolefins, most of these catalysts are designed to operate at fairly modest temperature (70°C) in the gas phase and are not suitable for high temperature solutions polymerization where the temperature can exceed 120 °C. In such condensed phase polymerization, a process using a set of hafnocene catalysts that can produce tactioselective to tactiospecific catalyst in condensed phase polymerizations would represent an advancement in the art.

SUMMARY OF THE INVENTION

The present invention provides a condensed phase polymerization process for polymerizing addition polymerizable monomers comprising the step of contacting, in a condensed phase, at least one addition polymerizable monomer capable of forming isotactic polymer units with at least one hafnocene catalyst/catalyst precursor of formula (I):



wherein:

- (a) Z and Z' are the same or different and are a cyclopentadienyl containing ligand, a hetero atom analog of a cyclopentadienyl containing ligand, or an open, 5 centered, 6 π electron ligand;
- (b) R'' is a structural bridge;

- (c) Q is a linear or branched alkyl radical, an aryl radical, an alkenyl radical, an alkylaryl radical, an arylalkyl radical or a halogen atom;
- (d) A is a counterion;
- (e) k is an integer having a value from 1 to 3;
- (f) l is an integer having a value from 0 to 2;
- (g) Z and Z' have at least one β substituent sterically larger than a hydrogen atom;
- (h) ZR''Z' has C_2 or near C_2 symmetry; and
- (i) the hafnocene forms polymers having an isotactic selectivity between 90% and 100% for the monomer capable of forming isotactic polymer units.

Preferably, the catalyst and monomer are contacted together in a reaction zone. Alternatively, the catalysts of formula (I) can be combined with a co-catalyst such as an alkyl aluminum or an alumoxane either prior to or after the hafnocene of formula (I) is brought into contact with monomer. The hafnocenes of the present invention are particularly useful for condensed phase polymerization of addition polymerizable monomers such as α -olefins into homopolymer and/or copolymers. However, these catalysts would also find utility in gas phase polymerization reactions and can be supported on supports to produce heterogeneous analogs.

The hafnocenes suitable for use in the method of the present invention comprise organotitanium coordination compounds of di and tri-functional ligand systems, where the ligand system is bridged and has a selected symmetry or near-symmetry condition. The bridging group R'' includes single atom bridges where the R'' group is bonded to one atom of Z and Z' and bridges that connect two sites of Z and Z' (especially adjacent sites) which

forms a ring bridge, *e.g.*, a ligand system having two dimethylsilylenyl moieties, one bonding the 1,1' and the other bonding 2,2' sites of two cyclopentadienyl rings.

Formula (I) also describes cationic catalysts where $l=1$ or 2 . These cationic catalysts are prepared by reacting an ion-pair or a strong Lewis acid compound with a neutral hafnocene (*i.e.*, $l=0$) to form a cationic hafnocene either prior to or concurrent with contacting the catalytic system with monomer. The cationic catalysts are used analogously to the neutral catalysts to polymerize addition polymerizable monomers.

Furthermore, the hafnocenes of formula (I) may be made into pre-polymerized catalytic systems prior to contacting the system with bulk monomer and/or prior to the stabilization of the reaction conditions.

The present invention can also be practiced to produce intimate blends of different types of polymers by contacting a hafnocene of formula (I) designed for each different polymer type with one or more monomers and to use a hafnocene of formula (I) with another polymerization catalyst.

The preferred applications of practicing this invention is in the production of polyethylene, polyethylene copolymers, polypropylene, polypropylene copolymers, isotactic polypropylene, syndiotactic polypropylene, hemi-isotactic polypropylene, or mixtures thereof as well as polymers and copolymers of other addition polymerizable monomers.

DEFINITIONS

"Cp" means a ligand containing an all carbon cyclopentadienyl ring;

"Op" means an all carbon, open, five centered, six π electron ligand such as 1,4-pentadiene;

"HCp" means a cyclopentadienyl containing ligand containing at least one non-carbon atom in the ring system;

"COp" means an all carbon, non-cyclopentadienyl, cyclic five centered, six π electron ligand such as 1,4-cyclohexadiene or 1,4-cycloheptadiene;

"HOp" means an open, five centered, six π electron ligand containing at least one non-carbon atom in the ligand such as 4-methylpenta-4-ene-2-thione;

"CHOp" means a non-cyclopentadienyl, cyclic five centered, six π electron ligand containing at least one non-carbon atom in the ligand such as 2,5-dihydropyridine;

The prefix "h-" connotes the heterocyclic analogs of an all carbon aromatic ring systems, *e.g.*, h-Flu means a fluorene or fluorane ring system containing at least one non-carbon atom or h-Ptene means a pentalene or pentalane ring system containing a least one hetero atom;

The prefix "o-" connotes the open-pentadienyl analog of an all carbon aromatic ring systems, *e.g.*, o-Flu represents 1,1-diphenyl methane;

"Tactioselectivity" means a polymer with some amount of tacticity such as isotacticity, syndiotacticity or hemi-isotacticity;

"Tactiospecificity" means a polymers with a high degree of tacticity generally above 80% tactioselectivity;

"Bilateral symmetry" means that one of the ligands of a bridged ligand system has a bisecting minor plane, *e.g.*, isopropenyl(3-t-butyl cyclopentadiene)(3,4-dimethylcyclopentadiene) has one ligand with bilateral symmetry, the 3,4-dimethylcyclopentadiene, and one ligand that does not have bilateral symmetry, the 3-t-butylcyclopentadiene);

"Pseudo or Near Bilateral symmetry" means that one of the ligands of a bridged ligand system has near bilateral symmetry, *e.g.*, isopropenyl(3-t-butyl cyclopentadiene)(3-chloro-4-methylcyclopentadiene) has one ligand with pseudo or near bilateral symmetry, the (3-chloro-4-methylcyclopentadiene) ligand. Thus, near or pseudo bilateral symmetry means

that substituents in symmetry equivalent sites on the ligand with respect to a bisecting mirror plane are not identical but similar;

"C₂ symmetry" has its traditional meaning, *i.e.*, the ligand has a C₂ axis of symmetry, *e.g.*, *rac*-isopropenylbis(3-*t*-butylcyclopentadiene);

"Near or Pseudo C₂ symmetry" means that the group in symmetry equivalent positions are not identical but similar, *e.g.*, *rac*-isopropenyl(3-*t*-butylcyclopentadiene)(3-isopropylcyclopentadiene);

"C_s symmetry has its traditional meaning, *i.e.*, the ligand is symmetric with respect to a bisecting mirror plane axis of symmetry, *e.g.*, isopropenyl(cyclopentadiene)(3,4-dimethylcyclopentadiene); and

"Near or Pseudo C_s symmetry" means that the group in symmetry equivalent positions are not identical but similar, *e.g.*, isopropenyl(cyclopentadiene)(3-chloro-4-methylcyclopentadiene).

DETAILED DESCRIPTION OF THE INVENTION

The Applicant has found that hafnocenes meeting certain symmetry conditions can make tactioselective polyolefins or copolymers having regions of tactioselectivity under condensed phase polymerization conditions, especially in solution polymerization or bulk polymerization, at elevated temperature generally above 50°C. The method broadly speaking involves contacting a hafnocene catalyst having a specific symmetry condition with an addition polymerizable monomer in a condensed (non-gaseous) phase at a temperature and pressure sufficient to maintain the reaction condition in a condensed phase to produce homopolymers having varying degrees of tactioselectivity or copolymers having regions having varying degrees of tactioselectivity.

The hafnocenes suitable for use in the method of the present invention are hafnocenes capable of polymerizing addition polymerizable monomers under condensed phase catalytic conditions are represented by formula (I):




wherein:

- (a) Z and Z' are the same or different and are a cyclopentadienyl containing ligand, a hetero atom analog of a cyclopentadienyl containing ligand, or an open, 5 centered, 6 π electron ligand;
- (b) R'' is a structural bridge;
- (c) Q is a linear or branched alkyl radical, an aryl radical, an alkenyl radical, an alkylaryl radical, an arylalkyl radical or a halogen atom;
- (d) A is a counterion;
- (e) k is an integer having a value from 1 to 3;
- (f) l is an integer having a value from 0 to 2;
- (g) Z and Z' have at least one β substituent sterically larger than a hydrogen atom;
- (h) ZR''Z' has C_2 or near C_2 symmetry; and
- (i) the hafnocene forms polymers having an isotactic selectivity between 90% and 100% for the monomer capable of forming isotactic polymer units.


In particular, the present invention is directed towards processes for the condensed phase polymerization of addition polymerizable vinyl monomers, including α -olefins such as propylene, butylene. The organohafnium catalyst systems are designed by having a selected symmetry condition to produce tacticselective polymers such as polymers having varying degrees of isotacticity, syndiotacticity, hemi-isotacticity polymers or copolymers with

symmetric monomers such as ethylene polymers where the copolymers have regions with varying degrees of tacticity. The selected symmetry conditions are specific for each type of tacticoselective polymers desired. For isotacticity, the hafnocene should have C_2 or near or pseudo C_2 symmetry, while for syndiotacticity, the hafnocene should have C_s or near or pseudo C_s symmetry.


Preferred ligand systems for the hafnocenes of formula (I) for generating polymers having varying degrees of isoselectivity are hafnocenes having C_2 or pseudo C_2 symmetry and where R'' is a single bridge (bridges only one atom of Z and Z') and Z and Z' bear identical substituents or similar substituents and are the same or different cyclopentadienyl containing ligands, hetero atom analogs of cyclopentadienyl containing ligands, non-cyclopentyl, cyclic 5 centered, 6 electron systems, or opened, 5 centered, 6 electron systems. Particularly preferred ligand systems are those with two bulky β substituents one on Z and one on the symmetrical equivalent site of Z' and two less bulky α substituents one on Z and one on a symmetrical equivalent site of Z'. Especially preferred Z and Z' ligands are represented by the following formula (a-c):



(a)



(b)




(c)

where R^α is the same or different and is any group including hydrogen than will bond to the ring atom (which may be other than carbon) including carbon containing groups, nitrogen containing groups, oxygen containing groups, boron containing groups, phosphorus

containing groups, sulfur containing groups or all other group capable of forming a stable bond with the ring atom; and where R^β and $R^{\beta'}$ are the same or different and are any non-hydrogen group and preferably groups having a steric bulk greater than a hydrogen atom and particularly greater than or equal to the steric bulk of a methyl group or aromatic carbon (which would be part of a fused ring system such as indene and fluorene).

Preferred ligand systems for use in making hafnocene capable of generating syndioselective polymers are double bridged ligand systems of formula (d) having C_s or pseudo C_s symmetry:



where R'' are the same or different and are as described above and R^α , R^β and $R^{\beta'}$ are as described above.

More than one hafnocene catalyst of the present invention or the hafnocenes of the present invention can be mixed with other polymerization catalysts to produce intimate mixtures of polymers. The polymers produced by the hafnocenes of the present invention are intended for fabrication into articles by extrusion, injection molding, thermoforming, rotational molding. Additionally, under certain conditions, preferred catalysts of the present invention can produce polymers with very high tacticity approaching tacticities of 80 to 100% and preferably 90 to 100%, *i.e.*, the polymers have near perfect tacticity such as nearly perfect isotactic polypropylene as measured by the melting point of the polymers which is 156°C.

The polymers which can be prepared using the hafnocenes of this invention include homopolymers and copolymers of vinyl monomers having from 2 to 20 carbon atoms and preferably from 2 to 12 carbon atoms with homopolymers and co-polymers of ethylene, propylene, butylene, and styrene being particularly preferred. Preferred polymers and copolymers of the present invention include polymers derived from monomers capable of yielding tactic polymers (monomers that do not have symmetry) having varying degrees of tacticselectivity or having regions of tacticselectivity. In addition, the vinyl monomers can also include various hetero atoms such monomers would include acrylonitrile, vinyl pyridine. In a preferred embodiment of the present invention, the hafnocenes of formula(I) are such that the ZR"Z' ligand system has C₂ or near (or pseudo) C₂ symmetry and generate polymers of non-symmetric α -olefins with varying degrees of isotacticity approaching, under appropriated conditions, near isospecific polymers having a melting point within 5% of the value for a pure isotactic polymer, *e.g.*, isotactic polypropylene with a melting point above 156°C and particularly with a melting point above 160°C. It should be recognized that the melting point of most polymers having varying degrees of tacticselectivity will vary somewhat depending on the exact method for performing the measurement. However, irrespective of the method used, the hafnocenes of the present invention can produce polymers with near perfect tacticity having melting points substantially the same as a pure sample of the given tactic polymer.

In another preferred embodiment of the present invention, the hafnocenes of formula (I) are such that the ZR"Z' ligand system has C_s or near (or pseudo) C_s symmetry and generate polymers of non-symmetric α -olefins with varying degrees of syndiotacticity approaching,

under appropriated conditions, near syndiospecific polymer with melting point within 5% of the value for a pure syndiotactic polymer for the given monomer used.

Generally, tactioselective catalyst/catalyst precursors, and even tactiospecific catalysts, of the present invention are formed when the ligands Z and Z' of the ligand system ZR''Z' of formula (I) bear the same or different substituents in some or all of the positions α and β to the atoms bonded to the bridging group R'' such that at least one β substituent is a bulky substituent. For the purposes of this invention the term bulky substituent will mean a non-hydrogen substituent. Therefore, any atom or group that can replace a hydrogen atom at a β site on the Z or Z' will be considered sterically bulkier than hydrogen. Preferably, the β substituent is bulkier than a methyl group or an aromatic carbon atom (which are of essentially the same relative steric bulk), *e.g.*, ethyl, isopropyl, t-butyl, methoxy, methylamino, *etc.* Preferably, such ligand systems possess a specific overall symmetry condition. Additional information on the effect of bulky β substituent can be found in United States Patent No. 5,459,117.

Hafnocenes of formula (I) capable of yielding polymers with varying degrees of selectivity to the isotactic joining of monomer units ("isoselective hafnocenes"), including nearly isospecific polymers ("isospecific hafnocenes"), are hafnocenes where the overall ligand system has either C₂ or near or pseudo C₂ symmetry. Isoselective catalysts include hafnocenes where neither Z or Z' is bilaterally or pseudo-bilaterally symmetric and both Z and Z' ligands have a single bulky β substituent irrespective of the number and type of α -substituents. Alternatively, isoselective hafnocenes include ligand systems where either the Z or Z' ligand is bilaterally or pseudo-bilaterally symmetric and where the non-bilaterally symmetric ligand has only one bulky β substituent. In the case of Op or HOOp containing

ligand systems, the substituents will be on positions structurally equivalent to the α and β sites of cyclopentadiene and for the purpose of this invention, the numbering system for Op or HOp containing ligand systems will be such that the atom(s) to which the bridging group R" is or are attached will represent the atom(s) from which the α and β sites will relate.

Hafnocenes of formula (I) capable of yielding polymers with varying degrees of selectivity to the syndiotactic joining of monomer units ("syndioselective"), including syndiospecific polymers ("syndiospecific hafnocenes"), are hafnocenes where the overall ligand system has either C_s or pseudo- C_s symmetry. Syndioselective catalysts include hafnocene where both Z and Z are bilaterally or pseudo-bilaterally symmetric and where either Z or Z, but not both, have bulky β substituents irrespective of the number and type of α -substituents.

In its broadest form the process of the present invention involves polymerizing an addition polymerizable monomer such as an α -olefin, either alone or together with other addition polymerizable monomers in the presence of a catalyst system including at least one component of formula (I) and optionally a co-catalyst such as an alumoxane. Alternatively, the process includes simply contacting at least one polymerizable monomer with a catalyst system including at least one hafnocene of formula (I) under condensed phase polymerization conditions, *i.e.*, conditions of temperature and pressure necessary to maintain the polymerizing system in a condensed phase. Maintaining the polymerization in a condensed phase does not mean and is not meant to indicate that solvent or monomer does not boil during the polymerization; this term only means that the polymerization reaction is not occurring in the gas phase.

The present invention further provides a process for producing copolymers having tacticoselective regions and even tacticospecific regions within the polymers comprising

contacting at least one non-symmetric addition polymerizable monomer and at least one symmetric addition polymerizable monomer with a catalyst system including at least one hafnocene of the formulas (I) where the ligand system of the hafnocene catalysts/catalyst precursors that bear tacticity controlling α and β substituents as described herein. Symmetric addition polymerizable monomers include, without limitation, ethylene, 1,1-difluoroethylene. Non-symmetric addition polymerizable monomers include, without limitation, all α -olefins such as propene, 1-butene, 1-hexene.

Many hafnocene catalysts/catalyst precursors of formulas (I) that are capable of producing tactioselective and/or tactiospecific polymers when contacted with monomers capable of forming polymers with tacticity, have certain specific substitution requirements that often impart actual or pseudo symmetry to the ligand system and/or the hafnocene catalyst/catalyst precursor. The symmetry terms generally used to describe hafnocene catalyst systems that generate tactioselective polymers are described below.

The term bilateral symmetry means that the ligands of the ligand system $ZR''Z'$ are symmetric with respect to a bisecting mirror plane perpendicular to the plane containing the ligand and bisecting the ligand into two parts. For bridged ligand systems where the bridge bonds to only one atom of Z and Z' of the $ZR''Z'$ ligand systems, bilateral symmetry will mean that the substituents with the 2 and 5 positions (the α sites) and the 3 and 4 positions (the β sites) which are in a mirror image relationship, respectively, will be identical, *e.g.*, 3,4-dimethyl Cp or 2,5-dimethyl Cp. The term pseudo-bilateral symmetry means that the 3,4 and 2,5 substituents are of similar but not identical, *e.g.*, methyl and ethyl, phenyl and pyridyl, naphthyl and quinoline, methyl and chloro, hydrogen and fluoro, *etc.* For bridged ligand systems where the bridge bonds two atoms on the Z and Z' ligand, bilateral symmetry and

pseudo bilateral symmetry are analogous except that for adjacent bridging schemes, there is only one β site so that the α substituents must be identical or similar.

To produce isoselective catalysts having either C_2 symmetry or pseudo- C_2 symmetry, the ligand systems are contacted with an appropriate metallic species which yields a mixture of *meso* isomers which yield atactic polymer and *rac* isomers which yield isoselective polymers. The *meso* and *rac* isomers can be separated by crystallization or other separation techniques well known in the art.

Moreover, isoselective catalyst can also be prepared that do not have inactive *meso* forms. Such isoselective catalysts generally comprise one bilaterally symmetric radical and one asymmetric radical (not bilaterally or pseudo-bilaterally symmetric).

In accordance with this invention, one can also produce olefin copolymers particularly copolymers of ethylene and/or propylene and other olefins by a judicious choice of hafnocenes of the general formula (I). The choice of hafnocenes of the present invention can be used to control comonomer content as well as other properties of the polymer such as tacticity for vinyl monomers other than ethylene or ethylene like monomers.

The hafnocene catalyst/catalyst precursors of the present invention include ligand systems bearing substituent other than hydrogen on any of the sites of the ligand system. The substituents can be of any chemically meaningful type, including, without limitation, boron containing (bonding through the boron atom), carbon containing (bonding through the carbon atom), nitrogen containing (bonding through the nitrogen atom), and analogous substituents for all other atomic species of the periodic table that are capable of forming bonded substituents. The substituents can also be fused rings attached to the central radical can be aromatic, non-aromatic, unsaturated and/or unsaturated ring or ring systems.

Additionally, the central radical can include the phosphino-boratabenzene radicals (that are prepared according to the procedure described in Quan, R.W. et al, *J. Am. Chem. Soc.*, **1994**, *116*, 4489)

Examples of substituents that can be attached (bonded) to the ligand Z and Z' include, without limitation, any B, C, N, O, Al, Si, P, S, Ga, Ge, As, Se, In, Sn, Sb, Te, transition metals, actinide or lanthanide or any other substituent as well as substituent containing any number of different atomic species. Exemplary examples of some heterocyclic ring substituents include, without limitation, pyrrole, isopyrroles, pyrazole, isoimidazole, 1,2,3-triazole, 1,2,4-triazole, imidazole, indolizine, thiophene, 1,3-dithiole, 1,2,3-oxathiole, 1,2-dithiole, thiazole, isothiazole, 1,2,3-oxadiazole, 1,2,4-oxadiazole, 1,3,4-oxadiazole, 1,2,3,4-oxatriazole, 1,2,3,5-oxatriazole, thionaphthene, isothionaphthene, isoindazole, benzoxazole, anthranil, benzothiophene, naphthothiophene, furane, isobenzofuran, benzofuran, indole, indazole, purine, carbazole, carboline, isothiazole, isoxazole, oxazole, furazan, thienofuran, pyrazinocarbazole, furopyran, pyrazolo-oxazole, selenazolo-benzothiazole, imidazothiozole, furocinnoline, pyridocarbazole, oxathioloprryole, imidazotriazine, pyridoimidazoquinoline, sila-2,4-cyclopentadiene, thiapentalenes, azapentalenes, dithiatricyclounnonatetraenes.


The hetero atom analogs of the all carbon ligands of the present invention can include any ligand where at least one of the carbon atoms has been replaced by a non-carbon atom. Of course, the non-carbon atom must be an atom having a valence capable of replacing the carbon atom and allowing for some degree of electron delocalization in a neutral or anionic form. For example, for a pentalene containing ring system, the hetero atom could be part of a fused ring attached to the central six electron radical such as thiapentalene, azapentalene,

dithiatricyclounnonatetraene, diazatriacyclounnonatetraene or thiaazatriacyclounnonatetraene radicals or the hetero atom can be contained in a radical bonded to the central atom, such as heterocyclic radical substituents bonded to the central radical such as a 3-pyridylCp radical. Additionally, the cyclopentadienyl ligands with nitrogen, oxygen, phosphorus or sulfur atoms replacing the carbon atoms of the ring are contemplated. The molecular systems must be chemically stable under the reaction conditions of solution or gas phase polymerization. The synthesis of cyclopenta[*b*]quinolines is described in Eisch, J.J.; Gadek, F.J, J. Org. Chem., **1971**, *36*, 2065-2071.

It should be apparent that certain of these ring systems will not support substituents at the hetero atom. Thus, oxygen and sulfur containing rings will not have substituents attached to the oxygen or sulfur atoms. Additionally, in the case of N, P, and As where these atoms are part of a double bond, they will not have substituents attached thereto.

The term five centered six π electron ligand refers to any structure containing five atoms in an configuration and capable of delocalizing 6 π electrons and that are not part of a cyclopentyl ring, preferably, the configuration should be an all cis configuration of the five centers. All five atoms should be sp^2 hybridized or in some other hybridization that can support electron delocalization over the five centers. One possible precursor to the Op ligands of this invention is a system where four of the atoms are part of two non-conjugated double bonds connected to and separated by a central atom, where the double bonds contribute two electrons each to the ligand system and the central atom supplies two electrons to the system either directly as the lone pair of a N or P atom or through the loss of a removable group to result in the formation of an anionic center as for a C or Si atom. Other central species could be used as well including Ge, As. Additionally, the 5 centered, 6 π

electron system can be part of a 6 to 20 or larger ring structure. Such ligands are better represented by formula (II):



where: G is a carbon atom, a nitrogen atom, a silicon atom or a phosphorus atom; J and J' are the same or different and where J is a CR³R^{3'} radical, a SiR³R^{3'} radical, a NR^{3''} radical, a PR^{3''} radical, an oxygen atom or a sulfur atom and J' is a CR⁴R^{4'} radical, a SiR⁴R^{4'} radical, a NR^{4''} radical, a PR^{4''} radical, an oxygen atom or a sulfur atom; R², R³, R^{3'}, R^{3''}, R⁴, R^{4'}, R^{4''}, and R⁵ can be the same or different and are a hydrogen atom, a linear or branched C1-C20 hydrocarbyl radical, a linear or branched C1-C20 halocarbyl radical, a linear or branched C1-C20 hydrohalocarbyl radicals, a linear or branched C1-C20 alkoxy radical, a C3-C12 cyclohydrocarbyl radical, a C3-C12 cyclohydrohalocarbyl radical, an aryl radical, an alkylaryl radical, an arylalkyl radical, a silicon hydrocarbyl radical, a germanium hydrocarbyl radical, a phosphorous hydrocarbyl radical, a nitrogen hydrocarbyl radical, a boron hydrocarbyl radical, an aluminum hydrocarbyl radical, a halogen atom, or R² and R³, R^{3'} or R^{3''} and/or R⁵ and R⁴, R^{4'} or R^{4''} can be joined together to form a 4 to 6 membered ring or a 6 to 20 fused ring system or where R³, R^{3'}, or R^{3''} and R⁴, R^{4'}, or R^{4''} can be joined together so that the five numbered atomic centers making up the five centered delocalized six π electron ligand are contained in a 6 to 20 ring.

The numbers associated with the five atoms in formula (II) are there to indicate how substituent positions will be addressed in the remainder of the specification. Thus, for those

hafnocenes having a structural bridge, the structural bridge will be bonded to the central atom which is designated as position 1, in a fashion analogous to the numbering in cyclopentadiene. Additionally, the 2 and 5 positions will sometimes be jointly referred to as the α positions or proximal positions (proximal to the 1 position), while the 3 and 4 positions will sometimes be jointly referred to as the β or distal positions.

For catalyst systems that produce stereoselective and/or tacticselective polyolefins, the ligand systems that make up the catalysts/catalyst precursors of the present invention can be substituted in such a way that the systems are stereorigid (bridged), stereolocked and stereodirected. It is thought that by making bridged ligand systems and appropriately substituting the ligands of the ligand system, the catalysts/catalyst precursors of the present invention can be designed to that: (1) the substituents lock and/or direct the polymer chain-end orientation and/or monomer approach such that each successive monomer addition is stereospecific or where the degree of stereoselectivity can be controlled; and (2) the bridging group renders the ligand system rigid so that ligand rotation or isomerization is prevented or restricted. These catalyst are characterized by having β or distal substituents or their equivalent (the group on a amine or phosphine anion ligand) on the ligands or the ligand system that control the orientation of monomer addition and catalyst configurations so that tacticselective can occur. Tacticselectivity generally means that the polymers are less stereoregular than tacticselectivity means in analogy to the used of stereoselectivity and stereospecificity in synthetic chemistry. Stereoregularity relates to the manner of addition such as head-to-head, head-to-tail, *etc.*

Traditionally, the term metallocene denoted an organometallic coordination compound in which two cyclopentadienyl containing ligands are coordinated to or "sandwiched" about a

central metal atom and where all five centers of the Cp ring are involved in metal coordination (haptic five coordinate ligands). The metal atom may be a transition metal or transition metal halide, alkylide, alkoxide. Such structures are sometimes referred to as "molecular sandwiches" since the cyclopentadienyl ligands are oriented above and below a plane containing the central coordinated metal atom nearly parallel to the planes containing the Cp ring. Similarly, the term "cationic metallocene" means a metallocene in which the central coordinated metallic species carries a positive charge, *i.e.*, the metallocene complex is a cation associated with a stable non-coordinating or pseudo-non-coordinating anion.

However, in addition to the traditional meaning of the term metallocene, the present invention expands this term to encompass ligand systems where neither of the ligands of the bridged ligand system are cyclopentadienyl containing ligands, but are instead a ligand that can be substituted analogously to cyclopentadienyl containing ligands so that the ligand system can have a given symmetry or pseudo symmetry necessary to generate tacticselective polymers.

One skilled in the art should also recognize that the permissible values for k and l will depend on the actual ligand system and these values are understood to conform to known organometallic structural and electronic requirements.

Suitable Z and Z' ligands for use in the present invention include, without limitation: (1) hetero atom containing ligands where the hetero atom is contained in a cyclopentadienyl containing ligand; (2) Op , HOp , $CHOp$, or COp containing ligands; (3) Cp containing ligands represented by the general formula $(C_5R'_{iii})$ where $(C_5R'_{iii})$ is a cyclopentadienyl or substituted cyclopentadienyl radical, each R' is the same or different group and can be any

non-hydrogen group as described above for radicals R^a or R^b or where two atoms are joined together to form a 4 to 20 membered ring and *iii* is an integer having a value from 0 to 5.

Suitable structural bridging groups R'' for use in this invention and impart stereorigidity to the hafnocene catalysts of this invention include, without limitation, a C1-C20 alkenyl radical, a peralkylated C1-C20 alkenyl radical, a dialkyl methyl radical, a C3-C12 cyclohydrocarbyl radical, an aryl radical, a diarylmethylene radical, a diaryl allyl radical, a silicon hydrocarbyl radical, dihydrocarbyl silenyl radicals, a germanium hydrocarbyl radical, a phosphorous hydrocarbyl radical, a nitrogen hydrocarbyl radical, a boron hydrocarbyl radical, an aluminum hydrocarbyl radical.

Other suitable bridging groups R'' , include ionic units such as $B(C_6F_5)_2$, and $Al(C_6F_5)_2$ and R_2C , R_2Si , R_4Et , R_6Pr where R can be any hydrocarbon, cyclic hydrocarbon, cyclic or linear hydrocarbons bearing another organometallic catalyst or carboranes, etc. Indeed, the bridges can be C_2 bridges (and C_3 etc.) which form the backbone of polymeric supports (e.g. the atactic, syndiotactic and isotactic polymers from vinyl-indene and 9-vinyl-fluorene etc.) as well as functionalized polystyrene precursors and all other polymers with terminal or branched boron or Al functional groups which are bonded to the catalysts, *e.g.*, in zwitterionic form. R_2C and R_2Si bridging groups are preferred with isopropylidene and dimethylsilenyl bridging groups being particularly preferred.

Another class of structural bridges are those involving more than a single atom on Z and Z'. Thus, R'' can represent structures that bridge two atoms on each of Z and Z' and preferably two adjacent atoms on Z and Z'. These bridges can be include carbon, silicone and other types of atomic centers as in the single atom bridging groups. Generally, when Z and Z' are bridged by more than one atom, the bridge is actually form as ring turning the $ZR''Z'$ ligand

system into a fused ring system. In the case of a double bridge dimethylsilylenyl bis cyclopentadienyl containing ligand system, the resulting ring system is a six membered ring containing two adjacent carbon atoms one each cyclopentadienyl ring and the two dimethylsilylenyl moieties in a 1,4 relationship to each other.

Suitable radicals corresponding to R, R', R^α, R^{α'} and R^β and R^{β'} include, without limitation, hydrogen atoms, linear or branched C1-C20 hydrocarbyl radicals, linear or branched C1-C20 halocarbyl radicals, linear or branched C1-C20 hydrohalocarbyl radicals, linear or branched C1-C20 alkoxy radical, C3-C12 cyclohydrocarbyl radicals, a C3-C12 cyclohydrohalocarbyl radicals, aryl radicals, alkylaryl radicals, arylalkyl radicals, silicon hydrocarbyl radicals, germanium hydrocarbyl radicals, phosphorus hydrocarbyl radicals, nitrogen hydrocarbyl radicals, boron hydrocarbyl radicals, aluminum hydrocarbyl radicals, halogen atoms. Preferable, non-hydrogen radicals include any group capable of covalently bonded to a site on the ligand system. Such groups include radicals that bond through any atom in the periodic table of elements; provided, of course, that the atom from covalent bonds with the given ligand cite. Examples include, without limitation, carbon containing radicals such as linear or branched alkyl radicals or aryl radicals, oxygen containing radicals such as alkoxy radicals, nitrogen containing radicals such as amino radicals, phosphorus containing radicals, sulfur containing radicals, silicone containing radicals trialkylsilyl radicals, and radicals bonding through B, Ge, Ga, Al, F, Cl, Br, I, Mg, Ca, or any other atomic center including metallic centers such as transition metals.

Additionally, suitable radicals corresponding to R, R', R^α, R^{α'} and R^β and R^{β'} include, without limitation, zwitterionic radicals such as Cp-B(C₆F₅)₃⁻, Cp-Al(C₆F₅)₃⁻, Cp-Al(CF₃)₃⁻, Cp-X-

$\text{Al}(\text{C}_6\text{F}_5)_3^-$, $\text{Cp-X-B}(\text{C}_6\text{F}_5)_3^-$ are also suitable radicals, where X can represent an alkenyl group, alkenoxy group.

Hafnocenes of this invention containing zwitterionic groups on either one of the ligand making up the ligand system of the present invention and incorporating a group 4 metal for Me would not need an independent and sometimes stereochemically interfering counterion (*i.e.*, $l=0$). In this case, one could obtain heterogeneous insoluble ion-pair systems for improved polymer particle size and morphology control.

Suitable hydrocarbyl radical or halogen corresponding to Q include, without limitation, a linear or branched C1-C20 alkyl radical, an aryl radical, an alkylaryl radical, an arylalkyl radical, a F atom, a Cl atom, a Br atom, and an I atom. Q is preferably a methyl or halogen, and more particularly a chlorine atom.

Exemplary hydrocarbyl radicals are methyl, ethyl, propyl, butyl, amyl, isoamyl, hexyl, isobutyl, heptyl, octyl, nonyl, decyl, cetyl, 2-ethylhexyl, phenyl. Exemplary alkylene radicals are methylene, ethylene, propylene, isopropylidene. Exemplary halogen atoms include fluorine, chlorine, bromine and iodine and of these halogen atoms, chlorine is preferred. Exemplary of the alkylidene radicals is methylenidene, ethylenidene and propylenidene. Exemplary nitrogen containing radicals include amines such as alkyl amines, aryl amines, arylalkyl amines, and alkylaryl amines.

Suitable non-coordinating counterions corresponding to A in the general formula include, without limitation, $[\text{BF}_4]^-$, $\text{B}(\text{PhF}_5)_4^-$, $[\text{W}(\text{PhF}_5)_6]^-$, $[\text{Mo}(\text{PhF}_5)_6]^-$ (wherein PhF_5 is pentafluorophenyl), $[\text{ClO}_4]^-$, $[\text{S}_n\text{O}_6]^-$, $[\text{PF}_6]^-$, $[\text{SbR}_6]^-$ or $[\text{AlR}_4]^-$ (wherein each R is independently, Cl, a C1-C5 alkyl group preferably a methyl group, an aryl group, e.g. a phenyl or substituted phenyl group, or a fluorinated aryl and alkyl group). By non-

coordinating the inventor means that the counterion will not so strongly associated with the hafnocene to interfere with monomer coordination and insertion or will not tend to reduce the hafnium ion from its active state.

Tactioselective hafnocene (*i.e.*, hafnocenes that produce tactioselective polymers) of the present invention are generally characterized by having symmetry or pseudo symmetry associated with the ligand system or the hafnocene. As stated previously, ligand systems including two bridged ligands and having C_2 or pseudo- C_2 symmetry or having one bilaterally symmetric ligand and one asymmetric ligand and at least one bulky β -substituent or pseudo β -substituent (in the case of hafnocenes having non-Cp groups) produce polymers with varying degrees of isotacticity; while, ligand systems including two ligands and having C_s or pseudo- C_s symmetry produce polymers with varying degrees of syndiotacticity.

The present catalysts can be tailored using a number of strategies to control properties such as the relative stereoselectivity and or stereospecificities of the polymer products produces, the molecular weight of the polymer products produced, and other significant polymer properties. The single carbon bridged metallocenes have been found to be more selective than the silicon bridged analogs for producing polymers with varying degrees of syndiotacticity; while the carbon bridged metallocenes are generally less selective than the silicon bridged analogs for generating polymers with varying degrees of isotacticity. Typically, it is also thought that the larger the steric requirements are for the β -substituents, the more stereospecific the catalyst is. The difference in the steric requirements for the β -substituent, which are thought to control the regularity of monomer addition, can be used to vary and indeed optimize the degree of stereoregularity in the final polymer product. It has

also been found that substituents at the α -positions tend to increase the molecular weight of the resulting polymer.

The present invention is directed to both neutral hafnocene and cationic hafnocene catalysts and catalyst precursors as evidenced by the subscript l associated with the counterion A (which is of course an anion) having permissible values of 0 to 2, i.e., when $l=0$, the catalysts are neutral and when $l=1$ or 2 the catalysts are cationic as evidenced by the inclusion of an anion in the general formula.

The catalysts of the present invention can also be designed to produce polymers with very high tacticity indices. In order to produce tactically specific polymers from the catalysts and/or catalyst precursors of the present invention, the characteristics of the β -substituents on the bridged ligands are important. Thus, the "steric requirement" or "steric size" of the β -substituents can be designed to control the steric characteristics of the catalysts/catalyst precursors such that the arrangement of the β -substituents allows control of the stereochemistry of each successive monomer addition.

It may also be possible to strategically arrange substituents with the proper steric properties on an appropriate ligand sites of the ligand system which serve as chain end conformational locks (preferably positioned in the mouth of the ligand) and which could also confer solubility (ion pair separation for better catalyst activity and stereospecificity) and/or insolubility (for better control of polymer morphology), as desired. The bridged, substituted catalysts/catalyst precursors are stereorigid, provide chain-end conformational locks, and are superior to those without such conformational locks.

Prior art has shown, for example, that a methyl substituent positioned at the α -Cp position on the C5 ring of bisindenyl catalysts increases the molecular weight of isotactic polypropylene

produced with the $\text{Et}[\text{Ind}]_2\text{ZrCl}_2$ based catalyst. Similarly, a methyl substituent on the C6 ring of the indenyl ring system has reduced the stereospecificity; depending on the positional isomerism. These effects can be reasonably expected to carry over to the catalyst system of the present invention.

Also, the addition of methyl, t-Bu, OMe, Ph, *etc.* substituents to the ligand system and to the bridging group R" can have steric, solubility, and/or electronic influences on catalysts in syndiotactic and isotactic specific polymerizations. These effects are likewise expected to be carried over to hafnocenes of the present invention and to their mixtures with other catalysts. Similarly the effects of substituting Al for B in the anions and the differences between carboranes and methylalumoxanes and other counter anions are reasonably expected to be carried over to the catalyst systems described herein.

By making the sterically larger β -substituents different and/or the sterically smaller β -substituents different, the tactioselective versions of the catalysts/catalyst precursors of the present invention can be designed to impart any degree of tacticity to the resulting polymers. Thus, if one β -substituent is t-butyl and another is ethyl, and the other two are methyls, the tactiospecificity of the catalyst system will be reduced relative to the one having two t-butyls and two methyls. Thus, hafnocenes having pure symmetry will generally yield polymers with high indices of tacticity (high degree of tactiospecificity) than hafnocenes with pseudo or near symmetry.

The concept of substituents with different steric requirements, size or bulk is well known in the art. However, to ensure that ordinary artisans understand its usage in the context of this invention, a non-exhaustive and illustrative list of the relative steric bulk of a variety of substituents can be found in Stoughtan and Adams article in *J. Am. Chem. Soc.*, 54, 4426

(1932) and Yuan and Adams article in J. Am. Chem. Soc. 54, 4434 (1932). Additionally, for purposes of this invention, a fluorine atom will be considered sterically larger than a hydrogen atom, even though many there is data to indicate that the two atoms have a similar steric bulk.

Cationic hafnocene catalysts/catalyst precursors require the counterion A to maintain their net neutrality. The counterion A in formula (I) is preferentially a compatible non-coordinating or weakly coordinating anion that either does not coordinate with the hafnocene cation or only weakly coordinates to the cationic hafnocene, yet remains sufficiently labile so that it can be readily displaced by a neutral Lewis base such as a monomer unit. Compatible non-coordinating or weakly coordinating anions are described as anions that stabilize the cationic hafnocene catalyst systems, but do not transfer an electron or electron equivalent to the cation to produce a neutral hafnocene and a neutral byproduct of the non-coordinating or weakly coordinating anion.

The useful size of the counterion A will also depend on the bulkiness or steric requirements of the ligand system including the substituents on the ligands of the ligand system. In addition to size, it is also thought that other characteristics are important for suitable non-coordinating or weakly coordinating counterions. Such characteristics include stability and bonding. The counterion must be sufficiently stable so that it cannot be rendered neutral by virtue of the hafnocene cation electron extraction and the bond strength with the cation must be sufficiently weak as to not interfere with monomer coordination and chain propagation.

A preferred procedure for producing cationic hafnocene catalyst of the present invention ($l=1$ or 2) involves the reaction of an ion-pair in a non-coordinating solvent with a hafnocene of the general formula where $l=0$. For example, triphenylcarbenium tetrakis(pentafluorophenyl)

boronate or a similar ion-pair may be reacted with a neutral hafnocene of the present invention in a solvent such as toluene to generate a cationic hafnocene analog thereof. This preparation method was referenced in U.S. Pat. No. 5,225,550.

A preferred application of the present invention is in the polymerization of alpha olefins, specifically propylene or propylene-ethylene copolymers, into all manners of polymers including atactic, isotactic, syndiotactic, hemi-isotactic polypropylenes or mixtures thereof. However, the invention may be employed in the preparation of hemi-isotactic, isotactic or syndiotactic polymers derived from other non-symmetric ethylenically unsaturated monomers. For example, syndiospecific, isospecific or hemi-isotactic specific polymers of 1-butene, 1-pentene, 1-hexene, styrene can be prepared using the catalysts of present invention.

Additional polymerizable monomers suitable for use in this invention include, without limitation, addition polymerizable, ethylenically unsaturated monomers or any organic molecule having a terminal vinyl group ($\text{CH}_2=\text{CH}$) such as, without limitation: α -olefins including propylene, 1-butene, 1-pentene, 1-hexene, 4-methyl-1-pentene; vinyl halides including vinyl fluoride, vinyl chloride; vinyl arenes including styrene, alkylated styrenes, halogenated styrenes, haloalkylated styrene; dienes such as 1,3-butadiene and isoprene (*i.e.*, 1,2-addition). Ethylene and polypropylene are probably of the greatest practical significance and the invention will be described in detail with reference to the production of polypropylenes and/or polypropylene copolymers, but it should be understood that this invention is generally applicable to all addition polymerizable monomers. The polymerization procedures disclosed in U.S. Pat. No. 4,892,851, may be also employed in carrying out the methods of the present invention.

The catalysts and catalyst precursors of the present invention can be used in conjunction with various co-catalysts. Although many of the species are active alone, many of the species of the general formula become activated (or become commercially active) upon the addition of various co-catalysts. Co-catalysts, usually organo-aluminum compounds such as trialkylaluminum, trialkyloxyaluminum, dialkylaluminum halides or alkylaluminum dihalides may be employed in the present invention. Especially suitable alkylaluminums are trimethylaluminum and triethylaluminum with the latter, commonly referred to as TEAL, being most preferred. Methylaluminoxane (MAO) are also usable in carrying out the methods of the present invention especially for neutral hafnocene catalyst precursors. MAO may be used as a co-catalyst with hafnocene catalysts in amounts well in excess of the stoichiometric equivalent.

The alumoxanes are polymeric aluminum compounds which can be represented by the general formulae $(R-Al-O)_n$ which is a cyclic compound and $R(R-Al-O)_n-AlR_2$, which is a linear compound and where R is a C_1-C_5 alkyl group such as, for example, methyl, ethyl, propyl, butyl and pentyl and n is an integer from 1 to 20. Most preferably, R is methyl and n is 4.

Generally, in the preparation of alumoxanes from, for example, aluminum trimethyl and water, a mixture of the linear and cyclic compounds is obtained. The alumoxane can be prepared in various ways. Preferably, they are prepared by contacting water with a solution of aluminum trialkyl, such as, for example, aluminum trimethyl, in a suitable organic solvent such as benzene or an aliphatic hydrocarbon. For example, the aluminum alkyl is treated with water in the form of a moist solvent. In an alternative method, the aluminum alkyl such as aluminum trimethyl can be desirably contacted with a hydrated salt such as hydrated copper

sulfate. Preferably, the alumoxane is prepared in the presence of a hydrated copper sulfate. The method comprises treating a dilute solution of aluminum trimethyl in, for example, toluene, with copper sulfate represented by the general formula $\text{CuSO}_4 \cdot 5\text{H}_2\text{O}$. The ratio of copper sulfate to aluminum trimethyl is desirably 1 mole of copper sulfate for 4 to 5 moles of aluminum trimethyl. The reaction is evidenced by the evolution of methane.

The ratio of aluminum in the alumoxane to total metal in the hafnocenes can be in the range of 0.5:1 to 10,000:1, and preferably 5:1 to 1000:1. The solvents used in the preparation of the catalyst system are inert hydrocarbons, in particular a hydrocarbon that is inert with respect to the catalyst system.

Such solvents are well known and include, for example, isobutane, butane, pentane, hexane, heptane, octane, cyclohexane, methylcyclohexane, toluene, xylene. As a further control and refinement of polymer molecular weight, one can vary the concentration alumoxane. Higher concentrations of alumoxane in the catalyst system results in higher polymer product molecular weight.

Since, in accordance with this invention, one can produce high viscosity polymer products at relatively high temperature, temperature does not constitute a limiting parameter; provided, however, that the pressure and temperature is such that the polymerization media is in a condensed phase. The hafnocenes described herein, therefore, are suitable for the condensed phase polymerization of olefins in solution, slurry or bulk and over a wide range of temperatures and pressures. Again the temperature and pressure are designed to maintain the polymerization reaction in a condensed phase such as a liquid phase, a liquid phase at its critical point or a liquid under super critical conditions. For example, such temperatures may be in the range of 50°C to 280°C and especially in the range of 80°C to 160°C. The

pressures employed in the process of the present invention are those well known for, for example, in the range of 1 to 500 atmospheres and greater and at the same time sufficient to maintain the polymerization in a condensed phase.

In a solution phase polymerization the alumoxane is preferably dissolved in a suitable solvent, typically in inert hydrocarbon solvent such as toluene, xylene, in molar ratios of $5 \times 10^{-3} \text{M}$. However greater or lesser amounts can be used. The soluble hafnocenes can be converted to supported heterogeneous catalyst by depositing said hafnocenes on typical catalyst supports such as, for example, silica, alumina, and polyethylene. The solid catalysts in combination with an alumoxane can be usefully employed in slurry and gas phase olefin polymerizations.

After polymerization and deactivation of the catalyst, the product polymer can be recovered by processes well known in the art for removal of deactivated catalysts and solution. The solvents may be flashed off from the polymer solution and the polymer obtained extruded into water and cut into pellets or other suitable comminuted shapes. Pigments, antioxidants and other additives, as is known in the art, may be added to the polymer.

The polymer product obtained in accordance with this invention will generally have a weight average molecular weight in the range of 1,400,000 to 500 and preferably 500,000 to 1000. The polydispersities (molecular weight distribution) expressed as M_w/M_n are typically from 1.5 to 4, but can be higher. The polymers contain 1.0 chain end unsaturation per molecule. Broadened MW can be obtained by employing two or more of the hafnocenes of this invention in combination with the alumoxane. The polymers produced by the process of this present invention are capable of being fabricated into a wide variety of articles, as is known for polymer products derived from addition polymerizable monomers.

While the applicant's invention is not to be restricted by theory, it is believed that neutral hafnocenes form cationic complexes by reaction with the MAO in the manner as disclosed by Zambelli, A. et al., "Isotactic Polymerization of Propene: Homogenous Catalysts Based on Group 4 Hafnocenes Without Methylaluminoxane", *Macromolecules* 1989, 22, pages 2186-2189.

The catalyst precursors used in the present invention may be prepared by procedures similar to those disclosed in U.S. Pat. No. 4,892,851, while the active cationic catalysts may be produced by simply converting the neutral hafnocene into the cationic state following procedures such as those disclosed in European applications 277,003 and 277,004 or by reaction with triphenylcarbenium boronates. Similarly, alcohol - $B(PhF_5)_3$ complexes can be used as anionic precursors for forming the active cationic hafnocenes of the present invention where the alcoholic proton reacts with an amine of an alkyl group on the coordinating metal atoms to generate a cationic hafnocene and an alkoxide - $B(PhF_5)_3$ anion. For additional information see, A.R. Siedle, W.M. Lammana, R.A. Newmark, J. St. Werrs, D.E. Richardson, M. Ryan, *Makromol Chern, Masroonal Symp.* 66, 215 (1993).

The catalysts of this invention can also be converted to supported heterogeneous catalysts by depositing the catalysts on supports including, without limitation, silica, alumina, magnesium dichloride, polystyrene beads. The supported analogs of the present catalyst can improve the bulk density of the polymer as further described in Canadian Pat. No. 2,027,145, U.S. Pat. Nos. 4,935,474 and 4,530,914 and European Appln. Nos. 0,427,697 and 0,426,638. The catalyst can also be chemically linked to the support by placing functional groups with ion pairs or Lewis acid centers or Lewis base centers on the ligands and/or supports.

Supporting can also be achieved by using large (oligomeric or polymeric) insoluble anions as counter ions.

The catalysts of the present invention can be used to prepare low, moderate and high molecular weight polymers, low, moderate and high density polymers, elastomers, aspecific, isospecific, syndiospecific, hemi-isospecific, and/or aspecific polymers, not only of propylene, but for all α -olefins such as 1-butene, 1-pentene, 1-hexene, 4-methyl-1-pentene, $\text{CH}_2=\text{CH}(\text{CH}_2)_p\text{Si}(\text{CH}_3)_3$ where p is 1 to 4. Additionally, the catalysts of this invention can polymerize singly or in mixtures all addition polymerizable monomer including vinyl monomers and diene monomers.

One of ordinary skill should recognize that the ligands that can give rise to isoselective catalysts will give rise to a *meso* form which is asymmetric and a *rac* form that is selective to specific to isotactic polymers. The stereospecific *rac* catalysts can be separated from the *meso* form by crystallization. Perhaps we should also mention that it is well known from the Bercaw *et al.* work (Reference: J. Ann Cherry Soc. 1992, 114, 7607 J.E. Bercaw and E.B. Coughlin.) in the prior art that *rac*-hafnocenes free of the undesirable aspecific *meso* stereoisomers can be prepared by placing suitable bulky substituents such as $\text{Si}(\text{Me})_3$ on the ligand atoms proximal to (α to) the bridgehead atom.

The catalysts of the present invention can obviously be used in conjunction with each other, all other hafnocene catalysts, $\text{TiCl}_3/\text{DEAC}$, and or $\text{TiCl}_4/\text{MgCl}_2/\text{TEAL}$ catalysts having internal electron donors such as diisobutylyphthalate and external donors such as diphenyldimethoxysilane, methanol, etc. to produce polymers with mixed stereochemical compositions, distributions or tailored molecular weight distributions. Reactor blends of polymers with optimized physical, thermal, mechanical, and rheological properties can be

tailored to produce the optimum mixture for specific applications requiring high melt strength, high clarity, high impact strength, and high rates of crystallization, simply by mixing catalyst species together in appropriate ratios.

The catalysts of the present invention clearly have the potential to influence the rate of termination by β -hydride elimination reactions. This, therefore, provides a novel ligand effect for controlling polymer molecular weights. These catalysts can be exploited to tailor molecular weights and hence molecular weight distributions with mixed species of the catalysts and any other class of catalysts. This would be advantageous in tailoring the polymer properties in HDPE, LLDPE, i-PP, s-PP, *etc.* Similarly the chain-end conformation locking substituent will influence the rate of reactivity of the new hafnocenes with α -olefins such as propylene, butene and hexene. The new ligand effects on the catalyst reactivity ratios can be exploited to produce reactor blends with varying compositions, sequences, distributions and/or molecular weight distributions. Similarly, the catalysts can reasonably be expected to provide improved tailored grades of polypropylene and propylene-ethylene high impact copolymers as reactor blends or from reactors in series including fluidized and stirred gas phase polymerizations.

The catalysts of the present invention can also be used to generate copolymers of olefins and copolymers of olefins and dienes with varying degrees of tacticity.

The generalized methods that follow describe the preparation of the catalyst and/or catalyst precursors and active catalysts. It is important that the catalyst complex be "pure" as low molecular weight, amorphous polymer can be produced by impure catalysts.


Generally, the preparation of the hafnocene complex consists of forming and isolating the ligand system which is then aromatized or deprotonated to form delocalized electron systems or hetero anions and are then reacted with a metal halide, alkylide, to form the complex.

The synthesis procedures are generally performed under an inert gas atmosphere using a glove box or Schlenk techniques. The synthesis process generally comprises the steps of 1) preparing the halogenated or alkylated metal compound, 2) preparing the ligand, 3) synthesizing the complex, and 4) purifying the complex.

The synthesis of the β -substituted Cp ligands of the present invention can be accomplished by contacting an appropriately substituted fulvene with an appropriately substituted cyclopentadienyl containing anion ring under reaction conditions sufficient to produce a bridged structure having the requisite β -substituents on the Cp rings to yield ligands with either C_2 or C_s or pseudo C_2 or pseudo C_s symmetry.

Fulvene is cyclopentadiene with an exo-cyclic methylene group at the 1 position of cyclopentadiene ring. The exo-cyclic methylene carbon is the 6 position of fulvene. Since this carbon can ultimately become the bridging group R" in formula (I), the preferred fulvenes for the preparation of the present catalysts are typically 6,6-disubstituted fulvenes so that the resulting bridging group is a tertiary carbon atom.

The fulvenes useful in preparing the ligands of the present invention have substituents in the 3 and 4 positions Q and are generally 6,6 disubstituted, while the other sites can be substituted or unsubstituted as shown below:



where R' become substituents on the resulting Cp ring, p is a integer having a value from 0 to the maximum number of substituents on the fulvene m and where the T, T' and the exocyclic carbon (C6 in fulvene) are the precursor to the structural bridging group R".

The preparation of bridged ligand systems where the bridge is between two atoms on each ligand Z and Z' are generally described in "Ziegler Catalyst," ed. G. Fink, R. Mulhaupt, H.H. Brintzinger, Recent Scientific Innovations and Technological Improvement, Pub. Springer Verlag (1995) pp. 318-320. Preferred bridged ligand systems where the bridge is bonded to two adjacent atoms of the ligands Z and Z' according to formula (d).

As noted previously, a preferred mode of converting the neutral hafnocenes to cationic hafnocene catalyst useful in the present invention involves reaction of the neutral hafnocenes with a triphenylcarbenium boronate. A preferred reactant is triphenylcarbenium tetrakis (pentafluorophenyl) boronate.

The catalysts of the present invention can also be made into efficient pre-polymerized catalysts by the methods disclosed in U.S. Pat. Nos. 3,893,989, 4,200,171, 4,287,328, 4,316,966 and 5,122,583. Essentially, the catalysts are used to polymerize monomer on a small scale. The pre-polymerized catalysts can be prepared in the presence of co-catalysts such as the ones described previously and optionally in the presence of various electron donors.

The pre-polymerized catalysts can then be introduced into a reaction zone containing monomer. The resulting polymerization can show greatly improved catalytic efficiencies. The preferred methods for using pre-polymerized catalysts of the present invention are: (1) contacting a pre-polymerized catalyst of formula (I) with a co-catalyst and introducing the catalyst into a polymerization reaction zone containing monomer and (2) contacting a pre-

polymerized catalyst of formula (I) with a co-catalyst and introducing the catalyst into a polymerization reaction zone containing monomer. The pre-polymerized catalysts of formula (I) can be introduced into the reaction zone in a stream either separately or in conjunction with separate streams containing the co-catalyst and/or electron donors.

Preferred pre-polymerized catalysts of the present invention have a weight ratio of polymer/catalyst of approximately 0.1-100 with ratios of less than 10 being particularly preferred. The syntheses are conveniently done at room temperature or lower in low boiling solvents which are readily evaporated *in vacuo*.

The preferred process of the present invention is in relative high temperature condensed phase polymerization in reactors such as stirred tank reactors or plug-flow reactors or other reactor systems that are intended to be used under condensed phase conditions for the polymerization of olefins. Generally, the polymerizations will be carried out in solution where the monomer(s) and resulting polymers are part of an organic solution. Suitable solvents for solution polymerizations include any standard hydrocarbon solvent well known in the polymerization art including, without limitation, relatively high boiling alkanes such as isopar, relatively high boiling aromatics such as toluene, xylene, or similar aromatic solvents or any other solvent that supports olefin polymerization. Alternative, the monomers themselves can serve as the solvent in what has become known in the art as bulk polymerization. Again, it must be stressed that the reactions is an temperatures and pressures where the polymerizing media is in a non-gaseous or condensed phase. Such phases include traditional liquid phases, but also include critical and supercritical phase conditions.

EXAMPLES

A number of polymerization runs were made using Ti, Zr, and Hf catalyst prepared from the ligand system dimethylsilylenylbis(2-methyl-4-phenylindene), abbreviated DMSMPI below, or the Et[Ind]₂ ligand system. The Zr and Hf catalyst were prepared by reacting the ligand system dianion with ZrCl₄ or HfCl₄, where the dianion is prepared by reacting the neutral ligand with two molar equivalents of an alkyllithium reagent such as nbutyllithium or methyllithium. Hafnocenes on the other hand are preferably prepared by reacting the dianion with TiCl₃ and then bubbling gaseous HCl through the reaction media to affect an oxidation of the Ti(III) system to a Ti(IV) system. The Following data was obtained from a series polymerization runs:

Table 1

Run and Polymerization Data

Run	Catalyst ^a (1×10^{-5} mol)	Propene ^b (atm)	T (°C)	t (min)	Yield (g)	Activity ^c	m.p. (°C)
1	DMSMPI ZrCl ₂	0.875	50	20	4.63	1596552	142.09
2	DMSMPI TiCl ₂	0.875	50	20	1.16	400000	146.23
3	DMSMPI HfCl ₂	0.875	50	20	traces	---	140.12
	Catalyst ^d (1×10^{-6} mol)	Propene (g)	T (°C)	t (min)	Yield (g)	Activity ^e	m.p.
4	DMSMPI ZrCl ₂	29.5	50	30	1.10	314286	160.88
5	DMSMPI TiCl ₂	33.9	50	60	0.650	160494	165.02
6	DMSMPI HfCl ₂	35.6	50	60	0.410	48235	162.44
7	DMSMPI ZrCl ₂	45.1	15	60	1.70	154545	158.40
8	DMSMPI TiCl ₂	51.9	15	60	0.290	24166	164.39
9	Et[Ind] ₂ ZrCl ₂	41.0	15	60	7.30	744898	143.67
10	DMSMPI HfCl ₂	24.3	80	30	5.450	1879310	156.03

	Catalyst (1×10^{-6} mol)	Propene/H ₂ (g)/(mL)	T (°C)	t (min)	Yield (g)	Activity ^g	m.p.
11 ^h	DMSMPI ZrCl ₂	23.5/17	50	10	1.850	19892473	159.22
12	DMSMPI TiCl ₂	23.6/17	50	10	0.300	150000	158.08
13	DMSMPI HfCl ₂	26.6/17	50	10	0.150	35714	160.88

^a Polymerizations run in 30 mL of toluene with an Al:Metal molar ratio of 1000.

^b Partial Pressure of propene

^c gPP/(mol catalyst)(h)(Partial Pressure of Propene)

^d Polymerizations run 100 mL toluene with an Al:Metal molar ratio of 5000

^e gPP/(mol catalyst)(h)(mol/l monomer)

^f Polymerizations run in 100 mL of toluene

^g gPP/(mol catalyst)(h)(mol/l monomer)

^h mol catalyst: 1×10^{-7} ; Al/Metal molar ratio 50000

While in accordance with the patent statutes, the best mode and preferred embodiments of the invention have been described, it is to be understood that the invention is not limited thereto, but rather is to be measured by the scope and spirit of the appended claims.

CLAIMS


1. A process for polymerizing addition polymerizable monomers comprising the step of contacting, in a condensed phase, at least one addition polymerizable monomer capable of forming isotactic polymer units with at least one hafnocene catalyst/catalyst precursor of formula (I):



wherein:

- (a) Z and Z' are the same or different and are a cyclopentadienyl containing ligand, a hetero atom analog of a cyclopentadienyl containing ligand, or an open, 5 centered, 6 π electron ligand;
 - (b) R'' is a structural bridge;
 - (c) Q is a linear or branched alkyl radical, an aryl radical, an alkenyl radical, an alkylaryl radical, an arylalkyl radical or a halogen atom;
 - (d) A is a counterion;
 - (e) k is an integer having a value from 1 to 3;
 - (f) l is an integer having a value from 0 to 2;
 - (g) Z and Z' have at least one β substituent sterically larger than a hydrogen atom;
 - (h) ZR''Z' has C_2 or near C_2 symmetry; and
 - (i) the hafnocene forms polymers having an isotactic selectivity between 90% and 100% for the monomer capable of forming isotactic polymer units.
2. The process of claim 1, wherein the condensed phase is a solution and the contacting occurs at a temperature above 50°C and at a pressure sufficient to maintain the contacting in solution.

3. The process of claim 2, wherein the solution includes a solvent.
4. The process of claim 3, wherein the solvent is an alkane or an aromatic solvent.
5. The process of claim 1, wherein the open, 5 centered, 6 π electron ligand is a ligand of formula (II):



where:

G is a carbon atom, a nitrogen atom, a silicon atom or a phosphorus atom;

J and J' are the same or different and J is a $\text{CR}^3\text{R}^{3'}$ radical, a $\text{SiR}^3\text{R}^{3'}$ radical, a $\text{NR}^{3''}$ radical,

a $\text{PR}^{3''}$ radical, an oxygen atom or a sulfur atom and J' is a $\text{CR}^4\text{R}^{4'}$ radical, a $\text{SiR}^4\text{R}^{4'}$ radical,

a $\text{NR}^{4''}$ radical, a $\text{PR}^{4''}$ radical, an oxygen atom or a sulfur atom;

$\text{R}^1, \text{R}^2, \text{R}^3, \text{R}^{3'}, \text{R}^{3''}, \text{R}^4, \text{R}^{4'}, \text{R}^{4''}$, and R^5 are the same or different and are a hydrogen atom, a linear or branched C1-C20 hydrocarbyl radical, a linear or branched C1-C20 halocarbyl radical, a C1-C20 hydrohalocarbyl radicals, a linear or branched C1-C20 alkoxy radical, a C3-C12 cyclohydrocarbyl radical, a C3-C12 cyclohydrohalocarbyl radical, an aryl radical, an alkylaryl radical, an arylalkyl radical, a silicon hydrocarbyl radical, a germanium hydrocarbyl radical, a phosphorous hydrocarbyl radical, a nitrogen hydrocarbyl radical, a boron hydrocarbyl radical, an aluminum hydrocarbyl radical, or a halogen atom or R^2 and $\text{R}^3, \text{R}^{3'}$ or $\text{R}^{3''}$ and/or R^5 and $\text{R}^4, \text{R}^{4'}$ or $\text{R}^{4''}$ can be


joined together to form a 4 to 6 membered ring or a fused ring system containing 6 to 20 atoms or where R^3 , $R^{3'}$, or $R^{3''}$ and R^4 , $R^{4'}$, or $R^{4''}$ can be joined together to form a non-cyclopentyl ring.

6. The process of claim 1, wherein $l=0$ and $k=2$ and the process further comprises the step of adding an organo-aluminum co-catalyst.
7. The process of claim 1, wherein $l=1$ and $k=1$.
8. A process for polymerizing addition polymerizable monomers comprising the step of contacting, in a condensed phase, at least one addition polymerizable monomer capable of forming isotactic polymer units with at least one hafnocene catalyst/catalyst precursor of formula (I):




where:


- (a) Z and Z' are the same or different ligands of formulas (a-c):



(a)



(b)



(c)

where each R^α is the same or different and is a hydrogen atom or non-hydrogen group and R^β and $R^{\beta'}$ are the same or different and are a non-hydrogen group;

- (b) R'' is structural bridge;


- (c) Q is a linear or branched alkyl radical, an aryl radical, an alkenyl radical, an alkylaryl radical, an arylalkyl radical or a halogen atom;
 - (d) A is a counterion;
 - (e) k is an integer having a value from 1 to 3;
 - (f) l is an integer having a value from 0 to 2;
 - (g) ZR"Z' has C₂ or near C₂ symmetry; and
 - (h) the hafnocene forms polymers having an isotactic selectivity between 90% and 100% for the monomer capable of forming isotactic polymer units.
9. The process of claim 8, wherein the condensed phase is a solution and the contacting occurs at a temperature above 50°C and at a pressure sufficient to maintain the contacting in solution.
 10. The process of claim 9, wherein the solution includes a solvent.
 11. The process of claim 10, wherein the solvent is an alkane or an aromatic solvent.
 12. The process of claim 8, wherein l=0 and k=2 and the process further comprises the step of adding an organo-aluminum co-catalyst.
 13. The process of claim 8, wherein l=1 and k=1.
 14. The process of claim 1, wherein ZR"Z' has C₂ symmetry, the β substituents are sterically equal to or larger than a methyl group, the monomer is propylene and the hafnocene generates isotactic polypropylene having a melting point above 156°C.
 15. The process of claim 1, wherein the hafnocene generates isotactic polypropylene having a melting point above 160°C.

16. A process for polymerizing addition polymerizable monomers comprising the step of contacting propylene with at least one hafnocene catalyst/catalyst precursor of formula (I):




wherein:


- (a) Z and Z' are the same ligands of formulas (a-c):



(a)



(b)



(c)

where each R^α is the same or different and is a hydrogen atom or non-hydrogen group and the R^β radicals or the $R^{\beta'}$ radicals are the same and are sterically equal to or larger than a methyl group;

- (b) R'' is structural bridge;
- (c) Q is a linear or branched alkyl radical, an aryl radical, an alkenyl radical, an alkylaryl radical, an arylalkyl radical or a halogen atom;
- (d) A is a counterion;
- (e) k is an integer having a value from 1 to 3;
- (f) l is an integer having a value from 0 to 2; and
- (g) $\text{ZR}''\text{Z}'$ has C_2 symmetry; and
- (h) the hafnocene generates isotactic polypropylene having a melting point temperature above 156°C .

17. The process of claim 16, wherein the hafnocene generates isotactic polypropylene having a melting point temperature above 160°C.
18. The process of claim 16, wherein the condensed phase is a solution and the contacting occurs at a temperature above 50°C and at a pressure sufficient to maintain the contacting in solution.
19. The process of claim 18, wherein the solution includes a solvent.
20. The process of claim 19, wherein the solvent is an alkane or an aromatic solvent.
21. The process of claim 16, wherein $l=0$ and $k=2$ and the process further comprises the step of adding an organo-aluminum co-catalyst.
22. The process of claim 8, wherein $l=1$ and $k=1$.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP 98/02741

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C08F4/64 C08F10/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 616 664 A (TIMMERS FRANCIS J ET AL) 1 April 1997 see example 40 see column 29, line 44 - column 30, line 7 ---	1-4,8-11
X	EP 0 748 824 A (CHISSO CORP) 18 December 1996 see example 1 see page 10; example 1; table 1 see page 6, line 21 - line 27 ---	1,6,8, 12, 14-17,21
X	WO 97 22635 A (EXXON CHEMICAL PATENTS INC) 26 June 1997 see page 22, line 1 - page 23, line 17 see examples 5,6; table 3 --- -/--	1-4,8-11

Further documents are listed in the continuation of box C.

Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

Date of mailing of the international search report

1 October 1998

12/10/1998

Name and mailing address of the ISA
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Fischer, B

INTERNATIONAL SEARCH REPORT

Inter. Patent Application No

PCT/EP 98/02741

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X A	WO 97 14727 A (AMOCO CORP) 24 April 1997 see claims 1,5,8,13 see page 9, line 4 - line 12 see page 11, line 1 - page 14, line 8 -----	1,6,8,12 3,4,10, 11
A	EP 0 544 308 A (SHOWA DENKO KK) 2 June 1993 see example 3 see page 9, line 42 - line 46 -----	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 98/02741

Patent document cited in search report	A	Publication date	Patent family member(s)	Publication date
US 5616664	A	01-04-1997	AU 693578 B	02-07-1998
			AU 3009095 A	04-03-1996
			BR 9508889 A	30-09-1997
			CA 2195789 A	15-02-1996
			CN 1156997 A	13-08-1997
			CZ 9700316 A	14-05-1997
			EP 0775148 A	28-05-1997
			FI 970429 A	31-01-1997
			HU 77589 A	29-06-1998
			JP 10503517 T	31-03-1998
			NO 970441 A	26-03-1997
			PL 318434 A	09-06-1997
			WO 9604290 A	15-02-1996
			US 5527929 A	18-06-1996

EP 0748824	A	18-12-1996	JP 8325327 A	10-12-1996
			CN 1147523 A	16-04-1997

WO 9722635	A	26-06-1997	WO 9722639 A	26-06-1997

WO 9714727	A	24-04-1997	US 5756609 A	26-05-1998

EP 0544308	A	02-06-1993	JP 5209013 A	20-08-1993
			JP 6087922 A	29-03-1994
			JP 5148284 A	15-06-1993
			DE 69224463 D	26-03-1998
			DE 69224463 T	09-07-1998
			US 5349032 A	20-09-1994
			US 5329031 A	12-07-1994
			JP 5208987 A	20-08-1993
