

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
20 October 2005 (20.10.2005)

PCT

(10) International Publication Number
WO 2005/097678 A1

- (51) International Patent Classification⁷: **C01B 33/143**, D21H 17/68
- (21) International Application Number: PCT/SE2005/000488
- (22) International Filing Date: 5 April 2005 (05.04.2005)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
60/559,958 7 April 2004 (07.04.2004) US
60/559,965 7 April 2004 (07.04.2004) US
04445049.2 16 April 2004 (16.04.2004) EP
04445048.4 16 April 2004 (16.04.2004) EP
- (71) Applicant (for all designated States except US): **AKZO NOBEL N.V.** [NL/NL]; P.O. Box 9300, NL-6800 SB Arnhem (NL).
- (71) Applicant (for SE only): **EKA CHEMICALS AB** [SE/SE]; S-445 80 Bohus (SE).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **NYANDER, Johan** [SE/SE]; Jordgränd 29, S-192 74 Sollentuna (SE). **MANKIN, Glenn** [US/US]; 514 Granite Point, Martinez, GA 30907 (US).
- (74) Agent: **NYANDER, Johan**; Eka Chemicals AB, Patent Department, P.O. Box 11556, S-100 61 Stockholm (SE).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: SILICA-BASED SOLS AND THEIR PRODUCTION AND USE

(57) Abstract: The present invention relates to a process for producing an aqueous silica-based sol which comprises: (a) providing a cationic ion exchange resin having at least part of its ion exchange capacity in hydrogen form; (b) bringing said ion exchange resin in contact with an aqueous alkali metal silicate to form an aqueous slurry; (c) stirring said aqueous slurry until the pH of the aqueous phase is in the range of from 5.0 to 11.5; and/or alternatively, stirring said aqueous slurry to allow particle aggregation or microgel formation corresponding to an S value up to 45 %, and obtain a pH of the aqueous phase of at least 5.0; (d) adjusting the pH of said aqueous phase to above 9.0 using one or more materials comprising at least one aluminium compound; and (e) separating said ion exchange resin from the aqueous phase after step (c) or after step (d). The invention also relates to a silica-based sol having an S value within the range of from 15 to 25 %, mole ratio Si:Al in the range of from 20:1 to 50:1, mole ratio Si:X, where X = alkali metal, in the range of from 5:1 to 17:1, SiO₂ content of at least 5 % by weight and containing silica-based particles having a specific surface area of at least 300 m²/g. The invention further relates to process for producing paper which comprises: (i) providing an aqueous suspension comprising cellulosic fibres; (j) adding to the suspension one or more drainage and retention aids comprising a silica-based sol according to the invention; and (k) dewatering the obtained suspension to provide a sheet or web of paper.



WO 2005/097678 A1

SILICA-BASED SOLS AND THEIR PRODUCTION AND USEField of the Invention

5 The present invention generally relates to aqueous silica-based sols suitable for use in papermaking. More particularly, the invention relates to silica-based sols, their production and use in papermaking. The present invention provides an improved method of producing silica-based sols with high stability and SiO₂ contents as well as improved drainage performance.

10

Background of the Invention

In the papermaking art, an aqueous suspension containing cellulosic fibres and optional fillers and additives, referred to as stock, is fed into a headbox which ejects the stock onto
15 a forming wire. Water is drained from the stock so that a wet web of paper is formed on the wire, and the web is further dewatered and dried in the drying section of the paper machine. Drainage and retention aids are conventionally introduced into the stock in order to facilitate drainage and to increase adsorption of fine particles onto the cellulosic fibres so that they are retained with the fibres on the wire.

20

Sols of silica-based particles are widely used as drainage and retention aids in combination with charged organic polymers. Such additive systems are among the most efficient now in use in the papermaking industry. One of the parameters affecting the properties and performance of silica-based sols is the specific surface area; stable, high-performance
25 silica-based sols usually contain particles with a specific surface area of at least 300 m²/g. Another parameter is the S value, which indicates the degree of aggregate or microgel formation; a lower S-value is indicative of a higher degree of aggregation. While high surface areas and a certain degree of aggregate or microgel formation may be advantageous from a performance point of view, very high surface areas and extensive particle aggregation or
30 microgel formation result in considerably decreased stability of silica-based sols, thereby making extreme dilution of the sols necessary so as to avoid gel formation.

U.S. Patent No. 5,368,833 discloses a silica sol comprising silica particles having a specific surface area within the range of from 750 to 1,000 m²/g which are surface-modified with
35 aluminium to a degree of from 2 to 25 % substitution of silicon atoms, and wherein the sol has an S value within the range of from 8 to 45 %. Said patent also discloses a process for producing the silica sol which comprises the steps of acidifying a water glass solution to a pH within the range of from 1 to 4; alkalisng the acid sol at an SiO₂ content within the

range of from 7 to 4.5 % by weight; allowing particle growth of the sol to a specific surface area within the range of from 750 to 1,000 m²/g; and subjecting the sol to aluminium modification.

5 U.S. Patent No. 5,603,805 discloses silica sols having an S value within the range of from 15 to 40 % comprising anionic silica particles, said silica particles optionally being aluminium modified, and having a specific surface area within the range of from 300 to 700 m²/g. Said patent also discloses a process for producing the silica sol comprising the steps of acidifying a water glass solution to a pH within the range of from 1 to 4; alkalisating the
10 acid sol at an SiO₂ content within the range of from 7 to 5 % by weight; alternatively alkalisating of the acid sol to a pH value between 7 and 9; and particle growth of the sol to a specific surface area within the range of from 300 to 700 m²/g; and optionally followed by aluminium modification.

15 International Patent Appln. Publ. No. WO 98/56715 discloses a process for preparing an aqueous polysilicate microgel which comprises mixing an aqueous solution of an alkali metal silicate with an aqueous phase of a silica-based material having a pH of 11 or less. The polysilicate microgel is used as a flocculating agent in combination with at least one cationic or amphoteric polymer in the production of pulp and paper and for water
20 purification.

International Patent Appln. Publ. No. WO 00/66492 discloses a process for the production of an aqueous sol containing silica-based particles which comprises acidifying an aqueous silicate solution to a pH of from 1 to 4 to form an acid sol; alkalisating the acid sol in a first
25 alkalisating step; allowing particle growth of the alkalisated sol for at least 10 minutes and/or heat-treating the alkalisated sol at a temperature of at least 30°C; alkalisating the obtained sol in a second alkalisating step; and optionally modifying the silica-based sol with, for example, aluminium.

30 U.S. Patent No. 6,372,806 discloses a process for preparing a stable colloidal silica having an S-value of from 20-50 and wherein said silica has a surface area of greater than 700 m²/g comprising: (a) charging a reaction vessel with a cationic ion exchange resin having at least 40 percent of its ion exchange capacity in the hydrogen form wherein said reaction vessel has means for separating said colloidal silica from said ion exchange resin; (b)
35 charging said reaction vessel with an aqueous alkali metal silicate having a mole ratio of SiO₂ to alkali metal oxide in the range of from 15:1 to 1:1 and a pH of at least 10.0; (c) stirring the contents of said reaction vessel until the pH of said contents is in the range of from 8.5 to 11.0; (d) adjusting the pH of the contents of said reaction vessel to above 10.0

using an additional amount of said alkali metal silicate; and (e) separating the resulting colloidal silica from said ion exchange resin while removing said colloidal silica from said reaction vessel.

- 5 U.S. Patent No. 5,176,891 discloses a method for the production of water soluble polyaluminosilicate microgels having a surface area of at least about 1,000 m²/g, comprising the steps of (a) acidifying a dilute solution of alkali metal silicate containing about 0.1 to 6 wt. % SiO₂ to a pH of between 2 and 10.5 to produce polysilicic acid; followed by (b) reacting a water soluble aluminate with the polysilicic acid before the
10 polysilicic acid has gelled such that a product with an alumina/silica mole ratio greater than about 1/100 is obtained; and then (c) diluting the reaction mix before gelation has occurred to the equivalence of about 2.0 wt. % SiO₂ or less to stabilize the microgels.

It would be advantageous to be able to provide silica-based sols with high stability and SiO₂
15 contents as well as improved drainage performance. It would also be advantageous to be able to provide improved processes for the preparation of silica-based sols with stability and SiO₂ contents as well as improved drainage performance. It would also be advantageous to be able to provide a papermaking process with improved drainage.

20

Summary of the Invention

The present invention is generally directed to a process for producing an aqueous silica-based sol which comprises:

- 25 (a) providing a cationic ion exchange resin having at least part of its ion exchange capacity in hydrogen form;
- (b) bringing said ion exchange resin in contact with an aqueous alkali metal silicate to form an aqueous slurry;
- (c) stirring said aqueous slurry until the pH of the aqueous phase is in the range of
30 from 5.0 to 11.5; and/or, alternatively, stirring said aqueous slurry to allow particle aggregation or microgel formation corresponding to an S value up to 45 %, and obtain a pH of the aqueous phase of at least 5.0;
- (d) adjusting the pH of said aqueous phase to above 9.0 using one or more materials comprising at least one aluminium compound; and
- 35 (e) separating said ion exchange resin from the aqueous phase after step (c) or after step (d).

The invention is further generally directed to a process for producing an aqueous silica-based sol which comprises:

- (a) providing a reaction vessel;
- (b) providing in said reaction vessel:
 - 5 (i) a cationic ion exchange resin having at least part of its ion exchange capacity in hydrogen form, and
 - (ii) an aqueous alkali metal silicate, to form an aqueous slurry;
- (c) stirring said aqueous slurry until the pH of the aqueous phase is in the range of
10 from 5.0 to 11.5; and/or, alternatively, stirring said aqueous slurry to allow particle aggregation or microgel formation corresponding to an S value up to 45 %, and obtain a pH of the aqueous phase of at least 5.0;
- (d) adding one or more materials comprising at least one aluminium compound to the aqueous phase obtained after step (c) to form an aqueous phase having a pH of
15 above 9.0;
- (e) separating said ion exchange resin from the aqueous phase after step (c) or after step (d).

The invention is further directed to a silica-based sol obtainable by the processes. The
20 invention is further generally directed to a silica-based sol and, in particular, a silica-based sol having an S value in the range of from 15 to 25 %, mole ratio Si:Al in the range of from 20:1 to 50:1, mole ratio Si:X, where X = alkali metal, in the range of from 5:1 to 17:1, SiO₂ content of at least 5 % by weight and containing silica-based particles having a specific surface area of at least 300 m²/g.

25

The invention is further directed to uses of the silica-based sol according to the invention, in particular as a drainage and retention aid in papermaking and for water purification.

The invention is further generally directed to a process for producing paper which comprises

- 30 (a) providing an aqueous suspension comprising cellulosic fibres;
- (b) adding to the suspension one or more drainage and retention aids comprising a silica-based sol according to the invention as defined herein; and
- (c) dewatering the obtained suspension to provide a sheet or web of paper.

Detailed Description of the Invention

In accordance with the present invention there is provided silica-based sols which are suitable for use as flocculating agents in water purification and as drainage and retention aids in papermaking. The silica-based sols of the invention exhibit good stability over extended periods of time, notably high surface area stability and high stability to avoid complete gel formation. The silica-based sols further result in very good drainage and retention when used in papermaking, in particular improved drainage. Hereby the present invention makes it possible to increase the speed of the paper machine and to use a lower dosage of additive to give a corresponding drainage effect, thereby leading to an improved papermaking process and economic benefits. The silica-based sols of the invention can be prepared by a process that is simple, quick and easy to control and regulate, and the process makes it possible to utilize simple and less expensive production equipment. Hereby the silica-sols of the invention can be produced by a process that is simplified, improved and more economic.

The ion exchange resin used in the process is cationic and has at least part of its ion exchange capacity in the hydrogen form, i.e. an acid cationic ion exchange resin, preferably a weak acid cationic ion exchange resin. Suitably, the ion exchange resin has at least 40 % of its ion exchange capacity in the hydrogen form, preferably at least 50 %. Suitable ion exchange resins are provided on the market by several manufacturers, for example Amberlite® IRC84SP from Rohm & Haas. Preferably, a reaction vessel equipped with means for mixing, e.g. a stirrer, is charged with the ion exchange resin. Preferably, the ion exchange resin is regenerated by addition of an acid, e.g. sulphuric acid, preferably according to manufacturer's instruction.

Step (b) of the process comprises bringing together the cationic ion exchange resin with an aqueous alkali metal silicate. Suitably, this is achieved by adding the ion exchange resin and aqueous alkali metal silicate to the reaction vessel. Preferably, the reaction vessel containing regenerated ion exchange resin is charged with the aqueous alkali metal silicate whereby an aqueous slurry is formed. Usually, the aqueous alkali metal silicate is added to a reaction vessel containing ion exchange resin having at least part of its ion exchange capacity in hydrogen form at a rate in the range of from 0.5 to 50 g SiO₂ per minute and kg ion exchange resin, calculated as ion exchange resin having 100 % of its ion exchange capacity in hydrogen form, suitably from 1 to 35, and preferably from 2 to 20. Alternatively, a reaction vessel containing the aqueous alkali metal silicate is charged with the regenerated ion exchange resin whereby an aqueous slurry is formed.

Examples of suitable aqueous alkali metal silicates or water glass include conventional materials, e.g. lithium, sodium and potassium silicates, preferably sodium silicate. The molar ratio of silica to alkali metal oxide, e.g. SiO_2 to Na_2O , K_2O or Li_2O , or a mixture thereof, in the silicate solution can be in the range of from 15:1 to 1:1, suitably in the range of from 4.5:1 to 1.5:1, preferably from 3.9:1 to 2.5:1. The aqueous alkali metal silicate used can have an SiO_2 content of from about 2 to about 35 % by weight, suitably from about 5 to about 30 % by weight, and preferably from about 15 to about 25 % by weight. The pH of the aqueous alkali metal silicate is usually above 11, typically above 12.

Step (c) of the process comprises stirring the aqueous slurry formed in step (b) until the pH of the aqueous phase is in the range of from 5.0 to 11.5. Alternatively, or additionally, step (c) of the process comprises stirring said aqueous slurry to allow particle aggregation or microgel formation, corresponding to an S value up to 45 %, and to obtain pH of the aqueous phase of at least 5.0. Suitably stirring is carried out until the pH of the aqueous phase is in the range of from 6.0 to 11.0, preferably to a pH in the range of from 6.5 to 10.0. In one preferred embodiment of the invention, the slurry is stirred until the pH of the aqueous phase is up to 8.0, suitably in the range of from 6.0 to 8.0, preferably from 6.5 to 7.5. In another preferred embodiment of the invention, the slurry is stirred until the pH of the aqueous phase is at least 8.0, suitably in the range of from 8.0 to 11.0, preferably from 9.0 to 10.0. Preferably, particle growth takes place while stirring the aqueous slurry. The silica-based particles formed usually have a specific surface area of at least $300 \text{ m}^2/\text{g}$, preferably at least $700 \text{ m}^2/\text{g}$. The specific surface area is suitably up to $1,500 \text{ m}^2/\text{g}$, preferably up to $1,000 \text{ m}^2/\text{g}$. Preferably, the slurry is stirred so as to achieve particle aggregation and microgel formation, usually corresponding to an S value in the range of from 5 to 45 %, suitably from 8 to 35 %, preferably from 10 to 25 % and most preferably from 15 to 23 %. The stirring usually takes place during a period of time of from 5 to 240 minutes, preferably from 15 to 120 minutes.

Step (c) of the process can be carried out simultaneously with and/or after step (b). In a preferred embodiment, the aqueous alkali metal silicate is added under stirring to the reaction vessel containing ion exchange resin having at least part of its ion exchange capacity in hydrogen form and then, after completed addition, the stirring continues to achieve the pH and/or particle aggregation or microgel formation as described above. In another preferred embodiment, the aqueous alkali metal silicate is added under stirring to the reaction vessel containing ion exchange resin having at least part of its ion exchange capacity in hydrogen form to achieve the pH and/or particle aggregation or microgel formation as described above.

Step (d) of the process comprises adding to the aqueous phase one or more materials comprising at least one aluminium compound. Suitably, the pH of the aqueous phase is adjusted to above 9.0, preferably above 10.0; suitably in the range of from 9.2 to 11.5, preferably from 9.5 to 11.2, and most preferably from 10.0 to 11.0. Preferably, the pH is adjusted by adding one or more materials comprising at least one aluminium compound, preferably the pH is raised by adding one or more alkaline materials comprising at least one aluminium compound. In a preferred embodiment, there is added an aluminium compound. In another preferred embodiment, there is added an alkaline material and an aluminium compound. Examples of suitable aluminium compounds include alkaline aluminium salts as well as neutral and essentially neutral aluminium salts. Examples of suitable alkaline aluminium salts include aluminates, suitably aqueous aluminates, e.g. sodium and potassium aluminates, preferably sodium aluminate. Examples of neutral and essentially neutral aluminium salts include aluminium nitrate. Examples of suitable alkaline materials include aqueous alkali metal silicates, e.g. any of those defined above; aqueous alkali metal hydroxides, e.g. lithium, sodium and potassium hydroxides, preferably sodium hydroxide; ammonium hydroxide; suitably sodium silicate or hydroxide, preferably sodium silicate. When using two or more materials comprising an alkaline material and aluminium compound, the materials can be added in any order, preferably the alkaline material is added first followed by adding the aluminium compound. In a preferred embodiment, aqueous alkali metal silicate is added first and then aqueous sodium aluminate is added. In another preferred embodiment, aqueous alkali metal hydroxide is added first and then aqueous sodium aluminate is added. The addition of aluminium compound provides an aluminated silica-based sol. Suitably, the addition of aluminium compound results in aluminium modification of the silica-based particles, preferably the particles are surface-modified by aluminium. The amount of aluminium compound used can be varied within wide limits. Usually the amount of aluminium compound added corresponds to a mole ratio of Si:Al of from 10:1 to 100:1, suitably from 20:1 to 50:1, preferably from 25:1 to 35:1, and most preferably from 25:1 to 30:1.

In step (d) of the process, when using an aqueous alkali metal silicate to adjust the pH of the aqueous phase, the weight ratio of alkali metal silicate used in step (b) to alkali metal silicate used in step (d) can vary within wide limits; usually the ratio is in the range 99:1 to 1:9, suitably from 19:1 to 1:2, preferably from 4:1 to 1:1.

In step (e) of the process, the ion exchange resin is separated from the aqueous phase, for example by filtration. This can be done after step (c), for example after step (c) but before step (d), or after step (d). It is also possible to separate the ion exchange resin from the aqueous phase during step (d). For example, the ion exchange resin can be separated

after adding the alkaline material but before adding the aluminium compound. It is also possible to add part of one alkaline material, e.g. aqueous alkali metal silicate, then separating the ion exchange resin from the aqueous phase followed by adding the remaining part of the alkaline material. Preferably, the ion exchange resin is separated
5 from the aqueous phase after step (d).

The concentration of the aqueous starting materials used in the process, e.g. the aqueous alkali metal silicate, aqueous alkali metal hydroxide and aqueous sodium aluminate, is preferably adjusted so as to provide a silica-based sol which usually has a SiO₂ content of
10 at least 3 % by weight, suitably at least 5 %, preferably at least 6 %, most preferably at least 7.5 %, and suitably up to 20 % by weight, preferably up to 15 % by weight. The silica-based sol produced by the process of this invention can have the properties defined hereinafter.

The aqueous silica-based sol according to the invention contains silica-based particles, i.e.
15 particles based on silica or SiO₂, that are preferably anionic and colloidal, i.e., in the colloidal range of particle size. The particles are suitably modified with aluminium, preferably surface modified with aluminium. The silica-based sol of the invention can have a mole ratio of Si:Al of from 10:1 to 100:1, suitably from 20:1 to 50:1, preferably from 25:1 to 35:1, and most preferably from 25:1 to 30:1.

20 The silica-based sol of the invention can have an S value in the range of from 10 to 50 %, suitably from 12 to 40 %, preferably from 15 to 25 %, and most preferably from 17 to 24 %. The S-value is measured and calculated as described by Iler & Dalton in J. Phys. Chem. 60(1956), 955-957. The S-value indicates the degree of aggregate or microgel formation and
25 a lower S-value is indicative of a higher degree of aggregation.

The silica-based particles present in the sol can have a specific surface area of at least 300 m²/g, suitably at least 700 m²/g, preferably at least 750 m²/g. The specific surface area is usually up to 1,000 m²/g, suitably up to 950 m²/g. The specific surface area is measured
30 by means of titration with NaOH as described by Sears in Analytical Chemistry 28(1956):12, 1981-1983, after appropriate removal of or adjustment for any compounds present in the sample that may disturb the titration like aluminium and boron compounds, for example as described by Sears and in U.S. Patent No. 5,176,891.

35 The silica-based sol of the invention usually has a mole ratio of Si:X, where X = alkali metal, of at least 3:1, suitably at least 4:1, preferably at least 5:1 and most preferably at least 6:1. The mole ratio of Si:X, where X = alkali metal, is usually up to 25:1, suitably up to 20:1, preferably up to 17:1, more preferably up to 15:1 and most preferably up to 10:1.

The silica-based sol of this invention is preferably stable. Suitably, the sol maintains a specific surface area of at least 300 m²/g, preferably at least 700 m²/g, for at least 3 months on storage or ageing at 20 °C in dark and non-agitated conditions. Suitably, the sol
5 maintains an S value in the range of from 10 to 50 %, preferably from 12 to 40 %, for at least 3 months on storage or ageing at 20 °C in dark and non-agitated conditions.

The silica-based sol according to this invention is suitable for use as a flocculating agent, for example in the production of pulp and paper, notably as a drainage and retention aid, and
10 within the field of water purification, both for purification of different kinds of waste water and for purification specifically of white water from the pulp and paper industry. The silica-based sols can be used as a flocculating agent, notably as a drainage and retention aid, in combination with organic polymers which can be selected from anionic, amphoteric, non-ionic and cationic polymers and mixtures thereof. The use of such polymers as flocculating agents
15 and as drainage and retention aids is well known in the art. The polymers can be derived from natural or synthetic sources, and they can be linear, branched or cross-linked. Examples of generally suitable main polymers include anionic, amphoteric and cationic starches; anionic, amphoteric and cationic acrylamide-based polymers, including essentially linear, branched and cross-linked anionic and cationic acrylamide-based polymers; as well as
20 cationic poly(diallyldimethyl ammonium chloride); cationic polyethylene imines; cationic polyamines; cationic polyamideamines and vinylamide-based polymers, melamine-formaldehyde and urea-formaldehyde resins. Suitably, the silica-based sols are used in combination with at least one cationic or amphoteric polymer, preferably cationic polymer. Cationic starch and cationic polyacrylamide are particularly preferred polymers and they can
25 be used singly, together with each other or together with other polymers, e.g. other cationic and/or anionic polymers. The molecular weight of the polymer is suitably above 1,000,000 and preferably above 2,000,000. The upper limit is not critical; it can be about 50,000,000, usually 30,000,000 and suitably about 25,000,000. However, the molecular weight of polymers derived from natural sources may be higher.

30 The present silica-based sol can also be used in combination with cationic coagulant(s), either with or without the co-use of the organic polymer(s) described above. Examples of suitable cationic coagulants include water-soluble organic polymeric coagulants and inorganic coagulants. The cationic coagulants can be used singly or together, i.e. a polymeric
35 coagulant can be used in combination with an inorganic coagulant.

Examples of suitable water-soluble organic polymeric cationic coagulants include cationic polyamines, polyamideamines, polyethylene imines, dicyandiamide condensation polymers

and polymers of water soluble ethylenically unsaturated monomer or monomer blend which is formed of 50 to 100 mole % cationic monomer and 0 to 50 mole % other monomer. The amount of cationic monomer is usually at least 80 mole %, suitably 100 %. Examples of suitable ethylenically unsaturated cationic monomers include dialkylaminoalkyl (meth)-
5 acrylates and -acrylamides, preferably in quaternised form, and diallyl dialkyl ammonium chlorides, e.g. diallyl dimethyl ammonium chloride (DADMAC), preferably homopolymers and copolymers of DADMAC. The organic polymeric cationic coagulants usually have a molecular weight in the range of from 1,000 to 700,000, suitably from 10,000 to 500,000. Examples of
10 suitable inorganic coagulants include aluminium compounds, e.g. alum and polyaluminium compounds, e.g. polyaluminium chlorides, polyaluminium sulphates, polyaluminium silicate sulphates and mixtures thereof.

The components of the drainage and retention aids according to the invention can be added to the stock in conventional manner and in any order. When using drainage and
15 retention aids comprising a silica-based sol and organic polymer, it is preferred to add the organic polymer to the stock before adding the silica-based sol, even if the opposite order of addition may be used. It is further preferred to add the organic polymer before a shear stage, which can be selected from pumping, mixing, cleaning, etc., and to add the silica-based sol after that shear stage. When using a cationic coagulant, it is preferably added to
20 the cellulosic suspension before the addition of the silica-based sol, preferably also before the addition of the organic polymer(s).

The components of the drainage and retention aids according to the invention are added to the stock to be dewatered in amounts which can vary within wide limits depending on, inter
25 alia, type and number of components, type of furnish, filler content, type of filler, point of addition, etc. Generally the components are added in amounts that give better drainage and retention than is obtained when not adding the components. The silica-based sol is usually added in an amount of at least 0.001% by weight, often at least 0.005% by weight, calculated as SiO_2 and based on dry furnish, i.e. dry cellulosic fibres and optional fillers, and the upper
30 limit is usually 1.0% and suitably 0.5% by weight. The organic polymer is usually added in an amount of at least 0.001%, often at least 0.005% by weight, based on dry furnish, and the upper limit is usually 3% and suitably 1.5% by weight. When using a cationic polymeric coagulant, it can be added in an amount of at least 0.05%, based on dry furnish. Suitably, the amount is in the range of from 0.07 to 0.5%, preferably in the range from 0.1 to 0.35%. When
35 using an aluminium compound as the inorganic coagulant, the total amount added is usually at least 0.05%, calculated as Al_2O_3 and based on dry furnish. Suitably the amount is in the range of from 0.1 to 3.0%, preferably in the range from 0.5 to 2.0%.

Further additives which are conventional in papermaking can of course be used in combination with the additives according to the invention, such as, for example, dry strength agents, wet strength agents, optical brightening agents, dyes, sizing agents like rosin-based sizing agents and cellulose-reactive sizing agents, e.g. alkyl and alkenyl ketene dimers and ketene
5 multimers, alkyl and alkenyl succinic anhydrides, etc. The cellulosic suspension, or stock, can also contain mineral fillers of conventional types such as, for example, kaolin, china clay, titanium dioxide, gypsum, talc and natural and synthetic calcium carbonates such as chalk, ground marble and precipitated calcium carbonate.

10 The process of this invention is used for the production of paper. The term "paper", as used herein, of course include not only paper and the production thereof, but also other cellulosic sheet or web-like products, such as for example board and paperboard, and the production thereof. The process can be used in the production of paper from different types of suspensions of cellulose-containing fibres and the suspensions should suitably contain at
15 least 25% by weight and preferably at least 50% by weight of such fibres, based on dry substance. The suspension can be based on fibres from chemical pulp such as sulphate, sulphite and organosolv pulps, mechanical pulp such as thermomechanical pulp, chemothermomechanical pulp, refiner pulp and groundwood pulp, from both hardwood and softwood, and can also be based on recycled fibres, optionally from de-inked pulps, and mixtures
20 thereof. The pH of the suspension, the stock, can be within the range of from about 3 to about 10. The pH is suitably above 3.5 and preferably within the range of from 4 to 9.

The invention is further illustrated in the following example which, however, is not intended to limit the same. Parts and % relate to parts by weight and % by weight, respectively,
25 unless otherwise stated.

Examples

The following equipment and starting materials were used throughout the Examples:

- 30 (a) Reactor equipped with a stirrer;
(b) Ion exchange resin Amberlite® IRC84SP (available from Rohm & Haas) which was regenerated with sulphuric acid according to manufacturer's instruction;
(c) Aqueous sodium silicate solution having a SiO₂ content of about 21 wt. % and mole ratio of SiO₂ to Na₂O of 3.32;
35 (d) Aqueous sodium aluminate solution containing 2.44 wt. % Al₂O₃; and
(e) Aqueous sodium hydroxide solution having a concentration of 5 moles per kilo.

Example 1

This example illustrates the preparation of a silica-based sol according to the invention: Regenerated ion exchange resin (471 g) and water (1,252 g) were charged into a reactor. 5 The obtained slurry was stirred vividly and heated to a temperature of 30 °C. Aqueous sodium silicate (298 g) was then added to the slurry at a rate of 5 g/min. After the addition of sodium silicate, the pH of the slurry was about 7.3. The slurry was then stirred for another 44 minutes, whereupon the pH of the aqueous phase was 6.9. Thereafter additional aqueous sodium silicate (487 g) was added to the slurry at a rate of 5 g/min, 10 whereupon the pH of the aqueous phase was 10.4. The obtained aqueous phase was separated from the ion exchange resin. Aqueous sodium aluminate (52 g) was added to the sol (527.4 g) under vigorous stirring during a period of 10 min.

The obtained silica-based sol had the following properties: SiO₂ content = 7.7 wt. %; mole 15 ratio Si:Na = 7.5; mole ratio Si:Al = 26.2; pH = 10.7; specific surface area = 790 m²/g; and S value = 18 %.

Example 2

20 This example illustrates the preparation of another silica-based sol according to the invention: Ion exchange resin (1,165 g), which was regenerated to approximately 40 % of its ion exchange capacity, and water (686 g) were charged into a reactor. The obtained aqueous slurry was stirred vividly. Aqueous sodium silicate (989 g) was then added to the slurry during a period of 10 min. After the addition of sodium silicate, the pH of the 25 aqueous slurry was about 10.7. The slurry was then stirred for 22 minutes, whereupon the resulting pH of the aqueous slurry was 9.8. Thereafter additional aqueous sodium silicate (128 g) was added to the slurry during 1 min, whereupon the pH of the aqueous slurry was 10.3. The aqueous phase was separated from the ion exchange resin. Aqueous sodium aluminate (57 g) was added to the aqueous phase (463 g) under vigorous stirring at a rate 30 of 5.7 g/min.

The obtained silica-based sol had the following properties: SiO₂ content = 10.3 wt. %; mole 35 ratio Si:Na = 4.9; mole ratio Si:Al = 33.6; pH = 11.0; specific surface area = 1,000 m²/g; and S value = 23 %.

Example 3

This example illustrates the preparation of yet another silica-based sol according to the invention: Regenerated ion exchange resin (600 g) and water (1,600 g) were charged into a reactor. The obtained aqueous slurry was stirred vividly and heated to a temperature of 30 °C. Aqueous sodium silicate (764 g) was then added to the slurry at a rate of 6.8 g/min. After the addition of sodium silicate, the pH of the aqueous slurry was about 8, whereupon the ion exchange resin was separated from the aqueous phase. Aqueous sodium hydroxide (30 g) was added to the aqueous phase at the rate of 10 g/min, whereupon the pH of the aqueous phase was 10. Aqueous sodium aluminate (83 g) was then added to the aqueous phase (776 g) under vigorous stirring during a period of 10 min.

The obtained silica-based sol had the following properties: SiO₂ content = 6.1 wt. %; mole ratio Si:Na = 5.9; mole ratio Si:Al = 20.3; pH = 10.9; specific surface area = 930 m²/g; and S value = 22 %.

Example 4

This example illustrates the preparation of another silica-based sol according to the invention: Ion exchange resin (1,785 g), which was regenerated to approximately 40 % of its ion exchange capacity, and water (920 g) were charged into a reactor. The obtained aqueous slurry was stirred vividly. Aqueous sodium silicate (1,390 g) was then added to the slurry during a period of 10 min. After the addition of sodium silicate, the pH of the aqueous slurry was about 10.4. The slurry was then stirred for 25 minutes, whereupon the pH of the aqueous slurry was 9.2. The ion exchange resin was separated from the aqueous phase. Aqueous sodium hydroxide (15.5 g) was added to the aqueous phase during a period of about 2 min, whereupon the pH of the aqueous phase was 10. Aqueous sodium aluminate (56.7 g) was then added to the aqueous phase (483 g) at a rate of 5.7 g/min under vigorous stirring.

The obtained silica-based sol has the following properties: SiO₂ content = 9.8 wt. %; mole ratio Si:Na = 6.1; mole ratio Si:Al = 30.2; pH = 10.8; specific surface area = 940 m²/g; and S value = 22 %.

Example 5

The following silica-based sols, Ref. 1 to Ref. 4, were prepared for comparison purposes:

5 Ref. 1 is a silica-based sol prepared according to the disclosure of Example 4 of U.S. Patent Nos. 6,372,089 and 6,372,806.

10 Ref. 2 is a silica-based sol prepared according to the disclosure of U.S. Patent No. 5,368,833 which had an S-value of about 25 %, a mole ratio of Si:Al of about 19 and contained silica particles with a specific surface area of about 900 m²/g SiO₂ which were surface-modified with aluminium.

15 Ref. 3 is a silica-based sol prepared according to the disclosure of U.S. Patent No. 5,603,805 with an S-value of 34 % and contained silica particles with a specific surface area of about 700 m²/g.

20 Ref. 4 is a silica-based sol prepared according to the disclosure of U.S. Patent No. 5,368,833 which had an S-value of 20 %, a mole ratio of Si:Al of about 18 and contained silica particles with a specific surface area of about 820 m²/g SiO₂ which were surface-modified with aluminium.

Example 6

25 In the following tests, drainage performance of the silica-based sols according to Examples 1 and 2 ("Ex. 1" and "Ex. 2", respectively) was tested against the drainage performance of silica-based sols according to Example 5. Drainage performance was evaluated by means of a Dynamic Drainage Analyser (DDA), available from Akribi, Sweden, which measures the time for draining a set volume of stock through a wire when removing a plug and applying a vacuum to that side of the wire opposite to the side on which the stock is present.

30

The stock used was based on a standard fine paper furnish consisting of 60 % bleached birch sulfate and 40 % bleached pine sulfate. 30 % ground calcium carbonate was added to the stock as filler and 0.3 g/l of Na₂SO₄·10 H₂O was added to increase conductivity. Stock pH was 8.1, conductivity 1.5 mS/cm and consistency 0.5 %. In the tests, the silica-based sols
35 were tested in conjunction with a cationic starch having a degree of substitution of about 0.042. The starch was added in an amount of 8 kg/tonne, calculated as dry starch on dry furnish.

The stock was stirred in a baffled jar at a speed of 1,500 rpm throughout the test and chemical additions to the stock were made as follows:

- i) adding cationic starch followed by stirring for 30 seconds,
- ii) adding silica-based sol followed by stirring for 15 seconds,
- 5 iii) draining the stock while automatically recording the drainage time.

Table 1 shows the results obtained when using varying dosages of silica-based sol, kg/tonne, calculated as SiO₂ and based on dry furnish.

10

Table 1

Test No.	Cationic Starch Dosage [kg/t]	Silica Dosage [kg/t]	Dewatering Time [s]			
			Ex. 1	Ex. 2	Ref. 1	Ref. 2
1	8	0	19.4	19.4	19.4	19.4
2	8	1.0	13.8	14.8	14.7	14.1
3	8	1.5	12.2	13.1	13.7	13.7
4	8	2.0	11.1	12.0	13.1	12.6

Example 7

15 Drainage performance of the silica-based sol according to Example 1 was further evaluated. The procedure according to Example 6 was followed except that a cationic polyacrylamide ("PAM") was used instead of cationic starch. In addition, the stock was stirred in a baffled jar at a speed of 1,500 rpm throughout the test and chemical additions to the stock were made as follows:

- 20 i) adding cationic polyacrylamide followed by stirring for 20 seconds,
- ii) adding silica-based sol followed by stirring for 10 seconds,
- iii) draining the stock while automatically recording the drainage time.

Table 2 shows the results obtained when using different dosages of cationic polyacrylamide, kg/tonne, calculated as dry starch on dry furnish, and silica-based sol, 25 kg/tonne, calculated as SiO₂ and based on dry furnish.

Table 2

Test No.	Cationic PAM Dosage [kg/t]	Silica Dosage [kg/t]	Dewatering Time [s]		
			Ex. 1	Ref. 1	Ref. 2
1	0.8	0	17.2	17.2	17.2
2	0.8	0.25	9.8	11.1	10.0
3	0.8	0.50	7.2	8.2	7.7
4	0.8	0.75	6.6	7.1	7.4

Example 8

5

Drainage performance of the silica-based sols according to Examples 3 and 4 was tested following the procedure according to Example 6. Table 3 shows the results obtained when using varying dosages of silica-based sol, kg/tonne, calculated as SiO₂ and based on dry furnish.

10

Table 3

Test No.	Cationic Starch Dosage [kg/t]	Silica Dosage [kg/t]	Dewatering Time [s]				
			Ex. 3	Ex. 4	Ref. 1	Ref. 2	Ref. 3
1	8	0	20.6	20.6	20.6	20.6	20.6
2	8	1.0	13.9	14.8	15.5	14.7	15.1
3	8	1.5	12.8	13.5	14.1	13.6	14.4
4	8	2.0	12.5	12.8	13.6	13.5	13.4

Example 8

15

Drainage performance of the silica-based sol according to Examples 3 and 4 was tested following the procedure according to Example 7. Table 4 shows the results obtained when using varying dosages of silica-based sol, kg/tonne, calculated as SiO₂ and based on dry furnish.

20

Table 4

Test No.	Cationic PAM Dosage [kg/t]	Silica Dosage [kg/t]	Dewatering Time [s]				
			Ex. 3	Ex. 4	Ref. 2	Ref. 3	Ref. 4
1	0.8	0	16.0	16.0	16.0	16.0	16.0
2	0.8	0.25	8.6	8.5	9.1	10.7	8.7
3	0.8	0.50	6.6	6.5	7.9	8.0	7.4
4	0.8	0.75	6.0	6.7	7.6	7.1	7.2

Claims

1. A process for producing an aqueous silica-based sol which comprises:
- 5 (a) providing a cationic ion exchange resin having at least part of its ion exchange capacity in hydrogen form;
- (b) bringing said ion exchange resin in contact with an aqueous alkali metal silicate to form an aqueous slurry;
- 10 (c) stirring said aqueous slurry until the pH of the aqueous phase is in the range of from 5.0 to 11.5; or alternatively, stirring said aqueous slurry to allow particle aggregation or microgel formation corresponding to an S value up to 45 %, and obtain a pH of the aqueous phase of at least 5.0;
- (d) adjusting the pH of said aqueous phase to above 9.0 using one or more materials comprising at least one aluminium compound; and
- 15 (e) separating said ion exchange resin from the aqueous phase after step (c) or after step (d).
2. A process for producing an aqueous silica-based sol which comprises:
- (a) providing a reaction vessel;
- (b) providing in said reaction vessel:
- 20 (i) a cationic ion exchange resin having at least part of its ion exchange capacity in hydrogen form, and
- (ii) an aqueous alkali metal silicate, to form an aqueous slurry;
- (c) stirring said aqueous slurry until the pH of the aqueous phase is in the range of
- 25 from 5.0 to 11.5; or, alternatively, stirring said aqueous slurry to allow particle aggregation or microgel formation corresponding to an S value up to 45 %, and obtain a pH of the aqueous phase of at least 5.0;
- (d) adding one or more materials comprising at least one aluminium compound to the aqueous phase obtained after step (c) to form an aqueous phase having a pH of
- 30 above 9.0;
- (e) separating said ion exchange resin from the aqueous phase after step (c) or after step (d).
3. The process according to any one of the preceding claims, wherein it further comprises (f)
- 35 obtaining an aqueous silica-based sol having an S value between 10 and 50 %.
4. The process according to any one of the preceding claims, wherein the ion exchange resin is separated from the aqueous phase after step (c) but before step (d).

5. The process according to any one of the preceding claims, wherein the ion exchange resin is separated from the aqueous phase after step (d).
- 5 6. The process according to any one of the preceding claims, wherein in step (d) said one or more materials comprise an alkaline material.
7. The process according to claim 5, wherein the alkaline material comprises an aqueous alkali metal silicate.
- 10 8. The process according to claim 5, wherein the alkaline material comprises an aqueous alkali metal hydroxide.
9. The process according to any one of the preceding claims, wherein in step (c) the aqueous slurry is stirred to allow particle aggregation or microgel formation corresponding to an S value up to 45 %, and obtain a pH of the aqueous phase of at least 5.0
- 15 10. The process according to any one of the preceding claims, wherein in step (c) the aqueous slurry is stirred until the pH of the aqueous phase is in the range of from 5.0 to 11.5.
- 20 11. The process according to any one of the preceding claims, wherein in step (c) the aqueous slurry is stirred until the pH of the aqueous phase is in the range of from 6.0 to 8.0.
- 25 12. The process according to any one of the preceding claims, wherein in step (c) the aqueous slurry is stirred until the pH of the aqueous phase is in the range of from 6.5 to 7.5.
- 30 13. The process according to any one of claims 1 to 10, wherein in step (c) the aqueous slurry is stirred until the pH of the aqueous phase is in the range of from 9.0 to 10.0.
14. The process according to any one of the preceding claims, wherein in step (c) the slurry is stirred to allow particle aggregation or microgel formation corresponding to an S-value in the range of from 10 to 25 %.
- 35 15. The process according to any one of the preceding claims, wherein in step (d) the aluminium compound is sodium aluminate.

16. The process according to any one of the preceding claims, wherein in step (d) the pH of the aqueous phase is adjusted to be in the range of from about 9.5 to about 11.2.

5 17. The process according to any one of the preceding claims, wherein in step (d) the pH of the aqueous phase is adjusted by first adding aqueous sodium silicate and subsequently adding aqueous sodium aluminate.

10 18. The process according to any one of the preceding claims, wherein in step (d) the pH of the aqueous phase is adjusted by first adding an aqueous alkali metal silicate, then the ion exchange resin is separated from the aqueous phase and an aqueous aluminium compound is subsequently added to the obtained aqueous phase.

15 19. The process according to any one of claims 1 to 16, wherein in step (d) the pH of the aqueous phase is adjusted by first adding aqueous sodium hydroxide and subsequently adding aqueous sodium aluminate.

20 20. Silica-based sol having an S value within the range of from 1.5 to 25 %, mole ratio Si:Al in the range of from 20:1 to 50:1, mole ratio Si:X, where X = alkali metal, in the range of from 5:1 to 17:1, SiO₂ content of at least 5 % by weight and containing silica-based particles having a specific surface area of at least 300 m²/g.

25 21. The silica-based sol according to claim 20, or the process according to any one of claims 1 to 19, wherein the silica-based sol has a mole ratio Si:X in the range of from 6:1 to 10:1.

30 22. The silica-based sol according to claim 20 or 21, or the process according to any one of claims 1 to 19 and 21, wherein the silica-based sol has an S-value is in the range of from 17 to 24 %.

23. The silica-based sol according to any one of claims 20 to 22, or the process according to any one of claims 1 to 19 and 21 to 22, wherein the silica-based sol contains silica-based particles having a specific surface area from 700 to 950 m²/g.

35 24. The silica-based sol according to any one of claims 20 to 23, or the process according to any one of claims 1 to 19 and 21 to 23, wherein the silica-based sol has a SiO₂ content in the range of from 6 to 15 % by weight.

25. A silica-based sol obtainable by the process according to any one of the preceding claims.

26. A process for producing paper which comprises

- 5 (i) providing an aqueous suspension comprising cellulosic fibres;
(ii) adding to the suspension one or more drainage and retention aids comprising a silica-based sol; and
(iii) dewatering the obtained suspension to provide a sheet or web of paper;
wherein the silica-based sol is obtainable by the process according to any one of claims 1
10 to 19.

27. A process for producing paper which comprises

- (i) providing an aqueous suspension comprising cellulosic fibres;
(ii) adding to the suspension one or more drainage and retention aids comprising a
15 silica-based sol; and
(iii) dewatering the obtained suspension to provide a sheet or web of paper;
wherein the sol is a silica-based sol according to any one of claims 20 to 24.

28. The process according to claim 26 or 27, wherein the drainage and retention aids
20 comprise cationic starch.

29. The process according to any one of claims 26 to 28, wherein the drainage and retention aids comprise a cationic synthetic polymer.

25 30. The process according to any one of claims 26 to 29, wherein the drainage and retention aids comprise an anionic polymer.

31. The process according to any one of claims 26 to 30, wherein it comprises adding a cationic coagulant to the suspension.

30

INTERNATIONAL SEARCH REPORT

International Application No
PCT/S E2005/000488

A. CLASSIFICATION OF SUBJECT MATTER IPC 7 C01B33/143 D21H17/68		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC 7 C01B D21H		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used) EPO-Internal, WPI Data, PAJ		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 572 888 A (BAYER AG) 8 December 1993 (1993-12-08) the whole document claim 1	1-31
X	EP 0 491 879 A (EKA NOBEL AB) 1 July 1992 (1992-07-01) the whole document claims 7-11	27-31
A		1-22
X	EP 0 502 089 A (EKA NOBEL AB) 9 September 1992 (1992-09-09) the whole document	27-31
A		1-22
A	US 5 603 805 A (LINDGREN ERIK ET AL) 18 February 1997 (1997-02-18) the whole document	1-31
	----- -/--	
<input checked="" type="checkbox"/> Further documents are listed in the continuation of box C.		
<input checked="" type="checkbox"/> Patent family members are listed in annex.		
° Special categories of cited documents :		
"A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed		"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "&" document member of the same patent family
Date of the actual completion of the international search <p style="text-align: center;">6 September 2005</p>		Date of mailing of the international search report <p style="text-align: center;">21/09/2005</p>
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel: (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016		Authorized officer <p style="text-align: center;">Arnotte, E</p>

INTERNATIONAL SEARCH REPORT

International Application No
PCT/SE2005/000488

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2003/024671 A1 (PERSSON MICHAEL ET AL) 6 February 2003 (2003-02-06) the whole document	20-24
X	US 2002/139502 A1 (HALLSTROM HANS ET AL) 3 October 2002 (2002-10-03) the whole document	26-31

INTERNATIONAL SEARCH REPORT

 Inter Application No
 PCT/SE2005/000488

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0572888	A	08-12-1993	BR 9302206 A	14-12-1993
			DE 4218306 A1	09-12-1993
			ES 2081163 T3	16-02-1996
			JP 7291613 A	07-11-1995
			US 5964693 A	12-10-1999
EP 0491879	A	01-07-1992	AR 243851 A1	30-09-1993
			AT 107608 T	15-07-1994
			AU 628692 B2	17-09-1992
			AU 6733490 A	13-06-1991
			BR 9007822 A	01-09-1992
			CA 2067506 A1	09-05-1991
			CN 1115817 A	31-01-1996
			DE 69010210 D1	28-07-1994
			DE 69010210 T2	13-10-1994
			DK 491879 T3	07-11-1994
			ES 2055581 T3	16-08-1994
			FI 922056 A	06-05-1992
			JP 4505314 T	17-09-1992
			JP 5009368 B	04-02-1993
			KR 9505762 B1	30-05-1995
			LT 445 A	25-10-1994
			LV 10227 A	20-10-1994
			NZ 235963 A	26-05-1992
			PT 95849 A	13-09-1991
			SE 500387 C2	13-06-1994
			SE 8903753 A	10-05-1991
			WO 9107350 A1	30-05-1991
			US 5368833 A	29-11-1994
EP 0502089	A	09-09-1992	AT 107609 T	15-07-1994
			AU 635365 B2	18-03-1993
			AU 6734290 A	13-06-1991
			CA 2067495 A1	10-05-1991
			DE 69010217 D1	28-07-1994
			DE 69010217 T2	13-10-1994
			DK 502089 T3	07-11-1994
			ES 2055580 T3	16-08-1994
			FI 922057 A	06-05-1992
			JP 4505315 T	17-09-1992
			JP 5074524 B	18-10-1993
			NZ 235964 A	25-09-1992
			SE 500367 C2	13-06-1994
			SE 8903754 A	10-05-1991
			WO 9107351 A1	30-05-1991
			US 5447604 A	05-09-1995
US 5603805	A	18-02-1997	AT 138354 T	15-06-1996
			AU 667966 B2	18-04-1996
			AU 4988193 A	29-03-1994
			BR 9306878 A	08-12-1998
			CA 2141551 A1	17-03-1994
			CN 1084490 A	30-03-1994
			DE 69302823 D1	27-06-1996
			DK 656872 T3	07-10-1996
			EP 0656872 A1	14-06-1995
			ES 2087767 T3	16-07-1996
			FI 950622 A	13-02-1995

INTERNATIONAL SEARCH REPORT

International Application No
P CT/SE2005/000488

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5603805	A	JP 2787377 B2	13-08-1998
		JP 8502016 T	05-03-1996
		MX 9305272 A1	28-02-1994
		NZ 255615 A	27-11-1995
		RU 2081060 C1	10-06-1997
		SE 501214 C2	12-12-1994
		SE 9202502 A	01-03-1994
		WO 9405596 A1	17-03-1994
<hr/>			
US 2003024671	A1	06-02-2003	NONE
<hr/>			
US 2002139502	A1	03-10-2002	NONE
<hr/>			