

Our Ref: SW/LS/GL 19 September 2018

**Report 328464** Page 1 of 2

Contrado Imaging Limited Unit 7 Space Business Park Abbey Road Park Řoyal London **NW107SU** 

Contact: Chris Childs: Annie Antoniou

DATE RECEIVED

11 SEP 2018 FR PVC LEATHERETTE NOT GIVEN QUALITY/REFERENCE

**REPUTED FIBRE CONTENT** FABRIC DESCRIPTION **WOVEN** COLOUR/DESIGN **BLACK** 

PERFORMANCE STANDARD : GENERAL



**REQUEST:** Martindale abrasion

L Sheridan

S. WISEMAN LABORATORY DIRECTOR

L. SHERIDAN LABORATORY MANAGER

This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method, preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior





19 September 2018

## <u>Report 328464</u> <u>Page 2 of 2</u>

## **PHYSICAL**

## BS EN 14465:2003 Annex A Abrasion Resistance

12 kPa load.

12 Ki ti lotti.	
	Number of rubs to breakdown:
	Head 1 20,000+
	Head 2 20,000+
	Head 3 20,000+
	Head 4 20.000+

## BS EN 14465:2003 Annex A Abrasion Resistance

12 kPa load.

Number of rubs to breakdown:
Head 1 30,000+
Head 2 30,000+
Head 3 30,000+
Head 4 30,000+

